2020 ► 2021

General Catalogue

SUMITOMO

CARBIDE - CBN - DIAMOND

PERFORMANCE CUTTING TOOLS



SUMITOMO ELECTRIC GROUP

SUMITOMO ELECTRIC

Contents

	Negative	Positive
C 80° Diamond Type	C18	C61
D 55° Diamond Type	C27	C68
R Round Type		C72
S Square Type	C35	C73
T 60° Triangular Type	C44	C78
V 35° Diamond Type	C53	C88
W 80° Trigon Type	C56	C92

Dimension symbols are compliant with ISO13399

The following table shows ISO13399-compliant dimension symbols. Contents corresponding to the sample symbols/notations are shown below. Tool shape diagrams and stock charts use the symbols and notation examples from the table below.

(1) Inserts (For Turning / For Milling)

Symbol	Description
AN	Clearance angle major
APMX	Depth of cut maximum
BS	Wiper edge length
CDX	Cutting depth maximum
CHW	Corner chamfer width
CW	Cutting width
D1	Fixing hole diameter
DMIN	Minimum bore diameter
IC	Inscribed circle diameter
INSL	Insert length
L	Cutting edge length
PDX	Profile distance ex
PDY	Profile distance ey
PNA	Profile included angle
RE	Corner radius
RER	Right side corner radius
REL	Left side corner radius
S	Insert thickness
W1	Insert width
WF	Functional width

(2) Tool Holders For Turning

Symbol	Description
APMX	Depth of cut maximum
B	Shank width
BD	Body diameter
CDX	Cutting depth maximum
CRKS	Connection retention knob thread size
DC	Cutting diameter
DCB	Connection bore diameter
DCON	Connection diameter
DCSFMS	Contact surface diameter machine side
DMIN	Minimum bore diameter
DMM	Shank diameter
DN	Neck diameter
GAMF	Rake angle radial
GAMP	Rake angle axial
H	Shank height
HBH	Head bottom offset height
HBKL	Head back offset length
HBKW	Head back offset width
HBL	Head bottom offset length
HF	Functional height
KDP	Groove depth
KWW	Keyway width
LF	Functional length
LH	Head length
LHD	Head length
LS	Shank length
LSCX	Clamping length maximum
LU	Usable length
LUX	Usable length maximum
WF	Functional width

(Turning Insert Example)



(Grooving Insert Example)



(External Holder Example)



Figure shows right-handed tool.

(Grooving Tool Holder Example)



Notes: The symbols in the above table are compliant with ISO13399 and do not include symbols unique to our company.
As symbols under review are not included, these may change over time.

(3) Cutters / Indexable Endmills

Symbol	Description
APMX	Depth Of Cut Maximum
BD	Body Diameter
BDX	Body Diameter Maximum
CBDP	Connection Bore Depth
CRKS	Connection Retention Knob Thread Size
CW	Cutting Width
DBC	Connection Bore Diameter
DC	Cutting Diameter
DCB	Clamping Diameter, Nominal, on Workpiece Side
DCON	Connection Diameter
DCSFMS	Contact Surface Diameter Machine Side
DCX	Cutting Diameter Maximum
DMM	Shank Diameter
DN	Neck Diameter
H	Shank Height
KDP	Groove Depth
KWW	Keyway Width
LBX	Body Length Maximum
LF	Functional Length
LH	Head Length
LS	Shank Length
LU	Usable Length
OAL	Overall Length
RMPX	Maximum Ramping Angle
THUB	Hub Thickness

(4) Endmills

Symbol	Description
APMX	Depth Of Cut Maximum
CHW	Corner Chamfer Width
DC	Cutting Diameter
DMM	Shank Diameter
DN	Neck Diameter
LF	Functional Length
LFS	Functional Length Secondary
LU	Usable Length
RE	Corner Radius

(5) Drills / Reamers

Symbol	Description
BD	Body Diameter
BDX	Body Diameter Maximum
CW	Cutting Width
DC	Cutting Diameter
DCB	Clamping Diameter, Nominal, on Workpiece Side
DCON	Connection Diameter
DCSFMS	Contact Surface Diameter Machine Side
DF	Flange Diameter
DMM	Shank Diameter
LBX	Body Length Maximum
LCF	Length Chip Flute
LF	Functional Length
LFA	A Dimension On Lf
LFS	Functional Length Secondary
LH	Head Length
LPR	Protruding Length
LS	Shank Length
LU	Usable Length
LUX	Usable Length Maximum
OAL	Overall Length
PL	Point Length
WBTHK	Web Thickness

(Shell Type Example)



(Shank Type Example)



(Endmill Example)



(Drill Example)



(Modular Type Example)



Notice

Thank you for using the Sumitomo Electric Hardmetal General Catalogue
(Sumitomo/SUMIBORON/SUMIDIA Cutting Tools Catalogue).

This catalogue presents the major items in the Sumitomo Cutting Tools product line.
The catalogue ist organised as follows:
(1) Cutting Tool Grades
(2) Sumitomo Products
(3) SUMIBORON, SUMIDIA Products
Ask for our brochures and pamphlets.
This catalogue is current as of January 2020.

As a result ot our ongoing research, product may reflect enhancements in qualitiy, performance and specifications not listed in this catalogue.
To order Sumitomo/SUMIBORON/SUMIDIA products, contact your nearest Sumitomo Electric Hardmetal dealer or distributor.
For inquiries or other requests, feel free to contact your nearest sales office.

Stock Marking Chart

● : Euro stock item

❍ : Japan stock item

❑ : Delivery on request

▲ : To be replaced by new item

□ : Made to order item

– : We cannot produce

Note:
Stocking policy may change without prior notice, please consult our sales representative for actual stock situation.

Meaning of Icons

Common

Featured for the first time in this catalogue

Grade

ISO classification of work material:

Steel

Stainless Steel

Cast Iron

Non Ferrous Alloy

Exotic Alloy

Hardened Steel

Miling Cutter



Max. depth of cut

Cutting edge angle

Endmill

Shape

Sharp edge

Corner with honing

Helix angle (ex.)

Radius

Ballnose

No. of teeth

Flutes

Insert Selection

A



Selection of Sumitomo Grades (Turning)





: 1st Recommendation : 2nd Recommendation : CVD Coating : PVD Coating Blank: Uncoated

Selection of Sumitomo Grades (Milling)





: 1st Recommendation : 2nd Recommendation : CVD Coating : PVD Coating Blank: Uncoated

Main Chipbreakers

Negative Type



Positive Type



Sub-Chipbreakers

Negative Type

Chipbreakers for High-Efficiency Machining



Strong Edge Chipbreakers



Chipbreakers for Small Depths



Wiper Inserts



Chipbreakers for Heavy Cutting



Grades

Fine Finishing to Finishing



Finishing to Rough Cutting



Grades

T1000A / T1500A / T1500Z



T1000A: An uncoated cermet grade designed with wear resistance in mind that provides long tool life and excellent wear resistance in continuous finishing and profiling applications.

T1500A: A general purpose uncoated cermet grade that provides excellent value for money and delivers improved finished surface quality while providing good wear and fracture resistance.

T1500Z: Superior turning quality thanks to „Brilliant Coat". PVD coating with excellent adhesion resistance. A general purpose coated cermet grade capable of maintaining high-quality finished surfaces while providing excellent wear resistance.

Performance

T1000A

Wear Resistance



Work Material: 34CrMo4 Insert: NMG120408NSU
Cutting Conditions: v_C=320 m/min, f=0,20 mm/rev, a_P=1,5mm, dry

Fracture Resistance



Work Material: 34CrMo4, Insert: CNMG120408NSU
Cutting Conditions: v_C=230 m/min, f=0,20 mm/rev, a_P=1,0 mm, wet

T1500A

Wear Resistance



Work Material: 34CrMo4 Insert: CNMG120408NSU
Cutting Conditions: v_c = 230 m/min, f = 0,20 mm/rev, a_p = 1,0 mm, wet

Machined Surface Finish



Work Material: C45, Insert: CNMG120408NLU,
Cutting Conditions: v_c = 150 m/min, f = 0,12 mm/rev, a_p =1,0 mm, wet

T1500Z

Wear Resistance



Work Material: 34CrMo: Insert: CNMG120408NSU
Cutting Conditions: v_C=230m/min, f=0,20mm/rev, a_P=1,0mm, wet

Machined Surface Finish



Work Material: 21NiCrMo2, Insert:DNMG150408NSU
Cutting Conditions: v_C=150m/min ,f=0,20mm/rev, a_P=1,0mm, wet



Work Material: H240LA, Insert: CNMG120408NSU
Cutting Conditions: v_C=100m/min, f=0,15mm/rev, a_P=1,0mm, wet

P Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

Work Material	Cutting Process	Chipbreaker	Grades	Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
Soft Steel	Fine Finishing	NFA / NFL	T1500Z	0,2–**0,5**–1,0	0,05–**0,15**–0,25	150–**280**–400
	Finishing	NLU	T3000Z	0,3–**1,0**–1,8	0,08–**0,20**–0,35	150–**280**–400
Alloy Steel Carbon Steel	Fine Finishing	NFA / NFL	T1500A	0,2–**0,5**–1,0	0,05–**0,15**–0,25	100–**200**–300
	Finishing	NSU / NSE	T1500A	0,5–**1,0**–2,0	0,08–**0,20**–0,35	100–**200**–300
	Medium	NGU	T1500Z	0,8–**2,2**–4,0	0,15–**0,25**–0,50	100–**200**–300
High Carbon Steel Carbon Steel	Fine Finishing	NFA / NFL	T1000A	0,2–**0,5**–1,0	0,05–**0,15**–0,25	50–**150**–250
	Finishing	NSU / NSE	T1500Z	0,5–**1,0**–2,0	0,08–**0,20**–0,35	50–**150**–250
	Medium	NGU	T1500Z	0,8–**2,2**–4,0	0,15–**0,25**–0,50	50–**150**–250

Grades

New AC8015P / New AC8025P / AC8035P / AC1030U

Covers a wide range of machining applications from high-speed cutting to interrupted cutting and small lathe machining.

AC8015P Development of crater damage is suppressed by controlling the orientation of the alumina crystal grains. Achieves long, stable tool life during high-speed and high feed cutting.

AC8025P The 1st recommendation grade for turning steel. Surface smoothing technology significantly suppresses adhesion of work material components. Achieves long, stable tool life with various cutting speeds and work materials.

AC8035P Tensile stress removal of the coating layer greatly improves fracture resistance. Achieves long, stable tool life during heavy interrupted cutting.

AC1030U Employs a new PVD coating and a dedicated tough carbide substrate. High-quality cutting edge grade suppresses adhesion and micro-chipping, realizing excellent machined surface quality.

Performance

AC8015P

Reduced crater damage due to chip abrasion through optimized crystal orientation in the alumina layer.

Conventional Grade



Work Material: 100Cr6, 1.3505, External continuous, Insert: CNMG120408NGU
Cutting Conditions: v_c = 300 m/min, f = 0,3 mm/rev, a_p = 1,5 mm, wet

AC8015P



Improved crater wear resistance.

AC8025P

Improved tool surface smoothness and significantly reduced adhesion through special surface treatment.

Conventional Grade



Adhesion resistance

Work Material: 25CrMo4, 1.7218, Facing, Insert: CNMG120408NGU
Cutting Conditions: v_c = 100–300 m/min, f = 0,3 mm/rev, a_p = 1,5 mm, wet,

AC8025P



Adhesion resistance

Extremely smooth surface prevents adhesion.

AC8035P

Drastically reduced tensile residual stress in coating through special surface treatment.

Conventional Grade







Work Material: 34CrMoS34, 1.7226, Interrupted cut, Insert: CNMG120408NGU
Cutting Conditions: v_c = 160 m/min, f = 0,2–0,3 mm/rev, a_p = 2 mm, dry

AC8035P







Cracks difficult to grow >>> excellent toughness

Grades and Chip breaker Selection Guide

1st Recommendation	
General Purpose	**AC8025P**

+

1st Recommendation

NGU



	Elevated Feed Rate Area	General Purpose	Tougher Cutting Edge
Finish–Small Depth	**NFE**   **NSE**  	**NSU**  	**NSX**  
General Purpose	**NGE**  	**NGU**  	**NUX**  
Rough–Larger Cutting Depth	**NME**  	**NMU**  	**NMX**  

Flank Wear

Crater Wear

Chipping

Fracture

Better Wear Resistance	
High Speed	**AC8015P**

Better Toughness	
Interrupted Cut	**AC8035P**

1st Recommendation	**NGU** 
Higher efficiency required	**NGE** 

1st Recommendation	**NGU** 
Higher stability required	**NUX** 

Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

Work Material	Cutting Process	Chipbreaker	Grade	Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (mm/min)
Soft Steel	Fine Finishing	NFB	**T1500Z**	0,2–**0,6**–1,0	0,05–**0,15**–0,25	100–**250**–400
	Finishing	NFE	**AC8015P**	0,5–**1,0**–1,5	0,1–**0,25**–0,4	260–**350**–440
	Medium Cutting	**NGU**	**AC8025P**	1,0–**2,5**–4,0	0,2–**0,35**–0,5	200–**260**–320
	Roughing	NMU	**AC8035P**	1,5–**4,0**–6,0	0,3–**0,45**–0,6	140–**180**–220
Alloy Steel Carbon Steel	Fine Finishing	NFB	**T1500Z**	0,2–**0,6**–1,0	0,05–**0,15**–0,25	100–**200**–300
	Finishing	NFE	**AC8015P**	0,5–**1,0**–1,5	0,1–**0,25**–0,4	210–**285**–360
	Medium Cutting	**NGU**	**AC5025P**	1,0–**2,5**–4,0	0,2–**0,35**–0,5	150–**190**–230
	Roughing	NMU	**AC8035P**	1,5–**4,0**–6,0	0,3–**0,45**–0,6	90–**135**–160
High Carbon Steel Carbon Steel	Fine Finishing	NFB	**T1500Z**	0,2–**0,6**–1,0	0,05–**0,15**–0,25	50–**150**–250
	Finishing	NFE	**AC8015P**	0,5–**1,0**–1,5	0,1–**0,25**–0,4	170–**235**–300
	Medium Cutting	**NGU**	**AC8025P**	1,0–**2,5**–4,0	0,2–**0,35**–0,5	130–**165**–200
	Roughing	NMU	**AC8035P**	1,5–**4,0**–6,0	0,3–**0,45**–0,6	90–**135**–160

Chipbreakers

Negative Type



Positive Type



Grades



M Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

Work Material			Cutting Range	Chipbreaker	Grade	Cutting Conditions		
						Depth of Cut a_p (mm)	Feed Rate f (mm/rev)	Cutting Speed v_c (m/min)
Cr-Based	Ferritic Materials	X6CrAl 13, X8CrNiS 18 9, X29CrS 13, X6CrMoS 17, X12CrS 13	Finishing	NEF (NSU)	AC6020M	0,5–**1,5**–2,0	0,05–**0,15**–0,25	170–**230**–300
			Medium	**NEG** · NEX · NGU	**AC6030M**	1,0–**2,5**–4,0	0,10–**0,25**–0,40	140–**170**–250
			Roughing	NEM	AC6040M	1,5–**3,5**–6,0	0,20–**0,35**–0,60	140–**170**–200
	Martensitic Materials	X12Cr 13, X20Cr 13, X30Cr 13, X6Cr 17, X19CrNi 17 2, X6CrNi 18 9	Finishing	NEF (NSU)	AC6020M	0,5–**1,5**–2,0	0,05–**0,15**–0,25	120–**180**–240
			Medium	**NEG** · NEX · NGU	**AC6030M**	1,0–**2,5**–4,0	0,10–**0,25**–0,40	100–**150**–200
			Roughing	NEM	AC6040M	1,5–**3,5**–6,0	0,20–**0,35**–0,60	80–**130**–180
Cr/Ni-Based	Austenitic Materials	X5CrNi 18 10, X2CrNi 19 11, X2CrNiMo 18 10, X4CrNiMo 17 12 2, X2CrNiMo 17 12 2, X5CrNiMo 17 13, X6CrNiTi 18 10, X70CrMo 15	Finishing	NEF (NSU)	AC6020M	0,5–**1,5**–2,0	0,05–**0,15**–0,25	120–**180**–240
			Medium	**NEG** · NEX · NGU	**AC6030M**	1,0–**2,5**–4,0	0,10–**0,25**–0,40	100–**150**–200
			Roughing	NEM	AC6040M	1,5–**3,5**–6,0	0,20–**0,35**–0,60	80–**130**–180
	Two-Phase (Austenite / Ferrite) Materials	X5CrNi 17 7, X2CrNi 18 9, X6CrNi 25 20, X2CrNiMoN 17 12 2, X6CrNiNb 18 10	Finishing	NEF (NSU)	AC6030M	0,5–**1,5**–2,0	0,05–**0,15**–0,25	100–**145**–180
			Medium	**NEG** · NEX · NGU	**AC6030M**	1,0–**2,5**–4,0	0,10–**0,25**–0,40	80–**120**–160
			Roughing	NEM	AC6040M	1,5–**3,5**–6,0	0,20–**0,35**–0,60	70–**100**–140
	Precipitation Hardening	X5CrNiCuNb 16 4, X7CrNiAl 17 7, X4CrNuMo 27 5 2, X2CrNiMoN 22 5 3, X2CrNiMoCuN 25 6 3	Finishing	NEF (NSU)	AC6030M	0,5–**1,5**–2,0	0,05–**0,15**–0,25	90–**115**–140
			Medium	**NEG** · NEX · NGU	**AC6030M**	1,0–**2,5**–4,0	0,10–**0,25**–0,40	70–**90**–110
			Roughing	NEM	AC6040M	1,5–**3,5**–6,0	0,20–**0,35**–0,60	50–**80**–120

Grades

AC6020M / AC6030M / AC6040M / AC1030U

AC6020M Employes "Absotech Platinum", a new CVD coating. The first recommended grade for continuous stainless steel machining that achieves a good balance between wear resistance and fracture resistance by combining a hardened substrate with excellent wear resistance.

AC6030M Employes "Absotech Platinum", a new CVD coating. The first recommended grade for general machining of stainless steel that drastically reduces the occurrence of abnormal damage, which is a problem in stainless steel machining. Achieves long and stable machining thanks to the improved coating strength and excellent adhesion.

AC6040M Employes "Absotech Bronze", a new PVD coating and exclusive tough carbide substrate. The first recommended grade for interrupted machining of stainless steel that drastically improves the reliability in unstable machining thanks to the excellent adhesion and peel-off resistance of the new PVD coating as well as the improved fracture resistance of the exclusive carbide substrate.

AC1030U Employes "Absotech Bronze", a new PVD coating with a special tough carbide substrate. Achieving excellent machined surface quality with a high-quality cutting edge that reduces adhesion and micro-chipping.

Performance

AC6020M

Continuous Cutting (Medium Speed)



Work Material: X2CrNiMo17 13 2 Insert: CNMG 120408 NGU
Cutting Conditions: v_c = 150 m/min, f = 0,3 mm/rev, a_p = 2,0 mm, wet

Continuous Cutting (High Speed)



Work Material: X2CrNiMo17 13 2 Insert: CNMG 120408 NGU
Cutting Conditions: v_c = 200 m/min, f = 0,3 mm/rev, a_p = 2,0 mm, wet

AC6030M

Continuous Cutting



Work Material: X6CrMo17 12 2 Insert: CNMG 120408 NEX
Cutting Conditions: v_c = 200 m/min, f = 0,2 mm/rev, a_p = 2,0 mm, wet

Interrupted Cutting



Work Material: X6CrMo17 12 2 Insert: CNMG 120408 NGU
Cutting Conditions: v_c = 100 m/min, f = 0,1 mm/rev, a_p = 1,0 mm, wet

AC6040M

Continuous Cutting



Work Material: X6CrMo17 12 2 Insert: CNMG 120408 NGU
Cutting Conditions: v_c = 150 m/min, f = 0,2 mm/rev, a_p = 2,0 mm, wet

Interrupted Cutting



Work Material: CNMG 120408 NGU Insert: CNMG 120408 NGU
Cutting Conditions: v_c = 230 m/min, f = 0,23 mm/rev, a_p = 0,80 mm, dry

Chipbreakers

Negative Type



Positive Type



Grades

Grey Cast Iron (GG)



Ductile Cast Iron (GGG)



Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

Work Materials	Cutting Process	Grades	Cutting Conditions		
			Depth of Cut a_p (mm/rev)	Feed Rate f (mm/rev)	Cutting Speed v_c (m/min)
Gray Cast Iron (GG-25, etc.)	High Speed Cutting	BN7000	0,1–**0,3**–1,0	0,10–**0,20**–0,50	500–**1.500**–2.000
	Continuous – General	**AC4010K**	0,5–**2,0**–6,0	0,10–**0,25**–0,40	200–**400**–700
	Interrupted	AC4015K	0,5–**2,0**–6,0	0,10–**0,30**–0,50	180–**300**–450
	Heavy Interrupted	AC420K	0,5–**2,0**–6,0	0,10–**0,30**–0,60	150–**200**–300
Ductile Cast Iron (GGG-40.3, etc.)	High Speed Cutting	BNC500	0,1–**0,2**–0,5	0,10–**0,20**–0,40	150–**350**–500
	Continuous – General	AC4010K	0,5–**2,0**–6,0	0,10–**0,25**–0,40	180–**300**–450
	Interrupted	**AC4015K**	0,5–**2,0**–6,0	0,10–**0,30**–0,50	160–**250**–400
	Heavy Interrupted	AC420K	0,5–**2,0**–6,0	0,10–**0,30**–0,60	120–**170**–250
High-strength Ductile Cast Iron (GGG-70, etc.)	High Speed Cutting	BNC500	0,1–**0,2**–0,5	0,10–**0,20**–0,40	200–**350**–500
	Continuous – General	AC4010K	0,5–**2,0**–6,0	0,10–**0,25**–0,40	160–**250**–400
	Interrupted	**AC4015K**	0,5–**2,0**–6,0	0,10–**0,30**–0,50	140–**200**–350
	Heavy Interrupted	AC420K	0,5–**2,0**–6,0	0,10–**0,30**–0,60	80–**150**–220

Grades

New AC4010K / New AC4015K / AC420K

AC4010K The 1st recommended grade for machining grey cast iron. Adopts an ultra-thick new CVD coating to realise ultra-high-speed machining at Vc = 700 m/min.

AC4015K The 1st recommendation grade for ductile cast iron. New high-adhesion, high-strength CVD coating realises both wear resistance and chipping resistance.

AC420K Superior fracture resistance, providing excellent stability in interrupted unstable cutting and when cutting mill-scaled work.

Performance

AC4010K / AC4015K

Wear Resistance, Gray Cast Iron (GG)



Work Material: GG-25, Continuous, Insert: CNMG120408
Cutting Conditions: v_c = 600 m/min, f = 0,4 mm/rev, a_p = 2,0 mm, dry

Wear Resistance, Ductile Cast Iron (GGG)



Work Material: GGG-70, Continuous, Insert: CNMG120408
Cutting Conditions: v_c = 140 m/min, f = 0,3 mm/rev, a_p = 1,5 mm, wet

AC4010K / AC4015K

Chipping Resistance, Gray Cast Iron (GG)





Work Material: GG-25, Interrupted, Insert: CNMG120408
Cutting Conditions: v_c = 400 m/min, f = 0,3 mm/rev, a_p = 2,0 mm, wet

Chipping Resistance, Ductile Cast Iron (GGG)





Work Material: GGG-40.3, Interrupted, Insert: CNMG120408
Cutting Conditions: v_c = 450 m/min, f = 0,3 mm/rev, a_p = 1,5 mm, wet

AC420K Fracture Resistance

GGG-40.3 Grooved (Heavy Interrupted Acceleration Test)



Edge Wear Comparison (After 150s)

Work Material: GGG-40.3, Toolholder: PCLNR2525-43 Insert: CNMG120408
Cutting Conditions: v_c = 350 m/min, f = 0,25 mm/rev, a_p = 1,5 mm, wet

Chipbreakers

Negative Type



Positive Type



Grades



S Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

Work Material	Cutting Process	Chipbreakers	Grades	Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
Heat-Resistant Alloy	Finishing	NEF (NSU)	**AC5010S** AC5025S	0,2–**0,5**–1,5	0,10–**0,12**–0,20	50–**70**–110
	Light	NEX	**AC5015S** AC5025S	0,5–**1,0**–3,0	0,10–**0,20**–0,30	40–**60**–90
	Medium	NEG	**AC5015S** AC5025S	0,5–**2,0**–4,0	0,15–**0,25**–0,30	40–**60**–90
	Rough	NMU/NEM	**AC5015S** AC5025S	1,0–**2,0**–4,0	0,20–**0,25**–0,40	30–**55**–80
Titanium Alloy	Finishing	NEF (NSU)	**EH510** (AC5015S)	0,2–**0,5**–1,5	0,10–**0,15**–0,20	50–**65**–80
	Light	NEX	**AC5015S**	0,5–**1,0**–2,5	0,10–**0,20**–0,25	40–**55**–70
	Medium	NEG	**EH510** (AC5015S)	0,5–**2,0**–3,5	0,15–**0,25**–0,30	40–**55**–70
	Rough	NMU/NEM	**AC5025S**	1,0–**2,0**–3,5	0,20–**0,25**–0,30	30–**40**–50

Grades

New AC5015S / New AC5025S / EH510 / EH520

PVD (Super ZX Coat) grade with excellent wear and thermal resistance.

AC5015S The 1st recommended grade for turning exotic alloys as it realises stable tool life with high-speed, high-efficiency machining.

AC5025S High-toughness grade for realising stable tool life for interrupted cutting machining or mill-scaled work.

Carbides with excellent thermal, wear, and fracture resistance for use with exotic alloys. Lineup also includes new chipbreaker design.

EH510 General purpose grade for titanium machining that features excellent wear and thermal resistance. For applications from roughing to finishing.

EH520 Tough grade for titanium machining with excellent fracture and thermal resistance. Perfect for interrupted cutting and mill-scaled work.

Performance

AC5015S

Wear Resistance



AC5015S | Conventional | Competitor

Work Material: Inconel 718 (44 HRC) Insert: CNMG120408
Cutting Conditions: v_c = 40 m/min, f = 0,1 mm/rev, a_p = 1,5 mm, wet

Fracture Resistance





AC5015S | Conventional | Competitor

Work Material: Hastelloy (22 HRC), Insert: CNMG120408
Cutting Conditions: v_c = 50 m/min, f = 0,1 mm/rev, a_p = 1,5 mm, wet

AC5025S

Wear Resistance





AC5025S | Conventional | Competitor

Work Material: Inconel 718 (44 HRC) Insert: CNMG120408
Cutting Conditions: v_c = 40 m/min, f = 0,1 mm/rev, a_p = 1,5 mm, wet

Fracture Resistance





AC5025S | Conventional | Competitor

Work Material: Hastelloy (22 HRC), Insert: CNMG120408
Cutting Conditions: v_c = 50 m/min, f = 0,1 mm/rev, a_p = 1,5 mm, wet

Chipbreakers

NSV Type Chipbreaker: For chip control during carburized layer removal
NLV Type / NFV Type Chipbreaker: For chip control during finishing of hardened steel



Grades



H Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

Cutting Process	Grade	Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
Continuous Cutting	**BNC2010**	0,03–**0,20**–0,35	0,03–**0,10**–0,20	120–**200**–300
	BNC100	0,03–**0,20**–0,30	0,03–**0,10**–0,20	120–**200**–300
	BN1000	0,03–**0,15**–0,20	0,03–**0,10**–0,15	100–**150**–300
	BNX10	0,03–**0,10**–0,20	0,03–**0,10**–0,15	120–**180**–300
	AC503U	0,03–**0,50**–1,00	0,02–**0,05**–0,10	40–**70**–100
General Turning	**BNC2020**	0,03–**0,30**–0,50	0,03–**0,20**–0,40	50–**130**–220
	BNC160	0,03–**0,20**–0,35	0,03–**0,10**–0,25	120–**180**–220
	BNC200	0,03–**0,30**–0,50	0,03–**0,10**–0,30	50–**130**–220
	BN2000	0,03–**0,20**–0,30	0,03–**0,10**–0,20	50–**100**–200
	BNX20	0,03–**0,20**–0,35	0,03–**0,15**–0,30	70–**130**–170
Interrupted Cutting	**BNC300**	0,03–**0,20**–0,30	0,03–**0,10**–0,20	50–**100**–150
	BN350	0,03–**0,20**–0,30	0,03–**0,10**–0,20	50–**100**–150
	BNX25	0,03–**0,20**–0,50	0,03–**0,15**–0,30	120–**160**–220

Grades

BNC2010 / BNC2020 / BN1000 / BN2000

BNC2010 A grade for high-precision machining applicable for finishing requiring good surface roughness and dimensional accuracy.
Provides further improved wear resistance thanks to a newly developed CBN substrate coated with a TiCN layer.
Reduces flank wear and achieves excellent surface finish thanks to newly developed special stable multi-layered coating.

BNC2020 A general-purpose grade applicable to general hardened steel machining.
A newly developed tough CBN-substrate coated with a highly wear-resistant TiAlN layer.
Achieves more stable machining and longer tool life by employing a highly adhesive layer for high chipping resistance.

BN1000 For high speed machining. BN1000 provides the highest wear resistance of all uncoated SUMIBORON grades.
Features improved fracture resistance while still placing a priority on wear resistance.

BN2000 General purpose grade suitable for typical hardened steel machining applications.
Provides a high degree of fracture and wear resistance.

Performance

BNC2010



Work Material:	15CrMo5, 58-62HRC, Continuous
Insert:	DNGA 150408 NC4 (BNC2010)
Cutting Edge Treatment:	S01225
Cutting Conditions:	v_c = 160 m/min, f = 0,08 mm/rev, a_p = 0,1mm, Wet

BNC2020



Work Material:	SCM415-5V, 58-62HRC, Interrupted
Insert:	CNGA 120412 NC4 (BNC2020)
Cutting Edge Treatment:	S01225
Cutting Conditions:	v_c = 130 m/min, f = 0,1 mm/rev, a_p = 0,6 mm, Dry

BN1000 / BN2000

Wear Resistance (Continuous Cutting)



Work Material: 15CrMo5, Round Bar (58-62HRC)
Cutting Conditions: v_c = 100 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, Dry



Work Material: 100Cr6, Round Bar (58-62HRC)
Cutting Conditions: v_c = 150 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, Dry

Chipping Resistance (Interrupted Cutting)

(Comparison based on conventional BN2000 as 100%.)



Work Material: 15CrMo5, 8V Grooved Material (58-62HRC)
Insert: CNGA120408 NU-2
Cutting Conditions: v_c = 150 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, Dry

Chipbreakers

Positive Type





Grades



N Recommended Cutting Conditions

(Min. - **Optimum** - Max.)

Cutting Process	Category	Grades	Cutting Conditions		
			Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
Continuous Cutting General Turning Interrupted Cutting	SUMIDIA	**DA1000**	0,1–**0,5**–3,0	0,05–**0,10**–0,20	–2000
	Carbide	**H1**	0,3–**1,0**–5,0	0,1–**0,20**–0,5	–1000

Grades DA1000

- Ultra-high-density sintered, ultra-fine diamond particles
- Significantly improved surface roughness on machined surfaces
- World's best wear resistance and strength
- Suitable for use with all aluminium and non-ferrous alloys

DA1000 Wear Resistance



Comparison of Surface Roughness of Nose Radius Cutting Edge



Insert: TPGW 160308
Cutting Conditions: v_c = 1000 m/min, f = 0,15 mm/rev, a_p = 0,2 mm, Wet

Wear Resistance in Turning Applications



Insert: TPGN160304
Cutting Conditions: v_c = 800 m/min, f = 0,12 mm/rev, a_p = 0,5 mm, wet

Wear Resistance in Milling Applications



Insert: SNEW1204 ADFR-NF
Cutting Conditions: v_c = 2000 m/min, f = 0,15 mm/rev, a_p = 3,0 mm, wet

Application Examples

H1 + NAG Type Breakers

ADC12 Aluminium Wheel

Excellent adhesion resistance.
Longer tool life.





Insert: VCGT160408 NAG (H1)
Cutting Conditions: v_c = 2000 m/min, f = 0,25 mm/rev, a_p = 2,0 mm, wet

DA1000

Copper Alloy Bush

Stable surface roughness with no edge breakage (3,2S).
Tool life improved to 3x that of conventional models.





Insert: TPGN160308 NF (DA1000)
Cutting Conditions: v_c = 300 m/min, f = 0,07 mm/rev, a_p = 0,08 mm, wet

Grades

Category	Application Range: High Precision / Finish-Light Cut / Medium Cut	Work Material: P General Steel	M Stainless Steel	K Cast Iron	S Heat Resistant Steel	H Hardened Steel	N Non-Ferrous Metal
Coated Carbide (PVD)	ACZ150	◎	◎				○
	New AC5015S	○	◎	○	◎		
	New AC5025S	○	◎	○	◎		
	AC530U	◎	◎	○	○		○
	AC1030U	◎	◎	○	○		○
Cermet/Coated Cermet	T1000A	◎	○	◎			○
	T1500A/T1500Z	◎	○	○			○
Carbide	H1	○	○	○			◎
	EH510	○	○	○	◎		○
CBN (SUMIBORON)	BN1000/BN2000			◎	○	◎	
	BN7000			◎	○	◎	
SUMIDIA	DA1000						◎

◎ Preferred Choice ○ Suitable

Chipbreakers

M-Class Finishing to Light Cut



G-Class Chipbreaker (Groove Design)



G-Class Chipbreaker (3D Design)



Recommended Cutting Conditions

Work Material / Grade	P Free Cutting Steel		P Carbon Steel		M Stainless Steel		S Heat Resistant Steel		H Hardened Steel		N Aluminium		N Brass	
	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)
ACZ150	50–200	0,02–0,10	50–150	0,01–0,08	50–150	0,01–0,05					70–300	0,05–0,20	70–300	0,05–0,20
AC5015S	50–200	0,02–0,15	50–200	0,02–0,10	50–200	0,02–0,10	30–100	0,02–0,10					70–300	0,05–0,20
AC5 25S	50–200	0,02–0,15	50–200	0,02–0,10	50–200	0,02–0,10	30–100	0,02–0,10					70–300	0,05–0,20
AC530U	50–200	0,02–0,15	50–200	0,02–0,10	50–200	0,02–0,10							70–300	0,05–0,20
AC1030U	50–200	0,02–0,15	50–200	0,02–0,10	50–150	0,02–0,10							70–300	0,05–0,20
T1000A	50–200	0,02–0,15	50–200	0,02–0,10	50–150	0,02–0,10					70–300	0,05–0,20	70–300	0,05–0,20
T1500A	50–200	0,02–0,15	50–200	0,02–0,10	50–150	0,02–0,10					70–300	0,05–0,20	70–300	0,05–0,20
T1500Z	50–200	0,02–0,15	50–200	0,02–0,10	50–150	0,02–0,10					70–300	0,05–0,20	70–300	0,05–0,20
BN1000									120–300	0,03–0,15				
BN2000									50–200	0,03–0,20				
BN7000							50–200	0,05–0,20						
DA1000											70–300	0,02–0,10	70–300	0,02–0,10

Application Range



AC1030U

Employs "Absotech Bronze", a new PVD coating, with a special tough carbide substate.
Achieving excellent machined surface quality with a high-quality cutting edge that reduces adhesion and micro-chipping.

AC1030U Performance



Material:	X5CrNiS18-10, 1.4301
Insert:	DCGT11T302RFY (AC1030U)
Cutting Data:	v_c=100 m/min, f=0,05 mm/rev, a_p=0,1 mm, wet (Oil)

Wear Resistance



Roughness



Application Examples

STKM12C-EC, Pipe



Insert	CCGT060201LFX (AC1030U)
Cutting Data:	v_c = 196 m/min, f = 0,04 mm/rev, a_p = 0,4 mm, wet

C45, Stator Shaft





Insert	VCGT110302RFX (AC1030U)
Cutting Data:	v_c=195 m/min, f= 0,12 mm/rev, a_p = 0,175-0,25 mm, wet

X5CrNiS18-10, 1.4301, Valve Body





Insert:	VCGT110301RFY (AC1030U)
Cutting Data:	v_c = 31,5 m/min, f = 0,025 mm/rev, a_p = 0,2 mm, wet

X6Cr17, Sensor Housing





Insert:	DCGT11T304M NFC (AC1030U)
Cutting Data:	v_c = 50 m/min, f =0,06 mm/rev, a_p = 0,2 mm, wet

Grades

B

B1–B14



Coated Carbide

The hardmetal's coating series combines a proprietary tough cemented carbide substrate with a multi-layered coating for use in high-speed, high-efficiency applications on a wide range of work materials including steel, cast iron and exotic alloys.

Features

ABSOTECH: New coating technology that realises absolute stability.

CVD



Special Surface Treatment:
Chipping resistance and adhesion resistance are significantly improved by special surface treatment applied to suit the application.

High Strength Alumina Layer:
Significantly improves the coating strength by controlling crystal growth direction.

High Hardness Micro-Grain TiCN Layer:
Significantly improves the coating hardness by using a fine and uniform crystal structure.

High Adhesion Technology:
Significantly improves adhesion strength through a smooth interface between the coating and carbide substrate.

- Suppresses abnormal damage such as chipping and adhesion. Stable machining is achieved in various situations.
- Next-level high strength and high hardness coating is achieved. Achieves long, stable tool life even in high-efficiency machining.

Applicable Grades

For steel turning	AC8015P, AC8025P, AC8035P
For stainless steel turning	AC6020M, AC6030M
For cast iron turning	AC4010K, AC4015K
For Milling	ACP2000, ACK2000

PVD

The Proprietary Super Multi-layered Coating Structure:
Advanced nanotechnology enables nanometer-level thickness (1 nanometer is one billion of a meter)
Hardness, thermal resistance and toughness are significantly improved by alternately layering one thousand layers of super thin films.

Cross section of cutting-edge coating

High Adhesion Technology.
Significantly improves adhesion strength through advanced control technology at the interface of the coating and carbide substrate.

- Optimised coating composition according to application. Achieves stable machining regardless of the work material.
- Significantly improves chipping resistance by improving coating adhesion strength. Stable machining is realised even under high load conditions.

Applicable Grades

For stainless steel turning	AC6040M
For exotic alloy turning	AC5015S, AC5025S
For small lathes	AC1030U
For Milling	AC2500, ACP3000, ACK3000

Brilliant Coat PVD

Brilliant Coat provides excellent lubricity for higher quality machining.





Brilliant Coat

Conventional Coating

Work Material: STKM13A
Insert: CNMG120408NLU
Cutting Conditions: v_c: 100 m/min
f: 0,15 mm/rev
a_p: 1,0 mm, wet

- PVD coating with excellent wear resistance and lubricity.
- Suppresses reactions with work material and realises beautiful machined surfaces.

Applicable Grades

For steel turning	T1500Z

AURORA Coat (DLC : Diamond Like Carbon) PVD

Using our proprietary PVD process tech nology, we have developed a hydrogen-free DLC coating that is extremely hard and smooth.



Comparison of Cutting Edge Adhesion After Cutting ADC12



AURORA Coat



Uncoated

Work Material : ADC12
Cutting Conditions: v_c : 300 m/min
f_t : 0,15 mm/t
a_p= a_e : 5mm, dry

- Second only to diamond in terms of hardness, this smooth coating has a low coefficient of friction and provides excellent adhesion resistance to deliver better-quality machined surfaces.
- Can be used for high-speed, high-efficiency cutting of aluminium alloys, copper alloys, resins, and more.

Applicable Grades

For Milling	DL1000, DL2000
For Endmilling	DL1000, DL1200
For Drilling	DL1300, DL1500

Characteristic Values

For Turning (CVD)

Class	Grade	Hardness (HRA)	TRS (GPa)	Coating Type	Coating Thickness (μm)	Characteristics	Old Grades
P	AC810P	91,0	2,2	Super FF Coat	18	A P10 grade with excellent wear resistance that features stability and longer tool life. Utilises a special carbide substrate with Super FF Coat for high to medium speed cutting.	AC700G
	New AC8015P	91,0	2,3	Absotech	14	For high-speed and high-efficiency machining of steel. Crystal orientation control technology is used to drastically suppress the advancement of crater wear, achieving long, stable tool life during high-speed and high-feed cutting.	AC810P
	AC820P	90,1	2,2	Super FF Coat	14	A P20 grade that features stability and longer tool life. Employs special carbide substrate and Super FF Coat to improve on P20 wear and fracture resistance.	AC2000
	AC8025P	90,1	2,3	Absotech	12	A P20 grade that drastically reduces the occurrence of abnormal damage and achieves long and stable tool life by employing a special carbide substrate and the new Absotech Platinum coating.	AC820P
	AC830P	89,4	2,6	Super FF Coat	8	Stable long-life grade employs special tough, carbide substrate and Super FF Coat. Improves on P30 grade fracture resistance and approaches P20 grade in terms of wear resistance.	AC3000
	New AC8035P	89,4	2,6	Absotech	9	For interrupted machining of steel. Coating layer tensile stress removal technology greatly improves fracture resistance and achieves long, stable tool life during heavy interrupted cutting.	AC830P
M	AC610M	91,0	2,2	Super FF Coat	5	A high efficiency M10 grade featuring improved wear resistance during stainless steel cutting. Employs special, ultra-hard substrate and thin Super FF Coat.	—
	AC6020M	90,1	2,3	Absotech	5	An M20 grade that maintains wear resistance in stainless steel machining while drastically reducing the occurrence of abnormal damage by employing a special carbide substrate and the new Absotech Platinum coating.	AC610M
	AC6030M	89,5	2,7	Absotech	5	The first recommended grade for general machining of stainless steel that drastically reduces the occurrence of abnormal damage in stainless steel machining and achieves long and stable tool life by employing a new coating: Absotech Platinum.	AC630M
	AC630M	89,5	2,7	Super FF Coat	5	A general purpose grade featuring improved wear and fracture resistance during stainless steel cutting. Utilises a special tough carbide substrate with a thin Super FF Coat.	AC304
K	AC405K	92,0	2,4	Super FF Coat	18	Employs an ultra-hard substrate and ultra-hard Super FF Coat to provide excellent resistance to wear and plastic deformation. Suitable for high-speed continuous cutting of cast iron.	AC410K
	New AC4010K	91,1	2,5	Absotech	20	1st recommended grade for turning grey cast iron. For high-speed cast iron milling. New thick coating realizes stable long tool life even with ultra-high-speed machining of grey cast iron at v_c = 700 m/min.	AC405K
	New AC4015K	91,1	2,5	Absotech	16	1st recommended grade for turning ductile cast iron. New high-adhesion, high-strength coating realises high wear resistance and chipping resistance for stable long tool life over a wide range of cutting conditions.	AC415K
	AC415K	91,1	2,5	Super FF Coat	18	Employs a special dedicated ultra-hard substrate that is also suitable for interrupted cutting and ultra-hard Super FF Coat to provide stability and long tool life in a wide range of processes. First recommended grade for cast iron turning.	AC410K
	AC420K	91,1	2,5	Super FF Coat	12	A new, extremely versatile grade that can be used for rough, interrupted cutting of ductile and grey cast iron. Employs special, ultra-hard carbide substrate and Super FF Coat to provide stability and long tool life.	AC700G

For Milling (CVD)

Class	Grade	Hardness (HRA)	TRS (GPa)	Coating Type	Coating Thickness (μm)	Characteristics	Old Grades
P	ACP100	89,3	3,1	Super FF Coat	6	A grade that employs a tough carbide substrate and thin-layer Super FF Coat to provide superior thermal crack and wear resistance in high-speed milling of steel.	AC230
	New ACP2000	89,5	3,2	Absotech	10	For high-speed machining of steel. Stable long tool life with high-speed machining is realized by adopting a tough carbide substrate and a new coating with excellent thermal crack resistance.	ACP100
M	ACM200	89,8	3,4	Super FF Coat	6	A grade ideal for hardened steel machining that provides excellent wear and heat resistance by employing a newly-developed ultra-hard carbide and Super FF Coat.	AC230
K	ACK100	92,0	2,4	Super FF Coat	6	A grade that employs a high-strength carbide substrate and Super FF Coat to provide excellent wear resistance in high-speed milling.	—
	ACK200	91,7	2,5	Super FF Coat	6	A grade that employs a tough carbide substrate and thin-layer Super FF Coat to provide superior thermal crack and wear resistance for high-speed milling.	AC211
	New ACK2000	91,7	3,1	Absotech	10	For high-speed cast iron milling. Stable long tool life with high-speed machining is realized by adopting a tough carbide substrate and a new coating with excellent thermal resistance.	ACK100 ACK200

Characteristic Values

For Turning (PVD)

Class	Grade	Hardness (HRA)	TRS (GPa)	Coating Type	Coating Thickness (μm)	Characteristics	Old Grades
P	**T1500Z** (Cermet)	92,0	2,2	Brilliant Coat*	3	Brilliant Coat* PVD coating gives excellent lubricity for higher quality machining. General-purpose coated cermet grade that can maintain high-quality machined surfaces and also gives excellent wear resistance.	T2000Z
	T3000Z (Cermet)	91,3	2,4	ZX Coat	3	An ultra-reliable coating grade with tough cermet substrate.	—
	AC530U	91,4	3,3	Super ZX Coat	3	For interrupted and general steel cutting. Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers, coupled with a fine-grained super tough substrate for excellent fracture resistance.	ACZ310
M	**AC6040M**	91,6	3,8	Absotech	3	The first recommended grade for interrupted machining of stainless steel that drastically improves the reliability in unstable machining thanks to the excellent adhesion and peel-off resistance of the new Absotech Bronze PVD coating, as well as the improved fracture resistance of the exclusive ultra-hard carbide substrate.	AC530U
	AC530U	91,4	3,3	Super ZX Coat	3	Heavy interrupted machining and stainless steel machining. Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers, coupled with a fine-grained super tough substrate for excellent fracture resistance.	ACZ310
S	**AC510U**	92,6	2,6	Super ZX Coat	3	Finishing to medium cutting of exotic alloys. Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers. Superior wear and heat resistance, and stable, long tool life.	EH510Z EH10Z
	New **AC5015S**	92,7	3,2	Absotech	5	The first recommended grade for turning exotic alloy. Adopts a carbide substrate with excellent thermal resistance and a new coating with excellent wear resistance and chipping resistance, realizing stable long tool life over a wide range of cutting conditions.	AC510U
	AC520U	91,7	3,0	Super ZX Coat	3	Medium to rough cutting of exotic alloys. Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers. Superior wear and heat resistance, and stable, long tool life even in interrupted cutting.	EH520Z EH20Z
	New **AC5025S**	91,8	3,6	Absotech	5	For partially interrupted to interrupted machining of exotic alloy. Adopts a carbide substrate with excellent fracture resistance and a new coating with excellent wear resistance and chipping resistance, realizing stable long tool life with unstable cutting conditions.	AC520U
H	**AC503U**	93,2	1,7	Super ZX Coat	3	For hardenend steel. Utilizing the super multi-layered PVD coating of nanometre thick TiAlN and AlCrN layers, coupled with an ultra-hard substrate for excellent wear resistance.	—
Small Product Machining	**ACZ150**	91,4	3,3	ZX Coat	1	For small tools, and high-precision finishing to general finishing applications. TiN ultra-thin coating and fine-grained, super tough substrate combine to give good edge sharpness and superior cut finish.	—
	AC1030U	91,6	3,8	Absotech	2	For precision machining that supports a wide range of work materials. Employs the new "Absotech Bronze" coating with excellent adhesion and peel-off resistance to deliver excellent machined surface quality with improvements in cutting edge quality and superb stability.	—

For Milling (PVD)

Class	Grade	Hardness (HRA)	TRS (GPa)	Main Coating Components	Coating Thickness (μm)	Characteristics	Old Grades
P	New **ACU2500**	91,6	3,8	Absotech	3	General purpose grade supporting steel, stainless steel and cast iron machining. Adopts a carbide substrate with excellent fracture resistance and wear resistance, plus a new coating with wear and chipping resistance, realizing stable long tool life with various work material grades.	—
	ACP200	89,5	3,2	Super ZX Coat	3	For general machining of general and die steel. Employs PVD coating consisting of multiple nanometre-thin layers. A general grade that achieves a good balance between fracture resistance and wear resistance when combined with an exclusive tough substrate.	ACZ330
	ACP300	89,3	3,1	Super ZX Coat	3	For interrupted machining and stainless steel machining. Employs PVD coating consisting of multiple nanometre-thin layers. Provides excellent fracture resistance when combined with an ultra-tough substrate.	ACZ350
	New **ACP3000**	89,5	3,2	Absotech	3	1st recommended grade for milling steel. Carbide substrate with excellent thermal crack resistance, plus a new coating with excellent wear and chipping resistance, realizes stable long tool life over a wide range of cutting conditions.	ACP200 ACP300
M	**ACM100**	91,4	3,3	Super ZX Coat	3	A grade that provides excellent wear resistance by employing an ultra-hard fine-grained carbide and New Super ZX Coating.	ACZ310
	ACM300	89,8	3,4	Super ZX Coat	3	The first recommended grade for stainless steel machining that achieves a good balance between wear resistance and fracture resistance by employing a newly-developed ultra-hard carbide and New Super ZX Coating.	—
K	**ACK300**	91,4	3,3	Super ZX Coat	3	General-purpose grade with an excellent balance of wear and fracture resistance.	ACZ310
	New **ACK3000**	91,7	3,1	Absotech	3	1st recommended grade for milling cast iron. Adopts a high thermal conductivity carbide substrate and a new coating with excellent wear and chipping resistance, realizing stable long tool life over a wide range of cast iron machining operations.	ACK300
N	**DL1000**	92,9	2,1	AURORA Coat (DLC Coat)	0,5	For milling non-ferrous metal, utilizing DLC coat with a low coefficient of friction and excellent adhesion resistance.	—
	New **DL2000**	91,6	3,8	AURORA Coat (DLC Coat)	0,5	For milling non-ferrous metal, utilizing DLC coat with a low coefficient of friction and excellent adhesion resistance.	—

*There may be minor differences in the colour tone/lustre of Brilliant Coat grades due to the interference of light. Such differences have no effect on performance.

Cermet

Various grades and expanded lineup of catalogue items meet a wide range of finishing needs.

Lineup includes wear-resistant T1000A, general purpose T1500A, general purpose coated cermet T1500Z and tough T2500A.
Significantly expanded lineup of catalogue items for a wide variety of finishing applications.

Characteristics

Uncoated Cermet

T1000A High Speed Finishing Grade

High speed finishing grade with excellent wear resistance.
- Improved wear and fracture resistance.
- Solid solution hard phase reduces reaction with steel.
- Perfect for high-speed continuous finishing of steel, cast iron and powdered metal.

Uncoated Cermet

T1500A New General Purpose Grade

General purpose cermet grade that provides both wear and fracture resistance with better qualitiy finished surfaces.
- Mixing hard phases of different functionality, grain size and compositions improves balance of wear and fracture resistance.
- Reduces adhesion of work material for beautiful finished surfaces.

Uncoated Cermet

T2500A

Tough grade with excellent fracture resistance and thermal crack resistance.
- Fine, uniform grain structure greatly improves toughness
- Improves thermal crack resistance due to the high thermal conductivity and realizes long stable tool life.

Coated Cermet

T1500Z New General Purpose Grade

General purpose coated cermet grade that employs new Brillant Coat* PVD coating with excellent lubricity.
- Excellent wear resistance provides long tool life.
- Reduces adhesion of work material for beautiful finished surfaces.

Characteristic Values

For Turning

Class	Grade	Hardness (HRA)	TRS (GPa)	Coating Type	Coating Thickness (μm)	Characteristics	Old Grades
P	T1000A	93,3	1,8	—	—	Uncoated cermet grade with excellent wear resistance that provides good cost efficiency. Demonstrates excellent wear resistance in continuous finishing applications, and stable finishing of cast iron and sintered alloy as well as steel.	T110A
P	T1500A	92,0	2,2	—	—	A general purpose grade that employs a substrate with improved balance of fracture and wear resistance to deliver superior finished surfaces in a wide variety of cutting conditions.	T1200A
P	New T2500A	91,8	2,4	—	—	For interrupted machining of steel. Fine, uniform grain structure greatly improves toughness, realizing long tool life and excellent surface finish even with interrupted cutting.	—
P	T1500Z	92,0	2,2	PVD Brilliant Coat*	3	Brilliant Coat's* new PVD coating gives excellent lubricity for higher quality machining. General-purpose coated cermet grade that can maintain high-quality machined surfaces and also gives excellent wear resistance.	T2000Z
P	T3000Z	91,3	2,4	PVD ZX Coat	3	An ultra-reliable coated grade with tough cermet substrate.	—
K	T1000A	93,3	1,8	—	—	Exclusive uncoated cermet grade with excellent cost efficiency suitable for cast iron finishing, which requires high hardness.	T110A

For Milling

Class	Grade	Hardness (HRA)	TRS (GPa)	Coating Type	Coating Thickness (μm)	Characteristics	Old Grades
P	T1500A	92,0	2,2	—	—	A general-purpose grade that employs a substrate with an improved balance between fracture and wear resistance to deliver superior finished surfaces in a wide variety of cutting conditions.	T1200A
P	T250A	91,4	2,1	—	—	Tough cermet grade with enhanced crack advancement resistance.	—
M	New T2500A	91,8	2,2	—	—	For finishing of steel and stainless steel. Fine, uniform grain structure greatly improves toughness, realizing long tool life and excellent surface finishing.	T250A
M	T4500A	91,0	2,3	—	—	For finishing of steel and stainless steel. Tough grade with excellent fracture resistance and reduced thermal cracking.	—

*There may be minor differences in the colour tone/lustre of Brilliant Coat grades due to the interference of light. Such differences have no effect on performance.

WC (Tungsten Carbide)
„Igetalloy“

Igetalloy carbides have a solid history and a big variety of grades to suit many different applications. They are widely used and appreciated for their superior performance.

The Igetalloy line-up consists of carbide cutting tools that are available in a variety of different structures and compositions, each differing in terms of WC grain size and containing varying amounts of CO binder and TiC, TaC, and other double carbide components. The wide selection enables excellent wear resistance and toughness with a variety of work materials and cutting conditions.

● For Steel



● For Stainless Steel



● For Cast Iron



Characteristic Values

Application	Grade	Hardness (HRA)	TRS (GPa)	Young's Modulus (GPa)	Thermal Conductivity (W/m·°C)	Compressive Strength (GPa)	Linear-Thermal Expansion Coefficient (X 10^{-6}/°C)
P	**ST10P**	92,1	1,9	470	25	4,9	6,2
	ST20E	91,8	1,9	550	42	4,8	5,2
	A30	91,3	2,1	520	—	—	5,2
	A30N	91,2	2,2	520	—	—	—
	ST40E	90,4	2,6	—	75	—	—
M	**EH510**	92,6	2,6	—	—	—	—
	EH520	91,7	3,0	—	—	—	—
	A30	91,3	2,1	520	—	—	5,2
	A30N	91,0	2,4	—	—	—	—
K	**BL130**	94,3	2,9	—	—	—	—
	H2	93,2	1,8	600	105	6,1	4,4
	H1	92,9	2,1	650	109	6,1	4,7
	EH510	92,6	2,6	—	—	—	—
	H10E	92,3	2,0	—	67	—	—
	EH520	91,7	3,0	—	—	—	—
	G10E	91,1	2,2	620	105	5,7	—
N	**H1**	92,9	2,1	650	109	6,1	4,7
	New **H20**	91,6	3,8	—	—	—	—
S	**EH510**	92,6	2,6	—	—	—	—
	EH520	91,7	3,0	—	—	—	—

High hardness and heat resistance for cutting high hardness steel and hard cast iron. Long tool life with high-speed finishing of grey cast iron.

In 1977, Sumitomo Electric Hardmetal successfully developed a revolutionary CBN sintered tool - SUMIBORON. The main component in SUMIBORON is Cubic Boron Nitride with a special ceramic binder sintered under super high pressure and temperature. As compared to other conventional tool materials, CBN has higher hardness and excellent heat resistance.

With these distinct characteristics, SUMIBORON can perform machining of hardened steel, high hardness cast iron and exotic metals where previously only grinding was done. Furthermore, excellent efficiency and longer tool life can also be achieved from high speed machining of cast irons.

Characteristics

Classifications	Structure	CBN Content	Hardness (GPa)	Grades	Application	Characteristics
Purely CBN particles, firmly bonded		High ↑	54 ↑	NCB100	Cast Iron, Titanium Alloy, Pure Titanium, Co-Cr-Alloy, Cemented Carbide, Cermet	Containing no binder, the nano-to sub-micron CBN particles have a directly bonded structure. The high hardness and thermal conductivity make it highly efficient with a long tool life when machining exotic alloys such as titanium alloys and Co-Cr alloys.
Mainly CBN grains fused together				BN700 BN7000 BN7500 BNS800	Carbide, Chilled cast iron, Ni-Hard cast iron,Heat-resistant alloy, Cast iron Sintered ferrous alloy	High carbon content. Structure consists of strongly fused CBN grains. Suited to cutting cast iron, heat-resistant alloy, ultra-hard alloy, and other hard materials.
Mainly CBN grains held together with a binder		↓ Low	↓ 27	BN1000, BN2000, BN350 BNX10, BNX20, BNX25 BN500, BN2010, BN2020 BNC300, BNC100, BNC160 BNC200, BNC500	Alloy steel, Case hardened steel, Carbon tool steels, Bearing steel, Die steel, Ductile cast iron	CBN grains are fused together strongly with a special ceramic binder. Strong CBN binding force gives superior wear resistance and toughness when cutting hardened steel and cast iron.

Grade Range Map



* Dedicated for Ductile Cast Iron.

Characteristic Values

Class	Grade	Binder	Carbon Content (%)	Grain Size (μm)	Hardness HV (GPa)	TRS (GPa)	Main Coating Components	Coating Thickness (μm)	Characteristics
H	**BNC2010**	TiCN	50–55	2	30–32	1,10–1,20	TiCN multi-layered	1,5	Improves the wear resistance of coating and substrate and stably achieves excellent surface roughness.
	BNC2020	TiN	70–75	5	34–36	1,20–1,30	TiAlN multi-layered	1,5	Provides long tool life in general and high-efficincy cutting thanks to tough substrate coated with a highly wear-resistant and highly adhesive layer.
	BNC100	TiN	40–45	1	29–32	1,05–1,15	TiAlN	1	Highly wear resistant coating makes this grade suited for high speed finishing.
	BNC160	TiN	60–65	3	31–33	1,10–1,20	TiAlN/TiCN	2	Stable, high precision finishing of hardened steel.
	BNC200	TiN	65–70	4	34–36	1,15–1,25	TiAlN/TiCN	2	Tough substrate with high wear resistant coating provide longer tool life.
	BNC300	TiN	60–65	1	33–35	1,15–1,25	TiAlN	2	Suited for finishing when there is a combination of continuous and interrupted cutting.
	BNX10	TiCN	40–45	3	27–31	0,80–0,90	–	–	Optimum wear resistance. Suited to continuous, high-speed cutting.
	BN1000	TiCN	40–45	1	27–31	0,90–1,00	–	–	Ultimate wear and fracture resistance. Suited to high-speed cutting.
	BNX20	TiN	55–60	3	31–33	0,95–1,10	–	–	Crater resistant grade, suitable for high efficiency cutting under high temperature conditions.
	BNX25	TiN	65–70	4	29–31	1,00–1,10	–	–	Excellent fracture resistance during high speed cutting. Suited to high speed interrupted cutting of hardened steel.
	BN2000	TiN	50–55	2	31–34	1,05–1,15	–	–	A general purpose grade for hardened steel that provides a high degree of fracture and wear resistance.
	BN350	TiN	60–65	1	33–35	1,20–1,30	–	–	High cutting edge strength. suited to heavy interrupted cutting.
Sintered Components	**BN7500**	Co Compound	90–95	1	41–44	1,40–1,50	–	–	Maintains optimum cutting edge sharpness. Suited for finishing of sintered alloy.
	BN700	Co Compound	90–95	2	40–43	1,20–1,30	–	–	Maintains good wear and fracture resistance in rough cutting of sintered components.
	BN7000	Co Compound	90–95	2	41–44	1,30–1,40	–	–	Improved wear and fracture resistance in rough cutting of sintered components.
K	**BN700**	Co Compound	90–95	2	40–43	1,20–1,30	–	–	Maintains good wear and fracture resistance in rough cutting of cast iron and exotic alloy.
	BN7000	Co Compound	90–95	2	41–44	1,30–1,40	–	–	Improved wear and fracture resistance in rough cutting of cast iron and exotic alloy.
	BNS800	Al Alloy	85–90	8	39–42	0,95–1,10	–	–	100% solid CBN structure with good thermal impact resistance.
	BNC500	TiC	60–65	4	32–34	1,00–1,10	TiAlN	2	Substrate with excellent wear resistance and coating makes this grade suited for hard-to-cut cast iron.
S	New **NCB100**	–	100	–0,5	51–54	1,8–1,9	-	–	Achieves high-efficiency, improved machining accuracy and long tool life in machining of exotic alloys such as titanium alloy and Co-Cr alloys.

Excellent wear resistance, longer tool life, and high-speed, high-efficiency, high-precision cutting of non-ferrous metals and non-metals.

SUMIDIA is a polycrystalline diamond material made from sintered diamond powder that was first created using our proprietary technology in 1978.
SUMIDIA's superior wear resistance achieves longer tool life, high speed, high efficiency and high precision in non-metal cutting and non-ferrous metal applications including aluminium, copper, magnesium and zinc alloys.

SUMIDIA Binderless uses nano-polycrystalline diamond for the cutting edge, demonstrating excellent wear resistance and fracture resistance.
In particular, it achieves extended tool life and machining accuracy superior to conventional polycrystalline diamond when machining hard brittle materials such as cemented carbides.

Features

Diamond particles on the order of submicrons to several dozen microns, sintered at high density.

Structure

SUMIDIA Binderless	SUMIDIA		
NPD10	DA1000	DA150	DA90
 Diamond particles			 Black areas in image are diamond particles.

Grade Range Map

Class	Series	Finishing – Light Cutting		Medium Cutting	Rough – Heavy Cutting
	Classification	01	10	20	30
Brittle Materials	SUMIDIA Binderless	NPD10			
	SUMIDIA		DA90		
	Classification	N01	N02	N20	N30
N	SUMIDIA	DA1000			
			DA150		
		DA90			

Characteristic Values

Class	Grade	Binder	Carbon Content (%)	Grain Size (μm)	Hardness HV (GPa)	TRS (GPa)	Characteristics
Brittle Materials	NPD10	Co	100	<=0,05	120–130	≈ 3,15	100% diamond that directly binds nano-order diamond particles with high strength. Demonstrates optimum wear and fracture resistance as well as the best edge sharpness.
N	DA1000	Co	90–95	–0,5	110–120	≈ 2,60	High density sintered material made of ultra-fine diamond particles that demonstrates optimum wear and fracture resistance, and edge sharpness.
	DA150	Co	85–90	5	100–120	≈ 1,95	Sintered material made of fine diamond particles that provides a good balance of workability and wear resistance.
	DA90	Co	90–95	50	50–65	≈ 1,10	Coarse sintered diamond particles, with high diamond content for excellent wear resistance.

SUMIDIA Binderless

SUMIDIA Binderless Series uses nano-polycrystalline diamond for the cutting edge and demonstrates excellent wear and fracture resistance compared to conventional sintered diamond tools.
In particular, SUMIDIA Binderless Series allows for improvements in tool life and machining precision that go far beyond conventional diamond tools in the machining of hard brittle materials, such as carbide.

Excellent for High Precision Machining of Carbide
Nano-polycrystalline diamond with excellent wear resistance achieves high precision machining of carbide.

Maintains Superior Dimensional Tolerances Over Many Hours
Greatly reduces the number of tool replacemets compared to conventional diamond tools and increases work efficiency while reducing total costs.

Suitable for Hard Brittle Material Machining
Hard brittle materials (such as ceramics) that could only be ground before can now be cut.

Characteristics

Comparison of Structure

Nano-Polycrystalline Diamond SEM Structure



Diamond Particles (30–50 nm)

Conventional PCD SEM Structure

Diamond Particles (1–10 μm)

Hardness



Application (Carbide Machining)

Hardness < 88HRA



Hardness ≥ 88HRA



Recommended Cutting Conditions (Carbide Machining)

Coolant: Dry Min. - **Optimum** - Max.

Work Material				Cutting Conditions		
Classification		Hardness (HRA)	SEH Grade	Cutting Speed v_c (m/min)	Feed Rate f (mm/rev)	Depth of Cut a_p (mm/rev)
VM VC	70 60 50	83–87	G7 G6	5–**20**–30	0,03–**0,10**–0,20	0,03–**0,10**–0,20
VM VC	40	≥ 88	G5 G2	5–**15**–30	0,03–**0,05**–0,07	0,03–**0,10**–0,20

Coated Carbide (CVD)

Application	Class	Grade	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Mitsubishi-Hitachi	Sandvik	Kennametal	SECO Tools Japan	WALTER	ISCAR	Taegu Tec	NTK
Turning	P	P05	**AC8015P AC810P**	UE6105	T9105	CA510 CA5505	HG8010	GC4305 GC4205	KCP05 KCP05B KC9105	TP0501 TP0500	WPP05S WPP05 WPP01	IC8005 IC8150 IC428	TT8105	
		P10	**AC8015P AC810P**	MC6015 UE6110	T9105 T9115	CA510 CA515 CA5515	HG8010	GC4305 GC4215 GC4315	KCP10 KCP10B	TP1501 TP1500	WPP10S WPP10	IC5100 IC8150 IC8250 IC9015	TT8115	CP7
		P20	**AC8025P AC820P**	MC6025 UE6020	T9115 T9125	CA025P CA525	HG8025 GM8020	GC4315 GC4225 GC4325 GC1515	KCP25 KCP25B	TP2501 TP2500	WPP20S WPP20	IC8150 IC8250 IC8350 IC9015	TT5100 TT8125	CP7
		P30	**AC8035P AC830P AC6030M AC630M**	MC6035 UE6035	T9125 T9135 T6130	CA025P CA525 CA530	GM25	GC2025 GC4325 GC4335 GC4235	KCP30 KCP30B	TP3500	WPP30S WPP30	IC8350 IC8025	TT7100 TT8135	
		P40	**AC8035P AC830P AC6030M AC630M**	UH6400	T9135 T6130	CA530 CA5535	GX30 GM8035	GC4335 GC4235 GC30	KCP40 KCP40B	TP3500		IC8350 IC8025	TT7100	
	M S	M10 S10	**AC610M AC6020M**	MC7015 US905 US7020	T9115	CA6515	HS9105	GC2015 GC1515 S05F	KCM15			IC6015 IC8025 IC8150 IC8250 IC5820	TT9215	
		M20 S20	**AC6020M AC6030M AC610M**	MC7025 US7020	T6120 T9125	CA6525	HG8025	GC2025 GC1515	KCM25	TP2501 TP2500 TM2000		IC6015 IC6025 IC8350	TT5100 TT9225	
		M30	**AC6030M AC630M AC8035P AC830P**	MC7025 US735	T6130	CA6535	GM8035 GX30 GM25	GC2035 GC235	KCM35 KC9240	TP3500 TM4000		IC6025	TT9235	
		M40	**AC6040M AC630M**	US735				GC235 GC2035		TM4000			TT7800	
	K	K05	**AC4010K AC405K**	MC5005 UC5105 UC5115	T5105	CA310 CA4505 CA4010	HG3305 HX3505	GC3005 GC3205 GC3210	KCK05	TK1000 TK1001	WAK10 WKK10S	IC5005	TT7005 TT7505	CP1
		K10	**AC4010K AC4015K AC405K AC415K**	MC5005 MC5015 MC5020 UC5105 UC5115	T515 T5105 T5115 T5125	CA315 CA4505 CA4515 CA4115	HX3305 HG3305 HG3315 HX3515 HG8010 TH315 ATH10E	GC3005 GC3210 GC4305	KCK15	TK1000 TK1001	WAK10 WAK20 WKK10S WKK20S	IC5005 IC5010 IC5100	TT7015	CP1
		K20	**AC4015K AC415K AC420K AC425K**	MC5015 UC5115 UE6110	T5125 T9125	CA320 CA4515 CA4120 CA4115	HX3315 HG3315 HG8025	GC3215 GC4325	KCK15 KCK20	TK2000 TK2001	WAK20 WAK30 WKK20S	IC5010 IC8150	TT7015	
Milling	P	P10	**ACP2000 ACP100**	FH7020 F7030 MV1020	T3130 T3030			GC4220 GC4230 GC3040	KC930M KC935M	MP1500 MP2500	WKP25 WKP25S WPP35G WKP35S	IC4100 IC4050 IC520M DT7150 IC5400	TT7080 TT7515 TT9300	
		P20	**ACP2000**	F7030				GC2040 GC4240	KCPM20				TT7400	
		P30	**ACP2000**	F7030					KCPK30 KCMP30				TT7800	
	M S	M10	**ACM100**											
		M20	**ACM200**	F7030	T3130	CA6535	GX2160 AX2040	GC2040		MS2500	WKP35S		TT7800	
		M30		F7030					KC994M			IC5820	TT7800	
	K	K10	**ACK2000 ACK100 ACK200**						KCK15			IC5100	TT7515	
		K20	**ACK2000 ACK200**	MV1020 MC5020 F5010 F5020	T1115	CA420M	GX2120	GC3330 GC3220 GC3225 GC3020 GC3040	KC915M KC930M KC935M	MK1500	WAK15 WKP25S	IC5100 DT7150 IC4010 IC4050 IC4100	TT6800 TT7080	

Coated Carbide (PVD)

Application	Class	Grade	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Mitsubishi-Hitachi	Sandvik	Kennametal	SECO Tools Japan	WALTER	ISCAR	Taegu Tec	NTK
Turning	P	P05	**ACZ150**		AH710 AH110	PR915 PR1005								
		P10	**AC1030U ACZ150 AC5025S AC520U**	VP15TF MS6015	AH120 AH725	PR930 PR1215 PR1225						IC807		TM1 VM4 DT4 DM4
		P20	**AC1030U AC5025S AC520U AC530U**	VP15TF VP20RT	AH120 AH725 AH3135	PR1225 PR1425	IP2000	GC15 GC1125	KCU25			IC807 IC808 IC810	TT9080	TM1 TM4 VM1 QM3 DM4
		P30	**AC1030U AC530U**	VP15TF VP20RT	AH120 AH725 SH730	PR1425 PR1525 PR1535	IP3000 CY250	GC1125				IC328 IC330 IC830 IC928	TT8020 TT8080 TT9080	QM3
		P40	**AC1030U**			PR660	IP3000	GC4335 GC4235				IC830	TT8020 TT8080	

Grade Comparison Chart

■ Coated Carbide (PVD)

Appli-cation	Class	Grade	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Mitsubishi-Hitachi	Sandvik	Kennametal	SECO Tools Japan	WALTER	ISCAR	Taegu Tec	NTK
Turning	M	M10 S10	**AC5015S AC5025S AC510U AC520U ACZ150**	MP9005 MP9015 VP15TF VP05RT VP10RT	AH110 AH710 AH725 AH905 AH8005	PR005S PR015S PR915 PR1025 PR1215 PR1225 PR1305 PR1310	IP050S IP100S JP9105 JP9115	GC1105 GC1115	KC5510 KCU10	TS2000	WSM01 WSM10 WSM10S	IC807 IC808 IC907 IC908	TT5080 TT3010	TM1 VM1 DT4 DM4 ZM3 ST4
	M S	M20 S20	**AC520U AC1030U AC5015S AC5025S**	MP9015 MP9025 VP15TF VP20RT VP20MF UP20M	AH630 AH120 AH725 AH8015	PR015S PR915 PR930 PR1025 PR1125 PR1215 PR1225 PR1325	IP100S HS9115	GC15 GC1115 GC1125	KC5525 KCU25 KC5025	TS2500	WSM20 WSM20S	IC330 IC806 IC808 IC830 IC908 IC928	TT9080 TT9020 TT3020	DT4 DM4 ZM3 QM3 TM4 ST4
		M30	**AC5025S AC6040M AC520U AC530U AC1030U**	MP7035 VP15TF VP20MF	AH630 AH645 AH725	PR1125 PR1525 PR1535		GC1125			WSM30 WSM30S	IC328 IC330 IC830 IC840 IC882	TT8020 TT8080 TT9080	QM3 TM4 DT4 DM4
		M40	**AC6040M AC530U AC1030U**	MP7035 VP15TF MS6015	AH645	PR1125 PR1535	GX30					IC830 IC928	TT8020 TT8080	
	K	K10	**ACZ150 AC1030U AC510U**	VP10RT	AH110 AH120	PR905	HX3305 HG3305 HG3315 HX3515 HG8010 TH315 ATH10E	GC15				IC810	TT6080	
		K20	**ACZ150 AC1030U AC510U AC530U**	VP10RT VP20RT VP15TF	AH120	PR905							TT6080	DM4 QM3
		K30	**AC1030U AC530U**	VP15TF VP20RT	AH110 AH120 AH725							IC830 IC908 IC910 IC928		
Milling	P	P10	**ACU2500 ACP200**	VP15TF MP6120	AH120 AH725	PR930 PR1225	PN215 PN15M JP4005 JP4105 JP4115 JP4120 GX2140		KC715M	T250M T350M F25M		IC807 IC903	TT2510 TT7080	TM1 DT4 DM4
		P20	**ACP3000 ACU2500 ACP200 ACP300**	VP15TF VP20RT MP6120 MP6130	AH9030 AH120 AH725 AH3135	PR1525 PR1225 PR1230 PR830	JP4020 JP4120 JS4045	GC1010 GC1025		MP3000 F30M	WSM20 WSM20S	IC807 IC808 IC810 IC380 IC330	TT7080 TT9030 TT9080	TM1 TM4 DT4 DM4
		P30	**ACP3000 ACU2500 ACP200 ACP300**	VP15TF VP30RT MP6130	AH3035 AH3135 AH120 AH130 AH140 AH725	PR1525 PR1535 PR1230	JD4045 JS4060 JX1045 JX1060 CY150 CY250 PTH30E	GC1030 GC1130 GC2030	KC725M KC730M KC735M KC7140 KCU40	MM4500 F40M	WSM35 WSP45 WSP45S	IC328 IC330 IC380 IC830 IC928	TT8080 TT8020	DM4 TM4 ZM3
		P40	**ACP3000 ACU2500 ACP300**	VP30RT	AH140		JS4060 JM4160 PTH40H					IC830	TT8020 TT8080	
	M	M10 S10	**ACM100 ACU2500 ACK300 ACP300**	MP9120 VP15TF VP10RT	AH110 AH120 AH330 AH725	PR1025 PR1225	JX1020 CY9020 JP4020 JP4120 PN08M PN215	GC1025 GC1030 GC1130	KC522M			IC807 IC808 IC903 IC907 IC908		TM1 DT4 DM4 ZM3
		M20	**ACM300 ACU2500 ACP300**	MP7130 MP9120 MP9130 UP20M VP15TF VP20RT	AH120 AH130 AH725 AH3135 AH6030	PR1025 PR1225 PR1525	JP4120 JS1025 JX1015 CY150 CY15		KC730M KC525M	F25M F30M T350M	WSM35 WSM35S WXM35	IC330 IC808 IC830 IC840 IC882 IC908 IC928	TT9080 TT9030	DT4 DM4 ZM3
		M30	**ACM300**	MP7130 MP7140 MP9130 VP15TF	AH130 AH140 AH330 AH725 AH3135	PR1525 PR1535	JX045 JM4160 PTH30E	GC2030 GC1040	KC725M KC7140 KCU40	F30M F40M MM4500	WSM35 WSM35S WXM35	IC328 IC330 IC830 IC840 IC882	TT8020 TT8080 TT9080	DT4 DM4 ZM3
		M40	**ACM300**	MP7140 VP15TF VP30RT	AH140	PR1535	GX30 JM4160 PTH40H					IC830 IC928	TT8020 TT8080	
	K	K05	**ACK3000**		AH110		TH303 TH308 ATH80D							
		K10	**ACK3000 ACU2500**		AH110 AH120	PR905 PR1210						IC810	TT6080 TT7080	
		K20	**ACK3000 ACU2500 ACK300**	VP20RT VP15TF	AH120 AH9030	PR905 PR1210 PR1510	JP4020 JP4120 PTH13S	K15W K20D K20W		MK3000 T150M	WKK25	IC808 IC810 IC830	TT6080 TT7515	DM4
		K30	**ACK3000 ACU2500 ACK300**	VP15TF VP20RT	AH725 AH110 AH120 AH330 GH110 GH130	PR1510 PR1210	JS4045 JX1045 CY150 CY250	GC1010 GC1020 GC1025 GC1030 GC1130	KC510M KC520M KC525M KCU40	MK2050 MH1000		IC830 IC810 IC908 IC910 IC928 IC950	TT6080	

Cermet

Application	Class		Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Mitsubishi-Hitachi	Sandvik	Kennametal	Dijet	Valenite	SECO Tools Japan	WALTER	ISCAR
Turning	P	P10	**T1500Z* T1000A T1500A**	AP25N* NX2525 NX3035 VP25N*	GT720* GT9530* J9530* NS520	TN30 PV30* TN60 TN6010 TN610 PV710 PV7005* PV7010*	CZ25* CH550	CT5015	KT125 HTX KT1120	LN10 CX50	VC605			IC20N IC30N IC520N
		P20	**T1500Z* T3000Z* T1500A T2500A**	AP25N* NX2525 NX3035 MP3025*	NS530 GT530* NS730 AT9530* NS9530 GT9530* GT730*	TN60 TN6020 TN620 PV60* TN90 PV7020* PV7025* PV720	CZ25* CH550	GC1525*	KT6215 KT315* KT175 KT5020*	CX50 CX75	VC610	CM CMP C15M TP1020		IC20N IC30N IC520N IC530N
		P30	**T2500A T3000Z***	MX2525 MP3025* VP45N	NS9530 GT9530* AT9530*	TN620 PV7025* PV90* PV720				CX90 CX99				
	K	K10	**T1000A**	AP25N* VP25N* NX2525	GT720* GT9530* NS9530 J9530* NS520	TN30 PV30* TN610 TN6010 PV710 PV7005* PV7010*	CH550	CT5015	KT125 HTX	LN10 CX50	VC605			
Milling	P	P30	**T2500A T250A T4500A**	NX2525 MX3030 NX4545 VP45N*	NS540 NS740	TN90 TC60M TN100M	MZ1000* MZ2000* MZ3000* CH7030 CH7035	CT530	KT530M* KTPK20*	CX90	VC630	C15M		IC30N

* denotes coated cermet

Uncoated Carbide

Class	Grade	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Hitachi	Sandvik	Kennametal	Dijet	SECO Tools Japan	ISCAR
P	P10	**ST10P**		TH10		WS10	S1P		SRT		
	P20	**ST20E**	UTi20T	KS20		EX35	SMA	K125M	SRT		IC70 IC50M
	P30	**A30 A30N**	UTi20T	KS15F UX30	PW30	EX35 EX40	SM30		DX30		IC54 IC28
	P40	**ST40E**		TX40		EX45	S6		SR30		IC54 IC28
M	M10	**EH510**		TH10		EX35 WA10B	H10A	KU10 K313 K68 KYSM10	UMN	890	IC07 IC08 IC20
	M20	**EH520**	UTi20T	KS20		EX35	H13A	K313 K68	DX25 UMS	HX 883	IC07 IC08 IC20
	M30	**A30 A30N**	UTi20T	UX30			H10F SM30		UMS UM40		IC28
K	K01	**H2 H1**	HTi05T	KS05F		WH01 WH05		KU10 K68 K313 K115M	KG03		IS8
	K10	**H1 EH510**	HTi10	TH10	KW10 GW15	WH10	H13A	KU10 K313 K68 K115M K110M KY3500	KG10 KT9 CR1	890	IC20 IS8
	K20	**G10E EH520**	UTi20T	KS15F KS20	GW25	WH20	H13A	KMF KY3500 KYHS10	KT9 KG20 CR1	890 883 HX	IC20 IS8
	K30	**G10E**	UTi20T			WH30		KY3500	KG30	883	
S	S10 S20	**EH510 EH520**	RT9005 RT9010 MT9015 TF15	TH10 KS05F KS15F KS20	SW05 SW10 SW25 KW10 GW15	WH10	H10A H10F H13A	KU10 K313 K68 KMF K110M K1025 KYHS10	KG10 KG20	HX H25	IC20 IC07 IC08 IC28
Fine-grained Carbide		**A1**		UM		NM25	N6F H10F		FZ20 FB20	883	IC08

Grade Comparision Chart

■ CBN

Class	Grade	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	NGK	Sandvik	Kennametal	Dijet	SECO Tools Japan
K	K01	**NCB100 BNC500 BN7000**	MB710 MB5015	BX930 BX870 BX910	KBN475 KBN60M	B30 B16	CB7525 CB7925	KB1340	JBN795	
	K10	**BN700 BN7000 BN7500**	MB710 MB730 MB5015	BX470 BX480 BX950	KBN65B KBN60M KBN900	B23 B16	CB7925 CB7525		JBN330	CBN200,CBN300 CBN300P,CBN400C
	K20	**BN700 BN7000 BNS800**	MB730 MBS140 BC5030	BX470 BX480 BXC90 BX90S	KBN900					
	K30	**BNS800**	MBS140	BX90S BXC90				KB5630		CBN500
S	S01	**NCB100 BN700 BN7000**	MB730 MB4020 MB4120	BX950 BX470 BX480				KB5630 KB1340		
H	H01	**BNC2010 BNC100 BN1000 BN2000 BNX10**	BC8105 BC8110 MBC010 MB810 MB8110	BXM10 BX310	KBN05M KBN25M KBN510	B5K B52		KB5610		CH0550 CBN10 CBN100 CBN60K
	H10	**BNC2010 BNC2020 BNC160 BNC200 BN2000**	BC8110 BC8120 MBC020 MB8025 MB825	BXM10 BX330 BX530	KBN05M KBN25M KBN525	B5K B6K B52 B36	CB7015 CB7115 CB20	KBH20 KB5610 KB5625	JBN300	CBN10,CBN150 CBN100,CBN60K CBN160C
	H20	**BNC2020 BNC200 BNX20**	BC8120 BC8020 MBC020 MB825	BXA20 BXM20 BX360	KBN30M KBN35M KBN900	B36 B40 B6K	CB7025 CB7125 CB50	KBH20 KB5625 KB5630	JBN245	CH2540 CBN150 CBN160C
	H30	**BNC300 BN350 BNX25**	MB835 MB8130 BC8130	BXM20 BXA20 BXC50 BX380	KBN30M KBN35M KBN900	B40	CB7525 CB7135	KB5630		CH3515

■ PCD

Class	Grade	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Sandvik	Kennametal	Dijet	SECO Tools Japan
N	N01	**DA90 DA1000**	MD205	DX180 DX160	KPD001	CD05 CD10	KD1400	JDA30 JDA735	
	N10	**DA150 DA1000**	MD205 MD220	DX140	KPD001 KPD010 KPD230	CD1810	KD1400 KD1425		PCD05 PCD10
	N20	**DA1000 DA2200**	MD220 MD230	DX120 DX110	KPD230		KD1400 KD1425	JDA10 JDA715	PCD05 PCD20
	N30	**DA1000 DA2200**	MD2030 MD230	DX110			KD1400		PCD05 PCD30 PCD30M

Indexable Inserts for Turning
Negative / Positive Inserts

C1–C94



Stock marking chart

- ● : Euro stock item
- ○ : Japan stock item
- ▲ : To be replaced by new item

[—] : We cannot produce

Note:
Stocking policy may change without prior notice, please consult our sales representative for actual stock situation.

Inserts Identification Table

C N M G

① **Insert Shape** — Chart 1

② **Relief Angle** — Chart 2

③ **Tolerance** — Chart 3

④ **Insert Type** — Chart 4

Chart 1: Insert Shape

Symbol	Insert Shape		Angle
C		Diamond	80°
D			55°
E			75°
F			50°
V			35°
R		Round	—
S		Square	90°
T		Triangle	60°
W		Trigon	80°
A		Parallelogram	85°
B			82°
K			55°
H		Hexagonal	120°
O		Octogonal	135°
P		Pentagonal	108°
L		Rectangular	90°
M		Rhombic	86°

Chart 2: Relief Angle

Symbol	Relief Angle
A	3°
B	5°
C	7°
D	15°
E	20°
F	25°
G	30°
N	0°
P*	11°
O	Others

* Inserts with a 10° relief angle are sometimes considered as "P"

Chart 3: Tolerance (mm)

Symbol	Nose Height	Inscribed Circle	Thickness
A	± 0,005	± 0,025	± 0,025
F	± 0,005	± 0,013	± 0,025
C	± 0,013	± 0,025	± 0,025
H	± 0,013	± 0,013	± 0,025
E	± 0,025	± 0,025	± 0,025
G	± 0,025	± 0,025	± 0,13
J*	± 0,005	±0,05 – ±0,15	± 0,025
K*	± 0,013	±0,05 – ±0,15	± 0,025
L*	± 0,025	±0,05 – ±0,15	± 0,025
M*	±0,08 – ±0,2	±0,05 – ±0,15	± 0,13
N*	±0,08 – ±0,2	±0,05 – ±0,15	± 0,025
U*	±0,13 – ±0,38	±0,08 – ±0,25	± 0,13



The height "m" on sharp corner.

Chart 4: Insert Hole or Breaker

Symbol	Hole	Hole Style	Chip Breaker	Shape	Symbol	Hole	Hole Style	Chip Breaker	Shape
N	No Hole	—	Nil		A	With Hole	Straight Hole	Nil	
R			One Face		M			One Face	
F			Both Faces		**G**			Both Faces	
W	With Hole	Straight hole with top end counter-sink (40°–60°)	Nil		B	With Hole	Straight hole with top end counter-sink (70°–90°)	Nil	
T			One Face		H			One Face	
Q	With Hole	Straight hole with top end counter-sink (40°–60°)	Nil		C	With Hole	Straight hole with top end counter-sink (70°–90°)	Nil	
U			Both Faces		J			Both Faces	
					X	—	—	—	Special

● Tolerance of Nose Height (M-Class)

Inscribed Circle	Triangle	Square	80° Diamond	55° Diamond	35° Diamond	Round
6,35	± 0,08	± 0,08	± 0,08	± 0,11	—	—
9,525	± 0,08	± 0,08	± 0,08	± 0,11	± 0,16	
12,70	± 0,13	± 0,13	± 0,13	± 0,15		
15,875	± 0,15	± 0,15	± 0,15	± 0,18		
19,05	± 0,15	± 0,15	± 0,15	± 0,18		
25,40	± 0,18	± 0,18	± 0,18			
31,75	—	± 0,20				

● Tolerance of Inscribed Circle (M-Class)

Inscribed Circle	Triangle	Square	80° Diamond	55° Diamond	35° Diamond	Round
6,35	± 0,05	± 0,05	± 0,05	± 0,05	—	—
9,525	± 0,05	± 0,05	± 0,05	± 0,05	± 0,05	± 0,05
12,70	± 0,08	± 0,08	± 0,08	± 0,08	—	± 0,08
15,875	± 0,10	± 0,10	± 0,10	± 0,10	—	± 0,10
19,05	± 0,10	± 0,10	± 0,10	± 0,10	—	± 0,10
25,40	± 0,13	± 0,13	± 0,13	—	—	± 0,10
31,75	—	± 0,15	—	—	—	± 0,12

Inserts Identification Table

12 04 08 N - GE

⑤ **Insert Size** — Chart 5

⑥ **Thickness** — Chart 6

⑦ **Corner Radius** — Chart 7

⑧ **Feed Direction** — Chart 8

⑨ **Chip Breaker** — Chart 9

Picture of insert shown as example
(ISO Cat, No,)

Chart 5: Cutting Edge Length (mm)

Shape	Symbol	Cutting Edge	Inscribed Circle	Shape	Symbol	Cutting Edge	Inscribed Circle	Shape	Symbol	Cutting Edge	Inscribed Circle
C	03	3,55	3,50	D	07	7,7	6,35	W	03	3,8	5,56
	04	4,97	4,30		09	9,7	7,94		04	4,3	6,35
	06	6,4	6,35		11	11,6	9,525		05	5,4	7,94
	08	8,0	7,94		15	15,5	12,70		06	6,5	9,525
	09	9,7	9,525		19	19,4	15,875		08	8,7	12,70
	12	12,9	12,70						10	10,9	15,875
	16	16,1	15,875	V	08	8,3	4,76				
	19	19,3	19,05		09	9,7	5,56				
	25	25,8	25,4		11	11,1	6,35	R	08	8,0	8,0
					16	16,6	9,525		10	10,0	10,0
					22	22,1	12,7		12	12,0	12,0
S	06	6,35	6,35	T	06	6,9	3,97		12	12,70	12,70
	S7	7,14	7,14		08	8,2	4,76		15	15,875	15,875
	07	7,94	7,94		09	9,6	5,56		16	16,0	16,0
	09	9,525	9,525		11	11,0	6,35		19	19,05	19,05
	12	12,70	12,70		13	13,7	7,94		20	20,0	20,0
	15	15,875	15,875		16	16,5	9,525		24	24,0	24,0
	19	19,05	19,05		22	22,0	12,70		25	25,0	25,0
	25	25,40	25,40		27	27,5	15,875		25	25,40	25,40
	31	31,75	31,75		33	33,0	19,05		32	32,0	32,0

Chart 6: Thickness

Symbol	Thickness (mm)
X1	*
01	1,59
02	2,38
T2	2,78
03	3,18
T3	3,97
04	4,76
05	5,56
06	6,35
07	7,94
09	9,52

(*):
CCET03X1 Insert thickness: 1,40
CCET04X1 Insert thickness: 1,80

Chart 7: Nose Radius

Symbol	Nose Radius (mm)
00	Sharp Point
003	0,03
008	0,08
01	0,1
015	0,15
018	0,18
02	0,2
0,35	0,35
04	0,4
08	0,8
10	1,0
12	1,2
16	1,6
20	2,0
24	2,4
32	3,2
M0	Round Insert (Metric)
00	Round Insert (Imperial)

An "M" after the nose radius indicates a negative tolerance
Example:
CCG T09T302 **M** NSI AC520U

Chart 8: Feed Direction

Symbol	Direction
R	Right-hand
L	Left-hand
N	Neutral

Chart 9: Chip Breaker

Symbol	Process	Bumpy Type	Standard	Handed
F	Fine Finishing to Finishing	FA, FL, FE, FB, FC FK, FP		FT, FX, FZ FY, FW
S L	Light Cut	SE, SEW, SI, SC, SF, SP, SU, SX LU, LUW, LB		SD SDW ST
G U	General	**GE**, GU, GUW UG, UP US, UX	GZ UZ	UM
M	Rough	MP, MU, MX, ME	MC	MM HM
H	Heavy	HG, HP, HF	HU HW	

Other Specials	
Wide Chipbreaker	W
For Countersink	C
For Round insert	RD, RP, RX, RH
For Exotic Alloy	EF, EG, EX, EM
For Aluminium	AG, LD, GD,
For Hardened Steel	FV, LV, GH
For Carburized Layer Removal	SV
For Stainless Steel	EF, EG, EM

Negative M Class Chipbreakers for Low Carbon and General Steel Turning

General Features

The high performance NFE type, which ensures stable chip control in a wide range of feed rate, has been added to the chipbreaker series for low carbon steel and general steel turning.
Extensive product lines are available to meet various machining requirements.
A positive insert execution of chipbreaker NFB is also available.

Application Range



NFE Chipbreaker for Finishing

Supports general purpose machining to high speed machining.

The arc-shaped main breaker ensures stable chip control in a wide feed rate range.

The two step chipbreakers enable stable chip control at a low feed rate of f = 0,1 mm/rev.

The sub-breaker controls cutting chips in profiling.



Cross-section of chipbreaker



Performance

Work Material:	Pipe steel (H240LA, 1.0480)
Insert:	CNMG 120408 NFE (AC8025P)
Cutting Conditions:	v_c=200 m/min, f=0,4 mm/rev, a_p=0,2 mm, dry

Excellent chip control under low depth of cut and high feed rate condition



NFE Type (AC8025P)



Conventional

Application Examples

Work Material:	Deep-draw steel (SPHC440)
Facing Insert:	CNMG 120408 NFE (AC8025P)
Cutting Conditions:	v_c = 200 m/min, f = 0,15 mm/rev, a_p = 0,2–0,5 mm, wet

Stable chip curling and breaking in facing of gummy steel.

NFE Type (AC8025P)

Competitor

Work Material:	C53E,1.1210, Ø20-100
Exter. Turning+Facing Ins.:	DNMG 150412 NFE (AC8025P)
Cutting Conditions:	v_c=180m/min, f=0,25mm/rev (radius), 0,45mm/rev (straight section), a_p = 0,3 mm, wet

Stable chip control even at a variable feed rate in shallow cutting.

NFE Type (AC8025P)

Conventional

NFB Chipbreaker for Low Feed Finishing

Supports low feed machining.

Smooth chipbreaker geometry with a high rake reduces cutting resistance.

The variable rake angle in nose radius makes effective strain on chips and improves the breaking performance.

Cross-section of chipbreaker



Application Example

Work Material:	Pipe steel (STKM13C)
Internal Turning Insert:	DNMG 150404 NFB (T3000Z)
Cutting Conditions:	v_c= 352 m/min, f=0,03–0,2 mm/rev a_p= 0,7 mm, Wet

Small chip curling and control



NFB Type (T3000Z)

Competitor

Chipbreaker
NGH Type

General Features

Enables medium roughing of hardened steel in combination with coating and grade AC503U.
Reduces heat generation and enables deep cutting (a_p = 1–3 mm) of hardened steel by using a wide neutral ground chipbreaker (rake angle: 4°) and sharp edge.
Discharges chips smoothly.

Negative Insert for Rough Cutting NGH Type Chipbreaker

Performance



Application Examples

NGH Type Chipbreaker

Only minor wear occured after 40 min cutting

Stable chip forming

Without Chipbreaker

Major wear occured after 20 min cutting

Work Material:	X155CrVMo12-1 (61HRC)
Insert:	TNGG 160404 NGH (AC503U)
Cutting Conditions:	v_c= 50 m/min, f= 0,05 mm/rev, a_p= 3,0 mm, dry

Recommended Cutting Conditions

Application Range	Cutting Speed v_c (m/min)	Feed Rate f (mm/rev)	Depth of Cut a_p (mm)	Recommended Chipbreaker
Finishing	40–100	0,02–0,10	<1	Without chipbreaker
Medium Roughing	20–60	0,02–0,05	1–3	NGH Type

Work Material: Hardened steel (50–62 HRC), X155CrVMo12-1, X40CrVMo5-1, S6-5-2, High-speed powder and high speed steel

Chipbreaker
NEG Type / NEF Type

For Exotic Alloys and Stainless Steel Turning

■ General Features

NEG/NEF type chipbreaker for exotic alloy machining can be used for Titanium alloys, heat-resistant alloys and a variety of other exotic alloys.
They deliver excellent wear resistance and superior chip management. These chipbreakers can solve quality problems caused by the unstable tool life and poor chip control provided by conventional chipbreakers for exotic alloys.

■ Application Range



NEG Chipbreaker for Roughing

Provides excellent wear resistance and chip control from general-purpose machining to roughing applications. Reduces damage to insert and eliminates trouble from chips specific to exotic alloys. Also demonstrates very high versatility.

Crater wear advancement is prevented by the round bumps, whilst maintaining excellent control.

The cutting edge maintains the strength slowing the progress of crater wear.



Excellent chip management and wear prevention is delivered by the special rake face design.

Cross Section of Chipbreaker



● Cutting Performance – NEG Type

Heat Resistant Alloy

Chipbreaker type: NEG (AC510U)

Suppresses the chipping of peripheral cutting edge and notch wear. Excellent chip management.

Work Material: Inconel 718

Insert: CNMG120412

Cutting Data:
v_c = 40 m/min
a_p = 2,5 mm
f = 0,2 mm/rev
wet
T_c = 7 min

Conventional tool (S10)



Notch wear / poor chip control

Titanium Alloy

Chipbreaker type: NEG (AC510U)

Suppresses crater wear and flank wear. Excellent chip management.

Work Material: Ti-6Al-4V

Insert: CNMG120412

Cutting Data:
v_c = 65 m/min
a_p = 2,5 mm
f = 0,2 mm/rev
wet
T_c = 8 min

Conventional tool (S10)

Crater wear / flank wear / poor chip control

● Application Example – NEG Type

Inconel 718, machine component



Insert: CNMG120408 NEG (AC520U)
Cutting Data: v_c = 50 m/min, a_p = 1,5 mm, f= 0,3 mm/rev, wet

Pure Titanium (Ti grade 3), machine component



Insert: CNMG120408 NEG (EH510)
Cutting Data: v_c=80–100 m/min, a_p=1,0mm, f=0,25mm/rev, wet

Chipbreaker
NEG Type / NEF Type

■ Material Application Range





NEF Chipbreaker for Finishing

The NEF chipbreaker reduces chip curl diameter in finishing applications.
Provides extremely good chip management not fluctuated by the material in use.

Main chipbreaker that enables good chip control even at low depths of cut.

Sharp edge with 20° rake angle reduces wear.



The grooves on the rake face reduce heat and assist chip flow away from the workpiece.

Cross Section of Chipbreaker



● Cutting Performance – NEF Type

Heat Resistant Alloy

Chipbreaker type: NEF (AC510U)

Improvements in chip control and chip removal management based on small curled chips.

Work Material: Inconel 718

Insert: CNMG120408

Cutting Data:
v_c = 55 m/min
a_p = 0,3 mm
f = 0,15 mm/rev
wet
T_c = 8 min

Conventional tool (S10)	Competitor's product (S10)
	

There is a problem in the length and the diameter of chips.

Titanium Alloy

Chipbreaker type: NEF (AC510U)

Improvements in chip control and chip removal management based on small curled chips.

Work Material: Ti-6Al-4V

Insert: CNMG120408

Cutting Data:
v_c = 80 m/min
a_p = 0,5 mm
f = 0,2 mm/rev
wet
T_c = 25 min

Conventional tool (S10)	Competitor's product (S10)
	

There is a problem in the length and the diameter of chips.

● Application Example – NEF Type

Inconel 718, shaft component



Great improvement in chip management. Keeps workpieces free of damage. It is possible to omit final polishing process.

NEF (AC510U)

Conventional tool

Insert: CNMG120408 NEF (AC510U)
Cutting Data: v_c= 45 m/min, a_p= 0,25 mm, f = 0,1 mm/rev, wet

Duplex stainless steel cover



Improvements in chip management. Suppress damage to finished surface with no entanglement of chips.

NEF (AC510U)

Conventional tool

Insert: CNMG120408 NEF (AC510U)
Cutting Data: v_c= 55 m/min, a_p = 0,3 mm, f = 0,125 mm/rev, wet

■ Application Range





NEM Chipbreaker for Rough Cutting

The NEM chipbreaker achieves excellent fracture and crater resistance and ensures extremely stable machining.



● Reduction of Damage

	Reduction of Boundary Damage		Reduction of Crater Wear	
	Cutting Edge	Boundary Wear Comparison	Cross Section	Crater Wear Comparison
Conventional Geometry				
NEM Type				
	The NEM chipbreaker has no changing points on the cutting edge, so boundary damage is reduced.		The NEM chipbreaker smoothly evacuates chips thanks to its large radius rake face design, so crater wear is reduced.	

● Application Example





Reduces breakage out of the cutting edge and ensures stable machining.

Work Material:	X5CrMo17 12 2
Insert:	SNMG190616NEM (AC6030M)
Cutting Conditions:	v_c = 70 m/min, f = 0,5 mm/rev, a_p = 3,0–8,0 mm, wet





Reduces crater wear and provides long tool life.

Work Material:	X5CrNiS18 10
Insert:	SNMG120408NEM (AC6030M)
Cutting Conditions:	v_c =100 m/min, f = 0,32 mm/rev, a_p = 2,0–2,5 mm, wet

Chipbreaker
NFB Type / NLB Type

■ Application Range



NFB Chipbreaker for Finishing

NLB Chipbreaker for Light Cutting

The NFB type for finishing and the NLB type for light cutting have been added to the chipbreaker series for low carbon and general steel machining in addition to the already present NLU type for finishing and NSU type for light cutting.
The NFB and NLB type chipbreakers improve chip control in finishing of low carbon and general steel.





Cross Section of Chipbreaker





Cross Section of Chipbreaker

● Performance

Chip Control

Achieves stable chip control at small cutting depth and low feed.



NFB Type Chipbreaker (T1500A)

Competitor's Product

Work Material:	Pipe (H240LA), Ø 30 Boring
Insert:	TPMT 110304 NFB (T1500A)
Cutting Conditions:	v_c = 100 m/min, f = 0,12 mm/rev, a_p = 0,1 mm, wet

Comparison of Surface Roughness of Finished Surfaces



NFB Type Chipbreaker (T1500A)



Competitor's Product

Work Material:	Pipe (H240LA), Ø 100 Boring
Insert:	TPMT 110304 NFB (T1500A)
Cutting Conditions:	v_c = 200 m/min, f = 0,07 mm/rev, a_p = 0,1 mm, wet

● Performance

Chip Control ①

Achieves stable chip control in light cutting.


NLB Type Chipbreaker (T1500A)


Competitor's Product

Work Material:	Pipe (H240LA), Ø 30 Boring
Insert:	TPMT 110304 NLB (T1500A)
Cutting Conditions:	v_c = 200 m/min, f = 0,15 mm/rev, a_p = 0,5 mm, wet

Chip Control ②


Doubles the tool life by improving chip control and reducing blemishes on machined surfaces.

NLB Type Chipbreaker (T1500A)

Competitor's Product

Work Material:	Hub (C45)
Insert:	VBMT 160408 NLB (T1500A)
Cutting Conditions:	v_c = 240 m/min, f =0 ,25–0,28 mm/rev, a_p = 0,6 mm, wet

(M)NSI Type

Nose radius with minus tolerance (**M**)

Example: DCGT 11T304**M** NSI

■ Application Range



■ Cutting Performance



Work Material: X5CrNiMo17122
Insert: DCGT11T304M NSI, Cutting Conditions: v_c = 100m/min

■ Application Examples

Inconel 718, machine component external turning



1,5 x higher tool life. Improved chip management.

Insert: DCGT11T302M NSI (AC510U)
Cutting Conditions: v_c = 35 m/min, f = 0,08 mm/rev, a_p = 0,8 mm, wet

X5CrNi1810, Shaft component external turning & facing



Improved chip management. Suppressing cutting edge adhesion to ensure a stable, long tool life.

Insert: DCGT11T304M NSI (AC520U)
Cutting Conditions: v_c = 100 m/min, f = 0,08 mm/rev, a_p = 0,5 mm, wet

– Sharp designed cutting edge with low-cutting force
– Better chip control in wide range DOC for bar feeder machine
– Combination of high rake edge design and G-class precision offers superior cutting performance
– Suitable for medical parts and high precision machining



Chipbreaker Comparison

■ Negative Type

Class	Application	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Mitsub.-Hitachi	Sandvik	Kennametal	SECO Tools	WALTER	ISCAR
P	Fine Finishing	**FA**	FH	TF	GP		QF	FF	FF1		SF
		FL, FB	FS,FY	NS,ZF	XP,XF,VF	FE			FF2	FP5	
	Finishing	**LU, FE**	SA,SY	NM, SS	XQ,CQ,PP	BE	LC	FN		NF3	
		SU	SH	TS,TSF,11	HQ	CE,B,BH	XF,MF	CT	MF2		NF,TF
	Wiper Edge	**LUW**		AFW, FW	WP		WL,WP		W-FF2		
		SEW	SW	ASW, SW	WQ		WF,WMX	FW	W-MF2	NF	WF
	Finishing to Light Cut	**SE, SX**	LP	AS,ZM,27	CJ,XS	AB,CT	PF,KF	LF, 33		MP3,NS6	F3P, TF
	Medium Cut	**GU** □UG□	MA,MV	TM	HS,PS	AH	XM,QM	P,MG	M3		GN, HT
		GE, UX	MH,MP	DM,AM	CS,GS,PQ,PT	AE,AY	PM,SM,KM	MN, MP1		MP5,NM4,NM6	RF, LF
	Wiper Edge	**GUW**	MW				WM	MW, RW	W-M3	NM	WG
	Roughing	**MU, ME**	GH, RP	TH, S	HT,GT,PH	RE,AR	PR,XMR,KR	RP	M5,MR7	NM7,NM9,RP5	M3P,NR
		MX	HAS,MT	CH				RN	MR6		
	Heavy Cut	**HG**	HA,HZ,HX,HBS	THS,TRS	PX,HX	TE,UE	QR	RM,MR	R4,R5,R6	NR6,NRF	NM
		HP	HH,HXD	65			HR,SR	RH	R7	NR8	TNM
		HU, HW	HV			H					
		HF	HCS	TUS		HX,HE	MR		RR9	NRR	R3P
M	Finishing	**SU, EF**	LM,SH	SS	MQ,GU	SE,MP	MF	FP,FS,LF	MF2	NF4	
	Light to Medium Cut	**EX, EG**	GM,MS	SF,SA	MS, MU	PV	23	MS	MF1,M1		TF,VL
		GU	MM	SM	HU	DE	MM, SMR	MP	MF3,M3	NM4	M3M,PP
	Roughing	**HM**	ES,1M,2M	S					MF4, MF5	NR4, RM5	
		EM, MU	GH,RM	SH	TK		MR, MRR		M5,MR3		MR
S	Finishing	**EF**	LS,FJ	HRF			SF, SGF			NFT	
	Medium Cut	**EG, EX**	MJ,MS	HMM,SA			SM, SMC			NMT	
	Roughing	**MU**	GJ,RS				SMR			NRT	
K	Light Cut	**UZ**	LK,MA,MK,SW	CM,CF	Standard	V,VA	KF	UN	M5	NM5	GN
	Medium Cut	**GZ** □UX□	GH,Standard	Standard,CH,33	ZS,GC	Y,RE	KM,KR		MR7	RK5, RK7	
H	Finishing	FV, GH									
	Light Cut	LV									
	Carburized Layer Removal	SV									

■ Positive Type

Class	Application	Sumitomo Electric	Mitsubishi	Tungaloy	Kyocera	Mitsub.-Hitachi	Sandvik	Kennametal	SECO Tools	WALTER	ISCAR
P	Finishing	**FC**	FJ,AM	01, JRP,JTS	CF,GF,VF		UM		GT-F1	FM4	
		FB, LU □FP, FK□	FP,FM,FV,SQ	PSF,PF,23	GP,XP,MQ,PP	JQ,MP	PF,UF,MF,KF	11,UF,FP	FF1	PF4	PF
	Wiper Edge	**LUW**	SW				WF	FW	W-F1	PF	WF
M		**SDW**					WK,WM	MW	W-F2		WG
	Finishing to Light Cut	**SI**	SMG	JS	CK						
K	Light Cut	**LB, SU** (SK, SF□	LP,LM,SV,MQ	PSS,PS,24	HQ,XQ,GK	JE	PM,UM,MM,PM	LF	F1	MP4,MM4,FK6	SM,14
		SC			GQ,SK			MP	MF2		
	Medium Cut	**MU**	MV,MM,MK	PM			PR,UR,MR,KR	MF	F2,M3,M5	PM5,RP4,RM4	19
N	Finishing	**AG**	AZ	AL,PP	AH		AL	HP	AL	PM2	AS,AF
	Finishing to Light Cut	**LD, GD**									
H	Finishing	**FV**									
	Light Cut	**LV**									

Chipbreaker Application

Bumpy Breaker | Standard Breaker | Handed Breaker
Break Master (CBN/PCD) | For Chamfering

Negative Type — Finishing to Medium Cutting



Fine Finishing

N-FB — P M K N S H
Better chipcontrol under low feed conditions with sharp edge shape.
0,80 | 27° | α= 0° | CNMG1204○○NFB
C D R S T V W

N-FA — P M K N S H
Profile breaker perfect for fine finishing
1,0 | 20° | α= 0° | CNMG1204○○NFA
C D R S T V W

N-FL — P M K N S H
Optimal breaker for chip management on iron sheeting
1,0 | 10° | α= 0° | CNMG1204○○NFL
C D R S T V W

N-FE — P M K N S H
Good chipcontrol from low to high feed rate
1,40 | 0,70 | 20° | α= 0° | CNMG1204○○NFE
C D R S T V W

Finishing

N-LU — P M K N S H
Effective chip management for fluctuating cut depths and copying
1,5 | 1,0 | 10° | α= 0° | CNMG1204○○NLU
C D R S T V W

N-SP — P M K N S H
Shows excellent cutting performance in finishing to light cutting
1,3 | 13° | α= 0° | CNMG1204○○NSP
C D R S T V W

N-SU — P M K N S H
Effective in high-speed fine finishing
1,3 | 13° | α= 0° | CNMG1204○○NSU
C D R S T V W

N-SE — P M K N S H
Finishing breaker reduces tool wear on rake face. Effective even for high efficiency machining.
0,1 | 1,5 | 17° | 5° | α= 0° | CNMG1204○○NSE
C D R S T V W

N-EF — P M K N S H
Chipbreaker for exotic alloy finishing with excellent chip management
1,2 | 20° | α= 0° | CNMG1204○○NEF
C D R S T V W

NLU-W — P M K N S H
High performance finishing breaker with wiper edge
Wiper
1,5 | 1,0 | 10° | α= 0° | CNMG1204○○NLUW
C D R S T V W

NSE-W — P M K N S H
New high feed finishing breaker with wiper edge
Wiper
0,13 | 1,9 | 17° | 5° | α= 0° | CNMG1204○○NSEW
C D R S T V W

L/R-FX — P M K N S H
Parallel breaker with superior sharp edge
1,5 | 14° | α= 0° | TNGG1604○○L/RFX
C D R S T V W

L/R-FY — P M K N S H
Wide type breaker with sharp edge
2,5 | 15° | α= 0° | TNGG1604○○L/RFY
C D R S T V W

L/R-FT — P M K N S H
Arc-shaped ground type finishing breaker
0,15 | 1,35 | α= 0° | TNGG1103○○L/RFT
C D R S T V W

Light to Medium

N-SJ — P M K N S H
Standard breaker with excellent cutting edge strength
0,18 | 1,2 | α= 0° | SNMG1204○○NSJ
C D R S T V W

L/R-ST — P M K N S H
Arc-shaped ground type breaker for light cutting
0,15 | 1,65 | α= 0° | TNGG1603○○L/RST
C D R S T V W

N-EX — P M K N S H
Standard breaker designed especially for use with exotic alloys
2,0 | 16° | α= 0° | CNMG1204○○NEX
C D R S T V W

N-UP — P M K N S H
Double positive edge for optimal stainless steel cutting
2,1 | 10° | α= 0° | CNMG1204○○NUP
C D R S T V W

N-SX — P M K N S H
Perform copying and raise steps
1,35 | 0,2 | 15° | 3° | α= 0° | CNMG1204○○NSX
C D R S T V W

Chipbreaker Application Range (Insert IC up to Ø 12,7 mm)



Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

Chipbreaker Application

Negative Type — Medium to Rough Cutting

Medium

N-GU — P M K N S H
Features low cutting resistance and excellent wear resistance


α= 0° — CNMG1204○○NGU
C D R S T V W

N-GE — P M K N S H
A versatile breaker with excellent rake surface wear in high efficiency cutting


α= 0° — CNMG1204○○NGE
C D R S T V W

N-UX — P M K N S H
Extremely reliable and versatile breaker with strong cutting edge


α= 0° — CNMG1204○○NUX
C D R S T V W

N-UG — P M K N S H
Popular and versatile breaker


α= 0° — CNMG1204○○NUG
C D R S T V W

N-EG — P M K N S H
General-purpose chipbreaker for exotic alloys with good chip control and wear resistance


α= 0° — CNMG1204○○NEG
C D R S T V W

NGU-W — P M K N S H
Finishing breaker with wiper edge for high efficiency medium finishing


Wiper
α= 0° — CNMG1204○○NGUW
C D R S T V W

L/R-UM — P M K N S H
General-purpose ground type medium cutting breaker


α= 0° — SNMG1204○○L/RUM
C D R S T V W

Medium to Rough

N-EM — P M K N S H
Achieves excellent fracture and crater resistance


α= 0° — CNMG1204○○NEM
C D R S T V W

N-MU — P M K N S H
Economical, double-sided breaker with low cutting resistance for high feed cutting


α= 0° — CNMG1204○○NMU
C D R S T V W

N-ME — P M K N S H
Chipbreaker for rough cutting that supports high-feed cutting with reduced rake face wear


α= 0° — CNMG1204○○NME
C D R S T V W

N-MX — P M K N S H
Strong cutting edge for interrupted cutting


α= 0° — CNMG1204○○NMX
C D R S T V W

N-UZ — P M K N S H
Standard breaker with stable cutting performance


α= 0° — CNMG1204○○NUZ
C D R S T V W

N-GZ — P M K N S H
Extremely reliable standard breaker with strong cutting edge


α= 0° — CNMG1204○○NGZ
C D R S T V W

L/R-HM — P M K N S H
Wide, M class, handed breaker with low cutting resistance for medium to rough cutting.


α= 0° — TNMG1604○○L/RHM
C D R S T V W

Chipbreaker Application Range (Insert IC up to Ø 12,7 mm)



Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

Chipbreaker Application

Bumpy Breaker | Standard Breaker | Handed Breaker
SUMIBORON Break Master | For Chamfering

Negative Type — Rough Cutting

Rough to Heavy

N-HG — P M K N S H
Excellent chip management for heavy cutting
0,4 | 22° | α= 0° | CNMM1606○○NHG
C D R S T W

N-MP — P M K N S H
Single-sided breaker with low cutting resistance for rough cutting
0,3 | 22° | α= 0° | CNMM1606○○NMP
C D R S T W

N-HP — P M K N S H
Strongest cutting edge for heavy cutting
0,3~0,6 | 22° | α= 0° | CNMM1606○○NHP
C D R S T W

N-HU — P M K N S H
Strong edges and excellent chip management for heavy cutting
3,2 | 0,6 | 0,25 | -15° | 16° | α= 0° | SNMM2507○○NHU
C D R S T W

N-HW — P M K N S H
Two step breaker with excellent chip evacuation for heavy cutting
6,3 | 0,3 | 0,75 | 17° | -15° | α= 0° | SNMM3109○○NHW
C D R S T W

N-HF — P M K N S H
Strong edge chipbreaker for heavy cutting with excellent chip evacuation even in high-feed cutting
4,5 | 0,2 | 0,4 | 20° | 15° | α= 0° | SNMM1906○○NHF
C D R S T W

Negative Type — For Hardened Steel

Finishing

N-GH — P M K N S H
For cutting hardened steel with low cutting force and excellent chip control
3,5 | 3° | α= 0° | CNGG1204○○NGH
C D R S T W

Chipbreaker Application Range

Rough to Heavy (IC Ø15,875 to 19,05 mm)



Rough to Heavy (IC Ø25,4 mm)



Rough to Heavy (IC Ø31 mm)



Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

Bumpy Breaker | Standard Breaker | Handed Breaker | Break Master (CBN/PCD)

Positive Type — Medium to Rough Cutting

Finish to Light

N-FB — P M K N S H
Finishing chipbreaker for soft steel providing excellent chip control and surface finish quality
0,5 | 20°
α= 5° 7° 11° | CCMT09T3○○NFB
C D R S T V W

N-LU — P M K N S H
Chip management significantly improved in fine finishing
0,8 | 15°
α= 5° 7° 11° | CCMT09T3○○NLU
C D R S T V W

NLU-W — P M K N S H
High performance finishing breaker with wiper edge
Wiper
1,5 | 10°
α= 7° 11° | CCMT09T3○○NLUW
C D R S T V W

N-FP — P M K N S H
Provides good chip control in fine finishing
1,40 | 10°
α= 7° | CCMT09T3○○NFP
C D R S T V W

N-FK — P M K N S H
Finishing breaker with sharp edge and good chip control
1,1
α= 11° | TPMT1604○○NFK
C D R S T V W

Light to Medium

N-LB — P M K N S H
Light-cutting breaker with sharp edge and good chip control
0,8 | 15°
α= 5° 7° 11° | CCMT09T3○○NLB
C D R S T V W

N-SU — P M K N S H
General-purpose breaker with sharp edge
1,45 | 8°
α= 7° 11° | TPMT1103○○NSU
C D R S T V W

N-US — P M K N S H
Breaker for small diameter boring bars
1,95 | 10°
α= 11° | CPMH0903○○NSU
C D R S

N-MU — P M K N S H
Long lifetime breaker with low cutting resistance
0,35 | 0,1 | 1,8 | 4° | 20°
α= 7° 11° | TPMT1604○○NMU
C D R S T

N-SF — P M K N S H
Very reliable breaker with sharp edge
0,2 | 1,6 | 14°
α= 11° | TPMT1604○○NSF
C D R S T

Positive Type — G Class with Ground Chipbreaker

Finish to Light

L/R-FW — P M K N S H
Wide dimple breaker with sharp edge
0,90 | 15° (20°)
α= 5° 11° | TPMT1102○○L/RFW
C D R S T V W

L/R-FX — P M K N S H
Parallel breaker with sharp edge
0,9 | 15°
α= 5° 7° 11° | TPGT1103○○L/RFX
C D R S T V W

L/R-FY — P M K N S H
Wide breaker with sharp edge
1,5 | 15°
α= 5° 7° 11° | TPGT1103○○L/RFY
C D R S T V W

L/R-FYS — P M K N S H
Breaker for fine cutting with sharp edge
0,5 | 15°
α= 5° 7° | CCGT04X1○○L/RFYS
C D R S T V W

L/R-W — P M K N S H
Wide type finishing breaker
0,15 | 1,0 | 10°
α= 5° 11° | TPGR1103○○L/RW
C D R S T V W

L/R-SD — P M K N S H
Stepped parallel ground type
0,9
α= 7° 11° | TPGT1103○○L/RNSD
C D R S T V W

L/R-SDW — P M K N S H
Parallel ground type with high performance wiper edge
Wiper
0,9
α= 11° | TPGX1103○○L/RSDW
C D R S T V W

Chipbreaker Application Range

M Class Finishing to Light Cutting



M Class Light to Medium Cutting



G Class with Ground Chipbreaker



Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

Chipbreaker Application

Bumpy Breaker | Standard Breaker | Handed Breaker | SUMIBORON Break Master

Positive Type — G Class

Finish to Light

N-FC* — P M K N S H

Peripheral grinding 3D breaker with good chip control and sharp edge



α= 7° 11°

CCGT09T3○○NFC

C D R S T V W

N-SI* — P M K N S H

Sharper-edge breaker for a wide range of cutting applications from finishing to light cutting



α= 7°

CCGT09T3○○NSI

C D R S T V W

N-SC* — P M K N S H

Two step breaker for light cutting



α= 7°

TCGT1103○○NSC

C D R S T V W

* Remarks:
N-FC, N-SI and N-SC have minus tolerance indicated by "M" after the nose radius.
Example:
DCGT 11T302 **M** NSI AC520U

Positive Type — Round Inserts

Round

N-RX — P M K N S H

Round, bumpy type insert with excellent chip management



α= 7°

RCMX1606MON-RX

C D R S T V W

N-RP — P M K N S H

Standard breaker for copying



α= 7°

RCMX1606MON-RP

C D R S T V W

Positive Type — For Al - Alloy Machining

Finishing

N-AG — P M K N S H

Al breaker for mirror finish and anti-adhesion



α= 7°

CCGT09T3○○NAG

C D R S T V W

Chipbreaker Application Range

G Class Chipbreakers



Round Insers (IC up to Ø 12,7 mm)



For Aluminium Alloy Machining



Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

Bumpy Breaker | Standard Breaker | Handed Breaker

SUMIBORON Insert — CBN

Finish to Light

N-LV

P M K N S H

Significantly improved chip control during hardened steel finishing



Break Master

α= 0° 7°

C D R S T V W

N-FV

P M K N S H

Significantly improved chip control during hardened steel finishing



Break Master

α= 0° 7°

C D R S T V W

Carburized Layer Removal

N-SV

P M K N S H

Significantly improved chip management with carburized layer removal



Break Master

α= 0°

C D R S T V W

SUMIDIA Insert — PCD

Finish to Light

N-LD

P M K N S H

Ideal for finishing of Al by utilizing a special cutting edge shape



Break Master

α= 7° 11°

NF-CCMT0602○○NLD

C D R S T V W

N-GD

P M K N S H

Ideal for finishing to general machining of Al by utilizing a special cutting edge shape



Break Master

α= 7° 11°

NF-CCMT0602○○NGD

C D R S T V W

L/R-DM

P M K N S H

Perfect for highspeed finishing of aluminium alloy



Break Master

α= 7° 11°

NU-CCMT09T3○○L/R-DM

C D R S T V W

Chipbreaker Application Range

SUMIBORON (Heavy Steel Machining) (IC up to Ø 12,7 mm)



SUMIBORON (Carburized Layer Removal) (IC up to Ø 12,7 mm)



SUMIDIA (For Aluminium Alloy Machining)



Indicated chipbreaker application ranges and shapes are representative values only. Actual values may change according to the actual catalogue number. For details, refer to stock pages (from Chapter B onward).

C DIAMOND TYPE
INSERTS FOR TURNING

Negative Inserts

80° Diamond Type	0° Relief With Insert Hole



Dimensions (mm)				
CN_ _	L	IC	S	D_1
0903..	9,7	9,525	3,18	3,81
0904..	9,7	9,525	3,18	3,81
1204..	12,9	12,7	4,76	5,16

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

CNMG ●●●●●● ■-■■

● M-Class, Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated		Cermet Uncoated		Carbide Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Fine Finishing	NFB	CNMG 090304 NFB	0,4									○														○	○		○				
		CNMG 090308 NFB	0,8									○														○	○		○				
		CNMG 090404 NFB	0,4									○														○	○		○				
		CNMG 090408 NFB	0,8									○														○	○		○				
		CNMG 120402 NFB	0,2									○														○	○	○	○				
		CNMG 120404 NFB	0,4									○														○	○	○	○				
		CNMG 120408 NFB	0,8									○														○	○	○	○				
Fine Finishing	NFA	CNMG 120402 NFA	0,2																							●	●	○	●				
		CNMG 120404 NFA	0,4																							●	○	○	●				
		CNMG 120408 NFA	0,8																							●	○	○	●				
Fine Finishing	NFL	CNMG 090308 NFL	0,8		○																												
		CNMG 120404 NFL	0,4		○			○					○								○		▲			●	○	○	●				
		CNMG 120408 NFL	0,8		○																○		▲			●	○	○	●				
Fine Finishing	NFE	CNMG 090304 NFE	0,4	○	○		▲		▲		○	○														○	○		○				
		CNMG 090308 NFE	0,8	○	○		▲		▲		○	○														○	○		○				
		CNMG 090404 NFE	0,4	○	○		▲		▲		○	○														○	○		○				
		CNMG 090408 NFE	0,8	○	○		▲		▲		○	○														○	○		○				
		CNMG 120402 NFE	0,2	○	○	○	▲		▲		○	○														○	○	○	○				
		CNMG 120404 NFE	0,4	○	○	○	▲		▲		○	○														○	○	○	○				
		CNMG 120408 NFE	0,8	○	○	○	▲		▲		○	○														○	○	○	○				
		CNMG 120412 NFE	1,2	○	○	○	▲		▲		○	○														○	○	○	○				
Finishing	"Standard" NLU	CNMG 090304 NLU	0,4	○	○		▲	▲			○															○	○		○				
		CNMG 090308 NLU	0,8	○	○		▲	▲			○		○													○	○		○				
		CNMG 120402 NLU	0,2								○		○													○	○	○	○				
		CNMG 120404 NLU	0,4	●	●	○	▲	▲			○		○													●	○	○	○				
		CNMG 120408 NLU	0,8	●	●	○	▲	▲	▲		○		○													●	●	○	○				
		CNMG 120412 NLU	1,2	●	●	○	▲	▲			○															●	○	○					
	"Wiper" W type NLU-W	CNMG 120404 NLU-W	0,4	●	●		▲	▲		●	○		●				▲	▲								●	●						
		CNMG 120408 NLU-W	0,8	●	●		▲	▲		●	○		●				▲	▲								●	○		○				
		CNMG 120412 NLU-W	1,2	●	●		▲	▲			○						▲	▲								○			○				
Finishing	NEF	CNMG 090404 NEF	0,4							○	○	○																					
		CNMG 090408 NEF	0,8							○	○	○																					
		CNMG 120404 NEF	0,4	○	●	○				●	●	●	○							●	●	▲	▲								●	●	
		CNMG 120408 NEF	0,8	○	●	○				●	●	●	○							●	●	▲	▲								○	○	
		CNMG 120412 NEF	1,2	○	●	○				○	●	●									●		▲										

Shape charts: Depth of cut (mm) vs. Feed rate (mm/rev)

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
CN_ _	L	IC	S	D_1
0903..	9,7	9,525	3,18	3,81
0904..	9,7	9,525	3,18	3,81
09T3..	9,7	9,525	3,97	3,81
1204..	12,9	12,7	4,46	5,16
1606..	16,1	15,875	6,35	6,35

⇨ D12, D18 D41 ⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						M			P/M	K			H	S			P/M	Cermet Coated P				Carbide Uncoated K	S	N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NSU	CNMG 090304 NSU	0,4	○	●		▲	▲		●			●																			
		CNMG 090308 NSU	0,8	●	○		▲	▲		●			●																			
		CNMG 09T304 NSU	0,4	○	○																											
		CNMG 09T308 NSU	0,8	○	○																											
		CNMG 090404 NSU	0,4	○	○		▲	▲	▲																○		○	○				
		CNMG 090408 NSU	0,8	○	○		▲		▲																○		○	○				
		CNMG 090412 NSU	1,2	○	○		▲		▲																○		○	○				
		CNMG 120402 NSU	0,2								●	●	○						○		●		▲		○	○	○	○				
		CNMG 120404 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●							●	●	▲	▲	○	●	○	●	●				
		CNMG 120408 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●							●	●	▲	▲	○	●	○	●	●				
		CNMG 120412 NSU	1,2	●	●	○	▲	▲	▲	●	●	●	○							●	●	▲	▲		●	●	○	●				
Finishing	 NSE / NSE-W	CNMG 120404 NSE	0,4	●	●	○	▲	▲	▲																	○		○	○				
		CNMG 120408 NSE	0,8	●	●	○	▲	▲	▲																	○		○	○				
		CNMG 120412 NSE	1,2	●	●	●	▲	▲	▲																								
		CNMG 090404 NSE-W	0,4	○	○		▲		▲																								
		CNMG 090408 NSE-W	0,8	○	○		▲		▲																								
		CNMG 120404 NSE-W	0,4	●	○		▲	▲																				○				
		CNMG 120408 NSE-W	0,8	●	●		▲	▲																	○			○				
		CNMG 120412 NSE-W	1,2	○	●		▲	▲																								
Finishing	 NSX	CNMG 120404 NSX	0,4	○	○	○	▲	▲	▲																	○	○		○				
		CNMG 120408 NSX	0,8	●	●	●	▲	▲	▲																	○			○				
		CNMG 120412 NSX	1,2	●	○	○			▲																								
Medium Cut	 NGU / NGU-W	CNMG 090304 NGU	0,4	○	●			▲	▲					○	○																		
		CNMG 090308 NGU	0,8	○				▲	▲					○	○																		
		CNMG 090404 NGU	0,4		○		▲		▲																	○		○	○				
		CNMG 090408 NGU	0,8		○		▲		▲																	○		○	○				
		CNMG 090412 NGU	1,2	○	○		▲		▲					○	○											○		○	○				
		CNMG 120404 NGU	0,4	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲		○	○			○				
		CNMG 120408 NGU	0,8	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲		○	○			○				
		CNMG 120412 NGU	1,2	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲		○								
		CNMG 120416 NGU	1,6	○	●	●	▲	▲	▲					○	○																		
		CNMG 160608 NGU	0,8	●	●	○	▲	▲	▲	●	○		●	○	○																		
		CNMG 160612 NGU	1,2	●	●	●	▲	▲	▲	●	○		●	○	○																		
		CNMG 160616 NGU	1,6	●	●	○	▲	▲	▲			○	●	○	○																		
		CNMG 120408 NGU-W	0,8	●	●		▲	▲		●			●				▲	▲														
		CNMG 120412 NGU-W	1,2	●	●		▲	▲		●			●				▲	▲														
		CNMG 160612 NGU-W	1,2	○	○	○																										

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 0° Relief / With Insert Hole



Dimensions (mm)				
CN__	L	IC	S	D_1
0903..	9,7	9,525	3,18	3,81
0904..	9,7	9,525	3,18	3,81
09T3..	9,7	9,525	3,97	3,81
1204..	12,9	12,7	4,46	5,16
1606..	16,1	15,875	6,35	6,35
1906..	19,3	19,05	6,35	7,94


⇨ D12, D18 D41


⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K			Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Medium Cut	 NGE	**CNMG 120404 NGE**	0,4	●	●	●	▲	▲	▲																						
		CNMG 120408 NGE	0,8	●	●	●	▲	▲	▲																						
		CNMG 120412 NGE	1,2	●	●	●	▲	▲	▲																						
		CNMG 120416 NGE	1,6	●	●	○	▲	▲																							
		CNMG 160608 NGE	0,8	○	○	○	▲																								
		CNMG 160612 NGE	1,2	●	●	○	▲	▲	▲																						
		CNMG 160616 NGE	1,6	●	●	●	▲	▲	▲																						
		CNMG 190612 NGE	1,2	●	●	○	▲	▲	▲																						
		CNMG 190616 NGE	1,6	○	●	○	▲	▲	▲																						
Medium Cut	 NUG	**CNMG 090304 NUG**	0,4		○			▲																						
		CNMG 090308 NUG	0,8		○				▲																						
		CNMG 090404 NUG	0,4		○																										
		CNMG 090408 NUG	0,8		○			▲	▲																						
		CNMG 09T304 NUG	0,4		○																										
		CNMG 09T308 NUG	0,8		○																										
		CNMG 120404 NUG	0,4	○	●	●		▲	▲																						
		CNMG 120408 NUG	0,8	●	●	●		▲	▲																						
		CNMG 120412 NUG	1,2	●	●	●			▲																						
		CNMG 120416 NUG	1,6		○	●																									
		CNMG 160608 NUG	0,3			○																									
		CNMG 160612 NUG	1,2			○																									
		CNMG 160616 NUG	1,6	○	○	○																									
		CNMG 190608 NUG	0,8			○			▲																						
		CNMG 190612 NUG	1,2		○	●			▲																						
		CNMG 190616 NUG	1,6		○	○																									
		CNMG 190624 NUG	2,4						▲																						
Medium Cut	 NEG	**CNMG 090408 NEG**	0,8							○	○	○																			
		CNMG 090412 NEG	1,2							○	○	○																			
		CNMG 120404 NEG	0,4	○	●	○				●	●	●							○	○										●	
		CNMG 120408 NEG	0,8	○	●	○				●	●	●	●						●	●	▲	▲								●	●
		CNMG 120412 NEG	1,2	○	●	○				●	●	●	○						○	●	▲	▲								○	●
		CNMG 160608 NEG	0,8	○	●	○				○	○	○																			
		CNMG 160612 NEG	1,2	○	●	○				●	●		○						○	●	▲	▲								○	○
		CNMG 160616 NEG	1,6	○	●	○				○									○	○											
		CNMG 190612 NEG	1,2	○	○	○				●	●									○										○	○
		CNMG 190616 NEG	1,6	○	○	○				●	●		○						●	○										○	○
Medium Cut	 NEX	**CNMG 120404 NEX**	0,4							●	●	●	●						●	●	▲	▲		○							
		CNMG 120408 NEX	0,8							●	●	●	●						●	●	▲	▲		○						○	
		CNMG 120412 NEX	1,2							●	●	●	●						●	●	▲	▲									
		CNMG 160612 NEX	1,2																○	●	▲	▲									
		CNMG 190612 NEX	1,2																○	○	▲	▲									

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
CN_ _	L	IC	S	D_1
1204..	12,9	12,7	4,46	5,16
1606..	16,1	15,875	6,35	6,35
1906..	19,3	19,05	6,35	7,94
2509..	25,8	25,4	9,52	9,2


⇨ D12, D18
D41


⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Coated P	Cermet Uncoated P	Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Medium Cut	 NUP	**CNMG 120404 NUP**	0,4		●	●		▲	▲	●	●	●	●							●	●	▲	▲		○					○			
		CNMG 120408 NUP	0,8		●	●		▲	▲	●	●	●	●							●	●	▲	▲		○								
		CNMG 120412 NUP	1,2		●	●		▲	▲	●	●	●	●							○	○	▲	▲		○								
		CNMG 120416 NUP	1,6					▲																									
		CNMG 160612 NUP	1,2			●			▲	●			●																				
		CNMG 190612 NUP	1,2		●	●		▲	▲				●																				
Medium Cut	 NEM	**CNMG 120408 NEM**	0,8	○	●	○				●	●	●									○												
		CNMG 120412 NEM	1,2	○	●	○				●	●	●																					
		CNMG 120416 NEM	1,6	○	●	○				○	●	●																					
		CNMG 160608 NEM	0,8	○	●	○				○	○	○																					
		CNMG 160612 NEM	1,2	○	●	○				●	●	●																					
		CNMG 160616 NEM	1,6	○	●	○				●	●	●																					
		CNMG 190612 NEM	1,2	○	●	○				●	●	●																					
		CNMG 190616 NEM	1,6	○	●	○				●	●	●									○												
		CNMG 190624 NEM	2,4	○	○	○				○		○																					
		CNMG 250924 NEM	2,4	○	○	○					○																						

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 0° Relief / With Insert Hole



Dimensions (mm)				
CN__	L	IC	S	D_1
0903..	9,7	9,525	3,18	3,81
1204..	12,9	12,7	4,76	5,16
1606..	16,1	15,875	6,35	6,35
1906..	19,3	19,05	6,35	7,94


⇨ D12, D18
D41


⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						M			P/M	K			H	S	K/S	M/S	P/M	Cermet Coated P				Carbide Uncoated K	S	N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing	 NMU	**CNMG 120408 NMU**	0,8	●	●	●	▲	▲	▲	●	●		●							●	●	▲	▲		○					○		
		CNMG 120412 NMU	1,2	●	●	●	▲	▲	▲	●	●		●							●	●	▲	▲									
		CNMG 120416 NMU	1,6	●	●	○	▲	▲	▲											○	●	▲	▲									
		CNMG 160608 NMU	0,8	●	●	●	▲	▲	▲	●	●		●																			
		CNMG 160612 NMU	1,2	●	●	●	▲	▲	▲	●	●		●							●	●	▲	▲									
		CNMG 160616 NMU	1,6	●	●	●	▲	▲	▲	●	●		●							●	●	▲	▲									
		CNMG 160624 NMU	2,4					▲																								
		CNMG 190608 NMU	0,8	○		●		▲	▲																							
		CNMG 190612 NMU	1,2	●	●	●	▲	▲	▲	●	●		●							○	●	▲	▲									
		CNMG 190616 NMU	1,6	●	●	●	▲	▲	▲	●	●		●							●	●	▲	▲									
		CNMG 190624 NMU	2,4	○	○	○		▲													○											
		CNMG 250924 NMU	2,4	○	○	●																										
Roughing	 NME	**CNMG 120408 NME**	0,8	●	●	●	▲	▲	▲					○	○																	
		CNMG 120412 NME	1,2	●	●	●	▲	▲	▲					○	○																	
		CNMG 120416 NME	1,6	●	●	○	▲	▲						○	○																	
		CNMG 160608 NME	0,8	○	●	○	▲	▲	▲					○	○																	
		CNMG 160612 NME	1,2	●	●	●	▲	▲	▲					○	○																	
		CNMG 160616 NME	1,6	●	●	○	▲	▲	▲					○	○																	
		CNMG 190612 NME	1,2	○	○	○	▲	▲						○	○																	
		CNMG 190616 NME	1,6	●	●	●	▲	▲	▲					○	○																	
		CNMG 190624 NME	2,4	○	○	○								○	○																	
		CNMG 250924 NME	2,4	○	○	○								○	○																	
Roughing	 NUX	**CNMG 090304 NUX**	0,4						▲																							
		CNMG 120404 NUX	0,4	○	●	●	▲	▲	▲																							
		CNMG 120408 NUX	0,8	●	●	●	▲	▲	▲																							
		CNMG 120412 NUX	1,2	●	●	●	▲	▲	▲																							
		CNMG 120416 NUX	1,6	●	●	○	▲	▲	▲																							
		CNMG 160608 NUX	0,8	●	○	○	▲	▲	▲																							
		CNMG 160612 NUX	1,2	●	●	●	▲	▲	▲							●																
		CNMG 160616 NUX	1,6	●	●	○	▲	▲	▲							●																
		CNMG 190608 NUX	0,8			●			▲																							
		CNMG 190612 NUX	1,2	○	○	○	▲	▲	▲																							
		CNMG 190616 NUX	1,6	○	●	○	▲	▲	▲																							
Roughing	 NMX	**CNMG 120408 NMX**	0,8		●	●		▲	▲																							
		CNMG 120412 NMX	1,2		●	●		▲	▲																							
		CNMG 120416 NMX	1,6		●	●		▲	▲																							
		CNMG 160608 NMX	0,8		●			▲																							
		CNMG 160612 NMX	1,2		●	●		▲	▲																							
		CNMG 160616 NMX	1,6		●	●		▲	▲																							
		CNMG 190612 NMX	1,2		●	●		▲	▲																							
		CNMG 190616 NMX	1,6		●	●		▲	▲																							

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
CN_ _	L	IC	S	D_1
0904..	9,7	9,525	3,18	3,81
1204..	12,9	12,7	4,76	5,16
1606..	16,1	15,875	6,35	6,35
1906..	19,3	19,05	6,35	7,94



- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K				Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P				Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing		**CNMG 090408 NGZ**	0,8											○	○	○	▲	▲														
		CNMG 090412 NGZ	1,2											○	○	○	▲	▲														
		CNMG 120404 NGZ	0,4											●	●	○	▲	▲														
		CNMG 120408 NGZ	0,8											●	●	●	▲	▲														
		CNMG 120412 NGZ	1,2											●	●	●	▲	▲														
		CNMG 120416 NGZ	1,6											●	●	●	▲	▲														
		CNMG 160608 NGZ	0,8											○	○			▲														
		CNMG 160612 NGZ	1,2											○	○	○	▲	▲														
		CNMG 160616 NGZ	1,6											○	●		▲	▲														
		CNMG 190612 NGZ	1,2											○	○		▲	▲														
		CNMG 190616 NGZ	1,6											○	○	○	▲	▲														
Roughing		**CNMG 120404 NUZ**	0,4		○			▲						●	○	○	▲	▲														
		CNMG 120408 NUZ	0,8		○	○		▲						●	●	●	▲	▲												○		
		CNMG 120412 NUZ	1,2		○	○								●	●	●	▲	▲														
		CNMG 120416 NUZ	1,6		○									○	○	●	▲	▲														
		CNMG 160608 NUZ	0,8		○	○												▲														
		CNMG 160612 NUZ	1,2		○	○								●	●	●	▲	▲														
		CNMG 160616 NUZ	1,6		○	○		▲						●	●	●	▲	▲														
		CNMG 190608 NUZ	0,8		○	○		▲	▲																							
		CNMG 190612 NUZ	1,2		○	○								○	○	●	▲	▲														
		CNMG 190616 NUZ	1,6		○	○		▲						○	●	●	▲	▲														

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
CN__	L	IC	S	D_1
1204..	12,9	12,7	4,76	5,16
1606..	16,1	15,875	6,35	6,35
1906..	19,3	19,05	6,35	7,94
2507..	25,8	25,4	7,94	9,2
2509..	25,8	25,4	9,52	9,2



- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						M			P/M	K				H	S	K/S	M/S	P/M	Cermet Coated P				Cermet Uncoated K	S	N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Heavy Roughing	 NMP	**CNMM 120408 NMP**	0,8	●	●	●	▲	▲	▲		●	●	●							○		▲										
		CNMM 120412 NMP	1,2	●	●	●	▲	▲	▲		●		●							○		▲										
		CNMM 120416 NMP	1,6	○	●	●	▲	▲	▲		●		○																			
		CNMM 160608 NMP	0,8		●	●		▲	▲		○		●							○		▲										
		CNMM 160612 NMP	1,2	●	●	●	▲	▲	▲		○		●							○		▲										
		CNMM 160616 NMP	1,6	●	●	●	▲	▲	▲		○		●							○		▲										
		CNMM 160624 NMP	2,4		●			▲																								
		CNMM 190608 NMP	0,8		●	●		▲	▲		○									○		▲										
		CNMM 190612 NMP	1,2	○	●	●		▲	▲		●		●							○		▲										
		CNMM 190616 NMP	1,6	●	●	●	▲	▲	▲		●		●							○		▲										
		CNMM 190624 NMP	2,4	○	●	●	▲	▲	▲		○		○																			
		CNMM 250724 NMP	2,4		○			▲																								
		CNMM 250924 NMP	2,4		○			▲																								
Heavy Roughing	 NMH	**CNMM 160612 NMH**	1,2	●	●	●		▲	▲		●																					
		CNMM 160616 NMH	1,6	●	●	●		▲	▲		●																					
		CNMM 190612 NMH	1,2	●	●	●		▲	▲		●																					
		CNMM 190616 NMH	1,6	●	●	●		▲	▲		●																					
		CNMM 190624 NMH	2,4	●	●	●		▲	▲																							
		CNMM 250924 NMH	2,4		●																											
Heavy Roughing	 NHG	**CNMM 120408 NHG**	0,8	●	●	●	▲	▲	▲				●																			
		CNMM 120412 NHG	1,2	●	●	●	▲	▲	▲				○																			
		CNMM 120416 NHG	1,6		○		▲	▲					●																			
		CNMM 160608 NHG	0,8	●			▲						●																			
		CNMM 160612 NHG	1,2	●	●	●	▲	▲	▲				●																			
		CNMM 160616 NHG	1,6	●	●	●	▲	▲	▲				●																			
		CNMM 160624 NHG	2,4		●			▲																								
		CNMM 190612 NHG	1,2	●	●	●	▲	▲	▲				○																			
		CNMM 190616 NHG	1,6	●	●	●	▲	▲	▲				●																			
		CNMM 190624 NHG	2,4	●	●	●	▲	▲	▲				○																			
Heavy Roughing	 NHP	**CNMM 120408 NHP**	0,8		●	●		▲	▲																							
		CNMM 120412 NHP	1,2		●	●		▲	▲																							
		CNMM 120416 NHP	1,6		○	○																										
		CNMM 160608 NHP	0,8		○	●		▲	▲																							
		CNMM 160612 NHP	1,2		○	●			▲																							
		CNMM 160616 NHP	1,6		●	●		▲	▲																							
		CNMM 190608 NHP	0,8		○	●		▲	▲				○																			
		CNMM 190612 NHP	1,2		●	●		▲	▲				○																			
		CNMM 190616 NHP	1,6		●	●		▲	▲				○																			
		CNMM 190624 NHP	2,4		●	●		▲	▲				○																			

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type — 0° Relief — With Insert Hole



Dimensions (mm)				
CN_ _	L	IC	S	D_1
1906..	19,3	19,05	6,35	7,94
2509..	25,8	25,4	9,52	9,2

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

CNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

Grade groups: Carbide Coated — P: AC8015P, AC8025P, AC8035P, AC810P, AC820P, AC830P; M: AC6020M, AC6030M, AC6040M; P/M: AC630M; K: AC4010K, AC4015K, AC420K, AC405K, AC415K; H: AC503U; S: AC5015S, AC5025S; K/S: AC510U; M/S: AC520U; P/M: AC1030U, AC530U. Cermet (Coated / Uncoated) — P: T1500Z, T3000Z, T1000A, T1500A. Carbide Uncoated — K: G10E; S: EH510, EH520; N: H1.

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Heavy Roughing	NHU	CNMM 190616 NHU	1,6				▲		▲				●																				
Heavy Roughing	NHU	CNMM 190624 NHU	2,4					▲																									
Heavy Roughing	NHU	CNMM 250924 NHU	2,4				▲	▲					●																				
Heavy Roughing	NHW	CNMM 250924 NHW	2,4						▲				●																				
Heavy Roughing	NHF	CNMM 190616 NHF	1,6		○	○		▲	▲																								
Heavy Roughing	NHF	CNMM 190624 NHF	2,4		○	○		▲	▲																								
Heavy Roughing	NHF	CNMM 250924 NHF	2,4		○	○		▲	▲																								
Heavy Roughing	NHF	CNMM 250932 NHF	3,2		○	○		▲	▲																								





● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

80° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
CN__	L	IC	S	D_1
1204..	12,9	12,7	4,76	5,16
1606..	16,1	15,875	6,35	6,35
1906..	19,3	19,05	6,35	7,94


⇨ D12, D18


⇨ E8

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CNMA / CNGA / CNMX

● Flat and One Side Handed Inserts

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K					Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P			Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing		**CNMA 120404**	0,4											○	○	●	▲	▲											●			
		CNMA 120408	0,8											●	●	●	▲	▲											●			
		CNMA 120412	1,2											●	●	●	▲	▲														
		CNMA 120416	1,6											●	●	●	▲	▲														
		CNMA 160608	0,8											○	○			▲														
		CNMA 160612	1,2											○	●	●	▲	▲														
		CNMA 160616	1,6											●	●	●	▲	▲														
		CNMA 190612	1,2											○	●	●	▲	▲														
		CNMA 190616	1,6											○	●	●	▲	▲														
Medium Cut		**CNGA 120402**	0,2																○													
		CNGA 120404	0,4																○													
		CNGA 120408	0,8																○													
Heavy Roughing		**CNMX 120408 L**	0,8		●			▲																								
		**CNMX 120408 R**	0,8		●			▲																								

CNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K					Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P			Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NSU	**CNGG 120402 NSU**	0,2																	○	○					○	○	○	○				
		CNGG 120404 NSU	0,4																	○	○					○	○	○	○				
		CNGG 120408 NSU	0,8																	○	○					○	○	○	○				
Finishing	 NGH	**CNGG 120402 NGH**	0,2																○													
		CNGG 120404 NGH	0,4																○													
		CNGG 120408 NGH	0,8																○													
Finishing	 NEF	**CNGG 120402 NEF**	0,2										○							○										○		
		CNGG 120404 NEF	0,4										○							○										○		
		CNGG 120408 NEF	0,8																														

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
DN_ _	L	IC	S	D_1
1104..	11,6	9,525	4,76	3,81
1504..	15,5	12,7	4,76	5,16
1506..	15,5	12,7	6,35	5,16


⇨ D13, D19 D41


⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P/M	Carbide Coated M	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC630M	AC6020M	AC4010K	AC503U	AC5015S	AC510U	AC520U	AC1030U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				AC8025P	AC6030M	AC6030M	AC4015K	AC420K	AC5025S			AC530U								
				AC8035P	AC6040M	AC6040M		AC405K												
				AC810P				AC415K												
				AC820P																
				AC830P																
Fine Finishing	NFB	DNMG 110404 NFB	0,4										○	○		○				
		DNMG 110408 NFB	0,8										○	○		○				
		DNMG 150404 NFB	0,4										○	○	○	○				
		DNMG 150408 NFB	0,8										○	○	○	○				
		DNMG 150604 NFB	0,4										○	○	○	○				
		DNMG 150608 NFB	0,8										○	○	○	○				
Fine Finishing	NFA	DNMG 150404 NFA	0,4										○	○	○	○				
		DNMG 150408 NFA	0,8										○	○	○	○				
		DNMG 150604 NFA	0,4										●		●	●				
		DNMG 150608 NFA	0,8										●		○	●				
Fine Finishing	NFL	DNMG 150404 NFL	0,4		○		▲						○	○	○	○				
		DNMG 150408 NFL	0,8		○		▲						○	○	○	○				
		DNMG 150412 NFL	1,2		○															
		DNMG 150604 NFL	0,4				▲						●	●						
		DNMG 150608 NFL	0,8				▲						●	●						
Fine Finishing	NFE	DNMG 110404 NFE	0,4	○	○	○	▲		▲				○	○		○				
		DNMG 110408 NFE	0,8	○	○	○	▲		▲				○	○		○				
		DNMG 110412 NFE	1,2	○	○	○	▲		▲				○	○		○				
		DNMG 150402 NFE	0,2	○	○	○	▲		▲				○	○	○	○				
		DNMG 150404 NFE	0,4	○	○	○	▲		▲				○	○	○	○				
		DNMG 150408 NFE	0,8	○	○	○	▲		▲				○	○	○	○				
		DNMG 150412 NFE	1,2	○	○	○	▲		▲				○	○	○	○				
		DNMG 150602 NFE	0,2	○	○	○	▲		▲				○	○	○	○				
		DNMG 150604 NFE	0,4	○	○	○	▲		▲				○	○	○	○				
		DNMG 150608 NFE	0,8	○	○	○	▲		▲				○	○	○	○				
		DNMG 150612 NFE	1,2	○	○	○	▲		▲				○	○	○	○				
Finishing	NLU	DNMG 110404 NLU	0,4	●	●		▲		▲				●			○				
		DNMG 110408 NLU	0,8	●	○		▲		▲				●			○				
		DNMG 150402 NLU	0,2	○	○		▲		▲				○	○	○	○				
		DNMG 150404 NLU	0,4	○	○	○	▲		▲			○	○	○	○	○				
		DNMG 150408 NLU	0,8	○	○	○	▲		▲			○	○	○	○	○				
		DNMG 150412 NLU	1,2	○	○	○	▲		▲			○	○			○				
		DNMG 150604 NLU	0,4	●	●		▲		▲				●							
		DNMG 150608 NLU	0,8	●	●		▲		▲				●							
		DNMG 150612 NLU	1,2	●	●		▲		▲				●							

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

55° Diamond Type

0° Relief
With Insert Hole



Dimensions (mm)				
DN_ _	L	IC	S	D_1
1104..	11,6	9,525	4,76	3,81
1504..	15,5	12,7	4,76	5,16
1506..	15,5	12,7	6,35	5,16

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker











				Carbide																						Cermet				Carbide			
				Coated																						Coated		Uncoated		Uncoated			
				P						M			P/M	K					H	S		K/S	M/S		P/M	P				K	S		N
Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	NEF	DNMG 110404 NEF	0,4	○	●	○				●	●	●									○		▲										
		DNMG 110408 NEF	0,8	○	●	○				●	●	●									○		▲										
		DNMG 110412 NEF	1,2	○	○	○				○	●	●									○		▲										
		DNMG 150404 NEF	0,4	○	○	○				○	○	○	○							○	○	▲	▲								○	○	
		DNMG 150408 NEF	0,8	○	○	○				○	○	○	○							○	○	▲	▲								○	○	
		DNMG 150412 NEF	1,2	○	○	○				○	○										○												
		DNMG 150604 NEF	0,4	○	●	○				●	●	●	○							●	●	▲	▲								○	○	
		DNMG 150608 NEF	0,8	○	●	○				●	●	●	○							●	●	▲	▲								○	○	
		DNMG 150612 NEF	1,2	○	●	○				●	●	○								●													
Finishing	NSU	DNMG 110404 NSU	0,4	●	●	○	▲	▲		●	○		●							●	●	▲	▲										
		DNMG 110408 NSU	0,8	●	●	○	▲	▲	▲	●	○		●							●	●	▲	▲										
		DNMG 110412 NSU	1,2	○	○	○																											
		DNMG 150402 NSU	0,2								○	○	○								○		▲		○	○	○	○	○				
		DNMG 150404 NSU	0,4	○	○	○	▲	▲	▲		○	○	○							○	○		▲		○	○	○	○					
		DNMG 150408 NSU	0,8	○	○	○	▲	▲	▲		○	○	○							○	○	▲	▲		○	○	○	○					
		DNMG 150412 NSU	1,2	○	○			▲			○		○													○	○	○	○				
		DNMG 150604 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●							●	●	▲	▲			●		○	●				
		DNMG 150608 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●							●	●	▲	▲			●		○	●				
		DNMG 150612 NSU	1,2	●	●	●	▲	▲	▲												●		▲			●		●	●				
Finishing	NSE	DNMG 110408 NSE	0,8	●	○	○	▲																										
		DNMG 150404 NSE	0,4	○	○	○	▲	▲	▲																	○		○	○				
		DNMG 150408 NSE	0,8	○	○	○	▲	▲	▲																	○		○	○				
		DNMG 150412 NSE	1,2	○	○	○	▲	▲																		○		○	○				
		DNMG 150604 NSE	0,4	●	●		▲	▲																				○					
		DNMG 150608 NSE	0,8	●	●		▲	▲																				○					
		DNMG 150612 NSE	1,2	●	●		▲	▲																									
Finishing	NSX	DNMG 150404 NSX	0,4	○	○	○	▲	▲																		○	○						
		DNMG 150408 NSX	0,8	○	○	○		▲																		○	○		○				
		DNMG 150412 NSX	1,2	○	○	○			▲																								
		DNMG 150604 NSX	0,4					▲																		○			○				
		DNMG 150608 NSX	0,8	●																						○			○				
Medium Cut	NGU	DNMG 110404 NGU	0,4	●	●	○	▲	▲	▲	●	●		○	○	○																		
		DNMG 110408 NGU	0,8	●	●	●	▲	▲	▲	●	●	○	●	○	○			▲															
		DNMG 110412 NGU	1,2	●	●	○	▲	▲		●			●	○	○			▲															
		DNMG 150404 NGU	0,4	○	○	○	▲	▲	▲	○	○	○	○	○	○						○		▲			○			○				
		DNMG 150408 NGU	0,8	○	○	○	▲	▲	▲	○	○	○	○	○	○								▲		○	○			○				
		DNMG 150412 NGU	1,2	○	○	○	▲	▲		○	○		○	○	○								▲		○	○			○				
		DNMG 150416 NGU	1,6		○									○	○																		
		DNMG 150604 NGU	0,4	●	●	●	▲	▲	▲	●	●	●	●	○	○																		
		DNMG 150608 NGU	0,8	●	●	●	▲	▲	▲	●	●	●	●	○	○																		
		DNMG 150612 NGU	1,2	●	●	○	▲	▲	▲	●	●	○	●	○	○																		
		DNMG 150616 NGU	1,6		○			▲						○	○																		

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

55° Diamond Type

0° Relief
With Insert Hole



Dimensions (mm)				
DN_ _	L	IC	S	D1
1104..	11,6	9,525	4,76	3,81
1504..	15,5	12,7	4,76	5,16
1506..	15,5	12,7	6,35	5,16

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

DNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker









Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated		Cermet Uncoated		Carbide Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Medium Cut	NGE	DNMG 110408 NGE	0,8	○	○	○	▲	▲	▲																								
		DNMG 110412 NGE	1,2	○	○	○																											
		DNMG 150404 NGE	0,4	○	○	○	▲	▲	▲																								
		DNMG 150408 NGE	0,8	○	○	○	▲	▲	▲																								
		DNMG 150412 NGE	1,2	○	○	○			▲																								
		DNMG 150416 NGE	1,6		○																												
		DNMG 150604 NGE	0,4	●	●	○	▲	▲	▲																								
		DNMG 150608 NGE	0,8	●	●	●	▲	▲	▲																								
		DNMG 150612 NGE	1,2	●	●	●	▲	▲	▲																								
		DNMG 150616 NGE	1,6	●	●	○	▲	▲	▲																								
Medium Cut	NUG	DNMG 110404 NUG	0,4		○	●			▲																								
		DNMG 110408 NUG	0,8		○	○			▲																								
		DNMG 150404 NUG	0,4			○																											
		DNMG 150408 NUG	0,8	○	○	○																											
		DNMG 150412 NUG	1,2		○	○																											
		DNMG 150604 NUG	0,4	●	○																												
		DNMG 150608 NUG	0,8	●	●	○		▲	▲																								
		DNMG 150612 NUG	1,2		○				▲																								
		DNMG 150616 NUG	1,6		○				▲																								
Medium Cut	NEG	DNMG 110408 NEG	0,8	○	●	○				●	●	●									○		▲										
		DNMG 110412 NEG	1,2	○	●	○				●	●	●									○		▲										
		DNMG 150404 NEG	0,4	○	○	○				○	○	○								○												○	
		DNMG 150408 NEG	0,8	○	○	○				○	○	○	○							○	○	▲	▲								○	○	
		DNMG 150412 NEG	1,2	○	○	○				○	○	○	○							○	○	▲	▲								○	○	
		DNMG 150604 NEG	0,4	○	●	○				●	●	●	○							○	○										○		
		DNMG 150608 NEG	0,8	○	●	○				●	●	●	●							●	●	▲	▲								○	●	
		DNMG 150612 NEG	1,2	○	●	○				●	●	●	○							●	●	▲	▲								○	○	
Medium Cut	NEX	DNMG 110404 NEX	0,4								●		●							●	●	▲	▲										
		DNMG 110408 NEX	0,8								●		●							●	●	▲	▲										
		DNMG 150404 NEX	0,4							○	○	○								○	○												
		DNMG 150408 NEX	0,8							○	○	○								○	○												
		DNMG 150412 NEX	1,2							○	○									○	○												
		DNMG 150604 NEX	0,4							●	●	●	●							●	●	▲	▲										
		DNMG 150608 NEX	0,8							●	●	●	●							●	●	▲	▲										
		DNMG 150612 NEX	1,2							●	●	○	○							●	●	▲	▲										

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type — 0° Relief — With Insert Hole



DN_ _	L	IC	S	D_1
1504..	15,5	12,7	4,76	5,16
1506..	15,5	12,7	6,35	5,16

Dimensions (mm)

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

DNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated		Cermet Uncoated		Carbide Uncoated			
				P	P	P	P	P	P	M	M	M	P/M	K	K	K	K	K	H	S	S	K/S	M/S	P/M	P/M	P	P	P	P	K	S	S	N
Medium Cut	NUP 	DNMG 150404 NUP	0,4					▲	▲		○	○	○							○	○	▲	▲										
Medium Cut	NUP	DNMG 150408 NUP	0,8					▲	▲		○	○	○							●	○	▲	▲										
Medium Cut	NUP	DNMG 150412 NUP	1,2					▲			○		○							○	○	▲	▲										
Medium Cut	NUP	DNMG 150604 NUP	0,4		●	●		▲	▲	●	●	●	●							●	●	▲	▲										
Medium Cut	NUP	DNMG 150608 NUP	0,8		●	●		▲	▲	●	●	●	●							●	●	▲	▲										
Medium Cut	NUP	DNMG 150612 NUP	1,2			●			▲	●			●							●	●	▲	▲										
Medium Cut	L/RUM 	DNMG 150404 LUM	0,4																							○			○				
Medium Cut	L/RUM	DNMG 150408 LUM	0,8																							○			○				
Medium Cut	L/RUM	DNMG 150404 RUM	0,4																							○			○				
Medium Cut	L/RUM	DNMG 150408 RUM	0,8																							○			○				
Roughing	NMU 	DNMG 150404 NMU	0,4				▲						○																				
Roughing	NMU	DNMG 150408 NMU	0,8	○	○	○	▲	▲	▲		○		○							○	○	▲	▲										
Roughing	NMU	DNMG 150412 NMU	1,2	○	○	○	▲	▲	▲		○									○	○	▲	▲										
Roughing	NMU	DNMG 150416 NMU	1,6		○	○		▲	▲												○		▲										
Roughing	NMU	DNMG 150608 NMU	0,8	●	●	●	▲	▲	▲	●	●		○																				
Roughing	NMU	DNMG 150612 NMU	1,2	●	●	●	▲	▲	▲	●	●		○																				
Roughing	NMU	DNMG 150616 NMU	1,6	●	●		▲	▲		●																							
Roughing	NEM 	DNMG 150408 NEM	0,8	○	○	○				○	○	○																					
Roughing	NEM	DNMG 150412 NEM	1,2	○	○	○				○	○	○																					
Roughing	NEM	DNMG 150416 NEM	1,6		○	○				○	○	○																					
Roughing	NEM	DNMG 150608 NEM	0,8	○	●	○				●	●	●																					
Roughing	NEM	DNMG 150612 NEM	1,2	○	●	○				●	●	●																					
Roughing	NEM	DNMG 150616 NEM	1,6		●																												
Roughing	NME 	DNMG 150408 NME	0,8	○	○	○		▲						○	○																		
Roughing	NME	DNMG 150412 NME	1,2	○	○	○			▲					○	○																		
Roughing	NME	DNMG 150416 NME	1,6		○									○	○																		
Roughing	NME	DNMG 150608 NME	0,8	●	●	●	▲	▲	▲					○	○																		
Roughing	NME	DNMG 150612 NME	1,2	●	●	○	▲	▲	▲					○	○																		
Roughing	NME	DNMG 150616 NME	1,6	●	●	○	▲	▲	▲					○	●																		

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type

0° Relief
With Insert Hole



Dimensions (mm)				
DN_ _	L	IC	S	D_1
1104..	11,6	9,525	4,76	3,81
1504..	15,5	12,7	4,76	5,16
1506..	15,5	12,7	6,35	5,16

P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

DNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide																						Cermet				Carbide			
				Coated																						Coated		Uncoated		Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Roughing	 L/RHM	DNMG 150404 LHM	0,4		○						○																						
		DNMG 150408 LHM	0,8		○						○																						
		DNMG 150404 RHM	0,4	○	○	○		▲	▲		○																						
		DNMG 150408 RHM	0,8	○	○	○	▲	▲	▲		○																						
Roughing	 NUX	DNMG 110408 NUX	0,8	○	○	○			▲																								
		DNMG 150404 NUX	0,4	○	○	○	▲	▲																									
		DNMG 150408 NUX	0,8	○	○	○	▲	▲																									
		DNMG 150412 NUX	1,2	○	○	○	▲	▲																									
		DNMG 150604 NUX	0,4	○	●	○		▲	▲																								
		DNMG 150608 NUX	0,8	●	●	●	▲	▲	▲																								
		DNMG 150612 NUX	1,2	●	●	●	▲	▲	▲																								
		DNMG 150616 NUX	1,6		●			▲																									
Roughing	 NMX	DNMG 150408 NMX	0,8		○	○		▲	▲																								
		DNMG 150412 NMX	1,2		○	○		▲																									
		DNMG 150608 NMX	0,8		●			▲																									
		DNMG 150612 NMX	1,2		●			▲																									
Roughing	 NGZ	DNMG 110408 NGZ	0,8											○	○	●	▲	▲															
		DNMG 110412 NGZ	1,2											○	○	●	▲	▲															
		DNMG 150404 NGZ	0,4											○	○																		
		DNMG 150408 NGZ	0,8					▲						○	○	○		▲															
		DNMG 150412 NGZ	1,2											○	○			▲															
		DNMG 150604 NGZ	0,4															▲															
		DNMG 150608 NGZ	0,8											●	●	●	▲	▲															
		DNMG 150612 NGZ	1,2											○	○	●	▲	▲															
Roughing	 NUZ	DNMG 150404 NUZ	0,4		○									○	○																		
		DNMG 150408 NUZ	0,8		○	○		▲						○	○	○		▲															
		DNMG 150412 NUZ	1,2		○	○								○	○																		
		DNMG 150608 NUZ	0,8		○			▲						○	●	●	▲	▲															
		DNMG 150612 NUZ	1,2		○									○	○	●	▲	▲															

Shape charts: Depth of cut (mm) vs. Feed rate (mm/rev)

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
DN__	L	IC	S	D_1
1504..	15,5	12,7	4,76	5,16
1506..	15,5	12,7	6,35	5,16

⇨ D13, D19 ⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K				Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Heavy Roughing	 NMP	**DNMM 150404 NMP**	0,4		○	○		▲	▲																						
		DNMM 150408 NMP	0,8	○	○	○	▲	▲																							
		DNMM 150412 NMP	1,2	○	○	○	▲	▲	▲																						
		DNMM 150416 NMP	1,6	○	○																										
		DNMM 150604 NMP	0,4		●	●		▲	▲																						
		DNMM 150608 NMP	0,8	●	●	●	▲	▲	▲				●																		
		DNMM 150612 NMP	1,2	●	●	●	▲	▲	▲				●																		
		DNMM 150616 NMP	1,6	○	●	●	▲	▲	▲				●																		
Heavy Roughing	 NHG	**DNMM 150604 NHG**	0,4				▲	▲																							
		DNMM 150608 NHG	0,8	●		●	▲	▲	▲				●																		
		DNMM 150612 NHG	1,2	●	●		▲	▲	▲				●																		
		DNMM 150616 NHG	1,6	●	●		▲	▲	▲				●																		
Heavy Roughing	 NHP	**DNMM 150404 NHP**	0,4		○	○																									
		DNMM 150408 NHP	0,8		○	○																									
		DNMM 150412 NHP	1,2		○	○																									
		DNMM 150416 NHP	1,6		○																										
		DNMM 150604 NHP	0,4		○																										
		DNMM 150608 NHP	0,8		●	○		▲	▲																						
		DNMM 150612 NHP	1,2		○	○		▲	▲																						
		DNMM 150616 NHP	1,6		○				▲																						

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
DN_ _	L	IC	S	D_1
1104..	11,6	9,525	4,76	3,81
1504..	15,5	12,7	4,76	5,16
1506..	15,5	12,7	6,35	5,16


⇨ D13, D19


⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DNMA / DNMX

Flat Inserts and One Side Handed Inserts

●M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated G10E	Carbide Uncoated EH510	EH520	H1
Roughing		**DNMA 150404**	0,4											○	○																	
		DNMA 150408	0,8											○	○	○																
		DNMA 150412	1,2											○	○		▲															
		DNMA 150608	0,8											●	●	●	▲	▲														
		DNMA 150612	1,2											○	○	●	▲	▲														
		**DNMX 150608 L**	0,8					▲																								
		**DNMX 150608 R**	0,8					▲																								
Finishing		**DNMX 110404 NSE-W**	0,4	●	○	○	▲	▲	▲																							
		DNMX 110408 NSE-W	0,8	○	○	○	▲	▲	▲																							
		DNMX 110412 NSE-W	1,2	○	○	○	▲	▲	▲																							
		DNMX 150404 NSE-W	0,4	○	○		▲																			○		○				
		DNMX 150408 NSE-W	0,8	○	○																					○						
		DNMX 150412 NSE-W	1,2	○	○																											
		DNMX 150604 NSE-W	0,4	●	●		▲	▲																								
		DNMX 150608 NSE-W	0,8	●	●		▲	▲																								
		DNMX 150612 NSE-W	1,2	●			▲	▲																								





(Note) The cutting point position of the SDW type does not follow the ISO standard.
Wenn using on a boring holder with a 93° approach angle, there is a need to revise the cutting point position (refer to right table) relative to using standard inserts.

r	Compensation (mm) X (Diam. change)	Z
0,4	-0,14 (Ø : -0,28)	-0,02
0,8	-0,14 (Ø : -0,28)	-0,02
1,2	-0,1 (Ø : -0,2)	-0,03

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type | 0° Relief / With Insert Hole



Dimensions (mm)				
DN__	L	IC	S	D_1
1104..	11,6	9,525	4,76	3,81
1504..	15,5	12,7	4,76	5,16

⇨ D13, D19 ⇨ E9

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DNGA ●●●●●●

● G-Class One Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated: T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated: G10E	EH510	EH520	Carbide Uncoated: H1
Medium Cut		**DNGA 150402**	0,2																○														
		DNGA 150404	0,4																○								○						
		DNGA 150408	0,8																○								○						

DNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated: T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated: G10E	EH510	EH520	Carbide Uncoated: H1
Finishing	 NEF	**DNGG 150404 NEF**	0,4																													○	
		DNGG 150408 NEF	0,8																		○												
Finishing	 NSU	**DNGG 150402 NSU**	0,2																	○	○					○		○	○				
		DNGG 150404 NSU	0,4																	○	○					○	○	○	○				
		DNGG 150408 NSU	0,8																	○	○					○	○	○	○				
Medium Cut	 L/RUM	**DNGG 110404 LUM**	0,4																							○		○	○				
		DNGG 110408 LUM	0,8																							○		○	○				
		DNGG 150404 LUM	0,4																							○		○	○				
		DNGG 150408 LUM	0,8																							○		○	○				
		DNGG 110404 RUM	0,4																							○		○	○	○			
		DNGG 110408 RUM	0,8																							○		○	○				
		DNGG 150404 RUM	0,4																							○		○	○				
		DNGG 150408 RUM	0,8																							○		○	○				
Finishing	 NGH	**DNGG 150402 NGH**	0,2																○														
		DNGG 150404 NGH	0,4																○														
		DNGG 150408 NGH	0,8																○														

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 0° Relief | With Insert Hole



Dimensions (mm)				
SN_ _	L	IC	S	D_1
1204..	12,7	12,7	4,76	5,16


⇨ D14, D20~21
D41


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Coated P	Cermet Coated P	Cermet Coated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Fine Finishing	 NFB	**SNMG 120404 NFB**	0,4									○														○	○	○	○				
		SNMG 120408 NFB	0,8									○														○	○	○	○				
Fine Finishing	 NFL	**SNMG 120408 NFL**	0,8		○			▲																		○	○		○				
Fine Finishing	 NFE	**SNMG 120404 NFE**	0,4	○	○	○	▲		▲		○	○														○	○	○	○				
		SNMG 120408 NFE	0,8	○	○	○	▲		▲		○	○														○	○	○	○				
		SNMG 120412 NFE	1,2	○	○	○	▲		▲		○	○														○	○	○	○				
Finishing	 NLU	**SNMG 120408 NLU**	0,8	○	○		▲	▲			○	○														○	○		○				
		SNMG 120412 NLU	1,2	○	●		▲	▲			○		○													○	○						
Finishing	 NSU	**SNMG 120408 NSU**	0,8	●	●	○	▲	▲	▲	●	●	●	○							●	●	▲	▲			○	○	○	○				
		SNMG 120412 NSU	1,2																		●	▲	▲										
Finishing	 NSE	**SNMG 120408 NSE**	0,8	○	○	○	▲	▲																									
		SNMG 120412 NSE	1,2	●	●	○	▲	▲	▲																								

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

90° Square Type	0° Relief / With Insert Hole



Dimensions (mm)				
SN_ _	L	IC	S	D_1
0903..	9,525	9,525	3,18	3,81
1204..	12,7	12,7	4,76	5,16
1506..	15,875	15,875	6,35	6,35



⇨ D14, D20~21
D41

⇨ E10

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated																						Cermet Coated		Cermet Uncoated		Carbide Uncoated			
				P	P	P	P	P	P	M	M	M	P/M	K	K	K	K	K	H	S	S	K/S	M/S		P/M	P	P	P	P	K	S	S	N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	NEF 	**SNMG 120404 NEF**	0,4	○	○	○				●	●	●																					
		SNMG 120408 NEF	0,8	○	●	○				○	●	●																					
Finishing	NSJ 	**SNMG 090304 NSJ**	0,4																										○				
		SNMG 120404 NSJ	0,4																										○				
Finishing	NSX 	**SNMG 120404 NSX**	0,4																							○	○		○				
		SNMG 120408 NSX	0,8	○	○	○																				○	○		○				
		SNMG 120412 NSX	1,2	○	○	○																											
Medium Cut	NGU 	**SNMG 090304 NGU**	0,4		●			▲						○	○																		
		SNMG 090308 NGU	0,8	○	●	○		▲	▲					○	○											○			○				
		SNMG 120404 NGU	0,4	●	●	○	▲	▲	▲	○	●	●	○	○	○						○		▲						○				
		SNMG 120408 NGU	0,8	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲			○			○				
		SNMG 120412 NGU	1,2	●	●	●	▲	▲	▲	●	●	●	○	○	○						○		▲										
		SNMG 120416 NGU	1,6	●	●	○		▲	▲		●		●	○	○																		
		SNMG 150608 NGU	0,8	○	○	○					○			○	○																		
		SNMG 150612 NGU	1,2	○	○	○		▲	▲		○			○	○																		
		SNMG 150616 NGU	1,6	○	○	○	▲							○	○																		
Medium Cut	NGE 	**SNMG 120408 NGE**	0,8	○	●	○	▲	▲	▲																								
		SNMG 120412 NGE	1,2	○	●	●	▲	▲	▲																								
		SNMG 120416 NGE	1,6	○	●	○	▲	▲	▲																								
		SNMG 150608 NGE	0,8	○	○	○																											
		SNMG 150612 NGE	1,2	○	○	○																											
		SNMG 150616 NGE	1,6	○	○	○	▲																										

Shape charts: Depth of cut (mm) vs. Feed rate (mm/rev)

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

Neg. Inserts
C
D
K
R
S
T
V
W

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 0° Relief | With Insert Hole



Dimensions (mm)				
SN_ _	L	IC	S	D_1
0903..	9,525	9,525	3,18	3,81
1204..	12,7	12,7	4,76	5,16
1506..	15,875	15,875	6,35	6,35
1906..	19,05	19,05	6,35	7,94
2509..	25,4	25,4	9,52	9,2


⇨ D14, D20~21 D41


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P/M	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Medium Cut	 NUG	**SNMG 090308 NUG**	0,8		○	●		▲	▲																							
		SNMG 120408 NUG	0,8	○	○	●			▲																							
		SNMG 120412 NUG	1,2		○	●																										
		SNMG 120416 NUG	1,6	●		○			▲																							
		SNMG 150612 NUG	1,2			○																										
		SNMG 190612 NUG	1,2			○			▲																							
		SNMG 190616 NUG	1,6			○																										
		SNMG 250924 NUG	2,4			○			▲																							
Medium Cut	 L/RUM	**SNMG 120404 LUM**	0,4																										○			
		SNMG 120408 LUM	0,8																										○			
		SNMG 120412 LUM	1,2																										○			
		SNMG 120404 RUM	0,4																										○			
		SNMG 120408 RUM	0,8																										○			
Medium Cut	 NEG	**SNMG 120404 NEG**	0,4	○	●	○				○	●	●								●	●	▲	▲							○	●	
		SNMG 120408 NEG	0,8	○	●	○				●	●	●	○							○	○	▲	▲							●	○	
		SNMG 120412 NEG	1,2	○	●	○				●	●	●	○																			
		SNMG 150608 NEG	0,8	○	○	○				○																						
		SNMG 150612 NEG	1,2	○	○	○				●	●		○							○	○									○		
		SNMG 150616 NEG	1,6	○	○	○				○																						
		SNMG 190612 NEG	1,2	○	○	○				○	●									○	○									○	○	
		SNMG 190616 NEG	1,6	○	○	○				○	●										○									○	○	
Medium Cut	 NEX	**SNMG 120404 NEX**	0,4							●	●	●	○							○	●	▲	▲									
		SNMG 120408 NEX	0,8							●	●	●	●							○	●	▲	▲									
		SNMG 120412 NEX	1,2							●	●	●	○							○	●	▲	▲									
		SNMG 150612 NEX	1,2																	○	○	▲	▲									
		SNMG 190612 NEX	1,2																	○	○	▲	▲									
		SNMG 190616 NEX	1,6																		●	▲	▲									
Medium Cut	 NUP	**SNMG 120404 NUP**	0,4		●	●		▲	▲		●		○							●	●	▲	▲									
		SNMG 120408 NUP	0,8		●	●		▲	▲	●	●	●	●							●	○	▲	▲						○			
		SNMG 120412 NUP	1,2					▲	▲	●	●	●	○							○	○	▲	▲									

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

90° Square Type | 0° Relief | With Insert Hole



Dimensions (mm)				
SN__	L	IC	S	D_1
0903..	9,525	9,525	3,18	3,81
1204..	12,7	12,7	4,46	5,16
1506..	15,875	15,875	6,35	6,35
1906..	19,05	19,05	6,35	7,94
2509..	25,4	25,4	9,52	9,2

⇨ D14, D20~21
D41



⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	Carbide Coated M	AC6020M	AC6030M	AC6040M	Carbide Coated P/M	AC630M	Carbide Coated K	AC4010K	AC4015K	AC420K	AC405K	AC415K	Carbide Coated H	AC503U	Carbide Coated S	AC5015S	AC5025S	Carbide Coated K/S	AC510U	Carbide Coated M/S	AC520U	Carbide Coated P/M	AC1030U	AC530U	Cermet Coated P	T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated P	Carbide Uncoated K	G10E	Carbide Uncoated S	EH510	EH520	Carbide Uncoated N	H1
Roughing	 NUX	**SNMG 090308 NUX**	0,8				○																																							
		SNMG 120404 NUX	0,4				○																																							
		SNMG 120408 NUX	0,8	●	●	●	●	▲	▲	▲																																				
		SNMG 120412 NUX	1,2	●	●	●	●	▲	▲	▲																																				
		SNMG 120416 NUX	1,6	○	○	○	○	▲	▲	▲																																				
		SNMG 190612 NUX	1,2	○	○	○	○	▲	▲	▲																																				
		SNMG 190616 NUX	1,6	○	○	○	○	▲	▲	▲																																				
Roughing	 NMU	**SNMG 120408 NMU**	0,8	●	●	●	●	▲	▲	▲	●	●		●												●	●	▲	▲			○	○															
		SNMG 120412 NMU	1,2	○	●	●	●	▲	▲	▲	●	●		●												●	●	▲	▲			○	○															
		SNMG 120416 NMU	1,6	●	●	○	●	▲	▲	▲	●			●																																		
		SNMG 150608 NMU	0,8	○	○	○																																								
		SNMG 150612 NMU	1,2	●	○	●	●	▲	▲	▲	●	●		●												○	○	▲	▲																			
		SNMG 150616 NMU	1,6	●	●	●	●	▲	▲	▲	●	●		●												○	○	▲	▲																			
		SNMG 190612 NMU	1,2	●	●	●	●	▲	▲	▲	●	●		●												○	●	▲	▲																			
		SNMG 190616 NMU	1,6	●	●	●	●	▲	▲	▲	●	●		●												○	●	▲	▲																			
		SNMG 190624 NMU	2,4	○	○	○																																								
		SNMG 250924 NMU	2,4	○	○	●			▲																																					
Roughing	 NEM	**SNMG 120408 NEM**	0,8	○	●	○				●	●	●													○	○																					
		SNMG 120412 NEM	1,2	○	●	○				●	●	●													○	○																					
		SNMG 120416 NEM	1,6		●																																										
		SNMG 150608 NEM	0,8	○	○	○				○	○	○																																		
		SNMG 150612 NEM	1,2	○	●	○				●	●	●													○	○																					
		SNMG 150616 NEM	1,6	○	●	○				●	●	●																																		
		SNMG 190612 NEM	1,2	○	●	○				●	●	●																																		
		SNMG 190616 NEM	1,6	○	●	○				●	●	●																																		
		SNMG 190624 NEM	2,4	○	○	○				○		○																																		
		SNMG 250924 NEM	2,4	○	○	○					○	○																																		
Roughing	 NME	**SNMG 120408 NME**	0,8	○	●	●	▲	▲	▲					○	○																																	
		SNMG 120412 NME	1,2	○	○	○	▲	▲	▲					○	○																																	
		SNMG 120416 NME	1,6	○	○	○	▲	▲	▲					○	○																																	
		SNMG 150608 NME	0,8	○	○	○								○	○																																	
		SNMG 150612 NME	1,2	○	●	○	▲		▲					○	○																																	
		SNMG 150616 NME	1,6	○	○	○	▲	▲	▲					○	○																																	
		SNMG 190612 NME	1,2	○	○	○	▲	▲	▲					○	○																																	
		SNMG 190616 NME	1,6	○	●	●	▲	▲	▲					○	○																																	
		SNMG 190624 NME	2,4	○	○	○		▲						○	○																																	
		SNMG 250924 NME	2,4	○	○	○								○	○																																	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 0° Relief | With Insert Hole



Dimensions (mm)				
SN_ _	L	IC	S	D_1
1204..	12,7	12,7	4,46	5,16
1506..	15,875	15,875	6,35	6,35
1906..	19,05	19,05	6,35	7,94


⇨ D14, D20~21
D41


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P/M	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC630M	AC6020M	AC630M	AC4010K	AC503U	AC5015S	AC510U	AC520U	AC1030U	T1500Z	T3000Z	G10E	EH510	H1
				AC8025P	AC6030M	AC6030M	AC6040M	AC4015K	AC5025S	AC5025S			AC530U	T1000A	T1500A		EH520	
				AC8035P	AC6040M	AC6040M		AC420K										
				AC810P				AC405K										
				AC820P				AC415K										
				AC830P														
Roughing		**SNMG 120408 LHM**	0,8	○	○	○	●											
	L/RHM	**SNMG 120408 RHM**	0,8	○	○	○	●											
Roughing		**SNMG 120408 NMX**	0,8		○	○		▲	▲									
	NMX	**SNMG 120412 NMX**	1,2		○	●		▲	▲									
		SNMG 120416 NMX	1,6		○			▲	▲									
		SNMG 150612 NMX	1,2		●			▲	▲									
		SNMG 150616 NMX	1,6		●			▲	▲									
		SNMG 190612 NMX	1,2		●	●		▲	▲									
		SNMG 190616 NMX	1,6		○	●		▲	▲									
Roughing		**SNMG 120408 NGZ**	0,8					●	●	●	▲	▲						
	NGZ	**SNMG 120412 NGZ**	1,2					○	●	●	▲	▲						
		SNMG 120416 NGZ	1,6					○	○	●	▲	▲						
		SNMG 150612 NGZ	1,2					○	○	○	▲	▲						
		SNMG 150616 NGZ	1,6					○	○	○	▲	▲						
		SNMG 190612 NGZ	1,2					○	○	○		▲						
		SNMG 190616 NGZ	1,6					○	○	○		▲						
Roughing		**SNMG 120408 NUZ**	0,8		○	○		▲								○		
	NUZ	**SNMG 120412 NUZ**	1,2		○	○			▲									
		SNMG 120416 NUZ	1,6		○	○				●	▲	▲						
		SNMG 150612 NUZ	1,2		○	○				●	▲	▲						
		SNMG 150616 NUZ	1,6							●		▲						
		SNMG 190612 NUZ	1,2		○	○			▲	●		▲						
		SNMG 190616 NUZ	1,6		○	○			▲	●		▲						

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 0° Relief | With Insert Hole



Dimensions (mm)				
SN__	L	IC	S	D_1
1204..	12,7	12,7	4,46	5,16
1506..	15,875	15,875	6,35	6,35
1906..	19,05	19,05	6,35	7,94
2507..	25,4	25,4	7,94	9,2
2509..	25,4	25,4	9,52	9,2
3109..	31,75	31,75	9,52	8,8


⇨ D14, D20~21


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K			Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Heavy Roughing	 NMP	**SNMM 120408 NMP**	0,8	○	●	●	▲	▲	▲		●		○							○		▲										
		SNMM 120412 NMP	1,2	○	○	●		▲	▲		●		●							○		▲										
		SNMM 120416 NMP	1,6	○	●	○	▲	▲	▲		●		○							○		▲										
		SNMM 120420 NMP	2,0		●	●		▲	▲																							
		SNMM 150612 NMP	1,2	○	●	●	▲	▲	▲		○		●																			
		SNMM 150616 NMP	1,6	●	●	●	▲	▲	▲		○		●																			
		SNMM 190612 NMP	1,2	○	●	●	▲	▲	▲		●		●							○		▲										
		SNMM 190616 NMP	1,6	●	●	●	▲	▲	▲		●		○							○		▲										
		SNMM 190624 NMP	2,4	●	●			▲	▲																							
		SNMM 250724 NMP	2,4	○	○	●	▲	▲	▲		○		○																			
		SNMM 250924 NMP	2,4	○	○		▲	▲			○		○																			
		SNMM 310924 NMP	2,4	○	○			▲			○		○																			
Heavy Roughing	 NMH	**SNMM 190612 NMH**	1,2	●	●	●		▲	▲		●																				
		SNMM 190616 NMH	1,6	●	●	●		▲	▲		●																				
		SNMM 250724 NMH	2,4		●	●																										
		SNMM 250924 NMH	2,4		●	●																										
Heavy Roughing	 NHG	**SNMM 120408 NHG**	0,8	●	○	○	▲	▲	▲				○																			
		SNMM 120412 NHG	1,2	○	●	○	▲	▲	▲				○																			
		SNMM 120416 NHG	1,6	○	●	○	▲	▲	▲				○																			
		SNMM 150612 NHG	1,2				▲						●																			
		SNMM 150616 NHG	1,6	○	●		▲	▲					●																			
		SNMM 190612 NHG	1,2	○	○	●	▲	▲	▲				○																			
		SNMM 190616 NHG	1,6	●	●	●	▲	▲	▲				●																			
		SNMM 190624 NHG	2,4	○	●	●		▲	▲				○																			
		SNMM 190616 NHGS	1,6		●			▲																								
Heavy Roughing	 NHP	**SNMM 120408 NHP**	0,8		○	●		▲	▲																							
		SNMM 120412 NHP	1,2		●	●		▲	▲																							
		SNMM 120416 NHP	1,6		○	○			▲																							
		SNMM 150612 NHP	1,2			●			▲																							
		SNMM 190612 NHP	1,2		●	●		▲	▲				○																			
		SNMM 190616 NHP	1,6		●	●		▲	▲				●																			
		SNMM 190624 NHP	2,4		●	●	▲	▲	▲																							
		SNMM 250724 NHP	2,4		●	●		▲	▲				○																			
		SNMM 250924 NHP	2,4		○	●	▲	▲	▲				○																			
		SNMM 310924 NHP	2,4			●	▲						○																			

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type — 0° Relief — With Insert Hole



Dimensions (mm)				
SN_ _	L	IC	S	D_1
1906..	19,05	19,05	6,35	7,94
2507..	25,4	25,4	7,94	9,2
2509..	25,4	25,4	9,52	9,2
3109..	31,75	31,75	9,52	8,8



- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

Carbide Coated: AC8015P–AC530U; Cermet (Coated: T1500Z, T3000Z; Uncoated: T1000A, T1500A); Carbide Uncoated: G10E, EH510, EH520, H1

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Heavy Roughing	NHU	SNMM 190616 NHU	1,6				▲						●																				
Heavy Roughing	NHU	SNMM 250724 NHU	2,4		●		▲	▲					●																				
Heavy Roughing	NHU	SNMM 250924 NHU	2,4		○		▲	▲					●																				
Heavy Roughing	NHU	SNMM 310924 NHU	2,4		○			▲																									
Heavy Roughing	NHW	SNMM 190616 NHW	1,6				▲						●																				
Heavy Roughing	NHW	SNMM 250724 NHW	2,4		●		▲	▲	▲				○																				
Heavy Roughing	NHW	SNMM 250924 NHW	2,4		●		▲	▲					○																				
Heavy Roughing	NHW	SNMM 310924 NHW	2,4		○			▲					○																				
Heavy Roughing	NHF	SNMM 190612 NHF	1,2					▲	▲																								
Heavy Roughing	NHF	SNMM 190616 NHF	1,6		○	○		▲	▲																								
Heavy Roughing	NHF	SNMM 190624 NHF	2,4		○	●	▲	▲	▲																								
Heavy Roughing	NHF	SNMM 250724 NHF	2,4		○	○		▲	▲				○																				
Heavy Roughing	NHF	SNMM 250732 NHF	3,2		○	○		▲																									
Heavy Roughing	NHF	SNMM 250924 NHF	2,4		○	●		▲	▲				○																				
Heavy Roughing	NHF	SNMM 250932 NHF	3,2		○	○		▲																									
Heavy Roughing	NHF	SNMM 310924 NHF	2,4		○	○		▲																									





● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 0° Relief | With Insert Hole



Dimensions (mm)				
SN__	L	IC	S	D_1
0903..	9,525	9,525	3,18	3,81
1204..	12,7	12,7	4,76	5,16
1506..	15,875	15,875	6,35	6,35
1906..	19,05	19,05	6,35	7,94


⇨ D14, D20-21
D25


⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SNMA/SNGA ●●●●●●

● G/M-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing		**SNMA 120404**	0,4											○	○																		
		SNMA 120408	0,8											○	○	●	▲	▲											○				
		SNMA 120412	1,2											●	●	●	▲	▲															
		SNMA 120416	1,6											○	●	●	▲	▲															
		SNMA 120420	2,0											○	○																		
		SNMA 150612	1,2											○	○	○		▲															
		SNMA 150616	1,6											○	○			▲															
		SNMA 190612	1,2											○	○	●	▲	▲															
		SNMA 190616	1,6											○	○	●	▲	▲															
Medium Cut		**SNGA 120404**	0,4																○														
		SNGA 120408	0,8																○														
		SNGA 120412	1,2																									○					

SNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cutting		**SNGG 090304 LST**	0,4																									○	○				
		SNGG 090308 LST	0,8																									○	○				
		SNGG 090304 RST	0,4																									○	○				
		SNGG 090308 RST	0,8																									○	○				
Medium Cut		**SNGG 120404 LUM**	0,4																									○	●				
		SNGG 120408 LUM	0,8																									○	●				
		SNGG 120404 RUM	0,4																									○	●				
		SNGG 120408 RUM	0,8																									●	●				
		SNGG 120412 RUM	1,2																									○	●				

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 0° Relief | Without Insert Hole



Dimensions (mm)				
SN_ _	L	IC	S	D_1
1204..	12,7	12,7	4,76	5,16

⇨ D14, D20-21
D25

⇨ E10

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SN_N ●●●●●● ■-■■

● G/M-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M: AC6020M	AC6030M	AC6040M	P/M: AC630M	K: AC4010K	AC4015K	AC420K	AC405K	AC415K	H: AC503U	S: AC5015S	AC5025S	K/S: AC510U	M/S: AC520U	P/M: AC1030U	AC530U	Cermet Coated P: T1500Z	T3000Z	Cermet Uncoated P: T1000A	T1500A	Carbide Uncoated K: G10E	S: EH510	EH520	N: H1
Medium Cut		**SNGN 120408**	0,8																						○		○	○				
Medium Cut		**SNMN 120408**	0,8											○	○										○		○	○				
		SNMN 120412	1,2											○	○																	
		SNMN 120416	1,6											○	○	○																

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

60° Triangle Type | 0° Relief | With Insert Hole



Dimensions (mm)				
TN__	L	IC	S	D_1
1604..	16,5	9,525	4,76	3,81

⇨ D15, D22~23
D42

⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K			Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P			Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Fine Finishing	 NFB	**TNMG 160402 NFB**	0,2									○														○	○	○	○				
		TNMG 160404 NFB	0,4									○														○	○	○	○				
		TNMG 160408 NFB	0,8									○														○	○	○	○				
Fine Finishing	 NFA	**TNMG 160402 NFA**	0,2																							●	○	○	●				
		TNMG 160404 NFA	0,4																							●	○	○	●				
		TNMG 160408 NFA	0,8																							●	○	○	●				
Fine Finishing	 NFL	**TNMG 160404 NFL**	0,4		○			▲					○													●	●	○	●				
		TNMG 160408 NFL	0,8		○			▲					○													●	○	○	●				
Fine Finishing	 NFE	**TNMG 160402 NFE**	0,2	○	○	○	▲		▲		○	○														○	○	○	○				
		TNMG 160404 NFE	0,4	○	○	○	▲		▲		○	○														○	○	○	○				
		TNMG 160408 NFE	0,8	○	○	○	▲		▲		○	○														○	○	○	○				
		TNMG 160412 NFE	1,2	○	○	○	▲		▲		○	○														○	○	○	○				
Finishing	 NLU	**TNMG 160402 NLU**	0,2								○		○													○	○	○					
		TNMG 160404 NLU	0,4	●	●	○	▲	▲			○		○													●	●	○	●				
		TNMG 160408 NLU	0,8	●	●	○	▲	▲			○		○													●	○	○	●				
		TNMG 160412 NLU	1,2	●	●	○	▲	▲	▲		○		○													●	●	○	●				
Finishing	 NEF	**TNMG 160404 NEF**	0,4	○	●	○				●	●	●	○							○	○	▲	▲							○	○		
		TNMG 160408 NEF	0,8	○	●	○				●	●	●	○							○	○	▲	▲							○	○		
Finishing	 NSU	**TNMG 160402 NSU**	0,2							●	●	●	○									▲				○	○	○	○				
		TNMG 160404 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●							●	●	▲	▲		○	●	○	●	●				
		TNMG 160408 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●							●	●	▲	▲		○	●	○	●	●				
		TNMG 160412 NSU	1,2	●	●		▲	▲	▲		●		○							○	○	▲	▲			●	●	○	●				

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

T TRIANGLE TYPE
INSERTS FOR TURNING

60° Triangle Type | 0° Relief | With Insert Hole



Dimensions (mm)				
TN__	L	IC	S	D_1
1603..	16,5	9,525	3,18	3,81
1604..	16,5	9,525	4,76	3,81
2204..	22,0	12,7	4,76	5,16

⇨ D15, D22~23 D42

⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K			Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P			Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N	
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NSE	**TNMG 160404 NSE**	0,4	●	●	○	▲	▲	▲																○		○	○				
		TNMG 160408 NSE	0,8	●	●	○	▲	▲	▲																○		○	○				
		TNMG 160412 NSE	1,2	●	●	○	▲	▲	▲																							
		TNMG 220404 NSE	0,4	●	●	○	▲	▲	▲																							
		TNMG 220408 NSE	0,8	●	○	○	▲	▲	▲																							
		TNMG 220412 NSE	1,2	○	○	○	▲																									
Finishing	 NSX	**TNMG 160308 NSX**	0,8			○																										
		TNMG 160404 NSX	0,4	●	○	○		▲																	○	○		○				
		TNMG 160408 NSX	0,8	○	●	○		▲	▲																○	○		○				
		TNMG 220404 NSX	0,4	○	○	○		▲																								
		TNMG 220408 NSX	0,8	○	○	○		▲																								
		TNMG 220412 NSX	1,2	○	○	○																										
Medium Cut	 NGU	**TNMG 160404 NGU**	0,4	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲			○	○		○				
		TNMG 160408 NGU	0,8	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲			○	○		○				
		TNMG 160412 NGU	1,2	●	●	●	▲	▲	▲	●	●	●	○	○	○						○		▲										
		TNMG 160416 NGU	1,6	○	●	●		▲	▲					○	○																		
		TNMG 220404 NGU	0,4		○			▲	▲					○	○							▲											
		TNMG 220408 NGU	0,8	●	●	○	▲	▲	▲				●	○	○																		
		TNMG 220412 NGU	1,2	●	○	●	▲	▲	▲				●	○	○																		
Medium Cut	 NGE	**TNMG 160404 NGE**	0,4	●	●	○	▲	▲	▲																							
		TNMG 160408 NGE	0,8	●	●	○	▲	▲	▲																							
		TNMG 160412 NGE	1,2	●	●	●	▲	▲	▲																							
		TNMG 220408 NGE	0,8	○	●	●	▲	▲	▲																							
		TNMG 220412 NGE	1,2	○	○	●	▲	▲	▲																							

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

60° Triangle Type

0° Relief
With Insert Hole



TN_ _	L	IC	S	D_1
	Dimensions (mm)			
1604..	16,5	9,525	4,76	3,81
2204..	22,0	12,7	4,76	5,16

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

TNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide																						Cermet				Carbide			
				Coated																						Coated		Uncoated		Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Medium Cut	 NUG	TNMG 160404 NUG	0,4	●	○	●		▲	▲																								
		TNMG 160408 NUG	0,8	●	●	●		▲	▲																								
		TNMG 160412 NUG	1,2		○	○																											
		TNMG 160416 NUG	1,6	●	○	○																											
		TNMG 220408 NUG	0,8		○	●			▲																								
		TNMG 220412 NUG	1,2	○	○	○																											
Medium Cut	 L/RUM	TNMG 160404 LUM	0,4																							○	○	○	○				
		TNMG 160408 LUM	0,8																							○	○	○	○				
		TNMG 220404 LUM	0,4																										○				
		TNMG 220408 LUM	0,8						▲																				○				
		TNMG 160404 RUM	0,4	●																						○	○	○	○				
		TNMG 160408 RUM	0,8	●																						○	○	○	○				
		TNMG 220404 RUM	0,4																										○				
		TNMG 220408 RUM	0,8					▲	▲																				○				
Medium Cut	 NEG	TNMG 160404 NEG	0,4	○	●	○				○	●	●																					
		TNMG 160408 NEG	0,8	○	●	○				●	●	●	○							●	●	▲	▲								○	○	
		TNMG 160412 NEG	1,2	○	●	○				●	●	●	○							○	○	▲	▲								○	○	
Medium Cut	 NEX	TNMG 160404 NEX	0,4							●	●	●	●							○	●	▲	▲										
		TNMG 160408 NEX	0,8							●	●	●	●							●	●	▲	▲		○								
		TNMG 160412 NEX	1,2							●	●	●	○							●	○	▲	▲										
Medium Cut	 NUP	TNMG 160404 NUP	0,4		●	●		▲	▲	●	●	●	●							●	○	▲	▲		○					○			
		TNMG 160408 NUP	0,8		●	●		▲	▲	●	●	●	●							●	○	▲	▲							○			
		TNMG 160412 NUP	1,2					▲			●	●	○							●	○	▲	▲										
		TNMG 220408 NUP	0,8		●	●		▲	▲											○	○												
		TNMG 220412 NUP	1,2					▲	▲																								

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

T TRIANGLE TYPE
INSERTS FOR TURNING

60° Triangle Type | 0° Relief | With Insert Hole



Dimensions (mm)				
TN__	L	IC	S	D_1
1604..	16,5	9,525	4,76	3,81
2204..	22,0	12,7	4,76	5,16
2706..	27,5	15,875	6,35	6,35
3309..	33,0	19,05	9,52	7,93

⇨ D15, D22~23 D42 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						M			P/M	K				H	S	K/S	M/S	P/M	Cermet Coated P				Carbide Uncoated K	S	N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing	 NUX	**TNMG 160404 NUX**	0,4	○	●	○	▲	▲	▲																						
		TNMG 160408 NUX	0,8	●	●	●	▲	▲	▲																						
		TNMG 160412 NUX	1,2	●	●	○	▲	▲	▲																						
		TNMG 220408 NUX	0,8	○	○	○	▲	▲	▲																						
		TNMG 220412 NUX	1,2	○	●	○	▲	▲	▲																						
Roughing	 NMU	**TNMG 160408 NMU**	0,8	●	●	●	▲	▲	▲	●	●		●								○			○							
		TNMG 160412 NMU	1,2	●	●	○	▲	▲	▲	●	●		○								○			○							
		TNMG 220408 NMU	0,8	●	●	●	▲	▲	▲	●			●								●										
		TNMG 220412 NMU	1,2	●	●	●	▲	▲	▲	●			●																		
		TNMG 220416 NMU	1,6	●	●	●	▲	▲	▲	●			●																		
		TNMG 270612 NMU	1,2	○	●	●		▲	▲																						
		TNMG 270616 NMU	1,6	○	○			▲																							
Roughing	 NEM	**TNMG 160408 NEM**	0,8	○	●	○				●	●	●									○										
		TNMG 160412 NEM	1,2	○	●	○				●	●	●																			
		TNMG 330924 NEM	2,4		○	○					○	○																			
Roughing	 NME	**TNMG 160408 NME**	0,8	○	●	○	▲	▲	▲					○	○																
		TNMG 160412 NME	1,2	●	●	○	▲	▲	▲																						
		TNMG 220408 NME	0,8	○	○	○		▲						○	○																
		TNMG 220412 NME	1,2	○	○	○		▲						○	○																
		TNMG 220416 NME	1,6	○	○	○	▲							○	○																
Roughing	 NMX	**TNMG 160408 NMX**	0,8		○	○		▲	▲																						
		TNMG 160412 NMX	1,2		●	●		▲	▲																						
		TNMG 220408 NMX	0,8		○	○		▲	▲																						
		TNMG 220412 NMX	1,2		○	○		▲	▲																						

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

60° Triangle Type | 0° Relief | With Insert Hole



Dimensions (mm)				
TN__	L	IC	S	D_1
1604..	16,5	9,525	4,76	3,81
2204..	22,0	12,7	4,76	5,16
2706..	27,5	15,875	6,35	6,35

⇨ D15, D22~23 D42 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K						Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P			Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing	 NGZ	TNMG 160404 NGZ	0,4											○	○	○	▲	▲														
		TNMG 160408 NGZ	0,8					▲						●	●	●	▲	▲														
		TNMG 160412 NGZ	1,2											○	○	●	▲	▲														
		TNMG 220408 NGZ	0,8											○	○		▲	▲														
		TNMG 220412 NGZ	1,2											○	○		▲	▲														
		TNMG 220416 NGZ	1,6											○	○		▲	▲														
Roughing	 L/RHM	TNMG 160404 LHM	0,4	○	○	○	▲	▲			●																					
		TNMG 160408 LHM	0,8	○	○	○	▲	▲			●																					
		TNMG 220404 LHM	0,4	○	○	○			▲																							
		TNMG 220408 LHM	0,8	○	○	○			▲																							
		TNMG 160404 RHM	0,4	●	○	○	▲	▲	▲		●		○																			
		TNMG 160408 RHM	0,8	○	○	○	▲	▲	▲		●																					
		TNMG 220404 RHM	0,4	○	○	○		▲	▲				○																			
		TNMG 220408 RHM	0,8	○	○	○	▲	▲	▲				○																			
Roughing	 NUZ	TNMG 160404 NUZ	0,4		○			▲						○	○	○	▲	▲														
		TNMG 160408 NUZ	0,8		○	○		▲						●	●	●	▲	▲														
		TNMG 160412 NUZ	1,2		○	○	▲							○	○	●	▲	▲														
		TNMG 160416 NUZ	1,6		○									○	○			▲														
		TNMG 160420 NUZ	2,0		○									○	○																	
		TNMG 220408 NUZ	0,8		○	●		▲	▲					○	○	○		▲														
		TNMG 220412 NUZ	1,2		○	○								○	○	○	▲	▲														
		TNMG 220416 NUZ	1,6		○	○								○	○	○	▲	▲														
		TNMG 270608 NUZ	0,8		○			▲																								
		TNMG 270612 NUZ	1,2		○																											
		TNMG 270616 NUZ	1,6		○				▲																							

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

60° Triangle Type

0° Relief
With Insert Hole



Dimensions (mm)				
TN_ _	L	IC	S	D_1
1604..	16,5	9,525	4,76	3,81
2204..	22,0	12,7	4,76	5,16
2706..	27,5	15,875	6,35	6,35

⇨D22-23 ⇨ E12

P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

TNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker







Application	Shape	ISO Cat. No.	RE	Carbide Coated																						Cermet Coated		Cermet Uncoated		Carbide Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Heavy Roughing	NMP	TNMM 160404 NMP	0,4		○																												
Heavy Roughing	NMP	TNMM 160408 NMP	0,8	●	●	●	▲	▲	▲				●																				
Heavy Roughing	NMP	TNMM 160412 NMP	1,2		●	●		▲	▲				●																				
Heavy Roughing	NMP	TNMM 160416 NMP	1,6					▲																									
Heavy Roughing	NMP	TNMM 220408 NMP	0,8		●	●	▲	▲	▲																								
Heavy Roughing	NMP	TNMM 220412 NMP	1,2	●	●	●	▲	▲	▲				●																				
Heavy Roughing	NMP	TNMM 220416 NMP	1,6		●	●	▲	▲	▲				●																				
Heavy Roughing	NMP	TNMM 270612 NMP	1,2		○			▲																									
Heavy Roughing	NMP	TNMM 270616 NMP	1,6		○			▲	▲																								
Heavy Roughing	NHG	TNMM 160408 NHG	0,8	●			▲		▲				●																				
Heavy Roughing	NHG	TNMM 160412 NHG	1,2	●			▲		▲				●																				
Heavy Roughing	NHG	TNMM 160416 NHG	1,6				▲																										
Heavy Roughing	NHG	TNMM 220408 NHG	0,8		○	○		▲	▲																								
Heavy Roughing	NHG	TNMM 220412 NHG	1,2		●	●	▲	▲	▲																								
Heavy Roughing	NHG	TNMM 220416 NHG	1,6		●	○	▲	▲	▲																								
Heavy Roughing	NHP	TNMM 160408 NHP	0,8		○	○		▲	▲																								
Heavy Roughing	NHP	TNMM 160412 NHP	1,2		○	●		▲	▲																								
Heavy Roughing	NHP	TNMM 220408 NHP	0,8		○	○			▲																								
Heavy Roughing	NHP	TNMM 220412 NHP	1,2		○	●		▲	▲																								
Heavy Roughing	NHP	TNMM 220416 NHP	1,6		○			▲	▲																								
Heavy Roughing	NHP	TNMM 270612 NHP	1,2		○	●			▲																								
Heavy Roughing	NHP	TNMM 270616 NHP	1,6		○	○			▲																								

TNMN ●●●●●●

● M-Class No Chipbreaker



Application	Shape	ISO Cat. No.	RE	Carbide Coated																						Cermet Coated		Cermet Uncoated		Carbide Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Medium Cut		TNMN 160408	0,8											○	○	○																	
Medium Cut		TNMN 160412	1,2											○	○																		
Medium Cut		TNMN 160416	1,6											○	○	○																	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

T TRIANGLE TYPE
INSERTS FOR TURNING

60° Triangle Type | 0° Relief | With Insert Hole



Dimensions (mm)				
TN__	L	IC	S	D_1
1604..	16,5	9,525	4,76	3,81
2204..	22,0	12,7	4,76	5,16

⇨ D15, D22~23 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TNMA ○○○○○○

● G/M-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K				Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing		**TNMA 160404**	0,4											○	○	○	▲	▲											○	○		
		TNMA 160408	0,8											○	○	●	▲	▲											○			
		TNMA 160412	1,2											○	○	●	▲	▲														
		TNMA 160416	1,6											○	●	○	▲	▲														
		TNMA 160420	2,0											○	○																	
		TNMA 220408	0,8											○	○	○	▲	▲														
		TNMA 220412	1,2											○	●	○	▲	▲														
		TNMA 220416	1,6											○	●	○	▲	▲														



⇨ D11 ⇨ E11

TRM ○○○○○○ -■■

● M-Class Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K				Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Fine Finishing	 -FL	**TRM 551704 -FL**	0,4		○																					○	○					
		TRM 551708 -FL	0,8		○																					○	○					
Finishing	 -LU	**TRM 551704 -LU**	0,4	●	○		▲	▲	▲																	○	○					
		TRM 551708 -LU	0,8	●	○		▲	▲	▲																	○	○					
		TRM 551712 -LU	1,2	○	○		▲	▲																		○	○					
	  -SU	**TRM 551704 -SU**	0,4		○			▲					○													○	○					
		TRM 551708 -SU	0,8		○		▲	▲					○													○	○					
		TRM 551712 -SU	1,2		○			▲					○																			
Light Cut	  -GU	**TRM 551704 -GU**	0,4	○	○		▲	▲	▲				○																			
		TRM 551708 -GU	0,8	○	○		▲	▲	▲				○																			
		TRM 551712 -GU	1,2	○	○		▲	▲	▲																							

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

T TRIANGLE TYPE
INSERTS FOR TURNING

60° Triangle Type | 0° Relief | With Insert Hole



Dimensions (mm)				
TN__	L	IC	S	D_1
1103..	11,0	6,35	3,18	2,26
1603..	16,5	9,525	3,18	3,81
1604..	16,5	9,525	4,76	3,81

⇨ D15, D22~23 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M AC6020M	AC6030M	AC6040M	PM AC630M	K AC4010K	AC4015K	AC420K	AC405K	AC415K	H AC503U	S AC5015S	AC5025S	KS AC510U	MS AC520U	PM AC1030U	AC530U	Cermet Coated P T1500Z	T3000Z	Uncoated P T1000A	T1500A	Carbide Uncoated K G10E	S EH510	EH520	N H1
Finishing	L/RFT	**TNGG 110302 LFT**	0,2																								○	○				
		TNGG 110304 LFT	0,4																								○	○				
		TNGG 110302 RFT	0,2																								○	○				
		TNGG 110304 RFT	0,4																								○	○				
Light Cutting	L/RST	**TNGG 160302 LST**	0,2																								○	○				
		TNGG 160304 LST	0,4																								○	○				
		TNGG 160308 LST	0,8																								○	○				
		TNGG 160402 LST	0,2																								○	○				
		TNGG 160404 LST	0,4																								○	○				
		TNGG 160408 LST	0,8																								○	○				
		TNGG 160412 LST	1,2																									○				
		TNGG 160302 RST	0,2																								○	○				
		TNGG 160304 RST	0,4																								○	○				
		TNGG 160308 RST	0,8																								○	○				
		TNGG 160402 RST	0,2																								○	○				
		TNGG 160404 RST	0,4																								○	○				
		TNGG 160408 RST	0,8																								○	○				
		TNGG 160412 RST	1,2																									○				
Finishing	NSU	**TNGG 160402 NSU**	0,2																	○	○					○	●	○	○				
		TNGG 160404 NSU	0,4																	○	○					○	○	○	○				
		TNGG 160408 NSU	0,8																	○	○					○	○	○	○				
Finishing	L/RFY	**TNGG 160401 LFY**	0,1																							○		○	○				
		TNGG 160402 LFY	0,2																					○		○	○	○	○				
		TNGG 160404 LFY	0,4																					○		○	○	○	○				
		TNGG 160408 LFY	0,8																					○		○		○	○				
		TNGG 160412 LFY	1,2																							○			○				
		TNGG 160401 RFY	0,1																							○		○	○				
		TNGG 160402 RFY	0,2																		○			○		○	○	○	○				
		TNGG 160404 RFY	0,4																					○		○	○	○	○				
		TNGG 160408 RFY	0,8																					○		○		○	○				
		TNGG 160412 RFY	1,2																							○			○				
Finishing	L/RFX	**TNGG 160402 LFX**	0,2																					○		○	○	○	○				
		TNGG 160404 LFX	0,4																					○	○	○	○	○	○				
		TNGG 160408 LFX	0,8																					○									
		TNGG 160402 RFX	0,2																					○		○	●	○	○				
		TNGG 160404 RFX	0,4																					○		○	○	○	○				
		TNGG 160408 RFX	0,8																					○									

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

60° Triangle Type

0° Relief
With Insert Hole



TN_ _	L	IC	S	D1
1103..	11,0	6,35	3,18	2,26
1604..	16,5	9,525	4,76	3,81
2204..	22,0	12,7	4,76	5,16

Dimensions (mm)

⇨ D15, D22~23 ⇨ E12

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker





L/RUM





NGH

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated	Cermet Uncoated			Carbide Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Medium Cut	L/RUM	TNGG 160402 LUM	0,2																							○	●	○	○				
		TNGG 160404 LUM	0,4																							○	○	●	●				
		TNGG 160408 LUM	0,8																							○	○	○	●				
		TNGG 160412 LUM	1,2																									○	○				
		TNGG 220404 LUM	0,4																									○	○				
		TNGG 220408 LUM	0,8																									○	○				
		TNGG 160402 RUM	0,2																							○	○	○	●				
		TNGG 160404 RUM	0,4																							○	○	●	●				○
		TNGG 160408 RUM	0,8																							○	○	○	●				
		TNGG 160412 RUM	1,2																									○	○				
		TNGG 220404 RUM	0,4																									○	○				
		TNGG 220408 RUM	0,8																									○	○				
Finishing	NGH	TNGG 160402 NGH	0,2																○														
		TNGG 160404 NGH	0,4																○														
		TNGG 160408 NGH	0,8																○														

TNGA ●●●●●●

● G-Class No Chipbreaker



Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated	Cermet Uncoated			Carbide Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Medium Cut		TNGA 110308	0,8																									○					
		TNGA 160402	0,2																○														
		TNGA 160404	0,4																○									○					
		TNGA 160408	0,8																○									○	○	○			○

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

V DIAMOND TYPE
INSERTS FOR TURNING

35° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
VN__	L	IC	S	D_1
1604..	16,6	9,525	4,76	3,81

⇨ D16

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

VNMA ●●●●●●

● M-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated: T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated: G10E	Carbide Uncoated: EH510	EH520	H1
Roughing		**VNMA 160404**	0,4											○	○	○	▲	▲															
		VNMA 160408	0,8											○	○	○	▲	▲															
		VNMA 160412	1,2											○	○	○	▲	▲															

VNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated: T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated: G10E	Carbide Uncoated: EH510	EH520	H1
Fine Finishing	 NFB	**VNMG 160404 NFB**	0,4									○													○	○	○	○				
		VNMG 160408 NFB	0,8									○													○	○	○	○				
Fine Finishing	 NFA	**VNMG 160404 NFA**	0,4																						○	○	○	○				
		VNMG 160408 NFA	0,8																						○	○	○	○				
Fine Finishing	 NFL	**VNMG 160404 NFL**	0,4		○			▲					○													●	●	○	●				
		VNMG 160408 NFL	0,8		●			▲					○													●	●	○	●				
Fine Finishing	 NFE	**VNMG 160402 NFE**	0,2	○	○	○	▲		▲		○	○														○	○	○	○				
		VNMG 160404 NFE	0,4	○	○	○	▲		▲		○	○														○	○	○	○				
		VNMG 160408 NFE	0,8	○	○	○	▲		▲		○	○														○	○	○	○				
		VNMG 160412 NFE	1,2	○	○	○	▲		▲		○	○														○	○	○	○				
Finishing	 NLU	**VNMG 160402 NLU**	0,2								○		○													●	●	○	●				
		VNMG 160404 NLU	0,4	●	●		▲	▲			○		○													●	○	○	●				
		VNMG 160408 NLU	0,8	●	●		▲	▲			○		○													●	○	○	●				
		VNMG 160412 NLU	1,2	●			▲																											
Medium Cut	 NEF	**VNMG 160402 NEF**	0,2	○	○	○				●	●		○																	○			
		VNMG 160404 NEF	0,4	○	●	○				●	●	●	○							○	○	▲	▲							○	●		
		VNMG 160408 NEF	0,8	○	●	○				●	●	●	●							○	○	▲	▲							○	○		

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

V DIAMOND TYPE
INSERTS FOR TURNING

35° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
VN__	L	IC	S	D_1
1604..	16,6	9,525	4,76	3,81

⇨ D16

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

VNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated PM	Carbide Coated K			Carbide Coated H	Carbide Coated S			Carbide Coated KS	Carbide Coated MS	Carbide Coated PM	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NSU	**VNMG 160402 NSU**	0,2					▲		●	●	○									○		▲		○	○	○		○				
		VNMG 160404 NSU	0,4	●	●	○	▲	▲	▲	●	●	●	●							○	○	▲	▲		○	○	○	○	○				
		VNMG 160408 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●							●	○	▲	▲		○	○	○	○	○				
Medium Cut	 NSE	**VNMG 160404 NSE**	0,4	○	○	○	▲	▲																		○		○	○				
		VNMG 160408 NSE	0,8	●	●	○	▲	▲																		○		○	○				
Medium Cut	 NSX	**VNMG 160404 NSX**	0,4	○	○	○																				○			○				
		VNMG 160408 NSX	0,8	○	○	○		▲																		○			○				
Medium Cut	 NGU	**VNMG 160404 NGU**	0,4	●	●	○	▲	▲	▲	●	●	●	○	○	○						○		▲			○			○				
		VNMG 160408 NGU	0,8	●	●	○	▲	▲	▲	●	●	●	●	○	○						○		▲			○			○				
		VNMG 160412 NGU	1,2	○	●	○		▲				●		○	○						○		▲										
Medium Cut	 NGE	**VNMG 160404 NGE**	0,4	○	○	○		▲	▲																								
		VNMG 160408 NGE	0,8	○	●	○	▲	▲	▲																								
		VNMG 160412 NGE	1,2	○	○	○		▲																									
Medium Cut	 NUG	**VNMG 160404 NUG**	0,4	○	○	○		▲																									
		VNMG 160408 NUG	0,8	○	○	○		▲	▲																								
		VNMG 160412 NUG	1,2	●																													
Medium Cut	 NEG	**VNMG 160404 NEG**	0,4	○	●	○				●	●	●																		○	○		
		VNMG 160408 NEG	0,8	○	●	○				●	●	●									○									○	○		
		VNMG 160412 NEG	1,2	○	●	○				●	●	●																					
Medium Cut	 NEX	**VNMG 160404 NEX**	0,4							●	●	●	●							●	○	▲	▲										
		VNMG 160408 NEX	0,8							●	●	●	●							●	●	▲	▲		○								

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

V DIAMOND TYPE
INSERTS FOR TURNING

35° Diamond Type | 0° Relief | With Insert Hole



Dimensions (mm)				
VN__	L	IC	S	D_1
1604..	16,6	9,525	4,76	3,81

⇨ D16

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

VNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M: AC6020M	AC6030M	AC6040M	PM: AC630M	K: AC4010K	AC4015K	AC420K	AC405K	AC415K	H: AC503U	S: AC5015S	AC5025S	KS/MS: AC510U	AC520U	PM: AC1030U	AC530U	Cermet Coated P: T1500Z	T3000Z	Cermet Uncoated P: T1000A	T1500A	Carbide Uncoated K: G10E	S: EH510	EH520	N: H1
Medium Cut	 NUP	**VNMG 160404 NUP**	0,4	●	●		▲	▲	●	●		○							●		▲	▲							○			
		VNMG 160408 NUP	0,8	●	●		▲	▲	●	●	○	○							●	●	▲	▲							○			
Medium Cut	 NUX	**VNMG 160404 NUX**	0,4	○	○	○	▲	▲	▲																							
		VNMG 160408 NUX	0,8	○	○	○	▲	▲	▲																							
		VNMG 160412 NUX	1,2	○	○	○	▲	▲	▲																							
Medium Cut	 NGZ	**VNMG 160404 NGZ**	0,4											○	○	○	▲	▲														
		VNMG 160408 NGZ	0,8											●	●	○	▲	▲														
		VNMG 160412 NGZ	1,2											●	○	○	▲	▲														
Medium Cut	 NUZ	**VNMG 160404 NUZ**	0,4		○	○								○	○		▲	▲														
		VNMG 160408 NUZ	0,8		○	○								○	○		▲	▲														
		VNMG 160412 NUZ	1,2		○	○								○	○	○	▲	▲														

VNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M: AC6020M	AC6030M	AC6040M	PM: AC630M	K: AC4010K	AC4015K	AC420K	AC405K	AC415K	H: AC503U	S: AC5015S	AC5025S	KS/MS: AC510U	AC520U	PM: AC1030U	AC530U	Cermet Coated P: T1500Z	T3000Z	Cermet Uncoated P: T1000A	T1500A	Carbide Uncoated K: G10E	S: EH510	EH520	N: H1
Finishing	 NSU	**VNGG 160402 NSU**	0,2																							○	○	○	○				
		VNGG 160404 NSU	0,4																							○	○	○	○				
		VNGG 160408 NSU	0,8																							○	○	○	○				
Medium Cut	 NEF	**VNGG 160402 NEF**	0,2																		○												
		VNGG 160404 NEF	0,4										○																				

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

W TRIGON TYPE
INSERTS FOR TURNING

80° Trigon Type | 0° Relief / With Insert Hole



Dimensions (mm)				
WN_ _	L	IC	S	D_1
0604..	6,5	9,525	4,76	3,81
0804..	8,7	12,7	4,76	5,16

⇨ D17, D24 D42 ⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

WNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M: AC6020M	AC6030M	AC6040M	PM: AC630M	AC4010K	AC4015K	K: AC420K	AC405K	AC415K	H: AC503U	S: AC5015S	AC5025S	KS: AC510U	MS: AC520U	PM: AC1030U	AC530U	Cermet Coated P: T1500Z	T3000Z	Cermet Uncoated P: T1000A	T1500A	Carbide Uncoated K: G10E	S: EH510	EH520	N: H1
Fine Finishing	 NFB  Depth of cut (mm) 0 1 2 0,2 0,4 Feed rate (mm/rev)	**WNMG 060404 NFB**	0,4									○														○	○		○				
		WNMG 060408 NFB	0,8									○														○	○		○				
		WNMG 080402 NFB	0,2									○														○	○	○	○				
		WNMG 080404 NFB	0,4									○														○	○	○	○				
		WNMG 080408 NFB	0,8									○														○	○	○	○				
Fine Finishing	 NFA  Depth of cut (mm) 0 2 4 0,2 0,4 0,6 Feed rate (mm/rev)	**WNMG 080402 NFA**	0,2																							○		○	○				
		WNMG 080404 NFA	0,4																							●	○	○	●				
		WNMG 080408 NFA	0,8																							●	○	○	●				
Fine Finishing	 NFL  Depth of cut (mm) 0 2 4 0,2 0,4 0,6 Feed rate (mm/rev)	**WNMG 080404 NFL**	0,4		○			▲					○														●	○	○	●				
		WNMG 080408 NFL	0,8		○			▲					○														●	●	○	●				
Fine Finishing	 NFE  Depth of cut (mm) 0 1 2 0,2 0,4 Feed rate (mm/rev)	**WNMG 060404 NFE**	0,4	○	○	○	▲		▲		○	○														○	○		○				
		WNMG 060408 NFE	0,8	○	○	○	▲		▲		○	○														○	○		○				
		WNMG 080402 NFE	0,2	○	○	○	▲		▲		○	○														○	○	○	○				
		WNMG 080404 NFE	0,4	○	○	○	▲		▲		○	○														○	○	○	○				
		WNMG 080408 NFE	0,8	○	○	○	▲		▲		○	○														○	○	○	○				
		WNMG 080412 NFE	1,2	○	○	○	▲		▲		○	○														○	○	○	○				
Finishing	 NLU  Depth of cut (mm) "Standard" 0 2 4 0,2 0,4 0,6 Feed rate (mm/rev)	**WNMG 060404 NLU**	0,4	○	○	○																				●	○	○	●				
		WNMG 060408 NLU	0,8	○	○	○																				●	○	○	●				
		WNMG 060412 NLU	1,2	○	○	○																				●	○		●				
		WNMG 080404 NLU	0,4	●	●	○	▲	▲			○		○													●	○	○	●				
		WNMG 080408 NLU	0,8	●	●	○	▲	▲			○		○													●	○	○	●				
		WNMG 080412 NLU	1,2	○	●	○	▲	▲			○		○													●	○		●				
Finishing	 NLU-W  Depth of cut (mm) "Wiper" W type 0 2 4 0,2 0,4 0,6 Feed rate (mm/rev)	**WNMG 060404 NLU-W**	0,4	●	●		▲	▲		●	○		○				▲	▲								●			●				
		WNMG 060408 NLU-W	0,8	●	●		▲	▲		●	○		○				▲	▲								●			●				
		WNMG 080404 NLU-W	0,4	●	●		▲	▲		●	○		○				▲	▲								●	○		●				
		WNMG 080408 NLU-W	0,8	●	●		▲	▲		●	○		○				▲	▲								●	●		●				
		WNMG 080412 NLU-W	1,2	●	●		▲	▲			○		○				▲	▲								○	○		○				

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

W TRIGON TYPE
INSERTS FOR TURNING

80° Trigon Type | 0° Relief | With Insert Hole



Dimensions (mm)				
WN_ _	L	IC	S	D_1
0604..	6,5	9,525	4,76	3,81
06T3..	6,5	9,525	3,97	3,81
0804..	8,7	12,7	4,76	5,16

⇨ D17, D24 D42 ⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

WNMG ●●●●●● ■-■■

●

Application	Shape	ISO Cat. No.	RE	Carbide Coated P					M			P M	K				H	S		K S	M S	P M	Cermet Coated P				Cermet Uncoated K	Carbide Uncoated S		N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NEF	WNMG 060404 NEF	0,4	○	●	○				●	●	●								○	○		▲									
		WNMG 060408 NEF	0,8	○	●	○				●	●	●								○	○		▲									
		WNMG 080404 NEF	0,4	○	●	○				●	●	●	○							○	○	▲	▲							○	○	
		WNMG 080408 NEF	0,8	○	●	○				●	●	●	○							●	●	▲	▲							○	○	
Finishing	 NSU	WNMG 060404 NSU	0,4	●	●	○	▲	▲	▲	●	○	○	●							●	●	▲	▲									
		WNMG 060408 NSU	0,8	●	●	○	▲	▲	▲	●	○		●							●	●	▲	▲									
		WNMG 060412 NSU	1,2	○	○	○																										
		WNMG 06T304 NSU	0,4		○			▲																								
		WNMG 06T308 NSU	0,8		○			▲																								
		WNMG 080404 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●							○	●	▲	▲		○	●	○	○	●				
		WNMG 080408 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●							●	●	▲	▲		○	●	○	○	●				
		WNMG 080412 NSU	1,2	●	●	●	▲	▲	▲		●	●	●							○	○	▲	▲		○	○	●	○	○				
Finishing	 "Standard" NSE "Wiper" W type NSE-W	WNMG 080404 NSE	0,4	●	●	○	▲	▲	▲																○		○	○				
		WNMG 080408 NSE	0,8	●	●	○	▲	▲	▲																○		○	○				
		WNMG 080412 NSE	1,2	●	●	○	▲	▲	▲																							
		WNMG 060404 NSE-W	0,4	○	○	○																										
		WNMG 060408 NSE-W	0,8	○	○	○	▲	▲	▲																							
		WNMG 080404 NSE-W	0,4	●	●		▲	▲																	○							
		WNMG 080408 NSE-W	0,8	●	●		▲	▲																	○			○				
		WNMG 080412 NSE-W	1,2	●	●		▲	▲																								
Finishing		WNMG 080404 NSX	0,4	○	○	○																			○	○		○				
		WNMG 080408 NSX	0,8	●	○	●		▲	▲																○	○		○				
		WNMG 080412 NSX	1,2	○	○	○																										
Medium Cut	 "Standard" NGU "Wiper" W type NGU-W	WNMG 060404 NGU	0,4	●	●	○	▲	▲	▲	●	○	○	●	○	○																	
		WNMG 060408 NGU	0,8	●	●	○	▲	▲		●	○		●	○	○																	
		WNMG 060412 NGU	1,2	●	●	○	▲	▲			●		●	○	○																	
		WNMG 080404 NGU	0,4	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲			○		○				
		WNMG 080408 NGU	0,8	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲			○		○				
		WNMG 080412 NGU	1,2	●	●	●	▲	▲	▲	●	●	●	●	○	○						○		▲									
		WNMG 060408 NGU-W	0,8	○	○	○		▲																								
		WNMG 080408 NGU-W	0,8	●	●		▲	▲					●				▲	▲														
		WNMG 080412 NGU-W	1,2	●	●		▲	▲					●				▲	▲														

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

Neg. Inserts
C
D
K
R
S
T
V
W

80° Trigon Type

0° Relief
With Insert Hole



Dimensions (mm)				
WN_ _	L	IC	S	D1
0604..	6,5	9,525	4,76	3,81
06T3..	6,5	9,525	3,97	3,81
0804..	8,7	12,7	4,76	5,16

⇨ D17, D24
D42

⇨ E13

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

WNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

				Carbide																						Cermet				Carbide			
				Coated																						Coated		Uncoated		Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Medium Cut	 NGE	WNMG 060408 NGE	0,8	●	○	○	▲	▲	▲																								
Medium Cut	NGE	WNMG 060412 NGE	1,2	●	●	○	▲	▲	▲																								
Medium Cut	NGE	WNMG 080404 NGE	0,4	○	●	○	▲	▲	▲																								
Medium Cut	NGE	WNMG 080408 NGE	0,8	●	●	●	▲	▲	▲																								
Medium Cut	NGE	WNMG 080412 NGE	1,2	●	●	●	▲	▲	▲																								
Medium Cut	NGE	WNMG 080416 NGE	1,6	●	●	○	▲	▲	▲																								
Medium Cut	 NUG	WNMG 060404 NUG	0,4		○																												
Medium Cut	NUG	WNMG 060408 NUG	0,8		○																												
Medium Cut	NUG	WNMG 06T304 NUG	0,4		○			▲																									
Medium Cut	NUG	WNMG 06T308 NUG	0,8		○			▲																									
Medium Cut	NUG	WNMG 080404 NUG	0,4		○	○		▲																									
Medium Cut	NUG	WNMG 080408 NUG	0,8	●	●	●		▲	▲																								
Medium Cut	NUG	WNMG 080412 NUG	1,2		●	●			▲																								
Medium Cut	 NEG	WNMG 060408 NEG	0,8	○	●	○				○	○	○																					
Medium Cut	NEG	WNMG 060412 NEG	1,2	○	●	○				○	●	●									○		▲										
Medium Cut	NEG	WNMG 080404 NEG	0,4	○	●	○				●	●	●																					
Medium Cut	NEG	WNMG 080408 NEG	0,8	○	●	○				●	●	●	●							●	●	▲	▲								●	○	
Medium Cut	NEG	WNMG 080412 NEG	1,2	○	●	○				●	●	●	○							○	○	▲	▲								○	○	
Medium Cut	 NEX	WNMG 060404 NEX	0,4							●			●							●	●	▲	▲										
Medium Cut	NEX	WNMG 060408 NEX	0,8							●			●							●	●	▲	▲										
Medium Cut	NEX	WNMG 080404 NEX	0,4							●	●	●	●							●	○	▲	▲										
Medium Cut	NEX	WNMG 080408 NEX	0,8							●	●	●	●							●	●	▲	▲		○								
Medium Cut	NEX	WNMG 080412 NEX	1,2							●	●	●	●							○	●	▲	▲										
Medium Cut	 NUP	WNMG 080408 NUP	0,8		●	●		▲	▲	●	●	●	●							●	●	▲	▲										
Medium Cut	NUP	WNMG 080412 NUP	1,2		●			▲	▲		●	●	○							○	○	▲	▲										
Medium Cut	 NEM	WNMG 080408 NEM	0,8	○	●	○				●	●	●																					
Medium Cut	NEM	WNMG 080412 NEM	1,2	○	●	○				●	●	●																					

(Shape charts: Depth of cut (mm) vs. Feed rate (mm/rev))

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

W TRIGON TYPE
INSERTS FOR TURNING

80° Trigon Type | 0° Relief | With Insert Hole



Dimensions (mm)				
WN_ _	L	IC	S	D_1
0604..	6,5	9,525	4,76	3,81
0804..	8,7	12,7	4,76	5,16

⇨ D17, D24 D42 ⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

WNMG ●●●●●● ■-■■

● M-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M: AC6020M	AC6030M	AC6040M	P/M: AC630M	K: AC4010K	AC4015K	AC420K	AC405K	AC415K	H: AC503U	S: AC5015S	AC5025S	K/S: AC510U	AC520U	M/S: AC1030U	P/M: AC530U	Cermet Coated P: T1500Z	T3000Z	Cermet Uncoated P: T1000A	T1500A	Carbide Uncoated K: G10E	S: EH510	EH520	N: H1
Roughing	 NUX	**WNMG 080404 NUX**	0,4	○	●	●	▲	▲	▲																								
		WNMG 080408 NUX	0,8	●	●	●	▲	▲	▲																								
		WNMG 080412 NUX	1,2	●	●	●	▲	▲	▲																								
Roughing	 NMU	**WNMG 060408 NMU**	0,8	●	○	●	▲	▲	▲	●			●							●	●	▲	▲										
		WNMG 060412 NMU	1,2	●	●		▲	▲	▲	●			●									▲	▲										
		WNMG 080408 NMU	0,8	●	●	●	▲	▲	▲	●	●		●							○	●	▲	▲		○								
		WNMG 080412 NMU	1,2	●	●	●	▲	▲	▲	●	●		●							○	●	▲	▲		○								
		WNMG 080416 NMU	1,6	●	●		▲	▲	▲																								
Roughing	 NME	**WNMG 060408 NME**	0,8	○	○	○			▲					○	○																		
		WNMG 060412 NME	1,2	○	●	○	▲	▲	▲					○	○																		
		WNMG 080408 NME	0,8	●	●	●	▲	▲	▲					○	○																		
		WNMG 080412 NME	1,2	●	●	●	▲	▲	▲					○	○																		
		WNMG 080416 NME	1,6	●	●	○	▲	▲	▲					○	○																		
Roughing	 NMX	**WNMG 080408 NMX**	0,8		○	●		▲	▲																								
		WNMG 080412 NMX	1,2		○	●		▲	▲																								
Roughing	 NGZ	**WNMG 060408 NGZ**	0,8											○	○	●	▲	▲															
		WNMG 060412 NGZ	1,2											○	○	●	▲	▲															
		WNMG 080404 NGZ	0,4											○	○	○	▲	▲															
		WNMG 080408 NGZ	0,8											○	●	●	▲	▲															
		WNMG 080412 NGZ	1,2											○	●	●	▲	▲															
Roughing	 NUZ	**WNMG 080404 NUZ**	0,4		○									○	○	○	▲	▲															
		WNMG 080408 NUZ	0,8		○									○	●	●	▲	▲															
		WNMG 080412 NUZ	1,2		○									●	○	○	▲	▲															

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

W TRIGON TYPE
INSERTS FOR TURNING

80° Trigon Type | 0° Relief | With Insert Hole



Dimensions (mm)				
WN_ _	L	IC	S	D_1
0804..	8,7	12,7	4,76	5,16

⇨ D17, D24 ⇨ E13

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

WNMM ●●●●●● ■-■■

● M-Class One Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated P				Carbide Coated K				Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P				Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N	
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Heavy Roughing	 **NMP**	**WNMM 080408 NMP**	0,8	●	●	●	▲	▲	▲				●																				
		WNMM 080412 NMP	1,2	●	●	●	▲	▲	▲				●																				
Heavy Roughing	 **NHG**	**WNMM 080408 NHG**	0,8				▲	▲	▲				●																				
		WNMM 080412 NHG	1,2	●			▲	▲	▲				●																				

WNMA ●●●●●●

● M-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated P				Carbide Coated K				Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P				Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N	
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing		**WNMA 080408**	0,8											○	●	●	▲	▲																
		WNMA 080412	1,2											○	●	●	▲	▲																
		WNMA 080416	1,6											○	●	●	▲	▲																

WNGG ●●●●●● ■-■■

● G-Class Double Sided Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated P				Carbide Coated K				Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P				Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N	
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 **NSU**	**WNGG 080404 NSU**	0,4																							○	○	○	○					

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type — 7° Relief — With Insert Hole



Dimensions (mm)				
CC_ _	L	IC	S	D_1
03X1..	3,55	3,5	1,4	1,9
04X1..	4,37	4,3	1,8	2,3
0602..	6,4	6,35	2,38	2,8
09T3..	9,7	9,525	3,97	4,4



- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

CCET ●●●●●● ●-■■

● E-Class

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated		Cermet Uncoated		Carbide Uncoated			
				P						M			P/M	K					H	S		K/S	M/S		P/M	P				K	S		N
Finishing	L/RFY	CCET 03X1003 LFY	0,03																						○			○	○				
		CCET 03X101 LFY	0,1																						○			○	○				
		CCET 03X102 LFY	0,2																						○			○	○				
		CCET 03X104 LFY	0,4																						○			○	○				
		CCET 04X1003 LFY	0,03																						○			○	○				
		CCET 04X101 LFY	0,1																						○			○	○				
		CCET 04X102 LFY	0,2																						○			○	○				
		CCET 04X104 LFY	0,4																						○			○					
		CCET 060201 LFY	0,1																									○	○				
		CCET 060202 LFY	0,2																									○	○				
		CCET 09T301 LFY	0,1																									○	○				
		CCET 09T302 LFY	0,2																									○	○				
		CCET 03X1003 RFY	0,03																									○	○				
		CCET 03X101 RFY	0,1																									○	○				
		CCET 03X102 RFY	0,2																									○	○				
		CCET 03X104 RFY	0,4																									○	○				
		CCET 04X1003 RFY	0,03																									○	○				
		CCET 04X101 RFY	0,1																									○	○				
		CCET 04X102 RFY	0,2																									○	○				
		CCET 04X104 RFY	0,4																									○	○				
		CCET 060201 RFY	0,1																									○	○				
		CCET 060202 RFY	0,2																									○	○				
		CCET 09T301 RFY	0,1																									○	○				
		CCET 09T302 RFY	0,2																									○	○				



● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

Pos. Inserts
C
D
K
R
S
T
V
W

80° Diamond Type

7° Relief
With Insert Hole



Dimensions (mm)				
CC_ _	L	IC	S	D1
03X1..	3,55	3,5	1,4	1,9
04X1..	4,37	4,3	1,8	2,3
0602..	6,4	6,35	2,38	2,8
09T3..	9,7	9,525	3,97	4,4



P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

CCGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide																						Cermet				Carbide			
				Coated																						Coated		Uncoated		Uncoated			
				P						M			P/M	K					H	S		K/S	M/S	P/M		P				K	S		N
Finishing	NFC 	CCGT 060201M NFC	<0,1																					●	●			○	○				
		CCGT 060202M NFC	<0,2																					●	●			●	○				
		CCGT 060204M NFC	<0,4																					●	●			○	○				
		CCGT 09T301M NFC	<0,1																					●	●			○	○				
		CCGT 09T302M NFC	<0,2																					●	●			○	○				
		CCGT 09T304M NFC	<0,4																					●	●			○	○				
Finishing	L/RFX 	CCGT 0602003 LFX	0,03																					○	○			○					
		CCGT 060201 LFX	0,1																					○	○	●		○	●				
		CCGT 060202 LFX	0,2																					●	●	●		○	●				
		CCGT 060204 LFX	0,4																					●	●	●		●	●				
		CCGT 09T3003 LFX	0,03																					○	○								
		CCGT 09T301 LFX	0,1																					●	○	●		○	●				
		CCGT 09T302 LFX	0,2																					●	●	●		○	●				
		CCGT 09T304 LFX	0,4																					●	●	●		●	●				
		CCGT 09T308 LFX	0,8																					○	○								
		CCGT 0602003 RFX	0,03																					○	○			○					
		CCGT 060201 RFX	0,1																					○	○	●		○	●				
		CCGT 060202 RFX	0,2																					●	●	●		●	●				
		CCGT 060204 RFX	0,4																					●	●	●		●	●				
		CCGT 09T3003 RFX	0,03																					●	●			○					
		CCGT 09T301 RFX	0,1																					●	●	●		○	●				
		CCGT 09T302 RFX	0,2																					●	●	●		○	●				
		CCGT 09T304 RFX	0,4																					●	●	●		●	●				
		CCGT 09T308 RFX	0,8																					○	○								
Finishing	L/RFYS 	CCGT 03X1003 LFYS	0,03																					○									
		CCGT 03X101 LFYS	0,1																					○									
		CCGT 03X102 LFYS	0,2																					○									
		CCGT 03X104 LFYS	0,4																					○									
		CCGT 04X1003 LFYS	0,03																					○									
		CCGT 04X101 LFYS	0,1																					○									
		CCGT 04X102 LFYS	0,2																					○									
		CCGT 04X104 LFYS	0,4																					○									
		CCGT 03X1003 RFYS	0,03																					○									
		CCGT 03X101 RFYS	0,1																					○									
		CCGT 03X102 RFYS	0,2																					○									
		CCGT 03X104 RFYS	0,4																					○									
		CCGT 04X1003 RFYS	0,03																					○									
		CCGT 04X101 RFYS	0,1																					○									
		CCGT 04X102 RFYS	0,2																					○									
		CCGT 04X104 RFYS	0,4																					○									

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
CC_ _	L	IC	S	D_1
03X1..	3,55	3,5	1,4	1,9
04X1..	4,37	4,3	1,8	2,3
0602..	6,4	6,35	2,38	2,8
0903..	9,7	9,525	3,18	4,4
09T3..	9,7	9,525	3,97	4,4
1204..	12,9	12,7	4,76	5,5

⇨ E14

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CCGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated T1500Z	T3000Z	Cermet Uncoated T1000A	T1500A	Carbide Uncoated G10E	EH510	EH520	H1
Finishing	 L/RFY	**CCGT 03X101 LFY**	0,1																				○	○								
		CCGT 03X102 LFY	0,2																				○	○			○					
		CCGT 03X104 LFY	0,4																				○	○								
		CCGT 04X101 LFY	0,1																				○	○								
		CCGT 04X102 LFY	0,2																				○	○								
		CCGT 04X104 LFY	0,4																				○	○								
		CCGT 03X101 RFY	0,1																				○	○								
		CCGT 03X102 RFY	0,2																				○	○								
		CCGT 03X104 RFY	0,4																				○	○								
		CCGT 04X101 RFY	0,1																				○	○								
		CCGT 04X102 RFY	0,2																				○	○								
		CCGT 04X104 RFY	0,4																				○	○								
Light Cut	 NAG	**CCGT 060202 NAG**	0,2																													●
		CCGT 060204 NAG	0,4																													●
		CCGT 09T302 NAG	0,2																													●
		CCGT 09T304 NAG	0,4																													●
		CCGT 09T308 NAG	0,8																													●
		CCGT 120404 NAG	0,4																													●
		CCGT 120408 NAG	0,8																													●
Light cut	 NSI	**CCGT 09T301M NSI**	<0,1										○							●	●	▲	▲	●	●	●		○		○			
		CCGT 09T302M NSI	<0,2										○							●	●	▲	▲	●	●	●		○					
		CCGT 09T304M NSI	<0,4										○							●	●	▲	▲	●	●	●		○		○			
Light cut	 NSC	**CCGT 0602003 NSC**	0,03																					○	○	○		○		○			
		CCGT 09T3003 NSC	0,03																					●	●	○		○		○			
		CCGT 060201M NSC	<0,1																					○	○	●		○		●			
		CCGT 060202M NSC	<0,2																					●	●	●		●		●			
		CCGT 060204M NSC	<0,4																					●	●	●				●			
		CCGT 080201M NSC	<0,1																							○		○		○			
		CCGT 080202M NSC	<0,2																							○		○		○			
		CCGT 090301M NSC	<0,1																							○		○		○			
		CCGT 090302M NSC	<0,2																							○		○		○			
		CCGT 09T301M NSC	<0,1																					●	●	●		○		●			
		CCGT 09T302M NSC	<0,2																					●	●	●		●		●			
		CCGT 09T304M NSC	<0,4																					●	●	●				●			
		CCGT 09T308M NSC	<0,8																					●	●	●				●			

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

80° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
CC__	L	IC	S	D_1
0602..	6,4	6,35	2,38	2,8
09T3..	9,7	9,525	3,97	4,4
1204..	12,9	12,7	4,76	5,5

⇨ D31 ⇨ E14

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CCMT ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M		Carbide Coated K			Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	NFB	CCMT 060202 NFB	0,2																					○	●	○	○	●				
		CCMT 060204 NFB	0,4																					○	●	○	●	●				
		CCMT 09T304 NFB	0,4																					○	●	○	●	●				
		CCMT 09T308 NFB	0,8																					○	●	○	○	●				
Finishing ~ Light Cut	NFP	CCMT 060202 NFP	0,2																						▲	▲	▲	▲				
		CCMT 060204 NFP	0,4																						▲	▲	▲	▲				
		CCMT 060208 NFP	0,8																						▲	▲	▲	▲				
		CCMT 09T302 NFP	0,2																						▲	▲	▲	▲				
		CCMT 09T304 NFP	0,4																						▲	▲	▲	▲				
		CCMT 09T308 NFP	0,8																						▲	▲	▲	▲				
		CCMT 120404 NFP	0,4																						▲			▲				
		CCMT 120408 NFP	0,8																						▲			▲				
Finishing	NLU	CCMT 060202 NLU	0,2	●	●		▲	▲		●	●	●	○											●	○	○	○	○				
		CCMT 060204 NLU	0,4	●	●		▲	▲		●	●	●	○											●	○	●	○	○				
		CCMT 09T302 NLU	0,2							●														●		●						
		CCMT 09T304 NLU	0,4	●	●		▲	▲		●	●	●	○											●	○	●	○	○				
		CCMT 09T308 NLU	0,8	●	●		▲	▲		●	●	●	○											●	○	○	○	○				
	NLU-W	CCMT 09T304 NLU-W	0,4	●	●		▲	▲		●			●				▲	▲						●	●	●		○				
		CCMT 09T308 NLU-W	0,8	●	●		▲	▲		●			○				▲	▲						●	●	●		○				
Light Cut	NLB	CCMT 060202 NLB	0,2		○	○		▲	▲	○	●	●													●	○		●				
		CCMT 060204 NLB	0,4		○	○		▲	▲	○	●	●													●	●		●				
		CCMT 060208 NLB	0,8		○	○		▲	▲	○	●	●													●	○		●				
		CCMT 09T302 NLB	0,2		○	○		▲	▲	○	●	●													●	○		●				
		CCMT 09T304 NLB	0,4		○	○		▲	▲	○	●	●													●	●		●				
		CCMT 09T308 NLB	0,8		○	○		▲	▲	○	●	●													●	○		●				
Light Cut	NSU	CCMT 060202 NSU	0,2	●	●	●	▲	▲	▲	●	●	●	●				▲	▲			●	▲	▲		●	●	●	○	●				
		CCMT 060204 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●				▲	▲		●	●	▲	▲		●	●	●	○	●				
		CCMT 060208 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●												●	●	●	○	●				
		CCMT 09T302 NSU	0,2	○	●	○		▲	▲	●	●	●	○												●	●	○	●	●				
		CCMT 09T304 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●				▲	▲		●	●	▲	▲		●	●	●	○	●				
		CCMT 09T308 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●				▲	▲		●	●	▲	▲		●	●	●	●	●				
		CCMT 120404 NSU	0,4	●	●	●	▲	▲	▲	●			●				▲	▲							●								
		CCMT 120408 NSU	0,8	●	●	●	▲	▲	▲	●			●				▲	▲							●								

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
C_ _ _	L	IC	S	D_1
0602..	6,4	6,35	2,38	2,8
0803..	8,0	7,94	3,18	3,4
0903..	9,7	9,525	3,18	4,4
09T3..	9,7	9,525	3,97	4,4
1204..	12,9	12,7	4,76	5,5

⇨ E15

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CCMT/-W ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						M			P M	K			H	S	K S	M S	P M	Cermet Coated P				Carbide Uncoated K	S	N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cut	 NUS	**CCMT 09T308 NUS**	0,8			●																									
Light Cut	  NSC	**CCMT 060204 NSC**	0,4		❍																						❍			
		CCMT 080304 NSC	0,4		●			▲																						
		CCMT 090304 NSC	0,4																								❍			
		CCMT 090308 NSC	0,8		❍			▲																						
		CCMT 120408 NSC	0,8		❍			▲	▲																					
Light Cut	  NSK	**CCMT 060204 NSK**	0,4	●	●	●		▲	▲																					
		CCMT 060208 NSK	0,8	❍	●	●		▲	▲																					
		CCMT 060212 NSK	1,2						▲																					
		CCMT 09T304 NSK	0,4	❍	●	●		▲	▲																					
		CCMT 09T308 NSK	0,8	❍	●	●		▲	▲																					
		CCMT 120404 NSK	0,4		●	●		▲	▲																					
		CCMT 120408 NSK	0,8		●	●		▲	▲																					
		CCMT 120412 NSK	1,2					▲																						
Roughing	 NMU	**CCMT 09T304 NMU**	0,4	●	●	●	▲	▲	▲	●	●		●	❍	●	●	▲	▲												
		CCMT 09T308 NMU	0,8	●	●	●	▲	▲	▲	●	●		●	●	●	●	▲	▲												
Roughing		**CCMW 060204**	0,4											❍	❍			▲												
		CCMW 09T304	0,4											❍	❍	❍	▲	▲												
		CCMW 09T308	0,8											❍	●	❍	▲	▲												

● = Euro stock
❍ = Japan stock
▲ = To be replaced by new item

80° Diamond Type | 11° Relief | With Insert Hole



Dimensions (mm)				
CP__	L	IC	S	D_1
0802..	8,0	7,94	2,38	3,4
0903..	9,7	9,525	3,18	4,4
1204..	12,9	12,7	4,76	5,5

⇨ E15

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CPGT ●●●●●● NSD

● G-Class

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated				Carbide Uncoated			
				P						M				K					H	S						P				K	S		N
Finishing ~ Light Cut	 NSD	**CPGT 080202 NSD**	0,2																	○	○								●	●			
		CPGT 080204 NSD	0,4																	○	○					●	○		●	●			
		CPGT 080208 NSD	0,8																							○			○	○			
		CPGT 090302 NSD	0,2																										○	○			
		CPGT 090304 NSD	0,4																	○						○	○		●	●			
		CPGT 090308 NSD	0,8																							○			○	○			
		CPGT 120402 NSD	0,2																										○	○			
		CPGT 120404 NSD	0,4																	○						○			○	○			
		CPGT 120408 NSD	0,8																										○	○			

CPMT ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated																						Cermet Coated				Carbide Uncoated			
				P						M				K					H	S						P				K	S		N
Finishing	 NFB	**CPMT 080204 NFB**	0,4																						○	●	○	○	○				
		CPMT 090304 NFB	0,4																						○	●	○	○	○				
		CPMT 090308 NFB	0,8																						○	●	○	○	○				
Finishing	 NLU	**CPMT 080204 NLU**	0,4	○	○																					○	○	○	○				
		CPMT 090304 NLU	0,4	○	○						○	○														○	○	○	○				
		CPMT 090308 NLU	0,8	○	○						○	○														○	○	○	○				
	 NLU-W	**CPMT 090304 NLU-W**	0,4	○	○																					○	○		○				
		CPMT 090308 NLU-W	0,8	○	○																					○	○		○				
Light Cut	 NLB	**CPMT 080204 NLB**	0,4		○	○		▲	▲	○	○	○														○	○						
		CPMT 090304 NLB	0,4		○	○		▲	▲	○	●	●														○	○		○				
		CPMT 090308 NLB	0,8		○	○		▲		○	●	●														○	○		○				

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

C DIAMOND TYPE
INSERTS FOR TURNING

80° Diamond Type | 11° Relief | With Insert Hole



Dimensions (mm)				
CP_ _	L	IC	S	D_1
0602..	6,4	6,35	2,38	2,8
0802..	8,0	7,94	2,38	3,4
0903..	9,7	9,525	3,18	4,4
09T3..	9,7	9,525	3,97	4,4
1204..	12,9	12,7	4,76	5,5
1604..	16,1	15,875	4,76	6,5

⇨ E15

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

CPMT/-H ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K				Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P				Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cut	 NSU	**CPMT 060204 NSU**	0,4	○																												
		CPMT 060208 NSU	0,8	○																												
		CPMT 080204 NSU	0,4	○	○	○	▲	▲	▲				○												○		○	○				
		CPMT 080208 NSU	0,8	○	○	○	▲	▲	▲				○												○	○	○	○				
		CPMT 090304 NSU	0,4	○	○	○	▲	▲	▲	○	○		○												○	○	○	○				
		CPMT 090308 NSU	0,8	○	●	○	▲	▲	▲	○	○		○												○	○	○	○				
Light Cut	 NUS	**CPMT 060204 NUS**	0,4			●							○																			
		CPMT 080308 NUS	0,8			●							○																			
		CPMT 09T308 NUS	0,8			●							○																			
		CPMH 120408 NUS	0,8			●																										
		CPMH 160408 NUS	0,8										○																			
Light -Medium Cut	 NMU	**CPMT 080204 NMU**	0,4	○	○									○	○																	
		CPMT 080208 NMU	0,8	○	○									○	○																	
		CPMT 090304 NMU	0,4	○	○					○	○			○	○																	
		CPMT 090308 NMU	0,8	○	○					○	○			○	○																	

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

55° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
DC__	L	IC	S	D_1
0702..	7,7	6,35	2,38	2,8
11T3..	11,6	9,525	3,97	4,4

➪ D32–33 ➪ E16–17

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DCGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NFC	**DCGT 070201M NFC**	<0,1																	❍				●	●			❍	❍				
		DCGT 070202M NFC	<0,2																	❍				●	●			❍	❍				
		DCGT 070204M NFC	<0,4																	❍				●	●			❍	❍				
		DCGT 11T301M NFC	<0,1																	❍				●	●			❍	❍				
		DCGT 11T302M NFC	<0,2																	❍				●	●			❍	❍				
		DCGT 11T304M NFC	<0,4																	❍				●	●			❍	❍				
Finishing	 L/R**FX**	**DCGT 0702003 LFX**	0,03																	❍				❍	❍								
		DCGT 070201 LFX	0,1																	❍			▲	●	●	●		❍	●				
		DCGT 070202 LFX	0,2																	❍			▲	●	●	●		❍	●				
		DCGT 070204 LFX	0,4																					●	●	●		●	●				
		DCGT 11T3003 LFX	0,03																	❍			▲	❍	❍								
		DCGT 11T301 LFX	0,1																	❍			▲	●	●	●		❍	●				
		DCGT 11T302 LFX	0,2																	❍			▲	●	●	●		●	●				
		DCGT 11T304 LFX	0,4																					●	●	●		●	●				
		DCGT 0702003 RFX	0,03																	❍				❍	❍								
		DCGT 070201 RFX	0,1																	❍			▲	●	●	●		●	●				
		DCGT 070202 RFX	0,2																	❍			▲	●	●	●		❍	●				
		DCGT 070204 RFX	0,4																					●	●	●		●	●				
		DCGT 11T3003 RFX	0,03																	❍			▲	❍	❍								
		DCGT 11T301 RFX	0,1																	❍			▲	●	●	●		❍	●				
		DCGT 11T302 RFX	0,2																	❍			▲	●	●	●		●	●				
		DCGT 11T304 RFX	0,4																					●	●	●		●	●				
Finishing	 L/R**FYS**	**DCGT 0702003 LFYS**	0,03																					❍									
		DCGT 070201 LFYS	0,1																					❍									
		DCGT 070202 LFYS	0,2																					❍									
		DCGT 070204 LFYS	0,4																					❍									
		DCGT 11T3003 LFYS	0,03																					❍									
		DCGT 11T301 LFYS	0,1																					❍									
		DCGT 11T302 LFYS	0,2																					❍									
		DCGT 11T304 LFYS	0,4																					❍									
		DCGT 0702003 RFYS	0,03																					❍									
		DCGT 070201 RFYS	0,1																					❍									
		DCGT 070202 RFYS	0,2																					❍									
		DCGT 070204 RFYS	0,4																					❍									
		DCGT 11T3003 RFYS	0,03																					❍									
		DCGT 11T301 RFYS	0,1																					❍									
		DCGT 11T302 RFYS	0,2																					❍									
		DCGT 11T304 RFYS	0,4																					❍									

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
DC_ _	L	IC	S	D_1
0702..	7,7	6,35	2,38	2,8
11T3..	11,6	9,525	3,97	4,4

⇨ D32–33 ⇨ E16–17

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DCGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Coated P	Cermet Coated P	Cermet Coated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 LFY	**DCGT 0702003 LFY**	0,03																					○							
		DCGT 070201 LFY	0,1																					○							
		DCGT 070202 LFY	0,2																					○							
		DCGT 070204 LFY	0,4																					○							
		DCGT 11T3003 LFY	0,03																					○							
		DCGT 11T301 LFY	0,1																					○							
		DCGT 11T302 LFY	0,2																					○							
		DCGT 11T304 LFY	0,4																					○	○						
Finishing	 RFY	**DCGT 0702003 RFY**	0,03																		○			○							
		DCGT 070201 RFY	0,1																					○							
		DCGT 070202 RFY	0,2																					○							
		DCGT 070204 RFY	0,4																					○							
		DCGT 11T3003 RFY	0,03																		○			○	○						
		DCGT 11T301 RFY	0,1																					○	○						
		DCGT 11T302 RFY	0,2																					○	○						
		DCGT 11T304 RFY	0,4																					○	○		○				
Finishing ~ Light Cut	 L/RSD	**DCGT 070202 LSD**	0,2																							○		○	○				
		DCGT 070204 LSD	0,4																							○		○	○				
		DCGT 11T304 LSD	0,4																							○		○	○				
		DCGT 11T308 LSD	0,8																							○		○	○				
		DCGT 070202 RSD	0,2																							○		○	○				
		DCGT 070204 RSD	0,4																							○		○	○				
		DCGT 11T304 RSD	0,4																							○		○	○				
		DCGT 11T308 RSD	0,8																							○		○	○				
Light Cut	 NAG	**DCGT 070202 NAG**	0,2																														●
		DCGT 070204 NAG	0,4																														●
		DCGT 11T302 NAG	0,2																														●
		DCGT 11T304 NAG	0,4																														●
		DCGT 11T308 NAG	0,8																														●

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

55° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
DC__	L	IC	S	D_1
0702..	7,7	6,35	2,38	2,8
0902..	9,7	7,94	2,38	3,4
1103..	11,6	9,525	3,18	4,4
11T3..	11,6	9,525	3,97	4,4

➪ D32–33 ➪ E16–17

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DCGT/-W ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M		Carbide Coated K			Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cut	 NSI	**DCGT 070201M NSI**	<0,1										○							●	●	▲	▲	●	●	●		○					
		DCGT 070202M NSI	<0,2										○							●	●	▲	▲	●	●	●		○					
		DCGT 070204M NSI	<0,4										○							●	●	▲	▲	●	●	●		○	○				
		DCGT 11T301M NSI	<0,1										○							●	●	▲	▲	●	●	●		○					
		DCGT 11T302M NSI	<0,2										○							●	●	▲	▲	●	●	●		○					
		DCGT 11T304M NSI	<0,4										○							●	●	▲	▲	●	●	●		○					
		DCGT 11T308M NSI	<0,8										○							●	●	▲	▲	●	●	●		○	○				
Light cut	 NSC	**DCGT 0702003 NSC**	0,03																					○	○	○		○	○				
		DCGT 11T3003 NSC	0,03																					○	○	●		○	○				
		DCGT 070201M NSC	<0,1																					●	●	●		○	●				
		DCGT 070202M NSC	<0,2																					●	●	●		○	●				
		DCGT 070204M NSC	<0,4																					●	●	●		●	●				
		DCGT 090201M NSC	<0,1																									○	○				
		DCGT 090202M NSC	<0,2																									○	○				
		DCGT 110301M NSC	<0,1																									○	○				
		DCGT 110302M NSC	<0,2																							●		○	●				
		DCGT 11T301M NSC	<0,1																					●	●	●		○	●				
		DCGT 11T302M NSC	<0,2																					●	●	●		●	●				
		DCGT 11T304M NSC	<0,4																					●	●	●		●	●				
		DCGT 11T308M NSC	<0,8																					●	●	●		●	●				
Light Cut		**DCGW 070202**	0,2																○														
		DCGW 070204	0,4																○														
		DCGW 070208	0,8																○														
		DCGW 11T302	0,2																○														
		DCGW 11T304	0,4																○														
		DCGW 11T308	0,8																○														

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

D DIAMOND TYPE
INSERTS FOR TURNING

55° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
DC_ _	L	IC	S	D_1
0702..	7,7	6,35	2,38	2,8
11T3..	11,6	9,525	3,97	4,4

⇨ D32–33 ⇨ E16–17

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

DCM_ ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M AC6020M	AC6030M	AC6040M	PM AC630M	K AC4010K	AC4015K	AC420K	AC405K	AC415K	H AC503U	S AC5015S	AC5025S	KS AC510U	MS AC520U	PM AC1030U	AC530U	Cermet Coated P T1500Z	T3000Z	Uncoated P T1000A	T1500A	Carbide Uncoated K G10E	S EH510	EH520	N H1
Finishing	NFB	DCMT 070202 NFB	0,2																						○	●	○	○	●				
		DCMT 070204 NFB	0,4																						○	●	○	●	●				
		DCMT 070208 NFB	0,8																						○	●	●	○	●				
		DCMT 11T302 NFB	0,2																						○	●	●	●	●				
		DCMT 11T304 NFB	0,4																						○	●	●	●	●				
		DCMT 11T308 NFB	0,8																						○	●	●	●	●				
Finishing	NFP	DCMT 070202 NFP	0,2																							▲	▲		▲				
		DCMT 070204 NFP	0,4																							▲	▲	▲	▲				
		DCMT 11T302 NFP	0,2																							▲	▲		▲				
		DCMT 11T304 NFP	0,4																							▲	▲	▲	▲				
		DCMT 11T308 NFP	0,8																							▲	▲	▲	▲				
		DCMT 11T312 NFP	1,2																							▲	▲		▲				
Finishing	NLU	DCMT 070202 NLU	0,2	●	○		▲	▲			●	●	○												●	○	●	○	○				
		DCMT 070204 NLU	0,4	●	●		▲	▲		●	●	●	○												●	○	○	○	○				
		DCMT 11T302 NLU	0,2	●	●		▲	▲		●		●	●												●	○	●	○	○				
		DCMT 11T304 NLU	0,4	●	●		▲	▲		●	●	●	●												●	●	●	○	○				
		DCMT 11T308 NLU	0,8	●	●		▲	▲		●	●	●	●												●	○	●	○	○				
Light Cut	NLB	DCMT 070202 NLB	0,2		○	○		▲	▲	○	●	●														●	●		●				
		DCMT 070204 NLB	0,4		○	○		▲	▲	○	●	●														●	○		●				
		DCMT 070208 NLB	0,8		○	○		▲	▲	○	●	●														●	●		●				
		DCMT 11T302 NLB	0,2		○	○		▲	▲	○	●	●														●	●		●				
		DCMT 11T304 NLB	0,4		○	○		▲	▲	○	●	●														●	●		●				
		DCMT 11T308 NLB	0,8		○	○		▲	▲	○	●	●														●	○		●				
Light Cut	NSU	DCMT 070202 NSU	0,2	●	●	●	▲	▲	▲	●	●	●	○				▲	▲		●	●	▲	▲		●	●	○	●	●				
		DCMT 070204 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●				▲	▲			●	▲	▲		●	●	●	○	●				
		DCMT 070208 NSU	0,8	●	●	●	▲	▲	▲	●	●	○	●				▲	▲							●	●	○	○	○				
		DCMT 11T302 NSU	0,2	●	●	○	▲	▲	▲	●	●	●	○				▲	▲							●	●	○	○	●				
		DCMT 11T304 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●					▲		●	●	▲	▲		●	●	●	○	●				
		DCMT 11T308 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●				▲	▲		●	●	▲	▲		●	●	●	○	●				
Light Cut	NSK	DCMT 070204 NSK	0,4		●	●		▲	▲																								
		DCMT 070208 NSK	0,8		●	●		▲	▲																								
		DCMT 11T304 NSK	0,4		●	●		▲	▲								▲																
		DCMT 11T308 NSK	0,8	●	●	●		▲	▲																								
		DCMT 11T312 NSK	1,2		●			▲										▲															
Roughing	NMU	DCMT 11T304 NMU	0,4	●	●	●	▲	▲	▲	●	●		●	○	●	●	▲	▲															
		DCMT 11T308 NMU	0,8	●	●	●	▲	▲	▲	●	●		●	●	●	●	▲	▲															
Roughing		DCMW 070204	0,4											○	○			▲															
		DCMW 070208	0,8											○	○	○																	
		DCMW 11T304	0,4											○	○	○	▲	▲															
		DCMW 11T308	0,8											●	●		▲	▲															
Finishing		DCMX 11T308 NLUW	0,8	●			▲	▲					●			●		▲															

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

Round Type Inserts | 7° Relief / With Insert Hole



RC--	L	IC	S	D_1
1003	–	10,0	3,18	3,6
10T3	–	10,0	3,97	3,6
12	–	12,0	4,76	4,2
16	–	16,0	6,35	5,2
20	–	20,0	6,35	6,5
25	–	25,0	7,94	7,2
32	–	32,0	9,52	9,5

(M0: IC is metric)

Lever lock holders for RCMX
⇨ D34–35

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

RCMT ●●●●M0 ●-■■

● M-Class Bumpy Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M			Carbide Coated K			Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M		Cermet Coated P				Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing	 NRX	**RCMT 1003M0 NRX**	–	●	●	○	▲	▲	▲				○																				
		RCMT 10T3M0 NRX	–	●	●	●	▲	▲	▲				●																				
		RCMT 1204M0 NRX	–	●	●	●	▲	▲	▲				●								●												
		RCMT 1606M0 NRX	–	●	●	●	▲	▲	▲				●								●												
		RCMT 2006M0 NRX	–	●	●	●	▲	▲	▲				●								●												
		RCMT 2507M0 NRX	–	○	○	○	▲	▲	▲				●																				
		RCMT 3209M0 NRX	–				▲																										
Roughing	 NRH	**RCMT 1204M0 NRH**	–	○	○	○	▲	▲	▲																								
		RCMT 1606M0 NRH	–	○	●	○	▲	▲	▲																								
		RCMT 2006M0 NRH	–	○	○	○	▲	▲	▲																								

RCMX ●●●●M0 ●-■■

● M-Class Grooved Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M			Carbide Coated K			Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M		Cermet Coated P				Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Roughing	 NRP	**RCMX 1003M0 NRP**	–	○	●	●	▲	▲	▲				○	○	○																		
		RCMX 1204M0 NRP	–	○	●	●	▲	▲	▲					○	○			▲		○		▲												
		RCMX 1606M0 NRP	–	○	●	●	▲	▲	▲				○	○	○																		
		RCMX 2006M0 NRP	–	○	●	●	▲	▲	▲				○							○		▲												
		RCMX 2507M0 NRP	–	○	○	○		▲	▲																								
		RCMX 3209M0 NRP	–	○	○		▲	▲	▲																								

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type

7° Relief
With Insert Hole



Dimensions (mm)				
SC_ _	L	IC	S	D_1
0702..	7,94	7,94	2,38	3,4
0903..	9,525	9,525	3,18	4,4
09T3..	9,525	9,525	3,97	4,4
1204..	12,7	12,7	4,76	5,5

⇨ D36

"S … SSKC" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SCGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						M			P M		K			H	S			K S	M S	P M	Cermet Coated P				Cermet Uncoated K			Carbide Uncoated S		N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1		
Finishing	 L/RFX	**SCGT 09T302 LFX**	0,2																				○	○										
		SCGT 09T304 LFX	0,4																				○	○										
		SCGT 120404 LFX	0,4																				○	○										
		SCGT 09T302 RFX	0,2																				○	○										
		SCGT 09T304 RFX	0,4																				○	○										
		SCGT 120404 RFX	0,4																				○	○										
Light Cut	 NSC	**SCGT 070201M NSC**	<0,1																				○	○			○	○						
		SCGT 070202M NSC	<0,2																				○	○			○	○						
		SCGT 090301M NSC	<0,1																								○	○						
		SCGT 090302M NSC	<0,2																								○	○						
		SCGT 09T301M NSC	<0,1																				○	○			○	○						
		SCGT 09T302M NSC	<0,2																				○	○			○	○						

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

90° Square Type | 7° Relief | With Insert Hole



Dimensions (mm)				
SC_ _	L	IC	S	D_1
09T3..	9,525	9,525	3,97	4,4
1204..	12,7	12,7	4,76	5,5

⇨ D36

"S … SSKC" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SCMT/-W ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M AC6020M	AC6030M	AC6040M	P/M AC630M	K AC4010K	AC4015K	AC420K	AC405K	AC415K	H AC503U	S AC5015S	AC5025S	K/S AC510U	M/S AC520U	P/M AC1030U	AC530U	Cermet Coated P T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated K G10E	S EH510	EH520	N H1
Finishing	 NFB	SCMT 09T304 NFB	0,4																						○	●	○	○	○				
		SCMT 09T308 NFB	0,8																						○	●	○	○	○				
Finishing	 NFP	SCMT 09T304 NFP	0,4																							▲		▲	▲				
		SCMT 09T308 NFP	0,8																							▲		▲	▲				
		SCMT 120404 NFP	0,4																										▲				
Finishing	 NLU	SCMT 09T304 NLU	0,4	○	○		▲				○	○														○	○		○				
		SCMT 09T308 NLU	0,8	●	○		▲				○															○	○	○	○				
		SCMT 120412 NLU	1,2		●																												
Light Cut	 NLB	SCMT 09T304 NLB	0,4		○	○		▲	▲	○	○	○														○	○		○				
		SCMT 09T308 NLB	0,8		○	○		▲	▲	○	○	○														○	○		○				
Light Cut	 NSU	SCMT 09T304 NSU	0,4	●	●	●	▲	▲		●	●		○				▲	▲		●	●	▲	▲		●								
		SCMT 09T308 NSU	0,8	●	●	●	▲	▲	▲	●	●	○	●				▲	▲		●	●	▲	▲		●								
		SCMT 120404 NSU	0,4	○	●	●	▲	▲	▲	●			●				▲	▲							●								
		SCMT 120408 NSU	0,8	●	●	●	▲	▲	▲	●			●				▲	▲							●								
Light Cut	 NSK	SCMT 09T304 NSK	0,4		●	●		▲	▲																								
		SCMT 09T308 NSK	0,8		●	●		▲	▲																								
		SCMT 120404 NSK	0,4		●			▲																									
		SCMT 120408 NSK	0,8		●	●		▲	▲																								
		SCMT 120412 NSK	1,2		●		▲	▲																									
Light-Medium Cut	 NMU	SCMT 09T308 NMU	0,8	○	●	●	▲	▲	▲	○	●		○	○	○	●	▲	▲															
		SCMT 120408 NMU	0,8	●	●	●	▲	▲	▲				○	○	○	●	▲	▲															
		SCMT 120412 NMU	1,2		●		▲	▲									▲	▲															
		SCMW 09T308	0,8											○	○	○		▲															
		SCMW 120408	0,8											○	○	○																	
		SCMW 120412	1,2											○	○	○																	

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 11° Relief | With Insert Hole



Dimensions (mm)				
SP_ _	L	IC	S	D_1
0602..	6,35	6,35	2,38	2,8
0703..	7,94	7,94	3,18	3,4
0903..	9,525	9,525	3,18	3,4
09T3..	9,525	9,525	3,97	4,4
1204..	12,7	12,7	4,76	5,5
1504..	15,875	15,875	4,76	6,5

⇨ E18

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SPMT/-H ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M AC6020M	AC6030M	AC6040M	PM AC630M	K AC4010K	AC4015K	AC420K	AC405K	AC415K	H AC503U	S AC5015S	AC5025S	KS AC510U	MS AC520U	AC1030U	PM AC530U	Cermet Coated P T1500Z	T3000Z	Uncoated T1000A	T1500A	Carbide Uncoated K G10E	S EH510	EH520	N H1
Finishing	NFB	**SPMT 090304 NFB**	0,4																						○	●	○	○	○				
		SPMT 090308 NFB	0,8																						○	●	○	○	○				
Finishing	NLU	**SPMT 090304 NLU**	0,4	○	○						○																○	○	○				
		SPMT 090308 NLU	0,8	○	○						○																○	○	○				
Finishing	NFK	**SPMT 090304 NFK**	0,4																										●				
Light Cut	NUS	**SPMT 060204 NUS**	0,4										○													○	○						
		SPMT 070308 NUS	0,8										○													○	○						
		SPMT 09T308 NUS	0,8										○																				
Light Cut	NUS	**SPMH 090308 NUS**	0,8										○																				
		SPMH 120408 NUS	0,8										○																				
		SPMH 150408 NUS	0,8										○																				
Light - Medium Cut	NLB	**SPMT 090304 NLB**	0,4		○	○		▲	▲	○	○	○																					
		SPMT 090308 NLB	0,8		○	○		▲	▲	○	○	○																					
Light - Medium Cut	NSF	**SPMT 090304 NSF**	0,4		○	○		▲	▲																								
		SPMT 090308 NSF	0,8		○	●		▲	▲																								

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

90° Square Type

11° Relief
With Insert Hole



Dimensions (mm)				
SP_ _	L	IC	S	D_1
0703..	7,94	7,94	3,18	3,4
0903..	9,525	9,525	3,18	3,4

⇨ E18

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SPGW ●●●●●●

● G-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M		Carbide Coated K					Carbide Coated H	Carbide Coated S			Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M		Cermet Coated P				Cermet Uncoated P				Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N	
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cut		**SPGW 090304 T**	0,4																									●										
		SPGW 070304	0,4																									○										
		SPGW 090304	0,4																									○										

SPGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M		Carbide Coated K					Carbide Coated H	Carbide Coated S			Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M		Cermet Coated P				Cermet Uncoated P				Carbide Uncoated K	Carbide Uncoated S		Carbide Uncoated N	
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing - Light Cut	 L/RSD	**SPGT 090302 LSD**	0,2																							○		○	○									
		SPGT 090304 LSD	0,4																							○	○	○										
		SPGT 090308 LSD	0,8																							○	○	○	○									
		SPGT 090302 RSD	0,2																							○		○	○									
		SPGT 090304 RSD	0,4																							○		○	○									
		SPGT 090308 RSD	0,8																							○		○	○									

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

S SQUARE TYPE
INSERTS FOR TURNING

90° Square Type | 11° Relief | Without Insert Hole



Dimensions (mm)				
SP_ _	L	IC	S	D_1
0903..	9,525	9,525	3,18	-
1203..	12,7	12,7	3,18	-

"S… CSKP…09/12" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

SPMR ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing		**SPMR 090304 NFK**	0,4																						○		○	●				
		SPMR 090308 NFK	0,8																						○	○	○	○				
		SPMR 120304 NFK	0,4																						○		○	○				
		SPMR 120308 NFK	0,8																						○		○	○				
Light- Medium Cut		**SPMR 090304 NSF**	0,4		○	○		▲	▲																							
		SPMR 090308 NSF	0,8		●	○		▲	▲																							
		SPMR 120304 NSF	0,4		●	○		▲	▲																							
		SPMR 120308 NSF	0,8		●	●		▲	▲																							
		SPMR 120312 NSF	1,2		●			▲																								
		**SPMR 090304 NUJ**	0,4		○																											
		SPMR 090308 NUJ	0,8		○	○																										
		SPMR 120304 NUJ	0,4		○			▲																								
		SPMR 120308 NUJ	0,8		○	○																										

SP_N ●●●●●●

● G/M-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Medium Cut		**SPGN 090304**	0,4																								○	●				
		SPGN 090308	0,8																								○	●				○
		SPGN 120304	0,4																								○	○				
		SPGN 120308	0,8																								○	○	○			
Medium Cut		**SPMN 090304**	0,4											○	○													○	○				
		SPMN 090308	0,8											○	○													○	○				
		SPMN 120304	0,4											○	○																		
		SPMN 120308	0,8											○	○													●	○				
		SPMN 120312	1,2											○	○										○			○	○				

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

60° Triangle Type | 5° Relief | With Insert Hole



Dimensions (mm)				
TB__	L	IC	S	D_1
0601..	6,9	3,97	1,59	2,2

⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TBGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 L/RFW	**TBGT 060102 LFW** **TBGT 060104 LFW**	0,2 0,4																						○ ○			○ ○				
		TBGT 060102 RFW **TBGT 060104 RFW**	0,2 0,4																						○ ○			○ ○				
Finishing	 L/RFX	**TBGT 060102 LFX** **TBGT 060104 LFX**	0,2 0,4																	○ ○		▲ ▲		● ●	○ ○								
		TBGT 060102 RFX **TBGT 060104 RFX**	0,2 0,4																	○ ○		▲ ▲		● ●	○ ○								
Finishing	 L/RFY	**TBGT 060101 LFY** **TBGT 060102 LFY** **TBGT 060104 LFY**	0,1 0,2 0,4																					○ ○ ○	○ ○ ○			○ ○	○				
		TBGT 060101 RFY **TBGT 060102 RFY** **TBGT 060104 RFY**	0,1 0,2 0,4																					○ ○ ○				○ ○ ○	○ ○				
Finishing-Light Cut	 L/RW	**TBGT 060102 LW** **TBGT 060104 LW**	0,2 0,4																					● ●	● ○	○ ○	○	○ ○	● ●				
		TBGT 060102 RW **TBGT 060104 RW**	0,2 0,4																					● ●	○ ○	○ ○		○ ○	● ●				

TBGW ●●●●●●

● G-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cut		**TBGW 060102** **TBGW 060104**	0,2 0,4																									○ ○				

●= Euro stock
○= Japan stock
▲= To be replaced by new item

60° Triangle Type

7° Relief
With Insert Hole



TC_ _	L	IC	S	D_1
0802..	8,2	4,76	2,38	2,3
0902..	9,62	5,56	2,38	2,5
1102..	11,0	6,35	2,38	2,8
16T3..	16,5	9,525	3,97	4,3

Dimensions (mm)

P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

TCGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated: P	P	P	P	P	P	M	M	M	P/M	K	K	K	K	K	H	S	S	K/S	M/S	P/M	P/M	Cermet Coated: P	Cermet Coated: P	Cermet Uncoated: P	Cermet Uncoated: P	Carbide Uncoated: K	S	S	N
Finishing	 L/RFX	TCGT 090201 LFX	0,1																					○									
		TCGT 090202 LFX	0,2																					○	○								
		TCGT 110201 LFX	0,1																					○	○								
		TCGT 110202 LFX	0,2																					○									
		TCGT 090201 RFX	0,1																					○									
		TCGT 090202 RFX	0,2																					○									
		TCGT 110201 RFX	0,1																					○									
		TCGT 110202 RFX	0,2																					○	○								
Finishing	 L/RFY	TCGT 090201 LFY	0,1																					○									
		TCGT 090202 LFY	0,2																					○	○								
		TCGT 110201 LFY	0,1																					○									
		TCGT 110202 LFY	0,2																					○	○								
		TCGT 090201 RFY	0,1																					○									
		TCGT 090202 RFY	0,2																					○									
		TCGT 110201 RFY	0,1																					○									
		TCGT 110202 RFY	0,2																					○									
Light cut	 NSI	TCGT 110204M NSI	<0,4										○							●	●	▲	▲	●	●								
Light Cut	 NAG	TCGT 110202 NAG	0,2																														●
		TCGT 110204 NAG	0,4																														●
		TCGT 16T304 NAG	0,4																														●
		TCGT 16T308 NAG	0,8																														●
Light Cut	 NSC	TCGT 080201M NSC	<0,1																					○	○			○	○				
		TCGT 080202M NSC	<0,2																					○	●			○	○				
		TCGT 090201M NSC	<0,1																					○	○			○	○				
		TCGT 090202M NSC	<0,2																					○	○			●	●				
		TCGT 110201M NSC	<0,1																					○	○			○	○				
		TCGT 110202M NSC	<0,2																					●	●			●	●				
		TCGT 110204M NSC	<0,4																					●	●				●				
		TCGT 110301M NSC	<0,1																									○	○				
		TCGT 110302M NSC	<0,2																									○	○				

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

Pos. Inserts
C
D
K
R
S
T
V
W

60° Triangle Type | 7° Relief | With Insert Hole



Dimensions (mm)				
TC_ _	L	IC	S	D_1
0902..	9,6	5,56	2,38	2,5
1102..	11,0	6,35	2,38	2,8
16T3..	16,5	9,525	3,97	4,3

⇨ D37 ⇨ E19

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TCMT/-W ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K				Carbide Coated H	Carbide Coated S			Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P				Cermet Uncoated K	Cermet Uncoated S	Cermet Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NFB	**TCMT 110204 NFB**	0,4																						○	●	○	○	●				
		TCMT 110208 NFB	0,8																						○	●	●	○	●				
Finishing	  NFP	**TCMT 090202 NFP**	0,2																										▲				
		TCMT 090204 NFP	0,4																										▲				
		TCMT 090208 NFP	0,8																										▲				
		TCMT 110202 NFP	0,2																						▲				▲				
		TCMT 110204 NFP	0,4																						▲	▲			▲				
		TCMT 110208 NFP	0,8																						▲	▲			▲				
		TCMT 16T304 NFP	0,4																						▲	▲			▲				
		TCMT 16T308 NFP	0,8																						▲	▲			▲				
Finishing	 NLU	**TCMT 110204 NLU**	0,4	○	●		▲	▲			○														●	○	○	○	○				
		TCMT 110208 NLU	0,8	○	○			▲			○														○	○	○	○	○				
Light Cut	 NLB	**TCMT 110204 NLB**	0,4		○	○		▲	▲	○	○	○														○	○						
		TCMT 110208 NLB	0,8		○	○		▲	▲	○	○	○													○	○						
Light Cut	 NSU	**TCMT 110204 NSU**	0,4	●	●	●	▲	▲	▲	●	●	●	●				▲	▲							●	●	●						
		TCMT 110208 NSU	0,8	●	●	●	▲	▲	▲	●	●	○					▲	▲							○								
		TCMT 16T304 NSU	0,4	●	●	●	▲	▲	▲	●	●		●				▲	▲							●								
		TCMT 16T308 NSU	0,8	●	●	●	▲	▲	▲	●	●	○	●				▲	▲							●								
Light Cut	 NSK	**TCMT 110204 NSK**	0,4	○	●	●		▲	▲																								
		TCMT 110208 NSK	0,8	○	●	●		▲	▲																								
		TCMT 16T304 NSK	0,4	○	●	●		▲	▲																								
		TCMT 16T308 NSK	0,8	○	●	●		▲	▲																								
		TCMT 16T312 NSK	1,2		●			▲										▲															
Light Cut		**TCMW 110204**	0,4											○	○		▲	▲															
		TCMW 110208	0,8											○	○		▲	▲															
		TCMW 16T304	0,4											○	○		▲	▲															
		TCMW 16T308	0,8											○	○	○	▲	▲															
		TCMW 16T312	1,2											○	○			▲															

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

T TRIANGLE TYPE
INSERTS FOR TURNING

60° Triangle Type | 11° Relief | With Insert Hole



Dimensions (mm)				
TP__	L	IC	S	D_1
0802..	8,2	4,76	2,38	2,4
0902..	9,6	5,56	2,38	2,8
1103..	11,0	6,35	3,18	3,4
1603..	16,5	9,525	3,18	4,4

⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TPGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P						Carbide Coated M			Carbide Coated P/M	Carbide Coated K				Carbide Coated H	Carbide Coated S		Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P		Cermet Uncoated P		Carbide Coated K	Carbide Uncoated S		Carbide Uncoated N
				AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NFC	**TPGT 110302M NFC**	<0,2																				○				○	○				
		TPGT 110304M NFC	<0,4																				○	○			○	○				
Finishing	 L/RFW	**TPGT 080202 LFW**	0,2																						○		○	○				
		TPGT 080204 LFW	0,4																						○		○					
		TPGT 110202 LFW	0,2																						○		○	○				
		TPGT 110204 LFW	0,4																						○		○	○				
		TPGT 080202 RFW	0,2																						○		○	○				
		TPGT 080204 RFW	0,4																						○		○	○				
		TPGT 110202 RFW	0,2																						○		○	○				
		TPGT 110204 RFW	0,4																						○		○	○				
Finishing	 L/RFX	**TPGT 080202 LFX**	0,2																				○	○								
		TPGT 080204 LFX	0,4																				○	○								
		TPGT 090204 LFX	0,4																								○	○				
		TPGT 110204 LFX	0,2																	○												
		TPGT 110302 LFX	0,2																		○		▲	●	●							
		TPGT 110304 LFX	0,4																		○		▲	●	●							
		TPGT 110308 LFX	0,8																					○								
		TPGT 160304 LFX	0,4																					○								
		TPGT 160308 LFX	0,8																					○								
		TPGT 080202 RFX	0,2																					○	●							
		TPGT 080204 RFX	0,4																					○								
		TPGT 110202 RFX	0,2																	○												
		TPGT 110302 RFX	0,2																		○		▲	●	○							
		TPGT 110304 RFX	0,4																		○		▲	●	●							
		TPGT 110308 RFX	0,8																		○		▲	○								
		TPGT 160304 RFX	0,4																					○								
		TPGT 160308 RFX	0,8																					○								

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

60° Triangle Type | 11° Relief | With Insert Hole



Dimensions (mm)				
TP_ _	L	IC	S	D_1
0802..	8,2	4,76	2,38	2,4
0902..	9,6	5,56	2,38	2,8
1102..	11,0	6,35	2,38	2,8
1103..	11,0	6,35	3,18	3,4
1603..	16,5	9,525	3,18	4,4

⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TPGT/-W ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated T1500Z	Cermet Coated T3000Z	Cermet Uncoated T1000A	Cermet Uncoated T1500A	Carbide Uncoated G10E	Carbide Uncoated EH510	Carbide Uncoated EH520	H1
Finishing	 L/RFY	**TPGT 0802003 LFY**	0,03																				○									
		TPGT 080201 LFY	0,1																				○									
		TPGT 080202 LFY	0,2																		○		○				○	○				
		TPGT 080204 LFY	0,4																				○	○			○	○				
		TPGT 090201 LFY	0,1																				○									
		TPGT 090202 LFY	0,2																				○									
		TPGT 090204 LFY	0,4																				○									
		TPGT 110202 LFY	0,2																								○	○				
		TPGT 110204 LFY	0,4																								○	○				
		TPGT 110208 LFY	0,8																									○				
		TPGT 1103003 LFY	0,03																						○								
		TPGT 110301 LFY	0,1																						○	○							
		TPGT 110302 LFY	0,2																		○				○	○	○	○	○	○			
		TPGT 110304 LFY	0,4																						○		○	○	○	○			
		TGPT 110308 LFY	0,8																						○				○				
		TPGT 160302 LFY	0,2																						○								
		TPGT 160304 LFY	0,4																						○								
		TPGT 160308 LFY	0,8																						○								
		TPGT 0802003 RFY	0,03																						○								
		TPGT 080201 RFY	0,1																						○								
		TPGT 080202 RFY	0,2																						○	○			○	○			
		TPGT 080204 RFY	0,4																						○				○	○			
		TPGT 090201 RFY	0,1																						○								
		TPGT 090202 RFY	0,2																						○								
		TPGT 090204 RFY	0,4																						○								
		TPGT 110202 RFY	0,2																										○	○			
		TPGT 110204 RFY	0,4																										○	○			
		TPGT 110208 RFY	0,8																											○			
		TPGT 1103003 RFY	0,03																						○								
		TPGT 110301 RFY	0,1																						○	○							
		TPGT 110302 RFY	0,2																						○		○	○	○	○			
		TPGT 110304 RFY	0,4																						○		○	○	○	○			
		TPGT 110308 RFY	0,8																						○				○				
		TPGT 160302 RFY	0,2																						○								
		TPGT 160304 RFY	0,4																						○								
		TPGT 160308 RFY	0,8																						○								
Light Cut		**TPGW 080202**	0,2																										○	○			
		TPGW 110302	0,2																							○							
		TPGW 110304	0,4																							○			○	○			
		TPGW 110308	0,8																										○	○			

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

T TRIANGLE TYPE
INSERTS FOR TURNING

60° Triangle Type — 11° Relief, With Insert Hole



Dimensions (mm)				
TP_ _	L	IC	S	D_1
0802..	8,2	4,76	2,38	2,4
1103..	11,0	6,35	3,18	3,4
1604..	16,5	9,525	4,76	4,4

⇨ E20

- **P** Steel
- **M** Stainless Steel
- **K** Cast Iron
- **N** Non-Ferrous Metals
- **S** Super Alloy
- **H** Hardened Steel

TPGT/-X ●●●●●● ●-■■

● G-Class Handed Chipbreaker

Grade groups: Carbide Coated (P: AC8015P–AC830P; M: AC6020M–AC6040M; P/M: AC630M; K: AC4010K–AC415K; H: AC503U; S: AC5015S, AC5025S; K/S: AC510U; M/S: AC520U; P/M: AC1030U, AC530U) · Cermet Coated (P: T1500Z, T3000Z) · Cermet Uncoated (T1000A, T1500A) · Carbide Uncoated (K: G10E; S: EH510, EH520; N: H1)

Application: Finishing-Light Cutting — Shape: L/RW



ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
TPGT 080202 LW	0,2																					○	○				●				
TPGT 080204 LW	0,4																					●	●				●				
TPGT 110302 LW	0,2																					●	●				●				
TPGT 110304 LW	0,4																					●	●				●				
TPGT 160402 LW	0,2																										●				
TPGT 160404 LW	0,4																										●				
TPGT 080202 RW	0,2																					○					●	○			
TPGT 080204 RW	0,4																					●	●				●				
TPGT 110302 RW	0,2																					●	●				●				
TPGT 110304 RW	0,4																					●	●				●				
TPGT 160404 RW	0,4																										●				

Application: Finishing-Light Cutting — Shape: L/RSD



ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
TPGT 110302 LSD	0,2																					○	○	○	○	○	●	○			
TPGT 110304 LSD	0,4																	○		▲		○	○	○	○	○	●	○			
TPGT 110308 LSD	0,8																					○	○	○	○	○	○				
TPGT 160402 LSD	0,2																									○	●				
TPGT 160404 LSD	0,4																	○		▲				○	○	○	●				
TPGT 160408 LSD	0,8																							○		○					
TPGT 110302 RSD	0,2																					○	○	○		○	●				
TPGT 110304 RSD	0,4																					○	○	○	○	○	●				
TPGT 110308 RSD	0,8																					○		○		○	○				
TPGT 160402 RSD	0,2																									○	○				
TPGT 160404 RSD	0,4																							○	○	○	●				
TPGT 160408 RSD	0,8																							○		○	●				

Application: Finishing-Light Cutting — Shape: L/RSDW



ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
TPGX 110304 L-SDW	0,4																								●						
TPGX 110308 L-SDW	0,8																								○						
TPGX 160404 L-SDW	0,4																							○			○				
TPGX 160408 L-SDW	0,8																							○			○				
TPGX 110304 R-SDW	0,4																								○						
TPGX 110308 R-SDW	0,8																								○						
TPGX 160404 R-SDW	0,4																							○			○				
TPGX 160408 R-SDW	0,8																							○			○				





(Note) The cutting point position of the SDW type does not follow the ISO standard.
Wenn using on a boring holder with a 93° approach angle, there is a need to revise the cutting point position (refer to right table) relative to using standard inserts.

RE	Compensation (mm)	
	X (Diam. change)	Z
0,4	+0,12 (Ø: +0,24)	-0,02
0,8	+0,12 (Ø: +0,24)	-0,02

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

60° Triangle Type | 11° Relief | With Insert Hole



Dimensions (mm)				
TP__	L	IC	S	D_1
0802..	8,2	4,76	2,38	2,4
0902..	9,6	5,56	2,38	2,8
1103..	11,0	6,35	3,18	3,4
1603..	16,5	9,525	3,18	4,4
1604..	16,5	9,525	4,76	4,4

⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TPMT ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Uncoated P	Carbide Coated K	Carbide Coated S	Carbide Coated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	 NFB  Depth of cut (mm) / Feed rate (mm/rev)	**TPMT 080202 NFB**	0,2																						○	●	○	○	○				
		TPMT 080204 NFB	0,4																						○	●	○	○	○				
		TPMT 090202 NFB	0,2																						○	●	○	○	○				
		TPMT 090204 NFB	0,4																						○	●		○	○				
		TPMT 110302 NFB	0,2																						○	●	○	○	○				
		TPMT 110304 NFB	0,4																						○	●	○	○	○				
		TPMT 110308 NFB	0,8																						○	●	○	○	○				
		TPMT 160304 NFB	0,4																						○	○	○	○	○				
		TPMT 160308 NFB	0,8																						○			○					
		TPMT 160404 NFB	0,4																						○	●	○	○	○				
		TPMT 160408 NFB	0,8																						○	●	○	○	○				
Light Cut	 NLB  Depth of cut (mm) / Feed rate (mm/rev)	**TPMT 080202 NLB**	0,2		○	○		▲	▲	○	○	○													○	○							
		TPMT 080204 NLB	0,4		○	○		▲	▲	○	○	○													○	○							
		TPMT 090202 NLB	0,2		○	○		▲	▲	○	●	●													○	○		○					
		TPMT 090204 NLB	0,4		○	○		▲	▲	○	●	●													○	○		○					
		TPMT 110302 NLB	0,2		○	○		▲	▲	○	●	●													○	○		○					
		TPMT 110304 NLB	0,4		○	○		▲	▲	○	●	●													○	○		○					
		TPMT 110308 NLB	0,8		○	○		▲	▲	○	●	●													○	○		○					
		TPMT 160304 NLB	0,4		○	○		▲	▲	○	○	○													○	○							
		TPMT 160308 NLB	0,8		○	○		▲	▲	○	○	○													○	○							
		TPMT 160404 NLB	0,4		○	○		▲	▲	○	○	○													○	○							
		TPMT 160408 NLB	0,8		○	○		▲	▲	○	○	○													○	○							
Finishing	 NFK  Depth of cut (mm) / Feed rate (mm/rev)	**TPMT 110304 NFK**	0,4																									●	●				
		TPMT 110308 NFK	0,8																									○	●				
		TPMT 160404 NFK	0,4																									●	●				
		TPMT 160408 NFK	0,8																									●	●				
Finishing	 NLU  Depth of cut (mm) / Feed rate (mm/rev)	**TPMT 080202 NLU**	0,2								●	●													○			○	○				
		TPMT 080204 NLU	0,4	●			▲				●	●													○		●	○	○				
		TPMT 090202 NLU	0,2	○	○			▲																		○	○	○	○				
		TPMT 090204 NLU	0,4	○	○			▲																		○	○	○					
		TPMT 110302 NLU	0,2									●														○		○	○				
		TPMT 110304 NLU	0,4	●	○		▲				●	●	○												●	○	○	○	○				
		TPMT 110308 NLU	0,8	●	○		▲				●	●	○												○	○	○	○	○				

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

T TRIANGLE TYPE
INSERTS FOR TURNING

60° Triangle Type | 11° Relief | With Insert Hole



Dimensions (mm)				
TP_ _	L	IC	S	D_1
0802..	8,2	4,76	2,38	2,4
1103..	11,0	6,35	3,18	3,4
1604..	16,5	9,525	4,76	4,4

⇨ E20

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TPMT ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Coated P	Cermet Coated P	Cermet Coated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cut		**TPMT 080202 NSU**	0,2							○	●	●														○	○						
		TPMT 080204 NSU	0,4							○	●	●	○												○			○	○				
		TPMT 110302 NSU	0,2	○	○	○		▲	▲	○	●	●													○	○		○	○				
		TPMT 110304 NSU	0,4	●	●	○	▲	▲	▲	●	●	●	●				▲	▲							●	○	○	○	●				
		TPMT 110308 NSU	0,8	●	●	○	▲	▲	▲	●	●	●	○				▲	▲							○	○	○	○	●				
		TPMT 160404 NSU	0,4	●	○	○	▲	▲	▲	●	○		●				▲	▲							●	○	○		○	●				
		TPMT 160408 NSU	0,8	●	○	○	▲	▲	▲	●	○		●				▲	▲							●	○	○		○	●				
Light -Medium Cut		**TPMT 110304 NMU**	0,4	○	○			▲		○	●		○	○	○																		
		TPMT 110308 NMU	0,8	○	○			▲		○	●		○	○	○																		
		TPMT 160404 NMU	0,4	○	○			▲		○	○			○	○																		
		TPMT 160408 NMU	0,8	○	○			▲		○	○			○	○																		

TPMT/H ●●●●●● NSF

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated M	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Carbide Coated P/M	Cermet Coated P	Cermet Coated P	Cermet Coated P	Cermet Coated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light -Medium Cut		**TPMH 110304 NSF**	0,4		●	●		▲	▲																								
		TPMH 110308 NSF	0,8		●	●		▲	▲																								
		TPMT 160404 NSF	0,4		○	●		▲	▲																								
		TPMT 160408 NSF	0,8		●	●		▲	▲																								

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

60° Triangle Type | 5°/11° Relief | Without Insert Hole



Dimensions (mm)				
TP/TB_	L	IC	S	D_1
0601..	6,9	3,97	1,59	-
0902..	9,6	5,56	2,38	-
1103..	11,0	6,35	3,18	-
1603..	16,5	9,525	3,18	-

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

TPGR ●●●●●● ●-■

● G-Class Handed Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing-Light Cut	 L-W	**TPGR 090202 LW**	0,2																									○				
		TPGR 090204 LW	0,4																									○				
		TPGR 090208 LW	0,8																									○				
		TPGR 110302 LW	0,2																						○		○	○				
		TPGR 110304 LW	0,4																						○		○	●				
		TPGR 110308 LW	0,8																						○		○	○				
		TPGR 160302 LW	0,2																						○		○	○				
		TPGR 160304 LW	0,4																						○		○	●				
		TPGR 160308 LW	0,8																						○		○	●				
Finishing-Light Cut	 R-W	**TPGR 090202 RW**	0,2																									○				
		TPGR 090204 RW	0,4																									○				
		TPGR 090208 RW	0,8																									○				
		TPGR 110302 RW	0,2																						○		○	○				
		TPGR 110304 RW	0,4																						○		○	●				
		TPGR 160302 RW	0,2																						○		○	○				
		TPGR 160304 RW	0,4																						○		○	●				
		TPGR 160308 RW	0,8																						○		○	●				

TBG_ ●●●●●● ●-■

● G-Class No Chipbreaker/ Handed Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing - Light-Cut		**TBGN 060104**	0,4																									○				
		**TBGR 060104 LW**	0,4																									○				

TPGN ●●●●●●

● G-Class No Chipbreaker

Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Light Cut		**TPGN 090202**	0,2																									○				
		TPGN 090204	0,4																									○				
		TPGN 090208	0,8																									○				○
		TPGN 110302	0,2																									○				○
		TPGN 110304	0,4																									○	○			○
		TPGN 110308	0,8																									○				
		TPGN 160302	0,2																									○				
		TPGN 160304	0,4																									○	○			
		TPGN 160308	0,8																									○				
		TPGN 160312	1,2																										○			

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

60° Triangle Type
11°/20° Relief
Without Insert Hole



Dimensions (mm)				
TP_ _	L	IC	S	D1
0902..	9,6	5,56	2,38	-
1103..	11,0	6,35	3,18	-
1603..	16,5	9,525	3,18	-
2204..	22,0	12,7	4,76	-

P Steel
M Stainless Steel
K Cast Iron
N Non-Ferrous Metals
S Super Alloy
H Hardened Steel

TPMR ●●●●●● ●-■■

● M-Class







Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated: P	P	P	P	P	P	M	M	M	P/M	K	K	K	K	K	H	S	S	K/S, M/S	K/S, M/S	P/M	P/M	Cermet Coated: P	P	Cermet Uncoated: P	P	Carbide Uncoated: K	S	S	N
Finishing	NFK	TPMR 090204 NFK	0,4																										○				
Finishing	NFK	TPMR 110302 NFK	0,2																										●				
Finishing	NFK	TPMR 110304 NFK	0,4																									○	●				
Finishing	NFK	TPMR 110308 NFK	0,8																										●				
Finishing	NFK	TPMR 160304 NFK	0,2																										●				
Finishing	NFK	TPMR 160308 NFK	0,4																								○	○	●				
Finishing	NFK	TPMR 160312 NFK	1,2																										○				
Light-Medium Cut	NSF	TPMR 110304 NSF	0,4		●	●		▲	▲																								
Light-Medium Cut	NSF	TPMR 110308 NSF	0,8	○	●	●		▲	▲																								
Light-Medium Cut	NSF	TPMR 160304 NSF	0,4		●	●		▲	▲																								
Light-Medium Cut	NSF	TPMR 160308 NSF	0,8	○	●	●		▲	▲																								
Light-Medium Cut	NSF	TPMR 160312 NSF	1,2		●	●		▲																									
Light-Medium Cut	NSF	TPMR 220408 NSF	0,8				▲	▲	▲																								
Light-Medium Cut	NSF	TPMR 220412 NSF	1,2				▲	▲																									
Light-Medium Cut	NUJ	TPMR 110304 NUJ	0,4		○	○		▲	▲																								
Light-Medium Cut	NUJ	TPMR 110308 NUJ	0,8		○	○																											
Light-Medium Cut	NUJ	TPMR 160304 NUJ	0,4		○	●		▲	▲																								
Light-Medium Cut	NUJ	TPMR 160308 NUJ	0,8		○	●		▲	▲																								

TPMN ●●●●●●

● M-Class No Chipbreaker



Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated: P	P	P	P	P	P	M	M	M	P/M	K	K	K	K	K	H	S	S	K/S, M/S	K/S, M/S	P/M	P/M	Cermet Coated: P	P	Cermet Uncoated: P	P	Carbide Uncoated: K	S	S	N
Medium Cut		TPMN 110304	0,4											○	○																		
Medium Cut		TPMN 110308	0,8											○	○																		
Medium Cut		TPMN 160304	0,4											○	○																		
Medium Cut		TPMN 160308	0,8											○	○	○												○	○				
Medium Cut		TPMN 160312	1,2											○	○																		
Medium Cut		TPMN 220408	0,8																									○	○				

TEGN ●●●●●●

● E-Class No Chipbreaker



Application	Shape	ISO Cat. No.	RE	AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
				Carbide Coated: P	P	P	P	P	P	M	M	M	P/M	K	K	K	K	K	H	S	S	K/S, M/S	K/S, M/S	P/M	P/M	Cermet Coated: P	P	Cermet Uncoated: P	P	Carbide Uncoated: K	S	S	N
Light-Medium Cut		TEGN 160308	0,8																										○				

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

Pos. Inserts
C
D
K
R
S
T
V
W

35° Diamond Type | 5° Relief | With Insert Hole



Dimensions (mm)				
VB_ _	L	IC	S	D_1
1102..	11,0	6,35	2,38	2,38
1103..	11,1	6,35	3,18	2,8
1604..	16,6	9,525	4,76	4,4

⇨ D38 ⇨ E21–22

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

VBMT/-W ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated K	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Coated P	Cermet Coated P	Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	NFB	**VBMT 110302 NFB**	0,2																					○	●	○	○	○				
		VBMT 110304 NFB	0,4																					○	●	○	○	○				
		VBMT 110308 NFB	0,8																					○	●	○	○	○				
		VBMT 160404 NFB	0,4																					○	●	●	●	●				
		VBMT 160408 NFB	0,8																					○	●	○	○	●				
Finishing	NFP	**VBMT 110202 NFP**	0,2																							▲	▲	▲				
		VBMT 110204 NFP	0,4																							▲	▲	▲				
		VBMT 160404 NFP	0,4																					▲		▲	▲	▲				
		VBMT 160408 NFP	0,8																					▲		▲	▲	▲				
Finishing	NLU	**VBMT 110302 NLU**	0,2																					○	○			○				
		VBMT 110304 NLU	0,4	○	●		▲	▲		●		●	○											○	○		○	○				
		VBMT 110308 NLU	0,8	○	○		▲			●	○	●	○																			
		VBMT 160404 NLU	0,4	●	○		▲	▲			○	●	○											●	○	○	○	○				
		VBMT 160408 NLU	0,8	●	●		▲	▲			○	●												○	○	○	○	○				
Light Cut	NLB	**VBMT 110302 NLB**	0,2		○	○		▲	▲	○	○	○													○			○				
		VBMT 110304 NLB	0,4		○	○		▲	▲	○	○	○													○	○						
		VBMT 110308 NLB	0,8		○	○		▲	▲	○	○	○													○	○						
		VBMT 160404 NLB	0,4		○	○		▲	▲	○	●	●													●	●		●				
		VBMT 160408 NLB	0,8		○	○		▲	▲	○	●	●													●	●		●				
		VBMT 160412 NLB	1,2		○	○		▲	▲	○	●	●													●	○		●				
Light Cut	NSU	**VBMT 110204 NSU**	0,4	●			▲	▲		●			●												●							
		VBMT 110208 NSU	0,8	●	●		▲	▲		●			●												●							
		VBMT 110302 NSU	0,2																						○							
		VBMT 110304 NSU	0,4	●	●		▲	▲		●		●	●				▲	▲							●		○					
		VBMT 110308 NSU	0,8	●	●		▲	▲	▲	●	●	○	○				▲	▲							○							
		VBMT 160404 NSU	0,4	●	●	●	▲	▲	▲	●	●	●	●				▲	▲		●	●	▲	▲	●	●	●	○	○				
		VBMT 160408 NSU	0,8	●	●	●	▲	▲	▲	●	●	●	●				▲	▲		●	●	▲	▲	●			○	○				
		VBMT 160412 NSU	1,2	○	○			▲																								
Light Cut	NSK	**VBMT 110204 NSK**	0,4		●	●		▲	▲																							
		VBMT 110208 NSK	0,8		●			▲	▲																							
		VBMT 160404 NSK	0,4	●	●	●		▲	▲											●	●	▲	▲									
		VBMT 160406 NSK	0,6		●	●		▲	▲																							
		VBMT 160408 NSK	0,8	●	●	●		▲	▲											●	●	▲	▲									
		VBMT 160412 NSK	1,2	●	●	●		▲	▲									▲														
Light - Medium Cut	NMU	**VBMT 160408 NMU**	0,8	●			▲						●																			
Light Cut		**VBMW 160404**	0,4											○	○		▲	▲														
		VBMW 160408	0,8											○	○		▲	▲														

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

V DIAMOND TYPE
INSERTS FOR TURNING

35° Diamond Type | 5° Relief | With Insert Hole



Dimensions (mm)				
VB_ _	L	IC	S	D_1
1103..	11,1	6,35	3,18	2,8
1604..	16,6	9,525	4,76	4,4

⇨ D38 ⇨ E21–22

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

VBGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P: AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M: AC6020M	AC6030M	AC6040M	PM: AC630M	AC4010K	AC4015K	K: AC420K	AC405K	AC415K	H: AC503U	S: AC5015S	AC5025S	KS: AC510U	MS: AC520U	PM: AC1030U	AC530U	Cermet Coated P: T1500Z	T3000Z	Cermet Uncoated P: T1000A	T1500A	Carbide Uncoated K: G10E	S: EH510	EH520	N: H1
Finishing	L/RFX	VBGT 110301 LFX	0,1																					○	○	○		○	○				
		VBGT 110302 LFX	0,2																					○	○	○		○					
		VBGT 110304 LFX	0,4																					○	○	○		○	○				
		VBGT 160402 LFX	0,2																									○	○				
		VBGT 160404 LFX	0,4																									○	○				
		VBGT 110301 RFX	0,1																					○	○	○		○	○				
		VBGT 110302 RFX	0,2																					○	○	○		○	○				
		VBGT 110304 RFX	0,4																					○		○		○	○				
		VBGT 160402 RFX	0,2																									○	○				
		VBGT 160404 RFX	0,4																									○	○				
Finishing	L/RFYS	VBGT 1103003 LFYS	0,03																					○									
		VBGT 110301 LFYS	0,1																					○									
		VBGT 110302 LFYS	0,2																					○									
		VBGT 110304 LFYS	0,4																					○									
		VBGT 110308 LFYS	0,8																					○									
		VBGT 1103003 RFYS	0,03																					○									
		VBGT 110301 RFYS	0,1																					○									
		VBGT 110302 RFYS	0,2																					○									
		VBGT 110304 RFYS	0,4																					○									
		VBGT 110308 RFYS	0,8																					○									
Finishing	L/RFY	VBGT 110301 LFY	0,1																					○		○		○	○				
		VBGT 110302 LFY	0,2																					○	○								
		VBGT 110304 LFY	0,4																					○									
		VBGT 110301 RFY	0,1																					○		○		○	○				
		VBGT 110302 RFY	0,2																					○		○		○	○				
		VBGT 110304 RFY	0,4																					○									
Light Cut	NSI	VBGT 110301M NSI	<0,1																					○									
		VBGT 110302M NSI	<0,2																					○									
		VBGT 110304M NSI	<0,4																					○	○								
		VBGT 110308M NSI	<0,8																					○									
		VBGT 160401M NSI	<0,1																					○									
		VBGT 160402M NSI	<0,2																					○									
		VBGT 160404M NSI	<0,4																					○									
		VBGT 160408M NSI	<0,8																		●	●		○									

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

35° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
VC__	L	IC	S	D_1
0802..	8,3	4,76	2,38	2,3
1103..	11,1	6,35	3,18	2,8
1604..	16,6	9,525	4,76	4,4

⇨ D39

"S…- SV…C" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

VCGT ●●●●●● ●-■■

● G-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P	AC8025P	**AC8035P**	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	**AC4010K**	**AC4015K**	AC420K	AC405K	AC415K	AC503U	**AC5015S**	**AC5025S**	AC510U	AC520U	AC1030U	AC530U	T1500Z	T3000Z	T1000A	T1500A	G10E	EH510	EH520	H1
Finishing	NFC	**VCGT 080204M NFC**	<0,4																					○	○								
		VCGT 110301M NFC	<0,1																					●	●			○	○				
		VCGT 110302M NFC	<0,2																					●	●			○	○				
		VCGT 110304M NFC	<0,4																		○			●	●			○	○				
Finishing	L/RFX	**VCGT 110301 LFX**	0,1																		○		▲	●	●			○	●				
		VCGT 110302 LFX	0,2																		○		▲	●	●			○	●				
		VCGT 110304 LFX	0,4																					●	○								
		VCGT 110301 RFX	0,1																		○		▲	●	●			○	●				
		VCGT 110302 RFX	0,2																		○		▲	●	●			●	●				
		VCGT 110304 RFX	0,4																					○	○								
Finishing	L/RFY	**VCGT 110301 LFY**	0,1																					○									
		VCGT 110302 LFY	0,2																					○									
		VCGT 110304 LFY	0,4																					○									
		VCGT 110301 RFY	0,1																		○			○	○								
		VCGT 110302 RFY	0,2																		○			○									
		VCGT 110304 RFY	0,4																					○									
Light Cut	NAG	**VCGT 110302 NAG**	0,2																														●
		VCGT 110304 NAG	0,4																														●
		VCGT 160408 NAG	0,8																														●
		VCGT 160412 NAG	1,2																														○
		VCGT 220530 NAG	3,0																														○
Light Cut	NSI	**VCGT 110301M NSI**	<0,1										○							●	●	▲	▲	●	●	●		○	○				
		VCGT 110302M NSI	<0,2										○							●	●	▲	▲	●	●	●		○	○				
		VCGT 110304M NSI	<0,4										○							●	●	▲	▲	●	●	●			○				
		VCGT 110308M NSI	<0,8										○							●	●	▲	▲	●	●	●		○	○				
		VCGT 160401M NSI	<0,1										○							●	●	▲	▲	●	●	●		○	○				
		VCGT 160402M NSI	<0,2										○							●	●	▲	▲	●	●	●		○	○				
		VCGT 160404M NSI	<0,4										○							●	●	▲	▲	●	●	●		●	○				
		VCGT 160408M NSI	<0,8																					○									

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

V DIAMOND TYPE
INSERTS FOR TURNING

35° Diamond Type | 7° Relief | With Insert Hole



Dimensions (mm)				
VC_ _	L	IC	S	D_1
0802..	8,3	4,76	2,38	2,3
1103..	11,1	6,35	3,18	2,8
1604..	16,6	9,525	4,76	4,4

⇨ D39

"S…- SV…C" - Type
(⇨ Stock in Japan)

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

VCMT ●●●●●● ●-■■

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated P AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	M AC6020M	AC6030M	AC6040M	PM AC630M	K AC4010K	AC4015K	AC420K	AC405K	AC415K	H AC503U	S AC5015S	AC5025S	KS AC510U	MS AC520U	PM AC1030U	AC530U	Cermet Coated P T1500Z	T3000Z	Uncoated T1000A	T1500A	Carbide Uncoated K G10E	S EH510	EH520	N H1
Finishing	NFB Depth of cut (mm) 0 1 2; 0,1 0,2 0,3 Feed rate (mm/rev)	VCMT 080202 NFB	0,2																						○	●	○	○	○				
		VCMT 080204 NFB	0,4																						○	●	○	○	○				
		VCMT 160404 NFB	0,4																						○	●	○	○	○				
		VCMT 160408 NFB	0,8																						○	●	○	○	○				
Finishing	NLU Depth of cut (mm) 0 1 2; 0,1 0,2 0,3 Feed rate (mm/rev)	VCMT 160404 NLU	0,4	○	○					○	○															○	○	○	○				
		VCMT 160408 NLU	0,8	○	○					○																○	○	○	○				
Light Cut	NLB Depth of cut (mm) 0 1 2; 0,1 0,2 0,3 Feed rate (mm/rev)	VCMT 080202 NLB	0,2		○	○		▲	▲	○	○	○														○	○						
		VCMT 080204 NLB	0,4		○	○		▲	▲	○	○	○														○	○						
		VCMT 160404 NLB	0,4		○	○		▲	▲	○	○	○														○	○						
		VCMT 160408 NLB	0,8		○	○		▲	▲	○	○	○														○	○						
Light Cut	NSU Depth of cut (mm) 0 1 2 3; 0,1 0,2 0,3 Feed rate (mm/rev)	VCMT 080204 NSU	0,4							○	○	●	○												○								
		VCMT 110302 NSU	0,2							●	●		●																				
		VCMT 110304 NSU	0,4		○			▲		●	●		●																				
		VCMT 110308 NSU	0,8		○					●	●		○																				
		VCMT 160404 NSU	0,4	●	●	●	▲	▲	▲	●	●	○	●				▲	▲		●	●	▲	▲		●								
		VCMT 160408 NSU	0,8	●	●	●	▲	▲	▲	●	●		●				▲	▲				▲	▲		●								
Light Cut	NSK Depth of cut (mm) 0 1 2 3; 0,1 0,2 0,3 Feed rate (mm/rev)	VCMT 160404 NSK	0,4		●	●	▲	▲													●			▲								
		VCMT 160408 NSK	0,8		●	●	▲	▲												●	●			▲								

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

80° Trigon Type | 5° Relief | With Insert Hole



Dimensions (mm)				
WB__	L	IC	S	D_1
0601..	3,2	3,97	1,59	2,2
0802..	4,6	4,76	2,38	2,4



⇨ E23

- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

WBGT ●●●●●● ●-■■

● G-Class Handed Chipbreaker

Application	Shape	ISO Cat. No.	RE	Carbide Coated P	Carbide Coated P/M	Carbide Coated M	Carbide Coated P/M	Carbide Coated K	Carbide Coated H	Carbide Coated S	Carbide Coated K/S	Carbide Coated M/S	Carbide Coated P/M	Cermet Coated P	Cermet Uncoated P	Carbide Uncoated P	Carbide Uncoated K	Carbide Uncoated S	Carbide Uncoated N
				AC8015P AC8025P AC8035P AC810P AC820P AC830P	AC6020M AC6030M AC6040M	AC630M AC4010K AC4015K	AC420K AC405K AC415K	AC503U AC5015S AC5025S	AC510U AC520U	AC1030U AC530U	T1500Z T3000Z	T1000A T1500A	G10E EH510 EH520	H1
Finishing	 L/RFW 	WBGT 060102 LFW	0,2										○	○				
		WBGT 060104 LFW	0,4										○	○				
		WBGT 080202 LFW	0,2										○	○				
		WBGT 080204 LFW	0,4										○					
		WBGT 060102 RFW	0,2										○	○				
		WBGT 060104 RFW	0,4										○	○				
		WBGT 080202 RFW	0,2										○	○				
		WBGT 080204 RFW	0,4										○	○				
Finishing	 L/RFX 	WBGT 060102 LFX	0,2								●	●						
		WBGT 060104 LFX	0,4								●	●						
		WBGT 080202 LFX	0,2								○	○						
		WBGT 080204 LFX	0,4								○	○						
		WBGT 060102 RFX	0,2								●	○						
		WBGT 060104 RFX	0,4								●	○						
		WBGT 080202 RFX	0,2								○	○						
		WBGT 080204 RFX	0,4								○							
Finishing	 L/RFY 	WBGT 0601003 LFY	0,03													○		
		WBGT 060101 LFY	0,1													○		
		WBGT 060102 LFY	0,2								○	○		○		○		
		WBGT 060104 LFY	0,4								○	○		○		○		
		WBGT 080201 LFY	0,1											○		○		
		WBGT 080202 LFY	0,2											○		○		
		WBGT 080204 LFY	0,4											○		○		
		WBGT 060101 RFY	0,1													○		
		WBGT 060102 RFY	0,2								○			○		○		
		WBGT 060104 RFY	0,4								○	○		○		○		
		WBGT 080201 RFY	0,1											○		○		
		WBGT 080202 RFY	0,2											○		○		
		WBGT 080204 RFY	0,4											○		○		
Finishing ~ Light Cut	 L/RW 	WBGT 060102 LW	0,2								●	●		○		●		
		WBGT 060104 LW	0,4								●	●		○		●		
		WBGT 060102 RW	0,2								●	●		○		●		
		WBGT 060104 RW	0,4								●	●		○		●		

Depth of cut (mm) 0 1 2 — 0,1 0,2 0,3 Feed rate (mm/rev)

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

W TRIGON TYPE
INSERTS FOR TURNING

80° Trigon Type | 11° Relief | With Insert Hole



Dimensions (mm)				
WP_ _	L	IC	S	D_1
1102..	4,3	6,35	2,38	2,8
1603..	6,5	9,525	3,18	4,4



- P Steel
- M Stainless Steel
- K Cast Iron
- N Non-Ferrous Metals
- S Super Alloy
- H Hardened Steel

WPMT ●●●●●● NLB

● M-Class

Application	Shape	ISO Cat. No.	RE	Carbide Coated AC8015P	AC8025P	AC8035P	AC810P	AC820P	AC830P	AC6020M	AC6030M	AC6040M	AC630M	AC4010K	AC4015K	AC420K	AC405K	AC415K	AC503U	AC5015S	AC5025S	AC510U	AC520U	AC1030U	AC530U	Cermet Coated T1500Z	T3000Z	T1000A	T1500A	Cermet Uncoated G10E	Carbide Uncoated EH510	EH520	H1
Light Cut	 NLB	**WPMT 110204 NLB**	0,4	○				▲	▲	○	●	●														○	○		○				
		WPMT 160308 NLB	0,8	○				▲	▲	○	●	●														○	○		○				

● = Euro stock
○ = Japan stock
▲ = To be replaced by new item

External Holders

D

D1–D46



Application	For Neg. Inserts	For Pos. Inserts	Special Type for Hardened Steel
General Turning	**P Type Lever Lock Type**  ⇨ D18–D22	**P Type Lever Lock Type**  ⇨ D31, D32	**D Type Double Lock Type**   ⇨ D12–D17 ⇨ D41–D42
	M Type Double Lock Type  ⇨ D23–D24	**S Type Screw On Type**   D31–D33 ⇨ D35–D37 ⇨D43–D45	**C Type Top Clamp Type**  ⇨ D25–D26
Copying	**T-REX**  ⇨D10–D11	**S Type Screw On Type**   ⇨D38–D39 ⇨D43–D45	**D Type Double Lock Type**   ⇨ D13, D16 ⇨ D41
Parting-Off Grooving	**GNDS, GNDM, GNDMS Type General Grooving**  ⇨F16, F18, F20 ⇨ F36-F39	**GNDL, GNDLS Type Deep Grooving**  ⇨ F16, F24 ⇨ F36-F39	**GNDF, GNDFS Type Axial Grooving**  ⇨ F32, F34 ⇨ F36-F39
	SCT and GWC Type  ⇨ F40–F44 ⇨ F41	**Sumi Grip and Sumi Grip Jr.**  ⇨ F45–F50	**GWB Type Hard Grooving**  ⇨ M42 ⇨ M43
Threading	**LTE and STE Type** Pitch { 1–4 mm / 24–8 Threads/inch  ⇨ F54	**THE Type** Pitch { 0,8–3 mm / 24–10 Threads/inch  ⇨ Stock in Jp.	**BNGG-TT Type Hard Threading** Pitch 1–3 mm  ⇨ M44

PSC Available in Polygon-Shank-Design

External Turning



Usage / Type	Cut - Off	Back Turning	Copying	General Turning	Grooving	Grooving & Cut-Off
	SCT Type	SBT Type	SV Type	P / S Type	GWC Type	GND Type



Holder Selection for Autolathe

	Offset - 0 mm Type Holders	Offset - 0,5 mm Type Holders
Tooling		
Features	Program correction is not necessary.	The position of cutting edge can be put in near guide bush through a program correction.
Holder Types	SDJC-X, SDAC-X SDLC-X, SCAC-X SVJC-X (⇨ Stock in Japan)	PDJC, SDJC, SDAC PCLC, SCAC STAC, SVLC

External Tool Holder Series

Lever Lock System

Double Lock (D)



D Type "Double Clamp" Holders
for high performance machining

■ TOOLING SELECTION

Application			General Turning & Facing		General Turning & Copying			General Turning	
Insert Type / System			80° Diamond Type		55° Diamond Type		T-REX 55°	90° Square Type	
Screw Lock System	S Type Mini Holder		 **SCLC** ⇨ D31	 **SCAC** ⇨ D31	 **SDJC** ⇨ D32 **SDHC** ⇨ D32	 **SDAC** ⇨ D33	–	–	 **SSBC** ⇨ D36
			–	–	 **SDNC** ⇨ D33	–	–	–	–
Lever Lock System	P Type (* Side Lever Lock Type)		 **PCLC** (*) ⇨ D31	–	 **PDJC** (*) ⇨ D32	–	–	 **PSBN** ⇨ D20	 **PSDN** ⇨ D20
			 **PCBN** ⇨ D18	 **PCLN** ⇨ D18	 **PDJN** ⇨ D19	–	–	 **PSKN** ⇨ D21	 **PSSN** ⇨ D21
Top-On Clamp System	C & M Type		 **CCLN** ⇨ D25	–	–	–	–	 **CSBN** ⇨ D25	 **CSKN** ⇨ D25
Double Lock (D) Dimple Lock (X)	D & X Type		 **DCLN** ⇨ D12	 **XCLN** ⇨ D27	 **DDJN** ⇨ D13	–	 **DTR** ⇨ D11	 **XSBN** ⇨ D27	–
			–	–	 **DDHN** ⇨ D13	 **DDNN** ⇨ D13	–	 **DSBN** ⇨ D14	 **DSDN** ⇨ D14

Top-On Clamp System



Screw Lock System

■ TOOLING SELECTION

Application		General Turning			Copying		General Turning	Special Turning	
Insert Type / System		60° Triangle Type			35° Diamond Type		80° Trigon Type	Round and Special Purpose Inserts	
Screw Lock System	S Type Mini Holder	STAC ⇨ D37	STGC ⇨ D37	–	SVJB ⇨ D38 SVLC ⇨ D39	SVVB ⇨ D38	–	SRDC ⇨ D35	SRSC ⇨ D35
		–	–	–	SVPB ⇨ D38 SVPC ⇨ D39	–	–	SBT ⇨ D30	–
Lever Lock System	P Type	PTGN ⇨ D22	PTFN ⇨ D22	PTTN ⇨ D22	–	–	PWLN ⇨ D24	PRDC ⇨ D34	PRGC ⇨ D34
		–	–	–	–	–	–	–	–
Top-On Clamp System	C & M Type	MTJN ⇨ D23	MTXN ⇨ D23	–	–	–	MWLN ⇨ D24	CRDN ⇨ D26	CRSN ⇨ D26
Double Lock (D) Dimple Lock (X)	D & X Type	DTJN ⇨ D15	DTFN ⇨ D15	–	DVJN ⇨ D16	–	DWLN ⇨ D17	–	–
		DTGN ⇨ D15	–	–	DVQN ⇨ D16	DVVN ⇨ D16	–	–	–

Polygon - Shank Holder - Produced According to ISO 26623-1

Negative Insert Type

■ TOOLING SELECTION

Application			General Turning & Facing		General Turning & Copying			General Turning	
Insert Type / System			80° Diamond Type		55° Diamond Type		T-REX 55°	90° Square Type	
Screw Lock System	S Type Mini Holder		 **SCLC** ⇨ D43	—	 **SDJC** ⇨ D43	—	—	—	 **SSBC** ⇨ D43
			—	—	 **SDHC** ⇨ D43	—	— SRSCR	—	—
Double Lock (D)	D Type		 **DCLN** ⇨ D41	—	 **DDJN** ⇨ D41	—	—	—	—
			—	—	 **DDHN** ⇨ D41	—	—	 **DSBN** ⇨ D41	—

■ Classification System for Polygon - Shank Holder

P S C 4 0 - S C L C R 2 7 0 5 0 - 0 9

- **P S C** — Polygon Shank
- **4 0** — Size (ø*D*)
- **S** — Clamping System: D: Double Clamp; S: Screw Clamp
- **C** — Insert Shape
- **L** — Holder Style
- **C** — Seat Clearance Angle: N = 0°; C = 7°; P = 11°
- **R** — Feed Direction: R: Right Hand; L: Left Hand; N: Neutral
- **2 7** — Size (*f*)
- **0 5 0** — Holder Length (L_1)
- **0 9** — Insert Cutting Edge Length

Positive Insert Type

TOOLING SELECTION

Application		General Turning			Copying		General Turning	Special Turning	
Insert Type / System		60° Triangle Type			35° Diamond Type		80° Trigon Type	Round and Special Purpose Inserts	
Screw Lock System	S Type Mini Holder	 **STJC** ⇨ D44	—	—	 **SVJB** ⇨ D44 **SVHB** ⇨ D44	 **SVJC** ⇨ D45 **SVHC** ⇨ D45	—	—	—
		—	—	—	 **SVVB** ⇨ D44	 **SVVC** ⇨ D45	—	—	—
Double Lock (D)	D Type	 **DTJN** ⇨ D42	—	—	—	—	 **DWLN** ⇨ D42	—	—
		—	—	—	—	—	—	—	—

Classification System for Polygon - Shank Holder

P S C 5 0 - S T J C R 3 5 0 6 0 - 1 6

- Polygon Shank
- Size (ø*D*)
- Clamping System D: Double Clamp S: Screw Clamp
- Insert Shape
- Holder Style
- Seat Clearance Angle N = 0° C = 7° P = 11°
- Feed Direction R: Right Hand L: Left Hand N: Neutral
- Size (*f*)
- Holder Length (L_1)
- Insert Cutting Edge Length

ISO Holders Identification

■ Catalogue Classification System for Tool Holders

D	T	F	N	R	25	25	M	16	E
Clamping System Chart 1	Insert Shape Chart 2	Holder Style Chart 3	Seat Clearance Angle Chart 4	Feed Direction Chart 5	Shank Height Chart 6	Shank Width Chart 7	Shank Length Chart 8	Insert Size Chart 9	For D-Type Euro-Inserts D□□□1506○○

DTFNR2525M16

Clamping: Double clamp system
Shape: Triangular insert with 91° approach angle
Shank: H = 25mm, W = 25mm, L = 150mm

External Holders

Chart 1

Clamping System					
Symbol	Clamp Types	Example of Structure	Symbol	Clamp Types	Example of Structure
C	Top Clamp		M	Top & Hole Clamp Type	
D	Double Clamp		P	Lever Lock Type (Insert is Supported by 1 face)	
E	Pin Lock Type (Insert is supported by 1 face)		S	Screw Clamp Type	

Chart 2

Insert Shape					
Symbol	Insert Shape		Symbol	Insert Shape	
A	Parallelogram 85°		M	Rhombic 86°	
B	Parallelogram 82°		O	Octagonal	
C	Diamond 80°		P	Pentagonal	
D	Diamond 55°		R	Round	
E	Diamond 75°		S	Square	
F	Diamond 50°		T	Triangular	
H	Hexagonal		V	Diamond 35°	
K	Parallelogram 55°		W	Trigon	
L	Rectangular				

Chart 4

Seat Clearance Angle	
Symbol	Relief Angle
A	3°
B	5°
C	7°
D	15°
E	20°
F	25°
G	30°
N	0°
P	11°
O	Special Angle

Chart 5

Feed Direction					
Symbol	Right Hand Feed	Symbol	Neutral Feed	Symbol	Left Hand Feed
R		N		L	

Chart 3

Holder Style					
Symbol	Shape	Offset	Symbol	Shape	Offset
A	90i	Nil	L	95i 95i	With Offset
B	75i	Nil	N	63i	Nil
D	45i	Nil	R	75i	With Offset
E	60i	Nil	S	45i	With Offset
F	90i	With Offset	T	60i	With Offset
G	90i	With Offset	U	93i	With Offset
J	93i	With Offset	W	60i	With Offset
K	75i	With Offset	Y	85i	With Offset

Chart 6

Shank Height	
Symbol	Height (mm)
12	12
16	16
20	20
25	25
32	32
40	40
50	50
00	Round shank, Shank Diamater is Shown for Round Shank,

2 digits are used for each dimension in mm.

Chart 7

Shank Width	
Symbol	Width (mm)
12	12
16	16
20	20
25	25
32	32
40	40
50	50

Chart 8

Shank Length	
Symbol	Length (mm)
F	80
H	100
K	125
M	150
N	160
P	170
Q	180
S	250
T	300
U	350

For some Products, a Hypen is used Instead of an alphabet.

Chart 9

Cutting Edge	
Symbol	Length (mm)

Eg. for Triangle Inserts:

06	6,9
08	8,2
09	9,6
11	11,0
16	16,5
22	22,0
27	27,5
33	33,0

For Round Inserts:

10	10
12	12
16	16
20	20
25	25
32	32

■ Cutting Edge Dimensions by Corner Radius

(This table shows X and Y dimensions based on 0° approach angle cutting edge inclination)

Holders			Dimensions(mm)			Holders			Dimensions(mm)		
Symbol	Shapes	Corner Shapes	RE	X	Y	Symbol	Shapes	Corner Shapes	RE	X	Y
A			0,4	0,291	–	K			0,4	0,024	0,089
			0,8	0,581	–				0,8	0,048	0,178
			1,2	0,872	–				1,2	0,072	0,268
			1,6	1,162	–				1,6	0,096	0,357
			2,4	1,743	–				2,4	0,143	0,535
B			0,4	0,089	0,024	L			0,4	0,040	0,040
			0,8	0,178	0,048				0,8	0,079	0,079
			1,2	0,268	0,072				1,2	0,119	0,119
			1,6	0,357	0,096				1,6	0,159	0,159
			2,4	0,535	0,143				2,4	0,238	0,238
D			0,4	0,164	0,164	N			0,4	0,463	0,263
			0,8	0,329	0,329				0,8	0,925	0,471
			1,2	0,493	0,493				1,2	1,388	0,707
			1,6	0,658	0,658				1,6	1,850	0,943
			2,4	0,986	0,986				2,4	2,776	1,414
E			0,4	0,396	0,229	S			0,4	0,164	0,164
			0,8	0,793	0,458				0,8	0,329	0,329
			1,2	1,190	0,687				1,2	0,493	0,493
			1,6	1,587	0,916				1,6	0,658	0,658
			2,4	2,381	1,374				2,4	0,986	0,986
F			0,4	–	0,291	T			0,4	0,396	0,229
			0,8	–	0,581				0,8	0,793	0,458
			1,2	–	0,872				1,2	1,190	0,687
			1,6	–	1,162				1,6	1,587	0,916
			2,4	–	1,743				2,4	2,381	1,374
G			0,4	0,291	–	U			0,4	0,253	0,058
			0,8	0,581	–				0,8	0,506	0,116
			1,2	0,872	–				1,2	0,759	0,175
			1,6	1,162	–				1,6	1,013	0,233
			2,4	1,743	–				2,4	1,519	0,350
J			0,4	0,344	0,033	Y			0,4	0,002	0,033
			0,8	0,687	0,079				0,8	0,005	0,066
			1,2	1,031	0,118				1,2	0,008	0,099
			1,6	1,375	0,157				1,6	0,011	0,132
			2,4	2,062	0,236				2,4	0,017	0,198

● Calculation of the Nose Radius Dimensions

(Unit in mm)

Insert Shape		Calculation
	Triangle	$B = \frac{3}{2}A - RE$
	Square	$B=(\sqrt{2}-1) \times (\frac{A}{2}-RE)$
	Rhombic	$B=\{\frac{1}{Sin(\theta/2)}-1\} \times (\frac{A}{2}-RE)$

Figures of „A“ and „RE“ to calculate Figure „B“

I.C. size (inch)		„øA“ dimensions (mm)
–	5/32	3,9688
–	6/32	4,7625
–	7/32	5,5562
2/8	8/32	6,3500
–	(0)	7,9375
3/8	–	9,5250
4/8	–	12,7000
5/8	–	15,8750
6/8	–	19,0500
8/8	–	25,4000

Nose symbol	Size (inch)	„RE“ dimension (mm)
02	(0)	0,203
04	1/64	0,397
08	2/64	0,794
12	3/64	1,191
16	4/64	1,588
24	6/64	2,389

T-REX Tool Holders

RIGIDITY - ECONOMY - PRECISION

SumiTurn T-REX

● T-REX clamping for maximum rigidity 50 % more cutting edges than a DNMG Insert

■ Advantages

● T-REX Inserts for Maximum Economy

With 6 cutting edges and a 55 degree included angle - T-Rex is the intelligent alternative to profile turning with a traditional 4 edge DNMG insert.

● Biting Performance from T-REX Teeth

The double clamp tool holder and powerful teeth of T-REX lock the insert to eliminate movement, dramatically improving tool life, machining accuracy, and cutting edge security.



● Application Range



■ Application Examples

● 20Cr4 Shaft



33 % cost saving



Insert: TRM551708-GU, AC2000
Cutting data: v_c= 150 m/min, f = 0,25 mm/rev, a_p < 2,0 mm, Wet

● 25CrMo4 Gear



1,3 times long tool life



Insert: TRM551708-LU, AC900G
Cutting data: v_c= 220 m/min, f = 0,2–0,3 mm/rev, a_p < 1,0 mm, Wet

■ Recommendations

● Depth of Cut

Max. a_p = 2,5 mm

● Approach Angle



(*) Angle of major cutting edge

C-Type: 95,5°
Q-Type: 107,5°

● Insert Clamping



Recommended Tightening Torque (N·m)

● = Euro stock
○ = Japan stock

SumiTurn

External Turning & Copying

DTR55C

Profiling





Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Clamp	Spring	Screw	Shim	Screw	Wrench	Wrench
	R	L	H	HF	B	LF	LH	WF							
DTR 55C-R/L 2020-K17	●	●	20	20	20	125	35	25	TRCP3	S-SP4-20	BX0520 3,5-4,5 (Nm)	TRW5505	BFTX0307N 2,0 (Nm)	TSW040	TRX10(*)
DTR 55C-R/L 2525-M17	●	●	25	25	25	150	35	32							

Spare Parts



(*) Note: Wrench (TRX) for shim clamp screw is not included.

DTR55Q

Profiling





Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Clamp	Spring	Screw	Shim	Screw	Wrench	Wrench
	R	L	H	HF	B	LF	LH	WF							
DTR 55Q-R/L 2020-K17	●	●	20	20	20	125	35	28,5	TRCP3	S-SP4-20	BX0520 3,5-4,5 (Nm)	TRW5505	BFTX0307N 2,0 (Nm)	TSW040	TRX10(*)
DTR 55Q-R/L 2525-M17	●	●	25	25	25	150	35	32							

Spare Parts



(*) Note: Wrench (TRX) for shim clamp screw is not included.

Inserts

Applic.	Shape	Ordering No.	RE	Coated Carbide: New AC8015P	AC8025P	AC810P	AC820P	AC830P	AC630M	Coated Cermet: T3000Z
Fine Finishing	FL	TRM 551704-FL	0,4		❍					❍
		551708-FL	0,8		❍					❍
Finishing	LU	TRM 551704-LU	0,4	●	❍	▲	▲	▲		❍
		551708-LU	0,8	●	❍	▲	▲	▲		❍
		551712-LU	1,2	❍	❍	▲	▲			❍
	SU	TRM 551704-SU	0,4		❍		▲		❍	❍
		551708-SU	0,8		❍	▲	▲		❍	❍
		551712-SU	1,2		❍		▲		❍	
Light Cut	GU	TRM 551704-GU	0,4	❍	❍	▲	▲	▲	❍	
		551708-GU	0,8	❍	❍	▲	▲	▲	❍	
		551712-GU	1,2	❍	❍	▲	▲	▲		



Application P Steel
M Stainless steel

● Recommended Cutting Conditions

Cutting speed (m/min)

Grade		Coated Carbide: AC810P	AC8025P	AC820P	AC830P	AC630M	Coated Cermet: T3000Z
Work materials	Low carbon steel	220 400	150 350	150 350	120 300	120 300	100 400
	Alloy steel	150 300	100 250	100 250	80 200	80 230	100 250
	Stainless steel				50 150	100 160	
Application range	Finishing	◎	○	○	○	○	◎
	Medium cutting	○	◎	◎	○	◎	○
	Interrupted cutting		○	○	◎	○	○

◎ Preferred choice ○ Suitable

Characteristics

Insert is clamping firmly for improved fracture resistance.
High indexing accuracy improves machining accuracy.
Insert can be changed from below the holder.
Suitable for high efficiency machining and interrupted cutting in hardened steel.

Clamp Mechanism

Secured in two directions and supported by two faces.



Insert can be changed from below the holder.

Index Accuracy Comparison (Length Wise)

D Type Tool Holders



Lever Lock



General Turning and Facing

Inserts

Eg.

N-GU

❶ CNMG 120408 N-GU
❷ CNMG 160608 N-GU
❸ CNMM 190612 N-HG
❹ CNMM 250924 N-HU

DCLN





Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF								
DCLN R/L 2020 K12	●	●	20	20	20	125	32	25	SCP2		5,0 (N·m)	CNS1204	BFTX0409N 3,4 (N·m)	TRX15(*)	LH040 LH025	❶
DCLN R/L 2525 M12	●	●	25	25	25	150	32	32								
DCLN R/L 2525 M16	●	●	25	25	25	150	32	32	SCP3		5,0 (N·m)	CNS1606	BFTX0509N 5,0 (N·m)	TRX20(*)	LH040 LH025	❷
DCLN R/L 3232 P16	●	●	32	32	32	170	32	40								
DCLN R/L 3232 P19	●	●	32	32	32	170	42	40	SCP5		5,0 (N·m)	CNS1906	BFTX0511N 5,0 (N·m)	TRX20(*)	LH040 LH025	❸
DCLN R/L 4040 S19	●	●	40	40	40	250	42	50								
DCLN R/L 4040 S25	●	●	40	40	40	250	53	50	SCP6		6,0 (N·m)	CNS2509	BFTX0615N 7,5 (N·m)	TRD25(*)	LH060	❹

(*) Note: Wrench (TRX / TRD) for shim clamp screw is not included.

● = Euro stock ❑ = Delivery on request (N·m) Recommended Tightening Torque (N·m)

External Tool Holders
D Type (Double Clamp)

General Turning and Copying

DDJN





Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF								
DDJN R/L 2020 K15			20	20	20	125	38	25	SCP2 5,0 (N·m)			DNS1504	BFTX0409N 3,4 (N·m)	TRX15(*)	LH040	❶
DDJN R/L 2020 K15E	●	●	20	20	20	125	38	25				DNS1506				❷
DDJN R/L 2525 M15	❑		25	25	25	150	38	32				DNS1504				❶
DDJN R/L 2525 M15E	●	●	25	25	25	150	38	32				DNS1506				❷

Inserts

Eg.

N-GU

❶ DNMG 150408 N-GU
❷ DNMG 150608 N-GU

Spare Parts



(*) Note: Wrench (TRX) for shim clamp screw is not included.

DDHN





Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF								
DDHN R/L 2020 K15E	●	●	20	20	20	125	35	25	SCP2 5,0 (N·m)			DNS1506	BFTX0409N 3,4 (N·m)	TRX15(*)	LH040	❷
DDHN R/L 2525 M15E	●	●	25	25	25	150	35	32								

Inserts

Eg.

N-GU

❷ DNMG 150608 N-GU

Spare Parts



(*) Note: Wrench (TRX) for shim clamp screw is not included.

DDNN





Holders

Above figures show right hand tools.

Cat. No.	Stock	Dimensions (mm)						Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
		H	HF	B	LF	LH	WF								
DDNN R/L 2020 K15E	●	20	20	20	125	40	10,5	SCP2 5,0 (N·m)			DNS1506	BFTX0409N 3,4 (N·m)	TRX15(*)	LH040	❷
DDNN R/L 2525 M15E	●	25	25	25	150	40	13,0								

Inserts

Eg.

N-GU

❷ DNMG 150608 N-GU

Spare Parts



(*) Note: Wrench (TRX) for shim clamp screw is not included.

General Turning and Facing

DSBN





Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)					
	R	L	H	HF	B	LF	LH	WF
DSBN R/L 3232 P19	●	●	32	32	32	170	45	27
DSBN R/L 4040 S2507	●	●	40	40	40	250	58	35
DSBN R/L 4040 S2509	●	●	40	40	40	250	58	35

Inserts

Eg.

N-UZ, N-HU

❶ SNMG 190612 N-UZ
❷ SNMM 250724 N-HU
❸ SNMM 250924 N-HU

Spare Parts

Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
SCP5		5,0 (N·m)	SNS1906	BFTX0511N 5,0 (N·m)	TRX20(*)	LH040, LH025	❶
SCP6		6,0 (N·m)	SNS2507	BFTX0615N 7,5 (N·m)	TRD25(*)	LH060	❷
			SNS2509				❸

(*) Note: Wrench (TRX / TRD) for shim clamp screw is not included.

DSDN





Holders

Above figures show right hand tools.

Cat. No.	Stock	Dimensions (mm)					
		H	HF	B	LF	LH	WF
DSDN N 3232 P19	●	32	32	32	170	50	16
DSDN N 4040 S2507	●	40	40	40	250	63	20
DSDN N 4040 S2509	●	40	40	40	250	63	20

Inserts

Eg.

N-UZ, N-HU

❶ SNMG 190612 N-UZ
❷ SNMM 250724 N-HU
❸ SNMM 250924 N-HU

Spare Parts

Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
SCP5		5,0 (N·m)	SNS1906	BFTX0511N 5,0 (N·m)	TRX20(*)	LH040, LH025	❶
SCP6		6,0 (N·m)	SNS2507	BFTX0615N 7,5 (N·m)	TRD25(*)	LH060	❷
			SNS2509				❸

(*) Note: Wrench (TRX / TRD) for shim clamp screw is not included.

● = Euro stock ❑ = Delivery on request (N·m) Recommended Tightening Torque (N·m)

External Tool Holders
D Type (Double Clamp)



General Turning and Facing

DTJN





Inserts

Eg.

N-GU

❶ TNMG 160408 N-GU

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Insert
	R	L	H	HF	B	LF	LH	WF	
DTGN R/L 2020 K16	●		20	20	20	125	31	25	❶
DTGN R/L 2525 M16	●	●	25	25	25	150	31	32	❶

Spare Parts

Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench
SCP1		5,0 N-m	TNS1604	BFTX0307N 2,0 N-m	TRX10(*)	LH040

(*) Note: Wrench (TRX) for shim clamp screw is not included.

DTGN





Inserts

Eg.

N-GU

❶ TNMG 160408 N-GU

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Insert
	R	L	H	HF	B	LF	LH	WF	
DTGN R/L 2020 K16	❑		20	20	20	125	31	25	❶
DTGN R/L 2525 M16	●	●	25	25	25	150	31	32	❶

Spare Parts

Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench
SCP1		5,0 N-m	TNS1604	BFTX0307N 2,0 N-m	TRX10(*)	LH040

(*) Note: Wrench (TRX) for shim clamp screw is not included.

DTFN





Inserts

Eg.

N-GU

❶ TNMG 160408 N-GU

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Insert
	R	L	H	HF	B	LF	LH	WF	
DTFN R/L 2020 K16	❑		20	20	20	125	30	25	❶
DTFN R/L 2525 M16	●	●	25	25	25	150	30	32	❶

Spare Parts

Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench
SCP1		5,0 N-m	TNS1604	BFTX0307N 2,0 N-m	TRX10(*)	LH040

(*) Note: Wrench (TRX) for shim clamp screw is not included.

General Turning and Copying

DVJN





Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)					
	R	L	H	HF	B	LF	LH	WF
DVJN R/L 2020 K16	●	●	20	20	20	125	35	25
DVJN R/L 2525 M16	●	●	25	25	25	150	35	32

Inserts

Eg.

❶ VNMG 160408 N-GU

N-GU

Spare Parts

Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
SCP4		5,0 (N·m)	VNS1604	BFTX0307N 2,0 (N·m)	TRX10(*)	LH040 LH025	❶

(*) Note: Wrench (TRX) for shim clamp screw is not included.

DVQN





Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)					
	R	L	H	HF	B	LF	LH	WF
DVQN R/L 2020 K16	●	●	20	20	20	125	35	25
DVQN R/L 2525 M16	●	●	25	25	25	150	35	32

Inserts

Eg.

❶ VNMG 160408 N-GU

N-GU

Spare Parts



Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
SCP4		5,0 (N·m)	VNS1604	BFTX0307N 2,0 (N·m)	TRX10(*)	LH040 LH025	❶

(*) Note: Wrench (TRX) for shim clamp screw is not included.

DVVN





Holders

Above figures show right hand tools.

Cat. No.	Stock	Dimensions (mm)					
		H	HF	B	LF	LH	WF
DVVN N 2020 K16	●	20	20	20	125	37	10,0
DVVN N 2525 M16	●	25	25	25	150	37	12,5

Inserts

Eg.

❶ VNMG 160408 N-GU

N-GU

Spare Parts



Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
SCP4		5,0 (N·m)	VNS1604	BFTX0307N 2,0 (N·m)	TRX10(*)	LH040 LH025	❶

(*) Note: Wrench (TRX) for shim clamp screw is not included.

● = Euro stock

(N·m) Recommended Tightening Torque (N·m)

External Tool Holders
D Type (Double Clamp)

General Turning and Facing

DWLN





Inserts

Eg.

N-GU

❶ WNMG 080408 N-GU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF								
DWLN R/L 2020 K08	●	●	20	20	20	125	32	25	SCP2		5,0 N·m	WNS0804	BFTX0409N 3,4 N·m	TRX15(*)	LH040 LH025	❶
DWLN R/L 2525 M08	●	●	25	25	25	150	32	32								

(*) Note: Wrench (TRX) for shim clamp screw is not included.

General Turning and Facing

PCBN





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PCBN R/L 2020 K12	●	❑	20	20	20	125	27	17	LCL4SD	LCS42BS-SD	LSC42SD	LSP4SD	LH030	❶
PCBN R/L 2525 M12	●	●	25	25	25	150	27,7	22						
PCBN R/L 3225 P12	❑	●	32	32	25	170	27,7	22						
PCBN R/L 2525 M16	❑	●	25	25	25	150	31,7	22	LCL5SD	LCS5B-SD	LSC53SD	LSP5SD	LH030	❷
PCBN R/L 3225 P16	❑	●	32	32	25	170	31,7	22						
PCBN R/L 3232 P19	●	●	32	32	32	170	37,9	27	LCL6SD	LCS6B-SD	LSC63SD	LSP6SD	LH040	❸

PCLN





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PCLN R/L 1616 H09	●	●	16	16	16	100	25,7	20	LCL3SD	LCS3TB-SD	LSC32SD	LSP3SD	LH025	❶
PCLN R/L 2020 K09	●	❑	20	20	20	125	27	25						
PCLN R/L 2525 M09	❑	❑	25	25	25	150	27	32						
PCLN R/L 1616 H12	●	●	16	16	16	100	26,1	20	LCL4SD	LCS 4CA	LSC42SD	LSP4SD	LH030	❷
PCLN R/L 2020 K12	●	❑	20	20	20	125	27,4	25		LCS42BS-SD				
PCLN R/L 2525 M12	●	●	25	25	25	150	28	32						
PCLN R/L 3225 P12	●	●	32	32	25	170	28	32						
PCLN R/L 2525 M16	●	❑	25	25	25	150	32,6	32	LCL5SD	LCS5B-SD	LSC53SD	LSP5SD	LH030	❸
PCLN R/L 3225 P16	●	❑	32	32	25	170	32,6	32						
PCLN R/L 3232 P16	●	●	32	32	32	170	32,6	40						
PCLN R/L 2525 M19	❑	●	25	25	25	150	37	32	LCL6SD	LCS6B-SD	LSC63SD	LSP6SD	LH040	❹
PCLN R/L 3225 P19	❑	❑	32	32	32	170	38	32						
PCLN R/L 3232 P19	❑	❑	32	32	32	170	38	40						
PCLN R/L 4040 S19	❑	❑	40	40	40	250	37,8	50						

● = Euro stock ❑ = Delivery on request

External Tool Holders
P Type (Lever Lock)

General Turning and Facing





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PDJN R/L 1616 H11	●	●	16	16	16	100	30	20	LCL3D-SD	LCS3TB-SD	LSD32SD	LSP3SD	LH025	❶
PDJN R/L 2020 K11	●	●	20	20	20	125	30	25						
PDLN R/L 2525 M11	●	●	25	25	25	150	30	32						
PDJN R/L 2020 K15	●	●	20	20	20	125	34,7	25	LCL4D-SD	LCS5DB-SD	LSD42SD	LSP4SD	LH030	❷
PDJN R/L 2525 M15	●	●	25	25	25	150	34,7	32						
PDJN R/L 3225 P15	●	●	32	32	25	170	34,7	32						

General Turning and Chamfering

PSBN





Inserts

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PSBN R/L 2020 K12	●	●	20	20	20	125	27,5	17	LCL4SD	LCS42BS-SD	LSS42SD	LSP4SD	LH030	❶
PSBN R/L 2525 M12	●	●	25	25	25	150	27,5	22						
PSBN R/L 2525 M15	●	●	25	25	25	150	32	22	LCL5SD	LCS5B-SD	LSS53SD	LSP5SD	LH030	❷
PSBN R/L 3225 P15	●	●	32	32	25	170	32	22						
PSBN R/L 3232 P19	●	●	32	32	32	170	39,2	27	LCL6SD	LCS6B-SD	LSS63SD	LSP6SD	LH040	❸

PSDN





Inserts

Spare Parts

Holders

Cat. No.	Stock	Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
		H	HF	B	LF	LH	WF						
PSDN N 1616 H09	●	16	16	16	100	21	8,3	LCL3SD	LCS 3TB-SD	LSS32SD	LSP3SD	LH025	❶
PSDN N 2020 K12	●	20	20	20	125	27,6	10,3	LCL4SD	LCS42BS-SD	LSS42SD	LSP4SD	LH030	❷
PSDN N 2525 M12	●	25	25	25	150	27,6	12,8						
PSDN N 3225 P12	●	32	32	25	170	27,6	12,8						
PSDN N 3225 P19	❑	32	32	25	170	40,6	13	LCL6SD	LCS6B-SD	LSS63SD	LSP6SD	LH040	❸
PSDN N 3232 P19	●	32	32	32	170	40,6	16,5						

● = Euro stock ❑ = Delivery on request

General Turning and Facing

PSKN





Inserts

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PSKN R/L 2020 K12	●	❑	20	20	20	125	22,7	17	LCL4SD	LCS42BS-SD	LSS42SD	LSP4SD	LH030	❶
PSKN R/L 2525 M12	●	●	25	25	25	150	22,7	32						
PSKN R/L 2525 M15	❑		25	25	25	150	32	32	LCL5SD	LCS5B-SD	LSS53SD	LSP5SD	LH030	❷
PSKN R/L 3225 P15		●	32	32	25	170	32	32						
PSKN R/L 3232 P19	❑		32	32	32	170	33,7	40	LCL6SD	LCS6B-SD	LSS63SD	LSP6SD	LH040	❸

PSSN





Inserts

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LF2	LH	WF						
PSSN R/L 2020 K12	●	●	20	20	20	125	116,7	29,3	25	LCL4SD	LCS42BS-SD	LSS42SD	LSP4SD	LH030	❶
PSSN R/L 2525 M12	●	●	25	25	25	150	141,7	29,3	32						
PSSN R/L 3225 P12	●	❑	32	32	25	170	161,7	29,3	32						
PSSN R/L 2525 M15	●	●	25	25	25	150	139,8	32	32	LCL5SD	LCS5B-SD	LSS53SD	LSP5SD	LH030	❷
PSSN R/L 3225 P15	❑		32	32	25	170	159,8	32	32						
PSSN R/L 3232 P15	●	❑	32	32	32	170	159,8	32	40						
PSSN R/L 3232 P19	●	●	32	32	32	170	157,5	40,2	40	LCL6SD	LCS6B-SD	LSS63SD	LSP6SD	LH040	❸

General Turning and Facing

PTGN





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PTGN R/L 1616 H16	●	●	16	16	16	100	20	20	LCL3SD	LCS3TB-SD	LST317SD	LSP3SD	LH025	❶
PTGN R/L 2020 K16	●	●	20	20	20	125	20	25						
PTGN R/L 2525 M16	●	●	25	25	25	150	22,2	32						
PTGN R/L 2525 M22	●	●	25	25	25	150	28,7	32	LCL4SD	LCS42BS-SD	LST42SD	LSP4SD	LH030	❷
PTGN R/L 3225 P22	●		32	32	25	170	28,7	32						
PTGN R/L 3232 P22	●	●	32	32	32	170	28,7	32						

PTFN





Inserts



Spare Parts



Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PTFN R/L 1616 H16	●	●	16	16	16	100	19,7	20	LCL3SD	LCS3TB-SD	LST317SD	LSP3SD	LH025	❶
PTFN R/L 2020 K16	●	●	20	20	20	125	20,2	25						
PTFN R/L 2525 M16	●	●	25	25	25	150	20,2	32						
PTFN R/L 2525 M22	●	❑	25	25	25	150	25,2	32	LCL4SD	LCS42BS-SD	LST42SD	LSP4SD	LH030	❷
PTFN R/L 3225 P22	●	●	32	32	25	170	25,2	32						

PTTN





Inserts



Spare Parts



Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PTTN R/L 2020 K16	❑	❑	20	20	20	125	25,9	17	LCL3SD	LCS3TB-SD	LST317SD	LSP3SD	LH025	❶
PTTN R/L 2525 M16	●		25	25	25	150	25,9	22						
PTTN R/L 3225 P22		●	31	32	25	170	31,9	22	LCL4SD	LCS42BS-SD	LST42SD	LSP4SD	LH030	❷

● = Euro stock
○ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

General Turning and Copying

MTJN





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Wedge	Shim pin	Shim	Clamp bold	Nut	Ring	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF								
MTJN R/L 2020-33 (K16)	●	●	20	20	20	125	37	25	MMW30	MP317 / MP320	STW323	BHA0525 4,0 Nm	CPM32N	ER04	LH030	❶
MTJN R/L 2525-33 (M16)	●	●	25	25	25	150	37	32								
MTJN R/L 2525-43 (M22)	●	●	25	25	25	150	37	32	MMW40	MP420	STW434	BHA0625 4,5 Nm	CPM43N	ER05	LH030 / LH040	❷
MTJN R/L 3225-43 (P22)	❍	❍	32	32	25	170	37	32								

MTXN





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Wedge	Shim pin	Shim	Clamp bold	Nut	Ring	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF								
MTXN R/L 2020-33 (K16)	❍	❍	20	20	20	125	32	25	MMW30	MP317 / MP320	STW323	BHA0525 4,0 Nm	CPM32N	ER04	LH030	❶
MTXN R/L 2525-33 (M16)	❍	❍	25	25	25	150	32	32								
MTXN R/L 2525-43 (M22)	❍		25	25	25	150	38	32	MMW40	MP420	STW434	BHA0625 4,5 Nm	CPM43N	ER05	LH030, 040	❷

General Turning and Facing

MWLN





Inserts

Eg.

❶ WNMG 080408 N-GU
❷ WNMM 080412 N-HG

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Wedge	Shim pin	Shim	Clamp bold	Nut	Ring	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF								
MWLN R/L 2020-43 (K08)	❍	❑	20	20	20	125	32	25	MWW40	MP416	SWW433	BHA0625	CPM43S	ER04	LH030 LH040	❶,❷
MWLN R/L 2525-43 (M08)	●	●	25	25	25	150	32	32		MP420		4,5 (N·m)	CPM43N			
MWLN R/L 3225-43 (P08)	❑	❍	32	32	25	170	32	32								

P Type Lever Lock Holders

PWLN





Inserts

Eg.

❶ WNMG 060408 N-SU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Lever pin	Clamp bolt	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF						
PWLN R/L 2020 K06 (PWLN R/L 2020-33)	●	❑	20	20	20	125	27	25	LCL3SD	LCS3TB-SD	LSW317	LSP3SD	LH025	❶
PWLN R/L 2525 M06	●	❑	25	25	25	150	27	32						

● = Euro stock
○ = Japan stock
❑ = Delivery on request
(N·m) Recommended Tightening Torque (N·m)

C Type Top Clamp Holders

CCLN



Fig.1



Fig.2



Inserts

❶ CNGN0903 **
❷ CNGN1203 **
❸ CNGN1204 **

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	H	HF	B	LF	LH	WF	WF2	Fig.	Clamp	Insert protector	Clamp bolt	Shim	Shim pin	Wrench		Insert
CCLN R/L 2525 M09	❑		25	25	25	150	25	32	7	1	CCM8UL	CBC0903	WB8-22T	SCN0903	SPP3	LT27		❶
CCLN R/L 2525 M12-03			25	25	25	150	30	32	7	1		CBC4		SCND433				❷
CCLN R/L 2525 M12-04	❑		25	25	25	150	30	32	7	2	CCM8-LONG	CBC4	WB8-30	SCND433	SPP3	LH040		❸

CSBN



Fig.1



Fig.2



Inserts

❶ SNGN0903 **
❷ SNGN1203 **
❸ SNGN1204 **

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	H	HF	B	LF	LH	WF	WF2	Fig.	Clamp	Insert protector	Clamp bolt	Shim	Shim pin	Spring	Wrench	Insert
CSBN R/L 2525 N09	❑		25	25	25	160	30	21,5	-	1	CCM8UL	CBS13	WB8-22T	SSN0903	-	-	LH040	❶
CSBN R/L 2525 N12-03	❑		25	25	25	160	35	21,5	-	1		CBS14		SSND423				❷
CSBN R/L 2525 N12-04	❑		25	25	25	160	33	21,5	-	2	DC-R/L 1	CBD 4 R/L	BH 0830 R/L	SSND423	SPP3	DSP5	LH040	❸

CSKN



Fig.1



Fig.2



Inserts

❶ SNGN0903 **
❷ SNGN1203 **
❸ SNGN1204 **

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	H	HF	B	LF	LH	WF	WF2	Fig.	Clamp	Insert protector	Clamp bolt	Shim	Shim pin	Spring	Wrench	Insert
CSKN R/L 2525 N09	❑		25	25	25	160	25	32	7	1	CCM8UL	CBS13	WB8-22T	SSN0903	-	-	LH040	❶
CSKN R/L 2525 N12-03	❑		25	25	25	160	25	32	7	1		CBS14		SSND423				❷
CSKN R/L 2525 N12-04	❑		25	25	25	160	21	32	7	2	DC-R/L 1	CBD 4 R/L	BH 0830 R/L	SSND423	SPP3	DSP5	LH040	❸

C Type Top Clamp Holders

CRDN





Inserts

❶ RNGN0903**
❷ RNGN1203**
❸ RNGN1204**

Spare Parts

Holders

Cat. No.	Stock	Dimensions (mm)							Clamp	Double screw	Shim	Shim pin	Wrench	Insert
		H	HF	B	LF	LH	WF	CDX						
CRDNN 2525 M09	●	25	25	25	150	35	-	15	CCM8-LONG	WB8-22T	SRND32	SPP3	LT27	❶
CRDNN 2525 M12-03	●	25	25	25	150	35	-	20			SRND42			❷
CRDNN 2525 M12-04	●	25	25	25	150	35	-	20						❸

CRSN





Inserts

❶ RNGN0903**
❷ RNGN1203**
❸ RNGN1204**

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Clamp	Double screw	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF	WF2						
CRSN R/L 2525 M09	●	●	25	25	25	150	30	32	7	CCM8-LONG	WB8-22T	SRND32	SPP3	LT27	❶
CRSN R/L 2525 M12-03	●	●	25	25	25	150	30	32	7			SRND42			❷
CRSN R/L 2525 M12-04	●	●	25	25	25	150	30	32	7						❸

● = Euro stock

X Type Dimple Lock Holders

XSBN





Inserts

❶ SNGX1204**

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)						Clamp	Clamp bolt	Shim	Shim pin	Spring	Wrench		Insert
	R	L	H	HF	B	LF	LH	WF								
XSBN R/L 2525 N12	●		25	25	25	160	38	21,5	DSLX8	BH0825	SSND423	SPP3	GSP10	LH050		❶

XCLN





Inserts

❶ CNGX1204**

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Clamp	Clamp bolt	Shim	Shim pin	Spring	Wrench		Insert
	R	L	H	HF	B	LF	LH	WF	WF2								
XCLN R/L 2525 N12	●		25	25	25	150	33	32	7	DSLX8	BH0825	SCND433	SPP3	GSP10	LH050		❶

External Mini Holders





Back-Turning Tool Holder SBT Type

Sharp cutting edges with good surface finish.
Max. reach of insert 8,0 mm, edge width 2,5 mm

Cut-off Tool Holder SCT Type

Easy insert change by just loosening the screw from the back.
Max. cut-off dia. Ø 5 mm, Ø 12 mm, Ø 16 mm

PDJCR type
lever lock holder



External Mini Holders

In 1984, Sumitomo Electric Hardmetal first released the Mini Tool Holder series for the machining of small components in small NC autolathes.
A full range of insert grades comprising of the Cermet T1500A, SUMIBORON BN2000, SUMIDIA DA1000 and especially AC530U, was also introduced to meet a variety of machining requirements.

Grade Selection

Category	Application Range			Work Material					
				P	M	K	S	H	N
	High Precision	Finish-Light Cut	Medium Cut	General Steel	Stainless Steel	Cast Iron	Heat Resistant Alloy	Hardenend Steel	Non-Ferrous Metal
Coated Carbide (PVD)	ACZ150			◎	◎				○
	New AC5015S			○	◎	○	◎		
	New AC5025S			○	◎	○	◎		
	AC530U			◎	◎	○	○		○
	AC1030U			◎	◎	○	○		○
Cermet/Coated Cermet	T1000A			◎	○	◎			○
	T1500A / T1500Z			◎	○	○			○
Carbide	BL130			○	○	○			○
		H1		○	○	○			◎
		EH510		○	○	○	◎		○
CBN (SUMIBORON)		BN1000 / BN2000						◎	
		BN7000				◎	○		
SUMIDIA		DA1000							◎

◎ Preferred Choice ○ Suitable

Recommended Cutting Conditions

Work Material / Grade	P Free Cutting Steel		P Carbon Steel		M Stainless Steel		S Heat Resistant Alloy		H Hardened Steel		N Aluminium		N Brass	
	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)	v_c (m/min)	f (mm/rev)
ACZ150	50–200	0,02–0,10	50–150	0,01–0,08	50–150	0,01–0,05					70–300	0,05–0,20	70–300	0,05–0,20
AC5015S	50–200	0,02–0,15	50–200	0,02–0,10	*50–200	*0,02–0,10							70–300	0,05–0,20
AC5025S	50–200	0,02–0,15	50–200	0,02–0,10	*50–200	*0,02–0,10	30–100	0,02–0,10					70–300	0,05–0,20
AC530U	50–200	0,02–0,15	50–200	0,02–0,10	*50–200	*0,02–0,10	30–100	0,02–0,10					70–300	0,05–0,20
AC1030U	50–200	0,02–0,15	50–200	0,02–0,10	*50–200	*0,02–0,10							70–300	0,05–0,20
T1000A	50–200	0,02–0,15	50–200	0,02–0,10	*50–150	*0,02–0,10					70–300	0,05–0,20	70–300	0,05–0,20
T1500A	50–200	0,02–0,15	50–200	0,02–0,10	*50–150	*0,02–0,10					70–300	0,05–0,20	70–300	0,05–0,20
T1500Z	50–200	0,02–0,15	50–200	0,02–0,10	*50–150	*0,02–0,10					70–300	0,05–0,20	70–300	0,05–0,20
BN1000									120–300	0,03–0,15				
BN2000									50–200	0,03–0,20				
BN7000							50–200	0,05–0,20						
DA1000											70–300	0,02–0,10	70–300	0,02–0,10

* Please use maximal possible C/speed

Special Mini Holders for Back Facing

SBT





SBT35 R1010:



Holders

Above figures show right hand tools.

Cat. No.	Stock	Dimensions (mm)							Screw	(N·m)	Wrench		Insert
		H	HF	B	LF	WF							
SBT 35-R 1010	●	10	10	10	120	7,5			BFTX0307N	**2,0**	TRX10		BTR 35_ _
SBT 35-R 1212	●	12	12	12	120	9,5							
SBT 35-R 1616	●	16	16	16	120	13,5							

Spare Parts


Inserts

Coated carbide Uncoated Cermet

BTR

Cat. No.	Stock				Dimensions (mm)			
	AC1030U	AC530U	ACZ310	T1500A	L	CDX	CW	RE
BTR 3505	❍		▲	❍	15	3,5	2,5	0,05
BTR 3515	❍	❍	▲	❍	15	3,5	2,5	0,15



Sharp cutting edge with 15° rake angle



Wide groove breaker for smooth chip evacuation

● Surface roughness comparision




BTR 3505 P10 des Wettbewerbs

Work Material: C45
Insert: BTR3505 (ACZ310)
Cutting Data: v_c = 80 m/min, f = 0,04 mm/rev
a_p = 3,0 mm, Wet

Recommended Cutting Data (SBT type)

Work Material	Tooling	v_c (m/min)	f (mm/rev)
General steel	Grooving	50–150	0,02–0,05
	Back facing		0,02–0,10
Free-cutting steel	Grooving	50–150	0,02–0,10
	Back facing		0,02–0,15
Stainless steel	Grooving	50–150	0,02–0,04
	Back facing		0,02–0,06

● = Euro stock
○ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
(N·m) Recommended Tightening Torque (N·m)

External Mini Tool Holders
PC/SC Type

P Type Lever Lock Holders

PCLC





PCLC R/L0810-K06:



Inserts

Eg.



❶ CCGT 060202 R-FX
❷ CCMT 09T304 N-SU

R-FX N-SU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Lever pin	Clamp screw	Side pin	Wrench	Insert
	R	L	H	HF	B	LF	WF							
PCLC R/L 0810 K06	❑		8	8	10	125	10,5			LCL 06	BTT 0407	LP 07	TH 020	❶
PCLC R/L 1010 K06	●	❑	10	10	10	125	10,5							
PCLC R/L 1212 K09	●	●	12	12	12	150	12,5			LCL 09	BTT 0411	LP 06		❷
PCLC R/L 1616 K09	●		16	16	16	150	16,5							

S Type Screw Lock Holders

SCLC





Inserts

Eg.



❶ CCGT 060202 R-FX
❷ CCMT 09T304 N-SU
❸ CCMT 120408 N-SU

R-FX N-SU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
SCLC R/L 0808 D06	●	●	8	8	8	60	10			BFTX02506N	1,5	TRX08		❶
SCLC R/L 1010 E06	●	●	10	10	10	70	12							
SCLC R/L 1212 F09	●	●	12	12	12	80	16			BFTX0409N	3,4	TRX15		❷
SCLC R/L 1616 H09	❑	●	16	16	16	100	20							
SCLC R/L 2020 H09	●	❑	20	20	20	100	25							
SCLC R/L 2020 K09	●	●	20	20	20	125	25							
SCLC R/L 2020 K12	●	●	20	20	20	125	25			BFTX0511N	5,0	TRX20		❸
SCLC R/L 2525 M12	●	●	20	25	25	150	32							

SCAC





Inserts

Eg.

❶ CCGT 060202 R-FX
❷ CCMT 09T304 N-SU

R-FX N-SU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
SCAC R/L 0808 D06	●	❑	8	8	8	60	8,5			BFTX02506N	1,5	TRX08		❶
SCAC R/L 1010 E06	●	❑	10	10	10	70	10,5							
SCAC R/L 1212 F09	●	❑	12	12	12	80	12,5			BFTX0409N	3,4	TRX15		❷

P Type Lever Lock Holders

PDJC





PDJC R/L0810-K07:



Inserts

Eg.

R-FX N-SU

❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Lever pin	Clamp screw	Side pin	Wrench	Insert
	R	L	H	HF	B	LF	WF							
PDJC R/L 0810 K07	●		8	8	10	125	10,5			LCL 06	BTT 0407	LP 04	TH 020	❶
PDJC R/L 1010 K07	●	●	10	10	10	125	10,5							
PDJC R/L 1212 M11	●	●	12	12	12	150	12,5			LCL 09		LP 07		❷
PDJC R/L 1616 M11	●	❍	16	16	16	150	16,5				BTT 0411			

S Type Screw Lock Holders

SDJ/HC



SDJC R/L



SDHC R/L



Inserts

Eg.

R-FX N-SU

❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
SDJC R/L 0808 D07	●	●	8	8	8	60	10			BFTX02506N	1,5	TRX08		❶
SDJC R/L 1010 E07	●		10	10	10	70	12							
SDJC R/L 1212 F07	●	●	12	12	12	80	16							
SDJC R/L 1616 H07	●	●	16	16	16	100	20							
SDJC R/L 2020 K07	●	●	20	20	20	125	25							
SDJC R/L 1212 F11	●	●	12	12	12	80	16			BFTX0409N	3,4	TRX15		❷
SDJC R/L 1616 H11	●	●	16	16	16	100	20							
SDJC R/L 2020 K11	●	●	20	20	20	125	25							
SDJC R/L 2525 M11	●	●	25	25	25	150	32							
SDHC R/L 1616 H11	●	●	16	16	16	100	20			BFTX0409N	3,4	TRX15		❷
SDHC R/L 2020 K11	●	●	20	20	20	125	25							
SDHC R/L 2525 M11	●	●	25	25	25	150	32							

● = Euro stock
○ = Japan stock

❑ = Delivery on request

N·m Recommended Tightening Torque (N·m)

S Type Screw Lock Holders

SDAC





Inserts

Eg.

R-FX N-SU

❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
SDAC R/L 0808 D07	❑	●	8	8	8	60	8,5			BFTX02506N	1,5	TRX08		❶
SDAC R/L 1010 E07	●	●	10	10	10	70	10,5							
SDAC R/L 1212 F11	●	●	12	12	12	80	12,5			BFTX0409N	3,4	TRX15		❷

SDNC





Inserts

Eg.

R-FX N-SU

❶ DCGT 070202 R-FX
❷ DCMT 11T304 N-SU

Spare Parts

Holders

Cat. No.	Stock	Dimensions (mm)							Screw	N·m	Wrench		Insert
		H	HF	B	LF	WF							
SDNCN 0808 D07	●	8	8	8	60	4,2			BFTX02506N	1,5	TRX08		❶
SDNCN 1010 E07	●	10	10	10	70	5,2							
SDNCN 1212 F07	●	12	12	12	80	6,2							
SDNCN 1616 H07	●	16	16	16	100	8,2							
SDNCN 2020 K07	●	20	20	20	125	10,2							
SDNCN 1212 F11	●	12	12	12	80	6,5			BFTX0409N	3,4	TRX15		❷
SDNCN 1616 H11	●	16	16	16	100	8,5							
SDNCN 2020 K11	●	20	20	20	125	10,5							
SDNCN 2525 M11	●	25	25	25	150	13							

External Holders for 7° RC_ _ pos. Inserts

P Type Lever Lock Holders

PRDCN



■ Inserts

Eg.

N-RP

❶ RCOO1003M0 N–RO
❷ RCOO1204M0 N–RO
❸ RCOO1606M0 N–RO
❹ RCOO2006M0 N–RO

■ Spare Parts

■ Holders

Cat. No.	Stock	Dimensions (mm)								Lever pin	Clamp screw	Shim	Shim pin	Wrench	Insert
		H	HF	B	LF	LH	WF	E1	IC						
PRDC N 2020 M10	●	20	20	20	150	22	15,0	1,0	10	LCL10	LCS10	LSR10	LSP10	LH020	❶
PRDC N 2525 M10	●	25	25	25	150	22	17,5	1,0	10						
PRDC N 2525 M12	●	25	25	25	150	24	18,5	1,2	12	LCL12	LCS12	LSR12	LSP10	LH025	❷
PRDC N 3225 Q12	●	32	32	25	180	24	18,5	1,2	12						
PRDC N 3225 Q16	●	32	32	25	180	28	20,5	1,5	16	LCL16	LCS16	LSR16	LSP16	LH025	❸
PRDC N 3232 Q20	●	32	32	32	180	32	26,5	1,7	20	LCL20	LCS20	LSR20	LSP20	LH030	❹

PRGC



■ Inserts

Eg.

N-RP

❶ RCOO 1003M0 N–RO
❷ RCOO 1204M0 N–RO
❸ RCOO 1606M0 N–RO
❹ RCOO 2006M0 N–RO

■ Spare Parts

■ Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Lever pin	Clamp screw	Shim	Shim pin	Wrench	Insert
	R	L	H	HF	B	LF	WF	E1	IC						
PRGC R/L 2020 K10	●	❍	20	20	20	125	25	1,5	10	LCL10	LCS10	LSR10	LSP10	LH020	❶
PRGC R/L 2525 M10	●	●	25	25	25	150	32	1,5	10						
PRGC R/L 2020 K12	●	❑	20	20	20	125	25	2,5	12	LCL12	LCS12	LSR12	LSP10	LH025	❷
PRGC R/L 2525 M12	❑	●	25	25	25	150	32	2,5	12						
PRGC R/L 3225 P12		❑	32	32	25	170	32	2,5	12						
PRGC R/L 2525 M16	●	❑	25	25	25	150	32	3,0	16	LCL16	LCS16	LSR16	LSP16	LH025	❸
PRGC R/L 3225 P16	●	❑	32	32	25	170	32	3,0	16						
PRGC R/L 3232 P20	●	❑	32	32	32	170	40	4,0	20	LCL20	LCS20	LSR20	LSP20	LH030	❹

● = Euro stock ❑ = Delivery on request Recommended Tightening Torque (N·m)

S Type Screw Lock Holders

SRDCN





Inserts

Spare Parts



Holders

Cat. No.	Stock	Dimensions (mm)								Screw	Shim	Screw	Wrench	Wrench	Insert
		H	HF	B	LF	LH	WF	E1	IC						
SRDC N 2020 K10T3	●	20	20	20	125	25	15,0	1,0	10	BFTX03510-SD 2,0 Nm	SRNS 103-SD	BW 0508F-SD	TRX 15 IP-35	LH 035	❶
SRDC N 2525 M10T3	●	25	25	25	150	25	17,5	1,0	10						
SRDC N 2525 M12	●	25	25	25	150	28	18,5	1,2	12	BFTX03512-SD 2,0 Nm	SRNS 123-SD				❷
SRDC N 3225 P12	●	32	32	25	170	28	18,5	1,2	12						
SRDC N 2525 M16	❑	25	25	25	150	35	20,5	1,5	16	BFTX0517-SD 5,0 Nm	SRNS 164-SD	BW 0810F-SD	LT 20 IP	LH 050	❸
SRDC N 3225 P16	●	32	32	25	170	35	20,5	1,5	16						
SRDC N 3232 P20	●	32	32	32	170	40	26,0	1,7	20	BFTX0618-SD 7,5 Nm	SRNS 204-SD	BW 0912F-SD	LT 25 IP	LH 060	❹

SRSC





Inserts

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)							Screw	Shim	Screw	Wrench	Wrench	Insert
	R	L	H	HF	B	LF	WF	E1	IC						
SRSC R/L 2020 K10T3	●	●	20	20	20	125	25	1,5	10	BFTX 03510-SD 2,0 Nm	SRNS 103-SD	BW 0508F-SD	TRX 15 IP-35	LH 035	❶
SRSC R/L 2525 M10T3	●	●	25	25	25	150	32	1,5	10						
SRSC R/L 2525 M12	●	●	25	25	25	150	32	2,5	12	BFTX 03512-SD 2,0 Nm	SRNS 123-SD				❷
SRSC R/L 3225 P12	●	●	32	32	25	170	32	2,5	12						
SRSC R/L 3225 P16	●	●	32	32	25	170	32	3,0	16	BFTX 0517-SD 5,0 Nm	SRNS 164-SD	BW 0810F-SD	LT 20 IP	LH 050	❸
SRSC R/L 3232 P20	●	●	32	32	32	170	40	4,0	20	BFTX 0618-SD 7,5 Nm	SRNS 204-SD	BW 0912F-SD	LT 25 IP	LH 060	❹

Mini Holders for 7° SC_ _ pos. Inserts



S Type Screw Lock Holders

SSBC





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
SSBC R/L 1010 E07	❑	❑	10	10	10	70	9			BFTX0307N	2,0	TRX10		❶
SSBC R/L 1212 F09	❑	❑	12	12	12	80	11			BFTX0409N	3,4	TRX15		❷
SSBC R/L 1616 H09	❑	❑	16	16	16	100	13							
SSBC R/L 2020 K12	❑	❑	20	20	20	125	17			BFTX0511N	5,0	TRX20		❸
SSBC R/L 2525 M12	▲	▲	25	25	25	150	22							

● = Euro stock
❑ = Delivery on request
▲ = To be replaced by new item
N·m Recommended Tightening Torque (N·m)

S Type Screw Lock Holders

STAC



■ Inserts



■ Holders

Above figures show right hand tools.

■ Spare Parts

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
STAC R/L 0808 D09	●		8	8	8	60	8,5			BFTX02205N	1,1	TRX06		❶
STAC R/L 1212 F11	●		12	12	12	80	12,5			BFTX02506N	1,5	TRX08		❷

STGC



■ Inserts



■ Holders

Above figures show right hand tools.

■ Spare Parts

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
STGC R/L 0808 D09			8	8	8	60	10			BFTX02205N	1,1	TRX06		❶
STGC R/L 1010 E09	●	●	10	10	10	70	12							
STGC R/L 1212 F11	●	●	12	12	12	80	16			BFTX02506N	1,5	TRX08		❷
STGC R/L 1616 H11	●	●	16	16	16	100	20							
STGC R/L 1616 H16	●	●	16	16	16	100	20			BFTX0409N	3,4	TRX15		❸
STGC R/L 2020 K16	●	●	20	20	20	125	25							
STGC R/L 2525 M16	❑	❑	25	25	25	150	32							



S Type Screw Lock Holders

SVJB





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Stopper	Nut	Shim	Wrench	Scew	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF	WF2							
SVJB R/L 1212 F11	●	●	12	12	12	80	25	16	4,5	-	-	-	-	BFTX02508NV 1,5 (N·m)	TRX08	❶
SVJB R/L 1616 H11	●	●	16	16	16	100	25	20	4,5							
SVJB R/L 2020 K16	●	●	20	20	20	125	41	25	5,0	VP20						
SVJB R/L 2525 M16	●	●	25	25	25	150	41	32	7,0	VP25	CPV33N	SVP32	LH025	BFTX03508 2,0 (N·m)	TRX10	❷
SVJB R/L 3225 P16	●	●	32	32	25	170	41	32	7,0	VP32						

SVPB





Inserts



Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Stopper	Nut	Shim	Wrench	Scew	Wrench	Insert
	R	L	H	HF	B	LF	LH	WF	WF2							
SVPB R/L 1212 F11	●	❑	12	12	12	80	25	16	4,5	-	-	-	-	BFTX02508NV 1,5 (N·m)	TRX08	❶
SVPB R/L 1616 H11	●	●	16	16	16	100	25	20	4,5							
SVPB R/L 2020 K16	●	●	20	20	20	125	36	25	5,0	VP20						
SVPB R/L 2525 M16	●	●	25	25	25	150	36	32	7,0	VP25	CPV33N	SVP32	LH025	BFTX03508 2,0 (N·m)	TRX10	❷
SVPB R/L 3225 P16	●	●	32	32	25	170	36	32	7,0	VP32						

SVVB





Inserts



Spare Parts

Holders

Cat. No.	Stock	Dimensions (mm)						Stopper	Nut	Shim	Wrench	Scew	Wrench	Insert
		H	HF	B	LF	LH	WF							
SVVB M 1212 F11	●	12	12	12	80	-	6	-	-	-	-	BFTX02508NV 1,5 (N·m)	TRX08	❶
SVVB N 1616 H11	●	16	16	16	100	-	8							
SVVB N 2020 K16	●	20	20	20	125	-	10	VP20						
SVVB N 2525 M16	●	25	25	25	150	-	12,5	VP25	CPV33N	SVP32	LH025	BFTX03508 2,0 (N·m)	TRX10	❷
SVVB N 3225 P16	●	32	32	25	170	-	12,5	VP32						

● = Euro stock ❑ = Delivery on request (N·m) Recommended Tightening Torque (N·m)

External Mini Tool Holders
SV Type

S Type Screw Lock Holders





Inserts

Eg.

R-FX

❶ VCGT 110302 R-FX

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)							Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	WF							
SVLC R/L 1010 H11	●	●	10	10	10	100	10,5			BFTX02508NV	1,5	TRX08		❶
SVLC R/L 1212 H11	●	●	12	12	12	100	12,5							
SVLC R/L 1616 H11	●	●	16	16	16	100	16,5							
SVLC R/L 2525 M11	●		20	20	20	150	25,5							





Inserts

Eg.

R-FX

❶ VCGT 110302 R-FX

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)								Screw	N·m	Wrench		Insert
	R	L	H	HF	B	LF	LH	WF	WF2						
SVPC R/L 1010 H11	❑	❑	10	10	10	100	-	14,5	4,5		BFTX02508NV	1,5	TRX08		❶
SVPC R/L 1212 H11	●	●	12	12	12	100	-	16,5	4,5						
SVPC R/L 1616 H11	●	●	16	16	16	100	-	20,5	4,5						

Polygon - Shank Holder

Features

The Sumitomo polygon shank holders enable an extremely high stiffness connection between machine and tool. The conical polygon can take high bending and torque moments based on the combination of the face contact to the spindle.
This self-guiding coupling system offers high precision and a repeatability of ± 2 µm in X, Y and Z axis.
While using this easy and quick coupling system it is possible to gain higher machine utilization time as the set-up and tool change times are reduced.
The compact design and the high stiffness connection to the spindle offer a versatile use e.g. on multi-task machines, machining centers and turning-milling centers.

Characteristics

- original SUMITOMO D-type double clamping system
- compact design
- monoblock system - no additional interfaces
- precise positioning; self-guiding with high repeatability
- high stiffness supported by face contact of holder
- carbide shims to prevent holders from damage
- simple tool holder change and low-maintenance operation
- internal coolant supply directly to the cutting edge
- Polygon shank and insert seat hardened for long holder life

Polygon - shank holder - produced according to ISO 26623-1

Negative Insert Type

Positive Insert Type

Classification System for Polygon - Shank Holder

P S C 4 0 - D C L N R 2 7 0 5 0 - 1 2

Polygon Shank	Size (DCSFMS)	Clamping System D: Double Clamp S: Screw Clamp		Holder Style		Feed Direction R: Right Hand L: Left Hand N: Neutral	Size (WF)	Holder Length (LF)		Insert Cutting Edge Length
			Insert Shape		Seat Clearance Angle N = 0° C = 7° P = 11°					

● = Euro stock

Recommended Tightening Torque (N·m)

General Turning, Copying and Facing

DCLN





Right hand shown.

■ Inserts

CNMG1204_ _ NGE
(Representative example)

■ Spare Parts



■ Holders

Cat. No.	Stock		Dimensions (mm)			Applicable Insert	Clamp Set	N·m	Shim	Shim Screw	Shim Wrench	Wrench
	R	L	LF	WF	DCSFMS							
PSC40 DCLN R/L 27050-12	●	●	50	27	40	CN□□ 1204	SCP-2	5,0	CNS1204	BFTX0409N	TRX15 (*)	LH040
PSC50 DCLN R/L 35060-12	●	●	60	35	50							

DDJN





Right hand shown.

■ Inserts

DNMG1506_ _ NGE
(Representative example)

■ Spare Parts



■ Holders

Cat. No.	Stock		Dimensions (mm)			Applicable Insert	Clamp Set	N·m	Shim	Shim Screw	Shim Wrench	Wrench
	R	L	LF	WF	DCSFMS							
PSC40 DDJN R/L 27055-15	●	●	55	27	40	DN□□ 1506	SCP-2	5,0	DNS1506	BFTX0409N	TRX15 (*)	LH040
PSC50 DDJN R/L 35060-15	●	●	60	35	50							

DDHN





Right hand shown.

■ Inserts

DNMG1506_ _ NGE
(Representative example)

■ Spare Parts



■ Holders

Cat. No.	Stock		Dimensions (mm)			Applicable Insert	Clamp Set	N·m	Shim	Shim Screw	Shim Wrench	Wrench
	R	L	LF	WF	DCSFMS							
PSC40 DDHN R/L 27055-15	●	●	55	27	40	DN□□ 1506	SCP-2	5,0	DNS1506	BFTX0409N	TRX15 (*)	LH040
PSC50 DDHN R/L 35060-15	●	●	60	35	50							

DSBN





Right hand shown.

■ Inserts

SNMG1204_ _ NGE
(Representative example)

■ Spare Parts



■ Holders

Cat. No.	Stock		Dimensions (mm)			Applicable Insert	Clamp Set	N·m	Shim	Shim Screw	Shim Wrench	Wrench
	R	L	LF	WF	DCSFMS							
PSC40 DSBN R/L 22050-12	●	●	50	22	40	SN□□ 1204	SCP-2	5,0	SNS1204	BFTX0409N	TRX15 (*)	LH040
PSC50 DSBN R/L 27060-12	●	●	60	27	50							

(*) Item is sold separately.

General Turning and Facing

DTJN









Right hand shown.

Inserts

TNMG1604_ _ NGE
(Representative example)

Spare Parts

Holders

Cat. No.	Stock		Dimensions (mm)			Applicable Insert	Clamp Set	(N·m)	Shim	Shim Screw	Shim Wrench	Wrench
	R	L	LF	WF	DCSFMS							
PSC40 DTJN R/L 27050-16	●	●	50	27	40	TN□□ 1604	SCP-1	5,0	TNS1604	BFTX0307N	TRX15 (*)	LH040
PSC50 DTJN R/L 35060-16	●	●	60	35	50							

DWLN









Right hand shown.

Inserts

WNMG0804_ _ NSE
(Representative example)

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)			Applicable Insert	Clamp Set	(N·m)	Shim	Shim Screw	Shim Wrench	Wrench
	R	L	LF	WF	DCSFMS							
PSC40 DWLN R/L 27050-06	●	●	50	27	40	WN□□ 06	SCP-1	5,0	WNS0604	BFTX0307N	TRX15 (*)	LH040
PSC50 DWLN R/L 35060-06	●	●	60	35	50							
PSC40 DWLN R/L 27050-08	●	●	50	27	40	WN□□ 08	SCP-2	5,0	WNS0804	BFTX0409N	TRX15 (*)	LH040
PSC50 DWLN R/L 35060-08	●	●	60	35	50							

(*) Item is sold separately.

● = Euro stock

(N·m) Recommended Tightening Torque (N·m)

General Turning, Copying and Facing

SCLC





Right hand shown.

■ Inserts

CCMT09T3_ _ NSU
(Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	L_1	f	DCSFMS							
PSC40 SCLC R/L 27050-09	●	●		50	27	40	CC□□ 09T3	CCS09T3	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SCLC R/L 35060-09	●	●		60	35	50							

SDJC





Right hand shown.

■ Inserts

DCMT11T3_ _ NMU
(Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SDJC R/L 27050-11	●	●		50	27	40	DC□□ 11T3	DCS11T3	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SDJC R/L 35060-11	●	●		60	35	50							

SDHC





Right hand shown.

■ Inserts

DCMT11T3_ _ NMU
(Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SDHC R/L 27050-11	●	●		50	27	40	DC□□ 11T3	DCS11T3	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SDHC R/L 35060-11	●	●		60	35	50							

SSBC





Right hand shown.

■ Inserts

SCMT1204_ _ NMU
(Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SSBC R/L 22050-12	●	●		50	22	40	SC□□ 1204	SCS1204	KGBS1221	KSS1221	4,5	LT15K	LH045K*
PSC50 SSBC R/L 27060-12	●	●		60	27	50							

(*) Item is sold separately.

General Turning, Copying and Facing

STJC





Right hand shown.

■ Inserts

TCMT16T3_ _ NSU (Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 STJC R/L 27050-16	●	●		50	27	40	TC□□ 16T3	TCS16T3	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 STJC R/L 35060-16	●	●		60	35	50							

SVJB





Right hand shown.

■ Inserts

VBMT1604_ _ NSU (Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SVJB R/L 27050-16	●	●		50	27	40	VB□□ 1604	VCS1604	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SVJB R/L 35060-16	●	●		60	35	50							

SVVB





Right hand shown.

■ Inserts

VBMT1604_ _ NSU (Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SVVB N 00050-16			●	50		40	VB□□ 1604	VCS1604	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SVVB N 00060-16			●	60		50							

SVHB





Right hand shown.

■ Inserts

VBMT1604_ _ NSU (Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SVHB R/L 27050-16	●	●		50	27	40	VB□□ 1604	VCS1604	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SVHB R/L 35060-16	●	●		60	35	50							

(*) Item is sold separately.

● = Euro stock

N·m Recommended Tightening Torque (N·m)

General Turning, Copying and Facing

SVJC





Right hand shown.

■ Inserts

VCMT1604_ _ NSU
(Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SVJC R/L 27050-16	●	●		50	27	40	VC□□ 1604	VCS1604	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SVJC R/L 35060-16	●	●		60	35	50							

SVVC





Right hand shown.

■ Inserts

VCMT1604_ _ NSU
(Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SVVC N 00050-16			●	50		40	VC□□ 1604	VCS1604	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SVVC N 00060-16			●	60		50							

SVHC



Right hand shown.

■ Inserts

VCMT1604_ _ NSU
(Representative example)

■ Spare Parts

■ Holders

Cat. No.	Stock			Dimensions (mm)			Applicable Insert	Shim	Shim Screw	Insert Screw	N·m	Wrench	Shim Wrench
	R	L	N	LF	WF	DCSFMS							
PSC40 SVHC R/L 27050-16	●	●		50	27	40	VC□□ 1604	VCS1604	KGBS1111	KSS1111	3,5	LT15K	LH035K*
PSC50 SVHC R/L 35060-16	●	●		60	35	50							

(*) Item is sold separately.

Boring Bars

E

E1–E24

Boring Tools Selection

According to Applications / Bore Diameter

■ BORING TOOLS

Coloured boxes indicate available size.

Application	Type	Boring Depth (L/D) Shank: Steel	Carbide	X-Bar (Steel)	Applicable Insert	Tooling	Min. Bore Diameter (mm) (Min. cutting diameter is shown when not matched in this table.)
Very Small Dia. Boring	BXBR ⇨ E24		–5		Special boring bar		○ 2 ○ 2,5 ○ 3 ○ 3,5 ○ 4 ○ 4,5 ○ 5
Very Small Dia. Boring	DABB ⇨M45		–2		Sumidia brazed		● 3 ● 4 ● 5 ● 7
Stop Boring	BSME ⇨M36–M38		–4		Sumiboron brazed		● 2,5 ● 3 ● 3,5 ● 4 ● 4,5 ● 5
Stop Boring	SEXC ⇨M36,37,39		–3		Sumiboron insert		● 4 ● 5 ● 6
Stop Boring	BNBB ⇨M40		–5		Sumiboron brazed		● 3,5 ● 4,5 ● 5,5 ● 6,5 ● 8,5
Stop Boring	BNB ⇨M41		–4		Sumiboron insert		● 10 ● 12 ● 14 ● 16 ● 18 ● 20
Stop Boring	S/C-SWUB ⇨ E23	–3	–8		Trigon Type 5° Pos.		● 5,5
Stop Boring	S-STFC ⇨ E19	–3			Triangle Type 5° & 11° Pos.		● 13 ● 16 ● 18 ● 20 ● 22 ● 25 ● 32 ● 35 ● 40 ● 44 ● 50
Stop Boring	B/D-STUP ⇨ E20			–6			● 10 ● 12 ● 14 ● 16 ● 18 ● 20 ● 22 ● 25 ● 40
Stop Boring	S-STUP(B) ⇨ E20	–3					● 8 ● 10 ● 12 ● 16 ● 18 ● 20 ● 22 ● 25
Stop Boring	C-STUP ⇨ E20		–8				● 8 ● 10 ● 12 ● 14 ● 16 ● 18 ● 20 ● 22 ● 25
Stop Boring	CTFP ⇨ Stock in Japan	–3			Triangle 11° Pos.		○ 16 ○ 18 ○ 20 ○ 22 ○ 25 ○ 32
Stop Boring	D-DTFN ⇨ E12	–3		–6	Triangle Neg. Type		● 32 ● 40 ● 50
Stop Boring	S-PTFN ⇨ E12						● 32 ● 40 ● 50
Bottom Facing	BNZ ⇨M33		–5		Sumiboron insert		● 8 ● 9 ● 11 ● 12 ● 16 ● 20 ● 22
Bottom Facing	S-SCLP ⇨ E15	–3			80 ° Diamond 11° Pos. Type		● 12 ● 16 ● 18 ● 20 ● 22 ● 25
Bottom Facing	B-SCLP ⇨ Stock in Japan			–6			○ 14 ○ 16 ○ 18 ○ 20
Bottom Facing	C-SCLP ⇨ E15		–8				● 12 ● 16 ● 18 ● 20
Bottom Facing	B/D-SCLC ⇨ E14			–6	80 ° Diamond 7° Pos. Type		● 10 ● 12 ● 14 ● 16 ● 18 ● 20 ● 22 ● 32 ● 40
Bottom Facing	S-SCLC ⇨ E14	–3					● 13 ● 16 ● 18 ● 20 ● 22 ● 25 ● 32 ● 40 ● 50
Bottom Facing	C-SCLC ⇨ Stock in Japan		–8				○ 5 ○ 6 ○ 7 ○ 8 ○ 10 ○ 12 ○ 13 ○ 14 ○ 16 ○ 20 ○ 22
Bottom Facing	D-DCLN ⇨ E8			–6	80 ° Diamond Neg. Type		● 32 ● 40 ● 50
Bottom Facing	S-PCLN ⇨ E8	–3					● 25 ● 30 ● 32 ● 40 ● 50 ● 63
Bottom Facing	D-DWLN ⇨ E13			–6	Trigon Neg. Type		● 32 ● 40 ● 50
Bottom Facing	S-MWLN ⇨ E13	–3					● 32 ● 40 ● 50

2 2,5 3 3,5 4 4,5 5 6 7 8 10 12 13 14 16 18 20 22 25 28 35 44 54 70

● = Eurostock
○ = Japanstock

■ BORING TOOLS

Coloured boxes indicate available size.

Application	Type	Boring Depth (L/D) Shank: Steel	Carbide	X-Bar (Steel)	Applicable Insert	Tooling	Min. Bore Diameter (mm) 6	8	10	12	13	14	16	18	20	22	25	28	32	34	35	40	44	50	54	70
Copying	B/D-SDUC ⇨ E16			–6	55 ° Diamond 7° Pos. Type						●		●		●		●		●			●				
	S-SDUC ⇨E16	–3									●		●		●		●		●			●				
	C-SDUC ⇨ Stock in Japan		–8								❍		❍		❍		❍									
	B/D-SDQC ⇨ E17			–6							●		●		●		●		●			●				
	S-SDQC ⇨E17	–3									●		●		●		●		●							
	D-SVUB ⇨ E21			–6	35 ° Diamond Type 5° & 7° Pos.											●		● 27			●	●				
	S-SVUB ⇨ E22	–3														●		● 27			●	●				
	S-SVQB ⇨ E22	–3														●		● 27			●	●				
	B/C-SVQB ⇨ Stock in Japan		–8	–6											❍		❍									
	D-SVZB ⇨ E21			–6												●		● 27			●	●				
	S-SVZB ⇨ E22															●		● 27			●	●				
	D-DDUN ⇨ E9			–6	55 ° Diamond Neg. Type														●			●				
	S-PDUN ⇨ E9	–3																	●			●		●		❍ 63
Through Boring	S-SSKP ⇨ E18	–3			55 ° Diamond Neg. Type								●		●		●	●								
	C-SSKP ⇨ E18		–8										●		●											
	SSKC ⇨ Stock in Japan	–3			Square Type 7° Pos.										❍		❍		❍			❍				
	CSKP ⇨ Stock in Japan	–3			Square Type 11° Pos.										❍		❍									
	S-PSKN ⇨ E10	–3			Square Neg. Type														●			●		●		● 63
Grooving	GNDI ⇨ F11/F28																		●			●		●		
	GNDIS ⇨ F11/F30											❍	❍		❍		❍									
							6	8	10	12	13	14	16	18	20	22	25	28	32	34	35	40	44	50	54	70

Boring Tool Series

■ TOOLING SELECTION

Application		Stop Boring		Bottom Facing		Trough Boring	Copying		
Insert Type / System		Triangle	Poligon / Others	80° Diamond		Square	55° T-REX	55° Diamond	35° Diamond
Screw Lock	Steel	 **S-STFC** ⇨E19 **S-STUP**(B)⇨E20	 **S-SWUB** ⇨ E23	 **S-SCLC** ⇨ E14	 **S-SCLP** ⇨ E15	 **S-SSKP** ⇨ E18	–	 **S-SDUC** ⇨E16 **S-SDQC** ⇨E17	 **S-SVUB** (S-SVQB / S-SVZB) ⇨ E22
	Anti-vibration	 **B-STUP** ⇨ E20	–	 **B-SCLC** ⇨ E14	–		–	 **B-SDUC** ⇨E16 **B-SDQC** ⇨E17	–
	Anti-vibration with Oil Hole	 **D-STUP** ⇨ E20	–	 **D-SCLC** ⇨ E14			–	 **D-SDUC** ⇨E16 **D-SDQC** ⇨E17	 **D-SVUB** ⇨E21 **D-SVZB** ⇨E21
	Carbide	 **C-STUP** (C-STUB) ⇨ E20	 **C-SWUB** ⇨ E23	–	 **C-SCLP** ⇨ E15	 **C-SSKP** ⇨ E18	–	–	–
Lever Lock	Steel	 **S-PTFN** ⇨ E12	–	 **S-PCLN** ⇨ E8	–	 **S-PSKN** ⇨ E10	–	 **S-PDUN** ⇨ E9	–
Top Clamp	Anti-vibration with Oil Hole	 **D-DTFN** ⇨ E12	 **D-DWLN** ⇨E13	 **D-DCLN** ⇨ E8			–	 **D-DDUN** ⇨E9	–
	Steel	–	 **S-MWLN** ⇨ E13	–	–	–	 **S-DTR** ⇨ E11	–	–
CBN	Carbide	 **BNB** ⇨ M41	 **BNBB** ⇨ M40	 **BNZ** ⇨ M41					
		 **BSME** ⇨ M38	 **SEXC** ⇨ M39						
	Carbide					 **BXBR** ⇨ E24			

Boring Bars

■ Catalogue Classification System For Boring Holders

S	16	R	–	S	T	U	P	R	11	03 - 18
①		②		③	④	⑤	⑥	⑦		
Shank Material Chart 1	Shank Diameter (mm)	Shank Length Chart 2		Clamping System Chart 3	Insert Shape Chart 4	Holder Style Chart 5	Seat Clearance Angle Chart 6	Feed Direction Chart 7	Insert Cutting Edge Length (mm)	※ Insert Thickness (mm) / ※ Min. Bore Diameter (mm)

※ This code may only be included in some of the catalogue nos.

① Chart 1

Shank Material	
S	Steel
B	Steel with Anti-vibration Mechanism without Oil Hole
C	Carbide
D	Steel with Anti-vibration Mechanism with Oil Hole
E	Carbide with Oil Hole

② Chart 2

Shank Length			
Symbol	Length (mm)	Symbol	Length (mm)
F	80	P	170
G	90	Q	180
H	100	R	200
J	110	S	250
K	125	T	300
L	140	U	350
M	150	V	400
N	160	W	450

③ Chart 3

Clamping System					
Symbol	System	Structure	Symbol	System	Structure
C	Top Clamp		M	Top & Hole Clamp Type	
D	Double Clamp		P	Lever Lock Type (Insert is Supported by 1 face)	
E	Pin Lock Type (Insert is supported by 1 face)		S	Screw Clamp Type	

⑦ Chart 7

Feed Direction	
Symbol	Feed Direction
R	Right Hand Feed
L	Left Hand Feed
N	Neutral Feed

④ Chart 4

Insert Shape			
Symbol	Insert Shape	Symbol	Insert Shape
A	Parallellogram 85°	M	Rhombic 86°
B	Parallelogram 82°	O	Octagonal
C	Diamond 80°	P	Pentagonal
D	Diamond 55°	R	Round
E	Diamond 75°	S	Square
F	Diamond 50°	T	Triangular
H	Hexagonal	V	Diamond 35°
K	Parallelogram 55°	W	Trigon
L	Rectangular		

⑤ Chart 5

Holder Style					
Symbol	Shape	Offset	Symbol	Shape	Offset
A		Nil	N		Nil
B		Nil	Q		With Offset
D		Nil	R		With Offset
E		Nil	S		With Offset
F		With Offset	T		With Offset
G		With Offset	U		With Offset
J		With Offset	W		With Offset
K		With Offset	Y		With Offset
L		With Offset	Z		With Offset

⑥ Chart 6

Seat Clearance Angle	
Symbol	Relief Angle
A	3°
B	5°
C	7°
D	15°
E	20°
F	25°
G	30°
N	0°
P	11°
O	Special Angle

Boring Tool Series

General Features

Since being the first in 1976 to introduce indexable boring bars, Sumitomo Electric has been continuously developing a comprehensive range which includes the SEC-Small Hole boring bar series, high rigidity boring head series, with either steel / carbide shanks, and the latest anti-vibration mechanism - SumiTurn X-Bar series coupled with a wide variety of insert grades and chipbreakers, cover a whole range of process requirements.

Features

- Wide selection for various boring operations
- Minimum bore diameter from ø 5,5 mm onwards
- New anti-vibration boring bars, SumiTurn X-Bar.
- High rigidity head-design for small boring bars
- Wide selection of grades and chipbreakers available for various processes and work materials

Series SumiTurn X Bar

Good Chip Evacuation from new head design

Evacuates long chips

Evacuates short chips



Strong cross section to withstand high cutting force

Ribbed structure for maximum rigidity

Chatter Killer System - Eliminates Vibration

Unique structure of X-Bar head



The damper resists vibration

● New negative type "X Bar" with high performance double clamping system



Application Guide

● Carbide shank
Rigid shank for long high precision bores

● Anti-Vibration Steel Shank
Low cost solution for long precision bores - eliminates chatter - improves productivity and surface finish



SumiTurn X Bar

⚠ ATTENTION:

Please keep this area free to get the effect of "X Bar" chattering killer system



Boring Tool Series

■ Recommended Over Hang Length / Shank Diameter (L/D)

Type of boring bar	Over hang length (L/D) 1 2 3 4 5 6 7 8 9 10
● Steel Shank Rigid head design for low cost hole boring.	
● Anti-Vibration Type Shank Chatter killer system eliminates vibration - improves productivity - improves quality	(X-Bar for pos. inserts) (X-Bar for neg. inserts) SumiTurn X Bar
● Carbide Shank High rigidity shank for high accuracy hole boring.	

■ Grades

Tool Material		Process: High Precision / Finish~Light Cut / Medium Cut	Work Material: P General Steel	M Stainless Steel	K Cast Iron	S Heat Resistive Alloy	H Hardened Steel	N Non-Ferrous Metal	Powder Metal
Coated Carbide	CVD	New AC8015P	◎						
		AC8025P	◎		○				
		New AC8035P	◎	○					
		AC6020M	○	◎					
		AC6030M	○	◎					
		New AC4010K			◎				
		New AC4015K			◎				
		AC420K			◎				
	PVD	ACZ150	◎	◎					
		New AC5015S	○		○	◎		○	
		New AC5025S	○	○	○	◎			
		AC530U	◎	◎	○	○		○	
		AC1030U	◎	◎	○	○		○	
		AC6040M		◎					
Cermet		T1000A	◎	○	◎			○	○
Coated Cermet		T1500A/T1500Z	◎	○	○			○	
		T3000Z	◎	○	○				
Carbide		G10E			◎			○	
SumiBoron		BN1000					◎		
		BN2000					◎		
		BNC2010					◎		
		BNC2020					◎		
		BN7000			◎	○			○
		BN7500							◎
SumiDia		DA1000						◎	
		DA150						◎	

◎ Preferred choice ○ Suitable

■ Recommended Chip Breakers

● M-Class Finish-Light-Cut



● M-Class Light-Medium-Cut



● G-Class Ground Typ



● G-Class Breaker



D...DCLN / S...PCLN Type



Anti-vibration D type with oil hole



SumiTurn X Bar



Insert (eg.)

N-GU

■ Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	øD$_{min}$	Dimensions (mm) ød	h	ℓ_1	ℓ_2	f	γ	Insert (eg.)
D25T - DCLN R/L 1204-32	●	●	32	25	23	300	26	17	-12°	CN□□1204○○
D32T - DCLN R/L 1204-40	●	●	40	32	30	300	26	22	-10°	
D40U - DCLN R/L 1204-50	●	●	50	40	37	350	26	27	-10°	

■ Spare Parts

Clamp	Spring	Clamp bolt	Shim	Shim screw	Wrench	Wrench	
SCP-2			CNS1203B	BFTX0307N	TRX10(*)	LH040	LH025
			CNS1204B	BFTX0409N (Nm) 3,4	TRX15(*)		

(*) Note: Wrench (TRX type) for shim screw is not included.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

■ Holders



Tool holders (P type) with lever-lock system

S - PCLN R/L





Cat. No.	Stock R	Stock L	øD$_{min}$	d	h	l_1	l_2	f	γ	
S20S - PCLN R/L09	●	●	25	20	18	250	29	13	-11°	CN_ _ 0903_ _
S25T - PCLN R/L09	●	●	30	25	23	300	33	17	-10°	
S25T - PCLN R/L12	●	●	32	25	23	300	42	17	-10°	CN_ _ 1204_ _
S32U - PCLN R/L12	●	●	40	32	30	350	49	22	-11°	
S40V - PCLN R/L12	●	●	50	40	37	400	56	27	-10°	
S32U - PCLN R/L16	●		40	32	30	350	56	22	-11°	CN_ _ 1606_ _
S40V - PCLN R/L16	●	●	50	40	37	400	56	27	-10°	
S50W - PCLN R/L16	❑	❑	63	50	47	450	56	35	-11°	
S50W - PCLN R/L19	❑	❑	63	50	47	450	63	35	-11°	CN_ _ 1906_ _

All figures show right hand tools.

■ Applicable Inserts

Holder	Carbides, Cermets: Double sided	Carbides, Cermets: One sided	CBN, PCD
S - PCLN R/L			
S.....09	CNMG 0903_ _ NGU	-	-
S25T.....12	CNMG 1204_ _ NGU	CNMM 1204_ _ NMP	CNGA 1204_ _
S32U.....12	CNMG 1204_ _ NGU	CNMM 1204_ _ NMP	CNGA 1204_ _
S40V.....12	CNMG 1204_ _ NGU	CNMM 1204_ _ NMP	CNGA 1204_ _
S.....16	CNMG 1606_ _ NGU	CNMM 1606_ _ NMP	-
S.....19	CNMG 1906_ _ NGU	CNMM 1906_ _ NMP	-

■ Spare Parts

Holder	Lever pin	Clamp bolt	Shim	Shim pin	Wrench	
S - PCLN R/L						
S.....09	LCL3C-SD	LCS3B-SD	-	-	LH020	
S25T.....12	LCL4C-SD	LCS4B-SD	-	-	LH025	
S32U.....12	LCL4T-SD	LCS41BS-SD	LSC42SD	LSP4SD	LH030	
S40V.....12	LCL4SD	LCS42BS-SD	LSC42SD	LSP4SD	LH030	
S.....16	LCL5SD	LCS5B-SD	LSC53SD	LSP5SD	LH030	
S.....19	LCL5C-SD	LCS6B-SD	LSC63SD	LSP6SD	LH040	

● = Euro stock
❑ = Delivery on request

(Nm) Recommended Tightening Torque (N·m)

Boring Bars
D...DDUN / S...PDUN Type

D-DDUN
Copying



Anti-vibration D type
with oil hole



SumiTurn X Bar



Insert (eg.)

N-GU

■ Spare Parts



■ Holders

Above figures show right hand tools.

Cat. No..	Stock R	Stock L	øD min	Dimensions (mm) ød	h	ℓ1	ℓ2	f	γ	Insert (eg.)	Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	
D32T - DDUN R/L 1104-40	●	●	40	32	30	300	26	22	-10°	DN□□1104○○	SCP-1			DNS1104B	BFTX0307N	TRX10 (*)	LH040	LH025
D32T - DDUN R/L 1506-40	●	●	40	32	30	300	26	22	-12°	DN□□1506○○	SCP-2			DNS1506B	BFTX0409N (Nm) 3,4	TRX15 (*)		
D40U - DDUN R/L 1506-50	●	●	50	40	37	350	26	27	-12°									

(*) Note: Wrench (TRX type) for shim screw is not included.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

■ Holders



Tool holders (P type)
with lever-lock system

S - PDUN R/L



Cat. No.	Stock R	Stock L	Dimensions (mm) øD min	d	h	l1	l2	f	γ	
S25T - PDUN R/L 11	●	●	32	25	23	300	35	17	-11°	DN_ _ 1104_ _
S32U - PDUN R/L 15 04	●	●	40	32	30	350	40	22	-11°	DN_ _ 1504_ _
S40V - PDUN R/L 15	●	●	50	40	37	400	56	27	-11°	DN_ _ 1506_ _
S50W - PDUN R/L 15	❑	❑	63	50	47	450	63	35	-10°	

All figures show right hand tools.

■ Applicable Inserts

■ Spare Parts

Holder	Carbides, Cermets: Double sided	Carbides, Cermets: One sided	CBN, PCD	Lever pin	Clamp bolt	Shim	Shim pin	Wrench	
S - PDUN R/L									
S25T 11	DNMG 1104_ _ NGU	-	DNGA 1104_ _	LCL3DB-SD	LCS3DB-SD	–	–	LH020	
S32U 15 04	DNMG 1504_ _ NGU	DNMM 1504_ _ NMP	DNGA 1504_ _	LCL4D-SD	LCS5DB-SD	LSD42SD	LSP4SD	LH030	
S40V 15	DNMG 1506_ _ NGU	DNMM 1506_ _ NMP	DNGA 1506_ _	LCL4D-SD	LCS5DB-SD	LSD42SD	LSP4SD	LH030	
S50W....15	DNMG 1506_ _ NGU	DNMM 1506_ _ NMP	DNGA 1506_ _	LCL4D-SD	LCS5DB-SD	LSD42SD	LSP4SD	LH030	

Holders

	Tool holders (P type) with lever-lock system	Cat. No.	Stock		Dimensions (mm)							
			R	L	$øD_{min}$	d	h	l_1	l_2	f	γ	
S - PSKN R/L 		S25T - PSKN R/L 12	●	●	32	25	23	300	42	17	-11°	SN_ _ 1204_ _
		S32U - PSKN R/L 12	●	●	40	32	30	350	45	22	-10°	
		S40V - PSKN R/L 12	●	●	50	40	37	400	50	27	-10°	
		S40V - PSKN R/L 15	●		63	40	47	400	60	35	-10°	SN_ _ 1506_ _
		S50W - PSKN R/L 15	❑	❑	63	50	47	450	60	35	-10°	
		S50W - PSKN R/L 19	❑	❑	63	50	47	450	60	35	-9°	SN_ _ 1906_ _

All figures show right hand tools.

Applicable Inserts

Holder	Carbides, Cermets		CBN
	Double sided	One sided	
S - PSKN R/L 			
S25T....12	SNMG 0903_ _ NGU	-	-
S32U....12	SNMG 1204_ _ NGU	SNMM 1204_ _ NMP	SNGA 1204_ _
S40V....12	SNMG 1204_ _ NGU	SNMM 1204_ _ NMP	SNGA 1204_ _
S....15	SNMG 1506_ _ NGU	SNMM 1506_ _ NMP	-
S....19	SNMG 1906_ _ NGU	SNMM 1906_ _ NMP	-

Spare Parts

Lever pin	Clamp bolt	Shim	Shim pin	Wrench	
					
LCL4C-SD	LCS4B-SD	–	–	LH025	
LCL4T-SD	LCS41BS-SD	LSS42SD	LSP4SD	LH030	
LCL4SD	LCS42BS-SD	LSS42SD	LSP4SD	LH030	
LCL5SD	LCS5B-SD	LSS53SD	LSP5SD	LH030	
LCL5C-SD	LCS6B-SD	LSS63SD	LSP6SD	LH040	

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
Recommended Tightening Torque (N·m)

Boring Bars
"T-REX" Type

Internal Turning & Copying

SumiTurn T-REX

S-DTR
Profiling





Spare Parts



Holders

Above figures show right hand tools.

Cat. No.	Stock		Dimensions (mm)								Clamp	Spring	Screw	Shim	Screw	Wrench	Wrench
	R	L	øDmin	ød	h	ℓ1	ℓ2	f	γ	e							
S32S-DTR55C R/L-17	●	❍	44	32	30	250	40	22	-12°	7	TRCP3	S-SP4-20	BX0520	TRW5505	BFTX0307N (Nm) 2,0	TSW040	TRX10(*)
S40T-DTR55C R/L-17	●	❍	50	40	37	300	40	25	-10°	6,2							

(*) Note: Wrench (TRX10) for shim is not included.

Advantages

● T-REX Inserts for Maximum Economy

With 6 cutting edges and a 55 degree included angle - T-Rex is the intelligent alternative to profile turning with a traditional 4 edge DNMG insert.

Inserts

Applic.	Shape	Cat. No.	r	Coated Carbide AC8015P	AC8025P	AC810P	AC820P	AC830P	AC630M	Coated Cermet T3000Z
Fine Finishing	FL	TRM 551704-FL	0,4				❍			❍
		551708-FL	0,8				❍			❍
Finishing	LU	TRM 551704-LU	0,4	●	❍	▲	▲	▲		❍
		551708-LU	0,8	●	❍	▲	▲	▲		❍
		551712-LU	1,2	❍	❍	▲	▲			❍
	SU	TRM 551704-SU	0,4		❍		▲		❍	❍
		551708-SU	0,8		❍	▲	▲		❍	❍
		551712-SU	1,2		❍		▲		❍	
Light Cut	GU	TRM 551704-GU	0,4	❍	❍	▲	▲	▲	❍	
		551708-GU	0,8	❍	❍	▲	▲	▲	❍	
		551712-GU	1,2	❍	❍	▲	▲	▲		



Application P Steel
M Stainless steel

● Recommended Cutting Conditions

Cutting speed (m/min)

Grade		Coated Carbide AC810P	AC8025P	AC820P	AC830P	AC630M	Coated Cermet T3000Z
Work materials	Low carbon steel	220 400	150 350	150 350	120 300	120 300	100 400
	Alloy steel	150 300	100 250	100 250	80 200	80 230	100 250
	Stainless steel				50 150	100 160	
Application range	Finishing	◎	○	○	○	○	◎
	Medium cutting	○	◎	◎	○	◎	○
	Interrupted cutting		○	○	◎	○	○

◎ Preferred choice ○ Suitable



D-DTFN
Stop boring



Anti-vibration D type with oil hole



Insert (eg.)

N-GU

Spare Parts



Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	øD min	Dimensions (mm) ød	h	ℓ_1	ℓ_2	f	γ	Insert (eg.)	Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	
D25T - DTFN R/L 1604-32	●	●	32	25	23	300	21	17	-12°	TN□□1604○○	SCP-1			TNS1603B	BFTX0307N (Nm) 2,0	TRX10 (*)	LH040	LH025
D32T - DTFN R/L 1604-40	●	●	40	32	30	300	26	22	-10°					TNS1604B				
D40U - DTFN R/L 1604-50	●	●	50	40	37	350	26	27	-10°									

(*) Note: Wrench (TRX type) for shim screw is not included.

Holders



Tool holders (P type) with lever-lock system

S - PTFN R/L





Cat. No.	Stock R	Stock L	Dimensions (mm) øD min	d	h	l_1	l_2	f	γ	
S20S - PTFN R/L 11			25	20	18	250	30	13	-12°	TN_ _ 1103_ _
S25T - PTFN R/L 16	●	●	32	25	23	300	43,3	17	-13°	TN_ _ 1604_ _
S32U - PTFN R/L 16	●	●	40	32	30	350	49,6	27	-12°	
S40V - PTFN R/L 16	●		50	40	37	400	49,5	27	-11°	
S50W - PTFN R/L 16	❑	❑	63	50	47	450	56	35	-10°	
S40V - PTFN R/L 22	●	●	50	40	37	400	59	27	-11°	TN_ _ 2204_ _
S50W - PTFN R/L 22	❑		63	50	47	450	66	35	-10°	

All figures show right hand tools.

Applicable Inserts

Holder	Carbides, Cermets Double sided	Carbides, Cermets One sided	CBN
S - PTFN R/L			
S....11	-	-	-
S....16	TNMG 1604_ _ NGU	TNMM 1604_ _ NMP	TNGA 1604_ _
S....22	TNMG 2204_ _ NGU	TNMM 2204_ _ NMP	TNGA 2204_ _

Spare Parts

Holder	Lever pin	Clamp bolt	Shim	Shim pin	Wrench
S - PTFN R/L					
S....11	LCL3T-SD	LCS3B-SD	–	–	LH020
S....16	LCL3SD	LCS3TB-SD	LST317SD	LSP3SD	LH025
S....22	LCL4SD	LCS42BS-SD	LST42SD	LSP4SD	LH030

● = Euro stock
❑ = Delivery on request

(Nm) Recommended Tightening Torque (N·m)

Boring Bars
D...DWLN / S...MWLN Type

D-DWLN
Bottom facing



Anti-vibration D type
with oil hole



SumiTurn X Bar



Insert (eg.)

N-GU

Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	øD min	Dimensions (mm) ød	h	ℓ_1	ℓ_2	f	γ	Insert (eg.)	Clamp	Spring	Clamp bolt	Shim	Shim Screw	Wrench	Wrench	
D25T - DWLN R/L 0804-32	●	●	32	25	23	300	26	17	-12°	WN□□0804○○	SCP-2			WNS0803B	BFTX0307N	TRX10 (*)	LH040	LH025
D32T - DWLN R/L 0804-40	●	●	40	32	30	300	26	22	-10°					WNS0804B	BFTX0409N (Nm) 3,4	TRX15 (*)		
D40U - DWLN R/L 0804-50	●	●	50	40	37	350	26	27	-10°									

Spare Parts



(*) Note: Wrench (TRX type) for shim screw is not included.

Holders



Tool holders (M type)
with wedge clamp system

S - MWLN R/L





Cat. No.	Stock R	Stock L	øD min	d	h	l_1	l_2	f	γ	
S25R - MWLN R/L 08	●	●	32	25	23	200	28	17	-15°	WNMG 0804_ _
S32S - MWLN R/L 08	●	●	40	32	30	250	28	22	-14°	
S40T - MWLN R/L 08	●	●	50	40	37	300	28	27	-12°	

All figures show right hand tools.

Applicable Inserts

Holder	Carbides, Cermets: Double sided	Carbides, Cermets: One sided	
S - MWLN R/L			
S....08	WNMG 0804_ _ NGU	WNMM 0804_ _ NMP	

Spare Parts

Clamp	Double screw	Pin	Shim	Wrench	
					
HE060011W	WB 6-16	HE060011P	HE060011E	LH025, LH030	

For Positive CC_ _- Inserts (α = 7°)

SumiTurn X Bar

B/D-SCLC
Bottom facing



B Type (Fig.1)
Min. Bore Dia.



D Type (Fig.2)



Insert (ex.)

Spare Parts


Holders

Steel shank	Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) ød	h	ℓ1	f	ℓ2	γ	Fig.	Insert (ex.)	Screw	Wrench
Anti-vibration B type	B08H - SCLC R/L 0602-10	●	●	10	8	7	100	5,5	19	-13°	1.	CC□T 0602○○	BFTX02505N (1,1)	TRX08
	B10K - SCLC R/L 0602-12	●	●	12	10	9	125	6	21	-12°				
Anti-vibration D type with oil hole	D12M - SCLC R/L 0602-14	●	●	14	12	11	150	7	25	-10°	2.		BFTX02506N	
	D16R - SCLC R/L 09T3-18	●	●	18	16	15	200	11	30	-8°		CC□T 09T3○○	BFTX0407N	TRX15
	D20S - SCLC R/L 09T3-22	●	●	22	20	18	250	13	30	-7°			BFTX0409N	
	D25T - SCLC R/L 1204-32	●	●	32	25	23	300	17	38	-6°		CC□T 1204○○	BFTX0511N (5,0)	TRX20
	D32T - SCLC R/L 1204-40	●	●	40	32	30	300	20	53	-6°				

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

Holders



Tool holders (S type)
with screw-lock system

S - SCLC R/L



Cat. No.	Stock R	Stock L	Dimensions (mm) øDmin	d	h	l1	l2	f	γ	
S10K - SCLC R/L 06	▲	▲	13	10	9	125	9	7	-12°	CC_ _ 0602_ _
S12M - SCLC R/L 06	▲	▲	16	12	11	150	11	9	-10°	
S16R - SCLC R/L 06	●	●	20	16	15	200	15	11	-8°	
S16R - SCLC R/L 09	▲	▲	20	16	15	200	15	11	-8°	CC_ _ 09T3_ _
S20S - SCLC R/L 09	▲	▲	25	20	18	250	20	13	-7°	
S25T - SCLC R/L 12		▲	32	25	23	300	20	17	-6°	CC_ _ 1204_ _
S32U - SCLC R/L 12	●	●	40	32	30	350	25	22	-10°	
S40V - SCLC R/L 12		●	50	40	37	400	25	27	-8°	

All figures show right hand tools.

Applicable Inserts

Holder	Carbides, Cermets			Screw	(N·m)	Wrench
S - SCLC R/L						
S.....06	CCMT 0602_ _ NFP	CCGW 0602_ _	-	BFTX02505N	1,1	TRX08
S16R.....09	CCMT 09T3_ _ NFP	CCGW 09T3_ _	-	BFTX0407N	3,0	TRX15
S20S.....09	CCMT 09T3_ _ NFP	CCGW 09T3_ _	-	BFTX0409N	3,4	TRX15
S.....12	CCMT 1204_ _ NFP	CCGW 1204_ _	-	BFTX0511N	5,0	TRX20

Spare Parts

● = Euro stock
❑ = Delivery on request
▲ = To be replaced by new item
(N·m) Recommended Tightening Torque (N·m)

Boring Bars
S/C...SCLP Type

Holders

	Tool holders (S type) with screw-lock system	Cat. No.	Stock		Dimensions (mm)							
			R	L	$øD_{min}$	d	h	l_1	l_2	f	γ	
S - SCLP R/L Steel shank 		S10K - SCLP R/L 08	●	●	12	10	9	125	12	6	-5°	CP_ T 0802_ _
		S12M - SCLP R/L 08	●	●	16	12	11	150	15	8	-3°	
		S16R - SCLP R/L 09		●	20	16	15	200	18	10	-3°	CP_ T 0903_ _
		S20S - SCLP R/L 09	●	●	25	20	18	250	18	12,5	0	
		S25T - SCLP R/L 12	●	●	28	25	22	300	17,4	14	-3°	CP_ T 1204_ _
C - SCLP R/L Carbide shank 		C10Q - SCLP R/L 08	●	❑	12	10	9	180	15	6	-5°	CP_ T 0802_ _
		C12R - SCLP R/L 08	❑	❑	16	12	11	200	15	8	-2°	
		C16S - SCLP R/L 09	●	❑	20	16	15	250	15	10	-2°	CP_ T 0903_ _

All figures show right hand tools.

Applicable Inserts

Holder	Carbides, Cermets	CBN	
S/C-SCLP R/L			
S/C 10.....08	CPGT 0802_ _ NSD	CPMW 0802_ _	
S/C 12.....08	CPGT 0802_ _ NSD	CPMW 0802_ _	
S/C 16.....09	CPGT 0903_ _ NSD	CPMW 0903_ _	
S 20.....09	CPGT 0903_ _ NSD	CPMW 0903_ _	
S 25.....12	CPGT 1204_ _ NSD	-	

Spare Parts

Screw	N·m	Wrench			
					
BFTX 0305 A	-	TRX 10			
BFTX 0305 A	-	TRX 10			
BFTX 0407 A	3,4	TRX 15			
BFTX 0407 A	3,4	TRX 15			
BFTX 0509 A	5,0	TRX 20			

B/D/S...SDUC Type

For Positive DC_ _- Inserts (α = 7°)



SumiTurn X Bar

B/D-SDUC
Copying



B Type (Fig.1)

Min. Bore Dia.



D Type (Fig.2)



Insert (ex.)

■ Spare Parts


■ Holders

Steel shank	Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) ød	h	ℓ1	f	e	γ	Fig.	Insert (ex.)	Screw	Wrench
Anti-vibration B type	B10M - SDUC R/L 0702-13	●	●	13	10	9	150	7	2,5	-8°	1.	DC□T 0702○○	BFTX02506N 1,5 (N·m)	TRX08
Anti-vibration D type with oil hole	D12M - SDUC R/L 0702-16	●	●	16	12	11	150	9	3,5	-8°	2.			
	D16R - SDUC R/L 0702-20	●	●	20	16	15	200	11	4,0	-6°				
	D20S - SDUC R/L 11T3-25	●	●	25	20	18	250	13	4,5	-6°		DC□T 11T3○○	BFTX0409N 3,4 (N·m)	TRX15
	D25S - SDUC R/L 11T3-32	●	●	32	25	22	250	17	7,0	-6°				
	D32T - SDUC R/L 11T3-40	●	●	40	32	30	300	22	8,0	-6°				

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

■ Holders



Tool holders (S type)
with screw-lock system

S - SDUC R/L





Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) d	h	l1	f	e	γ	
S10K - SDUC R/L 07	●	●	13	10	9	125	7	2,5	-8°	DC_ _ 0702_ _
S12M - SDUC R/L 07	●	●	16	12	11	150	9	3,5	-8°	
S16R - SDUC R/L 07	●	●	20	16	15	200	11	4	-6°	
S20S - SDUC R/L 11	●	●	25	20	18	250	13	4,5	-6°	DC_ _ 11T3_ _
S25T - SDUC R/L 11	●	●	32	25	22	300	17	7,5	-6°	
S32U - SDUC R/L 11	●	●	40	32	30	350	22	11	-6°	

All figures show right hand tools.

■ Applicable Inserts

■ Spare Parts

Holder	Carbides, Cermets		CBN, PCD	Screw	(N·m)	Wrench			
S - SDUC R/L S - SDQC R/L									
S10K.....07	DCMT 0702_ _ NFP	DCMT 0702_ _ NSK	DCGW 0702_ _	BFTX02506N	1,5	TRX08			
S12M.....07	DCMT 0702_ _ NFP	DCMT 0702_ _ NSK	DCGW 0702_ _	BFTX02506N	1,5	TRX08			
S16R.....07	DCMT 0702_ _ NFP	DCMT 0702_ _ NSK	DCGW 0702_ _	BFTX02506N	1,5	TRX08			
S.....11	DCMT 11T3_ _ NFP	DCMT 11T3_ _ NSK	DCGW 11T3_ _	BFTX0409N	3,4	TRX15			

● = Euro stock

(N·m) Recommended Tightening Torque (N·m)

Boring Bars
B/D/S...SDQC Type

SumiTurn X Bar

B/D-SDQC
Copying



B Type (Fig.1)
Min. Bore Dia.



D Type (Fig.2)



Insert (ex.)

■ Spare Parts


■ Holders

Steel shank	Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) ød	h	ℓ1	f	e	γ	Fig.	Insert (ex.)	Screw	Wrench
Anti-vibration B type	B10M - SDQC R/L 0702-13	●	●	13	10	9	150	7	2,5	-8°	1.	DC□T 0702○○	BFTX02506N 1,5 (N·m)	TRX08
Anti-vibration D type with oil hole	D12M - SDQC R/L 0702-16	●	●	16	12	11	150	9	3,5	-8°	2.			
	D16R - SDQC R/L 0702-20	●	●	20	16	15	200	11	4,0	-6°				
	D20S - SDQC R/L 11T3-25	●	●	25	20	18	250	13	4,5	-6°		DC□T 11T3○○	BFTX0409N 3,4 (N·m)	TRX15
	D25S - SDQC R/L 11T3-32	●	●	32	25	22	250	17	7,0	-6°				
	D32T - SDQC R/L 11T3-40	●	●	40	32	30	300	22	7,0	-10°				

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

■ Holders



Tool holders (S type)
with screw-lock system

S - SDQC R/L





Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) d	h	l1	f	e	γ	
S10K - SDQC R/L-07	●	●	13	10	9	125	7	2,5	-8°	DC_ _ 0702_ _
S12M - SDQC R/L-07	●	●	16	12	11	150	9	3,5	-8°	
S16R - SDQC R/L-07	●	●	20	16	15	200	11	4	-6°	
S20S - SDQC R/L-11	●	●	25	20	18	250	13	4,5	-6°	DC_ _ 11T3_ _
S25T - SDQC R/L-11	●	●	32	25	22	300	17	7	-6°	

All figures show right hand tools.

■ Applicable Inserts

■ Spare Parts

Holder	Carbides, Cermets		CBN, PCD	Screw	(N·m)	Wrench			
S - SDUC R/L S - SDQC R/L									
S10K.....07	DCMT 0702_ _ NFP	DCMT 0702_ _ NSK	DCGW 0702_ _	BFTX02506N	1,5	TRX08			
S12M.....07	DCMT 0702_ _ NFP	DCMT 0702_ _ NSK	DCGW 0702_ _	BFTX02506N	1,5	TRX08			
S16R.....07	DCMT 0702_ _ NFP	DCMT 0702_ _ NSK	DCGW 0702_ _	BFTX02506N	1,5	TRX08			
S.....11	DCMT 11T3_ _ NFP	DCMT 11T3_ _ NSK	DCGW 11T3_ _	BFTX0409N	3,4	TRX15			

For Positive SP_ _- Inserts (α = 11°)



Holders

	Tool holders (S type) with screw-lock system	Cat. No.	Stock		Dimensions (mm)							
			R	L	$øD_{min}$	d	h	l_1	l_2	f	γ	
S - SSKP R/L Steel shank 		S12M - SSKP R/L 09		●	16	12	11	150	9	8	-6°	SP_ T 0903_ _
		S16R - SSKP R/L 09	●	●	20	16	15	200	6,8	10	-4°	
		S20S - SSKP R/L 09	●	❑	25	20	18	250	8,5	12,5	-2°	
		S25T - SSKP R/L 09	●		28	25	22	300	5	14	0	
C - SSKP R/L Carbide shank 		C12R - SSKP R/L 09	●		16	12	11	200	25	8	-6°	SP_ T 0903 _ _
		C16S - SSKP R/L 09	●		20	16	15	250	30	10	-4°	

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.
SPGT figure shows left hand tool.

Applicable Inserts

Holder	Carbides, Cermets	CBN	
S/C-SSKP R/L			
S/C 12.....09	SPGT 0903_ _ L/R-SD	SPGW 0903_ _	
S/C 16.....09			
S 20.....09			
S 25.....09			

Spare Parts

Screw	N·m	Wrench			
					
BFTX 0307 A	2,0	TRX 10			

● = Euro stock
❑ = Delivery on request

N·m Recommended Tightening Torque (N·m)

Boring Bars
S ...STFC Type

■ Holders

	Tool holders (S type) with screw-lock system	Cat. No.	Stock		Dimensions (mm)							
			R	L	$øD_{min}$	d	h	l_1	l_2	f	γ	
S - STFC R/L		S10K - STFC R/L 09	●	●	13	10	9	125	-	10,5	-12°	TC_ _ 0902_ _
		S12M - STFC R/L 11	●	●	16	12	11	150	10	9	-10°	TC_ _ 1102_ _
		S16R - STFC R/L 11	●	●	20	16	15	200	12	11	-6°	
		S20S - STFC R/L 11	●	●	25	20	18	250	14	13	-3°	
		S25T - STFC R/L 16	●	❑	32	25	23	300	18	17	-6°	TC_ _ 16T3_ _
		S32U - STFC R/L 16	●		40	32	30	350	20	22	-10°	
		S40V - STFC R/L 16	❑		50	40	37	400	25	27	-8°	

All figures show right hand tools.

■ Applicable Inserts

Holder	Carbides, Cermets		CBN, PCD
S - STFC R/L			
S.....09	TCMT 0902_ _ NFP	-	TCGW 0902_ _
S.....11	TCMT 1102_ _ NFP	TCMT 1102_ _ NSK	TCGW 1102_ _
S.....16	TCMT 16T3_ _ NFP	TCMT 16T3_ _ NSK	TCGW 16T3_ _

■ Spare Parts

Screw	N·m	Wrench
		
BFTX02205N	0,5	TRX06
BFTX02506N	1,5	TRX08
BFTX0409N	3,4	TRX15

Boring Bars
B/D/S/C...STUP(B) Type

For Positive TB / TP _ _- Inserts (α = 5, 11°)

SumiTurn X Bar

B/D-STUP
Stop boring



B Type (Fig.1)
Min. Bore Dia.



D Type (Fig.2)



Insert (ex.)

■ Spare Parts


■ Holders

Steel shank	Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) ød	h	ℓ1	f	ℓ2	γ	Fig.	Insert (ex.)	Screw	Wrench
Anti-vibration B type	B08H - STUP R/L 0802-10	●	●	10	8	7	100	5	13	-10°	1.	TP□T 0802○○	BFTX0204A ⊜0,5	TRX06
	B10K - STUP R/L 1103-12	●	●	12	10	9	125	6	15	-8°		TP□T 1103○○	BFTX0306A (N·m) 2,0	TRX10
Anti-vibration D type with oil hole	D12M - STUP R/L 1103-14	●	●	14	12	11	150	7	17	-7°	2.			
	D16R - STUP R/L 1103-18	●	●	18	16	15	200	9	18	-4°				
	D20S - STUP R/L 1103-22	●	●	22	20	18	250	11	18	-3°			BFTX0307A ⊜2,0	
	D25T - STUP R/L 1604-28	●	●	28	25	22	300	14	18	-2°		TP□T 1604○○	BFTX0410A (N·m) 3,4	TRX15
	D32T - STUP R/L 1604-40	●	●	40	32	30	300	20	13	-2°				

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

■ Holders



Tool holders (S type)
with screw-lock system

		Cat. No.	Stock R	Stock L	Dimensions (mm) øDmin	d	h	l1	l2	f	γ	
S - STUP/B R/L Steel shank		S08H - STUB R/L 06-01	●	●	8	8	7	100	30	4	-12°	TB_T 0601_ _
		S08H - STUP R/L 08-02	●	●	10	8	7	100	13	5	-10°	TP_T 0802_ _
		S10K - STUP R/L 11-03	●	●	12	10	9	125	15	6	-8°	TP_T 1103_ _
		S12M - STUP R/L 11-03	●	●	16	12	11	150	17	8	-6°	
		S16R - STUP R/L 11-03	●	●	20	16	15	200	18	10	-2°	
		S20S - STUP R/L 16	●	●	25	20	18	250	18	12,5	-3°	TP_T 1604_ _
		S25T - STUP R/L 16	●	●	28	25	22	300	18	14	-2°	
C - STUP/B R/L Carbide shank		C08M - STUB R/L 06	●	●	8	8	7	150	50	4	-12°	TB_T 0601_ _
		C08M - STUP R/L 08	●	●	10	8	7	150	18	5	-10°	TP_T 0802_ _
		C10Q - STUP R/L 11	●	●	12	10	9	180	19	6	-8°	TP_T 1103_ _
		C12R - STUP R/L 11		●	16	12	11	200	25	8	-6°	
		C16S - STUP R/L 11	●	❑	20	16	15	250	30	10	-4°	

■ Applicable Inserts

Holder	Carbides, Cermets	CBN, PCD
S/C-STU_ R/L		
S/C 08.....06-01	TBGT 0601_ _L/R-W	-
S/C 08.....08-02	TPGT 0802_ _L/R-W	TPMW 0802_ _
S/C 10.....11-03	TPGT 1103_ _L/R-W	TPGW 1103_ _
S/C 12/16.....11-03	TPGT 1103_ _L/R-W	TPGW 1103_ _
S 20/25.....16	TPGT 1604_ _L/R-W	TPGW 1604_ _

■ Spare Parts

Screw	(N·m)	Wrench
		
BFTX 0204 A	0,5	TRX 06
BFTX 0204 A	0,5	TRX 06
BFTX 0306 A	2,0	TRX 10
BFTX 0307 A	2,0	TRX 10
BFTX 0410 A	3,4	TRX 15

● = Euro stock
❑ = Delivery on request

(N·m) Recommended Tightening Torque (N·m)

Boring Bars
D...SVUB / SVZB Type

SumiTurn X Bar

Anti-vibration D type with oil hole

D-SVUB

Copying



Fig.1



Fig.2



Insert (ex.)

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) ød	h	ℓ1	f	e	γ	Fig.	Insert (ex.)	Pin	Clamp screw	Shim	Screw	Wrench	Wrench
D16R - SVUB R/L 1103-22	●	●	22	16	15	200	13	5	-7°	1.	VB□□ 1103○○	–	–	–	BFTX02506	TRX08	–
D20S - SVUB R/L 1103-27	●	●	27	20	18	250	15	5	-5°								
D25T - SVUB R/L 1604-35	●	●	35	25	23	300	20,5	9	-7,5°	2.	VB□□ 1604○○	VP32B	BH03504	SVP32	BFTX03508 (M+) 2,0	TRX10	LH020
D32T - SVUB R/L 1604-40	●	●	40	32	30	300	22	9	-7,5°								

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

SumiTurn X Bar

Anti-vibration D type with oil hole

D-SVZB

Copying



Fig.1



Fig.2



Insert (ex.)

Spare Parts

Holders

Above figures show right hand tools.

Cat. No.	Stock R	Stock L	øDmin	Dimensions (mm) ød	h	ℓ1	f	e	γ	Fig.	Insert (ex.)	Pin	Clamp screw	Shim	Screw	Wrench	Wrench
D16R - SVZB R/L 1103-22	●	●	22	16	15	200	13	5	-7	1.	VB□□ 1103○○	–	–	–	BFTX02506	TRX08	–
D20S - SVZB R/L 1103-27	●	●	27	20	18	250	15	5	-5								
D25T - SVZB R/L 1604-35	●	●	35	25	23	300	20,5	9	-7,5	2.	VB□□ 1604○○	VP32B	BH03504	SVP32	BFTX03508 (M+) 2,0	TRX10	LH020
D32T - SVZB R/L 1604-40	●	●	40	32	30	300	22	9	-7,5								

Holders

	Tool holders (S type) with screw-lock system	Cat. No.	Stock R	Stock L	Dimensions (mm) øDmin	d	h	l1	f	γ	e	
S - SVQB R/L		S16R - SVQB R/L 11	●	●	22	16	15	200	13	-6,5°		VB_ _ 1102_ _
		S20S - SVQB R/L 11	●	●	27	20	18	250	15	-6,5°		
		S25T - SVQB R/L 16	●	●	35	25	23	300	20,5	-6,5°		VB_ _ 1604_ _
		S32U - SVQB R/L 16	●	●	40	32	30	350	22	-6,5°		
		S40V - SVQB R/L 16	❑	❑	50	40	37	400	27	-6,5°		
S - SVUB R/L		S16R - SVUB R/L 11	●	●	22	16	15	200	13	-7,5°		VB_ _ 1102_ _
		S20S - SVUB R/L 11	●	●	27	20	18	250	15	-7,5°		
		S25T - SVUB R/L 16	●	●	35	25	23	300	20,5	-7,5°		VB_ _ 1604_ _
		S32U - SVUB R/L 16	●	●	40	32	30	350	22	-7,5°		
		S40V - SVUB R/L 16	❑	❑	50	40	37	400	27	-7,5°		
S - SVZB R/L		S16R - SVZB R/L 11	●	●	22	16	15	200	13	-7,5°	5	VB_ _ 1102_ _
		S20S - SVZB R/L 11	●	●	27	20	18	250	15	-7,5°	5	
		S25T - SVZB R/L 16	●	●	35	25	23	300	20,5	-7,5°	9	VB_ _ 1604_ _
		S32U - SVZB R/L 16	●	●	40	32	30	350	22	-7,5°	9	
		S40V - SVZB R/L 16		❑	50	40	37	400	27	-7,5°	10	

All figures show right hand tools.

Applicable Inserts

Holder	Carbides, Cermets		CBN
			
S16R	VBMT 1102_ _ NFP	VBMT 1102_ _ NSK	-
S20S	VBMT 1102_ _ NFP	VBMT 1102_ _ NSK	-
S25T	VBMT 1604_ _ NFP	VBMT 1604_ _ NSK	VBGW 1604_ _
S32U	VBMT 1604_ _ NFP	VBMT 1604_ _ NSK	VBGW 1604_ _
S40V	VBMT 1604_ _ NFP	VBMT 1604_ _ NSK	VBGW 1604_ _

Spare Parts

Holder	Pin	Clamp bolt	Shim	Screw	Wrench	Wrench
						
S16R	-	-	-	BFTX02506N ⓜ 1,5	TRX08	-
S20S	-	-	-		TRX08	-
S25T	-	-	-	BFTX03508 ⓜ 2,0	TRX10	-
S32U	VP32B	BH03504	SVP32		TRX10	LH020
S40V	VP40B	BH03504	SVP32		TRX10	LH020

● = Euro stock
❑ = Delivery on request

ⓜ Recommended Tightening Torque (N·m)

Boring Bars
S/C...SWUB Type

■ Holders

	Tool holders (S type) with screw-lock system	Cat. No.	Stock		Dimensions (mm)							
			R	L	$øD_{min}$	d	h	l_1	l_2	f	γ	
S - SWUB R/L Steel shank 		S08H - SWUB R/L 06-01	●	●	5,5	8	7	100	18	3	-12°	WBGT 0601_ _
C - SWUB R/L Carbide shank 		C08K - SWUB R/L 06	●	●	5,5	8	7	125	30	3	-12°	WBGT 0601_ _

All figures show right hand tools.

Remarks: Right handed tool holders are applicable with left handed or neutral inserts.
Left handed tool holders are applicable with right handed or neutral inserts.

■ Applicable Inserts

■ Spare Parts

Holder	Carbides, Cermets	CBN		Screw	N·m	Wrench			
S/C-SWUBR/L									
S/C 08.....R 06	WBGT 0601_ _ LW	-		BFTX 0203 N	0,5	TRX 06			
S/C 08.....L 06	WBGT 0601_ _ RW	-		BFTX 0203 N	0,5	TRX 06			

BXBR Type

Characteristics

SumiSmall

- Economical, two-cornered insert.
- Maximum boring depth 5D (5 times the shank diameter)
- Usable at any desired overhang.
- Shank size = min. bore diameter for easy selection. (Available from ø 2 mm to ø 5 mm in 0,5 mm increments.)
- KBMX Type cutting edge used, no breaker versions also available in stock.

Small Hole Finishing





Figure shows tool with breaker.

Solid Carbide Bar

	Cat. No.	Stock		DMIN	Dimensions (mm)								Applicable Sleeve
		ACZ150	AC530U		DCON	H	LF	WF	LH	CDX	E1	RE	
With Breaker	BXBR 02005 R	❍		**2,0**	2,0	1,8	50	0,80	6,0	10,0	0,20	0,05	HBX 2016
	02020 R	❍		**2,0**	2,0	1,8	50	0,80	6,0	10,0	0,20	0,20	HBX 2016
	BXBR 02505 R	❍		**2,5**	2,5	2,2	50	1,05	7,5	12,5	0,20	0,05	HBX 2516
	02520 R	❍		**2,5**	2,5	2,2	50	1,05	7,5	12,5	0,20	0,20	HBX 2516
	BXBR 03005 R	❍		**3,0**	3,0	2,7	50	1,30	9,0	15,0	0,25	0,05	HBX 3016
	03020 R	❍		**3,0**	3,0	2,7	50	1,30	9,0	15,0	0,25	0,20	HBX 3016
	BXBR 03505 R	❍		**3,5**	3,5	3,1	60	1,55	10,5	17,5	0,25	0,05	HBX 3516
	03520 R	❍		**3,5**	3,5	3,1	60	1,55	10,5	17,5	0,25	0,20	HBX 3516
	BXBR 04005 R	❍		**4,0**	4,0	3,6	60	1,80	12,0	20,0	0,35	0,05	HBX 4016
	04020 R	❍		**4,0**	4,0	3,6	60	1,80	12,0	20,0	0,35	0,20	HBX 4016
	BXBR 04505 R	❍		**4,5**	4,5	4,1	70	2,05	13,5	22,5	0,35	0,05	HBX 4516
	04520 R	❍		**4,5**	4,5	4,1	70	2,05	13,5	22,5	0,35	0,20	HBX 4516
	BXBR 05005 R	❍		**5,0**	5,0	4,5	70	2,30	15,0	25,0	0,40	0,05	HBX 5016
	05020 R	❍		**5,0**	5,0	4,5	70	2,30	15,0	25,0	0,40	0,20	HBX 5016
No Breaker	BXBR 02005 R-NB	❍		**2,0**	2,0	1,8	50	0,80	6,0	10,0	0,20	0,05	HBX 2016
	02020 R-NB	❒		**2,0**	2,0	1,8	50	0,80	6,0	10,0	0,20	0,20	HBX 2016
	BXBR 02505 R-NB	❒		**2,5**	2,5	2,2	50	1,05	7,5	12,5	0,20	0,05	HBX 2516
	02520 R-NB	❍		**2,5**	2,5	2,2	50	1,05	7,5	12,5	0,20	0,20	HBX 2516
	BXBR 03005 R-NB	❍		**3,0**	3,0	2,7	50	1,30	9,0	15,0	0,25	0,05	HBX 3016
	03020 R-NB	❍		**3,0**	3,0	2,7	50	1,30	9,0	15,0	0,25	0,20	HBX 3016
	BXBR 03505 R-NB	❒		**3,5**	3,5	3,1	60	1,55	10,5	17,5	0,25	0,05	HBX 3516
	03520 R-NB	❍		**3,5**	3,5	3,1	60	1,55	10,5	17,5	0,25	0,20	HBX 3516
	BXBR 04005 R-NB	❍		**4,0**	4,0	3,6	60	1,80	12,0	20,0	0,35	0,05	HBX 4016
	04020 R-NB	❍		**4,0**	4,0	3,6	60	1,80	12,0	20,0	0,35	0,20	HBX 4016
	BXBR 04505 R-NB	❍		**4,5**	4,5	4,1	70	2,05	13,5	22,5	0,35	0,05	HBX 4516
	04520 R-NB	❍		**4,5**	4,5	4,1	70	2,05	13,5	22,5	0,35	0,20	HBX 4516
	BXBR 05005 R-NB	❍		**5,0**	5,0	4,5	70	2,30	15,0	25,0	0,40	0,05	HBX 5016
	05020 R-NB	❍		**5,0**	5,0	4,5	70	2,30	15,0	25,0	0,40	0,20	HBX 5016

Adaptor Sleeve (Optional)



Cat. No.	Stock	DCB (mm)	Applicable Bar
HBX 2016	❍	2,0	BXBR 020○○ R(-NB)
HBX 2516	❍	2,5	BXBR 025○○ R(-NB)
HBX 3016	❍	3,0	BXBR 030○○ R(-NB)
HBX 3516	❍	3,5	BXBR 035○○ R(-NB)
HBX 4016	❍	4,0	BXBR 040○○ R(-NB)
HBX 4516	❍	4,5	BXBR 045○○ R(-NB)
HBX 5016	❍	5,0	BXBR 050○○ R(-NB)

Spare Parts (For sleeve)

Screw	(N·m)	Setting Screw	Wrench
			
BFTX 0409 N	**3,4**	BT 06035 T	TRD 15

* BXBR bars can be used with HBB type sleeves. Commercially available sleeves may also be used.

❍ = Japan stock

(N·m) Recommended Tightening Torque (N·m)

Grooving & Parting-Off Threading Holders

F1–F56



GND Type

Characteristics

- Wide range of application processes
  Applicable for grooving, turning, copying, facing, boring and cut-off.
- Achieving stable tool life
  An array of chipbreakers improves the efficiency in chip control in various applications and prevents unexpected damages caused by chip blockade.
- Achieving smooth cutting and high efficiency machining
  Holders utilizing one-piece body construction made of special steel, reduce vibration by 30 % during machining as compared to conventional types.
- Achieving high precision grooving widths with moulded inserts
  Grooving insert width tolerance of ±0,03 mm over the entire range

Cutting Performance

Eliminates Vibration

Reduces vibration up to 30 % compared to conventional grades thanks to its high-rigidity design.





GND Type — Conventional Tool

Work Material:	15CrMo5
Holder:	GNDL R2525M 220
Insert:	GCM N2002 GG
Cutting Conditions:	v_c = 100 m/min, f = 0,10 mm/rev, a_p = 20 mm, wet

Ensures both, high rigidity and good chip evacuation

Internal



GND Type — Comp. A — Comp. B

Work Material:	15CrMo5
Holder:	GNDI R2532 T306
Insert:	GCM N3002 GG
Cutting Conditions:	v_c = 100 m/min, f = 0,05 mm/rev, a_p = 3,0 mm, wet

Application Examples

Substantially improved machining efficiency!

High rigidity holder enables high load machining at high feed rate.



Work Material:	42CrMo4
Holder:	GNDL R2525M 320
Insert:	GCM N3002 GG (AC530U)
Cutting Conditions:	v_c = 130 m/min, f = 0,30 mm/rev, wet

Stable and long tool life ensures reliable functionality even on automatic production lines!

Reduction of chattering prevents unexpected breakage.

GND Type — Competitor

Work Material:	C53
Holder:	GNDM L2525M 618
Insert:	GCM N6030 RG (AC530U)
Cutting Conditions:	v_c = 130 m/min, f = 0,30 mm/rev, wet

New

Internal Coolant Grooving Tool Holder
GNDM-JE Type / GNDL-JE Type

- Newly developed 2-hole coolant design optimizes cooling of the insert and improves chip removal, extending tool life and allowing for improved speeds and feeds in production.
- Grooving width range from 2,0 to 6,0 mm.
- Achieves both high efficiency in high speed machining and extension of tool life due to internal coolant supply to the cutting edge.
- Improves chip control by applying direct coolant from cutting edge side.

Wear Resistance





Chip Control



Coolant Pressure: 7 MPA

Coolant Pressure: 1 MPA

External Coolant

Work Material:	Ti-6Al-4V
Holder:	GNDM R2525K 312JE
Insert:	GCM N3002 GG (AC530U)
Cutting Conditions:	v_c = 60 m/min, f = 0,1 mm/rev, a_p = 5,0 mm, wet

CF Type Chipbreaker for Cut-Off

New

- Lead angle of 10°/15° for improved sharpness in cut-off machining.
- Asymmetrical chipbreaker design provides excellent chip control even in difficult to machine conditions.

10°/15°



GCMN20003 CF 10



GCMN20003 CF 15

Competitor

Work Material:	St42-3
Holder:	GNDM R2525M 220
Insert:	GCM N3002 CF-10,15 (AC1030U)
Cutting Conditions:	n = 2000 min^{-1}, f = 0,08 mm/rev, wet

GND Type

Inserts - Chipbreaker Series

Achieving stability and longer tool life. A variety of chipbreakers ensures outstanding chip control performance in many different types of applications.

Grooving / Turning		Grooving / Cut-Off			Cut-Off		Profiling	Necking	Non Ferrous Metals
General Type	Low Feed Type	General Type	Low Feed Type	Low Cutting ForceType	Cut-Off Type	Low Cutting ForceType	General Type	General Type	General Type
MG	ML	GG	GL	GF	CG	CF New	RG	RN	GA
									
Cross Section of Cutting Edge									
									
Grooving Width (mm)									
1,25 1,5 **2,0** **3,0 4,0 5,0** **6,0 7,0 8,0**	1,25 1,5 **2,0** **3,0 4,0 5,0** **6,0 7,0 8,0**	1,25 1,5 **2,0** **3,0 4,0 5,0** **6,0 7,0 8,0**	1,25 1,5 **2,0** **3,0 4,0 5,0** **6,0 7,0 8,0**	**1,25 1,5 2,0** **3,0 4,0 5,0** **6,0 7,0 8,0**	1,25 1,5 **2,0** **3,0 4,0** 5,0 6,0 7,0 8,0	1,25 1,5 **2,0** **3,0** 4,0 5,0 6,0 7,0 8,0	1,25 1,5 2,0 **3,0 4,0 5,0** **6,0 7,0 8,0**	1,25 1,5 **2,0** **3,0 4,0 5,0** **6,0** 7,0 8,0	1,25 1,5 **2,0** **3,0 4,0 5,0** **6,0** 7,0 8,0
Grade									
AC830P AC425K **AC520U AC530U** AC1030U T2500A H10	**AC830P AC425K** **AC520U AC530U** *AC1030U **T2500A** H10	**AC830P** AC425K **AC520U AC530U** AC1030U T2500A H10	**AC830P** AC425K **AC520U AC530U** AC1030U T2500A H10	**AC830P** AC425K **AC520U AC530U** *AC1030U **T2500A** H10	**AC830P** AC425K **AC520U AC530U** AC1030U T2500A H10	AC830P AC425K AC520U AC530U **AC1030U** T2500A H10	**AC830P AC425K** **AC520U AC530U** AC1030U **T2500A** H10	**AC830P AC425K** **AC520U AC530U** AC1030U T2500A H10	AC830P AC425K AC520U AC530U AC1030U T2500A **H10**

Stock

* Only use with GNDIS

Recommended Cutting Conditions

Work Material	P Carbon Steel / Alloy Steel				M Stainless Steel			K Cast Iron				S Exotic Alloy			N
Grade	AC830P	AC520U	AC530U	T2500A	AC830P	AC520U	AC530U	AC425K	AC520U	AC530U	AC1030U	AC520U	AC530U	AC1030U	H10
Cutting Speed (m/min)	80–200	80–200	50–200	50–200	70–150	70–150	50–150	80–200	60–200	50–200	50–200	20–80	20–60	20–60	150–300

Please see cutting data page F14

Excellent Chip Control

Grooving

GND Type
(**GG** Type Chipbreaker)

Conventional Tool

Work Material:	15CrMo5
Holder:	GNDL R2525M 320
Insert:	GCM N3002 GG
Cutting Conditions:	v_c=100 m/min, f=0,15 mm/rev, a_p=12,0 mm, wet

Turning

GND Type
(**ML** Type Chipbreaker)

Conventional Tool

Work Material:	15CrMo5
Holder:	GNDM R2525M 312
Insert:	GCM N3002 ML
Cutting Conditions:	v_c=100 m/min, f=0,10 mm/rev, a_p=0,5 mm, wet

Cut-Off

GND Type
(**CG** Type Chipbreaker)

Conventional Tool

Work Material:	X5CrMo17122 (Ø 30 mm)
Holder:	GNDL R2525M 220
Insert:	GCM R2002 CG 05
Cutting Conditions:	v_c = 100 m/min, f = 0,15 mm/rev, wet

Profiling

GND Type
(**RG** Type Chipbreaker)

Conventional Tool

Work Material:	15CrMo5
Holder:	GNDM R2525M 312
Insert:	GCM N3015 RG
Cutting Conditions:	v_c=100 m/min, f=0,15 mm/rev, a_p=0,1 mm, wet

Chipbreaker Selection

	Grooving / Turning	Grooving	Cut-Off
1st Recommendation	**MG** General Feed	**GG** General Feed	**GG** General Feed
	Improved Chip Control / Chipping Prevention	Improved Chip Control / Chipping Prevention	Prevent Nip Formation / Good Chip Control / Improved Chip Control / Chipping Prevention
2nd Recommendation	**ML** Low Feed, Good Chip Control	**GL** General Feed, Good Chip Control	**CG** General Feed, Feed Direction Front Cutting Edge Angle 5° / **GL** General Feed, Good Chip Control
		Good Chip Control / Reduce Chattering / Chipping Prevention	Prevent Nip Formation / Chipping Prevention / Good Chip Control / Reduce Chattering / Chipping Prevention
		GF Low Cutting Force	**CF** New, Low Cutting Force, Feed Direction Front Cutting Edge Angle 10°/15° / **GF** Low Cutting Force

	Profiling / Radius Grooving Outside Diameter	Necking / Radius Grooving Internal Profiling	For Non Ferrous Metals
Recommendation	**RG** General Feed, 1st Recommendation	**RN** General Feed	**GA** General Feed
	RN General Feed, 2nd Recommendation, w = 2 mm		

Grade Selection

	P Steel	M Stainless Steel	K Cast Iron	S Exotic Alloy	N Non Ferrous Metals
1st Recommendation	AC530U/AC1030U PVD	AC530U/AC1030U PVD	AC425K CVD	AC520U PVD	H10 Uncoated Carbide
	Insufficient Wear Resistance / Chipping Countermeasures; Importance of Surface Finish / Chipping Countermeasures	Insufficient Wear Resistance / Chipping Countermeasures	Chipping Countermeasures / Insufficient Wear Resistance	Chipping Countermeasures	
2nd Recommendation	AC520U PVD	AC520U PVD	AC520U PVD		
	Insufficient Wear Resistance / Chipping Countermeasures; Chipping Countermeasures	Insufficient Wear Resistance / Chipping Countermeasures	Chipping Countermeasures / Insufficient Wear Resistance	Insufficient Wear Resistance	
	AC830P CVD; T2500A Uncoated Cermet	AC830P CVD	AC530U/AC1030U PVD	AC530U/AC1030U PVD	

GND Type

For External Machining (Straight Type)

Turning / Profiling



Grooving Width (mm): 1,25 | 1,5 | 2,0 / 3,0 | 4,0 | 5,0 / 6,0 | 7,0 | 8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA



Grooving Width (mm): 1,25 | 1,5 | 2,0 / 3,0 | 4,0 | 5,0 / 6,0 | 7,0 | 8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA



Grooving Width (mm): 1,25 | 1,5 | 2,0 / 3,0 | 4,0 | 5,0 / 6,0 | 7,0 | 8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA



Grooving Width (mm): 1,25 | 1,5 | 2,0 / 3,0 | 4,0 | 5,0 / 6,0 | 7,0 | 8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

Grooving / Cut-Off



Grooving Width (mm): 1,25 | 1,5 | 2,0 / 3,0 | 4,0 | 5,0 / 6,0 | 7,0 | 8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA



Grooving Width (mm): 1,25 | 1,5 | 2,0 / 3,0 | 4,0 | 5,0 / 6,0 | 7,0 | 8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA



Grooving Width (mm): 1,25 | 1,5 | 2,0 / 3,0 | 4,0 | 5,0 / 6,0 | 7,0 | 8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

■ Series for External Machining (Straight Type)

Type	Shank Size Height	Shank Size Width	Cutting Width (mm)	Series	Max. Grooving Depth (mm)	Ref. Page	Applicable Chipbreaker
					5 10 15 20 25 30		MG ML GG GL GF CG CF RG RN GA
Small Tools	10	10	1,25 1,5	GNDL	10	→ F16	◎
			2	GNDL	10		○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDL	10		○ ○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
	12	12	1,25 1,5	GNDL	12	→ F16	◎
			2	GNDL	12,5		○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDL	12,5		○ ○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
	16	16	1,25	GNDM	8	→ F16	◎
			1,25 1,5	GNDL	12,5		◎
			1,5	GNDM	10		◎
			2	GNDM	12		○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			2	GNDL	16		○ ○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDM	12		◎ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDL	16		○ ○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
Straight Type	20	20	1,25 1,5	GNDM	10	→ F20	◎
			1,25 1,5	GNDL	16	→ F24	◎
			2	GNDS	6	→ F18	○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			2	GNDM	10	→ F20	○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			2	GNDM-JE	10	→ F22	○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			2	GNDL	20	→ F24	○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			2	GNDL-JE	20	→ F26	○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			3	GNDS	6	→ F18	◎ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDM	12	→ F20	◎ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDM-JE	12	→ F22	◎ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDL	20	→ F24	○ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
	20	20	3	GNDL-JE	20	→ F26	○ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
	25	25	4	GNDS	10	→ F18	◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			4	GNDM	18	→ F20	◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			4	GNDM-JE	18	→ F22	◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			4	GNDL	25	→ F24	○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			4	GNDL-JE	25	→ F26	○ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ◎
			5 6	GNDS	10	→ F18	◎ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎ ◎
			5 6	GNDM	18	→ F20	◎ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎ ◎
			5 6	GNDM-JE	18	→ F22	◎ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎ ◎
			5 6	GNDL	25	→ F24	○ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎ ◎
			5 6	GNDL-JE	25	→ F26	○ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎ ◎
			7 8	GNDM	18	→ F20	◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			7 8	GNDL	25	→ F24	○ ◎ ◎ ◎ ◎ ◎ ○ ◎
	32	25*	3	GNDM	12	→ F20	◎ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			3	GNDL	20	→ F24	○ ◎ ◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			4	GNDM	18	→ F20	◎ ◎ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎
			4	GNDL	25	→ F24	○ ◎ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎
	32	32	5 6	GNDM	18	→ F20	◎ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎ ◎
			5 6	GNDL	25	→ F24	○ ◎ ◎ ◎ ◎ ○ ◎ ○ ◎ ◎
			7 8	GNDM	18	→ F20	◎ ◎ ◎ ◎ ◎ ◎ ○ ◎
			7 8	GNDL	25	→ F24	○ ◎ ◎ ◎ ◎ ◎ ○ ◎

■ Stock　　* Make to order item (32x25mm)　　◎ 1st Recommendation　　○ 2nd Recommendation

GND Type

For External Machining (L Type)

Turning / Profiling



Grooving Width (mm)		
1,25	1,5	2,0
3,0	4,0	5,0
6,0	7,0	8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

Grooving / Cut-Off



Grooving Width (mm)		
1,25	1,5	2,0
3,0	4,0	5,0
6,0	7,0	8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

■ Series for External Machining (L Type)

Type	Shank Size Height	Shank Size Width	Cutting Width (mm)	Series	Max. Grooving Depth (mm)	Ref. Page	Applicable Chipbreaker MG	ML	GG	GL	GF	CG	CF (New)	RG	RN	GA
L Type	20	20	2	GNDLS	16	→ F24		○	◎	◎	◎	◎	◎		◎	◎
			3	GNDMS	10	→ F20	◎	◎	○	○	○	○	○	◎	○	○
			3	GNDLS	16	→ F24	○	○	◎	◎	◎	◎	◎	○	○	○
			4	GNDMS	12	→ F20	◎	◎	○	○	○	○		◎	○	○
			5	GNDMS	12	→ F20	◎	◎	○	○	○			◎	○	○
	25	25	2	GNDLS	18	→ F24		○	◎	◎	◎	◎	◎		◎	◎
			3	GNDMS	12	→ F20	◎	◎	○	○	○	○	○	◎	○	○
			3	GNDLS	18	→ F24	○	○	◎	◎	◎	◎	◎	○	○	○
			4	GNDMS	14	→ F20	◎	◎	○	○	○	○		◎	○	○
			4	GNDLS	23	→ F24	○	○	◎	◎	◎	◎		◎	○	○
			5 6	GNDMS	14	→ F20	◎	◎	○	○	○			◎	○	○
			5 6	GNDLS	23	→ F24	○	○	◎	◎	◎			◎	○	○

Stock

◎ 1st Recommendation ○ 2nd Recommendation

Cassettes for Radial Machining

Grooving



Grooving Width (mm)		
1,25	1,5	2,0
3,0	4,0	5,0
6,0	7,0	8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

■ Radial Grooving Cassettes

Type	Applicable Holders	Cutting Width (mm)	Series	Max. Grooving Depth (mm)	Ref. Page	Applicable Chipbreaker MG	ML	GG	GL	GF	CG	CF (New)	RG	RN	GA
Cassette	GND00	2	GNDCM	12	→ F36		○	◎	◎	◎	◎	◎	◎	◎	○
		3	GNDCM	12		◎	◎	○	○	○	○	○	◎	○	○
	GND90	4	GNDCM	18		◎	◎	○	○	○	○	○		◎	○
		5 6	GNDCM	18		◎	◎	○	○	○	○			◎	○

Stock

◎ 1st Recommendation ○ 2nd Recommendation

GND Type

For Face Machining

Grooving / Turning / Profiling



Grooving Width (mm)		
1,25	1,5	2,0
3,0	4,0	5,0
6,0	7,0	8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA



Grooving Width (mm)		
1,25	1,5	2,0
3,0	4,0	5,0
6,0	7,0	8,0

Chipbreaker: MG ML GG GL GF CG CF RG RN GA

■ Series for Face Machining

Type	Shank Size Height	Shank Size Width	Cutting Width (mm)	Series	Max. Grooving Depth (mm)	Bore (mm)	Ref. Page	Applicable Chipbreaker
Straight Type	20	20	3	GNDF	12	ø35 ø45	→ F32	◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			3		12	ø40 ø55		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			3		18	ø50 ø70		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			3		18	ø65 ø100		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			3		18	ø90 ø150		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			3		18	ø140 ø200		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			3		18	ø180 ø300		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			4	GNDF	18	ø40 ø55	→ F32	◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			4		23	ø50 ø70		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			4		23	ø65 ø90		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			4		23	ø85 ø130		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			4		23	ø125 ø200		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			4		23	ø180 ø300		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			4		23	ø280 ø1.000		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			5	GNDF	23	ø50 ø70	→ F32	◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			5		23	ø65 ø90		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			5		23	ø85 ø130		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			5		23	ø125 ø200		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			5		23	ø180 ø300		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			5		23	ø280 ø1.000		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6	GNDF	23	ø50 ø75	→ F32	◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		23	ø70 ø110		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		23	ø100 ø200		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		23	ø180 ø300		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		23	ø280 ø1.000		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
L Type	20	20	6	GNDFS	20	ø70 ø100	→ F34	◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		20	ø100 ø200		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		20	ø180 ø300		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		20	ø280 ø1.000		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			6		20	ø450~		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
	25	25	8	GNDFS	20	ø70 ø100	→ F34	◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			8		20	ø100 ø200		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			8		20	ø180 ø300		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			8		20	ø280 ø1.000		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎
			8		20	ø450~		◎ ◎ ○ ◎ ◎ ○ ○ ○ ◎ ◎

Stock Make to order item ◎ 1st Recommendation ○ 2nd Recommendation

Cassettes for Face Machining

Face Grooving / Turning / Profiling



Grooving Width (mm)

1,25	1,5	2,0
3,0	4,0	5,0
6,0	7,0	8,0

Chipbreaker

MG ML GG GL GF CG CF RG RN GA

■ Face Grooving Cassettes

Type	Cutting Width (mm) 3	4	5	6	7	8	Series	Max. Grooving Depth (mm) 5 10 15 20 25 30	Bore (mm) 50 100 150 200 250 300 1.000	Ref. Page	Applicable Chipbreaker MG	ML	GG	GL	GF	CG	CF	RG	RN	GA
Straight Type	3						GNDCF R/L	12	ø40 ø55	→ F38	◎	○	◎	○	○				○	◎
	3							15	ø50 ø75		◎	○	◎	○	○				○	◎
	3							15	ø65 ø100		◎	○	◎	○	○				○	◎
	3							18	ø90 ø150		◎	○	◎	○	○				○	◎
	3							18	ø140 ø200		◎	○	◎	○	○				○	◎
		4						18	ø40 ø55		◎	○	◎	○	○				○	◎
		4						18	ø50 ø70		◎	○	◎	○	○				○	◎
		4						18	ø65 ø90		◎	○	◎	○	○				○	◎
		4						18	ø85 ø130		◎	○	◎	○	○				○	◎
		4						18	ø125 ø200		◎	○	◎	○	○				○	◎
		4						18	ø180 ø300		◎	○	◎	○	○				○	◎
			5					18	ø50 ø70		◎	○	◎	○	○				○	◎
			5					18	ø65 ø90		◎	○	◎	○	○				○	◎
			5					18	ø85 ø130		◎	○	◎	○	○				○	◎
			5					18	ø125 ø200		◎	○	◎	○	○				○	◎
			5					18	ø180 ø300		◎	○	◎	○	○				○	◎
				6				18	ø50 ø75		◎	○	◎	○	○				○	◎
				6				18	ø70 ø110		◎	○	◎	○	○				○	◎
				6				18	ø100 ø200		◎	○	◎	○	○				○	◎
				6				18	ø180 ø300		◎	○	◎	○	○				○	◎
				6				18	ø280 ø1.000		◎	○	◎	○	○				○	◎

Stock Make to order item ◎ 1st Recommendation ○ 2nd Recommendation

GND Type

For Necking



Series for Necking

Type	Shank Size		Cutting Width (mm) 2	3	4	5	6	Series	Max. Grooving Depth (mm) 5 10 15 20 25 30	Min. Bore (mm)	Ref. Page	Applicable Chipbreaker MG	ML	GG	GL	GF	CG	CF	RG	RN	GA
Straight Type	20	20	2					GNDN	2,0	ø20	→ F31									◯	
				3					2,5	ø20										◯	
	25	25			4				3,0	ø30										◯	
						5			3,5	ø30										◯	
							6		4,0	ø30										◯	

Stock

Tips for Necking

Notes for Undercutting

Recommended Chipbreaker: **RN**

Distance between Workpiece and Necking



Edge Width CW (mm)	Depth of Necking APMX (mm)	Distance between Workpiece and Necking APMX2 (mm)
2,0	1,50	0,64
3,0	2,00	0,79
4,0	3,00	1,29
5,0	3,50	1,44
6,0	4,00	1,59

The recommended cutting conditions for necking are the same as grooving with RN type chipbreaker and edge width.
To prevent interference with the work material, do not use the holder for less than the minimum cutting diameter (DMIN) as specified for GNGN type holders.

Chip Shape





Work Material:	34CrMo4
Holder:	GNDN R2020K 325-020
Insert:	GCM N3015 RN
Cutting Conditions:	v_c = 100m/min, f = 0,1mm/rev
	Depth of Necking = 1,0mm, wet

GND Type

For Internal Machining (≥ Ø 14 mm ~)

Grooving / Turning / Copying



Grooving Width (mm)

1,5	2,0	3,0

Chipbreaker

ML	GF

For Internal Machining (≥ Ø 32 mm ~)

Grooving / Turning / Copying



Grooving Width (mm)

1,25	1,5	2,0
3,0	4,0	5,0
6,0	7,0	8,0

Chipbreaker

MG	ML	GG	GL	GF	CG	CF	RG	RN	GA

■ Series for Internal Machining (≥ Ø 14 mm ~)

Type	Shank Size ØDs(mm)	Cutting Width (mm) 1,5	2	3	Series	Max. Grooving Depth (mm) 5 10 15 20 25 30	Min. Bore (mm)	Ref. Page	Applicable Chipbreaker ML	GF
Straight Type	ø12	1,5			GNDIS	2,6	ø14	→ F30		◎
		1,5				3,6	ø14			◎
			2	3		2,6	ø14		◎	◎
			2	3		3,6	ø14		◎	◎
	ø16	1,5			GNDIS	3,6	ø16			◎
		1,5				4,6	ø20			◎
			2	3		3,6	ø16		◎	◎
			2	3		4,6	ø20		◎	◎
	ø20	1,5			GNDIS	6,6	ø25			◎
			2	3		6,6	ø25		◎	◎

Stock

GNDIS type: use smaller GXM type inserts

◎ 1st Recommendation

■ Series for Internal Machining (≥ Ø 32 mm ~)

Type	Shank Size ØDs(mm)	Cutting Width (mm) 2	3	4	5	6	Series	Max. Grooving Depth (mm) 5 10 15 20 25 30	Min. Bore (mm)	Ref. Page	Applicable Chipbreaker MG	ML	GG	GL	GF	CG	CF	RG	RN	GA
Straight Type	ø25	2					GNDI	6	ø32	→ F28		◎	○	◎	◎				◎	◎
			3	4	5			6	ø32		○	◎	○	◎	◎				◎	◎
	ø32	2						6	ø32			◎	○	◎	◎				◎	◎
			3	4	5			10	ø40		○	◎	○	◎	◎				◎	◎
	ø40		3	4	5	6		11	ø50		○	◎	○	◎	◎				◎	◎

Stock

◎ 1st Recommendation

○ 2nd Recommendation

Key Points for Face Machining

Holder Selection



Select a holder so that the outer diameter of the first groove to be machined comes within the range of maximum and minimum grooving diameter of the holder.

Precautions for Groove Expansion

Recommended Chipbreaker: **MG, ML, GG, GL, GF**



If the first groove meets the range of the effective grooving diameter during groove expansion, the grooving diameter will not be limited for the second and later passes.

Precautions for Turning

Recommended Chipbreaker: **MG, ML**

Considering the rigidity of the holder, we recommend machining from the outside to the inside.

O Outer Side → Inner Side



× Not Recommended: Inner Side → Outer Side



If machining is performed toward the outside, the wall thickness remaining on the principal force side will become thinner, which reduces the rigidity of the holder.

- If the first groove meets the range of the effective grooving diameter in face turning, the grooving diameter will not be limited for the second and later passes.
- Select the chipbreaker of the lower limit side of the recommended cutting conditions and straight chips before evacuation. (In face grooving, broken chips easily get stuck in grooves, which causes problems.)
- When breaking chips, step feed is required.

Key Points for Internal Machining

Precautions for Internal Machining

Recommended Chipbreaker: **ML, GL**

If the prepared hole diameter is small, use an ML or GL low-feed chipbreaker, each of which reduces chip curl diameter, to ensure adequate chip evacuation.

GCMN 3004 MG



GCMN 3002 ML

GCMN 3002 GG

GCMN 3002 GL

Work Material:	15CrMo5 (Ø 25 mm)
Holder:	GNDI R2532 T306
Insert:	GCM N300□-□□
Cutting Conditions:	v_c=100 m/min, f=0,10 mm/rev, a_p=3,0 mm, wet

Internal Machining

GCMN 3002 GG

External Machining

GCMN 3002 GG

⚠ Chip shapes differ between internal and external machining even under the same cutting conditions.

Work Material:	15CrMo5
Holder:	GNDL R2525M 320
Insert:	GCM N3002 GG
Cutting Conditions:	v_c=100 m/min, f=0,10 mm/rev, a_p=5 mm, wet

■ Notes on how to Attach Inserts

① Remove any foreign particles or oil from the insert seat before attaching the insert.
② Ensure the seat location is clean and free of damage.
③ Slide the insert level over its seat.
④ Push the insert with its opposite end (the holder side) firmly against the insert stop end.
⑤ The recommended tightening torque is 5 N·m. Tightening above the recommended torque may damage the insert or the holder which could cause injury and other accidents.

③ Attach insert on the seat flat.



④ Push insert fully into place.



■ Notes on how to Apply Holders

① Remove any foreign particles or oil from the tool post before attaching the holder.
② Ensure the seat location is clean and free of damage.
③ Attach the holder so that the insert is perpendicular to the workpiece.
④ Set holder with shortest possible overhang.
⑤ When grooving or turning, adjust the center height of the cutting edge to as close ±0 mm as possible. (Within ±0,1 mm is recommended)
⑥ Incorrect center height adjustment may cause chattering. (In cut-off applications, adjust the center height of the cutting edge to a value from 0,0 to +0,2 mm).
A lower center height will result in larger nip at the center.

③ Attach at right angle to workpiece.



④ Set with short overhang



⑥ Center height adjustment in cut-off applications



■ Notes on Setting Coolant Supply Nozzle

Set the coolant supply nozzle so that coolant can be supplied from the top of the upper clamp unit.



■ Maximum Depth of Cut

Maximum depth of cut when pulling up with RG chipbreaker



Grooving Width (mm)	Max. Depth of Cut (mm)
CW	E1
3,0	0,15
4,0	0,20
5,0	0,25
6,0	0,30
7,0	0,35
8,0	0,40

GND Type

■ Chipbreaker Selection Guide

Groov. Width (mm)	Recommended Cutting Conditions		Nose Radius (mm)	Inserts
	Grooving	Turning		
1,25			0,05	GCM N125005-GF
1,5			0,05	GCM N150005-GF
2,0			0,02 0,2 1,0	GCM R/L20002-CF-10 GCM R/L20002-CF-15 GCM N2002-ML GCM N2002-GG GCM N2002-GL GCM N2002-GF GCM R/L2002-CG-05 GCG N2002-GA GCM N2010-RN
3,0			0,02 0,2 0,4 1,5	GCM R/L30002-CF-10 GCM R/L30002-CF-15 GCM N3002-ML GCM N3002-GG GCM N3002-GL GCM N3002-GF GCM R/L3002-CG-05 GCG N3002-GA GCM N3004-MG GCM N3004-GG GCM N3015-RG GCM N3015-RN
4,0			0,2 0,4 0,8 2,0	GCM N4002-GG GCM N4002-GL GCM N4002-GF GCM R/L4002-CG-05 GCM N4004-ML GCM N4004-GG GCG N4004-GA GCM N4008-MG GCM N4020-RG GCM N4020-RN
5,0			0,2 0,4 0,8 2,5	GCM N5002-GG GCM N5002-GL GCM N5002-GF GCM N5004-ML GCM N5004-GG GCG N5004-GA GCM N5008-MG GCM N5025-RG GCM N5025-RN
6,0			0,2 0,4 0,8 3,0	GCM N6002-GG GCM N6002-GL GCM N6002-GF GCM N6004-ML GCM N6004-GG GCG N6004-GA GCM N6008-MG GCM N6030-RG GCM N6030-RN
7,0			0,2 0,4 0,8 3,5	GCM N7002-GF GCM N7004-ML GCM N7004-GG GCM N7004-GL GCM N7004-GF GCM N7008-MG GCM N7035-RG
8,0			0,2 0,4 0,8 4,0	GCM N8002-GF GCM N8004-ML GCM N8004-GG GCM N8004-GL GCM N8004-GF GCM N8008-MG GCM N8040-RG

■ Recommended Cutting Conditions

Work Material	P Carbon Steel, Alloy Steel				M Stainless Steel			K Cast Iron			S Exotic Alloy		N
Grade	AC830P	AC520U	AC530U AC1030U	T2500A	AC830P	AC520U	AC530U AC1030U	AC425K	AC520U	AC530U AC1030U	AC520U	AC530U AC1030U	H10
Cutting Speed (m/min)	80–200	80–200	50–200	50–200	70–150	70–150	50–150	80–200	60–200	50–200	20–80	20–60	150–300

GND Type

■ Identification Details – Holders

GND M R 25 25 (M) - (T) 3 12 (JE) (- 0 3 5)

①	②	③	④	⑤	⑥	⑦	⑧	⑨	⑩	⑪
Series Symbol: GND	Application: Chart 2	Holder Design: Chart 3	Shank Height / Dia.: Chart 4	Shank Width / Work Dia.: Chart 5	Shank Length: Chart 6	Type: Internal Grooving	Insert Width: Chart 7	Max. Grooving Depth: Chart 8	Coolant Supply: JE: Internal Coolant	Min. Machining Dia.: (mm)

② Application

Symbol	Application	
S	External Multi-Purpose	Grooving / Cut Off / Turning / Profiling
M	External Multi-Purpose	Grooving / Cut Off / Turning / Profiling
L	External Grooving	Grooving / Cut Off
MS	External L-Styled (Side Cut) Multi-Purpose	Grooving / Turning / Profiling
LS	External L-Styled (Side Cut) Deep Grooving	Grooving
N	Necking	Necking
I	Internal Grooving	Grooving / Turning / Profiling
IS	Internal Grooving	Grooving / Turning / Profiling
F	Face Grooving	Grooving / Turning / Profiling
FS	L-Shaped Tools for Facing	Grooving / Turning / Profiling
CM	Cassette for Polygon Holder	Radial Grooving
CF	Cassette for Polygon Holder	Face Grooving

③ Holder Design

Symbol	Direction
R	Right
L	Left

④ Shank Height / Diameter

Application	Symbol	Height (mm)
External/ Face Grooving (Shank Height)	10	10
	12	12
	16	16
	20	20
	25	25
Internal Grooving (Shank Diameter)	25	25
	32	32
	40	40

⑤ Shank Width / Work Dia.

Application	Symbol	Width (mm)
External/ Face Grooving (Shank Width)	10	10
	12	12
	16	16
	20	20
	25	25
Internal Grooving (Shank Diameter)	32	32
	40	40
	50	50

⑥ Shank Length

Symbol	Length (mm)
JX	120
K	125
M	150
P	170

⑧ Insert Width

Symbol	Groov. Width (mm)
1,25	1,25
1,5	1,5
2	2,0
3	3,0
4	4,0
5	5,0
6	6,0
7	7,0
8	8,0

⑨ Max. Grooving Depth

Symbol	Groov. Depth (mm)	Symbol	Groov. Depth (mm)
06	6,0	20	20,0
08	8,0	23	23,0
10	10,0	25	25,0
11	11,0		
12	12,0		
12,5	12,5		
14	14,0		
16	16,0		
18	18,0		

To ensure maximum rigidity, use the multi-purpose type holder to machine the maximum grooving depth.

■ Identification Details – Inserts

G C M N 30 02 (S) - G G - (05)

①	②	③	④	⑤	⑥	⑦	⑧	⑨
Series Symbol: **G**rooving	Front Relief Angle: **C**: 7°; X: Special	Tolerance: G Class; **M** Class	Insert Design: **N** Neutral; R Right Hand; L Left Hand	Insert Width	Nose Radius	Applicable Holder	Chipbreaker	Front Cutt. Edge Angle

⑤ Insert Width

Symbol	Groov. Width (mm)
125	1,25
150	1,5
20	2,0
30	3,0
40	4,0
50	5,0
60	6,0
70	7,0
80	8,0

⑥ Nose Radius

Symbol	R (mm)
005	0,05
02	0,2
04	0,4
08	0,8
15	1,5
20	2,0
25	2,5
30	3,0

⑦ Applicable Holder

Symbol	Holder
S	GNDIS

⑧ Chipbreaker

Symbol	Application
MG	Multi-Purpose: General Feed
ML	Multi-Purpose: Low Feed
GG	Grooving: General Feed
GL	Grooving: Low Feed
GF	Grooving: Low Cutting Forces
CG	Cut-Off
CF	Cut-Off: Low Cutting Forces
RG	Copying: General Feed
RN	Multi-Purpose: General Feed
GA	Multi-Purpose: General Feed

⑨ Front Cutt. Edge Angle

PSI
05 : 5°
10 : 10°
15 : 15°

GNDM /GNDL Type

External Multi-Purpose Small Tools Type (Grooving, Turning, Profiling)

GNDM

External Grooving (Small Tools)



External

Cut-Off



Use the multi-purpose profiling insert for turning (wide grooves).

Above figures show right hand tools.

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)							Grooving Width (mm)	Max. Groov. Depth (mm)	Max. Cutt-Off Dia (mm)	Applicable Insert	Cap Screw	N·m	Span-ner
	R	L	H	B	LF	WF	HF	LH	WF2	CW	CDX					
GNDM R/L 1616 JX 1.2508	●	●	16	16	120	(16)	16	26	0	1,25	8,0	16	GCM N125005 GF	BX0515	4,0	LH040
GNDM R/L 1616 JX 1.510	❍	❍	16	16	120	(16)	16	26	0	1,50	10,0	20	GCM N150005 GF			
GNDM R/L 1616 JX 212	❍	❍	16	16	120	(16)	16	30	0	2,00	12,0	24	GCM □20○○-□□			
GNDM R/L 1616 JX 312	❍	❍	16	16	120	(16)	16	30	0	3,00	12,0	24	GCM □30○○-□□			

Select holders and inserts with the same grooving width (CW).

External Grooving / Cut-Off Small Tools

GNDL

External Grooving (Small Tools)



External

Cut-Off

Fig. 1



Fig. 2



Above figures show right hand tools.

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)									Grooving Width (mm)	Max. Groov. Depth (mm)	Max. Cutt-Off Dia (mm)	Fig.	Applicable Insert	Cap Screw	N·m	Span-ner
	R	L	H	B	LF	WF	HF	HBH	LH	LH2	WF2	CW	CDX						
GNDL R/L 1010 JX 1.2510	●	●	10	10	120	(10)	10	2,0	18	18,3	0	1,25	10,0	20		GCM N125005 GF	BFTX0412N	**3,0**	LT15-10
GNDL R/L 1010 JX 1.510	●	●	10	10	120	(10)	10	2,0	18	18,3	0	1,50	10,0	20		GCM N150005 GF			
GNDL R/L 1010 JX 210	●	●	10	10	120	(10)	10	2,0	22	22,3	0	2,00	10,0	20	1	GCM □20○○-□□			
GNDL R/L 1010 JX 310	●	●	10	10	120	(10)	10	2,0	22	22,3	0	3,00	10,0	20		GCM □30○○-□□			
GNDL R/L 1212 JX 1.2512	●	●	12	12	120	(12)	12	2,0	19	19,3	0	1,25	12,0	24		GCM N125005 GF	BFTX0412N	**3,0**	LT15-10
GNDL R/L 1212 JX 1.512	●	●	12	12	120	(12)	12	2,0	19	19,3	0	1,50	12,0	24		GCM N150005 GF			
GNDL R/L 1212 JX 212.5	●	●	12	12	120	(12)	12	2,0	22	22,3	0	2,00	12,5	25	1	GCM □20○○-□□			
GNDL R/L 1212 JX 312.5	●	●	12	12	120	(12)	12	2,0	22	22,3	0	3,00	12,5	25		GCM □30○○-□□			
GNDL R/L 1616 JX 1.2512.5	●	●	16	16	120	(16)	16		28		0	1,25	12,5	20		GCM N125005 GF	BFTX0515	**4,0**	LH040
GNDL R/L 1616 JX 1.512.5	●	●	16	16	120	(16)	16		28		0	1,50	12,5	25		GCM N150005 GF			
GNDL R/L 1616 JX 216	●	●	16	16	120	(16)	16		32		0	2,00	16,0	32	2	GCM □20○○-□□			
GNDL R/L 1616 JX 316	●	●	16	16	120	(16)	16		32		0	3,00	16,0	32		GCM □30○○-□□			

Select holders and inserts with the same grooving width (CW).

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

■ Inserts for GNDM (Small Tools) / GNGL (Small Tools)

Application	Shape	Type	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		General Purpose	GCM N3004 MG	●	●	❍	●			**3,0**	±0,03	0,4	21,1	3,8
		Low Feed	GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
Copying / Cut-Off		General Purpose	GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N3004 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
		Low Feed	GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
			M3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
		Low Cutting Force	GCM N125005 GF				●			1,25	±0,03	0,05	17,4	3,2
			N150005 GF				●			1,5	±0,03	0,05	17,4	3,7
			N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
			N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
Copying		General Purpose	GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
Face / Necking		General Purpose	GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
Non Ferrous Metals		General Purpose	GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
			N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8

Application	Shape	Type	Cat. No.	Coated Carbide AC830P R	AC830P L	AC520U R	AC520U L	AC530U R	AC530U L	AC1030U R	AC1030U L	Cermet R	Cermet L	PSI	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Cut-Off	Figures show right hand tools. 	General Purpose	GCM R/L2002 CG 05	❍	❍	❍	❍	●	●					5°	2,0	±0,03	0,2	21,1	3,6
			R/L3002 CG 05	●	❍	❍	❍	●	●					5°	3,0	±0,03	0,2	21,3	3,8
			R/L4002 CG 05	❍	❍	❍	❍	●	●					5°	4,0	±0,04	0,2	26,7	4,0
Cut-Off		Low Cutting Force	New GCM R/L20003 CF 10							●	●			10°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 10							●	●			10°	3,0	±0,08	0,03	22,4	3,8
			R/L20003 CF 15							●	●			15°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 15							●	●			15°	3,0	±0,08	0,03	22,4	3,8

Select holders and inserts with the same grooving width (CW).

GNDS Type

External Multi-Purpose Shallow Grooves Type (Grooving, Turning, Profiling)





Use the multi-purpose profiling insert for turning (wide grooves).

Above figures show right hand tools.

Spare Parts

Holders

Cat. No.	Stock		Dimensions (mm)						Grooving Width (mm)	Max. Groov. Depth (mm)	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	H	B	LF	WF	HF	LH	CW	CDX				
GNDS R/L 2020 K 206	❍	❍	20	20	125	20	20	30	2,0	6	GCM □20○○-□□	BX0520	5,0	LH040
GNDS R/L 2020 K 306	❍	❍	20	20	125	20	20	30	3,0	6	GCM □30○○-□□			
GNDS R/L 2020 K 410	❍	❍	20	20	125	20	20	34	4,0	10	GCM □40○○-□□			
GNDS R/L 2020 K 510	❍	❍	20	20	125	20	20	34	5,0	10	GCM N50○○-□□			
GNDS R/L 2020 K 610	❍	❍	20	20	125	20	20	34	6,0	10	GCM N60○○-□□			
GNDS R/L 2525 M 206	❍	❍	25	25	150	25	25	30	2,0	6	GCM □20○○-□□			
GNDS R/L 2525 M 306	❍	❍	25	25	150	25	25	30	3,0	6	GCM □30○○-□□			
GNDS R/L 2525 M 410	❍	❍	25	25	150	25	25	34	4,0	10	GCM □40○○-□□			
GNDS R/L 2525 M 510	❍	❍	25	25	150	25	25	34	5,0	10	GCM N50○○-□□			
GNDS R/L 2525 M 610	❍	❍	25	25	150	25	25	34	6,0	10	GCM N60○○-□□			

Select holders and inserts with the same grooving width (CW).

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

■ Inserts for GNDS

Application	Shape	Type	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
		ML  CW=<4mm CW=>5mm Low Feed	GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
Copying / Cut-Off		**GG**  General Purpose	GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
		GL  Low Feed	GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
		GF  Low Cutting Force	GCM N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
			N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
Copying		**RG**  General Purpose	GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
			N4020 RG	❍	●	❍	●	❍		4,0	±0,03	2,0	26,4	4,0
			N5025 RG	●	●	❍	●			5,0	±0,03	2,5	27,2	4,1
			N6030 RG	❍	●	❍	●			6,0	±0,03	3,0	27,5	4,5
Face / Necking		**RN**  General Purpose	GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
			N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Application	Shape	Type	Cat. No.	Coated Carbide AC830P R	AC830P L	AC520U R	AC520U L	AC530U R	AC530U L	AC1030U R	AC1030U L	Cermet R	Cermet L	PSI	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Cut-Off	Figures show right hand tools. 	**CG**  General Purpose	GCM R/L2002 CG 05	❍	❍	❍	❍	●	●					5°	2,0	±0,03	0,2	21,1	3,6
			R/L3002 CG 05	●	❍	❍	❍	●	●					5°	3,0	±0,03	0,2	21,3	3,8
			R/L4002 CG 05	❍	❍	❍	❍	●	●					5°	4,0	±0,03	0,2	26,7	4,0
Cut-Off		**CF** New  Low Cutting Force	GCM R/L20003 CF 10							●	●			10°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 10							●	●			10°	3,0	±0,08	0,03	22,4	3,8
			R/L20003 CF 15							●	●			15°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 15							●	●			15°	3,0	±0,08	0,03	22,4	3,8

Select holders and inserts with the same grooving width (CW).

GNDM / GNDMS Type

External Multi-Purpose Type (Grooving, Turning, Profiling)

GNDM
External Grooving



External

Cut-Off

Use for multi-purpose or profiling insert for turning (wide grooves).



Above figures show right hand tools.

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)						Grooving Width (mm)	Max. Groov. Depth (mm)	Max. Cutt-Off Dia (mm)	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	H	B	LF	WF	HF	LH	CW	CDX					
GNDM R/L 2020 K 1.2510	●	●	20	20	125	20	20	34,0	1,25	10	20	GCM N125005 GF	BX0520	5,0	LH040
GNDM R/L 2020 K 1.510	●	●	20	20	125	20	20	34,0	1,50	10	20	GCM N150005 GF			
GNDM R/L 2020 K 210	○	○	20	20	125	20	20	33,6	2,00	10	20	GCM □20○○-□□			
GNDM R/L 2020 K 312	○	○	20	20	125	20	20	36,6	3,00	12	24	GCM □30○○-□□			
GNDM R/L 2020 K 418	○	○	20	20	125	20	20	45,0	4,00	18	36	GCM □40○○-□□			
GNDM R/L 2020 K 518	●	○	20	20	125	20	20	45,0	5,00	18	36	GCM N50○○-□□			
GNDM R/L 2020 K 618	○	○	20	20	125	20	20	45,0	6,00	18	36	GCM N60○○-□□			
GNDM R/L 2525 M 1.2510	●	●	25	25	150	25	25	36,0	1,25	10	20	GCM N125005 GF			
GNDM R/L 2525 M 1.510	●	●	25	25	150	25	25	36,0	1,25	10	20	GCM N150005 GF			
GNDM R/L 2525 M 210	○	○	25	25	150	25	25	33,6	2,00	10	20	GCM N20○○-□□			
GNDM R/L 2525 M 312	○	○	25	25	150	25	25	36,6	3,00	12	24	GCM □30○○-□□			
GNDM R/L 2525 M 418	○	○	25	25	150	25	25	45,0	4,00	18	36	GCM □40○○-□□			
GNDM R/L 2525 M 518	○	○	25	25	150	25	25	45,0	5,00	18	36	GCM N50○○-□□			
GNDM R/L 2525 M 618	●	○	25	25	150	25	25	45,0	6,00	18	36	GCM N60○○-□□			
GNDM R/L 3225 P 312			32	25	170	25	32	36,6	3,00	12	24	GCM □30○○-□□			
GNDM R/L 3225 P 418			32	25	170	25	32	45,0	4,00	18	36	GCM □40○○-□□			
GNDM R/L 3225 P 518			32	25	170	25	32	45,0	5,00	18	36	GCM N50○○-□□			
GNDM R/L 3225 P 618			32	25	170	25	32	45,0	6,00	18	36	GCM N60○○-□□			
GNDM R/L 3225 P 718			32	25	170	25	32	50,0	7,00	18	36	GCM N70○○-□□	BX0620	6,0	LH050
GNDM R/L 3225 P 818			32	25	170	25	32	50,0	8,00	18	36	GCM N80○○-□□			
GNDM R/L 3232 P 312	●	●	32	32	170	32	32	36,6	3,00	12	24	GCM □30○○-□□	BX0620	6,0	LH050
GNDM R/L 3232 P 418	●	●	32	32	170	32	32	45,0	4,00	18	36	GCM □40○○-□□			
GNDM R/L 3232 P 518	●	●	32	32	170	32	32	45,0	5,00	18	36	GCM N50○○-□□			
GNDM R/L 3232 P 618	●	●	32	32	170	32	32	45,0	6,00	18	36	GCM N60○○-□□			
GNDM R/L 3232 P 718	●	●	32	32	170	32	32	50,0	7,00	18	36	GCM N70○○-□□			
GNDM R/L 3232 P 818	●	●	32	32	170	32	32	50,0	8,00	18	36	GCM N80○○-□□			

Select holders and inserts with the same grooving width (CW).

External L-Styled (Side Cut) Multi-Purpose Type (Grooving, Turning, Profiling)

GNDMS
External Grooving



External

Use for multi-purpose or profiling insert for turning (wide grooves).



Above figures show right hand tools.

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)						Grooving Width (mm)	Max. Groov. Depth (mm)	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	H	B	LF	WF	HF	LH	CW	CDX				
GNDMS R/L 2020 K 310	●	●	20	20	125	32	20	25	3,0	10	GCM □30○○-□□	BX0520	5,0	LH040
GNDMS R/L 2020 K 412	●	●	20	20	125	34	20	25	4,0	12	GCM □40○○-□□			
GNDMS R/L 2020 K 512	●	●	20	20	125	34	20	25	5,0	12	GCM N50○○-□□			
GNDMS R/L 2525 M 312	●	●	25	25	150	39	25	25	3,0	12	GCM □30○○-□□			
GNDMS R/L 2525 M 414	●	●	25	25	150	41	25	25	4,0	14	GCM □40○○-□□			
GNDMS R/L 2525 M 514	●	●	25	25	150	41	25	25	5,0	14	GCM N50○○-□□			
GNDMS R/L 2525 M 614	●	●	25	25	150	41	25	25	6,0	14	GCM N60○○-□□			

Select holders and inserts with the same grooving width (CW).

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

■ Inserts for GNDM / GNDMS

Application	Shape	Type	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
			N7008 MG	❍	●	❍	●			7,0	±0,04	0,8	28,75	5,5
			N8008 MG	●	●	❍	●			8,0	±0,04	0,8	28,75	6,0
		ML  Low Feed	GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
			N7004 ML	●	●	❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 ML	❍	●	❍	●			8,0	±0,04	0,4	28,75	6,0
Copying / Cut-Off		**GG**  General Purpose	GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
			N7004 GG	❍		❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 GG	●		❍	●			8,0	±0,04	0,4	28,75	6,0
		GL  Low Feed	GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			N7004 GL	❍		❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 GL	❍		❍	●			8,0	±0,04	0,4	28,75	6,0
		GF  Low Cutting Force	GCM N125005 GF				●			1,25	±0,03	0,05	17,4	3,2
			N150005 GF				●			1,5	±0,03	0,05	17,4	3,7
			N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
			N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
			N7002 GF	❍		❍	●			7,0	±0,04	0,2	28,75	5,5
			N8002 GF	❍		❍	●			8,0	±0,04	0,2	28,75	6,0
			GCM N7004 GF	❍		❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 GF	❍		❍	●			8,0	±0,04	0,4	28,75	6,0
Copying		**RG**  General Purpose	GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
			N4020 RG	❍	●	❍	●	❍		4,0	±0,03	2,0	26,4	4,0
			N5025 RG	●	●	❍	●			5,0	±0,03	2,5	27,2	4,1
			N6030 RG	❍	●	❍	●			6,0	±0,03	3,0	27,5	4,5
			N7035 RG	❍	●	❍	●			7,0	±0,04	3,5	29,05	5,5
			N8040 RG	❍	●	❍	●			8,0	±0,04	4,0	29,25	6,0
Face / Necking		**RN**  General Purpose	GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
			N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Application	Shape	Type	Cat. No.	Coated Carbide AC830P R	AC830P L	AC520U R	AC520U L	AC530U R	AC530U L	AC1030U R	AC1030U L	R	L	Dimensions (mm) PSI	CW Cutting Width	CW Tolerance	RE	L	S
Cut-Off	Figures show right hand tools. 	**CG**  General Purpose	GCM R/L2002 CG 05	❍	❍	❍	❍	●	●					5°	2,0	±0,03	0,2	21,1	3,6
			R/L3002 CG 05	●	❍	❍	❍	●	●					5°	3,0	±0,03	0,2	21,3	3,8
			R/L4002 CG 05	❍	❍	❍	❍	●	●					5°	4,0	±0,04	0,2	26,7	4,0
Cut-Off		**CF** New  Low Cutting Force	GCM R/L20003 CF 10							●	●			10°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 10							●	●			10°	3,0	±0,08	0,03	22,4	3,8
			R/L20003 CF 15							●	●			15°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 15							●	●			15°	3,0	±0,08	0,03	22,4	3,8

Select holders and inserts with the same grooving width (CW).

GNDM-JE Type

New

Holder with Internal Coolant

External Multi-Purpose Type (Grooving, Turning, Profiling)



External

Internal Coolant

Cut-Off

Use for multi-purpose or profiling insert for turning (wide grooves).



Above figures show right hand tools.

Holders

Cat. No.	Stock		Dimensions (mm)						Grooving Width (mm)	Max. Groov. Depth (mm)	Max. Cutt-Off Dia (mm)	Applicable Insert	Cap Screw	N·m	Plug and Sealing	Grub Screw*	Span-ner
	R	L	H	B	LF	WF	HF	LH	CW	CDX							
GNDM R/L 2020 X 210 JE	●	●	20	20	100	20	20	33,6	2,00	10	20	GC□ □20○○-□□	BX0520	6,0	XP02-E	BT0505-E	LH040
GNDM R/L 2020 X 312 JE	●	●	20	20	100	20	20	36,6	3,00	12	24	GC□ □30○○-□□					
GNDM R/L 2020 X 418 JE	●	●	20	20	110	20	20	45,0	4,00	18	36	GC□ □40○○-□□					
GNDM R/L 2020 X 518 JE	●	●	20	20	110	20	20	45,0	5,00	18	36	GC□ N50○○-□□					
GNDM R/L 2020 X 618 JE	●	●	20	20	110	20	20	45,0	6,00	18	36	GC□ N60○○-□□					
GNDM R/L 2525 X 210 JE	●	●	25	25	100	25	25	33,6	2,00	10	20	GC□ □20○○-□□					
GNDM R/L 2525 X 312 JE	●	●	25	25	100	25	25	36,6	3,00	12	24	GC□ □30○○-□□					
GNDM R/L 2525 X 418 JE	●	●	25	25	110	25	25	45,0	4,00	18	36	GC□ □40○○-□□					
GNDM R/L 2525 X 518 JE	●	●	25	25	110	25	25	45,0	5,00	18	36	GC□ N50○○-□□					
GNDM R/L 2525 X 618 JE	●	●	25	25	110	25	25	45,0	6,00	18	36	GC□ N60○○-□□					

Select holders and inserts with the same grooving width (CW).

*Grub screws are sold separately (M5x5)

Spare Parts



Fig. 1



Fig. 1



Fig. 2



Fig. 3



Parts (Hose)

Cat. No.	Stock	L (mm)	Screw Stan-dard	Screw Stan-dard	Fig.
J-HOSE-G1/8-G1/8-200-E	●	200	G1/8	G1/8	1
J-HOSE-G1/8-G1/8-300-E	●	300	G1/8	G1/8	1

Hoses are sold separately.

Parts (Connector)

Cat. No.	Stock	Screw Stan-dard	Screw Stan-dard	Fig.
J-G1/8-G1/8-00-E	●	G1/8	G1/8	1
J-G1/8-G1/8F-90-E	●	G1/8	G1/8	2
J-G1/8-G1/8-90-E	●	G1/8	G1/8	3

Connectors are sold separately.

Piping Method for Hoses and Connectors



Apply sealant such as commercial sealing tape to the piping connection parts.
GNDM-JE type holders have a plug (XP02-E) mounted on the holder back end at shipping. (see fig.1)
When piping from the holder back end, mount a grub screw (BT0505-E) on the bottom of the holder for use. (see fig. 2)

Fig. 1 Piping from bottom.



Fig. 2 Piping from back end.



Grooving & Parting-Off

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

GNDM-JE Type

■ Inserts for GNDM-JE

Application	Shape	Type	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
		ML  CW=<4mm CW=>5mm Low Feed	GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
Copying / Cut-Off		**GG**  General Purpose	GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
		GL  Low Feed	GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
		GF  Low Cutting Force	GCM N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
			N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
Copying		**RG**  General Purpose	GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
			N4020 RG	❍	●	❍	●	❍		4,0	±0,03	2,0	26,4	4,0
			N5025 RG	●	●	❍	●			5,0	±0,03	2,5	27,2	4,1
			N6030 RG	❍	●	❍	●			6,0	±0,03	3,0	27,5	4,5
Face / Necking		**RN**  General Purpose	GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
			N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Application	Shape	Type	Cat. No.	Coated Carbide AC830P R	AC830P L	AC520U R	AC520U L	AC530U R	AC530U L	AC1030U R	AC1030U L	Cermet R	Cermet L	PSI	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Cut-Off	Figures show right hand tools. 	**CG**  General Purpose	GCM R/L2002 CG 05	❍	❍	❍	❍	●	●					5°	2,0	±0,03	0,2	21,1	3,6
			R/L3002 CG 05	●	❍	❍	❍	●	●					5°	3,0	±0,03	0,2	21,3	3,8
			R/L4002 CG 05	❍	❍	❍	❍	●	●					5°	4,0	±0,03	0,2	26,7	4,0
Cut-Off		**CF** New  Low Cutting Force	GCM R/L20003 CF 10							●	●			10°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 10							●	●			10°	3,0	±0,08	0,03	22,4	3,8
			R/L20003 CF 15							●	●			15°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 15							●	●			15°	3,0	±0,08	0,03	22,4	3,8

Select holders and inserts with the same grooving width (CW).

GNDL / GNDLS Type

External Deep Grooving and Cut-Off

GNDL
External Grooving



External

Cut-Off



Above figures show right hand tools.

■ Spare Parts

■ Holders

Cat. No.	Stock		Dimensions (mm)						Grooving Width (mm)	Max. Groov. Depth (mm)	Max. Cutt-Off Dia (mm)	Applicable Insert	Cap Screw	N·m	Span-ner
	R	L	H	B	LF	WF	HF	LH	CW	CDX					
GNDL R/L 2020 K 1.2516	●	●	20	20	125	20	20	38,0	1,25	16	32	GCM N125005 GF	BX0520	5,0	LH040
GNDL R/L 2020 K 1.516	●	●	20	20	125	20	20	38,0	1,50	16	32	GCM N150005 GF			
GNDL R/L 2020 K 220	●	●	20	20	125	20	20	44,5	2,00	20	40	GCM □20○○-□□			
GNDL R/L 2020 K 320	●	●	20	20	125	20	20	44,5	3,00	20(18)	40	GCM □30○○-□□			
GNDL R/L 2020 K 425	●	●	20	20	125	20	20	50,0	4,00	25(23)	50	GCM □40○○-□□			
GNDL R/L 2020 K 525	●	●	20	20	125	20	20	50,0	5,00	25(23)	50	GCM N50○○-□□			
GNDL R/L 2020 K 625	●	●	20	20	125	20	20	50,0	6,00	25(23)	50	GCM N60○○-□□			
GNDL R/L 2525 M 1.2516	●	●	25	25	150	25	25	40,0	1,25	16	32	GCM N125005 GF			
GNDL R/L 2525 M 1.516	●	●	25	25	150	25	25	40,0	1,50	16	32	GCM N150005 GF			
GNDL R/L 2525 M 220	●	●	25	25	150	25	25	44,5	2,00	20	40	GCM □20○○-□□			
GNDL R/L 2525 M 320	●	●	25	25	150	25	25	44,5	3,00	20(18)	40	GCM □30○○-□□			
GNDL R/L 2525 M 425	●	●	25	25	150	25	25	50,0	4,00	25(23)	50	GCM □40○○-□□			
GNDL R/L 2525 M 525	●	●	25	25	150	25	25	50,0	5,00	25(23)	50	GCM N50○○-□□			
GNDL R/L 2525 M 625	●	●	25	25	150	25	25	50,0	6,00	25(23)	50	GCM N60○○-□□			
GNDL R/L 3225 P 320			32	25	170	25	32	44,5	3,00	20(18)	40	GCM □30○○-□□			
GNDL R/L 3225 P 425			32	25	170	25	32	50,0	4,00	25(23)	50	GCM □40○○-□□			
GNDL R/L 3225 P 525			32	25	170	25	32	50,0	5,00	25(23)	50	GCM N50○○-□□			
GNDL R/L 3225 P 625			32	25	170	25	32	50,0	6,00	25(23)	50	GCM N60○○-□□			
GNDL R/L 3225 P 725			32	25	170	25	32	50,0	7,00	25(23)	50	GCM N70○○-□□	BX0520	6,0	LH050
GNDL R/L 3225 P 825			32	25	170	25	32	50,0	8,00	25(23)	50	GCM N80○○-□□			
GNDL R/L 3232 P 320	●	●	32	32	170	32	32	44,5	3,00	20(18)	40	GCM □30○○-□□	BX0620	6,0	LH050
GNDL R/L 3232 P 425	●	●	32	32	170	32	32	50,0	4,00	25(23)	50	GCM □40○○-□□			
GNDL R/L 3232 P 525	●	●	32	32	170	32	32	50,0	5,00	25(23)	50	GCM N50○○-□□			
GNDL R/L 3232 P 625	●	●	32	32	170	32	32	50,0	6,00	25(23)	50	GCM N60○○-□□			
GNDL R/L 3232 P 725	●	●	32	32	170	32	32	50,0	7,00	25(23)	50	GCM N70○○-□□			
GNDL R/L 3232 P 825	●	●	32	32	170	32	32	50,0	8,00	25(23)	50	GCM N80○○-□□			

Select holders and inserts with the same grooving width (CW). Dimensions in parentheses are for applications that use copying inserts (RG type breakers).

External L-Styled (Side Cut) Grooving

GNDLS
External Grooving



External



Above figures show right hand tools.

■ Spare Parts

■ Holders

Cat. No.	Stock		Dimensions (mm)						Grooving Width (mm)	Max. Groov. Depth (mm)	Applicable Insert	Cap Screw	N·m	Span-ner
	R	L	H	B	LF	WF	HF	LH	CW	CDX				
GNDLS R/L 2020 K 216	●	●	20	20	125	38	20	25	2,0	16	GCM □20○○-□□	BX0520	5,0	LH040
GNDLS R/L 2020 K 316	●	●	20	20	125	38	20	25	3,0	16	GCM □30○○-□□			
GNDLS R/L 2525 M 218	●	●	25	25	150	45	25	25	2,0	18	GCM □20○○-□□			
GNDLS R/L 2525 M 318	●	●	25	25	150	45	25	25	3,0	18	GCM □30○○-□□			
GNDLS R/L 2525 M 423	●	●	25	25	150	50	25	25	4,0	23	GCM □40○○-□□			
GNDLS R/L 2525 M 523	●	●	25	25	150	50	25	25	5,0	23	GCM N50○○-□□			
GNDLS R/L 2525 M 623	●	●	25	25	150	50	25	25	6,0	23	GCM N60○○-□□			

Select holders and inserts with the same grooving width (CW).

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

■ Inserts for GNDL / GNDLS

Application	Shape	Type	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
			N7008 MG	❍	●	❍	●			7,0	±0,04	0,8	28,75	5,5
			N8008 MG	●	●	❍	●			8,0	±0,04	0,8	28,75	6,0
		ML  Low Feed	GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
			N7004 ML	●	●	❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 ML	❍	●	❍	●			8,0	±0,04	0,4	28,75	6,0
Copying / Cut-Off		**GG**  General Purpose	GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
			N7004 GG	❍		❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 GG	●		❍	●			8,0	±0,04	0,4	28,75	6,0
		GL  Low Feed	GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			N7004 GL	❍		❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 GL	❍		❍	●			8,0	±0,04	0,4	28,75	6,0
		GF  Low Cutting Force	GCM N125005 GF				●			1,25	±0,03	0,05	17,4	3,2
			N150005 GF				●			1,5	±0,03	0,05	17,4	3,7
			N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
			N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
			N7002 GF	❍		❍	●			7,0	±0,04	0,2	28,75	5,5
			N8002 GF	❍		❍	●			8,0	±0,04	0,2	28,75	6,0
			GCM N7004 GF	❍		❍	●			7,0	±0,04	0,4	28,75	5,5
			N8004 GF	❍		❍	●			8,0	±0,04	0,4	28,75	6,0
Copying		**RG**  General Purpose	GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
			N4020 RG	❍	●	❍	●	❍		4,0	±0,03	2,0	26,4	4,0
			N5025 RG	●	●	❍	●			5,0	±0,03	2,5	27,2	4,1
			N6030 RG	❍	●	❍	●			6,0	±0,03	3,0	27,5	4,5
			N7035 RG	❍	●	❍	●			7,0	±0,04	3,5	29,05	5,5
			N8040 RG	❍	●	❍	●			8,0	±0,04	4,0	29,25	6,0
Face / Necking		**RN**  General Purpose	GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
			N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Application	Shape	Type	Cat. No.	Coated Carbide AC830P R	AC830P L	AC520U R	AC520U L	AC530U R	AC530U L	AC1030U R	AC1030U L	R	L	Dimensions (mm) PSI	CW Cutting Width	CW Tolerance	RE	L	S
Cut-Off	Figures show right hand tools. 	**CG**  General Purpose	GCM R/L2002 CG 05	❍	❍	❍	❍	●	●					5°	2,0	±0,03	0,2	21,1	3,6
			R/L3002 CG 05	●	❍	❍	❍	●	●					5°	3,0	±0,03	0,2	21,3	3,8
			R/L4002 CG 05	❍	❍	❍	❍	●	●					5°	4,0	±0,04	0,2	26,7	4,0
Cut-Off		**CF** New  Low Cutting Force	GCM R/L20003 CF 10							●	●			10°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 10							●	●			10°	3,0	±0,08	0,03	22,4	3,8
			R/L20003 CF 15							●	●			15°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 15							●	●			15°	3,0	±0,08	0,03	22,4	3,8

Select holders and inserts with the same grooving width (CW).

New

External Deep Grooving and Cut-Off

GNDL-JE
External Grooving



External

Cut-Off

Internal Coolant



Above figures show right hand tools.

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)						Grooving Width (mm)	Max. Groov. Depth (mm)	Max. Cutt-Off Dia (mm)	Applicable Insert	Cap Screw	N·m	Plug and Sealing	Grub Screw*	Spanner
	R	L	H	B	LF	WF	HF	LH	CW	CDX							
GNDL R/L 2020 X 210 JE	●	●	20	20	110	20	20	44,5	2,00	20	20	GC□ □20○○-□□	BX0520	6,0	XP02-E	BT0505-E	LH040
GNDL R/L 2020 X 312 JE	●	●	20	20	110	20	20	44,5	3,00	20	24	GC□ □30○○-□□					
GNDL R/L 2020 X 418 JE	●	●	20	20	115	20	20	50,0	4,00	25	36	GC□ □40○○-□□					
GNDL R/L 2020 X 518 JE	●	●	20	20	115	20	20	50,0	5,00	25	36	GC□ N50○○-□□					
GNDL R/L 2020 X 618 JE	●	●	20	20	115	20	20	50,0	6,00	25	36	GC□ N60○○-□□					
GNDL R/L 2525 X 210 JE	●	●	25	25	110	25	25	44,5	2,00	20	20	GC□ □20○○-□□					
GNDL R/L 2525 X 312 JE	●	●	25	25	110	25	25	44,5	3,00	20	24	GC□ □30○○-□□					
GNDL R/L 2525 X 418 JE	●	●	25	25	115	25	25	50,0	4,00	25	36	GC□ □40○○-□□					
GNDL R/L 2525 X 518 JE	●	●	25	25	115	25	25	50,0	5,00	25	36	GC□ N50○○-□□					
GNDL R/L 2525 X 618 JE	●	●	25	25	115	25	25	50,0	6,00	25	36	GC□ N60○○-□□					

Select holders and inserts with the same grooving width (CW).

*Grub screws are sold separately (M5x5)

Fig. 1



Fig. 1



Fig. 2



Fig. 3



Parts (Hose)

Cat. No.	Stock	L (mm)	Screw Standard	Screw Standard	Fig.
J-HOSE-G1/8-G1/8-200-E	●	200	G1/8	G1/8	1
J-HOSE-G1/8-G1/8-300-E	●	300	G1/8	G1/8	1

Hoses are sold separately.

Parts (Connector)

Cat. No.	Stock	Screw Standard	Screw Standard	Fig.
J-G1/8-G1/8-00-E	●	G1/8	G1/8	1
J-G1/8-G1/8F-90-E	●	G1/8	G1/8	2
J-G1/8-G1/8-90-E	●	G1/8	G1/8	3

Connectors are sold separately.

Piping Method for Hoses and Connectors



Apply sealant such as commercial sealing tape to the piping connection parts.
GNDL-JE type holders have a plug (XP02-E) mounted on the holder back end at shipping. (see fig.1)
When piping from the holder back end, mount a grub screw (BT0505-E) on the bottom of the holder for use. (see fig. 2)

Fig. 1 Piping from bottom.



Fig. 2 Piping from back end.



Grooving & Parting-Off

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

GNDL-JE Type

■ Inserts for GNDL-JE

Application	Shape	Type	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
		ML  CW=<4mm CW=>5mm Low Feed	GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
Copying / Cut-Off		**GG**  General Purpose	GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
		GL  Low Feed	GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
		GF  Low Cutting Force	GCM N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
			N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
Copying		**RG**  General Purpose	GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
			N4020 RG	❍	●	❍	●	❍		4,0	±0,03	2,0	26,4	4,0
			N5025 RG	●	●	❍	●			5,0	±0,03	2,5	27,2	4,1
			N6030 RG	❍	●	❍	●			6,0	±0,03	3,0	27,5	4,5
Face / Necking		**RN**  General Purpose	GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
			N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Application	Shape	Type	Cat. No.	Coated Carbide AC830P R	AC830P L	AC520U R	AC520U L	AC530U R	AC530U L	AC1030U R	AC1030U L	Cermet R	Cermet L	PSI	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Cut-Off	Figures show right hand tools. 	**CG**  General Purpose	GCM R/L2002 CG 05	❍	❍	❍	❍	●	●					5°	2,0	±0,03	0,2	21,1	3,6
			R/L3002 CG 05	●	❍	❍	❍	●	●					5°	3,0	±0,03	0,2	21,3	3,8
			R/L4002 CG 05	❍	❍	❍	❍	●	●					5°	4,0	±0,03	0,2	26,7	4,0
Cut-Off		**CF** New  Low Cutting Force	GCM R/L20003 CF 10							●	●			10°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 10							●	●			10°	3,0	±0,08	0,03	22,4	3,8
			R/L20003 CF 15							●	●			15°	2,0	±0,08	0,03	22,4	3,6
			R/L30003 CF 15							●	●			15°	3,0	±0,08	0,03	22,4	3,8

Select holders and inserts with the same grooving width (CW).

GNDI Type

Internal Grooving



Use for multi-purpose or profiling insert for turning (wide grooves).



Above figures show right hand tools.

■ Spare Parts

■ Holders

Cat. No.	Stock		Dimensions (mm)				Min. Bore (mm)	Groov. Width (mm)	Max. Groov. Depth (mm)	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	DCON	H	LF	WF	DMIN	CW	CDX				
GNDI R/L 2532 T 206	●	●	25	23	200	16	32	2,0	6	GCM N20OO-□□	BH0516	5,0	LH030
GNDI R/L 3240 T 210	●	●	32	30	250	26	40	2,0	10	GCM N20OO-□□	BH0616	6,0	LH040
GNDI R/L 2532 T 306	●	●	25	23	200	16	32	3,0	6	GCM N30OO-□□	BH0516	5,0	LH030
GNDI R/L 3240 T 310	●	●	32	30	250	26	40	3,0	10	GCM N30OO-□□	BH0616	6,0	LH040
GNDI R/L 4050 T 311	●	●	40	38	300	31	50	3,0	11	GCM N30OO-□□			
GNDI R/L 2532 T 406	●	●	25	23	200	19	32	4,0	6	GCM N40OO-□□	BH0516	5,0	LH030
GNDI R/L 3240 T 410	●	●	32	30	250	26	40	4,0	10	GCM N40OO-□□	BH0616	6,0	LH040
GNDI R/L 4050 T 411	●	●	40	38	300	31	50	4,0	11	GCM N40OO-□□			
GNDI R/L 2532 T 506	●	●	25	23	200	19	32	5,0	6	GCM N50OO-□□	BH0516	5,0	LH030
GNDI R/L 3240 T 510	●	●	32	30	250	26	40	5,0	10	GCM N50OO-□□	BH0616	6,0	LH040
GNDI R/L 4050 T 511	●	●	40	38	300	31	50	5,0	11	GCM N50OO-□□			
GNDI R/L 4050 T 611	●	●	40	38	300	31	50	6,0	11	GCM N60OO-□□	BH0616	6,0	LH040

Select holders and inserts with the same grooving width (CW).

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

GNDI Type

■ GNDI Inserts

Application	Shape	Type	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
		ML  CW=<4mm CW=>5mm Low Feed	GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
Copying / Cut-Off		**GG**  General Purpose	GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
		GL  Low Feed	GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
			N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
		GF  Low Cutting Force	GCM N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
			N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
Copying		**RG**  General Purpose	GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
			N4020 RG	❍	●	❍	●	❍		4,0	±0,03	2,0	26,4	4,0
			N5025 RG	●	●	❍	●			5,0	±0,03	2,5	27,2	4,1
			N6030 RG	❍	●	❍	●			6,0	±0,03	3,0	27,5	4,5
Face / Necking		**RN**  General Purpose	GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
			N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Select holders and inserts with the same grooving width (CW).

GNDIS Type

Internal Grooving





Above figures show right hand tools.

Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)					Min. Bore (mm)	Groov. Width (mm)	Max. Groov. Depth (mm)	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	DCON	H	LF	LH	WF	DMIN	CW	CDX				
GNDIS R/L 1214 T 1526	❍	❍	12	11	150	30	9,0	14	1,5	2,6	GXM N150005S GF			
GNDIS R/L 1214 T 1536	❍	❍	12	11	150	30	10,0	14	1,5	3,6	GXM N150005S GF	BFTX0409N	3,4	LT15
GNDIS R/L 1616 T 1536	❍	❍	16	15	160	35	11,5	16	1,5	3,6	GXM N150005S GF			
GNDIS R/L 1620 T 1546	❍	❍	16	15	160	40	14,5	20	1,5	4,6	GXM N150005S GF	BFTX0511N	5,0	LT20
GNDIS R/L 2025 T 1566	❍	❍	20	19	180	40	19,0	25	1,5	6,6	GXM N150005S GF			
GNDIS R/L 1214 T 2026	❍	❍	12	11	150	30	9,0	14	2,0	2,6	GXM N2002S-□□			
GNDIS R/L 1214 T 2036	❍	❍	12	11	150	30	10,0	14	2,0	3,6	GXM N2002S-□□	BFTX0409N	3,4	LT15
GNDIS R/L 1616 T 2036	❍	❍	16	15	160	35	11,5	16	2,0	3,6	GXM N2002S-□□			
GNDIS R/L 1620 T 2046	❍	❍	16	15	160	40	14,5	20	2,0	4,6	GXM N2002S-□□	BFTX0511N	5,0	LT20
GNDIS R/L 2025 T 2066	❍	❍	20	19	180	40	19,0	25	2,0	6,6	GXM N2002S-□□			
GNDIS R/L 1214 T 3026	❍	❍	12	11	150	30	9,0	14	3,0	2,6	GXM N3002S-□□			
GNDIS R/L 1214 T 3036	❍	❍	12	11	150	30	10,0	14	3,0	3,6	GXM N3002S-□□	BFTX0409N	3,4	LT15
GNDIS R/L 1616 T 3036	❍	❍	16	15	160	35	11,5	16	3,0	3,6	GXM N3002S-□□			
GNDIS R/L 1620 T 3046	❍	❍	16	15	160	40	14,5	20	3,0	4,6	GXM N3002S-□□	BFTX0511N	5,0	LT20
GNDIS R/L 2025 T 3066	❍	❍	20	19	180	40	19,0	25	3,0	6,6	GXM N3002S-□□			

Select holders and inserts with the same grooving width (CW). Only GXM inserts can be used.

GNDIS Inserts

Application	Shape	Type	Cat. No.	Coated Carbide		Dimensions (mm)				
				AC520U	AC1030U	CW		RE	L	S
						Cutting Width	Tolerance			
Grooving / Turning		**ML**  Low Feed	GXM N2002S ML	❍	❍	2,0	±0,03	0,2	11,1	3,1
			N3002S ML	❍	❍	3,0	±0,03	0,2	11,1	3,1
Grooving		**GF**  Low Cutting Force	GXM N150005S GF		❍	1,5	±0,03	0,05	11,1	3,1
			N2002S GF	❍	❍	2,0	±0,03	0,2	11,1	3,1
			N3002S GF	❍	❍	3,0	±0,03	0,2	11,1	3,1

Select holders and inserts with the same grooving width (CW). GCM and GCG inserts are not compatible.

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

Necking







Above figures show right hand tools.

Spare Parts

Holders

Cat. No.	Stock		Dimensions (mm)							Min. Bore (mm)	Groov. Width (mm)	APMX	APMX2	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	H	B	LF	WF	HF	LH	WF2	DMIN	CW						
GNDN R/L2020 K 215-020	❍	❍	20	20	125	23	20	30	3,0	20	2,0	1,5	0,64	GCM N2010 RN	BX0520	5,0	LH040
GNDN R/L2020 K 320-020	❍	❍	20	20	125	23	20	30	3,0	20	3,0	2,0	0,79	GCM N3015 RN			
GNDN R/L2020 K 430-030	❍	❍	20	20	125	24	20	32	4,0	30	4,0	3,0	1,29	GCM N4020 RN			
GNDN R/L2020 K 535-030	❍	❍	20	20	125	25	20	35	5,0	30	5,0	3,5	1,44	GCM N5025 RN			
GNDN R/L2020 K 640-030	❍	❍	20	20	125	25	20	35	5,0	30	6,0	4,0	1,59	GCM N6030 RN			
GNDN R/L2525 M 215-020	❍	❍	25	25	150	28	25	30	3,0	20	2,0	1,5	0,64	GCM N2010 RN	BX0520	5,0	LH040
GNDN R/L2525 M 320-020	❍	❍	25	25	150	28	25	30	3,0	20	3,0	2,0	0,79	GCM N3015 RN			
GNDN R/L2525 M 430-030	❍	❍	25	25	150	29	25	32	4,0	30	4,0	3,0	1,29	GCM N4020 RN			
GNDN R/L2525 M 535-030	❍	❍	25	25	150	30	25	35	5,0	30	5,0	3,5	1,44	GCM N5025 RN			
GNDN R/L2525 M 640-030	❍	❍	25	25	150	30	25	35	5,0	30	6,0	4,0	1,59	GCM N6030 RN			

Select holders and inserts with the same grooving width (CW).

GNDN Inserts

Application	Shape	Type	Cat. No.	Coated Carbide				Dimensions (mm)				
				AC830P	AC425K	AC520U	AC530U	CW		RE	L	S
								Cutting Width	Tolerance			
Face / Necking		**RN**  General Purpose	GCM N2010 RN	-	-	❍	❍	2,0	±0,03	1,0	21,7	3,6
			N3015 RN	❍	❍	❍	❍	3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍	4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍	5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍	6,0	±0,03	3,0	28,1	4,5

Select holders and inserts with the same grooving width (CW).

GNDF Type

Face Grooving

GNDF
Face Grooving



Face





Work diameters in the stock indicate external diameters of face grooving.

Use for multi-purpose or profiling insert for turning (wide grooves).

Above figures show right hand tools.

Holders

Spare Parts

Cat. No.	Stock		Dimensions (mm)						Work Dia. (mm)	Groov. Width (mm)	Max. Cut-off Dia. (mm)	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	H	B	LF	WF	HF	LH	DC	CW	CDX				
GNDF R/L 2020 K 312-035	●	●	20	20	125	20	20	35,6	35–45	3,0	12	GCM N30○○-□□	BX0520	5,0	LH040
GNDF R/L 2020 K 312-040	●	●	20	20	125	20	20	35,6	40–55	3,0	12				
GNDF R/L 2020 K 318-050	●	●	20	20	125	20	20	41,6	50–70	3,0	18				
GNDF R/L 2020 K 318-065	●	●	20	20	125	20	20	41,6	65–100	3,0	18				
GNDF R/L 2020 K 318-090	●	●	20	20	125	20	20	41,6	90–150	3,0	18				
GNDF R/L 2020 K 318-140	●	●	20	20	125	20	20	41,6	140–200	3,0	18				
GNDF R/L 2020 K 318-180	●	●	20	20	125	20	20	41,6	180–300	3,0	18				
GNDF R/L 2020 K 418-040	●	●	20	20	125	20	20	41,6	40–55	4,0	18	GCM N40○○-□□	BX0520	5,0	LH040
GNDF R/L 2020 K 423-050	●	●	20	20	125	20	20	46,6	50–70	4,0	23				
GNDF R/L 2020 K 423-065	●	●	20	20	125	20	20	46,6	65–90	4,0	23				
GNDF R/L 2020 K 423-085	●	●	20	20	125	20	20	46,6	85–130	4,0	23				
GNDF R/L 2020 K 423-125	●	●	20	20	125	20	20	46,6	125–200	4,0	23				
GNDF R/L 2020 K 423-180	●	●	20	20	125	20	20	46,6	180–300	4,0	23				
GNDF R/L 2020 K 423-280	●	●	20	20	125	20	20	46,6	280–1000	4,0	23				
GNDF R/L 2020 K 523-050	●	●	20	20	125	20	20	46,6	50–70	5,0	23	GCM N50○○-□□	BX0520	5,0	LH040
GNDF R/L 2020 K 523-065	●	●	20	20	125	20	20	46,6	65–90	5,0	23				
GNDF R/L 2020 K 523-085	●	●	20	20	125	20	20	46,6	85–130	5,0	23				
GNDF R/L 2020 K 523-125	●	●	20	20	125	20	20	46,6	125–200	5,0	23				
GNDF R/L 2020 K 523-180	●	●	20	20	125	20	20	46,6	180–300	5,0	23				
GNDF R/L 2020 K 523-280	●	●	20	20	125	20	20	46,6	280–1000	5,0	23				
GNDF R/L 2020 K 623-050	●	●	20	20	125	20	20	46,6	50–75	6,0	23	GCM N60○○-□□	BX0520	5,0	LH040
GNDF R/L 2020 K 623-070	●	●	20	20	125	20	20	46,6	70–110	6,0	23				
GNDF R/L 2020 K 623-100	●	●	20	20	125	20	20	46,6	100–200	6,0	23				
GNDF R/L 2020 K 623-180	●	●	20	20	125	20	20	46,6	180–300	6,0	23				
GNDF R/L 2020 K 623-280	●	●	20	20	125	20	20	46,6	280–1000	6,0	23				
GNDF R/L 2525 M 312-035	●	●	25	25	150	25	25	35,6	35–45	3,0	12	GCM N30○○-□□	BX0520	5,0	LH040
GNDF R/L 2525 M 312-040	●	●	25	25	150	25	25	35,6	40–55	3,0	12				
GNDF R/L 2525 M 318-050	●	●	25	25	150	25	25	41,6	50–70	3,0	18				
GNDF R/L 2525 M 318-065	●	●	25	25	150	25	25	41,6	65–100	3,0	18				
GNDF R/L 2525 M 318-090	●	●	25	25	150	25	25	41,6	90–150	3,0	18				
GNDF R/L 2525 M 318-140	●	●	25	25	150	25	25	41,6	140–200	3,0	18				
GNDF R/L 2525 M 318-180	●	●	25	25	150	25	25	41,6	180–300	3,0	18				
GNDF R/L 2525 M 418-040	●	●	25	25	150	25	25	41,6	40–55	4,0	18	GCM N40○○-□□	BX0520	5,0	LH040
GNDF R/L 2525 M 423-050	●	●	25	25	150	25	25	46,6	50–70	4,0	23				
GNDF R/L 2525 M 423-065	●	●	25	25	150	25	25	46,6	65–90	4,0	23				
GNDF R/L 2525 M 423-085	●	●	25	25	150	25	25	46,6	85–130	4,0	23				
GNDF R/L 2525 M 423-125	●	●	25	25	150	25	25	46,6	125–200	4,0	23				
GNDF R/L 2525 M 423-180	●	●	25	25	150	25	25	46,6	180–300	4,0	23				
GNDF R/L 2525 M 423-280	●	●	25	25	150	25	25	46,6	280–1000	4,0	23				
GNDF R/L 2525 M 523-050	●	●	25	25	150	25	25	46,6	50–70	5,0	23	GCM N50○○-□□	BX0520	5,0	LH040
GNDF R/L 2525 M 523-065	●	●	25	25	150	25	25	46,6	65–90	5,0	23				
GNDF R/L 2525 M 523-085	●	●	25	25	150	25	25	46,6	85–130	5,0	23				
GNDF R/L 2525 M 523-125	●	●	25	25	150	25	25	46,6	125–200	5,0	23				
GNDF R/L 2525 M 523-180	●	●	25	25	150	25	25	46,6	180–300	5,0	23				
GNDF R/L 2525 M 523-280	●	●	25	25	150	25	25	46,6	280–1000	5,0	23				
GNDF R/L 2525 M 623-050	●	●	25	25	150	25	25	46,6	50–75	6,0	23	GCM N60○○-□□	BX0520	5,0	LH040
GNDF R/L 2525 M 623-070	●	●	25	25	150	25	25	46,6	70–110	6,0	23				
GNDF R/L 2525 M 623-100	●	●	25	25	150	25	25	46,6	100–200	6,0	23				
GNDF R/L 2525 M 623-180	●	●	25	25	150	25	25	46,6	180–300	6,0	23				
GNDF R/L 2525 M 623-280	●	●	25	25	150	25	25	46,6	280–1000	6,0	23				

Select holders and inserts with the same grooving width (CW).

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

GNDF Type

■ Inserts for GNDF

Application	Shape	Type	Cat. No.	Coated Carbide				Cermet	Carbide	Dimensions (mm)				
				AC830P	AC425K	AC520U	AC530U	T2500A	H10	CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
		ML  CW=<4mm CW=>5mm Low Feed	GCM N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
Copying / Cut-Off		**GG**  General Purpose	GCM N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
		GL  Low Feed	GCM N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
		GF  Low Cutting Force	GCM N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
Face / Necking		**RN**  General Purpose	GCM N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Select holders and inserts with the same grooving width (CW).

GNDFS Type

Face Grooving L-Styled (Non-Adjustable Type)

GNDFS
Face Grooving



Face

Use the multi-purpose copying inserts for turning (wide grooves).



Above figures show right hand tools.



■ Spare Parts



■ Holders

Cat. No.	Stock		Dimensions (mm)						Work Dia. (mm)	Min. Bore Ø Inner (mm)	Groov. Width (mm)	Max. Groov Depth (mm)	Applicable Insert	Cap Screw	N·m	Spanner
	R	L	H	B	LF	WF	HF	LH	DC		CW	CDX				
GNDFS R/L2525M 620 070			25	25	150	47	25	25	70–100	58	6,0	20	GC□ N60○○-□□	BX0520	5,0	LH040
GNDFS R/L2525M 620 100			25	25	150	47	25	25	100–200	88	6,0	20				
GNDFS R/L2525M 620 180			25	25	150	47	25	25	180–300	168	6,0	20				
GNDFS R/L2525M 620 280			25	25	150	47	25	25	280–1000	268	6,0	20				
GNDFS R/L2525M 620 450			25	25	150	47	25	25	>450	438	6,0	20				
GNDFS R/L3232P 620 070			32	32	170	54	32	25	70–100	58	6,0	20	GC□ N60○○-□□	BX0620	6,0	LH050
GNDFS R/L3232P 620 100			32	32	170	54	32	25	100–200	88	6,0	20				
GNDFS R/L3232P 620 180			32	32	170	54	32	25	180–300	168	6,0	20				
GNDFS R/L3232P 620 280			32	32	170	54	32	25	280–1000	268	6,0	20				
GNDFS R/L3232P 620 450			32	32	170	54	32	25	>450	438	6,0	20				
GNDFS R/L2525M 820 070			25	25	150	47	25	30	70–100	54	8,0	20	GCM N80○○-□□	BX0620	6,0	LH050
GNDFS R/L2525M 820 100			25	25	150	47	25	30	100–200	84	8,0	20				
GNDFS R/L2525M 820 180			25	25	150	47	25	30	180–300	164	8,0	20				
GNDFS R/L2525M 820 280			25	25	150	47	25	30	280–1000	264	8,0	20				
GNDFS R/L2525M 820 450			25	25	150	47	25	30	>450	434	8,0	20				
GNDFS R/L3232P 820 070			32	32	170	54	32	30	70–100	54	8,0	20	GCM N80○○-□□	BX0620	6,0	LH050
GNDFS R/L3232P 820 100			32	32	170	54	32	30	100–200	84	8,0	20				
GNDFS R/L3232P 820 180			32	32	170	54	32	30	180–300	164	8,0	20				
GNDFS R/L3232P 820 280			32	32	170	54	32	30	280–1000	264	8,0	20				
GNDFS R/L3232P 820 450			32	32	170	54	32	30	>450	434	8,0	20				

Select holders and inserts with the same grooving width (CW).

■ Inserts for GNDFS

Application	Shape	Type	Cat. No.	Coated Carbide				Cermet	Carbide	Dimensions (mm)				
				AC830P	AC425K	AC520U	AC530U	T2500A	H10	CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG** General Purpose	GCM N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
			N8008 MG	●	●	❍	●			8,0	±0,04	0,8	28,75	6,0
		ML Low Feed	GCM N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
			N8004 ML	❍	●	❍	●			8,0	±0,04	0,4	28,75	6,0
Copying / Cut-Off		**GG** General Purpose	GCM N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
			N8004 GG	●		❍	●			8,0	±0,04	0,4	28,75	6,0
		GL Low Feed	GCM N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			N8004 GL	❍		❍	●			8,0	±0,04	0,4	28,75	6,0
		GF Low Cutting Force	GCM N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
			N8002 GF	❍		❍	●			8,0	±0,04	0,2	28,75	6,0
			N8004 GF	❍		❍	●			8,0	±0,04	0,4	28,75	6,0
Face / Necking		**RN** General Purpose	GCM N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA** General Purpose	GCG N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Select holders and inserts with the same grooving width (CW).

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

■ Application Examples

20CrMo5, Automotive Part, Face Profiling



Target:
- Higher rigidity
- Vibration reduction
- Chip control
- Wear resistance performance

Holder:	GNDF R2525M 423-125
Insert:	GCM N4020 RG
Grooving width:	4 mm
Cutting conditions:	v_c= 200 m/min f = 0,14 mm/rev wet

Stable machining free of vibration!
Excellent chip control using the GND type.

C53, Cam Shaft Grooving / Finishing (Contin. to Heavy Interrupted)



Target:
- Higher rigidity
- Vibration reduction
- Chip control
- Fracture resistance

Holder:	GNDM L2525M 618
Insert:	GCM N6030 RG
Grooving width:	6 mm
Cutting conditions:	v_c= 130 m/min f = 0,36 mm/rev wet

Stable machining free of vibration!
Excellent fracture resistance
Stable chip control

C48, Machine Part, Cut-Off



Normal Wear **GND** | Chipping / Large Wear Conventional Tool

Target:
- Higher rigidity
- Vibration reduction
- Fracture resistance

Holder:	GNDL R2525M 320
Insert:	GCM N3002 GG
Grooving width:	3 mm
Cutting conditions:	n = 1600 min^{-1} v_c= 200 m/min f = 0,05 mm/rev wet

Stable machining free of vibration!
Excellent fracture resistance
Stable fracture resistance

34CrMo4, Crank, Cut-Off



Target:
- Higher rigidity
- Vibration reduction
- Chip control

Holder:	GNDL R2525M 320
Insert:	GCM N3002 GG
Grooving width:	3 mm
Cutting conditions:	v_c= 115 m/min f = 0,30 mm/rev wet

Improved efficiency
Stable machining free of vibration
Stable chip control

X40CrVMo5-1, (45-48HRC), Machine Part, Cut-Off



Target:
- Higher rigidity
- Vibration reduction
- Chip control

Holder:	GNDL R2525M 425
Insert:	GCM N4002 GG
Grooving width:	4 mm
Cutting conditions:	v_c= 50 m/min f = 0,03 mm/rev wet

Stable machining free of vibration!
Excellent chip control using the GND type.
No more unexpected breakage!

20Cr4, Gear Shaft, Grooving / Pocketing



Target:
- Higher rigidity
- Vibration reduction
- Chip control

Holder:	GNDM R2020K 518
Insert:	GCM N5008 MG
Grooving width:	5 mm
Cutting conditions:	v_c= 150 m/min f = 0,1 mm/rev wet

Stable machining free of vibration!
Excellent chip control using the GND type.

GND Grooving System





General Features

New grades and chipbreakers have been added to the already established GND grooving system with polygon shank and a flexible and economical cassette system for inserts. An array of chipbreakers improves the efficiency in chip control in various applications such as grooving, turning, profiling and cut-off.

Advantages

- GND inserts for soft grooving from 2,0 - 6,0 mm width
- Expanded grade selection with 9 different chipbreakers for a wide application range
- Provides excellent chip control
- Achieves stable long tool life

Cassette

Cat. No.	R	L	CW (mm)	CDX (mm)	Inserts	Cap Screw	Tightening Torque (N·m)	Spanner
GNDCM R/L 212	●	●	2	12	GCM □20○○-□□	BX0512	5,0	LH040
GNDCM R/L 312	●	●	3		GCM □30○○-□□			
GNDCM R/L 418	●	●	4	18	GCM □40○○-□□		6,0	
GNDCM R/L 518	●	●	5		GCM □50○○-□□			
GNDCM R/L 618	●	●	6		GCM □60○○-□□			

Holder

PSC__GM**00**
(straight)



PSC__GM**90**
(L-style)



Note:
The **right** handed PSC40/50GM90R holder needs a **left** cassette.
The **left** handed PSC40/50GM90L holder needs a **right** cassette.

Style	Cat. No.	R	L	DCSFMS (mm)	WF (mm)	LF (mm)	Cap Screw	Tightening Torque (N·m)	Spanner
Straight	PSC40GM00 R/L	●	●	40	22	**80***	BFTX0619N	7,5	LT25
	PSC50GM00 R/L	●	●	50	27				
L-Style	PSC40GM90 R/L	●	●	40	**42***	52,5			
	PSC50GM90 R/L	●	●	50	**47***	55,0			

* Dimension when using radial grooving cassettes.

Identification Details - Polygon-Toolholder

PSC	**40**	-	**G**	**M**	**00**	**R**
Polygonshank	Shank Diameter (DCSFMS)		Series Symbol GND	Application External Multi-Purpose	Style 00 = Straight 90 = L-Style	Holder Design R = Right L = Left

Identification Details - Cassette

GND	**C**	**M**	**L**	**3**	**12**
Series Symbol GND	Cassette	Application External Multi-Purpose	Holder Design R = Right L = Left	Grooving Width	Max. Grooving Depth

● = Euro stock
○ = Japan stock

Recommended Tightening Torque (N·m)

Inserts

Application	Shape	Type	Cross section of cutting edge	Cat. No.	Coated Carbide AC830P	AC425K	AC520U	AC530U	Cermet T2500A	Carbide H10	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose		GCM N3004 MG	●	●		●			3,0	±0,03	0,4	21,1	3,8
				N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
				N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
				N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
		ML  Low Feed		GCM N2002 ML			❍	●			2,0	±0,03	0,2	21,1	3,6
				N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
				N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
				N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
				N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
Copying / Cut-Off		**GG**  General Purpose		GCM N2002 GG	●		●	●			2,0	±0,03	0,2	21,1	3,6
				N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
				N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
				N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
				N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
				GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
				N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
				N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
				N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
		GL  Low Feed		GCM N2002 GL	●		❍	●			2,0	±0,03	0,2	21,1	3,6
				N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
				N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
				N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
				N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
		GF  Low Cutting Force		N2002 GF				●	❍		2,0	±0,03	0,2	21,1	3,6
				N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
				N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
				N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
				N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
Copying		**RG**  General Purpose		GCM N3015 RG	●	●	❍	●	❍		3,0	±0,03	1,5	21,1	3,8
				N4020 RG	❍	●	❍	●	❍		4,0	±0,03	2,0	26,4	4,0
				N5025 RG	●	●	❍	●			5,0	±0,03	2,5	27,2	4,1
				N6030 RG	❍	●	❍	●			6,0	±0,03	3,0	27,5	4,5
Face / Necking		**RN**  General Purpose		GCM N2010 RN			❍	❍			2,0	±0,03	1,0	21,7	3,6
				N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
				N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
				N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
				N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose		GCG N2002 GA						❍	2,0	±0,025	0,2	21,1	3,6
				N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
				N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
				N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
				N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Select holders and inserts with the same grooving width (CW).

Application	Shape	Type	Cross section of cutting edge	Cat. No. R / L	Coated Carbide AC830P R	AC830P L	AC520U R	AC520U L	AC530U R	AC530U L	AC1030U R	AC1030U L	Cermet R	Cermet L	PSI	Dimensions (mm) CW Cutting Width	CW Tolerance	RE	L	S
Cut-Off	Figures show right hand tools. 	**CG**  General Purpose		GCM□2002 CG 05	❍	❍	❍	❍	●	●					5°	2,0	±0,03	0,2	21,1	3,6
				□3002 CG 05	●	❍	❍	❍	●	●					5°	3,0	±0,03	0,2	21,3	3,8
				□4002 CG 05	❍	❍	❍	❍	●	●					5°	4,0	±0,03	0,2	26,7	4,0
Cut-Off		**CF** New  Low Cutting Force		GCM□20003 CF 10							●	●			10°	2,0	±0,08	0,03	22,4	3,6
				□30003 CF 10							●	●			10°	3,0	±0,08	0,03	22,4	3,8
				□20003 CF 15							●	●			15°	2,0	±0,08	0,03	22,4	3,6
				□30003 CF 15							●	●			15°	3,0	±0,08	0,03	22,4	3,8

GND Grooving System

New

GNDCF
Face Grooving



Face





DC Work Diameter (mm)



Above figures show right hand tools.



Work diameters in the stock indicate external diameters of face grooving.

Cassette

Cat. No.	R	L	CW (mm)	Diameter Range (mm)	DC (mm)	CDX (mm)	Inserts	Cap Screw	Tightening Torque (N·m)	Spanner
GNDCF R/L 312-040	●	●	3	40–200	40–55	12	GC□ N30○○-□□	BX0512	5,0	LH040
GNDCF R/L 315-050	●	●			50–70	15				
GNDCF R/L 315-065	●	●			65–100	15				
GNDCF R/L 318-090	●	●			90–150	18				
GNDCF R/L 318-140	❑	❑			140–200	18				
GNDCF R/L 418-040	●	●	4	40–300	40–55	18	GC□ N40○○-□□		6,0	
GNDCF R/L 418-050	●	●			50–70	18				
GNDCF R/L 418-065	●	●			65–90	18				
GNDCF R/L 418-085	●	●			85–130	18				
GNDCF R/L 418-125	❑	❑			125–200	18				
GNDCF R/L 418-180	❑	❑			180–300	18				
GNDCF R/L 518-050	❑	❑	5	50–300	50–70	18	GC□ N50○○-□□			
GNDCF R/L 518-065	❑	❑			65–90	18				
GNDCF R/L 518-085	❑	❑			85–130	18				
GNDCF R/L 518-125	❑	❑			125–200	18				
GNDCF R/L 518-180	❑	❑			180–300	18				
GNDCF R/L 618-050	❑	❑	6	50–1000	50–75	18	GC□ N60○○-□□			
GNDCF R/L 618-070	❑	❑			70–110	18				
GNDCF R/L 618-100	❑	❑			100–200	18				
GNDCF R/L 618-180	❑	❑			180–300	18				
GNDCF R/L 618-280	❑	❑			280–1000	18				

Holder

PSC__GM**00**
(straight)



PSC__GM**90**
(L-style)



Note:
The **right** handed PSC40/50GM90R holder needs a **left** cassette.
The **left** handed PSC40/50GM90L holder needs a **right** cassette.

Style	Cat. No.	R	L	DCSFMS (mm)	WF (mm)	LF (mm)	Cap Screw	Tightening Torque (N·m)	Spanner
Straight	PSC40GM00 R/L	●	●	40	22	**81***	BFTX0619N	7,5	LT25
	PSC50GM00 R/L	●	●	50	27				
L-Style	PSC40GM90 R/L	●	●	40	**43***	52,5			
	PSC50GM90 R/L	●	●	50	**48***	55,0			

* Dimension when using face grooving cassettes.

Identification Details - Polygon-Toolholder

PSC	40	-	G	M	00	R
Polygonshank	Shank Diameter (DCSFMS)		Series Symbol GND	Application External Multi-Purpose	Style 00 = Straight 90 = L-Style	Holder Design R = Right L = Left

Identification Details - Cassette

GND	C	F	L	3	12
Series Symbol GND	Cassette	Application Face Grooving	Holder Design R = Right L = Left	Grooving Width	Max. Grooving Depth

● = Euro stock
○ = Japan stock
❑ = Delivery on request
Recommended Tightening Torque (N·m)

■ Inserts

Application	Shape	Type	Cat. No.	Coated Carbide				Cermet	Carbide	Dimensions (mm)				
				AC830P	AC425K	AC520U	AC530U	T2500A	H10	CW Cutting Width	CW Tolerance	RE	L	S
Grooving / Turning		**MG**  General Purpose	GCM N3004 MG	●	●	❍	●			3,0	±0,03	0,4	21,1	3,8
			N4008 MG	●	●	❍	●			4,0	±0,03	0,8	26,4	4,0
			N5008 MG	●	●	❍	●			5,0	±0,03	0,8	26,4	4,1
			N6008 MG	●	●	❍	●			6,0	±0,03	0,8	26,4	4,5
		ML  CW=<4mm CW=>5mm Low Feed	GCM N3002 ML	●	●	❍	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4004 ML	●	●	❍	●	❍		4,0	±0,03	0,4	26,4	4,0
			N5004 ML	●	●	❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 ML	●	●	❍	●			6,0	±0,03	0,4	26,4	4,5
Copying / Cut-Off		**GG**  General Purpose	GCM N3002 GG	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GG	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GG	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GG	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
			GCM N3004 GG	●		❍	●			3,0	±0,03	0,4	21,1	3,8
			N4004 GG	●		❍	●			4,0	±0,03	0,4	26,4	4,0
			N5004 GG	❍		❍	●			5,0	±0,03	0,4	26,4	4,1
			N6004 GG	❍		❍	●			6,0	±0,03	0,4	26,4	4,5
		GL  Low Feed	GCM N3002 GL	●		❍	●			3,0	±0,03	0,2	21,1	3,8
			N4002 GL	●		❍	●			4,0	±0,03	0,2	26,4	4,0
			N5002 GL	❍		❍	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GL	❍		❍	●			6,0	±0,03	0,2	26,4	4,5
		GF  Low Cutting Force	GCM N3002 GF	●		●	●	❍		3,0	±0,03	0,2	21,1	3,8
			N4002 GF	●		●	●	❍		4,0	±0,03	0,2	26,4	4,0
			N5002 GF	❍		●	●			5,0	±0,03	0,2	26,4	4,1
			N6002 GF	❍		●	●			6,0	±0,03	0,2	26,4	4,5
Face / Necking		**RN**  General Purpose	GCM N3015 RN	❍	❍	❍	❍			3,0	±0,03	1,5	22,4	3,8
			N4020 RN	❍	❍	❍	❍			4,0	±0,03	2,0	28,0	4,0
			N5025 RN	❍	❍	❍	❍			5,0	±0,03	2,5	28,1	4,1
			N6030 RN	❍	❍	❍	❍			6,0	±0,03	3,0	28,1	4,5
Non Ferrous Metals		**GA**  General Purpose	GCG N3002 GA						❍	3,0	±0,025	0,2	21,1	3,8
			N4004 GA						❍	4,0	±0,025	0,4	26,4	4,0
			N5004 GA						❍	5,0	±0,025	0,4	26,4	4,1
			N6004 GA						❍	6,0	±0,025	0,4	26,4	4,5

Select holders and inserts with the same grooving width (CW).

TGA-BF Type

Characteristics

- Outstanding chip control when grooving
- Excellent chip control when finishing wide grooves using axial feed
- Grooving inserts from 1,5–4,5 mm wide
- Grade AC530U with Super ZX ultra hard coating for steels, stainless steels and cast iron increases productivity and extends tool life

External Grooving

Figures show right hand tools.

GWC
External Grooving



Fig. 1



Fig. 2



Fig. 3



The rake angle R varies depending on the insert grade. For details, see the table at the lower part of page F39.

Holders

Right handed tool holders are applicable with **left** handed inserts (TGA-L).

Cat. No.	Stock		Dimensions (mm)					Fig.	Grooving Width	Maximum Grooving Depth (mm)	Applicable Insert Group No.	Spare Parts					
	R	L	H	B	LF	WF	HF		CW (mm)			Screw	(N·m)	Wrench	Clamp	Screw	Wrench
GWC R/L 1010-3	❍	❍	10	10	125	10	10	2	0,33–2,80	0,8–2,5	❶	BFTX 0409N	3,4	TRX15	–	–	–
GWC R/L 1212-3	❍	❍	12	12	125	12	12	2	0,33–2,80	0,8–2,5	❶						
GWC R/L 1616-3	●	❍	16	16	125	16	16	3	0,33–2,80	0,8–2,5	❶						
GWC R/L 2020-3	❍	❍	20	20	125	25	20	1	0,33–2,80	0,8–2,5	❶	BFTX 0409N	3,4	TRX15	CCM 6B -L/R	WB 6-20 -T/TL	LT20
GWC R/L 2525-3	❍	●	25	20	150	30	25	1	0,33–2,80	0,8–2,5	❶						
GWC R/L 2020-15	●	●	20	20	125	25	20	1	1,25–1,45	2,0	❷	BFTX 0511N	5,0	TRX20	CCM 8U -L/R	WB 8-22 -T/TL	LT27
GWC R/L 2020-25	●	●	20	20	125	25	20	1	1,50–2,30	3,5	❸						
GWC R/L 2020-35	●	●	20	20	125	25	20	1	2,50–4,80	5,0	❹						
GWC R/L 2525-15	●	●	25	25	150	30	25	1	1,25–1,45	2,0	❷						
GWC R/L 2525-25	●	●	25	25	150	30	25	1	1,50–2,30	3,5	❸						
GWC R/L 2525-35	●	●	25	25	150	30	25	1	2,50–4,80	5,0	❹						

Spare Parts



GWCS
External Grooving





The rake angle R varies depending on the insert grade. For details, see the table at the lower part of page F39.

Figures show right hand tools.

Holders

Right handed tool holders are applicable with **left** handed inserts (TGA-L).

Cat. No.	Stock		Dimensions (mm)					Grooving Width	Maximum Grooving Depth (mm)	Applicable Insert Group No.	Spare Parts					
	R	L	H	B	LF	WF	HF	CW (mm)			Screw	(N·m)	Wrench	Clamp	Screw	Wrench
GWCS R/L 2020-3			20	20	125	25	20	0,33–2,80	0,8–2,5	❶	BFTX 0409N	3,4	TRX15	CCM 6B -L/R	WB 6-20 -T/TL	LT20
GWCS R/L 2525-3			25	25	150	30	25	0,33–2,80	0,8–2,5	❶						
GWCS R/L 2020-15	❍	❍	20	20	125	27	20	1,25–1,45	2,0	❷	BFTX 0511N	5,0	TRX20	CCM 8U -L/R	WB 8-22 -T/TL	LT27
GWCS R/L 2020-25	❍	❍	20	20	125	27	20	1,50–2,30	3,5	❸						
GWCS R/L 2020-35	❍	❍	20	20	125	27	20	2,50–4,80	5,0	❹						
GWCS R/L 2525-15	❍	❍	25	25	150	32	25	1,25–1,45	2,0	❷						
GWCS R/L 2525-25		❍	25	25	150	32	25	1,50–2,30	3,5	❸						
GWCS R/L 2525-35	❍	❍	25	25	150	32	25	2,50–4,80	5,0	❹						

● = Euro stock
○ = Japan stock
❑ = Delivery on request
(N·m) Recommended Tightening Torque (N·m)

ISO-PSC Polygon Modular

PSC

Holder

Cat. No.	R	L	Ø (mm)	F (mm)	L (mm)	Cap Screw	(N·m)	Spanner
PSC 40 GM00 R/L	●	●	40	22	80,0	BFTX0619N	7,5	LT25
PSC 50 GM00 R/L	●	●	50	27	80,0			
PSC 40 GM90 R/L	●	●	40	42	52,5			
PSC 50 GM90 R/L	●	●	50	47	55,0			

Cassette

Cat. No.	R	L	Grooving Width (mm)	Grooving Depth (mm)	Insert	Insert Screw	Spanner	Spring	Clamp Finger	Cap Screw	(N·m)	Spanner
GWCCM R/L 25	●	●	1,5–2,3	3,9	TGA□4□□□BF	BFTX0511N	TRX20	SCP4A			3,0	LH030
GWCCM R/L 35	●	●	2,5–4,5	5,4	TGA□4□□□BF	**5,0** (N·m)						

Internal Grooving

GWCI
Internal Grooving





The rake angle R varies depending on the insert grade. For details, see the table at the lower part of page F39.

Figures show right hand tools.

Spare Parts


Holders

Right handed tool holders are applicable with **left** handed inserts (TGA-L).

Cat. No.	Stock R	Stock L	Dimensions (mm) DMIN	DCON	LF	H	HF	WF	Grooving width CW (mm)	Maximum Grooving Depth (mm)	Applicable Insert Group No.	Screw	(N·m)	Wrench
GWCI R/L 325	❑	❑	35	25	100	23	11,5	17,5	0,33–2,80	0,8–2,0	❶	BFTX0409N	3,4	TRX 15
GWCI R/L 432	❑	❑	40	32	250	30	15,0	17,5	1,25–4,80	2,0–2,5	❷❸❹	BFTX0511N	5,0	TRX 20

Inserts

Fig. 1



Fig. 2



Notice:
Please note the cutting edge position E2, for grooving widths below 1,85 mm..

(Note 2) Figures show right hand tools.

Cat. No.	Coated AC530U R	Coated AC530U L	Dimensions (mm) ( ) CDX: presents max. depth CW	CDX	RE	E2	Fig.	Applicable holder & insert group
TGA R/L 4140BF01	❍	❍	1,40	2,5 (2,0-1,7)	0,1	0,300	2	❷
TGA R/L 4150BF	●	●	1,50	3,9 External (3,5) Internal (2,5)	0,2	0,250	2	❸
TGA R/L 4165BF	❍	❍	1,65			0,175		
TGA R/L 4175BF	❍	❍	1,75			0,125		
TGA R/L 4185BF	❍	❍	1,85			0,075		
TGA R/L 4200BF	●	●	2,00			0	1	
TGA R/L 4220BF	❍	❍	2,20					
TGA R/L 4230BF	❍	❍	2,30					
TGA R/L 4250BF	●	●	2,50	5,4 External (5,0) Internal (2,5)	0,3	0	1	❹
TGA R/L 4265BF	❍	❍	2,65					
TGA R/L 4270BF	❍	❍	2,70					
TGA R/L 4280BF	❍	❍	2,80					
TGA R/L 4300BF	●	●	3,00					
TGA R/L 4320BF	❍	❍	3,20					
TGA R/L 4330BF	❍	❍	3,30					
TGA R/L 4350BF	●	●	3,50					
TGA R/L 4370BF	❍	❍	3,70					
TGA R/L 4390BF	❍	❍	3,90					
TGA R/L 4400BF	●	●	4,00		0,4			
TGA R/L 4410BF	❍	❍	4,10					
TGA R/L 4420BF		❍	4,20					
TGA R/L 4430BF	❍	❍	4,30					
TGA R/L 4440BF	❍	❍	4,40					
TGA R/L 4450BF	●	●	4,50					

*) Please select applicable inserts for the holders by using matching group numbers.

Recommended Cutting Conditions

Grooving

Feed direction



Wet condition is recommended.

Work Material		General Steel		Stainless Steel	
Cutting speed (m/min)		50–180		50–160	
Groove width (mm)		1,5–2,3	2,5–3,3	3,5–4,5	
Feed rate (mm/rev)		0,03–0,12	0,04–0,12	0,05–0,12	
Depth of cut (mm)	Ext.	–3,5	–5,0	–5,0	
	Int.	–2,5			

Axial Feed

Feed direction for axial feed



Wet condition is recommended.

Work Material	General Steel		Stainless Steel
Cutting speed (m/min)	50–180		50–160
Feed rate (mm/rev)	0,03–0,10	0,05–0,10	0,07–0,12
Depth of cut (mm)	–0,3	–0,5	–0,7

Rake Angle with a Holder Fitted (E)

Grooving	AC530U	H1	T3000Z	T1500A	BN2000	DA2200
External GMC, GWCS	10°	20°	10°	5°	0°	10°
Internal GMCI	1°	11°	1°	–4°	–9°	1°

TGA Type

■ Inserts



This figure shows right handed tools.

Grade		Cutting Edge	GAN
Coated Carbide	AC530U	Honing	15°
Carbide	H1	Sharp	25°
Coated Cermet	T3000Z	Honing	15°
Cermet	T1500A	Sharp	10°
SUMIBORON	BN2000	K-Land	5°
SUMIDIA	DA2200	Sharp	15°

* See page F39 for the rake angle with a holder fitted.

Dimensions (mm)

Cat. No. (The part numbers of T1500A end with E)	AC530U		H1		T3000Z		T1500A		BN2000		DA2200		CW	Max. Groove Depth		CDX	RE	IC	S	Insert /Holder Group No.*
	R	L	R	L	R	L	R	L	R	L	R	L		External	Internal					
TGA R/L 3033 (E)	○		○						–	–	–	–	0,33	0,8	0,5	1,0	0,05	9,525	3,18	❶
TGA R/L 3050 (E)	○	○			○				–	–	–	–	0,50	1,2	0,8	1,4				
TGA R/L 3075 (E)	○	○	○										0,75	2,0	1,5	2,5	0,1 (T1500A 0,2)			
R/L 3095 (E)	○	○											0,95							
R/L 3100 (E)	○	○	○		○	○	○	○					1,00							
R/L 3110 (E)	○	○											1,10							
R/L 3125 (E)	○	○	○		○								1,25							
R/L 3135 (E)	○				○		○						1,35							
R/L 3145 (E)	○	○											1,45							
R/L 3150 (E)	○	○	○										1,50							
R/L 3165 (E)	○												1,65							
R/L 3175 (E)	○	○			○								1,75							
R/L 3185 (E)	○												1,85							
TGA R/L 3200 (E)	○	○	○		○		○						2,00	2,5	2,0	3,0				
R/L 3220 (E)		○											2,20							
R/L 3230 (E)													2,30							
R/L 3250 (E)	○		○										2,50							
R/L 3265 (E)													2,65							
R/L 3270 (E)													2,70							
R/L 3280 (E)	○												2,80							
TGA R/L 4125 (E)	○	○									○		1,25	2,0	1,7	2,5	0,2 *2	12,70	4,76	❷
R/L 4145 (E)	○	○											1,45							
TGA R/L 4150 (E)		○	○	○							❑		1,50	3,5	2,5	3,9				❸
R/L 4165 (E)													1,65							
R/L 4175 (E)													1,75							
R/L 4185 (E)		○	○	○									1,85							
R/L 4200 (E)	○	○							○		○		2,00							
R/L 4220 (E)		○											2,20							
R/L 4230 (E)	○	○											2,30							
TGA R/L 4250 (E)	○		○				○		○				2,50	5,0 *1	2,5	5,4 *1	0,3 *2			❹
R/L 4265 (E)	○		○										2,65							
R/L 4270 (E)													2,70							
R/L 4280 (E)	○												2,80							
R/L 4300 (E)	○	○	○				○				○		3,00							
R/L 4320 (E)													3,20							
R/L 4330 (E)	○												3,30							
TGA R/L 4350 (E)	○												3,50	5,0	2,5	5,4	0,4 *2		5,00	
R/L 4370 (E)													3,70							
R/L 4390 (E)													3,90							
R/L 4400 (E)	○								○				4,00							
R/L 4410 (E)													4,10							
R/L 4420 (E)													4,20							
R/L 4430 (E)													4,30							
R/L 4440 (E)													4,40							
R/L 4450 (E)			○										4,50							
R/L 4480 (E)													4,80							

* See the group numbers of GWC, GWCS and GWCI types on page F38 and F39 to find applicable holders. Inserts and holders that have corresponding group numbers can be used together.

*1: CDX for SUMIBORON and SUMIDIA = 4,4, maximum groove depth 4,0 (2,5 during internal machining)
*2: RE for SUMIBORON = 0,2, RE for SUMIDIA = 0,1

○ = Japan stock ❑ = Delivery on request

TGA Type

Inserts



This figure shows right handed tools.

Grade		Cutting Edge	GAN
Coated Carbide	AC530U	Honing	15°
Carbide	H1	Sharp	25°
Coated Cermet	T3000Z	Honing	15°
Cermet	T1500A	Sharp	10°
SUMIBORON	BN2000	K-Land	5°
SUMIDIA	DA2200	Sharp	15°

* See page F39 for the rake angle with a holder fitted.

Dimensions (mm)

Cat. No.	AC530U		H1		T3000Z		T1500A		BN2000		DA2200		CW	Max. Groove Depth		CDX	RE	IC	S	Insert /Holder Group No.*
	R	L	R	L	R	L	R	L	R	L	R	L		External	Internal					
TGA R/L 4050 R	❍	❍											1,00	2,0	1,7	2,5	0,50	12,70	4,76	❷
TGA R/L 4075 R	❍	❍											1,50	3,5	2,5	3,9	0,75			❸
R/L 4100 R	❍	❍											2,00				1,00			
TGA R/L 4125 R	❍	❍											2,50	5,0 *1	2,5	5,4 *1	1,25			❹
R/L 4150 R	❍				❍						❑		3,00				1,50			
R/L 4200 R	❍												4,00				2,00			

* See the group numbers of GWC, GWCS and GWCI types on page F38 and F39 to find applicable holders. Inserts and holders that have corresponding group numbers can be used together.

*1 CDX for SUMIBORON and SUMIDIA = 4,4, maximum groove depth 4,0 (2,5 during internal machining)

Recommended Cutting Conditions

Work Material	P General Steel			M Stainless Steel			N Non-Ferrous Metal		H Hardened Steel
Grade	AC530U	T3000Z	T1500A	AC530U	T3000Z	T1500A	H1	DA2200	BN2000
Cutting Speed (m/min)	50–200	100–180	100–180	50–200	80–150	80–120	200–300	200–300	80–120
Feed Rate (mm/rev)	0,02–0,10	0,05–0,10	0,05–0,08	0,02–0,10	0,05–0,08	0,05–0,08	0,05–0,15	0,05–0,15	0,03–0,07

Insert Blanks

(Incomplete products. Machine them to meet your edge width, nose radius and rake angle requirements.)

Fig. 1



Fig. 2



This figure shows right handed tools.

Dimensions (mm)

Cat. No.	KH03		H1		EH510		T1500A		CW	CDX	IC	S	Fig.
	R	L	R	L	R	L	R	L					
TGA R/L 3 T18									1,85	(3,4)	9,525	3,18	1
R/L 3 T23							❍	❍	2,35	(3,4)			
R/L 3 T31	❍								3,18	–			2
TGA R/L 4 T22									2,20	(4,8)	12,70	4,76	1
R/L 4 T37									3,75	(6,2)			
R/L 4 T47	❍						❍		4,76	–			2

Note: CDX values in parentheses are for reference only.

Notes for Machining an Insert

Make the cutting edge so that the rake angle, back taper, etc. as shown in fig. 3. When you have installed an insert into a holder, it becomes a cutting blade element as shown in fig. 4.

Suggested Shape

Fig. 3



Cutting blade element during holder installation

Fig. 4



SCT Type



Fig. 1



Fig. 2



Above figures show right hand tools.

Spare Parts

Holders

Cat. No.	Stock	Dimensions (mm) H	B	LF	WF	HF	LH	Applicable inserts	Fig.	Screw	Wrench
SCT R 1010	●	10	10	120	10	10	15	CT R05_ _ _ CT R12_ _ _	1	BFTX0410T8L	TRX 08
SCT R 1212	●	12	12	120	12	12	15				
SCT R 1616	●	16	16	120	16	16	15				
SCT R 101016	❍	10	10	120	10	10	18	CT R16_ _ _	2		
SCT R 121216	❍	12	12	120	12	12	18				
SCT R 161616	❍	16	16	120	16	16	18		1		
SCT L 1010	●	10	10	120	10	10	15	CT L05 _ _ _ CT L12 _ _ _	1	BFTX0410T8R	
SCT L 1212	●	12	12	120	12	12	15				
SCT L 1616	●	16	16	120	16	16	15				
SCT L 101016	❍	10	10	120	10	10	18	CT L16 _ _ _	2		
SCT L 121216	❍	12	12	120	12	12	18				
SCT L 161616	❍	16	16	120	16	16	18		1		

Inserts

	For Right Handed Holder (SCTR)			For Left Handed Holder (SCTL)		
	CTR _ _ R	CTR _ _ N	CTR _ _ L	CTL _ _ R	CTL _ _ N	CTL _ _ L
Installation Conditions for Holder						
Insert Shape and Dimensions						

Cat. No.	AC1030U R	N	L	AC530U R	N	L	Max. Cut-Off Ø (mm)	CW	RE	L	S	Chip Breaker	Applicable Holder
CTR 050505 R/N/L	❍	❍	❍	❍	❍	❍	5	0,5	0,05	19	7	With Chip Breaker	SCT R1010 SCT R1212 SCT R1616
050500 R/N/L	❍	❍		❍	❍		5		0				
CTR 121005 R/N/L	❍	❍	❍	❍	❍	❍	12	1,0					
121505 R/N/L	●	●	❍	❍	❍	❍	12	1,5	0,05				
122005 R/N/L	●	●		❍	❍		12	2,0					
121000 R/N/L	❍	❍		❍	❍		12	1,0					
121500 R/N/L	❍	❍		❍	❍		12	1,5	0				
122000 R/N/L	❍	❍		❍	❍		12	2,0					
CTR 161005 R/N/L							16	1,0		23,1	8,3		SCT R101016 SCT R121216 SCT R161616
161505 R/N/L	❍	❍		❍	❍		16	1,5	0,05				
162005 R/N/L	❍	❍	❍		❍	❍	16	2,0					
161000 R/N/L							16	1,0					
161500 R/N/L	❍	❍		❍	❍		16	1,5	0				
162000 R/N/L	❍	❍	❍	❍	❍	❍	16	2,0					
CTR 050500 R/N/L NB							5	0,5	0	19	7	Without Chip Breaker	SCT R1010 SCT R1212 SCT R1616
CTR 121000 R/N/L NB	❍			❍			12	1,0					
121500 R/N/L NB	❍			❍			12	1,5					
122000 R/N/L NB	❍			❍			12	2,0					
CTR 161000 R/N/L NB							16	1,0		23,1	8,3		SCT R101016 SCT R121216 SCT R161616
161500 R/N/L NB							16	1,5					
162000 R/N/L NB	❍			❍			16	2,0					

CTL 050505 R/N/L	❍	❍		❍	❍		5	0,5	0,05	19	7	With Chip Breaker	SCT R1010 SCT R1212 SCT R1616
050500 R/N/L	❍	❍		❍	❍		5		0				
CTL 121005 R/N/L	❍	❍	●	❍	❍	❍	12	1,0					
121505 R/N/L	❍	❍	●	❍	❍	❍	12	1,5	0,05				
122005 R/N/L	❍	●		❍	❍		12	2,0					
121000 R/N/L	❍	❍		❍	❍		12	1,0					
121500 R/N/L	❍	❍		❍	❍		12	1,5	0				
122000 R/N/L	❍	❍		❍	❍		12	2,0					
CTL 161005 R/N/L							16	1,0		23,1	8,3		SCT R101016 SCT R121216 SCT R161616
161505 R/N/L	❍	❍			❍		16	1,5	0,05				
162005 R/N/L	❍	❍	❍	❍	❍	❍	16	2,0					
161000 R/N/L							16	1,0					
161500 R/N/L	❍	❍		❍	❍		16	1,5	0				
162000 R/N/L	❍	❍		❍	❍		16	2,0					



Wide groove breaker for smooth chip evacuation

Surface Finish Comparison

Work Material:	X6Cr17 (ø8 mm)
Insert:	CTR 121005 R, (b =1,0 mm)
Cutting Data:	v_c = 45 m/min
	f = 0,02 mm/rev, Wet

● = Euro stock
○ = Japan stock

Characteristics

- Holders available in carbide (SumiGrip) and steel (SumiGrip JR).
- Capable on interrupted machining.
- Can be used for cut-off, grooving and chamfering applications.

Type

- Tool block type
  STFH (steel) / WCFH (carbide)
- Shank type
  STFS (steel) / WCFS (carbide)

Cut-Off



Features of Design



Twice the Insert Holding Force



Low Vibration



Work Material: C45 (Ø 50 mm, 250 HB)
Insert: 3 mm width, coated carbide
Cutting Conditions: v_c = 80 m/min, dry

Wear Resistance



Work Material: C45 (hexagonal)
Insert: 3 mm width, coated carbide
Cutting Conditions: v_c = 150 m/min, f = 0,15 mm/rev, wet (water soluble)

GG Type/GF Type/CF Type Chipbreaker, Grade AC1030U

Utilizing grooving tool GND type chipbreaker series for excellent chip control.
Low cutting force chipbreaker GF type (neutral) or CF type (left or right handed) inserts, coupled with a carbide blade, enables stable machining and prevents chattering even when machining stainless steel.
Achieving stable and longer tool life with the new AC1030U grade.

GG	GF	CF
 Neutral	 Neutral	 L/R handed
General purpose	Exotic alloy, Low cutting force	Exotic alloy, Low cutting force

Performance (Chipbreaker)

Chip Control Capability


GF


GG


Conventional

Work Material: X5CrMo17 12 2 (Ø 40 mm)
Cutting Conditions: v_c = 100 m/min, f = 0,1 mm/rev, wet

Sumi-Grip Jr.

Cut-Off (Steel Holder/Tool Block Type)

STFH
Cut-Off





Above figures show right hand tools.

Holders

Cat. No.	Stock	Dimensions (mm) H	B	LF	HF	LF2	CW	Max. Cut-Off Dia.	Applicable Inserts	Applicable Tool Blocks	Wrench
STFH 26-2	●	26	1,6	109	21,4	108	2,0	40	WCF _ 2 _		
26-3	●	26	2,4	109	21,4	108	3,0	70	WCF _ 3 _	SBN 20-26	
26-4	●	26	3,4	109	21,4	108	4,0	70	WCF _ 4 _	SBU 20-26	
26-5	●	26	4,3	109	21,4	108	5,0	70	WCF _ 5 _		
STFH 32-2	●	32	1,6	149	25,0	148	2,0	40	WCF _ 2 _	SBN 20-32	SL 4
32-3	●	32	2,4	149	25,0	148	3,0	100	WCF _ 3 _	SBN 25-32	
32-4	●	32	3,4	149	25,0	148	4,0	100	WCF _ 4 _	SBU 20-32	
32-5	●	32	4,3	149	25,0	148	5,0	100	WCF _ 5 _	SBU 25-32	

Parts

Tool Blocks

SBN Type, One piece type



Cat. No.	Stock	Dimensions (mm) H	Ha	Hb	Hc	L	Applicable Carbide Blades
SBN 20-26	●	45	20	20	10,0	80	STFH 26_
SBN 20-32	●	50	20	20	13,5	100	STFH 32_
SBN 25-26	❑	48	25	25	10,0	80	STFH 26_
SBN 25-32	●	50	25	25	8,5	110	STFH 32_

Parts

Clamp	Screw	Wrench
		
BWS 30	WB 8-20	LH 040

SBU Type, Separate type



Cat. No.	Stock	Dimensions (mm) H	Ha	Hb	Hc	L	Applicable Carbide Blades
SBU 20-26	●	45	20	20	10,0	80	STFH 26_
SBU 20-32	●	50	20	20	13,5	100	STFH 32_
SBU 25-26	❑	48	25	25	10,0	80	STFH 26_
SBU 25-32	●	50	25	25	8,5	110	STFH 32_

Wedge		
		
BCS 15	BCS 20	BCS 25
Screw	**Wrench**	
		
BX 0622	LH 050	

*Tool blocks selection guide see page F46

Cut-Off (Steel Holder/Shank Type)

STFS
Cut-Off





Parts

Holders

Cat. No.	Stock R	Stock L	Dimensions (mm) H	B	LF	WF	HF	LH	LH2	CW	Max. Cut-Off Dia.	Applicable Inserts	Wrench
STFS R/L 1010-2	❍		10	10	86	10	10	17	17	2,0	28		
R/L 1212-2	●	●	12	12	110	12	12	18	18	2,0	30	WCF _ 2 _	
R/L 1616-2	❍	❍	16	16	110	16	16	–	19	2,0	32		
R/L 2020-2	●	❍	20	20	125	20	20	–	24	2,0	40		
STFS R/L 1616-3	❍	●	16	16	110	16	16	20	22	3,0	35		
R/L 2012-3	❍	❍	20	12	110	12	20	–	24	3,0	40	WCF _ 3 _	
R/L 2020-3	●	●	20	20	125	20	20	–	30	3,0	50		
R/L 2525-3	●	●	25	25	150	25	25	–	30	3,0	50		
STFS R/L 2020-4	❍	●	20	20	125	20	20	–	33	4,0	55	WCF _ 4 _	SL 4
R/L 2525-4	●	❍	25	25	150	25	25	–	38	4,0	65		
STFS R/L 2020-5	❍	❍	20	20	125	20	20	–	35	5,0	60	WCF _ 5 _	
R/L 2525-5	❍	❍	25	25	150	25	25	–	40	5,0	70		

● = Euro stock
○ = Japan stock
❑ = Delivery on request

Sumi-Grip Jr. Inserts

Inserts

Neutral (N)



Right Handed (R)



Left Handed (L)



* WCF_2T: 2_RE=0,15

External Appearance	Cat. No.	AC830P	AC225	AC1030U	T1500A	A30	G10E	CW	Applicable Holder	
WCF N _ GG General purpose	WCF N2 GG	❍						2,0	STFH _ _ 2	STFS R/L _ _ _ _ 2
	N3 GG	●						3,0	STFH _ _ 3	STFS R/L _ _ _ _ 3
	N4 GG	●						4,0	STFH _ _ 4	STFS R/L _ _ _ _ 4
	N5 GG	❍						5,0	STFH _ _ 5	STFS R/L _ _ _ _ 5
WCF N _ GF Exotic alloy Low feed	WCF N2 GF			❍				2,0	STFH _ _ 2	STFS R/L _ _ _ _ 2
	N3 GF			❍				3,0	STFH _ _ 3	STFS R/L _ _ _ _ 3
	N4 GF			❍				4,0	STFH _ _ 4	STFS R/L _ _ _ _ 4
	N5 GF			❍				5,0	STFH _ _ 5	STFS R/L _ _ _ _ 5
WCF _ _ CF Exotic alloy Low feed	WCF R3 CF			❍				3,0	STFH _ _ 3	STFS R/L _ _ _ _ 3
	L3 CF			❍				3,0		
	R4 CF							4,0	STFH _ _ 4	STFS R/L _ _ _ _ 4
	L4 CF			❍				4,0		
WCF _ 2T Small diameter Low cutting force	WCF N2T	●						2,0	STFH _ _ 2	STFS R/L _ _ _ _ 2
	R2T	❍						2,0		
	L2T	❍						2,0		
WCF _ _ Without chip breaker General steel	WCF N3	●						3,0	STFH _ _ 3	STFS R/L _ _ _ _ 3
	R3	●						3,0		
	L3	●						3,0		
	WCF N4	●						4,0	STFH _ _ 4	STFS R/L _ _ _ _ 4
	R4	❍						4,0		
	L4	●						4,0		
	WCF N5	●						5,0	STFH _ _ 5	STFS R/L _ _ _ _ 5
	R5							5,0		
	L5	❍						5,0		
WCF _ _ A Exotic alloy Low feed	WCF N2A		●					2,0	STFH _ _ 2	STFS R/L _ _ _ _ 2
	WCF N3A	●	●		❍			3,0	STFH _ _ 3	STFS R/L _ _ _ _ 3
	R3A		●					3,0		
	L3A		●					3,0		
	WCF N4A		●			❍		4,0	STFH _ _ 4	STFS R/L _ _ _ _ 4
	R4A		●					4,0		
	L4A		●					4,0		
	WCF N5A		●					5,0	STFH _ _ 5	STFS R/L _ _ _ _ 5
	R5A		❍					5,0		
	L5A							5,0		
WCF _ _ B Cast iron Light alloys	WCF N3B						●	3,0	STFH _ _ 3	STFS R/L _ _ _ _ 3
	R3B						●	3,0		
	L3B						●	3,0		
	WCF N4B						●	4,0	STFH _ _ 4	STFS R/L _ _ _ _ 4
	R4B							4,0		
	L4B							4,0		
	WCF N5B						❍	5,0	STFH _ _ 5	STFS R/L _ _ _ _ 5
	R5B							5,0		
	L5B							5,0		

Note:
With the similar chip breaker style as for general steel (WCF _ _) but with smaller edge preparation.

Recommended Cutting Conditions

Work Material		Cutting Speed (m/min)					
		AC830P	AC225	AC1030U	T1500A	A30	G10
Steel	General Steel	80–200	80–200	50–200	80–200	50–120	–
	Soft Steel	100–230	100–230	50–230	100–230	70–150	–
	Die Steel	60–150	60–150	50–150	60–150	50–120	–
Stainless Steel		70–150	70–150	50–150	–	70–130	–
Cast Iron		–	–	50–200	–	–	50–120
Non-Ferrous Metal		–	–	200–500	–	–	200–500

Chip Breaker		Feed Rate (mm/rev)										
		Neutral						Left or Right Handed				
		GG	GF	Without Chip Breaker	T	A	B	Without Chip Breaker	CF	T	A	B
		General Purpose	Exotic Alloy Low Cutting Force	General Steel	Small Diam. Low Cutting Force	Exotic Alloy Low Feed	Cast Iron Light Alloys	General Steel	Exotic Alloy Low Cutting Force	Small Diam. Low Cutting Force	Exotic Alloy Low Feed	Cast Iron Light Alloys
Groove Width W (mm)	**2,0**	0,05–0,20	0,03–0,12	–	0,03–0,10	0,03–0,12	–	–	–	0,03–0,10	–	–
	3,0	0,08–0,25	0,04–0,15	0,08–0,25	–	0,04–0,15	0,05–0,15	0,08–0,25	0,08–0,12	–	0,04–0,15	0,05–0,15
	4,0	0,10–0,30	0,05–0,18	0,10–0,30	–	0,05–0,18	0,05–0,18	0,10–0,30	0,10–0,30	–	0,05–0,18	0,05–0,18
	5,0	0,10–0,35	0,05–0,20	0,10–0,30	–	0,05–0,20	0,06–0,20	0,10–0,20	0,10–0,30	–	–	0,06–0,20

Sumi-Grip Series

Cut-Off (Carbide Holder/Tool Block Type)

WCFH
Cut-Off



CW: 3 mm
4 mm
5 mm



CW: 2 mm



(WCFH 32-2)

Above figures show right hand tools.

■ Holders

Cat. No.	Stock	Dimensions (mm)						Max. Cut-Off Dia.	Applicable Inserts	Applicable Tool Blocks	Wrench
		H	B	LF	HF	LF2	CW				
WCFH 26-2	●	26	1,7	110	21,4	109,0	2,0	40	WCF _ 2 _		SL 2
26-3	●	26	2,4	110	21,4	108,5	3,0	70	WCF _ 3 _	SBN 20-26	
26-4	●	26	3,4	110	21,4	108,5	4,0	70	WCF _ 4 _	SBU 20-26	SL 1
26-5	●	26	4,3	110	21,4	108,5	5,0	70	WCF _ 5 _		
WCFH 32-2	●	32	1,7	150	25,0	149,0	2,0	40	WCF _ 2 _	SBN 20-32	SL 2
32-3	●	32	2,4	150	25,0	148,5	3,0	100	WCF _ 3 _	SBN 25-32	
32-4	●	32	3,4	150	25,0	148,5	4,0	100	WCF _ 4 _	SBU 20-32	SL 1
32-5	●	32	4,3	150	25,0	148,5	5,0	100	WCF _ 5 _	SBU 25-32	

See F48 for applicable inserts.

■ Parts

■ Tool Blocks

SBN Type, Mono-block Type



Cat. No.	Stock	Dimensions (mm)					Applicable Carbide Blades
		H	Ha	Hb	Hc	L	
SBN 20-26	●	45	20	20	10,0	80	WCFH 26_
SBN 20-32	●	50	20	20	13,5	100	WCFH 32_
SBN 25-26	❑	48	25	25	10,0	80	WCFH 26_
SBN 25-32	●	50	25	25	8,5	110	WCFH 32_

■ Parts

Clamp	Screw	Wrench
		
BWS 30	WB 8-20	LH 040

SBU Type, Separate Type



Cat. No.	Stock	Dimensions (mm)					Applicable Carbide Blades
		H	Ha	Hb	Hc	L	
SBU 20-26	●	45	20	20	10,0	80	WCFH 26_
SBU 20-32	●	50	20	20	13,5	100	WCFH 32_
SBU 25-26	❑	48	25	25	10,0	80	WCFH 26_
SBU 25-32	●	50	25	25	8,5	110	WCFH 32_

Wedge		
		
BCS 15	BCS 20	BCS 25

Screw	Wrench	
		
BX 0622	LH 050	

■ Tool Block Type Selection Guide

Tool Block (Mono-Block Type)

SBN Type



This tool block can be used for the machining tool post **A** shown on the right.

Tool Block (Separate Type)

SBU Type



This tool block can be used for the machining tool posts **A** and **B** shown on the right.
Since the clamp is large it has a large scope even when the holder has a long overhang.

A General Purpose Lathe, etc.
SBN Type, SBU Type



(Overhead clamp)

B Turret Type Tool Post, etc.
SBU Type



(Side clamp)

● = Euro stock
○ = Japan stock

❑ = Delivery on request

Cut-Off (Carbide Holder/Shank Type)

WCFS
Cut-Off





Above figures show right hand tools.

■ Holders

■ Parts

Cat. No.		Stock R	Stock L	H	B	LF	WF	HF	LH	CW	Max. Cut-Off Dia.	Applicable Blades	Applicable Inserts	Fig.	Wrench
Brazed Type	WCFS R/L 1010-2	●		10	10	86	10	10	10	2,0	28	–	WCF _ 2 _	1	SL 2
	R/L 1212-2	●		12	12	110	12	12	18	2,0	30	–	WCF _ 2 _	1	
	R/L 1616-2	❍	●	16	16	100	16	16	25	2,0	35	–	WCF _ 2 _	2	
	R/L 1616-3			16	16	100	16	16	25	3,0	35	–	WCF _ 3 _	2	SL 1
Clamp Type	WCFS R/L 20-3	●	●	20	20	125	23	20	46	3,0	50	WCFH17-3	WCF _ 3 _	3	SL 1
	R/L 20-4	●		20	20	125	24	20	46	4,0	50	WCFH17-4	WCF _ 4 _	3	
	R/L 20-5	❍		20	20	125	25	20	46	5,0	50	WCFH17-5	WCF _ 5 _	3	
	WCFS R/L 25-3	●	❍	25	25	150	28	25	46	3,0	50	WCFH17-3	WCF _ 3 _	4	
	R/L 25-4		❍	25	25	150	29	25	46	4,0	50	WCFH17-4	WCF _ 4 _	4	
	R/L 25-5		❍	25	25	150	30	25	46	5,0	50	WCFH17-5	WCF _ 5 _	4	

See F48 for applicable inserts.

Blade included in holder.

■ Blades



Cat. No.	Stock	Dimensions (mm) CW	Dimensions (mm) B	Applicable Blades
WCFH 17-3	●	3	2,4	WCFS R/L 20-3, 25-3
WCFH 17-4	●	4	3,4	WCFS R/L 20-4, 25-4
WCFH 17-5	●	5	4,3	WCFS R/L 20-5, 25-5

■ Parts

Cap Screw	Wrench	Applicable Holders
BX0622	LH050	All clamp type holders.

Sumi-Grip Inserts

■ Inserts

Neutral (N)



Right Handed (R)



Left Handed (L)



* WCF_2T: 2_RE=0,15

External Appearance	Cat. No.	AC830P	AC225	AC1030U	T1500A	A30	G10	CW	Applicable Holder	
WCF N _ GG General purpose	WCF N2 GG	❍						2,0	WCFH _ _ 2	WCFS R/L _ _ _ _ 2
	N3 GG	●						3,0	WCFH _ _ 3	WCFS R/L _ _ _ 3, WCFS R/L _ _ 3
	N4 GG	●						4,0	WCFH _ _ 4	WCFS R/L _ _ 4
	N5 GG	❍						5,0	WCFH _ _ 5	WCFS R/L _ _ 5
WCF N _ GF Exotic alloy Low feed	WCF N2 GF			❍				2,0	WCFH _ _ 2	WCFS R/L _ _ _ _ 2
	N3 GF			❍				3,0	WCFH _ _ 3	WCFS R/L _ _ _ 3, WCFS R/L _ _ 3
	N4 GF			❍				4,0	WCFH _ _ 4	WCFS R/L _ _ 4
	N5 GF			❍				5,0	WCFH _ _ 5	WCFS R/L _ _ 5
WCF _ _ CF Exotic alloy Low feed	WCF R3 CF			❍				3,0	WCFH _ _ 3	WCFS R/L _ _ _ _ 3
	L3 CF			❍				3,0		WCFS R/L _ _ 3
	R4 CF							4,0	WCFH _ _ 4	WCFS R/L _ _ 4
	L4 CF			❍				4,0		
WCF _ 2T Small diameter Low cutting force	WCF N2T	●						2,0	WCFH _ _ 2	WCFS R/L _ _ _ _ 2
	R2T	❍						2,0		
	L2T	❍						2,0		
WCF _ _ Without chip breaker General steel	WCF N3	●						3,0	WCFH _ _ 3	WCFS R/L _ _ _ _ 3 WCFS R/L _ _ 3
	R3	●						3,0		
	L3	●						3,0		
	WCF N4	●						4,0	WCFH _ _ 4	WCFS R/L _ _ 4
	R4	❍						4,0		
	L4	●						4,0		
	WCF N5	●						5,0	WCFH _ _ 5	WCFS R/L _ _ 5
	R5							5,0		
	L5	❍						5,0		
WCF _ _ A Exotic alloy Low feed	WCF N2A		●					2,0	WCFH _ _ 2	WCFS R/L _ _ _ _ 2
	WCF N3A	●	●		❍			3,0	WCFH _ _ 3	WCFS R/L _ _ _ _ 3 WCFS R/L _ _ 3
	R3A		●					3,0		
	L3A		●					3,0		
	WCF N4A		●			●		4,0	WCFH _ _ 4	WCFS R/L _ _ 4
	R4A		●					4,0		
	L4A		●					4,0		
	WCF N5A		●					5,0	WCFH _ _ 5	WCFS R/L _ _ 5
	R5A		❍					5,0		
	L5A							5,0		
WCF _ _ B Cast iron Light alloys Note: With the similar chip breaker style as for general steel (WCF _ _) but with smaller edge preparation.	WCF N3B						●	3,0	WCFH _ _ 3	WCFS R/L _ _ _ _ 3 WCFS R/L _ _ 3
	R3B						●	3,0		
	L3B						●	3,0		
	WCF N4B						●	4,0	WCFH _ _ 4	WCFS R/L _ _ 4
	R4B							4,0		
	L4B							4,0		
	WCF N5B						❍	5,0	WCFH _ _ 5	WCFS R/L _ _ 5
	R5B							5,0		
	L5B							5,0		

■ Recommended Cutting Conditions

Work Material		Cutting Speed (m/min)					
		AC830P	AC225	AC1030U	T1500A	A30	G10
Steel	General Steel	80–200	80–200	50–200	80–200	50–120	–
	Soft Steel	100–230	100–230	50–230	100–230	70–150	–
	Die Steel	60–150	60–150	50–150	60–150	50–120	–
Stainless Steel		70–150	70–150	50–150	–	70–130	–
Cast Iron		–	–	50–200	–	–	50–120
Non-Ferrous Metal		–	–	200–500	–	–	200–500

Chip Breaker		Feed Rate (mm/rev)										
		Neutral						Left or Right Handed				
		GG	GF	Without Chip Breaker	T	A	B	Without Chip Breaker	CF	T	A	B
		General Purpose	Exotic Alloy Low Cutting Force	General Steel	Small Diam. Low Cutting Force	Exotic Alloy Low Feed	Cast Iron Light Alloys	General Steel	Exotic Alloy Low Cutting Force	Small Diam. Low Cutting Force	Exotic Alloy Low Feed	Cast Iron Light Alloys
Groove Width W (mm)	**2,0**	0,05–0,20	0,03–0,12	–	0,03–0,10	0,03–0,12	–	–	–	0,03–0,10	–	–
	3,0	0,08–0,25	0,04–0,15	0,08–0,25	–	0,04–0,15	0,05–0,15	0,08–0,25	0,08–0,12	–	0,04–0,15	0,05–0,15
	4,0	0,10–0,30	0,05–0,18	0,10–0,30	–	0,05–0,18	0,05–0,18	0,10–0,30	0,10–0,30	–	0,05–0,18	0,05–0,18
	5,0	0,10–0,35	0,05–0,20	0,10–0,30	–	0,05–0,20	0,06–0,20	0,10–0,20	0,10–0,30	–	–	0,06–0,20

● = Euro stock
○ = Japan stock

General Features

Sumitomo Electric has developed „TME“ external threading inserts with pitch ranges of 1,0–3,0 mm or 10–24 threads/inch and „TMI“ internal threading inserts with a pitch range of 1,0–3,0 mm.

The superior features of the new sintered threading inserts include an M-class tolerance and dimple shaped chip breaker. The M-class tolerance reduces insert cost by eliminating the need for expensive grinding.

Furthermore, chip control is greatly improved as a result of the specially designed dimple chip breakers.

New Series of Indexable Inserts and Holders for Threading

For External Threading

For external thread

ISO-Metric 60°



TME with flat wiper edge

Pitch (mm)

1,0 1,25 1,5 1,75 2,0 2,5 3,0

TME without flat wiper edge

Pitch (mm)

1,0–2,0 , 1,5–3,0

Whitworth 55°

TWE without flat wiper edge

Number of threads / inch

14–10 , 24–16

LTER (Ø 20, Ø 25 mm)

(Lever lock system)

STER (Ø 12, Ø 16 mm)

(Screw on system)

For Internal Threading

For internal thread

ISO-Metric 60°



TMI with flat wiper edge

Pitch (mm)

1,0 1,25 1,5 1,75 2,0 2,5 3,0

TMI without flat wiper edge

Pitch (mm)

1,0– 2,0 , 1,5–3,0

STIR (Ø 16, Ø 20 mm)

(Screw on system)

Threading Insert



Indexable inserts
TME type for external threading

New sintered threading insert
with special dimple shaped chip breaker

■ General Features

- A positive rake angle encourages good chip control and reduces cutting resistance.
- Two tier dimple-style chip breakers evacuate chip smoothly and easily.
- M-class tolerance reduces insert cost.
- Four available grades cover a wider range of applications.
- The LTER type holder is designed for easy clamping and replacement.

● Comparison of Chip Control



Competitor's ground insert

Work material: 25 CrMo 4
Cutting speed: 100 m/min
Pitch: 1,5 mm

● Comparison of Tool Life



Work Material :	X5CrNi1810 (Stainless steel)
Cutting Conditions:	v_c = 100 m/min
	Pitch: 1,5 mm
	7 Passes
	Wet

■ Cutting Grades for Threading

AC225
The AC225 is a carbide insert with a 2 µm multiple-layer coating. This design results in improved toughness and adhesion resistance making this grade **suitable for stainless steel and general steel**.



Neue Cermet-Grade T130A

T130A
The T130A is a cermet grade containing high TiN with a uniform fine-grain microstructure which results in improved wear resistance and toughness.
Thus, the T130A **produces a goods surface finish**.

Cutting Conditions

■ Recommended Cutting Conditions

● Cutting Speed (m/min.)

Work material \ Grade	AC225	T1500A/T130A
Soft steel	150–170	100–150
Carbon steel	100–170	80–130
Alloy steel	90–150	80–120
Stainless steel	70–140	-

● Depth of Cut (Wiper Insert)

		Cat. No.	Pitch	Depth of Cut	Pass	1	2	3	4	5	6	7	8	9	10	11	12	13	14
ISO-Metric 60°	External	TME 100R	1,00	0,68	5	0,20	0,16	0,14	0,11	0,07									
		TME 125R	1,25	0,82	6	0,20	0,18	0,15	0,12	0,10	0,07								
		TME 150R	1,50	0,96	7	0,22	0,18	0,14	0,13	0,12	0,10	0,07							
		TME 175R	1,75	1,12	8	0,22	0,19	0,16	0,14	0,13	0,12	0,09	0,07						
		TME 200R	2,00	1,25	8	0,25	0,21	0,18	0,16	0,15	0,13	0,10	0,07						
		TME 250R	2,50	1,55	10	0,27	0,24	0,20	0,18	0,16	0,13	0,11	0,10	0,09	0,07				
		TME 300R	3,00	1,86	12	0,28	0,25	0,20	0,19	0,17	0,15	0,13	0,12	0,10	0,10	0,09	0,07		
		TME 350R	3,50	2,25	13	0,30	0,27	0,24	0,22	0,20	0,18	0,16	0,15	0,14	0,12	0,11	0,09	0,07	
		TME 400R	4,00	2,57	14	0,35	0,32	0,29	0,26	0,23	0,20	0,17	0,15	0,14	0,12	0,10	0,09	0,08	0,07
	Internal	TMI 100R	1,00	0,63	5	0,18	0,16	0,12	0,10	0,07									
		TMI 125R	1,25	0,77	6	0,18	0,16	0,14	0,12	0,10	0,07								
		TMI 150R	1,50	0,90	7	0,20	0,16	0,14	0,13	0,11	0,09	0,07							
		TMI 170R	1,75	1,03	8	0,20	0,18	0,15	0,14	0,11	0,10	0,08	0,07						
		TMI 200R	2,00	1,18	8	0,22	0,19	0,17	0,15	0,14	0,13	0,11	0,07						
		TMI 250R	2,50	1,44	10	0,25	0,22	0,19	0,16	0,14	0,12	0,10	0,10	0,07	0,07				
		TMI 300R	3,00	1,70	12	0,27	0,24	0,20	0,17	0,14	0,12	0,10	0,10	0,10	0,09	0,06	0,07		

● Depth of Cut (Non Wiper Insert)

		Cat. No.	Radius	Pitch	Depth of Cut	Pass	1	2	3	4	5	6	7	8	9	10	11	12	13	14
ISO-Metric 60°	External	TME 1020R	0,13	1,00	0,68	5	0,20	0,16	0,12	0,10	0,07									
				1,25	0,84	6	0,20	0,18	0,16	0,13	0,10	0,07								
				1,50	1,03	7	0,22	0,20	0,17	0,15	0,12	0,10	0,07							
				1,75	1,22	8	0,22	0,21	0,18	0,16	0,15	0,13	0,10	0,07						
				2,00	1,41	10	0,22	0,20	0,18	0,16	0,14	0,13	0,12	0,10	0,09	0,07				
		TME 1530R	0,20	1,50	0,95	7	0,22	0,17	0,14	0,13	0,12	0,10	0,07							
				1,75	1,14	8	0,22	0,18	0,15	0,14	0,13	0,12	0,09	0,07						
				2,00	1,33	9	0,25	0,20	0,18	0,16	0,15	0,13	0,10	0,09	0,07					
				2,50	1,71	12	0,25	0,22	0,19	0,17	0,15	0,14	0,13	0,12	0,10	0,09	0,08	0,07		
				3,00	2,09	14	0,25	0,22	0,20	0,20	0,18	0,17	0,15	0,14	0,14	0,10	0,10	0,09	0,08	0,07
	Internal	TMI 1020R	0,06	1,00	0,59	6	0,16	0,12	0,10	0,08	0,08	0,05								
				1,25	0,75	7	0,16	0,14	0,12	0,10	0,10	0,08	0,05							
				1,50	0,92	8	0,18	0,15	0,14	0,12	0,10	0,10	0,08	0,05						
				1,75	1,08	9	0,18	0,16	0,14	0,13	0,12	0,12	0,10	0,08	0,05					
				2,00	1,24	10	0,20	0,18	0,15	0,14	0,12	0,12	0,10	0,10	0,08	0,05				
		TMI 1530R	0,09	1,50	0,91	8	0,18	0,14	0,14	0,12	0,10	0,10	0,08	0,05						
				1,75	1,07	9	0,18	0,16	0,13	0,13	0,12	0,12	0,10	0,08	0,05					
				2,00	1,23	10	0,20	0,18	0,14	0,14	0,12	0,12	0,10	0,10	0,08	0,05				
				2,50	1,56	12	0,20	0,18	0,16	0,16	0,15	0,13	0,13	0,11	0,11	0,10	0,08	0,05		
				3,00	1,88	14	0,22	0,20	0,18	0,18	0,16	0,16	0,14	0,14	0,10	0,10	0,10	0,08	0,07	0,05

The shorter pitch, the slower speed. In case of non wiper insert or internal threading, passing time should be requested to increase.

LTER / STER Type



These figures show right hand tools.



These figures show right hand tools.

Holders with Lever Lock System

Cat. No.	Stock	Dimensions (mm)				
		H	HF	B	LF	WF
LTER 2020	●	20	20	20	125	25
LTER 2525	●	25	25	25	150	32
LTER 2525M22	❍	25	25	25	150	32
LTER 3232P22	❍	32	32	32	170	40

Holders with Screw on System

Cat. No.	Stock	Dimensions (mm)				
		H	HF	B	LF	WF
STER 1212	●	12	12	12	100	16
STER 1616	●	16	16	16	100	20

Inserts



Types	Cat. No.	Pitch		Stock			Dimensions (mm)						Applicable Holders	
		(mm)	Threads No./inch	AC225	T1500A	T130A	RE	PDX	PDY	IC	S			
60° Metric Thread	TME 100R	1,00	–	●	❍	●	0,11	0,8	1,2	9,525	3,65	(1)	LTER 2020 LTER 2525	STER 1212 STER 1616
	TME 125R	1,25	–	●	❍		0,15	0,8	1,2	9,525	3,65	(1)		
	TME 150R	1,50	–	●	❍	●	0,19	1,0	1,2	9,525	3,65	(1)		
	TME 175R	1,75	–	●		❍	0,22	1,2	1,2	9,525	3,65	(1)		
	TME 200R	2,00	–	●	❍	❍	0,26	1,4	1,2	9,525	3,65	(1)		
	TME 250R	2,50	–	●		❍	0,33	1,4	1,2	9,525	3,65	(1)		
	TME 300R	3,00	–	●			0,40	1,8	1,2	9,525	3,65	(1)		
	TME 350R	3,50	–				0,47	2,5	1,7	12,70	4,60	(1)	LTER 2525M22	
	TME 400R	4,00	–	❍	❍		0,54	2,5	1,7	12,70	4,60	(1)	LTER 3232P22	
	TME 1020R	1,00–2,00	24–12	●			0,11	1,1	1,2	9,525	3,65	(2)		
	TME 1530R	1,50–3,00	16–8	●			0,19	1,6	1,0	9,525	3,65	(2)	LTER 2020 LTER 2525	
55° Whitworth Thread	TWE 1410R	–	14–10				0,21	1,4	1,2	9,525	3,65	(3)		
	TWE 2416R	–	24–16				0,11	1,1	1,2	9,525	3,65	(3)		

Remarks: (1) TME100R–300R (ISO Thread), (2) TME1020R,1530R ISO Thread) without chamfer, (3) TWE1410R, 2416R (Whitworth Thread) without chamfer

LTER Type Holder Shim Selection



Spare Parts

Holder	Lever Pin	Screw	Shim	Shim pin	Wrench
					
LTER2020,2525	LCL3S	LCS3TE	LSTE31-0*)	LSP3	LH025
LTER2525M22, 3232P22	LCL4S	LCS4	LSTE42-0	LSP4	LH030

*) Remarks: LTER type has supplement of β =1° shim LSTE 31-0
Shims LSTE 31-1 for β = 2° and LSTE 31-2 for β = 3° are option.

Spare Parts

Holder	Screw		Wrench
		N·m	
STER	BFTX03508	**2,0**	TRX 10

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)





These figures show right hand tools.

■ Holders with Screw on System

Cat. No.	Stock	Dimensions (mm)					
		DCON	H	LF	E1	WF	DMIN
STIR 316	●	16	15	150	3,5	11	20
STIR 320	●	20	18	180	5,0	14	25

■ Inserts



Cat. No..	Pitch		Stock		Dimensions (mm)				
	(mm)	Threads No./inch	AC225	T1500A	RE	β	PDX	PDY	
TMI 100R	1,00	-	●	❍	0,04	60	0,8	1,2	
TMI 125R	1,25	-	❍		0,05	60	0,8	1,2	
TMI 150R	1,50	-	●		0,07	60	1,0	1,2	
TMI 175R	1,75	-			0,09	60	1,2	1,2	(1)
TMI 200R	2,00	-	●		0,10	60	1,4	1,2	
TMI 250R	2,50	-	●		0,14	60	1,4	1,2	
TMI 300R	3,00	-	●		0,18	60	1,8	1,2	
TMI 1020R	1,00–2,00	24–12			0,04	60	1,0	1,2	(2)
TMI 1530R	1,50–3,00	16–8	●		0,07	60	1,5	1,2	

Remarks: (1) TME100R–300R (ISO Thread)
(2) TME1020R,1530R (ISO Thread) without chamfer

■ Spare Parts

Holder	Screw		Wrench
		N·m	
STIR	BFTX03508	**2,0**	TRX 10

Milling Cutters

G

G1–G70

Selection Guide

Application	Cutter Type	Series	Insert Type	Approach Angle / Max. Depth of Cut (mm)	Cutter Diameter (mm)	Application: Face Milling – General Purpose	Face Milling – Finishing	Face Milling – High Feed	Shoulder Milling	Groove Milling	Ramping	Chamfering	Drilling	Profiling	Profile Finishing	Work Material: P – Carbon Steel / Alloy Steel	P – Tempered Steel / Die Steel	M – Stainless Steel	K – Cast Iron / Ductile Cast Iron	N – Non-Ferrous Metal	N – Aluminium Alloy	S – Ti Alloy / Heat Resistant Alloy	H – Hardened Steel HRC 45 ~ 55	Ref. Page
Face Milling	DGC 	DGC (-M/F) 13000RS	SNM/EU 13T6..  ONM/EU 05T6.. 	SNMU 6 mm 45°	40–250	◎				○						◎	◎	◎	◎	◎	◎	○		G8
				ONMU 3 mm 45°	42,9–52,9																			
	WGX 	WGX (-M/F) 13000RS	SEE/MT 13T3.. 	6 mm 45°	40–250	◎	◎			○						◎	◎	◎	◎	◎	◎	○		G10
	WGC 	WGC 3000 RS 4000 RS	SEE/MT0903.. (IC/ l = 9,525) SEE/MT13T3.. (IC/ l = 13,4) 	4 mm 45°	32–100	◎	◎			○						◎	◎	◎	◎	◎	◎	◎		G12
		WGC (-M/F) 4000 RS		6 mm 45°	40–200																			
	UFO 	UFO (-F) 4000 RS	SFK-N/R12T3.., SFK-N1504... 	5 mm 45°	50–315	○	○			○						○	○	○	○	○	○	○		G14 G15
		UFO 5000 RS		7 mm 45°	80–315																			
	DNX 	DNX (-F) 12000RS	SNMT 1205.. 	8 mm 65°	80–250	○	○									○			◎					G16
Radius Milling	RSX 	RSX (-F) 10000RS	RDET10T3.. RDET1204.. 	5 mm	40–52	◎		○	◎	○	◎		◎			◎	◎	◎	◎			◎		G22
		RSX (-F) 12000RS		6 mm	40–100																			
		RSX (-F) 16000RS	RDET1606.. RDET2006..	8 mm	63–160																			
		RSX (-F) 20000RS		10 mm	80–160																			
Multi-Purpose	WRCX 	WRCX (-F/X) 12000RS 16000RS 20000RS	QPMT1204../1606../2006 QPET1204../1606.. 	6 ~ 10 mm	40–160	◎		○	◎	○	◎		◎			◎	◎	◎	◎		◎	○	○	G19
High Feed Milling	MSX 	MSX 08000RS 12000RS 14000RS	WDMT0603../0804../1205.. 1406.. 	1,5 ~ 2,5 mm 20°	40–100			◎	○	○	○					◎	◎	◎	◎			○		G43
	WFXH 	WFXH 08000RS	SOMT0803.. SOMT1204.. 	1,5 mm 15°	40–63			◎	○	○	○					◎	◎	◎	◎	◎	◎	○		G46 G47
		WFXH 12000RS		2,5 mm 15°	50–63																			
Shoulder Milling	DFC 	DFC (-M/F) 09000RS	XNMU0606.. 	6 mm 90°	50–200	◎	○		◎	○						◎	◎	○	◎			○		G26
	WFX 	WFX (-F/-M) 08000RS WFX (-F) 12000 RS	SOMT080.. SOMT1204.. 	6 mm 90°	50–160	○	◎		◎	○						◎	◎	◎	◎	◎	◎	○		G30 G31
				10 mm 90°																				

◎ : Best
○ : Suitable

Application	Cutter Type	Series	Insert Type	Approach Angle / Max. Depth of Cut (mm)	Cutter Diameter (mm)	Application: Face Milling – General Purpose	Face Milling – Finishing	Face Milling – High Feed	Shoulder Milling	Groove Milling	Ramping	Chamfering	Drilling	Profiling	Profile Finishing	Work Material: P – Carbon Steel / Alloy Steel	P – Tempered Steel / Die Steel	M – Stainless Steel	K – Cast Iron / Ductile Cast Iron	N – Non-Ferrous Metal	N – Aluminium Alloy	S – Ti Alloy / Heat Resistant Alloy	H – Hardened Steel HRC 45 ~ 55	Ref. Page
Shoulder Milling	TSX 	TSX (-F) 08000RS TSX (-M) 13000 RS	LNEX0804..,LNEX1306.. 	8 mm 90° 12 mm 90°	40–63 40–160	◎	◎		◎	○						◎	◎	◎	◎	◎	◎	◎		G34 G35
	PWS 	PWS (-F) 4000 RS	LNMX1708.. 	16 mm 90°	80–250	○		◎	◎	○						◎	○	○	○					G37
	WEZ New 	WEZ 11000R(S) WEZ 17000R(S)	AOMT11T302PEER-G 	10 mm 90° 15 mm 90°	40–100 40–160	◎	◎		◎	◎	◎					◎	◎	◎	◎	◎	◎	◎		G45 G47
	WEX 	WEX 1000F WEX 2000F WEX 3000F	AXMT0602.. AXMT1235.. AXMT1705.. 	5 mm 90° 10 mm 90° 14 mm 90°	10–100	○			◎	◎	○					◎	◎	◎	◎	◎	◎	◎		G48
	WRX 	WRX 2000F WRX 3000F	AXMT12350../1705.. 	18 ~ 36 mm 90° 27 ~ 53 mm 90°	40–50 50–100	○			◎	◎	○					◎	◎	◎	◎	◎	◎	◎		G49
	PWC 	PWC (-F) 4000 RS	LNMX1606.. 	12 mm 88°	80–200	○		◎	○	○									◎					G50
	CNP 	CNP (-F) 13000 RS	CNMU1306.. CNMQ1306.. 	12 mm 90°	40–200				◎							◎	◎	◎	◎					G52
Aluminium Alloy and Non-Ferrous Metals	WAX 	WAX 3000 RS WAX 4000 RS	AECT1604 	16 ~ 18 mm 90° 22 ~ 24 mm 90°	50–125	○			◎	◎	◎			◎						○	◎			G58 G59
	ANX New 	ANXS 16000R(S) ANXA 16000R(S)	ANB 1600R-L 	3 mm 90°	40–125 80–160	○	◎	◎	◎											◎	◎			G62 G63
	RF 	RF 4000 RS	SNEW1204.. SDET1204.. 	3 mm 90°	80–315	◎	◎													○	◎			G66
	SRF 	SRF 50/63 RS	SNEW09T3.. 	5 mm 90°	30–63	◎	◎		○											○	◎			G67
High Speed Finishing of Cast Iron	FMU 	FMU 4000 RS	SNEW1203.. 	0,5 mm 45°	80–315		◎												◎					G68

ISO Identification Table

Insert shape			
C	80°	A	85°
D	55°	B	82°
E	75°	K	55°
F	50°	H	120°
V	35°	O	135°
R	-	P	108°
S	90°	L	90°
T	60°	M	86°
W	80°		

Clearance angle	
A	3°
B	5°
C	7°
D	15°
E	20°
F	25°
G	30°
N	0°
P	11°



O Other clearance angle with specific description

Insert type			
A		W	
G		T	
M			
N			
R		X	Non standard

S E M T

Tolerances



IC: theoretical diameter of inscribed circle
m: nose height
s: thickness

Class	Tolerances (mm)		
	m	IC	s
A	±0,005	±0,025	±0,025
F	±0,005	±0,013	±0,025
C	±0,013	±0,025	±0,025
H	±0,013	±0,013	±0,025
E	±0,025	±0,025	±0,025
G	±0,025	±0,025	±0,13

Class	Tolerances (mm)		
	m	IC	s
J	±0,005	±0,05 – ±0,13*	±0,025
K	±0,013	±0,05 – ±0,13*	±0,025
L	±0,025	±0,05 – ±0,13*	±0,025
M	±0,08~ ±0,18*)	±0,05 – ±0,13*	±0,13
N	±0,08~ ±0,18*)	±0,05 – ±0,13*	±0,025
U	±0,13~ ±0,38*)	±0,08 – ±0,25*	±0,13



*) The tolerance is dependent upon the insert size of IC. See tables below.

Tolerance class for dimension m

m	S	T	C	W	V	D
6,35	±0,08				-	±0,11
9,525	±0,08				±0,13	±0,11
12,7	±0,13					±0,15
15,875	±0,15					±0,18
19,05	±0,15					±0,18
25,4	±0,18					



Tolerance class for dimension IC

IC	S	T	C	D	V	W	R
6,35	±0,05						
9,525	±0,05						±0,05
12,7	±0,08						±0,08
15,875	±0,10						±0,10
19,05	±0,10						±0,10
25,4	±0,13						±0,10

ISO Identification Table

Thickness



02	s = 2,38 mm
03	s = 3,18
T3	**s = 3,97**
04	s = 4,76
05	s = 5,56
06	s = 6,35
07	s = 7,94
09	s = 9,52

Corner geometry with wiper flat

Entering angle

Feed direction



A	**45°**
D	60°
E	75°
F	85°
P	90°
Z	- Others

1. Major cutting edge
2. Chamfered corner
3. Wiper flat
4. Side cutting edge

Clearance angle on wiper flat



A	3°
B	5°
C	7°
D	15°
E	20°
F	**25°**
G	30°
N	0°
P	11°
Z	- **Others**

Radius



02	r = 0,2 mm
04	r = 0,4
08	r = 0,8
12	r = 1,2
16	r = 1,6
20	r = 2,0
24	r = 2,4

M0 - Round insert (metric)
00 - Round insert (inch)

1 3 T 3 A G S R

Insert size

Symbol and cutting edge length (mm)

Insert type / IC / d (mm)	C	D	R	S	T	V	W
3,97					**06** (6,9)		
4,76					**08** (8,2)		
5,0			**05** (5,0)				
5,56					**09** (9,6)	**09** (9,7)	**03** (3,8)
6,0			**06** (6,0)				
6,35	**06** (6,4)	**07** (7,7)		**06** (6,35)	**11** (11,0)	**11** (11,1)	**04** (4,3)
7,94	**08** (8,0)			**07** (7,94)			**05** (5,4)
8,0			**08** (8,0)				
9,525	**09** (9,7)	**11** (11,6)	**09** (9,525)	**09** (9,525)	**16** (16,5)	**16** (16,6)	**06** (6,5)
10			**10** (10,0)				
12			**12** (12,0)				
12,7	**12** (12,9)	**15** (15,5)	**12** (12,7)	**12** (12,7)	**22** (22,0)		**08** (8,7)
15,875	**16** (16,1)	**19** (19,4)	**15** (15,875)	**15** (15,875)	**27** (27,5)		**10** (10,9)
16			**16** (16,0)				
19,05	**19** (19,3)		**19** (19,05)	**19** (19,05)	**33** (33,0)		
20			**20** (20,0)				
25			**25** (25,0)				
25,4			**25** (25,4)	**25** (25,4)			
31,75			**31** (31,75)	**31** (31,75)			
32			**32** (32,0)				

Cutting edge condition

F	Sharp
E	Rounded
T	Chamfered
S	Rounded and chamfered

Feed direction



DGC(M/F) Type

General Features

Sumi Dual Mill DGC type utilizes double-sided inserts for excellent economy. This is a general-purpose cutter featuring high cutting edge strength for high efficiency milling and low-burr chipbreaker design that provides high qualitiy machined surface.

The DGC type insert lineup includes double-sided SNMU / SNEU and ONMU / ONEU types.
Up to 16 corners can be used for improved economy.

Characteristics

- Same cutting performance as single-sided inserts plus superior economy.
- Achieves level of cutting edge sharpness and machined surface quality equivalent to single-sided cutter at a maximum cutting depth of $a_p \leq 3$ mm.

Recommended Cutting Conditions for General Steel Milling



Cutting Force Comparison



Work Material: 34CrMo4
Tool: Ø 100
Cutting Data: v_c=200m/min, f_t=0,3mm/t, a_p=3mm, a_e=85mm

Dual-Purpose Body

Two types of inserts can be used with a single body depending on milling application to help reduce costs. Stronger than single-sided cutters.

– first recommendation
– economical double-sided design offers 8 cutting edges with SN_U inserts
– maximum depth of cut: a_p = 6 mm

– double-sided design with 16 corners for improved economy
– maximum depth of cut: a_p = 3 mm

max. a_p = 6 mm
8 corners use

Use two types of inserts for different applications.

max. a_p = 3 mm
16 corners use

Line-up

Choose a tool that fits your application from a comprehensive line-up

Cat. No	DGC 13000 RS	DGCM 13000 RS	DGCF 13000 RS	DGC 13000 EW
Type	Standard pitch	Medium pitch	Fine pitch	Endmill type
Cutter Diameter	Ø 40 mm – Ø 250 mm	Ø 50 mm – Ø 250 mm	Ø 50 mm – Ø 250 mm	Ø 40 mm – Ø 63 mm
Cutting Edges	3–10	4–14	5–18	3–4
Shape				 H6

High Reliability

Employs New Super ZX Coating, a multi-layer PVD coating grade and CVD coating grade with enhanced coating strength provided by newly developed stress control technology.
Improved run-out precision reduces tool life deviation to achieve highly reliable tool life.

Multi-layer PVD Coating



Wear Resistance



Cutter Diameter and Cutter Body Height

Insert: SN_U 13T6 ANER (square)

Insert: ON_U 05T6 ANER (octagonal)



Example: DC = 100mm	Number of Cutting Edges	Tool Diameter (mm)	Cutter Height (mm)	Max. Depth of Cut (mm)
SNMU/SNEU 	8	100,0	63,0	6,0
ONMU/ONEU 	16	102,9	61,4	3,0

Square inserts (SNMU/SNEU) and octagonal inserts (ONMU/ONEU) can be used interchangeably on the same body.
Using these inserts the cutter will have different cutter diameter and cutter body height.

DGC(M/F) Type

General Milling of Steel and Cast Iron

Rake Angle		
	Radial	–10°
	Axial	–5°



SNMU ONMU

Body – Shell type

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Cutter body Ø DC ≥ 160 mm: no inner coolant

Body

● Type: DGC, Standard Pitch

Cat. No.	Stock	Dimension (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP			
DGC 13040 RS	●	40 (42,90)	54	36	40 (38,44)	16	13,5	8,4	5,6	18	3	0,3	1
13050 RS	●	50 (52,90)	64	40	40 (38,44)	22	18,0	10,4	6,3	20	3	0,4	1
13063 RS	●	63 (65,90)	77	50	40 (38,44)	22	18,0	10,4	6,3	20	4	0,5	1
13080 RS	●	80 (82,90)	94	60	50 (48,44)	27	20,0	12,4	7,0	25	4	1,2	1
DGC 13100 RS	●	100 (102,90)	114	70	50 (48,44)	32	46,0	14,4	8,5	32	5	1,6	2
13125 RS	●	125 (127,90)	139	80	63 (61,44)	40	52,0	16,4	9,5	29	6	2,8	1
13160 RS	●	160 (162,90)	174	130	63 (61,44)	40	88,0	16,4	9,5	29	7	4,5	3
DGC 13200 RS	❑	200 (202,90)	214	150	63 (61,44)	60	130,0	25,7	14,0	35	8	7,1	4
13250 RS	❑	250 (252,90)	264	190	63 (61,44)	60	160,0	25,7	14,0	35	10	11,2	4

● Type: DGCM, Medium Pitch

Cat. No.	Stock	Dimension (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP			
DGCM 13050 RS	●	50 (52,90)	64	40	40 (38,44)	22	18	10,4	6,3	20	4	0,3	1
13063 RS	●	63 (65,90)	77	50	40 (38,44)	22	18	10,4	6,3	20	5	0,5	1
13080 RS	●	80 (82,90)	94	60	50 (48,44)	27	20	12,4	7,0	25	6	1,1	1
DGCM 13100 RS	●	100 (102,90)	114	70	50 (48,44)	32	46	14,4	8,5	32	7	1,5	2
13125 RS	●	125 (127,90)	139	80	63 (61,44)	40	52	16,4	9,5	29	8	2,8	1
13160 RS	●	160 (162,90)	174	130	63 (61,44)	40	88	16,4	9,5	29	10	4,6	3
DGCM 13200 RS	❑	200 (202,90)	214	150	63 (61,44)	60	130	25,7	14,0	35	12	7,0	4
13250 RS	❑	250 (252,90)	264	190	63 (61,44)	60	160	25,7	14,0	35	14	11,1	4

● Type: DGCF, Fine Pitch

Cat. No.	Stock	Dimension (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP			
DGCF 13050 RS	●	50 (52,90)	64	40	40 (38,44)	22	18	10,4	6,3	20	5	0,3	1
13063 RS	●	63 (65,90)	77	50	40 (38,44)	22	18	10,4	6,3	20	6	0,5	1
13080 RS	●	80 (82,90)	94	60	50 (48,44)	27	20	12,4	7,0	25	8	1,1	1
DGCF 13100 RS	●	100 (102,90)	114	70	50 (48,44)	32	46	14,4	8,5	32	10	1,4	2
13125 RS	●	125 (127,90)	139	80	63 (61,44)	40	52	16,4	9,5	29	12	2,7	1
13160 RS	●	160 (162,90)	174	130	63 (61,44)	40	88	16,4	9,5	29	14	4,4	3
DGCF 13200 RS	❑	200 (202,90)	214	150	63 (61,44)	60	130	25,7	14,0	35	16	6,9	4
13250 RS	❑	250 (252,90)	264	190	63 (61,44)	60	160	25,7	14,0	35	18	11,0	4

( ) Figures in brackets indicate values for ONMU inserts.
Inserts are not included.

Identification Details

DGC	M	13	050	R	S
Cutter Series	M: Medium F: Fine	Insert Size	Cutter Diameter	Direction	Metric

● = Euro stock
❑ = Delivery on request

Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide							
High Speed/Light cut	P			K		MS		
General Purpose		PM	M	K		MS		
Roughing		PM	PM		K		MS	
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	Fig.
SNMU 13T6ANER L	●	●	●	●	●			1
13T6ANER G	●	●	●	●	●			1
13T6ANER H	●	●	●	●	●			1
13T6ANER FL	●	●	●	●	●			2
13T6ANER FG	●	●	●	●	●			2
SNEU 13T6ANER L						●	●	1
13T6ANER G						●	●	1
13T6ANER FL						●	●	2
13T6ANER FG						●	●	2
XNEU 13T6ANEN W		●			●			3
ONMU 05T6ANER L	●	●	●	●	●			4
05T6ANER G	●	●	●	●	●			4
ONEU 05T6ANER L						●	●	4
05T6ANER G						●	●	4

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Chipbreaker



Improved Milling Quality

FG type chipbreakers feature chamfer to minimize burrs and provide excellent milling qualitiy.



FG



No burrs

Competitor

Burrs

FG type inserts with low-burr design enable high-qualitiy milling with few burrs and little edge chipping.

Attaching Inserts

Octagonal Inserts

Firmly align insert with supporting face, press down in the direction of the arrow and tighten the screw to fix the insert.

Press down firmly from above



Spare Parts

Shim	Shim Screw	L Seat Wrench	Insert Srew	Insert Wrench
				
DGCS13R	BW0609F	LH040	BFTX0412IP	TRDR15IP

Optional

Insert Srew (*)

BFTX0418IP

*Corners can be changed simply by loosening the screw. (Only suitable for DGC/DGCM types with body size ≥ Ø 80 mm).

Recommended Cutting Conditions (SN_U)

ISO	Work Material	Fit-ness	Cutting Speed v_c (m/min)	Feed Rate f_t (min/t)	Depth of Cut (mm)	Grade
P	General Steel	◎	150–**200**–250	0,10–**0,25**–0,40	<4	ACP200 ACP300
	Alloyed Steel	◎	180–**250**–350	0,10–**0,30**–0,45	<4	ACP200 ACP300
	Die Steel	◎	100–**150**–200	0,15–**0,25**–0,35	<4	ACP200 ACP300
M	Stainless Steel	○	160–**200**–250	0,15–**0,23**–0,30	<3	ACM200 ACM300 ACP300
K	GG+GGG	◎	100–**200**–250	0,10–**0,25**–0,40	<5	ACK200 ACK300

Min. – **Optimum** – Max.

Recommended Cutting Conditions (ON_U)

ISO	Work Material	Fit-ness	Cutting Speed v_c (m/min)	Feed Rate f_t (min/t)	Depth of Cut (mm)	Grade
P	General Steel	◎	150–**200**–250	0,10–**0,30**–0,50	<2	ACP200 ACP300
	Alloyed Steel	◎	180–**250**–350	0,10–**0,50**–0,50	<2	ACP200 ACP300
	Die Steel	◎	100–**150**–200	0,15–**0,25**–0,30	<2	ACP200 ACP300
M	Stainless Steel	○	160–**200**–250	0,15–**0,23**–0,30	<2	ACM200 ACM300 ACP300
K	GG+GGG	◎	100–**200**–250	0,10–**0,30**–0,50	<2	ACK200 ACK300

◎ Preferred choice ○ Suitable

WGX (M/F) Type

General Milling of Steel and Cast Iron

Rake Angle		
	Radial	20°–24°
	Axial	20°–22°



Body – Shell type

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Cutter body DC ≥ 160 mm: no inner coolant

Body

Inner coolant available for DC ≤ Ø 125mm

● Type: WGX, Standard Pitch

Cat. No.	Stock	Dimension (mm)										No. of Teeth	Weight (kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	D2	KWW	KDP	CBDP			
WGX 13040 RS	●	40	52	32	40	16	14,0	9,0	8,4	5,6	18	3	0,3	1
13050 RS	●	50	62	40	40	22	18,0	11,0	10,4	6,3	20	3	0,4	1
13063 RS	●	63	76	50	40	22	18,0	11,0	10,4	6,3	20	4	0,6	1
13080 RS	●	80	93	55	50	27	20,0	13,5	12,4	7,0	25	4	1,2	1
WGX 13100 RS	●	100	113	70	50	32	46,0	-	14,4	8,5	32	5	1,6	2
13125 RS	●	125	138	80	63	40	52,0	29,0	16,4	9,5	29	6	2,8	1
13160 RS	●	160	173	130	63	40	88,0	-	16,4	9,5	29	7	4,5	3
WGX 13200 RS	●	200	213	150	63	60	130,0	-	25,7	14,0	35	8	7,1	4
13250 RS	❑	250	263	190	63	60	160,0	-	25,7	14,0	35	10	11,2	4

● Type: WGXM, Medium Pitch

Cat. No.	Stock	Dimension (mm)										No. of Teeth	Weight (kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	D2	KWW	KDP	CBDP			
WGXM 13050 RS	●	50	62	40	40	22	18,0	11,0	10,4	6,3	20	4	0,4	1
13063 RS	●	63	77	50	40	22	18,0	11,0	10,4	6,3	20	5	0,6	1
13080 RS	●	80	94	55	50	27	20,0	13,5	12,4	7,0	25	6	1,1	1
WGXM 13100 RS	●	100	114	70	50	32	46,0	-	14,4	8,5	32	7	1,6	2
13125 RS	●	125	139	80	63	40	52,0	29,0	16,4	9,5	29	8	2,8	1
13160 RS	●	160	174	130	63	40	88,0	-	16,4	9,5	29	10	4,5	3
WGXM 13200 RS	●	200	214	150	63	60	130,0	-	25,7	14,0	35	12	7,0	4
13250 RS	❑	250	264	190	63	60	160,0	-	25,7	14,0	35	14	11,1	4

● Type: WGXF, Fine Pitch

Cat. No.	Stock	Dimension (mm)										No. of Teeth	Weight (kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	D2	KWW	KDP	CBDP			
WGXF 13050 RS	●	50	62	40	40	22	18,0	11,0	10,4	6,3	20	5	0,4	1
13063 RS	●	63	77	50	40	22	18,0	11,0	10,4	6,3	20	6	0,6	1
13080 RS	●	80	94	55	50	27	20,0	13,5	12,4	7,0	25	8	1,1	1
WGXF 13100 RS	●	100	114	70	50	32	46,0	-	14,4	8,5	32	10	1,5	2
13125 RS	●	125	139	80	63	40	52,0	29,0	16,4	9,5	29	12	2,7	1
13160 RS	●	160	174	130	63	40	88,0	-	16,4	9,5	29	16	4,5	3
WGXF 13200 RS	●	200	214	150	63	60	130,0	-	25,7	14,0	35	20	6,9	4
13250 RS	❑	250	264	190	63	60	160,0	-	25,7	14,0	35	24	11,0	4

( ) Figures in brackets indicate values for ONMU inserts.
Inserts are not included.

Identification Details

WGX	M	13	050	R	S
Cutter Series	M: Medium F: Fine	Insert Size	Cutter Diameter	Direction	Metric

● = Euro stock
❍ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

WGX (M/F) Type

General Features

The Wavemill WGX Type employs unique chipbreaker design to provide lower cutting resistance and higher quality surface finishes than conventional tools.

Series

Type	Cat. No.	Cutter	No. of Teeth
Standard Pitch	WGX 13000RS	Ø 40 – Ø 250	3–10
Medium Pitch	WGXM 13000RS	Ø 50 – Ø 250	4–14
Fine Pitch	WGXF 13000RS	Ø 50 – Ø 250	5–24
Endmill Type	WGX 13000EW	Ø 32 – Ø 63	3–5

Inner coolant available for DC ≤ Ø 125 mm

☞ H7

Characteristics

- **Stable Cutting**
  Special chipbreaker designed for WGX enables lower cutting forces.
- **High Quality**
  Improved run-out precision and unique wiper edge shape ensure excellent surface finish quality.
  Optimised chamfer edge reduces burr and edge chipping.
- **Long Tool Life**
  Features high precision technology that reduces insert run-out variation and a new coating to provide stable and long tool life.

Insert Shape Characteristics

Unique wiper edge shape for improved surface roughness



Inserts

Application	Coated Carbide							Carb.	DLC	
High Speed/Light Cut	P			K		MS		KN	N	
General Purpose		PM	M	K		MS	MS		N	
Roughing		PM	PM		K		MS			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Fig.
SEET 13T3AGFR-L								❍	❍	1
SEET 13T3AGSR-L	❍	●	❍	❍	❍	●	❍			1
13T3AGSR-G	❍	●	●	●	❍	●	❍			1
SEMT 13T3AGSR-L	●	●	●	●	❍	●	●			1
13T3AGSR-G	●	●	●	●	●	●	●			1
13T3AGSR-H	●	●	●	●	●	●	●			1
SEMT 13T3AGSR-FG	❍	●	●	❍	●	●	●			2
XEEW 13T3AGER-WR		❍			❍					3

Fig. 1



Fig. 2



Fig. 3





Spare Parts

Applicable Cutters	Shim	Shim Screw	Insert Screw	Insert Wrench	Seat Wrench
			 3,0 N·m		
WGX (-M/F)	WGCS 13 R	BW 0507 F	BFTX 03512 IP	TRDR 15 IP	LH 035

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/tooth)	Grade
P	General Steel	180–280	150–**200**–250	0,15–**0,20**–0,25	ACP200
P	Soft Steel	≤180	180–**265**–350	0,10–**0,25**–0,40	ACP200
P	Die Steel	200–220	100–**150**–200	0,15–**0,20**–0,25	ACP200
M	Stainless Steel	-	160–**205**–250	0,15–**0,23**–0,30	ACM300
K	Cast Iron	250	100–**175** –250	0,15–**0,23**–0,30	ACK200
N	Non Ferrous Alloy	-	500–**750**–1000	0,15–**0,23**–0,30	DL1000
S	Exotic Alloy	-	30 – **50**– 80	0,10–**0,20**–0,30	ACM300

Minimum-**Optimum**-Maximum

WGC (M/F) Type

General Milling for Steel, Cast Iron & Exotic Material

Fig. 1



Fig. 2



Fig. 3



■ Body

● Standard WGC - Type

Cat. No.	Stock	Dimensions (mm)										No. of Teeth	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	KWW	KDP	DCB	D2	D1	CBDP			
WGC 3032 RS	▲	32	41	32	40	8,4	5,6	16	9	14	18	4	0,2	1
3040 RS	▲	40	49	32	40	8,4	5,6	16	9	14	18	4	0,3	1
3050 RS	▲	50	59	40	40	10,4	6,3	22	11	18	20	5	0,4	1
3063 RS	▲	63	72	50	40	10,4	6,3	22	11	18	20	6	0,6	1
3080 RS		80	89	60	50	12,4	7,0	27	13,5	20	25	6	1,1	1
WGC 3100 RS		100	109	70	50	14,4	8,5	32	-	-	32	7	1,5	2
WGC 4040 RS	▲	40	52	32	40	8,4	5,6	16	9	14	18	3	0,4	1
4050 RS	▲	50	63	40	40	10,4	6,3	22	11	18	20	3	0,5	1
4063 RS	▲	63	76	50	40	10,4	6,3	22	11	18	20	4	0,6	1
4080 RS	▲	80	93	60	50	12,4	7,0	27	13,5	20	25	4	1,0	1
WGC 4100 RS	▲	100	113	70	50	14,4	8,5	32	-	-	32	5	1,5	2
4125 RS	▲	125	138	80	63	16,4	9,5	40	-	-	38	6	2,6	2
4160 RS	▲	160	173	100	63	16,4	9,5	40	-	-	38	7	4,0	2
WGC 4200 RS	▲	200	213	130	63	25,7	14,0	60	-	-	35	8	6,6	3

● Medium Pitch WGCM - Type

Cat. No.	Stock	Dimensions (mm)										No. of Teeth	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	KWW	KDP	DCB	D2	D1	CBDP			
WGCM 4050 RS	▲	50	63	40	40	10,4	6,3	22	11	18	20	4	0,5	1
4063 RS	▲	63	76	50	40	10,4	6,3	22	11	18	20	5	0,6	1
4080 RS	▲	80	93	60	50	12,4	7,0	27	13,5	20	25	6	1,0	1
WGCM 4100 RS	▲	100	113	70	50	14,4	8,5	32	-	-	32	7	1,5	2
4125 RS	▲	125	138	80	63	16,4	9,5	40	-	-	38	8	2,6	2
4160 RS	▲	160	173	100	63	16,4	9,5	40	-	-	38	10	4,0	2
WGCM 4200 RS	▲	200	213	130	63	25,7	14,0	60	-	-	35	12	6,6	3

● Fine Pitch WGCF - Type

Cat. No.	Stock	Dimensions (mm)										No. of Teeth	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	KWW	KDP	DCB	D2	D1	CBDP			
WGCF 4050 RS	▲	50	63	40	40	10,4	6,3	22	11	18	20	5	0,5	1
4063 RS	▲	63	76	50	40	10,4	6,3	22	11	18	20	6	0,6	1
4080 RS	▲	80	93	60	50	12,4	7,0	27	13,5	20	25	8	1,0	1
WGCF 4100 RS	▲	100	113	70	50	14,4	8,5	32	-	-	32	10	1,5	2
4125 RS	▲	125	138	80	63	16,4	9,5	40	-	-	38	12	2,6	2
4160 RS	▲	160	173	100	63	16,4	9,5	40	-	-	38	16	4,0	2
WGCF 4200 RS	▲	200	213	130	63	25,7	14,0	60	-	-	35	20	6,6	3

■ Spare Parts

Cutter	Shim	Shim screw	Insert screw		Wrench	Wrench
						
WGC 3000 RS	-	-	BFTX 0307 IP	**2,0**	TRDR 10 IP	-
WGC/-F 4000 RS	WGCS 13 R	BW 0507 F	BFTX 03512 IP	**3,0**	TRDR 15 IP	LH035

■ Structure

▲ = To be replaced by new item

Recommended Tightening Torque (N·m)

Face Mill
WGC (M/F) Type

Features

- Suitable for high speed machining v_c < 400 m/min.
- Tough lightweight cutter body with wide chip pockets for fast metal removal.
- Low cost precision moulded inserts give G class performance at greatly reduced cost.
- Wide range of grades for most workpiece materials - including steels, irons, high temperature alloys, aluminium's etc.
- Improves metal removal rates, flatness, dimensional accuracy, and surface finish.


SEET, SEMT


SECW


XEEW

Insert

Application		Coated Carbide					DLC	Carbide		Cermet	PCD		
High Speed/Light Cut		P			K		N		KN		N		
General Purpose			PM	M	K		N	KS		P	N		
Roughing			PM	PM		K					N		
Cat. No.		ACP100	ACP200	ACP300	ACK200	ACK300	DL1000	EH520	H1	T250A	DA2200	Fig.	Applicable Endmill
SEET	0903 AGFN-L	▲	▲	▲	▲	▲			▲			1	WGC 3000 Type
SEET	0903 AGSN-G	▲	▲	▲	▲	▲						1	
	0903 AGSN-N	▲	▲	▲	▲	▲						1	
SEMT	0903 AGSN-L	▲	▲	▲	▲	▲						1	
	0903 AGSN-G	▲	▲	▲	▲	▲						1	
SEET	13T3 AGFN-L	▲	▲	▲	▲	▲	▲	▲	▲			2	WGC 4000 Type WGC M/F 4000 Type
SEET	13T3 AGSN-G	▲	▲	▲	▲	▲				▲		2	
	13T3 AGSN-N	▲	▲	▲	▲	▲				▲		2	
SEMT	13T3 AGSN-L	▲	▲	▲	▲	▲						2	
	13T3 AGSN-G	▲	▲	▲	▲	▲						2	
	13T3 AGSN-H	▲	▲	▲	▲	▲						2	
SECW	13T3 AGTN-N-NF											2	
XEEW	13T3 AGFR-W-NF											3	
XEEW	13T3 AGER-W					▲						3	

Fig. 1



Fig. 2



Fig. 3



Specifications



Approach angle: 45°
Axial rake angle: + 20° ~ +22°
(+ 20°)
Radial rake angle: - 20° ~ - 24°
(- 10° ~ - 19°)

0,03 mm

Max. depth of cut: 6 mm
(4 mm)

0,02 mm
Run-out with M class insert SEMT13T3

( ) shows WGC 3000 type

Chip Breaker System



● Cutting Edge Geometry



Recommended Cutting Conditions

(v_c =m/min, f_t =mm/tooth) (min.– **optimum** – max.)

Insert Type		SEMT 13T3 AGSN-G											
Grade		ACP100			ACP200			ACP300		ACK200		ACK300	
Type / Work Material		Low carbon steel	Alloy steel	Die steel	Low carbon steel	Alloy steel	Die steel	Stainless steel austenitic	Stainless steel martensitic	Cast iron	Ductile cast iron	Cast iron	Ductile cast iron
WGC (-M/-F) 4040–4200	v_c	100-**250**-400	80-**220**-280	80-**150**-250	80-**200**-370	70-**150**-250	60-**130**-220	120-**180**-240	100-**140**-200	220-**270**-450	150-**180**-250	180-**220**-270	130-**160**-220
	f_t	0,1-**0,25**-0,4	0,1-**0,25**-0,4	0,1-**0,2**-0,3	0,1-**0,25**-0,4	0,1-**0,25**-0,4	0,1-**0,2**-0,3	0,1-**0,2**-0,3	0,1-**0,2**-0,3	0,1-**0,25**-0,4	0,1-**0,25**-0,4	0,1-**0,25**-0,4	0,1-**0,25**-0,4
	a_p	1,0-**3,0**-5,0			1,0-**3,0**-5,0			1,0-**2,0**-3,0		1,0-**3,0**-5,0		1,0-**3,0**-5,0	

UFO / UFOF Type

General Milling for Steel, Cast Iron & Exotic Material

Specifications



Approach angle: 45°
Axial rake angle: + 27°
Radial rake angle: - 7°
(-10° for ø 50 and ø 63)
max depth of cut: 5,0 mm (UFO 4000 type)
7,0 mm (UFO 5000 type)

Body

Cat. No.	Stock		Dimensions (mm)								No. of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
	R	L	DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP				
UFO 4050 R/L-S	●		50	74	45	50	22	10,4	6,3	20	4		1,3	1
4063 R/L-S	●		63	86	50	50	22	10,4	6,3	20	5		1,6	1
4080 R/L-S	●		80	103	60	50	27	12,4	7,0	25	5		2,1	1
UFO 4100 R/L-S	●		100	122	75	50	32	14,4	8,5	29	6		2,9	2
4125 R/L-S	●		125	146	75	63	40	16,4	9,5	29	7	5,0	4,2	2
4160 R/L-S	●		160	180	100	63	40	16,4	9,5	29	9		6,6	3
UFO 4200 R/L-S	●		200	220	130	63	60	25,7	14,0	32	11		9,5	4
4250 R/L-S	❑		250	270	300	63	60	25,7	14,0	40	13		14,8	4
UFO 4315 R/L-S	❑		315	335	240	80	60	25,7	14,0	40	15		26,6	5
UFO 5080 R/L-S	●		80	102	60	50	27	12,4	7,0	25	5		2,1	1
UFO 5100 R/L-S	●		100	119	75	50	32	14,4	8,5	29	6		2,9	2
5125 R/L-S	●		125	143	75	63	40	16,4	9,5	29	7		4,2	2
5160 R/L-S	●		160	177	100	63	40	16,4	9,5	29	9	7,0	6,6	3
UFO 5200 R/L-S	●		200	217	130	63	60	25,7	14,0	32	11		9,5	4
5250 R/L-S	❑		250	267	200	63	60	25,7	14,0	40	13		14,8	4
UFO 5315 R/L-S	❑		315	332	240	80	60	25,7	14,0	40	15		26,6	5

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Fig. 5



Spare Parts

Cutter	Locator	Insert block	Insert clamp
			
4050–4063	UF 4 K R/L	S-UF 4 S R/L	UFTW R/L
4080–4315	UF 4 K R/L	UF 4 S R/L	
5080–5315	UF 5 K R/L	UF 5 S R/L	

Cutter	Locator clamp	Double screw	Wrench
			
4050–4063	UFKW R/L	WB 7-15 T	TT 25
4080–4315			
5080–5315			

Structure



● = Euro stock
○ = Japan stock
❑ = Delivery on request

Face Mill
UFO / UFOF Type

Features

- 45° approach face mills
- 27° super high rake multi purpose cutter for outstanding productivity milling steels, irons and alloys
- Substantially improves metal removal rates on low powered machines
- Differential pitched inserts guarantee smooth cutting action
- Rigid body incorporates carbide locators and HSS shims resulting in extremely low run out

Body (Fine Pitch Type)

Cat. No.	Stock		Dimensions (mm)								No. of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
	R	L	DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP				
UFOF 4080 R/L-S	●		80	103	60	50	27	12,4	7,0	25	6		2,1	1
UFOF 4100 R/L-S	●		100	122	75	50	32	14,4	8,5	29	8		2,9	2
4125 R/L-S	●		125	146	75	63	40	16,4	9,5	29	10		4,2	2
4160 R/L-S	●		160	180	100	63	40	16,4	9,5	29	12	5,0	6,6	3
UFOF 4200 R/L-S	❑		200	220	130	63	60	25,7	14,0	32	16		9,5	4
4250 R/L-S	❑		250	270	300	63	60	25,7	14,0	40	20		14,8	4
UFOF 4315 R/L-S	❑		315	335	240	80	60	25,7	14,0	40	24		26,6	5

Insert

Grade		Coated Carbide					Cermet	Uncoated Carbide				
High Speed/Light Cut		P			K							K M
General Purpose			P M	P M	K		P	P	K	K		
Roughing			P M	P M		K						
Cat. No.		ACP100	ACP200	ACP300	ACK200	ACK300	T250A	A30N	G10E	H1	H10E	Fig.
UFO(F) 4000	SFKN 12T3 AZFN				●	●			●	❍		1(2)
	12T3 AZTN	●	●	●			●	❍				2
	SFKR 12T3 AZTN	❍	❍									3
	UW 12500 R										❍	4
UFO 5000	SFKN 1504 AZFN				●	❍			❍			5(6)
	1504 AZTN	●	●	●				❍				6
	UW 15500 R										❍	7

Fig. 1 (Grades: ACP_, ACK_)



Fig. 2



Fig. 3



Fig. 4



Fig. 5 (Grades: ACP_, ACK_)



Fig. 6



Fig. 7



Recommended Cutting Conditions

(v_c =m/min, f_t =mm/tooth) (min.– **optimum** – max.)

Grade		ACP100			ACP200			ACP300		ACK200		ACK300	
Work Material / Insert Type		Low carbon steel	Alloy steel	Die steel	Low carbon steel	Alloy steel	Die steel	Stainless steel austenitic	Stainless steel martensitic	Cast iron	Ductile cast iron	Cast iron	Ductile cast iron
UFO (-F) 4000	v_c	100–**250**–400	80–**220**–280	80–**150**–250	80–**200**–370	70–**150**–250	60–**130**–220	120–**180**–240	100–**140**–200	220–**270**–450	150–**180**–250	180–**220**–270	130–**160**–220
	f_t	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,2**–0,3	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,2**–0,3	0,1–**0,2**–0,3	0,1-**0,2**-0,3	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,25**–0,4
	a_p	1,0–**3,0**–5,0			1,0–**3,0**–5,0			1,0–**2,0**–3,0		1,0–**3,0**–5,0		1,0–**3,0**–5,0	
UFO (-F) 5000	v_c	100–**250**–400	80–**220**–280	80–**150**–250	80–**200**–370	70–**150**–250	60–**130**–220	120–**180**–240	100–**140**–200	220-**270**-450	150–**180**–250	180–**220**–270	130–**160**–220
	f_t	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,2**–0,3	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,2**–0,3	0,1–**0,2**–0,3	0,1–**0,2**–0,3	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,25**–0,4	0,1–**0,25**–0,4
	a_p	1,0–**4,0**–7,0			1,0–**4,0**–7,0			1,0–**2,0**–5,0		1,0–**4,0**–7,0		1,0–**4,0**–7,0	

DNX / DNXF Type

General Milling for Cast Iron and Steel

Approach angle	:	65°
Axial rake angle	:	+ 5°
Radial rake angle	:	- 6°

8 mm / 65°

Fig. 1



Fig. 2



Fig. 3



Fig. 4



■ Body

● Standard DNX - Type

Cat. No.	Stock	Dimensions (mm)									No of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP				
DNX 12080 RS	●	80	88	60	50	27	-	12,4	7,0	25	6	8,0	1,2	1
DNX 12100 RS	●	100	108	80	50	32	46	14,4	8,5	29	7		1,6	2
12125 RS	●	125	133	80	63	40	56	16,4	9,5	29	8		2,8	2
12160 RS	●	160	168	100	63	40	88	16,4	9,5	29	10		4,4	3
DNX 12200 RS	❑	200	210	150	63	60	130	25,7	14,0	35	16		8,0	4
12250 RS	❑	250	260	180	63	60	160	25,7	14,0	25	20		12,2	4

● Fine Pitch DNXF - Type

Cat. No.	Stock	Dimensions (mm)									No of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP				
DNXF 12080 RS	●	80	88	60	50	27	-	12,4	7,0	25	8	8,0	1,2	1
DNXF 12100 RS	●	100	108	80	50	32	46	14,4	8,5	29	10		1,6	2
12125 RS	●	125	133	80	63	40	56	16,4	9,5	29	11		2,7	2
12160 RS	●	160	168	100	63	40	88	16,4	9,5	29	12		4,4	3

■ First Recommendation: DNX



DNX / DNXF



Wiper width = 1,2 mm

Max. depth of cut : 8 mm, Approach angle : 65°		
Cutter Type	Diameter Range	Characteristics
DNX 12000 RS	Ø 80–Ø 250 mm	- General purpose - Medium pitch type
DNXF 12000 RS	Ø 80–Ø 160 mm	- General purpose - Fine pitch type

■ Spare Parts

Cutter	Insert Screw	Insert Wrench	Locator	Clamp Screw	Wrench
	 3,0 N·m				
Ø 80 – Ø 160	BFTX0412 IP	TRDR15 IP	–	–	–
Ø 200, Ø 250			DNXK 12 R	BX 0515	LH 040

■ Identification Details

DNX F 12 080 R S

Cutter type	Fine pitch	Insert size	Diam.	Cutting direction	Shell type

● = Euro stock
○ = Japan stock

❑ = Delivery on request

N·m Recommended Tightening Torque (N·m)

DNX / DNXF Type

Features

- Small inserts with 8 cutting edges
- Economic by double-side usage
- Excellent grade for cast iron machining
- Optimised geometry for best results in cast iron
- Special inserts for steel machining

Insert

Application	Coated Carbide					
High Speed/Light cut			K	K		
General Purpose	PM	PM	K	K		
Roughing	PM	PM			K	
Cat. No.	ACP200	ACP300	ACK100	ACK200	ACK300	Fig.
SNMT 1205 ZNEN-G	●		❍	●	❍	1
1205 ZNEN-H	●		❍	●	●	2
1205 ZNEN-SH	●	❑	●	●	●	3

Fig. 1 **G** Type



Fig. 2 **H** Type



Fig. 3 **SH** Type



G Type : For general purpose
H Type : For heavy machining
SH Type : For steel machining

- Negative inserts
- Inserts with 8 cutting edges
- Applicable for steel machining

Advantage of SH-Type when Steel machining

G Type

Chip packing causes higher cutting forces !

SH Type

Smooth chip evacuation reduces cutting forces !

Recommended Cutting Conditions

(v_c = m/min, f_t = mm/tooth) (min.– **optimum** – max.)

ISO	Work Material	Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/tooth)	Insert Grade
P	Carbon steel	180–280	150–**175**–200	0,10–**0,15**–0,20	ACP200
	Alloy steel	180–280	150–**175**–200	0,10–**0,15**–0,20	ACP200
K	Grey cast iron (GG)	250	150–**225**–300	0,10–**0,20**–0,30	ACK200/ACK300
	Ductile cast iron (GGG)	250	150–**225**–250	0,10–**0,18**–0,25	ACK200/ACK300

Wave Radius Mill
WRCX Type

High Durable Mill with Polygon Inserts

Grades for Steels, Cast Iron and Aluminium

Features

The "Wave Mill" WRCX type is a new multi purpose milling cutter for face milling, slotting, helical boring, plunging and profiling. Its unique design features 16 corner polygon inserts and a durable cutter body manufactured from high tensile alloyed steel protected by a hard surface treatment. Insert rigidity is maximised via close tolerance seat pockets and centre clamped using a torxscrew . Choose from a variety of insert grades such as our award winning Diamond like Carbon DL 1000 capable of high feed machining aluminium, our uncoated H1 grade suitable for non-ferrous metals or our new ACP/ACK grades for steels and irons.

Advantages

- Durable cutter body – Special alloyed steel with hard surface.
- High feed cutting – Optimised pitch and high number of cutting edges
- Excellent chip removal – Wide pocket and integral coolant hole
- Maximum rigidity – Rigid clamping of inserts with TORXPLUS screw
- Wide application range – Carbon steels, alloy steels, stainless steels, high temperature alloys, diemould steels, aluminiums, non-ferrous metals etc

Insert

Application	Coated Carbide					Uncoated Carbide	Diamond Coated	Dimensions (mm)			Fig.	Applicable Endmill
								IC	RE	S		
High Speed / Light cut	P			K		K N	N					
General Purpose		P M	P M	K			N					
Roughing		P M	P M		K							
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	H1	DL1000					
QPMT 120440 PPEN	●	●	●	●	●			12	4,0	4,76	1	WRCX/-F 12000 RS
120440 PPEN-H	●	●	●	●	●							
QPET 120460 PPFR-S						●	●		6,0		2	WRCX/-F/-X 16000 RS
QPMT 160660 PPEN	●	●	●	●	●			16	6,0	6,5	1	
160660 PPEN-H	●	●	●	●	●							
QPET 160680 PPFR-S						●	●		8,0		2	WRCXF 20000 RS
QPMT 200670 PPEN	●	●	●	●	●			20	7,0	6,5	1	
200670 PPEN-H	●	●	●	●	●							

Fig. 1



Fig. 2



QPMT... : Standard 16 cornered polygon type
QPMT...-H: Stronger cutting edge type

QPET...-S: Polished round insert for non-ferrous material

● Anti-Vibration Type (Paired Sets for Vibration Free Machining)

Application	Coated Carbide					Uncoated Carbide	Diamond Coated	Dimensions (mm)			Fig.	Applicable Endmill
								IC	RE	S		
High Speed / Light cut	P			K		K N	N					
General Purpose		P M	P M	K			N					
Roughing		P M	P M		K							
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	H1	DL1000					
QPMT 160608 PPEN	●	●	●	●	●			16	0,8	6,5	1	WRCX/-F/-X 16000 RS
160608 PPEN-CP	●	●	●	●	●						3	
QPMT 200608 PPEN	●	●	●	●	●			20	0,8	6,5	1	WRCXF 20000 RS
200608 PPEN-CP	●	●	●	●	●						3	

Fig. 1
08



Fig.3
CP



The combination of different inserts in a staggered formation varies the cut depth and eliminates vibration when feed rate is

$f_t < 0,15$ (IC = 16 mm)
or
$f_t < 0,2$ (IC = 20 mm).



● Chip Formation

Anti-vibration Type	Standard Type
	

Work Material:	50C
Cutting Data:	f_t = 0,1mm/tooth, a_p = 7 mm
Insert Size:	IC = 20 mm

Milling Cutters

● = Euro stock
❑ = Delivery on request

Recommended Tightening Torque (N·m)

Fig. 1



Fig. 2



Fig. 3

Axial rake angle: - 3°
Radial rake angle: 0°



■ Body

* Note Fig.3 for DCX=160 : Coolant cap (CCAP-160) with 4 screws (BX0620) and wrench (TH050) is available seperately.

● Standard WRCX Type

Cat. No.	Stock	Dimensions (mm)											No. of Teeth	Helical Boring øB Standard	Ramping αmax.	Weight (Kg)	Fig.
		DCX*	DC	BD	DCSFMS	LF*	KWW	KDP	DCB	D2	D1	CBDP					
WRCX 12040 RS	●	40	28	36	36	40	8,4	5,6	16	9	14	18	4	68 ± 11	10°	0,2	1
12050 RS	●	50	38	46	40	40	10,4	6,3	22	11	18	20	4	88 ± 11	7°	0,3	1
12052 RS	●	52	40	48	40	40	10,4	6,3	22	11	18	20	5	92 ± 11	6°30'	0,3	1
12063 RS	●	63	51	59	40	40	10,4	6,3	22	11	18	20	5	114 ± 11	5°	0,4	1
12080 RS	●	80	68	76	55	50	12,4	7,0	27	13,5	20	25	6	148 ± 11	3°30'	0,9	1
WRCX 16063 RS	●	63	47	50	50	40	10,4	6,3	22	11	18	20	3	110 ± 15	8°	0,4	1
16080 RS	●	80	64	70	55	50	12,4	7,0	27	13,5	20	25	4	144 ± 15	5°30'	0,8	1
WRCX 16100 RS	●	100	84	90	70	50	14,4	8,5	32	-	46	32	5	184 ± 15	4°	1,3	2
16125 RS	❑	125	109	115	80	63	16,4	9,5	40	-	52	38	5	234 ± 15	3°	2,4	2

● Fine Pitch WRCXF Type

Cat. No.	Stock	Dimensions (mm)											No. of Teeth	Helical Boring øB Standard	Ramping αmax.	Weight (Kg)	Fig.
		DCX*	DC	BD	DCSFMS	LF*	KWW	KDP	DCB	D2	D1	CBDP					
WRCXF 12050 RS	❑	50	38	46	40	40	10,4	6,3	22	11	18	20	5	88 ± 11	7°	0,3	1
12063 RS	❑	63	51	59	40	40	10,4	6,3	22	11	18	20	6	114 ± 11	5°	0,4	1
WRCXF 16052 RS	●	52	36	45	45	40	10,4	6,3	22	11	17,7	20	4	88 ± 15	10°	0,3	1
16063 RS	●	63	47	50	50	40	10,4	6,3	22	11	18	20	4	110 ± 15	8°	0,4	1
16080 RS	●	80	64	70	55	50	12,4	7,0	27	13,5	20	25	5	144 ± 15	5°30'	0,8	1
WRCXF 16100 RS	●	100	84	90	70	50	14,4	8,5	32	-	46	32	6	184 ± 15	4°	1,3	2
16125 RS	●	125	109	115	80	63	16,4	9,5	40	29	52	29	6	234 ± 15	3°	2,4	1
16160 RS	●	160	144	150	100	63	16,4	9,5	40	-	93	29	8	304 ± 15	2°	4,0	3*
WRCXF 20080 RS	●	80	60	68	55	50	12,4	7,0	27	13,5	20	25	5	140 ± 18	7°	0,7	1
WRCXF 20100 RS	●	100	80	88	70	50	14,4	8,5	32	-	46	32	6	180 ± 18	5°	1,1	2
20125 RS	●	125	105	113	80	63	16,4	9,5	40	29	52	29	6	230 ± 18	3°30'	2,3	1
20160 RS	●	160	140	148	100	63	16,4	9,5	40	-	93	29	8	300 ± 18	2°30'	3,9	3*

● Extra Fine Pitch WRCXX Type

Cat. No.	Stock	Dimensions (mm)											No. of Teeth	Helical Boring øB Standard	Ramping αmax.	Weight (Kg)	Fig.
		DCX*	DC	BD	DCSFMS	LF*	KWW	KDP	DCB	D2	D1	CBDP					
WRCXX 16080 RS	●	80	64	70	55	50	12,4	7,0	27	13,5	20	25	6	144 ± 15	5°30'	0,8	1
16100 RS	●	100	84	90	70	50	14,4	8,5	32	-	46	32	7	184 ± 15	4°	1,3	2

* Note : When using CP type anti-vibration inserts / IC = 16, please change above dimensions: DCX* +0,3 & LF* +0,15 mm
In case of anti-vibration inserts / IC = 20, please change above dimensions: DCX* +0,4 & LF* +0,2 mm



■ Maximum Rotation (min^{-1}) for Non-ferrous cutting when using QPET Insert

Cutter DC (mm)	Insert Cat. No.		
	QPET**10**...**S**	QPET**12**...**S**	QPET**16**...**S**
25	28.000		
32	25.000		
40		22.000	15.000
50		20.000	14.000
63		18.000	13.000
80		16.000	12.000
100			10.000
125			9.000
160			8.000

Ramping (Slant Milling)



α max : (see tables)

Helical Boring

øB Standard : (see tables)



■ Spare Parts

Cutter		Screw		Screw
			N·m	
WRCX	12○○○	BFTX 0409 IP	3,0	TRDR 15 IP
WRCX/-F/-X	16052–16100	BFTX 0511 IP	5,0	TRDR 20 IP
	16125–16160	BFTX 0513 IP	5,0	
WRCX/-F	20○○○	BFTX 0615 IP	5,0	TRDR 25 IP

■ Recommended Cutting Conditions

DCX (mm) \ Material / Grade		Carbon steel (ex. C40 ~ C50)	Alloy steel (Below HRC40)	Stainless steel (ex. X10CrNiS18-9)	Cast iron (ex. GG20)	Non-ferrous material
		ACP100, ACP200	ACP100, ACP200	ACP200, ACP300	ACK200, ACK300	DL1000, H1
40 ~ 80	v_c	100–**160**–200	100–**140**–180	80–**120**–160	80–**120**–160	200–**500**–1000
	f_t	0,2–**0,4**–0,6	0,2–**0,3**–0,4	0,1–**0,2**–0,3	0,1–**0,2**–0,4	0,1–**0,3**–0,4
100 ~ 160	v_c	150–**200**–250	100–**160**–200	160–**180**–200	100–**150**–200	200–**500**–1000
	f_t	0,3–**0,4**–0,6	0,1–**0,3**–0,5	0,15–**0,2**–0,3	0,1–**0,15**–0,2	0,2–**0,3**–0,6

[v_c = m/min, f_t = mm/tooth] [min.– optimum – max.]

☞ H52

Features

The Wave Radius Mill RSX Series enables stable machining even when using equipment with low clamp rigidity thanks to its body design achieving excellent cutting performance and rigidity.
In addition to the ACM Series for stainless steel and exotic alloys two grades have been added:
ACP200 grade for steel machining and
ACK300 grade for cast iron machining.
Handle an even wider range of milling needs with the RSX(F)08000 and RSX(F)20000 types.

Characteristics

Smooth cutting action and low vibration machining provided based on the high rake angle design and high rigidity body.
High reliability achieved with ACM100/ACM200/ACM300 adopted for exotic alloy machining.
ACP200 for steel and ACK300 for cast iron enable stable machining in a wide range of applications.

Series

Image	Series	Insert Size	Cat. No.	External Diameter (mm)											
				Ø 20	Ø 25	Ø 32	Ø 40	Ø 50	Ø 52	Ø 63	Ø 66	Ø 80	Ø 100	Ø 125	Ø 160
Shank Type  ☞ H54	Standard	08	RSX 08000 ES	●	●										
		10	10000 ES		●	●									
		12	12000 ES			●									
	Fine Pitch	08	RSXF 08000 ES	●	●										
		10	10000 ES		●	●									
		12	12000 ES			●									
Shell Type 	Standard	10	RSX 10000 RS				●	●	●						
		12	12000 RS				●	●	●	●	●	●	●		
		16	16000 RS							●		●	●	●	
		20	20000 RS									●	●	●	●
	Fine Pitch	10	RSXF 10000 RS				●	●	●						
		12	12000 RS				●	●	●	●	●	●	●		
		16	16000 RS							●		●	●	●	❑
		20	20000 RS									●	●	●	●
Modular Type  ☞ H55	Standard	08	RSX 08000 M	●	●	●									
		10	10000 M		●	●									
		12	12000 M			●	●								
	Fine Pitch	08	RSXF 08000 M	●	●	●									
		10	10000 M		●	●									
		12	12000 M			●	●								

Cutting Performance

Tool Life Comparison (Fracture Resistance)



Cutting Resistance Comparison



Work Material: X5CrNiS1810
Tool: Ø 50
Cutting Data: v_c = 200m/min, f_t = 0,5mm/t, a_p = 2,0mm, a_e= 10,0mm, Wet

Cutting Vibration Comparison



● = Euro stock
❑ = Delivery on request

Low Cutting Resistance, Less Vibration

Low cutting resistance and low vibration machining have been achieved with super high rake angle design + high rigidity body.



High Operability

Ease of corner control has been achieved with the adoption of a unique positioning mechanism that is highly precise and highly operable.



Insert size of 12 and 16 mm uses a maximum of 8 corners and an insert size of 10 mm uses a maximum of 4 corners.

Stable and Long Tool Life



A long life ensured with the adoption of the ACM series and significant improvements have been made in processing exotic alloy and stainless steel machining.

ACM100/ACM300



ACM200



New Super ZX Coat

The product series with a coating film hardness approximately 40 % higher and an oxidation onset temperature 200 °C higher than conventional products.
Enables machining at least 1,5 times faster and more efficiently than conventional products.
A product life at least twice as long as that of conventional products achieved under the same machining conditions.

Super FF Coat

Smooth coating surface provides excellent adhesion and chipping resistance.
Improved coating adhesion strength.
Harder than conventional coatings with hugh improvements in wear resistance.
High speed, high effiency machining of more than 1,5 times than of conventional grades possible.
Achieving more than double the tool life of conventional grades under the same cutting conditions.

Milling of steel, stainless steel, cast iron and exotic alloys

Rake Angle		
	Radial	–5°
	Axial	10°

5 mm (10000RS) | 6 mm (12000RS) | 8 mm (16000RS) | 10 mm (20000RS)

Body – Dimensions

Fig. 1



Fig. 2



Fig. 3



Body

● RSX...RS, Standard

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Fig.
		DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
RSX 10040 RS	●	40	34	40	16	8,4	5,6	18	14	9	4	0,2	1
10050 RS	●	50	40	40	22	10,4	6,3	20	18	11	5	0,3	1
10052 RS	●	52	40	40	22	10,4	6,3	20	18	11	5	0,4	1
RSX 12040 RS	●	40	32	40	16	8,4	5,6	18	13,5	9	3	0,2	1
12050 RS	●	50	40	40	22	10,4	6,3	20	18	11	4	0,3	1
12052 RS	●	52	40	40	22	10,4	6,3	20	18	11	4	0,3	1
12063 RS	●	63	40	40	22	10,4	6,3	20	18	11	5	0,4	1
12066 RS	●	66	55	50	27	12,4	7,0	25	20	14	6	0,7	1
12080 RS	●	80	55	50	27	12,4	7,0	25	20	14	6	1,0	1
RSX 12100 RS	●	100	70	50	32	14,4	8,5	32	46	-	6	1,4	2
RSX 16063 RS	●	63	50	40	22	10,4	6,3	20	18	11	4	0,5	1
16080 RS	●	80	55	50	27	12,4	7,0	25	20	14	5	0,9	1
RSX 16100 RS	●	100	70	50	32	14,4	8,5	32	46	-	6	1,3	2
16125 RS	●	125	80	63	40	16,4	9,5	29	52	29	6	2,6	1
RSX 20080 RS	●	80	55	50	27	12,4	7,0	22	20	14	4	0,9	1
RSX 20100 RS	●	100	70	63	32	14,4	8,0	32	46	-	5	1,8	2
20125 RS	●	125	80	63	40	16,4	9,0	29	52	29	6	2,6	1
20160 RS	●	160	130	63	40	16,4	9,0	29	90	-	7	4,7	3

● RSXF...RS, Fine Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Fig.
		DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
RSXF 10040 RS	●	40	34	40	16	8,4	5,6	18	14	9	5	0,2	1
10050 RS	●	50	40	40	22	10,4	6,3	20	18	11	6	0,3	1
10052 RS	●	52	40	40	22	10,4	6,3	20	18	11	6	0,3	1
RSXF 12040 RS	●	40	32	40	16	8,4	5,6	18	13,5	9	4	0,2	1
12050 RS	●	50	40	40	22	10,4	6,3	20	18	11	5	0,3	1
12052 RS	●	52	40	40	22	10,4	6,3	20	18	11	5	0,3	1
12063 RS	●	63	40	40	22	10,4	6,3	20	18	11	6	0,4	1
12066 RS	●	66	55	50	27	12,4	7,0	25	20	14	7	0,7	1
12080 RS	●	80	55	50	27	12,4	7,0	25	20	14	7	0,9	1
RSXF 12100 RS	●	100	70	50	32	14,4	8,5	32	46	-	10	1,3	2
RSXF 16063 RS	●	63	50	40	22	10,4	6,3	20	18	11	5	0,4	1
16080 RS	●	80	55	50	27	12,4	7,0	25	20	14	6	0,8	1
RSXF 16100 RS	●	100	70	50	32	14,4	8,5	32	46	-	7	1,3	2
16125 RS	●	125	80	63	40	16,4	9,5	29	52	29	8	2,5	1
16160 RS	❑	160	130	63	40	16,4	9,5	29	88	-	10	4,8	3
RSXF 20080 RS	●	80	55	50	27	12,4	7,0	22	20	14	5	0,9	1
RSXF 20100 RS	●	100	70	50	32	14,4	8,0	32	46	-	6	1,8	2
20125RS	●	125	80	63	40	16,4	9,0	29	52	29	7	2,6	1
20160RS	●	160	130	63	40	16,4	9,0	29	90	-	9	4,6	3

Identification Details

RSX	F	12	040	R	S
Cutter Series	Fine Pitch Type	Insert Size	Cutter Diameter	Cutting Direction	Metric

● = Euro stock
○ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

Various Machining Use

Various types of processing, such as mould engraving, slant milling and helical processing.

Helical Milling



Ramping



Recommended Values for Helical and Ramping

Insert Cat. No.	Helical				Taper
	Cutter ØDC	Work Diameter			Ramping Angle α°(max)
		Min.	Optimal Ø	Max.	
RDET10...	25	33,0	40	49	10°30'
	32	46,0	54	63	6°45'
	40	62,0	70	79	4°30'
	50	82,0	90	99	3°15'
	52	86,0	94	103	3°10'
RDET12...	32	41,5	52	63	12°30'
	40	57,5	68	79	8°00'
	50	77,5	88	99	5°30'
	52	81,5	92	103	5°15'
	63	103,5	114	125	4°00'
	66	109,5	120	131	3°45'
	80	137,5	148	159	2°50'
	100	177,5	188	199	2°10'
RDET16...	63	96,0	110	125	6°00'
	80	130,0	144	159	4°10'
	100	170,0	184	199	3°00'
	125	220,0	234	249	2°20'
RDET20...	80	122,0	140	159	4°15'
	100	162,0	180	199	3°00'
	125	212,0	230	249	2°00'
	160	282,0	300	319	1°15'

Inserts

Application	Grade				
High Speed/Light Cut			MS	MS	
General Purpose	PM		MS	MS	MS
Roughing	PM	K			MS

Cat. No.	ACP200	ACK300	ACM100	ACM200	ACM300	Dimens. ød (IC)	Dimens. S	Applicable Cutters
RDET 10T3M0EN G	●	●	●	●	●	10	3,97	RSX(F) 10000RS
10T3M0EN H	●	●	●	●	●	10	3,97	
RDET 1204M0EN G	●	●	●	●	●	12	4,76	RSX(F) 12000RS
1204M0EN H	●	●	●	●	●	12	4,76	
RDET 1606M0EN G	●	●	●	●	●	16	6,5	RSX(F) 16000RS
1606M0EN H	●	●	●	●	●	16	6,5	
RDET 2006M0EN G	●	●	●	●	●	20	6,5	RSX(F) 20000RS
2006M0EN H	❍	●	●	●	●	20	6,5	



Cutting Edge Cross Section

G - Type **H** - Type

M0: IC is metric

Spare Parts

Applicable Cutters	Wrench	Screw	
			N·m
RSX(F) 10000RS	TRDR15IP	BFTX03584IP	**3,0**
RSX(F) 12000RS		BFTX0409IP	**3,0**
RSX(F) 16000RS	TRDR20IP	BFTX0511IP	**5,0**
RSX(F) 20000RS	TRDR25IP	BFTX0615IP	**5,0**

Recommended Cutting Conditions

Min.-**Optimum**-Max.

ISO	Work Material			Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/t)	Grade
P	Carbon Steel			180–280	100–**160**–200	0,20–**0,40**–0,60	ACP200
	Alloy Steel			180–280	100–**140**–180	0,20–**0,30**–0,40	ACP200
M	Stain-less Steel	Cr Based	Ferritic	200	150–**180**–200	0,15–**0,25**–0,35	ACM300
			Martensitic	200–330	80–**120**–180	0,15–**0,25**–0,35	ACM300
		Cr-Ni Based	Austenitic	200	150–**180**–200	0,15–**0,25**–0,35	ACM300
			Austenitic, ferritic	230–270	80–**120**–180	0,15–**0,25**–0,35	ACM200
			Precipitation hardening	330	60–**100**–160	0,15–**0,25**–0,35	ACM200
K	Cast Iron			250	80–**120**–160	0,10–**0,30**–0,40	ACK300
S	Heat resistant alloy		Ni based material	250–350	20–**30**–40	0,10–**0,20**–0,30	ACM100 ACM200
	Titanium		Pure Titanium	(Rm 400)	60–**80**–100	0,10–**0,20**–0,30	
			$\alpha + \beta$ alloy system	(Rm 1050)	40–**50**–60	0,10–**0,20**–0,30	

DFC Type

General Features

The Sumi Dual Mill DFC type employs cost effective double-sided inserts for high toughness and enhanced accuracy.
The double-side inserts are flexible and reduces costs.

Large Line-up

- Diameter from Ø 25 mm to Ø 200 mm
- Available as standard, fine and extra-fine pitch
- Bore diameter: metric
- Insert geometry: L, G, H

Cutter Body

Type		Cat. No.	Diameter (mm)	No. of Teeth	Image
Shank ☞ H14	Standard Pitch	DFC 09000 E	Ø 25–Ø 80	2–5	
	Medium Pitch	DFCM 09000 E	Ø 32–Ø 80	3–7	
Shell	Standard Pitch	DCF 09000 RS	Ø 50–Ø 200	4–8	
	Medium Pitch	DFCM 09000 RS	Ø 50–Ø 200	5–12	
	Fine Pitch	DFCF 09000 RS	Ø 50–Ø 200	6–16	

90 Degree Accuracy

Work material: Carbon steel

Cutting conditions:
v_c = 200 m/min, f_t = 0.1 mm/t
a_e = 5.0 mm, a_p = 5.0 mm x 3 passes



Shell type: ø 63 mm



Number of passes (1 pass = 0.30 mm)

Suitable Applications

Face milling

Shoulder milling



Slot milling



Side face milling



● = Euro stock

■ New Insert Design Provides Excellent Machining Accuracy

- The new insert design separates the location area and cutting edge producing an optimized solution.
- Machining accuracy is comparable to single sided inserts provided the DOC is less than 3 mm.
- The SEC-Sumi Dual Mill design, equips the user with a highly stable cutter for high feed machining applications.

● Chipbreaker Selection Map



● Inserts

Cat. No.	RE0,4	RE0,8	RE1,2	RE1,6
XNMU0606__PNER-L	●	●	●	●
XNMU0606__PNER-G	●	●	●	●
XNMU0606__PNER-H	●	●	●	●

Work Material	Steel, Cast Iron		
Chipbreaker	L type	G type	H type
			
Feature	Low cutting force	General purpose	Strong edge
Cutting edge geometry			
Application	Light cut, low rigidity milling and reduced burrs	Main breaker for general purpose applications	Roughing, heavy interrupted and hardness steel milling

■ Stable and High Cutting Performance Combined with High Toughness

- The excellent cutter performance offers efficient machining, enables high feed rate capability.
- The new insert construction provides extremely accurate edge to edge indexing whilst the location area offers high security and stability.



DFC(M/F) 09000RS Type

Body – Shell type

Rake Angle		
	Radial	–9°
	Axial	–5°

Max. a_p: 6 mm

Fig.1



Fig.2



Fig.3



■ Body – Dimensions

● Sumi Dual Mill DFC type, Standard Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
DFC 09050RS	●	50	41	40	22	10,4	6,3	20	18	11	4	0,3	1
09063RS	●	63	50	40	22	10,4	6,3	20	18	11	4	0,5	1
09080RS	●	80	55	50	27	12,4	7	22	20	14	5	1,0	1
DFC 09100RS	●	100	70	50	32	14,4	8	26	46	-	6	1,4	2
09125RS	●	125	80	63	40	16,4	9	29	52	29	7	2,8	1
09160RS	●	160	130	63	40	16,4	9	29	90	-	8	4,6	3
DFC 09200RS	❑	200	150	63	60	25,7	14	35	135	-	10	5,7	

● Sumi Dual Mill DFC type, Medium Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
DFCM 09050RS	●	50	41	40	22	10,4	6,3	20	18	11	5	0,3	1
09063RS	●	63	50	40	22	10,4	6,3	20	18	11	6	0,5	1
09080RS	●	80	55	50	27	12,4	7	22	20	14	7	0,9	1
DFCM 09100RS	●	100	70	50	32	14,4	8	26	46	-	8	1,4	2
09125RS	●	125	80	63	40	16,4	9	29	52	29	11	2,7	1
09160RS	●	160	130	63	40	16,4	9	29	90	-	12	4,5	3
DFCM 09200RS	❑	200	150	63	60	25,7	14	35	135	-	16	5,6	

● Sumi Dual Mill DFC type, Fine Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
DFCF 09050RS	●	50	41	40	22	10,4	6,3	20	18	11	6	0,3	1
09063RS	●	63	50	40	22	10,4	6,3	20	18	11	7	0,5	1
09080RS	●	80	55	50	27	12,4	7	22	20	14	9	0,9	1
DFCF 09100RS	●	100	70	50	32	14,4	8	26	46	-	11	1,3	2
09125RS	●	125	80	63	40	16,4	9	29	52	29	14	2,6	1
09160RS	●	160	130	63	40	16,4	9	29	90	-	16	4,6	3
DFCF 09200RS	❑	200	150	63	60	25,7	14	35	135	-	20	5,5	

■ Identification Details

DFC	M	09	050	R	S
Cutter Series	M: Medium F: Fine	Insert Size	Cutter Diameter	Direction	Metric

■ Spare Parts

Screw		Wrench
		
BFTX03512IP	5,0	TRDR15IP

● = Euro stock
❑ = Delivery on request

Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide								
High Speed / Light Cutting	PM			K		MS		P	Steel
General Purpose Cutting		PM	PM	K		MS	MS	M	Stainless Steel
Rough Cutting		PM	PM		K		MS	K	Cast Iron
								S	Exotic Alloy
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	Radius RE	
XNMU 060604 PNER-L		●	●		●		●	0,4	
060608 PNER-L		●	●		●		●	0,8	
XNMU 060604 PNER-G	●	●	●	●	●	●	●	0,4	
060608 PNER-G	●	●	●	●	●	●	●	0,8	
060612 PNER-G	●	●	●	●	●	●	●	1,2	
060616 PNER-G	●	●	●	●	●	●	●	1,6	
XNMU 060608 PNER-H	●	●	●	●	●	●	●	0,8	
060612 PNER-H	●	●	●	●	●	●	●	1,2	
060616 PNER-H	●	●	●	●	●	●	●	1,6	



Recommemded Cutting Conditions

ISO	Work-material	Hardness (HB)	Cutting Speed (m/min) Min. - Optimum - Max.	Feed Rate Min. - Optimum - Max.	Depth of Cut (mm)	Grade
P	General Steel	180–280	150–**200**–250	0,10–**0,20**–0,30	< 6	ACP200 ACP300
	Soft Steel	≤ 180	180–**250**–350	0,15–**0,25**–0,35	< 6	ACP200 ACP300
	Die Steel	200–220	100–**150**–200	0,10–**0,18**–0,25	< 4	ACP200 ACP300
M	Stainless Steel	-	160–**205**–250	0,12–**0,18**–0,25	< 6	ACM200 ACM300
K	Cast Iron	250	100–**175**–250	0,10–**0,20**–0,30	< 6	ACK200 ACK300

Application Examples

Work piece		Sumitomo	Comp.
Workpiece material: Steel (HRB 269-330)	Breaker	G	
	Grade	ACP200	
	v_c (m/min)	226	200
	v_f (mm/min)	1260	
	f_t (mm/t)	0,28	0,2
	a_p (mm)	2	2
	a_e (mm)	5	5
	Dry or Wet	Wet	Wet
	Tool diam. Ø	80	
	No. of Teeth	5	
	Result	Efficiency: 158 % achieved	
	Evaluation	Wear resistance, efficiency	

Work piece		Sumitomo	Comp.
Workpiece material: S235 (Carbon steel) Face milling	Breaker	G	
	Grade	ACP200	
	v_c (m/min)	180	180
	v_f (mm/min)	1092	910
	f_t (mm/t)	0,3	0,2
	a_p (mm)	2 x 2 mm	2 x 2 mm
	a_e (mm)	50	50
	Dry or Wet	Dry	Dry
	Tool diam. Ø	63 mm	63 mm
	No. of Teeth	4	5
	Result	Efficiency: 120 % achieved	
	Evaluation	Wear resistance, efficiency	

Work piece		Sumitomo	Comp.
Workpiece material: Cast Iron	Breaker	G	
	Grade	ACP200	
	v_c (m/min)	156	156
	v_f (mm/min)	536	404
	f_t (mm/t)	0,17	0,09
	a_p (mm)	2,2	2,2
	a_e (mm)	63,5	63,5
	Dry or Wet	Dry	Dry
	Tool diam. Ø	80 mm	80 mm
	No. of Teeth	5	7
	Result	Efficiency: 133 % achieved Tool life: 138 % achieved	
	Evaluation	Efficiency, tool life	



Work piece		Sumitomo	Comp.
Workpiece material: Cr-Mo alloy	Breaker	G	
	Grade	ACP200	
	v_c (m/min)	200	200
	v_f (mm/min)	838	838
	f_t (mm/t)	0,2	0,13
	a_p (mm)	6	6
	a_e (mm)	43	43
	Dry or Wet	Dry	Dry
	Tool diam. Ø	80 mm	80 mm
	No. of Teeth	5	8
	Result	Efficiency: 120 % achieved	
	Evaluation	Efficiency	



WFX Type

General Features

Wave Mill WFX type for shoulder milling is a screw-locking type cutter capable of using four corners.
Ideal cutting edge design delivers good squareness.
Series expansion with the high-feed **WFXH** type and the **WFXC** type for chamfering.
A comprehensive lineup that covers a wide variety of applications.



Characteristics

The insert shape, optimized for shoulder milling and combined with a high-precision body, leaves a superior machined surface finish.

● Max. Depth of Cut



WFX08000 type　　WFX12000 type

● Optimized Edge Shape



① The convex shape ensures the cutting edge strength.

② The flat shape minimises differences in step levels.



③ The wiper edge function improves the surface roughness.

Product Range

Application	Type	Cat. No.	No. of Teeth	Cutter Diameter (mm)	Shape
Shoulder Milling	Shell Type	WFX 08000 RS	3 - 8	40–1 00	
		WFXM 08000 RS	4 - 10	40–100	
		WFXF 08000 RS	6 - 12	40–100	
		WFX 08000 R	6 - 8	80–100	
		WFXM 08000 R	8 - 10	80–100	
		WFXF 08000 R	10 - 12	80–100	
		WFX 12000 RS	3 - 5	60–100	
		WFXF 12000 RS	4 - 7	60–100	
		WFX 12000 R	4 - 12	80–250	
		WFXF 12000 R	6 - 18	80–250	
	Endmill Type	WFX 08000 E	2 - 5	20–63	
		WFXM 08000 E	3 - 6	25–63	
		WFX 12000 E	3 - 4	40–80	
		WFXF 12000 E	4 - 6	60–80	
	Modular Type	WFX 08000 M	2 - 3	20–40	
High Efficiency	Shell Type	WFXH 08000 RS	4 - 6	40–63	
		WFXH 12000 RS	4 - 5	60– 63	
	Modular Type	WFXH 08000 M	2 - 3	25–32	
		WFXH 12000 M	3	40	
Chamfering	Endmill Type	WFXC 08000 E	1 - 2	8–16	
		WFXC 12000 E	3	25–32	
	Modular Type	WFXC 08000 M	2	16	
		WFXC 12000 M	3	25–32	

☞H16/17

Inserts

Cat. No.	RE0,2	RE0,4	RE0,8	RE1,2	RE1,6
SOMT 0803_ _PZER-L		●	●		
0803_ _PZER-G		●	●	●	
0803_ _PZER-H			●	●	
SOET 0803_ _PZER-G		●	●	●	
0803_ _PZFR-S	●	●	●		
SOMT 1204_ _PDER-L			●		
1204_ _PDER-G		●	●	●	●
1204_ _PDER-H			●		
SOET 1204_ _PDFR-S			●		

WFX08000 type insert (General Purpose G type chipbreaker)

WFX12000 type insert (General Purpose G type chipbreaker)

● = Euro stock

Cutting Performance

Squareness of Machined Shoulder





Work Material:	C50
Tool:	WFX12100RS (Ø 100 mm x 5 teeth)
Cutting Conditions:	v_c = 200m/min, a_p = 8,0 mm x 3 times
	f_t = 0,15mm/t, a_e = 20 mm

Grade Selection

ISO	Grade	Finishing to Light Cutting	Medium Cut	Rough to Heavy Cutting
P	Coated Carbide	ACP100	ACP200	ACP300
M S	Coated Carbide	ACM200		ACM300

ISO	Grade	Finishing to Light Cutting	Medium Cut	Rough to Heavy Cutting
K	Coated Carbide	ACK200	ACK300	
N	Coated Carbide	DL1000		
N	Carbide	H1		

CVD PVD

Chipbreaker Selection



Work Material	P K Steel, Cast Iron				N Aluminium Alloy
	L Type	**G Type**	**H Type**	**Wiper Type**	**S Type**
Breaker					
Characteristic	Low Cutting Force	General Purpose	Strong Edge	Wiper Edge	Sharp Edge
Cutting Edge Figure					
Work Material-Application	Light Cutting Low rigidity Milling Low-Burr Design	**Main Chipbreaker** General to Interrupted Milling	Heavy Cut Heavy Interrupted Machining Tempered Steel	Precision Finishing	Non-Ferrous Metal

Wiper Insert

Optimised wiper edge shape provides superior surface roughness.





Wiper inserts are single-cornered.
Attach the wiper insert so that the chamfered corner is in location ① shown in the figure.
Be sure to use the corner with the ID mark (② in the figure).
(08 size inserts have no marks)

WFX(M/F) 08000 RS

Shoulder Milling for Steel, Stainless Steel,
Die Steel, Cast Iron, Non-Ferrous Metal, Exotic Alloy

Body - Shell Type

Rake Angle		
Radial	–6°	6 mm
Axial	12°	90°

WFX08000RS

WFXM08000RS

WFXF08000RS

Fig. 1



Fig. 2



Body - WFX, Standard Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Figure
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
WFX 08040 RS	●	40	33	40	16	8,4	5,6	18	14	9	3	0,2	1
08050 RS	●	50	41	40	22	10,4	6,3	20	18	11	4	0,3	1
08063 RS	●	63	50	40	22	10,4	6,3	20	18	11	5	0,6	1
08080 RS	●	80*	55	50	27	12,4	7,0	25	20	14	6	1,0	1
WFX 08100 RS	●	100*	70	50	32	14,4	8,0	32	46	-	8	1,4	2

Body - WFXM, Medium Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Figure
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
WFXM 08040 RS	●	40	33	40	16	8,4	5,6	18	14	9	4	0,2	1
08050 RS	●	50	41	40	22	10,4	6,3	20	18	11	5	0,3	1
08063 RS	●	63	50	40	22	10,4	6,3	20	18	11	6	0,5	1
08080 RS	●	80*	55	50	27	12,4	7,0	25	20	14	8	1,0	1
WFXM 08100 RS	●	100*	70	50	32	14,4	8,0	32	46	-	10	1,4	2

Body - WFXF, Fine Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Figure
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
WFXF 08040 RS	●	40	33	40	16	8,4	5,6	18	14	9	6	0,2	1
08050 RS	●	50	41	40	22	10,4	6,3	20	18	11	7	0,3	1
08063 RS	●	63	50	40	22	10,4	6,3	20	18	11	8	0,5	1
08080 RS	●	80*	55	50	27	12,4	7,0	25	20	14	10	0,9	1
WFXF 08100 RS	●	100*	70	50	32	14,4	8,0	32	46	-	12	1,4	2

Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø80: M12x30~35mm, Ø100: M16x40~45mm) for securing Ø80 / Ø100 cutter on the arbor.

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed	Feed Rate	DOC	Grades
P	General Steel	180–280	150–**200**–250	0,08–**0,12**–0,18	<6	ACP200 ACP300
P	Soft Steel	≤180	180–**250**–350	0,10–**0,15**–0,20	<6	ACP200 ACP300
P	Die Steel	200–220	100–**150**–200	0,08–**0,12**–0,18	<4	ACP200 ACP300
M	Stainless Steel	-	160–**200**–250	0,10–**0,15**–0,20	<6	ACM300
K	Cast Iron	250	100–**175**–250	0,10–**0,15**–0,20	<6	ACK200 ACK300
N	Non Ferrous Metal	-	300–**500**–1000	0,10–**0,15**–0,20	<6	H1 DL1000

Min. - **Optimum** - Max.

Identification Details

WFX	F	08	040	R	S
Cutter Series	M: Medium Pitch F: Fine Pitch	Insert Size	Cutter Diameter	Direction	Metric Type

Spare Parts

Screw		Wrench
		
BFTX0306IP	2,0	TRDR08IP

Inserts

Fig. 3



Fig. 4 Wiper Insert



Application	Coated Carbide							Carbide	DLC		
High Speed / Light cut	P			K		M S		K N	N		
General Purpose		P M	P M	K		M S	M S		N		
Roughing		P M	P M		K		M S				
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE	Fig.
SOMT 080304 PZER L	❍	❍	❍	❍	●	❍	❍	–	–	0,4	3
080308 PZER L	❍	❍	❍	❍	❍	❍	●	–	–	0,8	3
SOMT 080304 PZER G	❍	●	●	●	❍	❍	❍	–	–	0,4	3
080308 PZER G	❍	●	●	●	●	❍	●	–	–	0,8	3
080312 PZER G	❍	●	❍	❍	❍	❍	❍	–	–	1,2	3
SOMT 080308 PZER H	❍	●	●	❍	●	❍	❍	–	–	0,8	3
080312 PZER H	❍	❍	●	❍	❍	❍	❍	–	–	1,2	3
SOET 080304 PZER G	❍	❍	❍	❍	●	❍	❍	–	–	0,4	3
080308 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	0,8	3
080312 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	1,2	3
SOET 080302 PZFR S	–	–	–	–	–	–	–	●	●	0,2	3
080304 PZFR S	–	–	–	–	–	–	–	●	●	0,4	3
080308 PZFR S	–	–	–	–	–	–	–	●	●	0,8	3
XOEW 080308 PZTR W	–	–	–	–	❍	–	–	–	–	0,8	4

● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

"Wave Mill" Series
WFX(F) 12000 RS

Body - Shell Type

Rake Angle		
	Radial	–8°
	Axial	8°

10 mm, 90°

WFX 12000RS

WFXF12000RS

Fig. 1



Fig. 2



Fig. 3



Body - WFX, Standard Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Figure
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
WFX 12050 RS	●	50	40	40	22	10,4	6,3	20	18	11	3	0,2	1
12063 RS	●	63	50	40	22	10,4	6,3	20	18	11	4	0,4	1
12080 RS	●	80*	60	50	27	12,4	7,0	25	20	13,5	4	0,9	1
WFX 12100 RS	●	100*	70	50	32	14,4	8,5	32	46	-	5	1,3	2
12125 RS	●	125	90	63	40	16,4	9,5	29	52	-	6	2,7	2
12160 RS	●	160	130	63	40	16,4	9,5	29	88	-	8	4,8	3

Body - WFXF, Fine Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Figure
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
WFXF 12050 RS	●	50	40	40	22	10,4	6,3	20	18	11	4	0,2	1
12063 RS	●	63	50	40	22	10,4	6,3	20	18	11	5	0,4	1
12080 RS	●	80*	60	50	27	12,4	7,0	25	20	13,5	6	0,9	1
WFXF 12100 RS	●	100*	70	50	32	14,4	8,5	32	46	-	7	1,2	2
12125 RS	●	125	90	63	40	16,4	9,5	29	52	-	8	2,6	2
12160 RS	●	160	130	63	40	16,4	9,5	29	88	-	12	4,7	3

Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø80: M12x30~35mm, Ø100: M16x40~45mm) for securing Ø80 / Ø100 cutter on the arbor.
Cutters ≥ Ø160 do not have coolant holes.

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed	Feed Rate	DOC	Grades
P	General Steel	180–280	150–**200**–250	0,10–**0,15**–0,20	<10	ACP200 ACP300
P	Soft Steel	≤180	180–**250**–350	0,10–**0,15**–0,20	<10	ACP200 ACP300
P	Die Steel	200–220	100–**150**–200	0,10–**0,15**–0,20	<6	ACP200 ACP300
M	Stainless Steel	-	160–**200**–250	0,10–**0,15**–0,20	<10	ACM300
K	Cast Iron	250	100–**175**–250	0,10–**0,15**–0,20	<10	ACK200 ACK300
N	Non Ferrous Metal	-	300–**500**–1000	0,10–**0,15**–0,20	<10	H1 DL1000

Min. - **Optimum** - Max.

Identification Details

WFX	F	12	050	R	S
Cutter Series	F: Fine Pitch	Insert Size	Cutter Diameter	Direction	Metric Type

Inserts

Fig. 3



Fig. 4 Wiper Insert



Application	Coated Carbide							Carbide	DLC		
High Speed / Light cut	P			K		M S		K N	N		
General Purpose		P M	P M	K		M S	M S		N		
Roughing		P M	P M		K		M S				
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE	Fig.
SOMT 120408 PDER L	●	●	●	○	○	○	●	–	–	0,8	3
SOMT 120404 PDER G	○	○	●	○	●	○	●	–	–	0,4	3
120408 PDER G	●	●	●	●	○	●	●	–	–	0,8	3
120412 PDER G	○	○	○	○	○	○	●	–	–	1,2	3
120416 PDER G	○	●	○	○	○	○	○	–	–	1,6	3
SOMT 120408 PDER H	○	●	○	●	●	○	○	–	–	0,8	3
SOET 120408 PDFR S	–	–	–	–	–	–	–	●	●	0,8	3
XOEW 120408 PDTR W	–	–	–	–	○	–	–	–	–	–	4

Spare Parts

Shim	Shim Screw	Insert Screw		Insert Wrench	Wrench (Shim)
					
WFXS4R	BW0507F	BFTX03512IP	**3,0**	TRDR15IP	LH035



TSX Type

General Features

High-efficient and high precision tangential shoulder milling cutter with tangentially mounted carbide inserts.

Characteristics

- **Tough & Sharp cutting edge**
  Tangentially mounted carbide insert design and optimized edge geometry realize extremely tough and sharp cutting action.

- **Very accurate and excellent surface finish**
  Thanks to newly developed fine carbide press / sintering technology and very accurate grinding technics, very periphery ground inserts generate very accurate and excellent surface finish.

- **Wide product range**
  2 different insert size series, 3 chip breaker range and various carbide grade combination offers wide range of machining application.

Product Range

	Cat. No.	Series	Diameter Range / No of Teeth											Shape
			Ø16	Ø20	Ø25	Ø32	Ø40	Ø50	Ø63	Ø80	Ø100	Ø125	Ø160	
Shell Type	TSX 08000RS	Standard Pitch					4	5	6					
	TSXF 08000RS	Fine Pitch					6	8	10					
	TSX 13000RS	Standard Pitch					3	4	5	5	6	7	8	
	TSXM 13000RS	Medium Pitch					4	5	6	7	8	10	12	
Shank Type	TSX 08000E	Standard Pitch	2	2	3	3	4							
	TSXF 08000E	Fine Pitch		3	4	5	6							
	TSX 13000E	Standard Pitch			2	2	3	4						
	TSXM 13000E	Medium Pitch				3	4	5						☞ H18

Special TSX Mills

Special orders repeater and side cutter available.

● = Euro stock

Recommended Tightening Torque (N·m)

Insert Grade Selection

We have released ACP100 / ACP200 / ACP300 grades for steel machining, ACM200 / ACM300 grades for stainless stell machining and ACK200 / ACK300 grades for cast iron machining to cover a wide range of work materials.



Chipbreaker Selection



Inserts

Cat. No.	RE0,4	RE0,8	RE1,2	RE1,6	RE2,4	RE3,2
LNEX0804__PNER-L	●	●				
LNEX0804__PNER-G	●	●	●	●		
LNEX1306__PNER-L	●	●				
LNEX1306__PNER-G		●		●	●	●
LNEX1306__PNER-H	●	●		●	●	●

Chipbreaker Lineup

Work Material	P M K S		
Chipbreaker	L type	G type	H type
			
Feature	Low cutting force	General purpose	Strong edge
LNEX08 Cutting edge geometry			–
LNEX13 Cutting edge geometry			
Application	Light cut, low rigidity milling and reduced burrs	Main breaker for general purpose applications	Roughing, heavy interrupted and hardness steel milling

Suitable Applications

Face milling

Shoulder milling



Slot milling

Side face milling

TSX(F) 08000 RS

Body - Shell Type

Rake Angle		
	Radial	–20°
	Axial	–6°

8 mm, 90°



Body - TSX, Standard Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2		
TSX 08040 RS	●	40	33	40	16	8,4	5,6	18	14	9	4	0,21
08050 RS	●	50	41	40	22	10,4	6,3	20	18	11	5	0,30
08063 RS	●	63	50	40	22	10,4	6,3	20	18	11	6	0,53

Inserts are not included.

Body - TSXF, Fine Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2		
TSXF 08040 RS	●	40	33	40	16	8,4	5,6	18	14	9	6	0,21
08050 RS	●	50	41	40	22	10,4	6,3	20	18	11	8	0,31
08063 RS	●	63	50	40	22	10,4	6,3	20	18	11	10	0,54

Inserts are not included.

Inserts

Application	Coated Carbide						
High Speed / Light Cutting	PM			K		MS	
General Purpose Cutting	PM	PM		K		MS	MS
Rough Cutting		PM	PM		K		MS

P Steel
M Stainless Steel
K Cast Iron
S Exotic Alloy

Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	Radius RE
LNEX 080404 PNER-L	●	●	●	●	●	●	●	0,4
080408 PNER-L	●	●	●	●	●	●	●	0,8
LNEX 080404 PNER-G	●	●	●	●	●	●	●	0,4
080408 PNER-G	●	●	●	●	●	●	●	0,8
080412 PNER-G	●	●	●	●	●	●	●	1,2
080416 PNER-G	●	●	●	●	●	●	●	1,6



Recommended Cutting Conditions

Min. - **Optimum** - Max.

ISO	Work-material	Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/T)	Grade
P	Carbon Steel	180–280	150–**225**–300	0,08–**0,20**–0,30	ACP100 ACP200 ACP300
		> 280	75–**150**–230	0,08–**0,20**–0,30	
	Alloy Steel	180–280	100–**175**–250	0,08–**0,15**–0,25	
M	Stainless Steel	220–280	90–**135**–180	0,08–**0,15**–0,25	ACM200 ACM300
		>280	75–**125**–170	0,08–**0,15**–0,25	
K	Cast Iron Ductile Cast Iron	250	100–**175**–250	0,08–**0,20**–0,30	ACK200 ACK300
S	Exotic Material	-	30– **60**–90	0,05–**0,10**–0,15	ACM200 ACM300

Identification Details

TSX	F	08	050	R	S
Cutter Series	F: Fine Pitch	Insert Size	Cutter Diameter	Direction	Metric Type

Spare Parts

Screw		Wrench
		
BFTX0308IP	2,0	TRDR08IP

● = Euro stock

Recommended Tightening Torque (N·m)

Body - Shell Type

Rake Angle		
	Radial	–15°
	Axial	–6°

12 mm, 90°

Fig. 1



Fig. 2



Fig. 3



Body - TSX, Standard Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
TSX 13040 RS	●	40	33	40	16	8,4	5,6	18	14	9	3	0,20	1
13050 RS	●	50	41	40	22	10,4	6,3	20	18	11	4	0,30	1
13063 RS	●	63	50	40	22	10,4	6,3	20	18	11	5	0,50	1
13080 RS	●	80	55	50	27	12,4	7,0	22	20	14	5	0,92	1
TSX 13100 RS	●	100	70	50	32	14,4	8,0	32	46	-	6	1,35	2
13125 RS	●	125	80	63	40	16,4	9,0	29	52	29	7	2,55	1
13160 RS	●	160	130	63	40	16,4	9,0	29	90	-	8	4,97	3

Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø 80: M12 x 30–35 mm, Ø 100: M16 x 40–45 mm) for securing Ø 80 / Ø 100 cutter on the arbor.

Body - TSXM, Medium Pitch

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)	Fig.
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2			
TSXM 13040 RS	●	40	33	40	16	8,4	5,6	18	14	9	4	0,19	1
13050 RS	●	50	41	40	22	10,4	6,3	20	18	11	5	0,28	1
13063 RS	●	63	50	40	22	10,4	6,3	20	18	11	6	0,50	1
13080 RS	●	80	55	50	27	12,4	7,0	22	20	14	7	0,92	1
TSXM 13100 RS	●	100	70	50	32	14,4	8,0	32	46	-	8	1,36	2
13125 RS	●	125	80	63	40	16,4	9,0	29	52	29	10	2,57	1
13160 RS	●	160	130	63	40	16,4	9,0	29	90	-	12	5,02	3

Inserts are not included.
*Please use JIS B1176 hexagonal bolt (Ø 80: M12 x 30 ~ 35 mm, Ø 100: M16 x 40 ~ 45 mm) for securing Ø 80 / Ø 100 cutter on the arbor.

Inserts

Application	Coated Carbide						
High Speed / Light Cutting	P M			K		M S	
General Purpose Cutting	P M	P M		K		M S	M S
Rough Cutting		P M	P M		K		M S

P Steel
M Stainless Steel
K Cast Iron
S Exotic Alloy

Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	Radius RE
LNEX 130604 PNER-L	●	●	●	●	●	●	●	0,4
130608 PNER-L	●	●	●	●	●	●	●	0,8
LNEX 130604 PNER-G	●	●	●	●	●	●	●	0,4
130608 PNER-G	●	●	●	●	●	●	●	0,8
130616 PNER-G	●	●	●	●	●	●	●	1,6
130624 PNER-G	●	●	●	●	●	●	●	2,4
130632 PNER-G	●	●	●	●	●	●	●	3,2
LNEX 130608 PNER-H	●	●	●	●	●			0,8
130616 PNER-H		●	●	●	●			1,6
130624 PNER-H		●	●	●	●			2,4
130632 PNER-H		●	●	●	●			3,2



Recommended Cutting Conditions

☞ G34

Identification Details

TSX	M	13	100	R	S
Cutter Series	M: Medium Pitch	Insert Size	Cutter Diameter	Direction	Metric Type

Spare Parts

Screw		Wrench
		
BFTX03510IP	3,0	TRDR15IP

PWS (-F) Type

Features

- **Smooth and stable performance under rough milling conditions**
  Tangentially mounted inserts, offering positive rake angle and unique curved cutting edge, realize stable and long lasting smooth cutting actions.
- **Precision 4 cutting edge inserts**
  The 4 cutting edge inserts offer maximum cost performance.
- **Less vibration under unstable condition**
  Optimized variable pitch design of the serrated inserts minimizes vibration during unstable conditions.
- **Tough and durable body**
  Cutter body shows excellent toughness and durability through special steel and surface treatment.

Inserts - Design and Performance

Comparison of Chip Shape

General Purpose: Type G



Work Material: C50
Cutter: DC =100mm
Cutting Data: v_c =200m/min, f_t =0,20mm/t, a_p =20mm, a_e =10mm
Coolant: Dry
Evaluation: The serrated inserts achieve high efficient machining by reducing chattering.

Heavy Cut: Type R



Comparison of Cutting Edge Stability (Type G)



Serrated Insert Application Guidance (Type R)



Setting instruction:
Please use two different serrated inserts (3x and 4x) as shown in the left figure.

Remark about cutting conditions:
Adjust feed rate up to f_t = 0,25mm/tooth.

Comparison of Cutting Force (Type G)



Comparison of Cutting Force (Type G and R)



Type R is suitable to reduce cutting forces and to prevent vibrations.

▲ = To be replaced by new item

Recommended Tightening Torque (N·m)

Body - Dimensions

Rake Angle	Radial	−15°
	Axial	−6°

16 mm, 90°

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Fig. 5



Cutter body DC ≥ 160 mm: no inner coolant
Cutter body DC ≥ 200 mm: with seat PWSS4R

Body - PWS, Standard

Cat. No.	Stock	Dimensions (mm)								No. of Teeth	Weight (kg)	Fig.
		DC	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP			
PWS 4080 RS	▲	80	60	50	27	20	12,4	7	25	4	1,0	1
PWS 4100 RS	▲	100	70	50	32	46	14,4	8,5	32	6	1,4	2
4125 RS	▲	125	80	63	40	52	16,4	9,5	29	6	2,4	3
4160 RS	▲	160	100	63	40	88	16,4	9,5	29	8	4,2	4

Body - PWSF, Fine pitch

Cat. No.	Stock	Dimensions (mm)								No. of Teeth	Weight (kg)	Fig.
		DC	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP			
PWSF 4080 RS	▲	80	60	50	27	20	12,4	7	25	6	0,9	1
PWSF 4100 RS	▲	100	70	50	32	46	14,4	8,5	32	8	1,3	2
4125 RS	▲	125	80	63	40	52	16,4	9,5	29	8	2,3	3
4160 RS	▲	160	100	63	40	88	16,4	9,5	29	10	4,1	4

Inserts are not included.

Inserts

Application	Coated Carbide				
High speed/Light cut	P			K	
General purpose		P M	M	K	
Roughing		P M	P M		K

Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	Application	Remarks	Fig.
LNMX 170808PNSR-L	▲	▲	▲	▲	▲	Light cut		6
170808PNSR-G	▲	▲	▲	▲	▲	General purpose	1st Choice	6
170808PNSR-R	▲	▲	▲	▲	▲	Heavy cut	Serrated design	7

Fig. 6



Fig. 7



Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/t)	Grade
P	Carbon Steel	180–280	150–**250**–350	0,10–**0,23**–0,35	ACP200
	Alloy Steel	180–280	100–**175**–250	0,10–**0,18**–0,25	ACP200
M	Stainless Steel	-	100–**150**–200	0,15–**0,18**–0,25	ACP300
K	Cast Iron Ductile Iron	250	100–**175**–250	0,10–**0,23**–0,35	ACK200

Min.-**Optimum**-Max.

Spare Parts

Screw	Torx wrench	Sumi-Paste	Seat *
 3,0 Nm			
BFTX0412IP	TTR15IP	SUMI-P	PWSS4R

* from DC ≥ 200mm

Cutter Body DC ≥ 200mm
Please use seat PWSS4R for protection of cutter body.

Insert *PWSS4R



Special Cutter Type PWSR

Rake Angle	Radial	−15°
	Axial	−6°

31 mm, 90°

Delivery on request

"Wave Mill" Series
WEZ Type

New

General Features

- **Supports Various Machining Operations**
  Applicable to various machining applications, the cutter lineup includes diameters of Ø 14 mm to Ø 160 mm, enabling large ramping.
- **Excellent Machining Quality**
  With a combination of optimised cutting edge shape and high-precision molding technology, superb wall surface accuracy and surface finish qualitiy are achieved.
- **Excellent Sharpness with Low Resistance**
  Reduces machining noise and suppresses burrs.
  Lineup includes ground inserts with a focus on sharpness.
- **General-purpose Grade Applicable to any Work Material**
  Introducing the new grade ACU2500, supporting machining in a wide range of fields and applicable to steel, stainless steel and cast iron.

Product Range

Type	Cat. No.	Diameter Range (mm) / No of Teeth															
		Ø14	Ø16	Ø18	Ø20	Ø22	Ø25	Ø28	Ø30	Ø32	Ø35	Ø40	Ø50	Ø63	Ø80	Ø100	Ø125	Ø160
Shell	WEZ 11000RS											4, 6	5,7	6, 8	7, 10	9, 12		
	WEZ 11000R (Inch)														7, 10	9, 12		
	WEZ 17000RS											3, 4	3, 5	4, 6	4, 7	5, 8	6, 9, 11	8, 10 12
	WEZ 17000R (Inch)														4, 7	5, 8	6, 9, 11	8, 10 12
Shank	WEZ 11000E	1	2*	2	2*, 3*	3	2, 3*, 4*	4	4	2, 3, 4, 5*	5	2, 4, 6	5, 7	8	10			
	WEZ 11000EL	1	2*	2	2*	2	2*, 3	2	2	2*, 3	2, 3	2	3					
	WEZ 17000E						2*	2	3	2, 3*	3	3, 4	3*, 5*	4*, 6*	7			
	WEZ 17000EL						2	2	2	2*, 3	2	2, 3, 4	3*, 5*	4*, 6*				

Shank Type ☞ H20-31

* Different shank diameters in stock

Suitable Applications

- **Supports Ramping, Helical Milling, Plunge Cutting**

Face milling



Shoulder milling



Side face milling

Groove milling



Hole expansion milling



Ramping



Helical milling



Plunge cutting



Optimised Body Design

Wide guide face for stable insert clamping.

WEZ11 type

● = Euro stock
❍ = Japan stock

Chipbreaker Lineup

Work Material	P M K S H					N
Chipbreaker	L Type	G Type	H Type	F Type	P Type	S Type
						
AO_T11 Cutting edge geometry						
AO_T17 Cutting edge geometry						
Applications	Light cut, low rigidity machining	Main breaker for general purpose to interrupted machining	Heavy cut, heavy interrup-ted machining, hardened steel	Light cut, finishing, low-burr design	Light cut, high-precision machining, high surface wall quality	For non-ferrous metals



Product Range Inserts

●: Standard stock ❍: Planned stock

Cat. No.	Nose Radius (mm)											
	R0,2	R0,4	R0,8	R1,2	R1,6	R2,0	R2,4	R3,0	R3,2	R4,0	R5,0	R6,4
AOMT 11T3__PEER-G	●	●	●	●	●	●	●	●	●			
AOMT 11T3__PEER-H		●	●	●	●							
AOET 11T3__PEER-F	❍	●	●	❍								
AOET 11T3__PEER-P16	❍	❍	❍	❍								
AOET 11T3__PEER-P20	❍	❍	❍	❍								
AOET 11T3__PEER-P25	❍	❍	❍	❍								
AOET 11T3__PEFR-S	❍	●	●	❍								
AOMT 1705__PEER-L	●	●	●	●	●							
AOMT 1705__PEER-G	●	●	●	●	●	●	●	●	●	●	●	●
AOMT 1705__PEER-H		●	●	❍	●							
AOET 1705__PEER-F	❍	●	●	❍								
AOET 1705__PEER-P25	❍	❍	❍	❍								
AOET 1705__PEER-P32	❍	❍	❍	❍								
AOET 1705__PEFR-S	❍	●	●	❍								

Improved Milling Quality

● Excellent Squareness



Machine:	Vertical Machining Centre BT40,
Work Material:	C50
Tool:	WEZ 11020 E03 (Ø 20, 3 teeth)
Insert:	AOMT11T308PEER-G (ACU2500)
Cutting Conditions:	v_c = 150 m/min, f_z = 0,15 mm/t, a_p = 6 mm x 4 passes, a_e = 5 mm, dry

● Excellent Surface Quality



● Lower cutting force helps reduce machining noise



Machine:	Vertical Machining Centre BT40,
Work Material:	C50
Tool:	WEZ 11020 E03 (Ø 20, 3 teeth)
Insert:	AOMT11T308PEER-G (ACU2500)
Cutting Conditions:	v_c = 150 m/min, f_z = 0,15 mm/t, a_p = 8 mm, a_e = 5 mm, dry

High-precision Ground Class Insert with Excellent Sharpness

Ground Finish on Cutting Edge and Guide Face

The guide face has a ground finish as well as the cutting edge, minimizing corner difference when mounting on the body.
Stable runout precision and machining qualitiy.



Lineup of Chipbreakers for Ground Inserts

F Type

Cutting edge specialized for sharpness and machining accuracy

Sharpness from ground finish enables burr control.

Excellent squareness with all diameters.

Machine:	Vertical Machining Centre BT50,
Work Material	X5CrNiS18 9
Tool:	WEZ 11050 RS07 (Ø 50, 7 teeth)
Insert:	AOET11T308PEER-F (ACU2500)
Cutting Conditions:	v_c = 120 m/min, f_z = 0,12 mm/t, a_p = 1 mm, a_e = 30 mm, dry

P Type

Chipbreaker for wall surface squareness equivalent to solid endmills

Premium item with cutting edge shape optimised for each cutter diameter while maintaining the F type chipbreaker's sharpness.

Enables wall surface squareness equal to solid endmills through a blade shape optimised for each tool diameter.





P Type Chipbreaker Selection

Cat. No.	Cutter Diameter (mm)										
	Ø14	Ø16	Ø18	Ø20	Ø22	Ø25	Ø28	Ø30	Ø32	Ø35	=> Ø40
AOET11T3_ _PEER-P_ _	-P16		-P20		–	-P25		–			
AOET1705_ _PEER-P_ _	–					-P25		-P32			–

Machine:	Vertical Machining Centre BT50,
Work Material:	C50
Tool:	WEZ 11020 E03 (Ø 20, 3 teeth)
Insert:	AOET11T308PEER-P20 (ACU2500)
Cutting Conditions:	v_c = 150 m/min, f_z = 0,1 mm/t, a_p = 8 mm x 3 passes, a_e = 1 mm, dry

S Type

Sharp edge chipbreaker for non-ferrous metals, with excellent adhesion resistance

Suppresses adhesion with rake face lapping.

DLC coat inserts available for further improved adhesion resistance.

Machine:	Vertical Machining Centre BT50,
Work Material:	AlSi12Cu
Tool:	WEZ 11020 E03 (Ø 20, 3 teeth)
Insert:	AOET11T308PEER-S (H20)
Cutting Conditions:	v_c = 350 m/min, f_z = 0,1 mm/t, a_p = 3 mm, a_e = 10 mm, dry

■ Insert Grades Selection Guide

Newly developed general-purpose ACU2500 grade suitable for various work materials has been released. Enhanced lineup of coatings, cemented carbide and cermet for milling steel, stainless steel, cast iron and aluminum alloy.



■ Coating Features

New Absotech ™ (absolute technology) coating technology that realises absolute stability.

ABSOTECH **CVD**



Special Surface Treatment
Suppresses thermal cracking by introducing high compressive stress, resulting in chipping resistance more than twice as good as conventional types

Crystal Orientation Control Al_2O_3
By controlling the growth direction, Al_2O_3 is reinforced for crater wear resistance more than twice as good as conventional types

High Hardness TiCN
Increased TiCN hardness by using a C-rich composition for flank wear resistance more than twice as good as conventional types.

Grades: ACP2000, ACK2000

ABSOTECH **PVD**



New Super Multi-Layered Composition
Higher hardness and twice the conventional wear resistance due to a fine crystal structure AlTiCrBN-based nano-layered coating.

High Adhesion Strength
Significantly improved coating adhesion. Chipping resistance more than twice as good as conventional types.

Grades: ACU2500, ACP3000, ACK3000

ISO	Grade	Coating Thickness (μm)	Features
P M K	ACU2500	3	General purpose grade applicable to steel and cast iron. Adopts a carbide substrate with excellent fracture resistance and wear resistance plus a new coating with excellent wear resistance and chipping reistance, realising stable long tool life with various work material grades.
P	ACP2000	10	Stable long tool life with high-speed machining is realised by adopting a new coating and a tough carbide substrate with excellent thermal crack resistance.
	ACP3000	3	Adopts a very tough carbide substrate plus a new coating with excellent wear resistance and chipping resistance, realising stable long tool life for wet machining of steel in particular.
	T2500A	–	Thanks to the excellent thermal crack resistance conferred by high termal conductivity and the impoved toughness due to the finer and more uniform structure, this cermet grade achieves high levels of fracture resistance and wear resistance.
M	ACM200	6	Realises superb stability in machining of high-hardness stainless steel, due to a high-strength carbide substrate and highly wear-resistant coating.
	ACM300	3	Realises superb stability in machining of stainless steel, due to a high-strength carbide substrate and highly chipping-resistant coating.
K	ACK2000	10	Stable long tool life with high-speed machining of cast iron is realised by adopting a new coating with excellent thermal resistance and a tough carbide substrate.
	ACK3000	3	Adopts a carbide substrate with excellent wear resistance plus a new coating with excellent wear resistance and chipping resistance, realising stable long tool life in dry machining of cast iron.
N	DL2000	0,5	DLC coating grade for non-ferrous metal machining with a low coefficient of friction and excellent adhesion resistance.
	H20	–	Uncoated grade for non-ferrous metal machining with excellent wear resistance and fracture resistance.

Recommended Cutting Conditions

WEZ11 Type

Cutter: WEZ 11020 E03
Insert: AO_T11T3 type
Cutting Data: a_p = 3 mm, a_e = 10 mm, dry



Min. - **Optimum** - Max.

ISO	Material	HB	Chipbreaker	Grade								
				ACU2500	ACP2000	ACP3000	T2500A	ACK2000	ACK3000	ACM200	ACM300	DL2000
				Feed Rate (mm/tooth)								
				0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,18	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,05–**0,10**–0,15
				Cutting Speed v_c (m/min)								
P	Unalloyed steel, <0, 15%C, annealed	125	G	270–**320**–370	300–**350**–400	250–**300**–350	230–**280**–330					
	" , <0, 45%C, annealed	190	G	170–**220**–270	200–**250**–300	150–**200**–250	130–**180**–230					
	" , <0, 45%C, tempered	250	G	140–**180**–220	160–**200**–245	120–**160**–200	105–**145**–185					
	" , <0, 75%C, annealed	270	G	110–**145**–175	130–**165**–195	100–**130**–165	85–**115**–150					
	" , <0, 75%C, tempered	300	G	70–**90**–110	80–**100**–120	60–**80**–100	50–**70**–90					
	Low alloyed steel, annealed	180	G	160–**205**–255	190–**235**–280	140–**190**–235	120–**170**–215					
	" , tempered	275	G	90–**120**–150	110–**135**–165	80–**110**–140	70–**100**–125					
	" , tempered	300	G	85–**110**–130	100–**125**–150	75–**100**–125	65–**90**–115					
	" , tempered	350	G	60–**80**–100	70–**90**–110	50–**70**–90	45–**65**–85					
	High alloyed and tool steel, annealed	200	G	140–**180**–220	160–**200**–245	120–**160**–205						
	" , tempered	325	G	55–**70**–85	60–**80**–100	50–**65**–80						
M	Stainless steel, ferritic/martensitic, annealed	200	G	110–**140**–170						140–**170**–190	90–**110**–140	
	" , martensitic, tempered	240	G	100–**125**–150						125–**150**–170	80–**100**–125	
	" , austenitic, plunged	180	G	120–**150**–180						150–**180**–200	100–**120**–150	
K	Grey cast iron		G	150–**200**–250				250–**300**–350	170–**220**–270			
	Nodular cast iron		G	90–**120**–150				150–**180**–210	100–**130**–160			
S	High tempered resist. alloys, Fe based, annealed		G	30–**40**–55						35–**45**–60	25–**35**–50	
	" , hardened		G	60–**80**–100						70–**90**–110	50–**70**–90	
N	Aluminium alloy, Si < 12,6%		S									500–**750**–100
	" , Si > 12,6%		S									170–**200**–250
	Copper alloy		S									300–**330**–350

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

WEZ17 Type

Cutter: WEZ 17032 E03
Insert: AO_T1705 type
Cutting Data: a_p = 5 mm, a_e = 16 mm, dry



Min. - **Optimum** - Max.

ISO	Material		Chipbreaker	Grade								
				ACU2500	ACP2000	ACP3000	T2500A	ACK2000	ACK3000	ACM200	ACM300	DL2000
				Feed Rate (mm/tooth)								
				0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,15**–0,22	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,05–**0,10**–0,15
				Cutting Speed v_c (m/min)								
P	Unalloyed steel, <0, 15%C, annealed	125	G	285–**335**–390	315–**360**–420	265–**315**–370	240–**295**–345					
	" , <0, 45%C, annealed	190	G	180–**230**–285	210–**265**–315	160–**210**–265	135–**190**–240					
	" , <0, 45%C, tempered	250	G	145–**190**–230	170–**210**–255	130–**170**–215	110–**155**–195					
	" , <0, 75%C, annealed	270	G	115–**150**–185	135–**170**–205	100–**135**–170	90–**125**–155					
	" , <0, 75%C, tempered	300	G	70–**90**–115	85–**105**–125	65–**85**–105	55–**75**–95					
	Low alloyed steel, annealed	180	G	170–**220**–265	200–**245**–295	150–**200**–250	130–**180**–225					
	" , tempered	275	G	100–**130**–155	115–**145**–175	85–**115**–145	75–**105**–135					
	" , tempered	300	G	90–**115**–140	105–**130**–155	75–**105**–130	65–**90**–120					
	" , tempered	350	G	65–**85**–100	75–**95**–115	55–**75**–95	50–**70**–85					
	High alloyed and tool steel, annealed	200	G	145–**185**–230	170–**215**–255	130–**170**–215						
	" , tempered	325	G	55–**75**–90	65–**85**–100	50–**65**–85						
M	Stainless steel, ferritic/martensitic, annealed	200	G	115–**145**–175						145–**175**–195	100–**115**–145	
	" , martensitic, tempered	240	G	105–**130**–155						130–**155**–175	85–**105**–130	
	" , austenitic, plunged	180	G	125–**155**–190						160–**190**–210	105–**125**–160	
K	Grey cast iron		G	160–**210**–265				265–**315**–370	180–**230**–285			
	Nodular cast iron		G	95–**125**–160				160–**190**–220	105–**140**–170			
S	High tempered resist. alloys, Fe based, annealed		G	30–**40**–60						35–**45**–60	25–**35**–50	
	" , hardened		G	60–**85**–105						75–**95**–115	50–**75**–95	
N	Aluminium alloy, Si < 12,6%		S									500–**750**–100
	" , Si > 12,6%		S									170–**200**–250
	Copper alloy		S									300–**330**–350

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

■ Ramping / Helical Milling Upper Limits

Ramping



Flat Bottom Machining



Machining with Prepared Hole



● WEZ11 Type

DC Ø (mm)	Max.Ramping Angle	Flat Bottom Machining				Machining with Prepared Hole	
	RPMX (°)	Max. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)
14	13,2	25,3	8,4	23,1	5,9	19,0	1,9
16	10,5	29,3	7,6	27,0	5,6	21,7	1,5
18	8,1	33,3	6,7	30,9	5,0	25,2	1,4
20	6,5	37,3	6,0	34,9	4,6	29,1	1,3
22	5,3	41,3	5,4	38,8	4,3	32,9	1,3
25	4,1	47,3	4,8	44,8	3,9	38,9	1,3
28	3,4	53,3	4,4	50,7	3,6	44,9	1,3
30	3,0	57,3	4,2	54,7	3,5	48,8	1,3
32	2,7	61,3	4,0	58,7	3,3	52,8	1,2
35	2,3	67,3	3,8	64,6	3,1	58,8	1,2
40	1,8	77,3	3,4	74,6	2,9	68,8	1,2
50	1,2	97,3	3,0	94,6	2,6	88,8	1,1
63	0,8	123,3	2,8	120,5	2,5	114,7	1,1

● WEZ17 Type

DC Ø (mm)	Max.Ramping Angle	Flat Bottom Machining				Machining with Prepared Hole	
	RPMX (°)	Max. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)
25	10,8	47,3	13,0	41,0	8,3	33,1	1,8
28	8,1	53,3	11,1	46,9	7,5	39,0	1,8
30	7,0	57,3	10,2	50,9	7,0	43,0	1,8
32	6,1	61,3	9,5	54,9	6,7	47,0	1,7
35	5,1	67,3	8,7	60,8	6,2	53,0	1,7
40	4,0	77,3	7,7	70,8	5,7	63,0	1,7
50	2,5	97,3	6,5	90,7	5,0	83,0	1,6
63	1,8	123,3	5,6	116,7	4,5	109,0	1,6

* The table above shows values with nose radius 0,8 mm

■ Plunge Cutting - Upper Limit for Radial Width a_e



Type	Max. a_e (mm)
WEZ11	3
WEZ17	5

WEZ 11000 R(S)

New

Rake Angle		
	Radial	-7° – -11°
	Axial	14° – 15°

10 mm 90°

Fig. 1



Fig. 2



Fig. 3



Body - WEZ (Shell Type)

Dimensions (mm)

	Cat. No.	Stock	DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2	D3	No. of Teeth	Weight (kg)	Fig.
Metric	WEZ 11040RS04	●	40	33	40	16	8,4	5,6	18	14	9	–	4	0,21	1
	11040RS06	●	40	33	40	16	8,4	5,6	18	14	9	–	6	0,20	1
	11050RS05	●	50	41	40	22	10,4	6,3	20	18	11	–	5	0,32	1
	11050RS07	●	50	41	40	22	10,4	6,3	20	18	11	–	7	0,31	1
	11063RS06	●	63	50	40	22	10,4	6,3	20	18	11	–	6	0,58	1
	11063RS08	●	63	50	40	22	10,4	6,3	20	18	11	–	8	0,57	1
	11080RS07	●	*80	55	50	27	12,4	7,0	22	20	14	–	7	1,08	1
	11080RS10	●	*80	55	50	27	12,4	7,0	22	20	14	–	10	1,07	1
	11100RS09	●	100	70	50	32	14,4	8,0	32	46	–	–	9	1,57	3
	11100RS12	●	100	70	50	32	14,4	8,0	32	46	–	–	12	1,56	3
Inch	WEZ 11080R07	❍	*80	55	50	25,4	9,5	6,0	25	20	14	–	7	1,09	1
	11080R10	❍	*80	55	50	25,4	9,5	6,0	25	20	14	–	10	1,08	1
	11100R09	❍	*100	70	63	31,75	12,7	8,0	32	46	27	18	9	2,12	2
	11100R12	❍	*100	70	63	31,75	12,7	8,0	32	46	27	18	12	2,10	2

Inserts are sold separately. Check the arbor mounting size (DCB) when selecting the cutter.

* For securing the Ø 80 mm and Ø 100 mm cutter to the arbors, use JIS B1176 hexagonal bolt.
(Ø 80 mm: M12x30 to 35 mm, Ø 100 mm: M16x40x45 mm)

Spare Parts

Applicable Cutters	Insert Screw		Wrench
		N·m	
WEZ 11040RS04 11040RS06 11050RS05 11050RS07 11063RS06 11063RS08 11080R(S)07 11080R(S)10 11100R(S)09 11100R(S)12	BFTX0306IP	1,5	TRDR08IP

Identification Details

WEZ	11	050	R	S	07
Cutter Series	Insert Size	Cutter Diameter	Feed Direction	Metric	Number of Teeth

Recommended Cutting Conditions

☞ G42

● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide							Carbide	DLC	Cermet	
High Speed / Light Cut		P		K		M S			N	P	
General Purpose	K P M S		P		K	M S	M S	N	N		
Roughing	K P M S		P		K		M S				
Cat. No.	ACU2500	ACP2000	ACP3000	ACK2000	ACK3000	ACM200	ACM300	H20	DL2000	T2500A	RE (mm)
AOMT 11T302PEER-G	●	●	●	●	●	●	●	–	–	●	0,2
11T304PEER-G	●	●	●	●	●	●	●	–	–	●	0,4
11T308PEER-G	●	●	●	●	●	●	●	–	–	●	0,8
11T312PEER-G	●	●	●	●	●	●	●	–	–	●	1,2
11T316PEER-G	●	●	●	●	●	●	●	–	–	●	1,6
11T320PEER-G	●	●	●	●	●	●	●	–	–	●	2,0
11T324PEER-G	●	●	●	●	●	●	●	–	–	●	2,4
11T330PEER-G	●	●	●	●	●	●	●	–	–	●	3,0
11T332PEER-G	●	●	●	●	●	●	●	–	–	●	3,2
AOMT 11T304PEER-H	●	●	●	●	●	●	●	–	–	–	0,4
11T308PEER-H	●	●	●	●	●	●	●	–	–	–	0,8
11T312PEER-H	●	●	●	●	●	●	●	–	–	–	1,2
11T316PEER-H	●	●	●	●	●	●	●	–	–	–	1,6
AOET 11T302PEER-F	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-F	●	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-F	●	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-F	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 11T302PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P16	❍	–	–	–	–	–	–	–	–	–	1,2
11T302PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P20	❍	–	–	–	–	–	–	–	–	–	1,2
11T302PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P25	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 11T302PEFR-S	–	–	–	–	–	–	–	❍	❍	–	0,2
11T304PEFR-S	–	–	–	–	–	–	–	●	●	–	0,4
11T308PEFR-S	–	–	–	–	–	–	–	●	●	–	0,8
11T312PEFR-S	–	–	–	–	–	–	–	❍	❍	–	1,2



L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P16 is applicable to cutter diameters Ø 14 mm and Ø 16 mm.
*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

– = Not available

Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.



*When mounting inserts with nose radius of ≥ 3,0 mm, modification of the body is required.



Reworking guidelines
Nose radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Nose radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

WEZ 17000 R(S)

New

Rake Angle		
	Radial	-4° – -9°
	Axial	10° – 15°

15 mm 90°

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Fig. 5



Body - WEZ (Shell Type)

Dimensions (mm)

	Cat. No.	Stock	DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2	D3	No. of Teeth	Weight (kg)	Fig.
Metric	WEZ 17040RS03	●	40	33	40	16	8,4	5,6	18	14	9	–	3	0,19	1
	17040RS04	●	40	33	40	16	8,4	5,6	18	14	9	–	4	0,16	1
	17050RS03	●	50	41	40	22	10,4	6,3	20	18	11	–	3	0,30	1
	17050RS05	●	50	41	40	22	10,4	6,3	20	18	11	–	5	0,26	1
	17063RS04	●	63	50	40	22	10,4	6,3	20	18	11	–	4	0,54	1
	17063RS06	●	63	50	40	22	10,4	6,3	20	18	11	–	6	0,51	1
	17080RS04	●	*80	55	50	27	12,4	7,0	22	20	14	–	4	1,10	1
	17080RS07	●	*80	55	50	27	12,4	7,0	22	20	14	–	7	1,05	1
	17100RS05	●	100	70	50	32	14,4	8,0	32	46	–	–	5	1,58	3
	17100RS08	●	100	70	50	32	14,4	8,0	32	46	–	–	8	1,57	3
	17125RS06	●	125	80	63	40	16,4	9,0	29	52	29	–	6	3,04	1
	17125RS09	●	125	80	63	40	16,4	9,0	29	52	29	–	9	3,07	1
	17125RS11	●	125	80	63	40	16,4	9,0	29	52	29	–	11	3,02	1
	17160RS08	●	160	130	63	40	16,4	9,0	29	90	–	–	8	5,24	5
	17160RS10	●	160	130	63	40	16,4	9,0	29	90	–	–	10	5,31	5
	17160RS12	●	160	130	63	40	16,4	9,0	29	90	–	–	12	5,26	5
Inch	WEZ 17080R04	❍	*80	55	50	25,4	9,5	6,0	25	20	14	–	4	1,10	1
	17080R07	❍	*80	55	50	25,4	9,5	6,0	25	20	14	–	7	1,06	1
	17100R05	❍	*100	70	63	31,75	12,7	8,0	32	46	27	18	5	2,08	2
	17100R08	❍	*100	70	63	31,75	12,7	8,0	32	46	27	18	8	2,07	2
	17125R06	❍	125	80	63	38,1	15,9	10,0	35,5	55	30	–	6	3,09	1
	17125R09	❍	125	80	63	38,1	15,9	10,0	35,5	55	30	–	9	3,11	1
	17125R11	❍	125	80	63	38,1	15,9	10,0	35,5	55	30	–	11	3,06	1
	17160R08	❍	160	100	63	50,8	19,1	11,0	38	72	–	–	8	5,04	4
	17160R10	❍	160	100	63	50,8	19,1	11,0	38	72	–	–	10	5,09	4
	17160R12	❍	160	100	63	50,8	19,1	11,0	38	72	–	–	12	5,04	4

Inserts are sold separately. Check the arbor mounting size (DCB) when selecting the cutter.

* For securing the Ø 80 mm and Ø 100 mm cutter to the arbors, use JIS B1176 hexagonal bolt. (Ø 80 mm: M12x30 to 35 mm, Ø 100 mm: M16x40x45 mm)

Spare Parts

Applicable Cutters	Insert Screw		Wrench	Handle Grip	Wrench Bit
WEZ 17040RS03	BFTX0409IP	3,0	–	HPS1015	TRB15IP
17040RS04					
17050RS03					
17050RS05					
17063RS04					
17063RS06					
17080R(S)04					
17080R(S)07					
17100R(S)05					
17100R(S)08					
17125R(S)06					
17125R(S)09					
17125R(S)11					
17160R(S)08			TRDR15IP	–	–
17160R(S)10					
17160R(S)12					

Identification Details

WEZ	17	100	R	S	05
Cutter Series	Insert Size	Cutter Diameter	Feed Direction	Metric	Number of Teeth

Recommended Cutting Conditions

☞ G42

● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide							Carbide	DLC	Cermet	
High Speed / Light Cut		P		K		M S			N	P	
General Purpose	K P M S		P		K	M S	M S	N	N		
Roughing	K P M S		P		K		M S				
Cat. No.	ACU2500	ACP2000	ACP3000	ACK2000	ACK3000	ACM200	ACM300	H20	DL2000	T2500A	RE (mm)
AOMT 170502PEER-L	●	–	●	–	●	●	●	–	–	●	0,2
170504PEER-L	●	–	●	–	●	●	●	–	–	●	0,4
170508PEER-L	●	–	●	–	●	●	●	–	–	●	0,8
170512PEER-L	●	–	●	–	●	●	●	–	–	●	1,2
170516PEER-L	●	–	●	–	●	●	●	–	–	●	1,6
AOMT 170502PEER-G	●	●	●	●	●	●	●	–	–	●	0,2
170504PEER-G	●	●	●	●	●	●	●	–	–	●	0,4
170508PEER-G	●	●	●	●	●	●	●	–	–	●	0,8
170512PEER-G	●	●	●	●	●	●	●	–	–	●	1,2
170516PEER-G	●	●	●	●	●	●	●	–	–	●	1,6
170520PEER-G	●	●	●	●	●	●	●	–	–	●	2,0
170524PEER-G	●	●	●	●	●	●	●	–	–	●	2,4
170530PEER-G	●	●	●	●	●	●	●	–	–	●	3,0
170532PEER-G	●	●	●	●	●	●	●	–	–	●	3,2
170540PEER-G	●	●	●	●	●	●	●	–	–	●	4,0
170550PEER-G	●	●	●	●	●	●	●	–	–	●	5,0
170564PEER-G	●	●	●	●	●	●	●	–	–	●	6,4
AOMT 170504PEER-H	●	●	●	●	●	●	●	–	–	–	0,4
170508PEER-H	●	●	●	●	●	●	●	–	–	–	0,8
170512PEER-H	❍	●	●	●	●	●	●	–	–	–	1,2
170516PEER-H	●	●	●	●	●	●	●	–	–	–	1,6
AOET 170502PEER-F	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-F	●	–	–	–	–	–	–	–	–	–	0,4
170508PEER-F	●	–	–	–	–	–	–	–	–	–	0,8
170512PEER-F	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 170502PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,4
170508PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,8
170512PEER-P25	❍	–	–	–	–	–	–	–	–	–	1,2
170502PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,4
170508PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,8
170512PEER-P32	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 170502PEFR-S	–	–	–	–	–	–	–	❍	❍	–	0,2
170504PEFR-S	–	–	–	–	–	–	–	●	●	–	0,4
170508PEFR-S	–	–	–	–	–	–	–	●	●	–	0,8
170512PEFR-S	–	–	–	–	–	–	–	❍	❍	–	1,2



L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P25 is applicable to cutter diameters Ø 25 mm and Ø 28 mm.
*P32 is applicable to cutter diameters Ø 30 mm, Ø 32 mm and Ø 35 mm.

– = Not available

Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.



*When mounting inserts with nose radius of ≥ 3,0 mm, modification of the body is required.



Reworking guidelines
Nose radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Nose radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Nose radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Nose radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Nose radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

WEX (-F) Type







Body (Shell Type "F")

Cat. No.	Stock	DC	DCB	D2	KWW	KDP	LF	CBDP	No.of Teeth	Fig.
WEX 1032 F	●	32	16	9	8,4	5,6	40	18	8	1
1040 F	●	40	16	11	8,4	5,6	40	18	10	1
1050 F	●	50	22	11	10,4	6,3	40	20	12	1
1063 F	●	63	22	11	10,4	6,3	40	20	14	1
WEX 2040 F	●	40	16	9	8,4	5,6	40	18	6	2
2050 F	●	50	22	11	10,4	6,3	40	20	7	2
2063 F	●	63	22	11	10,4	6,3	40	20	8	2
2080 F	●	80	27	13,5	12,4	7,0	50	25	10	2
WEX 2100 F	❑	100	32	32	14,4	8,5	50	26	12	2
WEX 3040 F	●	40	16	9	8,4	5,6	40	18	4	3
3050 F	●	50	22	11	10,4	6,3	40	20	5	3
3063 F	●	63	22	11	10,4	6,3	40	20	6	3
3080 F	●	80	27	13,5	12,4	7,0	50	25	7	3
WEX 3100 F	●	100	32	32	14,4	8,5	50	26	8	3

Inserts for WEX1000 / 2000 Type



Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		MS		KN	N	
General Purpose		P		K		MS	MS		N	
Roughing		P	P		K		MS			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 060204 PDER-L	❍	●	❍	❍	●	●	●			0,4
060208 PDER-L	❍	❍	❍	❍	❍	❍	❍			0,8
060212 PDER-L	❍	❍	❍	❍	❍	❍	❍			1,2
AXMT 060204 PDER-G	❍	●	●	❍	❍	❍	●			0,4
060208 PDER-G	❍	●	●	❍	❍	●	●			0,8
060212 PDER-G	❍	●	❍	❍	❍	❍	●			1,2
AXMT 060204 PDER-H	❍	●	●	❍	●	❍	●			0,4
060208 PDER-H	❍	●	●	❍	●	●	●			0,8
060212 PDER-H	❍	❍	❍	❍	❍	❍	❍			1,2
AXMT 123504 PEER-G	●	●	●	●	●			–	–	0,4
123508 PEER-G	●	●	●	●	●			–	–	0,8
123512 PEER-G	●	●	●	●	●			–	–	1,2
AXMT 123504 PEER-H	●	●	●	●	●			–	–	0,4
123508 PEER-H	●	●	●	●	●			–	–	0,8
123512 PEER-H	●	●	●	❍	●			–	–	1,2
AXMT 123504 PEER-E						●	●	–	–	0,4
123508 PEER-E			▲			●	●	–	–	0,8
123512 PEER-E						●	●	–	–	1,2
AXMT 123508 PEER-EH			▲			●	●	–	–	0,8
AXMT 060202 PDFR-S	–	–	–	–	–	–	–	❍	❍	0,2
AXET 123502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
123504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
123508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

Inserts for WEX3000 Type



Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		MS		KN	N	
General Purpose		P		K		MS	MS		N	
Roughing		P	P		K		MS			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 170508 PEER-L	●	●	●	❍	●			–	–	0,8
AXMT 170504 PEER-G	❍	●	●	●	●			–	–	0,4
170508 PEER-G	●	●	●	●	●			–	–	0,8
170512 PEER-G	❍	●	●	❍	●			–	–	1,2
170516 PEER-G	❍	●	●	❍	●			–	–	1,6
170520 PEER-G*	❍	●	●	●	●			–	–	2,0
170530 PEER-G*	●	●	●	●	●			–	–	3,0
AXMT 170508 PEER-H	●	●	●	●	●			–	–	0,8
170512 PEER-H	●	●	●	●	●			–	–	1,2
AXMT 170504 PEER-E						●	●	–	–	0,4
170508 PEER-E			▲			●	●	–	–	0,8
170512 PEER-E						●	●	–	–	1,2
170516 PEER-E						❍	●	–	–	1,6
170520 PEER-E*						❍	●	–	–	2,0
170530 PEER-E*						●	●	–	–	3,0
AXMT 170508 PEER-EH			▲			●	●	–	–	0,8
AXET 170502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
170504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
170508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

* Cutter body modification is required. ☞ H36

– Unable to produce

L – Low cutting force
G – General type
H – Strong cutting edge
E – For stainless steel
EH– Strong edge for stainless steel
S – For aluminium

Spare Parts

Screw	Wrench		N·m	Applicable Endmill
BFTX 01804 IP	TRX 06 IP		0,5	WEX 1000 F
BFTX 0306 IP		TRDR 08 IP	2,0	WEX 2000 F
BFTX 0409 IP		TRDR 15 IP	3,0	WEX 3000 F

Identification Details

WEX	2	016	F
Cutter Series	2000 Series	Cutter Diameter	Shell Type

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item

☞ H34-36

N·m Recommended Tightening Torque (N·m)

WRX (-F) Type

18–36 mm 90°



27–53 mm 90°



Body (Shell Type "F")

Cat. No.	Stock	Depth of cut (a_p)	Dimensions (mm) øD	ød1	ød2	a	b	l1	l	l	No. of teeth	No. of rows	Effective teeth
WRX2040RH18F16	❑	18	40	16	9	8,4	5,6	50	39	18	10	2	5
WRX2040RH36F16	●	36	40	16	9	8,4	5,6	55	44	18	16	4	4
WRX2050RH18F22	❑	18	50	22	11	10,4	6,3	50	36	20	10	2	5
WRX2050RH36F22	●	36	50	22	11	10,4	6,3	55	41,5	20	16	4	4

Body (Shell Type "F")

Cat. No.	Stock	Depth of Cut (a_p)	Dimensions (mm) øD	ød1	ød2	a	b	l1	l	l	No. of teeth	No. of rows	Effective teeth
WRX3050RH27F22	❑	27	50	22	11	10	6,3	50	36	20	8	2	4
WRX3050RH53F22	●	53	50	22	11	10	6,3	70	56	20	12	4	3
WRX3063RH27F27	❑	27	63	27	13,5	12	7	70	34	2	10	2	5
WRX3063RH53F27	●	53	63	27	13,5	12	7	70	54	2	16	4	4
WRX3080RH27F32	❑	27	80	32	17	14	8	50	30	2	12	2	6
WRX3080RH53F32	●	53	80	32	17	14	8	85	63	2	20	4	5
WRX3100RH27F40	❑	27	100	40	21	16	9,5	85	40	30	14	2	7
WRX3100RH53F40	●	53	100	40	21	16	9,5	85	59	30	24	4	6

Inserts (Same as for Wavemill WEX 2000 Type)



Application	Coated Carbide							Carbide	DLC
High Speed / Light cut	P			K		M S		K N	N
General Purpose		P		K		M S	M S		N
Roughing		P	P		K		M S		

Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 123504 PEER-G	●	●	●	●	●			–	–	0,4
123508 PEER-G	●	●	●	●	●			–	–	0,8
123512 PEER-G	●	●	●	●	●			–	–	1,2
AXMT 123504 PEER-H	●	●	●	●	●			–	–	0,4
123508 PEER-H	●	●	●	●	●			–	–	0,8
123512 PEER-H	●	●	●	❍	●			–	–	1,2
AXMT 123504 PEER-E						●	●	–	–	0,4
123508 PEER-E			▲			●	●	–	–	0,8
123512 PEER-E						●	●	–	–	1,2
AXMT 123508 PEER-EH			▲			●	●	–	–	0,8
AXET 123502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
123504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
123508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

– Unable to produce

L – Low cutting force
G – General type
H – Strong cutting edge
E – For stainless steel
EH– Strong edge for stainless steel
S – For aluminium

Inserts (Same as for Wavemill WEX 3000 Type)



Application	Coated Carbide							Carbide	DLC
High Speed / Light cut	P			K		M S		K N	N
General Purpose		P		K		M S	M S		N
Roughing		P	P		K		M S		

Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 170508 PEER-L	●	●	●	❍	●			–	–	0,8
AXMT 170504 PEER-G	❍	●	●	●	●			–	–	0,4
170508 PEER-G	●	●	●	●	●			–	–	0,8
170512 PEER-G	❍	●	●	❍	●			–	–	1,2
170516 PEER-G	❍	●	●	❍	●			–	–	1,6
170520 PEER-G*	❍	●	●	●	●			–	–	2,0
170530 PEER-G*	●	●	●	●	●			–	–	3,0
AXMT 170508 PEER-H	●	●	●	●	●			–	–	0,8
170512 PEER-H	●	●	●	●	●			–	–	1,2
AXMT 170504 PEER-E						●	●	–	–	0,4
170508 PEER-E			▲			●	●	–	–	0,8
170512 PEER-E						●	●	–	–	1,2
170516 PEER-E						❍	●	–	–	1,6
170520 PEER-E*						❍	●	–	–	2,0
170530 PEER-E*						●	●	–	–	3,0
AXMT 170508 PEER-EH			▲			●	●	–	–	0,8
AXET 170502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
170504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
170508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

* Cutter body modification is required. ☞ H36

Spare Parts

Screw	Wrench	N·m	Applicable Endmill
BFTX 0306 IP	TRDR 08 IP	2,0	WRX 2_ _ _ _ RH_ _F_ _
BFTX 0409 IP	TRDR 15 IP	3,0	WRX 3_ _ _ _ RH_ _F_ _

Identification Details

WRX 20 (Insert Size) 40 (Tool øD) R (Cutting Direction) H (Inner coolant) 18 (Cutting Edge Length) F (Arbor Type) 16 (Arbor Diameter)

E - Straight Shank
W - Weldon Shank
F - Shell Type

☞ H44-47

PWC Type

Powerful Tangential Milling System for Cast Iron

Approach angle	:	88°
Axial rake angle	:	+ 5°
Radial rake angle	:	- 5°

Fig. 1



Fig. 2



Fig. 3



Body (Standard, PWC Type)

Cat. No.	Stock		Dimensions (mm)								No of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
	R	L	DC	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP				
PWC 4080 R/L-S	▲	▲	80	60	50	27	29,5	12,4	7,0	25	7		0,9	1
PWC 4100 R/L-S	▲	▲	100	70	50	32	46	14,4	8,5	29	8		1,3	2
4125 R/L-S	▲	▲	125	80	63	40	56	16,4	9,5	29	10	12,0	2,5	2
4160 R/L-S	▲	▲	160	100	63	40	88	16,4	9,5	29	12		4,2	3
PWC 4200 R/L-S	▲	▲	200	150	63	60	130	25,7	14,0	35	16		7,2	3

Body (Fine Pitch, PWCF Type)

Cat. No.	Stock		Dimensions (mm)								No of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
	R	L	DC	DCSFMS	LF	DCB	D1	KWW	KDP	CBDP				
PWCF 4080 R/L-S	▲	▲	80	60	50	27	29,5	12,4	7,0	25	9		0,9	1
PWCF 4100 R/L-S	▲	▲	100	70	50	32	46	14,4	8,5	29	12		1,4	2
4125 R/L-S	▲	▲	125	80	63	40	56	16,4	9,5	29	15	12,0	2,6	2
4160 R/L-S	▲	▲	160	100	63	40	88	16,4	9,5	29	18		4,3	3
PWCF 4200 R/L-S	▲	▲	200	150	63	60	130	25,7	14,0	35	24		7,4	3

Performance

● Comparison of cutting force



Work Material : GG25
Tool : PWC 4080 RS, ø 80
Insert : LNMX160608PNSN-G
Grade : ACK200

Cutting Conditions
v_c = 200 m/min
f_t = 0,1 mm/tooth
Depth of cut : 4,0 mm
Width of cut : 50 mm
Dry

● Comparison of cutting edge strength



Work Material : GG25
Tool : PWC 4080 RS, ø 80
Insert : LNMX160608PNSN-G
Grade : ACK200

Cutting Conditions
v_c = 160 m/min
f_t = 0,3–0,5 mm/tooth
Depth of cut : 5,0 mm
Width of cut : 80 mm
Dry

Recommended Cutting Conditions

Material	Grey Cast Iron (GG)	Ductile Cast Iron (GGG)
Cutting speed (m/min)	100 150 200 250 300	100 150 200 250
Feed rate (mm/tooth)	0,1 0,2 0,3 0,4 0,5	0,05 0,1 0,2 0,25 0,3
Grade	ACK200, ACK300	

Spare Parts

Cutter	Screw	Wrench
	 3,0 (N·m)	
PWC (F) 4000	BFTX 0412 N	TTX 15 W

▲ =To be replaced by new item

(N·m) Recommended Tightening Torque (N·m)

PWC Type

High Metal Removal
High Volume Insert Capacity
High Performance Inserts

● Geometry

Rake angle
G type : 20°
H type : 15°

Wiper width = 2,4 mm

■ Advantages

● High volume insert capacity
The tangential orientation of the strong carbide inserts increases the number of cutting edges (eg 3 edges /inch) maximising edge contact with the workpiece.

● Cost effective tooling
Using M Class precision sintered inserts with 8 cutting edges both acquisition and operating costs are substantially reduced.

● Increased tool life
New Cast Iron grades ACK200 for general cutting and ACK300 for heavy cutting provide increased tool life and high productivity

● Durable cutter body
The robust cutter body is manufactured from a special alloyed steel then coated with a hard surface to resist swarf damage, scratching, and corrosion.

■ Inserts



● G type insert
for light cutting

(Fig. 1)

● H type insert
with strong cutting edge

(Fig. 2)

Application	Coated Carbide		
High speed/Light cut	K	K	
General purpose	K	K	
Roughing			K

Cat. No.	ACK100	ACK200	ACK300	Fig.	Application	Remarks
LNMX 160608 PNSN-G		▲	▲	1	General application	First remommendation
160608 PNSN-L	▲	▲	▲	2	Instable machining, heavy interruption	Suitable for instable condition

■ New Coated Grade for Cast Iron





Grade	Characteristic · Application
ACK100	High wear resistance with special hard substrate and fine Ti-based Al_2O_3 CVD coating for high speed machining
ACK200	Excellent wear resistance with fine Ti-based and tough Al_2O_3 CVD coating
ACK300	Excellent toughness with fine grain carbide substrate. Cr added new PVD coating could improve hardness and oxidation resistance.

CNP / CNPF Type

Shoulder Milling for Steel, Stainless Steel & Cast Iron

Approach angle	:	90°
Axial rake angle	:	+ 10° – 17°
Radial rake angle	:	+ 10° – 16°

Fig. 1



Fig. 2



Fig. 3



Body (Standard, CNP Type)

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
		DC	DCSFMS	LF	DCB	D1	D2	KWW	KDP	CBDP				
CNP 13040 RS	▲	40	36	40	22	14	9	8,4	5,6	18	4	12,0	0,3	1
13050 RS	▲	50	40	40	27	18	11	10,4	6,3	20	4		0,4	1
13063 RS	▲	63	40	40	22	18	11	10,4	6,3	20	5		0,4	1
13080 RS	▲	80	60	50	27	20	13	12,4	7,0	25	5		0,9	1
CNP 13100 RS	▲	100	70	50	32	-	-	14,4	8,5	32	6		1,3	2
13125 RS	▲	125	80	63	40	-	-	16,4	9,5	38	7		2,5	2
13160 RS	▲	160	100	63	40	-	-	16,4	9,5	38	8		4,2	2
CNP 13200 RS		200	150	63	60	-	-	25,7	14,0	34	10		7,2	3

Body (Fine Pitch, CNPF Type)

CNPF 13063 RS	▲	63	40	40	22	18	11	10,4	6,3	20	7	12,0	0,4	1
13080 RS	▲	80	60	50	27	20	13	12,4	7,0	25	7		0,9	1
CNPF 13100 RS	▲	100	70	50	32	-	-	14,4	8,5	32	8		1,4	2
13125 RS	▲	125	80	63	40	-	-	16,4	9,5	38	9		2,4	2
13160 RS	▲	160	100	63	40	-	-	16,4	9,5	38	11		4,3	2
CNPF 13200 RS		200	150	63	60	-	-	25,7	14,0	34	13		7,4	3

Inserts

Fig. 1



Fig. 2



Application	Coated Carbide					
High Speed / Light cut	P	P M	P M	K		
General Purpose		P M	P M	K		
Roughing					K	
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	Fig.
CNMU 130608 N-G	▲	▲	▲	▲	▲	1.
130608 N-H	▲	▲	▲	▲	▲	
CNMQ 130608 N						2.
130616 N	▲	▲	▲	▲	▲	

G: General purpose
H: Strong cutting edge

Spare Parts

Cutter	Screw	Wrench
	 3,0 (N·m)	
CNP-(F) 13000	BFTX 0412 N	TTX 15 W

Recommended Cutting Conditions

[v_c =m/min, f_t =mm/tooth] [min.– **optimum** – max.]

Insert Type		CNMU / CNMQ 1306○○ N / -G/ -H											
Grade		ACP100			ACP200			ACP300		ACK200		ACK300	
Work Material / Type		Low carbon steel	Alloy steel	Die steel	Low carbon steel	Alloy steel	Die steel	Stainless steel austenitic	Stainless steel martensitic	Cast iron	Ductile cast iron	Cast iron	Ductile cast iron
CNP 13000	v_c	100-**250**-400	80-**220**-280	80-**150**-250	80-**200**-370	70-**150**-250	60-**130**-220	120-**180**-240	100-**140**-200	220-**270**-450	150-**180**-250	180-**220**-270	130-**160**-220
	f_t	0,1-**0,25**-0,4	0,1-**0,25**-0,35	0,1-**0,2**-0,3	0,1-**0,25**-0,4	0,1-**0,25**-0,35	0,1-**0,2**-0,3	0,1-**0,2**-0,25	0,1-**0,2**-0,25	0,1-**0,25**-0,4	0,1-**0,25**-0,4	0,1-**0,25**-0,4	0,1-**0,25**-0,4
	a_p	~**10**			~**10**			~**10**		~**10**		~**10**	

● = Euro stock
❍ = Japan stock

▲ = To be replaced by new item

(N·m) Recommended Tightening Torque (N·m)

High Feed Milling of Steel, Stainless Steel, Die Steel and Cast Iron

H8-10

1,5 mm 20° (MSX 08000□□)

2,0 mm 20° (MSX 12000□□)

2,5 mm 20° (MSX 14000□□)

Fig. 1



Fig. 2



Body

Cat. No.	Stock	Dimensions (mm)									No. of teeth	Helical Boring øB (max-min)	Ramping αmax.	Weight (Kg)	Fig.
		DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2					
MSX 08040 RS	●	40	37	45	16	8,4	5,6	18	13,5	9	4	65 ~ 78	1°30'	0,2	1
MSX 12050 RS	●	50	47	50	22	10,4	6,3	20	18	11	4	78 ~ 99	2°30'	0,3	1
12052 RS	●	52	47	50	22	10,4	6,3	20	18	11	4	82 ~ 103	2°00'	0,3	1
12063 RS	●	63	60	50	22	10,4	6,3	20	18	11	5	104 ~ 125	1°30'	0,4	1
12066 RS	●	66	60	63	27	12,4	7,0	25	20	13,5	5	110 ~ 131	1°00'	0,4	1
MSX 14050 RS	●	50	47	50	22	10,4	6,3	20	17	11	3	73 ~ 98	3°30'	0,3	1
14063 RS	●	63	60	50	22	10,4	6,3	20	18	11	4	99 ~ 124	2°00'	0,6	1
14066 RS	●	66	60	63	27	12,4	7,0	25	13,5	20	4	107 ~ 132	2°00'	0,7	1
14080 RS	●	80	76	63	27	12,4	7,0	25	13,5	20	5	133 ~ 158	1°30'	1,2	1
MSX 14100 RS	●	100	96	63	32	14,4	8,5	32	-	44	6	173 ~ 198	1°00'	1,8	2

Ramping (Slant Milling)



Helical Boring



Inserts



Application	Coated Carbide		
High Speed / Light cut			
General Purpose	P M	P M	
Roughing	P M	P M	K

Cat. No.	ACP200	ACP300	ACK300	Dimensions (mm) IC	S	RE
WDMT 0804 ZDTR	●	●	❍	8,5	4,0	2,0
0804 ZDTR-H	●	●	❍			
WDMT 1205 ZDTR	●	●	●	12	5,0	2,0
1205 ZDTR-H	●	●	●			
WDMT 1406 ZDTR	●	●	●	14	6,0	2,0
1406 ZDTR-H	●	●	●			

ZDTR-H : Stronger cutting edge

Recommended Cutting Conditions

Depth of cut : a_p (mm)
Feed rate : f_t (mm/tooth)

Work Material	Insert Type	Cutting Speed v_c (m/min)	Insert Cat. No.	ø 40		ø 50–66		ø 80–100	
				a_p	f_t	a_p	f_t	a_p	f_t
General Steel (Below HB200)	ACP200	100-**150**-200	WDMT 0804	1,0	1,2	–	–	–	–
			WDMT 1205	–	–	1,2	1,4	–	–
			WDMT 1406	–	–	1,5	1,5	1,5	1,5
Alloy Steel (Below HRC45)	ACP200	80-**130**-180	WDMT 0804	0,8	1,2	–	–	–	–
			WDMT 1205	–	–	1,0	1,4	–	–
			WDMT 1406	–	–	1,3	1,5	1,3	1,5
Stainless Steel (X5CRNI1810)	ACP300	80-**120**-150	WDMT 0804	1,0	0,8	–	–	–	–
			WDMT 1205	–	–	1,2	1,2	–	–
			WDMT 1406	–	–	1,5	1,3	1,5	1,3
Cast Iron GG, GGG	ACK300	100-**150**-200	WDMT 0804	1,0	1,4	–	–	–	–
			WDMT 1205	–	–	1,2	1,5	–	–
			WDMT 1406	–	–	1,5	1,8	1,5	1,8
Hardened Steel (Below HRC50)	ACK300	40-**80**-100	WDMT 0804	0,5	0,8	–	–	–	–
			WDMT 1205	–	–	0,6	1,0	–	–
			WDMT 1406	–	–	1,0	1,2	1,0	1,2

- The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity.
- The above figures are guidelines for use with the BT50 machine tool.

Spare Parts

Screw		Wrench	Clamp	C Ring	Cramp screw	Applicable endmill
BFTX 0306 IP	**2,0**	TRDR 08 IP	CCH 3,5	CR 03	BFTX 03510 IP 08	MSX 08000RS
BFTX 0409 IP	**3,0**	TRDR 15 IP	CCH 3,5	CR 03	BFTX 03510 IP 15	MSX 12000RS
BFTX 0511 IP	**5,0**	TRDR 20 IP	CCH 4,5	CR 03	BFTX 04513 IP 20	MSX 14000RS

Remark: If depth-of-cut exceeds 5 mm, reduce recommended feedrates by 50 %.
The conditions above are meant as a guide, please adjust the cutting conditions according to actual work material and machine ridgidity.

WFXH Type

General Features

WaveMill WFXH type is a high efficiency, multi-purpose cutter, that uses the WFX series inserts for high-feed roughing and a variety of processes.

Characteristics

Stable, high-efficiency milling with superior cutting edge sharpness.
Supports various types of processes (ramping and helical milling).
Able to use the selection of inserts from the WFX series.

Chipbreaker Selection



Work Material	P M K Steel, Stainless Steel, Cast Iron			N Aluminium Alloy
Breaker	**L Type**	**G Type**	**H Type**	**S Type**
				
Characteristic	Low Cutting Force	General Purpose	Strong Edge	Sharp Edge
Cutting Edge Figure	 20°	 15°	 10°	 25°
Work Material Application	Light Cutting Low rigidity Milling Low-Burr Design	**Main Chipbreaker** General to Interrupted Milling	Heavy Cut Heavy Interrupted Machining Tempered Steel	Non-Ferrous Metal

Notes on Corner Finishing - Remaining Material

Actual machined corners will have uncut and overcut portions due to the shape of the inserts.

Fig. 1



Fig. 2



WFXH 08000 RS Type

Programmed Corner R	SOMT 08○○04-□			SOMT 08○○08-□			SOMT 08○○12-□		
	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape
2,0	1,41	0	Fig. 1	1,30	0	Fig. 1	1,21	0	Fig. 1
2,5	1,30	0,02	Fig. 2	1,19	0,01	Fig. 2	1,09	0	Fig. 2
3,0	-	-	-	-	-	-	0,98	0,05	Fig. 2

WFXH 12000 RS Type

Programmed Corner R	SOMT 12○○04-□			SOMT 12○○08-□			SOMT 12○○12-□			SOMT 12○○16-□		
	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape
2,0	2,58	0	Fig. 1	2,48	0	Fig. 1	2,37	0	Fig. 1	2,25	0	Fig. 1
2,5	2,47	0	Fig. 1	2,37	0	Fig. 1	2,25	0	Fig. 1	2,14	0	Fig. 1
3,0	2,36	0	Fig. 1	2,26	0	Fig. 1	2,14	0	Fig. 1	2,11	0	Fig. 1
3,5	2,24	0,01	Fig. 2	2,14	0	Fig. 1	2,03	0	Fig. 1	1,91	0	Fig. 1
4,0	-	-	-	2,03	0,04	Fig. 2	1,91	0,03	Fig. 2	1,8	0,01	Fig. 2

Minimum Cutting Diameter

Minimum cutting diameter (DCN) will depend on the insert that is used. Using an insert with a large nose radius is recommended for the WFXH type.





Body Cat. No.	DC	DCN based on insert nose			
		RE0,4	RE0,8	RE1,2	RE1,6
WFXH 08025 M12Z2	25	10,4	10,9	11,5	-
08032 M12Z3	32	17,4	17,9	18,5	-
WFXH 08040 RS	40	25,4	25,9	26,5	-
08050 RS	50	35,4	35,9	36,5	-
08050 RSZ6	50	35,4	35,9	36,5	-
08063 RS	63	48,4	48,9	49,5	-
WFXH 12040 M12Z3	40	16,6	17,1	17,5	18,1
WFXH 12050 RS	50	26,6	27,2	27,7	28,2
12063 RS	63	39,5	40,0	40,4	41,1

Taper Cutting and Helical Milling



Minimum and Maximum Diameters

Ramping Angle

Insert Cat. No.	DC	Helical Millilng		Taper Cutting
		Min.	Max.	Max. Ramping Angle
SOMT 08○○04-□	25	35	49	1°30'
	32	49	63	0°30'
	40	65	79	0°30'
	50	Impossible	Impossible	0°30'
	63	Impossible	Impossible	Impossible
SOMT 08○○08-□	25	35	48	3°
	32	49	62	1°30'
	40	65	78	1°
	50	85	98	0°30'
	63	111	124	0°30'
SOMT 08○○12-□	25	34	47	4°30'
	32	48	61	2°30'
	40	64	77	1°30'
	50	84	97	1°
	63	110	123	0°30'

Insert Cat. No.	DC	Helical Millilng		Taper Cutting
		Min.	Max.	Max. Ramping Angle
SOMT 12○○04-□	40	56	79	1°
	50	76	99	0°30'
	63	Impossible	Impossible	Impossible
SOMT 12○○08-□	40	56	78	1°30'
	50	76	98	1°
	63	102	124	0°30'
SOMT 12○○12-□	40	55	77	2°30'
	50	75	97	1°30'
	63	101	123	1°
SOMT 12○○16-□	40	55	76	3°30'
	50	75	96	2°
	63	101	122	1°30'

Maximum Width of Cut when Plunge Milling



Insert Cat. No.	Max. Width of Cut ae (max)
SOMT08	6 mm
SOMT12	10 mm

Lower the feed rate when plunge milling.

Recommended Cutting Conditions

ISO	Work Material	Grade	Cutting Speed (vc (m/min)	Insert Cat. No.	Ø 25		Ø 32		Ø 40		Ø 50		Ø 63	
					ap (mm)	ft (mm/t)	ap (mm)	ft (mm/t)	ap (mm)	ft (mm/t)	ap (mm)	ft (mm/t)	ap (mm)	ft (mm/t)
P	General Steel <200HB	ACP200	100 - **150** - 200	SOMT08	0,8	0,8	0,8	0,8	-	-	0,8	0,8	0,8	0,8
				SOMT12	-	-	-	-	1,0	1,0	1,0	1,0	1,0	1,0
	Alloy Steel <HRC45	ACP200	80 - **130** - 180	SOMT08	0,7	0,8	0,7	0,8	-	-	0,7	0,8	0,7	0,8
				SOMT12	-	-	-	-	0,8	1,0	0,8	1,0	0,8	1,0
K	Stainless Steel (X5CrNiS18 10, other)	ACM300	80 - **120** - 150	SOMT08	0,8	0,7	0,8	0,7	-	-	0,8	0,7	0,8	0,7
				SOMT12	-	-	-	-	1,0	0,8	1,0	0,8	1,0	0,8
M	Cast Iron FC, FCD	ACK300	100 - **150** - 200	SOMT08	0,8	1,0	0,8	1,0	-	-	0,8	1,0	0,8	1,0
				SOMT12	-	-	-	-	1,0	1,2	1,0	1,2	1,0	1,2
H	Hardened Steel <HRC50	ACK300	40 - **80** - 100	SOMT08	0,5	0,5	0,5	0,5	-	-	0,5	0,5	0,5	0,5
				SOMT12	-	-	-	-	0,6	0,8	0,6	0,8	0,6	0,8

The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity. The above figures are guidelines for use with the BT50 machine tool.
The above conditions assume a tool overhang length of L/D = 3 (i.e. overhang length is 3 times tool diameter) or less.
When tool overhang is more than L/D = 3 and less or equal L/D = 5, settings should be adjusted to approximately 70 % to 80 % of those indicated in the above cutting conditions (i.e. a_p and f_z).
When tool overhang is more than L/D = 5 and less or equal L/D = 8, settings should be adjusted to approximately 50 % to 60 % of those indicated in the above cutting conditions (i.e. a_p and f_z).

WFXH 08000 RS

High Efficiency Machining for Steel, Stainless Steel, Die Steel and Non-Ferrous Metal

Rake Angle		
	Radial	–6°
	Axial	6°

1,5 mm, 15°



Body - WFXH08000RS

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2		
WFXH 08040 RS	❍	40	33	40	16	8,4	5,6	18	14	9	4	0,2
08050 RS	❍	50	41	40	22	10,4	6,3	20	18	11	5	0,3
08050 RSZ6	❍	50	41	40	22	10,4	6,3	20	18	11	6	0,3
08063 RS	❍	63	50	40	22	10,4	6,3	20	18	11	6	0,5

Inserts are not included.

Identification Details

WFX	H	08	040	R	S	- Z6
Cutter Series	High Efficiency Milling	Insert Size	Cutter Diameter	Direction	Metric Type	Fine Pitch Type (Value is number of teeth)

Inserts

Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		MS		KN		
General Purpose		PM	PM	K		MS	MS		N	
Roughing		PM	PM		K		MS		N	
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius (mm) RE
SOMT 080304 PZER L	❍	❍	❍	❍	●	❍	❍	–	–	0,4
080308 PZER L	❍	❍	❍	❍	❍	❍	●	–	–	0,8
SOMT 080304 PZER G	❍	●	●	●	❍	❍	●	–	–	0,4
080308 PZER G	❍	●	●	●	●	❍	●	–	–	0,8
080312 PZER G	❍	●	❍	❍	❍	❍	●	–	–	1,2
SOMT 080308 PZER H	❍	●	●	❍	●	❍	●	–	–	0,8
080312 PZER H	❍	❍	●	❍	❍	❍	●	–	–	1,2
SOET 080304 PZER G	❍	❍	❍	❍	●	❍	●	–	–	0,4
080308 PZER G	❍	❍	❍	❍	❍	❍	●	–	–	0,8
080312 PZER G	❍	❍	❍	❍	❍	❍	●	–	–	1,2
SOET 080302 PZFR S*	–	–	–	–	–	–	–	●	●	0,2
080304 PZFR S*	–	–	–	–	–	–	–	●	●	0,4
080308 PZFR S*	–	–	–	–	–	–	–	●	●	0,8



* If the cutting edge lacks strength when performing high efficiency milling of non-ferrous metals, try G type chipbreakers (ACK300).

Spare Parts

Screw		Wrench
BFTX0306IP	2,0	TRDR08IP

Recommended Cutting Conditions

☞ G55

Programming and Dimension Information

☞ G54

● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

WFXH 12000 RS

High Efficiency Machining for Steel, Stainless Steel, Die Steel and Non-Ferrous Metal

Rake Angle		
	Radial	–6°
	Axial	6°

2,5 mm, 15°



Body - WFXH12000RS

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DC	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2		
WFXH 12050 RS	❍	50	41	40	22	10,4	6,3	20	18	11	4	0,3
12063 RS	❍	63	50	40	22	10,4	6,3	20	18	11	5	0,4

Inserts are not included.

Identification Details

WFX	H	12	050	R	S
Cutter Series	High Efficiency Milling	Insert Size	Cutter Diameter	Direction	Metric Type

Inserts

Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		MS		KN		
General Purpose		PM	PM	K		MS	MS		N	
Roughing		PM	PM		K		MS		N	
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius (mm) RE
SOMT 120408 PDER L	●	●	●	❍	❍	❍	●	–	–	0,8
SOMT 120404 PDER G	❍	❍	●	❍	●	❍	●	–	–	0,4
120408 PDER G	●	●	●	●	❍	●	●	–	–	0,8
120412 PDER G	❍	❍	❍	❍	❍	❍	●	–	–	1,2
120416 PDER G	❍	●	❍	❍	❍	❍	❍	–	–	1,6
SOMT 120408 PDER H	❍	●	❍	●	●	❍	❍	–	–	0,8
SOET 120408 PDFR S*	–	–	–	–	–	–	–	●	●	0,8



* If the cutting edge lacks strength when performing high efficiency milling of non-ferrous metals, try G type chipbreakers (ACK300).

Spare Parts

Screw		Wrench
		
BFTX03512IP	3,0	TRDR15IP

Recommended Cutting Conditions

☞ G55

Programming and Dimension Information

☞ G54

WAX 3000 RS Type

16–18mm 90° P M K S N

(Shellmill)



Body

(For inserts with nose radius ≤ 3,2 mm)

Cat. No.	Stock	Dimensions (mm)							No.of teeth	Weight (Kg)
		DC	DCB	LF	D2	KWW	KDP	CBDP		
WAX 3050 RS-3.2	●	50	22	50	11	10,4	6.3	21	4	0,34
3063 RS-3.2	●	63	22	50	11	10,4	6.3	21	5	0,6
3080 RS-3.2	●	80	27	50	13,5	12,4	7	23	5	1,0
WAX 3100 RS-3.2	●	100	32	63	18	14,4	8	26	6	2,2
3125 RS-3.2	●	125	40	63	22	16,4	9	29	7	3,5

Body

(For inserts with nose radius ≥ 4,0mm)

Cat. No.	Stock	Dimensions (mm)							No.of teeth	Weight (Kg)
		DC	DCB	LF	D2	KWW	KDP	CBDP		
WAX 3050 RS-4.0	●	50	22	50	11	10,4	6.3	21	4	0,34
3063 RS-4.0	●	63	22	50	11	10,4	6.3	21	4	0,6
3080 RS-4.0	●	80	27	50	13,5	12,4	7	23	5	1,0
WAX 3100 RS-4.0	●	100	32	63	18	14,4	8	26	6	2,2
3125 RS-4.0	●	125	40	63	22	16,4	9	29	7	3,5

Inserts for WAX 3000 Type

Application	DLC Coated	Carbide
High Speed / Light cut	K N	N
General Purpose		N
Roughing		

Cat. No.	DL1000	H1	Dimensions (mm)					
			APMX	INSL	BS	RE	S	D1
AECT 160404 PEFRA	●	●	18	16,4	1,4	0,4	5	4,4
160408 PEFRA	●	●	18	16,4	1,0	0,8	5	4,4
160412 PEFRA	●	●	18	16,4	0,6	1,2	5	4,4
160416 PEFRA	●	●	17,5	16,4	0,5	1,6	5	4,4
160420 PEFRA	●	●	17,5	16,4	0,5	2,0	5	4,4
160430 PEFRA	●	●	17	16,4	0,7	3,0	5	4,4
160432 PEFRA	●	●	17	16,4	0,5	3,2	5	4,4
AECT 160440 PRFRA	●	●	16,5	16,4	0,5	4,0	5	4,4
160450 PEFRA	●	●	16	16,4	0,4	5,4	5	4,4



Spare Parts

Screw	Insert Wrench	Applicable Endmill
 3,0 N·m		
BFTX 0408	TRD 15	Ø 50 – Ø 125

● = Euro stock
❑ = Delivery on request

H39-40

N·m Recommended Tightening Torque (N·m)

WAX 4000 RS Type

22–24mm 90°

(Shellmill



Body

(For inserts with nose radius ≤ 3,2 mm)

Cat. No.	Stock	Dimensions (mm)							No.of teeth	Weight (Kg)
		DC	DCB	LF	D2	KWW	KDP	CBDP		
WAX 4050RS-3.2	❑	50	16	50	9	8,4	5,6	18	2	0,37
4063RS-3.2	❑	63	22	50	11	10,4	6,3	21	3	0,54
4080RS-3.2	❑	80	27	50	13,5	12,4	7	23	4	0,81
WAX 4100RS-3.2	❑	100	32	63	18	14,4	8	26	5	1,7
4125RS-3.2	❑	125	40	63	22	16,4	9	29	6	2,6

Body

(For inserts with nose radius ≥ 4,0 mm)

Cat. No.	Stock	Dimensions (mm)							No.of teeth	Weight (Kg)
		DC	DCB	LF	D2	KWW	KDP	CBDP		
WAX 4050RS-4.0	❑	50	16	50	9	8,4	5,6	18	2	0,37
4063RS-4.0	❑	63	22	50	11	10,4	6,3	21	3	0,54
4080RS-4.0	❑	80	27	50	13,5	12,4	7	23	4	0,81
WAX 4100RS-4.0	❑	100	32	63	18	14,4	8	26	5	1,7
4125RS-4.0	❑	125	40	63	22	16,4	9	29	6	2,6

Inserts for WAX 4000 Type

Application	DLC Coated	Carbide
High Speed / Light cut	K N	N
General Purpose		N
Roughing		

Cat. No.	DL1000	H1	Dimensions (mm)					
			APMX	INSL	BS	RE	S	D1
AECT 220604 PEFRA	❑	❑	24	21,8	1,5	0,4	6,35	6
220608 PEFRA	❑	❑	24	21,8	1,2	0,8	6,35	6
220612 PEFRA	❑	❑	24	21,8	0,8	1,2	6,35	6
220616 PEFRA	❑	❑	24	21,8	0,4	1,6	6,35	6
220620 PEFRA	❑	❑	24	21,8	0,5	2,0	6,35	6
220630 PEFRA	❑	❑	23	21,8	0,6	3,0	6,35	6
220632 PEFRA	❑	❑	23	21,8	0,4	3,2	6,35	6
AECT 220640 PRFRA	❑	❑	22	21,8	1,2	4,0	6,35	6
220650 PEFRA	❑	❑	22	21,8	0,4	5,0	6,35	6



Spare Parts

Screw	Insert Wrench	Applicable Endmill
 5,0 N·m		
BFTX0511N	TRD20	Ø 50 – Ø 125

☞ H41

ANX Series

New

Features

- **Drastically Reduced Runout Adjustment Time**
  Simple screw-fastening structure enables fine adjustments to be made easily.

- **Blade Through Coolant**
  Secures a supply of coolant to the cutting edge and breaks chips thoroughly.

- **Lightweight Aluminum Alloy Body**
  Utilizing aluminum alloy to achieve a total weight of less than 1,3 kg for a Ø 125 mm cutter with 22 teeth.

Product Range

Type	Cat. No.	Body Material	Diameter Range (mm) / No of Teeth							
			Ø32	Ø40	Ø50	Ø63	Ø80	Ø100	Ø125	Ø160
Shell	ANXA 16000RS	Aluminum Alloy					10, 14	12, 18	14, 22	20, 28
	ANXA 16000R (Inch)	Aluminum Alloy					10, 14	12, 18	14, 22	20, 28
	ANXS 16000RS	Steel		6	6, 9	8, 12	10, 14	12, 18	14, 22	
	ANXS 16000R (Inch)	Steel				8, 12	10, 14	12, 18	14, 22	
Shank	ANXS 16000E ☞ H61	Steel	4	6						

Inch Inch Bore

Blade Selection Guide

Work Material	N					
Type	L	G	GX	H	—	W
Cutting Edge Shape						
Features	Low Cutting Force	Standard	Long Edge	High Strength	Corner Radius	Wiper
Applications	Finishing / Light Cutting	General Purpose	Roughing			
Edge Length*	6,0 mm	6,0 mm	9,0 mm	6,0 mm		

*Edge length
GX type = 9,0 mm

Edge Selection Guide



- **Reduces Running Costs by Drastically Increasing Blade, Insert Regrinding Allowance (to 1,0 mm)**

Assuming 0,2 mm of regrinding each time, an edge can be used up to 6 times.
(Peripheral edge cannot be reground.)





If you wish to use reground blades you shall use sets of blades with matching size of the same level in order to keep the balance.

Performances

High-Speed / High-Efficiency Cutting

Realizes ultra-high efficiency machining with v_f = 30.000 mm/min



Comparison: Cutter Diameter Ø 100 mm

	Spindle Speed min^{-1}	Number of Teeth	Feed Rate v_f (mm/min)
ANX Series	18.000	18	32.400
Competitor	9.500	12	11.400

Drastically Reduces Runout Adjustment Time

– Simple screw-fastening structure
– Enables fine adjustments to be made easily
– High-rigidity body





Chip Control

Blade-Through Coolant Chip Breaking

ALNEX ANX Series | Competitor

Work Material:	G-AlSi12Cu
Cutting Conditions:	v_c = 2500 m/min, f_z = 0,05 mm/t, a_p = 0,5 mm, wet

ANXS 16000 R(S)

New

Rake Angle		
	Radial	+5°
	Axial	+5°

3 mm | 90°

Fig. 1



Fig. 2



Body - ANXS (Steel)

Dimensions (mm)

	Cat. No.	Stock	DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2	No. of Teeth	Weight (kg)	Fig.
Metric	ANXS 16040RS06	❍	38	40	38,5	40	16	8,4	5,6	26	14	9	6	0,3	1
	16050RS06	❍	48	50	48,5	40	22	10,4	6,3	26	18	11	6	0,4	1
	16050RS09	❍	48	50	48,5	40	22	10,4	6,3	26	18	11	9	0,5	1
	16063RS08	❍	61	63	50	40	22	10,4	6,3	26	18	11	8	0,7	1
	16063RS12	❍	61	63	50	40	22	10,4	6,3	26	18	11	12	0,7	1
	16080RS10	❍	78	80	50	50	27	12,4	7	34	35	14	10	1,2	1
	16080RS14	❍	78	80	50	50	27	12,4	7	34	35	14	14	1,2	1
	16100RS12	❍	98	100	80	50	32	14,4	8	32	46	–	12	2,0	2
	16100RS18	❍	98	100	80	50	32	14,4	8	32	46	–	18	2,0	2
	16125RS14	❍	123	125	80	63	40	16,4	9	35	52	–	14	3,9	2
	16125RS22	❍	123	125	80	63	40	16,4	9	35	52	–	22	3,9	2
Inch	ANXS 16063R08	❍	61	63	50	50	25,4	9,5	6	31	20	14	8	0,9	1
	16063R12	❍	61	63	50	50	25,4	9,5	6	31	20	14	12	0,9	1
	16080R10	❍	78	80	50	50	25,4	9,5	6	34	35	14	10	1,2	1
	16080R14	❍	78	80	50	50	25,4	9,5	6	34	35	14	14	1,2	1
	16100R12	❍	98	100	80	50	31,75	12,7	8	36	42	–	12	2,0	2
	16100R18	❍	98	100	80	50	31,75	12,7	8	36	42	–	18	2,0	2
	16125R14	❍	123	125	80	63	38,1	15,9	10	42,5	52	–	14	3,9	2
	16125R22	❍	123	125	80	63	38,1	15,9	10	42,5	52	–	22	3,9	2

Blades are sold separately. If using a blade for corner radius machining (ANB1604R), DC = DCX.

Identification Details

ANX	S	16	100	R	S	18
Cutter Series	Steel Body	Blade Size	Cutter Diameter	Feed Direction	Metric	Number of Teeth

Blades

☞ G64

Recommended Cutting Conditions

☞ G64

Max. Allowable Spindle Speed

Cat. No.	n max (min^{-1})
ANXS 16040RS06	25.000
16050RS06	25.000
16050RS09	25.000
16063RS08	22.000
16063RS12	22.000
16080RS10	20.000
16080RS14	20.000
16100RS12	18.000
16100RS18	18.000
16125RS14	16.000
16125RS22	16.000
ANXS 16063R08	22.000
16063R12	22.000
16080R10	20.000
16080R14	20.000
16100R12	18.000
16100R18	18.000
16125R14	16.000
16125R22	16.000

Spare Parts

Sold separately.

Applicable Cutters	Clamp Screw		Adjustment Screw	Wrench	Adjustment Wrench	Centre Bolt	Assembly Wrench
							
ANXS 16040RS06	BXA0310IP	2,0	HFJ	TRXW10IP	ANT	BXH0825-D13	HFVT
16050RS_ _						BXH1030-D16	
16063RS_ _							
16080RS_ _						BXH1235-D33	
16100RS_ _						BXH1635-D40	
16125RS_ _						BXH2036-D50	
16063R_ _						BXH1235-D18	
16080R_ _						BXH1235-D33	
16100R_ _						BXH1635-D40	
16125R_ _						BXH2036-D50	

❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

ANXA 16000 R(S)

New

Rake Angle		
	Radial	+5°
	Axial	+5°

3 mm | 90°



Fig. 1



Body - ANXA (Aluminum Alloy)

Dimensions (mm)

	Cat. No.	Stock	DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2	No. of Teeth	Weight (kg)
Metric	ANXA 16080RS10	❍	78	80	50	50	27	12,4	7	34	35	14	10	0,5
	16080RS14	❍	78	80	50	50	27	12,4	7	34	35	14	14	0,5
	16100RS12	❍	98	100	50	50	27	12,4	7	34	35	14	12	0,8
	16100RS18	❍	98	100	50	50	27	12,4	7	34	35	14	18	0,9
	16125RS14	❍	123	125	50	50	27	12,4	7	34	35	14	14	1,2
	16125RS22	❍	123	125	50	50	27	12,4	7	34	35	14	22	1,3
	16160RS20	❍	158	160	80	63	40	16,4	9	35	52	29	20	2,6
	16160RS28	❍	158	160	80	63	40	16,4	9	35	52	29	28	2,6
Inch	ANXA 16080R10	❍	78	80	50	50	25,4	9,5	6	34	35	14	10	0,5
	16080R14	❍	78	80	50	50	25,4	9,5	6	34	35	14	14	0,5
	16100R12	❍	98	100	50	50	25,4	9,5	6	34	35	14	12	0,9
	16100R18	❍	98	100	50	50	25,4	9,5	6	34	35	14	18	0,9
	16125R14	❍	123	125	50	50	25,4	9,5	6	34	35	14	14	1,2
	16125R22	❍	123	125	50	50	25,4	9,5	6	34	35	14	22	1,3
	16160R20	❍	158	160	80	63	38,1	15,9	10	42,5	55	30	20	2,4
	16160R28	❍	158	160	80	63	38,1	15,9	10	42,5	55	30	28	2,6

Blades are sold separately. If using a blade for corner radius machining (ANB1604R), DC = DCX.

Identification Details

ANX	A	16	100	R	S	18
Cutter Series	Aluminum Alloy Body	Blade Size	Cutter Diameter	Feed Direction	Metric	Number of Teeth

Blades

☞ G64

Recommended Cutting Conditions

☞ G64

Max. Allowable Spindle Speed

Cat. No.	n max (min^{-1})
ANXA 16080RS10	20.000
16080RS14	20.000
16100RS12	18.000
16100RS18	18.000
16125RS14	16.000
16125RS22	16.000
16160RS20	14.000
16160RS28	14.000
ANXA 16080R10	20.000
16080R14	20.000
16100R12	18.000
16100R18	18.000
16125R14	16.000
16125R22	16.000
16160R20	14.000
16160R28	14.000

Spare Parts

Sold separately.

Applicable Cutters	Clamp Screw		Adjustment Screw	Wrench	Adjustment Wrench	Centre Bolt	Assembly Wrench
							
ANXA 16080RS_ _	BXA0310IP	2,0	HFJ	TRXW10IP	ANT	BXH1235-D33	HFVT
16100RS_ _							
16125RS_ _						BXH2036-D50	
16160RS_ _							
16080R_ _						BXH1235-D33	
16100R_ _							
16125R_ _							
16160R_ _						BXH2036-D50	

Blades

Application	SUMIDIA
High Speed / Light Cut	N
General Purpose	N
Roughing	N

Cat. No.	DA1000	Cutting Edge Length	Wiper Edge Shape	Applications	Fig.
ANB 1600R-L	❍	6,0	Linear	Low Cutting Force	1
1600R-G	❍	6,0	Arc-Shaped	General Purpose	1
1600R-H	❍	6,0	Arc-Shaped	Strong Edge	1
1600R-GX	❍	9,0	Arc-Shaped	Long Edge	2
1604R	❍	6,0	Linear	Corner Radius	3
1600R-W	❍	–	Arc-Shaped	Wiper	4

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Wiper Blade

Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

ISO	Work Material	Hard-ness	Cutting Speed v_c (m/min)	Feed Rate f_z (mm/t)	Grade
N	Aluminium alloy	–	2.000–**2.500**–3.000	0,05–**0,13**–0,20	DA1000

Si content ≥ 12,6 %

Min. - **Optimum** - Max.

ISO	Work Material	Hard-ness	Cutting Speed v_c (m/min)	Feed Rate f_z (mm/t)	Grade
N	Aluminium alloy	–	400–**600**–800	0,05–**0,13**–0,20	DA1000

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

❍ = Japan stock

Recommended Tightening Torque (N·m)

■ ALNEX Series Usage Manual

● Adjustment of the Blades, Runout Alignment

① Before inserting the blade, make sure that the seat and screws are free of debris by cleaning those areas.

② Insert the blade into its seat.

③ While holding the blade against the seat, install the clamping bolt using the provided wrench, pre-tightening the bolt (recommended pre-torque is 1 N·m).

④ Using the provided wrench for the height adjustment screw, set the height to your predetermined value.

⑤ Fully tighten the clamp bolt (recommended torque is 2 N·m).

⑥ Use 1 blade as a datum point and adjust all blade heights to match.

⑦ After tightening, verify that there is no gap between the seat and blade.

② 

③ 
Pre-tighten (1N·m)

④ 
Adjust height

⑤ 
Final tighten (2N·m)

● Balance Adjustments

The cutter comes pre-balanced to a G 6,3 specification.
Under normal circumstances, it is not necessary to adjust the balance of the cutter.



● Clamp Bolts for Arbor

Work Material	Dim.			Max. Torque	Applicable Cutters
	M	L	D		
BXH0825-D13	8	25	13	15	ANXS16040RS_ _
BXH1030-D16	10	30	16	25	ANXS16040RS_ _ , ANXS16063RS_ _
BXH1235-D18	12	35	18	40	ANXS16063R_ _
BXH1235-D33	12	35	33	50	ANXS16080R(S)_ _ , ANXA16080/100/125R(S)_ _
BXH1635-D40	16	35	40	100	ANXS16100R(S)_ _
BXH2036-D50	20	36	50	200	ANXS16125R(S)_ _ , ANXA16160R(S)_ _



● Other Precautions

- Please use only Sumitomo genuine parts.
- Please regularly replace clamp bolts.
- If you wish to reduce the # of effective blades in use, to maintain balance and protect the body, please use dummy blades (set height well below effective blades).
- Please do not operate after releasing the interlock or opening the cover.
- Please avoid use and consult with Sumitomo if you mistakenly crash the body.
- As the blades are very sharp, it is very easy to get hurt when touching the blades with your hands directly, so please wear gloves when taking the blade out of the case to set into the cutter or when setting the cutter into machine tool.

RF Type

High Speed Finishing of Aluminium Alloy

Fig. 1



Fig. 2



■ Body

Cat. No.	Stock	Dimensions (mm)								No. of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP				
RF 4080 RS	●	80	82	60	50	27	12,4	7,0	29	6	3,0	0,7	1
RF 4100 RS	●	100	102	75	50	32	14,4	8,5	29	6		1,0	1
4125 RS	●	125	127	75	63	40	16,4	9,5	29	8		1,6	1
4160 RS	❑	160	162	100	63	40	16,4	9,5	29	10		2,6	2

Remark: PCD blades and inserts are not included.

■ Insert for Roughing and Finishing



Fig. 1



Fig. 2



Fig. 3

Application	Carbide	SUMIDIA		
High Speed / Light cut	N	N	N	
General Purpose	N	N	N	
Roughing	N	N	N	
Cat. No.	**H1**	**DA1000**	**DA2200**	**Fig.**
SDET 1204 ZDFR	●			1
SNEW 1204 ADFR-NF		●	▲	2
SNEW 1204 ADFR-W-NF		❍	▲	3

■ Structure



■ "Sumidia" Blade

PCD grade DA2200	Cat. No.	Stock
Standard type 	**RFB**	❑
Wiper type 	**RFBW**	❑

■ Cartridge

Shape	Cat. No.	Stock
For carbide insert 	**RFR**	●
For Sumidia insert 	**RFF**	●

■ Dummy Blade

	**RFD**	❑

■ Cutting Insert Selection

For easy assembling:
PCD blade **RFB**
PCD blade **RFB** (wiper type)

For finishing:
Cartridge **RFF**
PCD insert SNEW 1204 ADFR-NF (standard type)
SNEW 1204 ADFR-W-NF (wiper type)
PCD grade: DA1000

For roughing:
Cartridge **RFR**
Uncoated carbide insert
SDET 1204 ZDFR, grade: H1

■ Spare Parts

		 10,0 N·m	 3,0 N·m			 6,0 N·m	 TH050 TH015,TH025	
Cover	Position setting stoper	Main clamp screw	Sub clamp screw	Cover clamp screw	Adjustment screw	Insert clamp screw	Insert wrench	Cartridge wrench
RFC	RFS	BX0620	BTD0510	FBUP2-A0-8	RFJ	BFTX0509N	TH015, TH025 TH050	TTX20

■ Setting Gauge

RF-SET

Dial-gauge is not included.

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item

High Speed Finishing of Aluminium Alloy

Fig. 1



Fig. 2



Body

Cat. No.	Stock	Dimensions (mm) DC	Dimensions (mm) DCSFMS	No. of teeth	Fig.	Weight (Kg)
SRF 30 R-ST	❍	30	-	3	1	0,34
SRF 40 R-ST	❍	40	-	4	1	0,50
SRF 50 RS	❑	50	46,5	5	2	0,59
SRF 63 RS	❑	63	45,0	6	2	0,67

Inserts are sold seperately.

Inserts



Fig. 1 Fig. 2 Fig. 3

Application	SUMIDIA
High Speed / Light cut	N
General Purpose	N
Roughing	N

Cat. No.	DA1000	Cutting Edge	Fig.
SNEW 09T3 ADTR-NF	❍	Standard	1
09T3 ADTR-U-NF	❍	Wiper	2
09T3 ADTR-R-NF	❍	Nose Radius	3

- Standard inserts and Wiper inserts can be used on the same cutter body.
- Standard inserts with nose radius should be used where vibration is present. As such, Wiper-inserts will not be applicable.
- Inserts can be regrind 3 times (up to minimum IC diameter 9,225 mm).
- When using reground inserts, it is advisable to reconfirm insert height and cutting diameter with a tool pre-setter.
- Do not mix new and reground inserts, or even inserts with different regrind amount on the same cutter.

Spare Parts



Maximum D.O.C. Guide (SRF50RS, 5 teeth)

The contains guidelines on the maximum D.O.C., determined from internal tests. "O" mark indicates the possible application range. Actual cutting conditions should be set, based on actual machine and work characteristics.

D.O.C. (mm) \ Feed	Feed Speed, v_f (mm/min) 2.500	4.000	5.000
	Feed Rate, f_t (mm/tooth) 0,05	0,08	0,10
0,5	○	○	○
1,0	○	○	○
1,5	○	○	○
2,0	○	○	○
2,5	○	○	○
3,0	○	○	○
3,5	○	○	–
4,0	○	–	–
4,5	○	–	–
5,0	○	–	–

● Cutting Conditions

Cutter: SRF 50 RS
Insert: SNEW 09T3 ADFR-NF (DA1000)
n : 10.000 rpm
Width: 35mm at D.O.C. indicated above

Recommended Cutting Conditions for RF and SRF Type Cutters

Work Material		Process	Grade	Cutting Speed (m/min) RF Type	Cutting Speed (m/min) SRF Type	Feed Rate (mm/tooth)	Depth of Cut (mm) RF Type	Depth of Cut (mm) SRF Type
Aluminium Alloy	Si < 13 %	Finishing	**DA1000** (PCD)	2.000–5.000	–4.000	0,05–0,2	–3,0	–5,0
		Roughing	H1 (Carbide)	1.000–2.500	–			
	Si ≥ 13 %	Finishing	**DA1000** (PCD)	400–800	–800			
		Roughing	H1 (Carbide)	200–400	–			

FMU Type

High Speed Finishing of Grey Cast Iron

Features

- High speed machining v_c=1.500m/min
- Excellent surface roughness Rz = 3,2 (Ra = 1,0)
- Safety structure for the centrifugal force under high speed cutting conditions
- Run-out is less than 10 µm
- Easy assembling method using the setting gauge
- Running cost is reduced because of economical insert

SUMIBORON ”BN Finish Mill”

Application

GG25–GG30 (HB200–250) grey cast iron with pearlite matrix, and ferrite matrix (HB130–160)
Application examples: engine block, cylinder block, etc

Specifications

FMU Type: ø80–ø315 mm
Insert: SNEW1203ADTR/L
Low cutting force type: SNEW1203ADTR/L-S

Recommended Cutting Conditions

Speed: v_c = 800–2000 m/min
Feed: f_t = 0,1–0,3 mm/tooth
Depth: a_p = 0,5 mm or less
Dry cutting

Performance

● Tool Life Diagram



Work Material : GG25 H_B 240 (Pearlite)
Cutting Speed : v_c = 600–4000 m/min
Feed Rate : f_t = 0,15 mm/tooth
Depth of Cut : a_p = 0,5 mm, Dry

● Estimated Tool Life



Work Material : GG25 H_B 240 (Pearlite)
Cutting Speed : v_c = 400–4000 m/min
Feed Rate : f_t = 0,15 mm/tooth
Depth of Cut : a_p = 0,5 mm, Dry

- Milling of ductile cast iron and alloy steel casting do not produce the best results.
- Dry cutting is recommended. Wet cutting will result in chipping of cutting edges in the early stages due to thermal cracking.

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
Recommended Tightening Torque (N·m)

FMU Type

Specifications

Approach angle: 90°
Axial rake angle: + 8°
Radial rake angle: + 2°



Structure



Body

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Fig. 5



Cat. No.	Stock	Dimensions (mm)								No. of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP				
FMU 4080 RS	●	80	82,8	60	63	27	12,4	7,0	25	6	0,5	1,6	1
FMU 4100 RS	●	100	102,8	76	63	32	14,4	8,5	29	8		2,4	2
4125 RS	❑	125	127,8	75	63	40	16,4	9,5	29	10		3,4	2
4160 RS	❑	160	162,8	100	63	40	16,4	9,5	29	12		5,6	3
FMU 4200 RS	❑	200	202,8	130	63	60	25,7	14,0	38	16		9,2	4
4250 RS	❑	250	252,8	130	63	60	25,7	14,0	38	20		14,3	4
FMU 4315 RS		315	317,8	240	80	60	25,7	14,0	40	24		27,8	5

Inserts

Fig. 1



Fig. 2



Application	CBN	
High Speed / Light cut	K	K
General Purpose	K	K
Roughing		

Cat. No.	BN700	BN7000	Figure
SNEW 1203 ADT R	▲	❍	1
1203 ADT R-S	▲	❍	2

Cartridge



Cartridge	Insert Screw	Adjustment Screw	O-ring	Insert Wrench	Pin
FMUU	BFTX0509N	FMUJ	P3	TRX20	1,8 x 45

Spare Parts



Cartridge Screw	Screw	Setting clamp	Double screw	Wrench	Wrench	Wrench
BH0620	BTD0609	FMUE	WB5-10	TH040	LH030	LH025

Gauge

RF-SET

Dial-gauge is not included.

Indexable Endmills

H1–H62

Selection Guide

Application	Cutter Type	Series	Insert Type	Approach Angle / Max. Depth of Cut (mm)	Cutter Diameter (mm)	Application: Face Milling – General Purpose	Face Milling – Finishing	Face Milling – High Feed	Shoulder Milling	Groove Milling	Ramping	Chamfering	Drilling	Profiling	Profile Finishing	Work Material: P – Carbon Steel / Alloy Steel	P – Tempered Steel / Die Steel	M – Stainless Steel	K – Cast Iron / Ductile Cast Iron	N – Non-Ferrous Metal	N – Aluminium Alloy	S – Ti Alloy / Heat Resistant Alloy	H – Hardened Steel HRC 45–55	Ref. Page
Face Milling	DGC	DGC 13000-EW	SNMU13T6.. ONMU05T6..	3–6 mm, 45°	40(42,9)–63 (65,9)	◎				○						◎	◎	◎	◎	◎	◎	○		H6
	WGX	WGX 13000-EW	SEE/MT 13T3..	6 mm, 45°	32–63	◎	◎			○						◎	◎	◎	◎	◎	◎	○		H7
High Feed Milling	MSX	MSX(ES/EM/EW) 06000 08000 12000 14000	WDMT0603.. WDMT0804.. WDMT1205.. WDMT1406..	1,0–2,5 mm, 20°	16–63			◎	○	○	○					◎	◎	◎	◎				○	H9
	MSX-M	MSX 06000-M 08000-M 12000-M		1,0–2,0 mm, 20°	16–40			◎	○	○	○					◎	◎	◎	◎				○	H10
	WFXH-M	WFXH 08000-M	(12000 Type) SOMT 1204..	1,5 mm, 15°	25–32			◎	○	○	○					◎	◎	◎	◎	◎	◎	○		H13
		WFXH 12000-M		2,5 mm, 15°	40																			
Shoulder Milling	DFC	DFC (M) 09000-E	XNMU 0606..	6 mm, 90°	25–80	◎	○		◎	○						◎	◎	○	◎			○		H15
	WFX	WFX(M/F) 08000-E 12000-E	SOMT 0803..	6 mm, 90°	20–80	○	◎		◎	○						◎	◎	◎	◎	◎	◎	○		H16 H17
	WFX-M	WFX 08000-M	SOMT 1204..	10 mm, 90°																				
	TSX	TSX (-F) 08000E TSX (-M) 13000E	LNEX 0804..,LNEX1306..	8 mm, 90°	40–63	◎	◎		◎	○						◎	◎	◎	◎	◎	◎	◎		H19
				12 mm, 90°	40–160																			
	WEZ New	WEZ 11000-E/EL	AOMT 170502-PEER-G	10 mm, 90°	14–80	◎	◎		◎	◎	◎					◎	◎	◎	◎	◎	◎	◎		H24 H26 H28 H30
		WEZ 17000-E/EL		15 mm, 90°	25–80																			
	WEX	WEX 1000-E/EL	AXMT0602 (WEX 1000 E/F)	5 mm, 90°	10–25	◎	◎		◎	◎	◎					◎	◎	◎	◎	◎	◎	◎		H34 H35 H36
		WEX 2000-E/EL		10 mm, 90°	14–63																			
		WEX 3000-E/EL	AXMT1235 (WEX 2000 E/F/M)	14 mm, 90°	25–63																			
	WEX-M	WEX 2000-M		10 mm, 90°	16–40	○			◎	◎	○					◎	◎	◎	◎	◎	◎	◎		H35 H36
		WEX 3000-M	AXMT1705.. (WEX 3000 E/F/M)	14 mm, 90°	25–40																			
	WRX	WRX 2000-E/W	AXMT1235.. (WRX2000)	18–36 mm, 90°	20–40	○			◎	◎	○					◎	◎	◎	◎	◎	◎	◎		H45 H46
		WRX 3000-E/W	AXMT1705.. (WRX3000)	27–53 mm, 90°	32–50																			

◎ : Preferred choice
○ : Suitable

Application	Cutter Type	Series	Insert Type	Approach Angle / Max. Depth of Cut (mm)	Cutter Diameter (mm)	Application: Face Milling – General Purpose	Face Milling – Finishing	Face Milling – High Feed	Shoulder Milling	Groove Milling	Ramping	Chamfering	Drilling	Profiling	Profile Finishing	Work Material: P – Carbon Steel / Alloy Steel	P – Tempered Steel / Die Steel	M – Stainless Steel	K – Cast Iron / Ductile Cast Iron	N – Non-Ferrous Metal	N – Aluminium Alloy	S – Ti Alloy / Heat Resistant Alloy	H – Hardened Steel HRC 45–55	Ref. Page
Multi-Purpose	WRCX 	WRCX 08000-E 10000-E	QPMT 0803../10T3../1204.. QPET 10T35../1204..	4–5 mm	12–32	◎		○	◎	○	◎			◎		◎	◎	◎	◎		◎	○	○	H52
	WRCX-M 	WRCX 08000-M 12000-M		4–6 mm	20–40	◎		○	○	○	◎			◎		◎	◎	◎	◎		◎	○	○	H53
	RSX 	RSX(F) 08000-ES 10000-ES 12000-ES	RDET0803..RDET10T3.. RDET1204..	4 mm 5 mm 6 mm	20– 32(ES) 40(M)	◎		○	◎	○	◎			◎		◎	◎	◎	◎			◎		H54 H55
	RSX-M 	RSX(F) 08000-M 10000-M 12000-M																						
	WMM(H) 	WMM(H) 2000 3000	APMT 1035../1605.. APET 1035../1605..	17–26 mm 90° 39 mm 90°	20–25 32–40	◎			◎	◎	◎		○			◎	◎	◎	◎	◎	◎	◎		H43
Alumimium	WAX 	WAX 3000-E/EL	AECT1604.. (WAX 3000E/EL)	16–18 mm 90°	20–40	○			◎	◎	◎			◎						○	◎			H40 H41
		WAX 4000-E/EL	 AECT2206.. (WAX 4000E/EL)	22–24 mm 90°	25–40																			
3D Profiling	WBMR 	WBMR 2000	ZNMT 1804100-C 2004100-S	20–43 mm	R10 (20)– R25 (50)					◎				◎		◎	◎	◎	◎			○	○	H49
		WBMR 2000-L																						
	WBMF 	WBMF 1000	ZPGU 1551050	0,1–0,4 mm	R5 (10)– R15 (30)					◎				◎	◎	◎	◎	◎	◎				○	H51
Chamfering	WFXC-E 	WFXC 08000-E	SOMT0803../1204.. SOET0803../1204..	45°	08–16							◎				◎	◎	◎	◎	◎	◎	○		H57
		WFXC 12000-E			25–32																			
	WFXC-M 	WFXC 08000-M		45°	16							◎				◎	◎	◎	◎	◎	◎	○		H58
		WFXC 12000-M			25–32																			
	ANX New 	ANXS 16000-E	ANB 1600R-L 	3 mm 90°	32–40	○	◎	◎	◎											◎	◎			H61

Modular Tools

General Features

- Exchangeable head endmills are available in 7types !
  - Endmill for Shoulder Milling **WFX** Type
  - High Feed Endmill **WFXH** Type
  - Radius Endmill **RSX** Type
  - Endmill for Chamfering **WFXC** Type
  - Endmill for Shoulder Milling **WEX** Type
  - High Feed Endmill **MSX** Type
  - Multipurpose Radius Endmill **WRCX** Type
- A wide variety of possible combinations with carbide arbors (16 items) and steel arbors (4 items) !

Characteristics

● Up to 6 x D from Modular End Mill with Carbide Arbor

Modular Head + Carbide Arbor



Standard Shank Type Endmill



Work Material	:	C50
Tool	:	WEX2025M12Z4 (ø D = 25, 4 teeth)
Cutting Conditions:		v_c = 100 m/min, f_t = 0,1 mm/tooth
		a_p = 8 mm x 3 passes, a_e = 2,0 mm, Equipment: M/C BT50

Note
Cutting conditions can vary according to cutter reach, rigidity of machine tool / workpiece etc.

Performance

● A Carbide Arbor improves feed rates, surface finish, sizing, and tool life.



● **Shoulder Milling Squareness**



Carbide Arbor Comparison ...



Work Material	:	C50
Tool	:	WEX2025M12Z4 (ø D = 25, 4 teeth)
Cutting Conditions:		v_c = 100 m/min, f_t = 0,1mm/tooth
		a_p = 8 mm x 3 passes, a_e = 2,0 mm, Equipment: M/C BT50

Suitable for milling with **long overhangs** when combined with carbide or steel arbors!

Economically designed exchangeable head!

Easy to change screw-on endmill type WEX and carbide arbor

● = Euro stock

Recommended Tightening Torque (N·m)

Modular Type

Carbide and Steel Arbor





Carbide Arbor

Cat. No.	Stock	Dimensions (mm)						
		CRKS	DCB	DMM	LF2	L4	L5	LF*
MA 15 M08 L120C	●	M8	8,5	15	120	10	18	145
15 M08 L160C	●	M8	8,5	15	160	10	18	185
MA 16 M08 L120C	●	M8	8,5	16	120	10	18	145
16 M08 L160C	●	M8	8,5	16	160	10	18	185
MA 18 M10 L150C	●	M10	10,5	18	150	10	20	180
18 M10 L200C	●	M10	10,5	18	200	10	20	230
MA 20 M10 L150C	●	M10	10,5	20	150	10	20	180
20 M10 L200C	●	M10	10,5	20	200	10	20	230
MA 23 M12 L200C	●	M12	12,5	23	200	10	22	235
23 M12 L250C	●	M12	12,5	23	250	10	22	285
MA 25 M12 L200C	●	M12	12,5	25	200	10	22	235
25 M12 L250C	●	M12	12,5	25	250	10	22	285
MA 28 M16 L200C	●	M16	17,0	28	200	10	24	240
28 M16 L300C	●	M16	17,0	28	300	10	24	340
MA 32 M16 L200C	●	M16	17,0	32	200	10	24	240
32 M16 L300C	●	M16	17,0	32	300	10	24	340

●*Modular Tool System



Steel Arbor

Cat. No.	Stock	Dimensions (mm)						
		CRKS	DCB	DMM	LF2	L4	L5	LF*
MA 16 M08 L120S	●	M8	8,5	16	120	10	18	145
MA 20 M10 L150S	●	M10	10,5	20	150	10	20	180
MA 25 M12 L200S	●	M12	12,5	25	200	10	22	235
MA 32 M16 L200S	●	M16	17,0	32	200	10	24	240

Identification of Catalogue No.

MA 15 M08 L120 C

- MA: Modular Arbor
- 15: Shank Diameter
- M08: Mounting Screw
- L120: Arbor Length
- C: Material (C: Carbide, S: Steel)

Recommended Tightening Torque

Screw	Wrench		(N·m)
	W	S	
M 8	8	13	23
M10	8	15	46
M12	10	19	60
M16	10	24	80

Notes about tightening the head:

- Refer to the Head Cat. No. chart on pages H18, H19, H35 and H37 to select the arbor size in the table above.
- Check the mounting screw size of the head and arbor beforehand.
- When attaching head to an arbor, follow the standard tighting torque in the table above.

Product Range

Application	Work Material	Series	Cat. No.	Page
Shoulder Milling	Shoulder milling of Steel, Die Steel, Cast Iron, Stainless Steel and Non-Ferrous Metal	„Wave Mill“ - Series	WFX 08000-M	☞ H16
	High efficiency milling of Steel, Cast Iron, Stainless Steel and Non-Ferrous Metal	„Wave Mill“ - Series	WEX 2000-M 3000-M	☞ H35 ☞ H36
High Feed Milling	High feed milling of Steel, Die Steel, Cast Iron, Stainless Steel and Non-Ferrous Metal	„Wave Mill“ - Series	WFXH 08000-M 12000-M	☞ H13
	High feed milling of Steel, Cast Iron and Stainless Steel	„Metal Slash Mill“ - Series	MSX 06000-M 08000-M 12000-M	☞ H10
Radius Milling	Milling of Exotic Alloy	„Wave Radius Mill“ - Series	WRCX 08000-M 12000-M 16000-M	☞ H53
	Milling of Steel, Cast Iron, Stainless Steel and Non-Ferrous Metal	„Wave Radius Mill“ - Series	RSX(F) 10000-M 12000-M	☞ H55
Chamfering	Chamfering of Steel, Die Steel, Cast Iron, Stainless Steel and Non-Ferrous Metal	„Wave Mill“ - Series	WFXC 08000-M	☞ H58

"Sumi Dual Mill" Face Mill
DGC (EW) Type

General Milling for Steel and Cast Iron

Rake Angle		
	Radial	-10°
	Axial	-5°

SNMU / SNEU: 6 mm, 45°

ONMU / ONEU: 3 mm, 45°

Body – Shank Type



Body

Cat. No.	Stock	Dimensions (mm)						No. of Teeth	Weight (kg)
		DC	DCX	DMM	LH	LS	LF		
DGC 13040 EW	●	40 (42,90)	54	32	40 (38,44)	85	125	3	0,7
13050 EW	●	50 (52,90)	65	32	40 (38,44)	85	125	3	0,9
13063 EW	●	63 (65,90)	77	32	40 (38,44)	85	125	4	1,1

( ) Figures in brackets indicate values for inserts of type ONMU

Identification Details

DGC	13	040	EW
Cutter Series	Insert Size	Cutter Diameter	Endmill Type Weldon

Inserts

Application	Coated Carbide							
High Speed/Light cut	P			K		MS		
General Purpose		PM	M	K		MS		
Roughing		PM	PM		K		MS	
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	Fig.
SNMU 13T6ANER L	●	●	●	●	●			1
13T6ANER G	●	●	●	●	●			1
13T6ANER H	●	●	●	●	●			1
13T6ANER FL	●	●	●	●	●			2
13T6ANER FG	●	●	●	●	●			2
SNEU 13T6ANER L						●	●	1
13T6ANER G						●	●	1
13T6ANER FL						●	●	2
13T6ANER FG						●	●	2
XNEU 13T6ANEN W		●			●			3
ONMU 05T6ANER L	●	●	●	●	●			4
05T6ANER G	●	●	●	●	●			4
ONEU 05T6ANER L						●	●	4
05T6ANER G						●	●	4

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Attaching Octagonal Inserts

Firmly align insert with supporting face, press down in the direction of the arrow and tighten the screw to fix the insert.

Press down firmly from above



Spare Parts

Shim	Shim Screw	L Seat Wrench	Insert Srew	Insert Wrench
				
DGCS 13 R	BW 0609 F	LH 040	BFTX 0412 IP	TRDR 15 IP

Optional

Insert Srew (*)

BFTX 0418 IP

*Corners can be changed simply by loosening the screw. (Only suitable for DGC / DGCM types with body size ≥ Ø 80).

SNMU – Recommended Cutting Conditions

ISO	Work Material	Fit-ness	Cutting Speed v_c (m/min)	Feed Rate f_t (min/t)	Depth of Cut (mm)	Grade
P	General Steel	◎	150–**200**–250	0,10–**0,25**–0,40	<4	ACP200 ACP300
P	Alloyed Steel	◎	180–**250**–350	0,10–**0,30**–0,45	<4	ACP200 ACP300
P	Die Steel	◎	100–**150**–200	0,15–**0,25**–0,35	<4	ACP200 ACP300
M	Stainless Steel	○	160–**200**–250	0,15–**0,23**–0,30	<3	ACM200 ACM300 ACP300
K	GG+GGG	◎	100–**200**–250	0,10–**0,25**–0,40	<5	ACK200 ACK300

Min. – **Optimum** – Max.

ONMU – Recommended Cutting Conditions

ISO	Work Material	Fit-ness	Cutting Speed v_c (m/min)	Feed Rate f_t (min/t)	Depth of Cut (mm)	Grade
P	General Steel	◎	150–**200**–250	0,10–**0,30**–0,50	<2	ACP200 ACP300
P	Alloyed Steel	◎	180–**250**–350	0,10–**0,50**–0,50	<2	ACP200 ACP300
P	Die Steel	◎	100–**150**–200	0,15–**0,25**–0,30	<2	ACP200 ACP300
M	Stainless Steel	○	160–**200**–250	0,15–**0,23**–0,30	<2	ACM200 ACM300 ACP300
K	GG+GGG	◎	100–**200**–250	0,10–**0,30**–0,50	<2	ACK200 ACK300

◎ Preferred choice ○ Suitable

● = Euro stock
○ = Japan stock

G6/G7

Recommended Tightening Torque (N·m)

General Milling for Steel and Cast Iron

Rake Angle		
	Radial	-20°–24°
	Axial	20°–22°

6 mm 45°

Body – Shank Type



Body – Dimensions

Cat. No.	Stock	Dimensions (mm)						No. of Teeth
		DC	DCX	DMM	LH	LS	LF	
WGX 13032 EW	❍	32	44	32	40	85	125	3
13040 EW	❍	40	52	32	40	85	125	3
13050 EW	❍	50	62	32	40	85	125	4
13063 EW	❍	63	76	32	40	85	125	5

Inserts are not included.
ø32 mm cutters do not have a seat.

Identification Details

WGX	13	032	EW
Cutter Series	Insert Size	Cutter Diameter	Endmill Type Weldon

Insert Shape Characteristics

Unique wiper edge shape for improved surface roughness



Inserts

Application	Coated Carbide							Carb.	DLC	
High Speed/Light Cut	P			K		MS		KN	N	
General Purpose		PM	M	K		MS	MS		N	
Roughing		PM	PM		K		MS			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Fig.
SEET 13T3AGFR-L								❍	❍	1
SEET 13T3AGSR-L	❍	●	❍	❍	❍	●	❍			1
13T3AGSR-G	❍	●	●	●	❍	●	❍			1
SEMT 13T3AGSR-L	●	●	●	●	❍	●	●			1
13T3AGSR-G	●	●	●	●	●	●	●			1
13T3AGSR-H	●	●	●	●	●	●	●			1
SEMT 13T3AGSR-FG	❍	●	●	❍	●	●	●			2
XEEW 13T3AGER-WR		❍			❍					3

Fig. 1



Fig. 2



Fig. 3





Spare Parts

Applicable Cutters	Seat	Seat Screw	Insert Screw	Insesrt Wrench	N·m	Spanner (for Seat)
WGX 130__EW						
øD = 32	–	–	BFTX 03512 IP	TRDR 15 IP	3,0	–
øD = 40–63	WGCS 13 R	BW 0507 F	BFTX 03512 IP	TRDR 15 IP	3,0	LH 035

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/tooth)	Grade
P	General Steel	180–28	150–**200**–250	0,15–**0,20**–0,25	ACP200
P	Soft Steel	≤ 180	180–**265**–350	0,10–**0,25**–0,40	ACP200
P	Die Steel	200–220	100–**150**–200	0,15–**0,20**–0,25	ACP200
M	Stainless Steel	-	160–**205**–250	0,15–**0,23**–0,30	ACM300
K	Cast Iron	250	100–**175**–250	0,15–**0,23**–0,30	ACK200
S	Exotic Alloy	-	30–**50**–80	0,10–**0,20**–0,30	ACM300

Minimum-**Optimum**-Maximum

☞ G10/G11

"METAL SLASH MILL"
MSX Type

Ultra High Feed

Boosts Productivity – Cuts Costs

Features

The Metal Slash Mill type MSX is a new multi function high shear milling cutter with ultra high feed capability suitable for face milling, slotting, plunging and helical boring. At 50GPa the ultra hard Super ZX coated inserts feature a sharp cutting edge which demonstrates extreme resistance to wear and heat massively boosting productivity and tool life.

The vibration free cutting action ensures accurate sizing, improved surface finish, and protection of the machine tool/workpiece from damage. Inserts are double clamped in wide chip gullets to maximise rigidity and chip evacuation with temperature at the cutting edge being easily controlled via an optional air blast through integral coolant holes.The MSX cutter is readily applied to general purpose machining across the P (steel) M (stainless) and K (cast iron) range of workpiece materials with impressive results.

Advantages

Integral Coolant Hole

Otimised chip removal – massive chip avacuation pockets

Wide Application Range

Face milling, slotting, helical boring and plunging

Low Cutting Force

Unique insert shape reduces cutting force



Double Clamp

Secure insert clamping for stable cutting

Application Range

Roughing operation (Carbon steel, a_e = 30 %)



	Face Milling		Slotting	Helical Boring	Profiling
	General Condition	High Feed Condition			
MSX	☺	☺☺☺	☺	☺☺☺	–
WRCX	☺☺☺	☺	☺	☺☺	☺☺

☺☺☺ excellent
☺☺ very good
☺ good

● = Euro stock
❍ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

"METAL SLASH MILL"
MSX 06000/08000 ES/EM/EW

"METAL SLASH MILL"
MSX 12000/14000 ES/EM/EW

1,0 mm 20° 1,5 mm 20° 2,0 mm 20° 2,5 mm 20°

Fig. 1



Fig. 2



Body

For insert type : WDMT 0603 □□□□

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Fig.
		DCX	DMM	LH	LS	LF		
MSX 06016 ES	❑	16	16	30	80	110	2	1
06016 EM	●	16	16	70	80	150	2	1
06016 EM15	❑	16	15	30	120	150	2	1
MSX 06017 EM	❑	17	16	20	130	150	2	1
MSX 06018 EM	❑	18	16	20	130	150	2	1
MSX 06020 ES	●	20	20	50	80	130	3	1
06020 EM	●	20	20	100	80	180	3	1
06020 EM19	❑	20	19	50	130	180	3	1
MSX 06022 EM	❑	22	20	30	150	180	3	1
MSX 06025 ES	●	25	25	60	80	140	3	1
06025 ES24	❑	25	24	60	80	140	3	1
06025 EM	●	25	25	120	130	250	3	1
06025 EM24	❑	25	24	60	190	250	3	1
MSX 06020 EW	●	20	20	50	80	130	3	1
MSX 06025 EW	●	25	25	60	80	140	3	1

Body

For insert type : WDMT 0804 □□□□

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Fig.
		DCX	DMM	LH	LS	LF		
MSX 08020 ES	●	20	20	50	80	130	2	1
08020 EM	●	20	20	100	80	180	2	1
08020 EM19	❑	20	19	50	130	180	2	1
MSX 08022 EM	❑	22	20	30	150	180	2	1
MSX 08025 ES	●	25	25	60	80	140	2	2
08025 EM	●	25	25	120	130	250	2	2
08025 EM24	❑	25	24	60	190	250	2	2
MSX 08028 EM	❑	28	25	40	210	250	2	2
MSX 08032 ES	❑	32	32	70	80	150	3	2
08032 EM	❑	32	32	120	130	250	3	2
MSX 08035 EM	❑	35	32	50	200	250	3	2
MSX 08020 EW	●	20	20	50	80	130	2	1
MSX 08025 EW	●	25	25	60	80	140	2	2
MSX 08032 EW	●	32	32	70	80	150	3	2

Identification Details

MSX	06	016	E	S
Cutter type	Insert size	Cutter Diameter	Shank Type	

S: Short type with cylindrical shank
M: Long type with cylindrical shank
W: Short type with Weldon shank

Body

For insert type : WDMT 1205 □□□□

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Fig.
		DCX	DMM	LH	LS	LF		
MSX 12032 ES	●	32	32	70	80	150	2	2
12032 EM	●	32	32	120	130	250	2	2
MSX 12035 EM	❑	35	32	50	200	250	2	2
MSX 12040 ES	❑	40	32	50	100	150	3	2
12040 EM	❑	40	32	50	200	250	3	2
MSX 12050 EM	❑	50	42	50	200	250	4	2
MSX 12032 EW	●	32	32	70	80	150	2	2

Body

For insert type : WDMT 1406 □□□□

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Fig.
		DCX	DMM	LH	LS	LF		
MSX 14040 ES	❑	40	32	50	100	150	2	2
14040 EM	❑	40	32	50	200	250	2	2
MSX 14050 ES	❑	50	42	50	100	150	3	2
MSX 14050 EM	❑	50	42	50	200	250	3	2
14063 ES	❑	63	42	50	100	150	4	2
MSX 14063 EM	❑	63	42	50	200	250	4	2

Inserts

Application	Coated Carbide			
High Speed / Light cut			K	
General Purpose	P M	P M	K	
Roughing	P M	P M		K



Cat. No.	ACP200	ACP300	ACK200	ACK300	Dimensions (mm) IC	S	RE	Applicable Endmill
WDMT0603 ZDTR	●	●	❍	❍	6,35	3,0	1,5	MSX06000E□
0603 ZDTR-H	●	●	❍	●				
WDMT0804 ZDTR	●	●		❍	8,5	4,0	2,0	MSX08000E□
0804 ZDTR-H	●	●		❍				
WDMT1205 ZDTR	●	●		●	12	5,0	2,0	MSX12000E□
1205 ZDTR-H	●	●		●				
WDMT1406 ZDTR	●	●		●	14	6,0	2,0	MSX14000E□
1406 ZDTR-H	●	●		●				

ZDTR-H : Stronger cutting edge

Spare Parts

Insert Screw		Insert Wrench	Clamp	C Ring	Clamp Screw	Applicable Endmill
	N·m					MSX - EO
BFTX 02505 IP	1,5	TRDR 08 IP	–	–	–	MSX 06000E□
BFTX 0306 IP	2,0	TRDR 08 IP	–	–	–	MSX 08020E□, MSX 08022E□
BFTX 0306 IP	2,0	TRDR 08 IP	CCH 3,5	CR 03	BFTX 03510 IP 08	MSX 08025E□, MSX 08028E□, MSX 08032E□, MSX 08035E□
BFTX 0409 IP	3,0	TRDR 15 IP	CCH 3,5	CR 03	BFTX 03510 IP 15	MSX 12000E□
BFTX 0511 IP	5,0	TRDR 20 IP	CCH 4,5	CR 03	BFTX 04513 IP 20	MSX 14000E□

☞ G53

Exchangeable Head Endmills
MSX 06000/08000 M Type

1,0 mm 20°

High feed and high efficiency machining endmills



Axial rake angle: 8°
Radial rake angle: -3°– -8°

Modular Type

Exchangeable Head Endmills
MSX 08000/12000 M Type

1,5 mm 20° (MSX 08000M)

2,0 mm 20° (MSX 12000M)

High feed and high efficiency machining endmills



Axial rake angle: 8°
Radial rake angle: -3°– -8°

■ Heads

For insert type : WDMT 0603

Cat. No.	Stock	Dimensions (mm)									No. of teeth
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
MSX 06016M08Z2	●	16	8,5	M8	42	25	5	17	8	13	2
06018M08Z2	❑	18	8,5	M8	42	25	5	17	8	13	2
MSX 06020M10Z3	●	20	10,5	M10	49	30	5	19	8	15	3
06022M10Z3	❑	22	10,5	M10	49	30	5	19	8	15	3
MSX 06025M12Z3	●	25	12,5	M12	56	35	5	21	10	19	3

Inserts are not included.

■ Heads

For insert type : WDMT 0804

Cat. No.	Stock	Dimensions (mm)									No. of teeth
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
MSX 08025M12Z2	●	25	12,5	M12	56	35	5	21	10	19	2
08028M12Z2	❍	28	12,5	M12	56	35	5	21	10	19	2
MSX 08030M16Z3	❍	30	17,0	M16	63	40	5	23	10	24	3
08032M16Z3	●	32	17,0	M16	63	40	5	23	10	24	3
MSX 08035M16Z3	❑	35	17,0	M16	63	40	5	23	10	24	3

Inserts are not included.

■ Heads

For insert type : WDMT 1205

Cat. No.	Stock	Dimensions (mm)									No. of teeth
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
MSX 12032M16Z2	●	32	17,0	M16	63	40	5	23	10	24	2
12035M16Z2	❑	35	17,0	M16	63	40	5	23	10	24	2
MSX 12040M16Z3	●	40	17,0	M16	63	40	5	23	10	24	3

Inserts are not included.

■ Inserts

Application	Coated Carbide			
General Purpose	PM	PM	K	
Roughing	PM	PM		K

Cat. No.	ACP200	ACP300	ACK200	ACK300	Dimensions (mm) IC	S	RE	Applicable Endmill
WDMT 0603 ZDTR	●	●	❍	❍	6,35	3,0	1,5	MSX06000M□
0603 ZDTR-H	●	●	❍	●				
WDMT 0804 ZDTR	●	●		❍	8,5	4,0	2,0	MSX08000M□
0804 ZDTR-H	●	●		❍				
WDMT 1205 ZDTR	●	●		●	12	5,0	2,0	MSX12000M□
1205 ZDTR-H	●	●		●				



H – Strong Cutting Edge

■ Identification Details

MSX	06	016	M08	Z2
Cutter type	Insert size	Diameter	Mounting screw	No. of teeth

■ Spare Parts

Clamp Screw		Insert Wrench	Clamp	C Ring	Insert Screw	Applicable Endmill
	N·m					
BFTX 02505 IP	1,5	TRDR 08 IP	–	–	–	MSX 06016M – MSX 06025M
BFTX 0306 IP	2,0	TRDR 08 IP	CCH 3,5	CR 03	BFTX 03510 IP 08	MSX 08025M – MSX 08035M
BFTX 0409 IP	3,0	TRDR 15 IP	CCH 3,5	CR 03	BFTX 03510 IP 15	MSX 12032M – MSX 12040M

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
N·m Recommended Tightening Torque (N·m)

■ Recommended Cutting Conditions

Work Material	Coated Carbide Grade	Cutting Speed v_c (m/min)	Insert Cat. No.	Endmill Type (Ø DC) 16 a_p (mm)	16 Feed rate (mm/tooth)	20 a_p (mm)	20 Feed rate (mm/tooth)	25 a_p (mm)	25 Feed rate (mm/tooth)	32 a_p (mm)	32 Feed rate (mm/tooth)	40 a_p (mm)	40 Feed rate (mm/tooth)	Shell Type (Ø DC) 50–66 a_p (mm)	50–66 Feed rate (mm/tooth)	80–100 a_p (mm)	80–100 Feed rate (mm/tooth)
General Steel (Below HB200)	ACP200	100–**150**–200	WDMT 0603	0,8	0,8	0,8	0,8	0,8	0,8	–	–	–	–	–	–	–	–
			WDMT 0804	–	–	1,0	1,0	1,0	1,2	1,0	1,2	–	–	–	–	–	–
			WDMT 1205	–	–	–	–	–	–	1,2	1,4	1,2	1,4	1,2	1,4	–	–
			WDMT 1406	–	–	–	–	–	–	–	–	1,5	1,5	1,5	1,5	1,5	1,5
Alloy Steel (Below HRC45)	ACP200	80–**130**–180	WDMT 0603	0,7	0,8	0,7	0,8	0,7	0,8	–	–	–	–	–	–	–	–
			WDMT 0804	–	–	0,8	1,0	0,8	1,2	0,8	1,2	–	–	–	–	–	–
			WDMT 1205	–	–	–	–	–	–	1,0	1,4	1,0	1,4	1,0	1,4	–	–
			WDMT 1406	–	–	–	–	–	–	–	–	1,3	1,5	1,3	1,5	1,3	1,5
Stainless Steel X5CRNI1810, Others	ACP300	80–**120**–150	WDMT 0603	0,8	0,7	0,8	0,7	0,8	0,7	–	–	–	–	–	–	–	–
			WDMT 0804	–	–	1,0	0,8	1,0	0,8	1,0	0,8	–	–	–	–	–	–
			WDMT 1205	–	–	–	–	–	–	1,2	1,2	1,2	1,2	1,2	1,2	–	–
			WDMT 1406	–	–	–	–	–	–	–	–	1,5	1,3	1,5	1,3	1,5	1,3
Cast Iron GG, GGG	ACK300	100–**150**–200	WDMT 0603	0,8	1,0	0,8	1,0	0,8	1,0	–	–	–	–	–	–	–	–
			WDMT 0804	–	–	1,0	1,2	1,0	1,4	1,0	1,4	–	–	–	–	–	–
			WDMT 1205	–	–	–	–	–	–	1,2	1,5	1,2	1,5	1,2	1,5	–	–
			WDMT 1406	–	–	–	–	–	–	–	–	1,5	1,8	1,5	1,8	1,5	1,8
Hardened Steel (Below HRC50)	ACK300	40–**80**–100	WDMT 0603	0,5	0,5	0,5	0,5	0,5	0,5	–	–	–	–	–	–	–	–
			WDMT 0804	–	–	0,5	0,6	0,5	0,8	0,5	0,8	–	–	–	–	–	–
			WDMT 1205	–	–	–	–	–	–	0,6	1,0	0,6	1,0	0,6	1,0	–	–
			WDMT 1406	–	–	–	–	–	–	–	–	1,0	1,2	1,0	1,2	1,0	1,2

Insert Cat. No.	Max a_p	RE
WDMT 0603....	1,0	1,5
WDMT 0804....	1,5	2,0
WDMT 1205....	2,0	2,0
WDMT 1406....	2,5	2,0

- The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity. The above figures are guidelines for use with the BT50 machine tool.
- The above cutting conditions assume a tool overhang length of L/D = 3 (i.e. overhang length is 3 times tool diameter) or less. When tool overhang is **more than L/D = 3 and less than or equal L/D = 5**, settings should be adjusted to approximately **70 to 80 %** of those indicated in the above cutting conditions (i.e. a_p and Feed Rate). When tool overhang is **more than L/D = 5 and less than or equal L/D = 8**, settings should be adjusted to approximately **50 to 60 %** of those indicated in the above cutting conditions (i.e. a_p and Feed Rate).

■ Information for Programming

For machine programming, please use the theoretical corner radius (R) shown in the list.
Maximum depth (d) between theoretical radius and actual profile will be left on the finished surface, as shown below.



Body	Insert	Theoretical Radius (R)	Remaining Depth (d)
MSX **06**000	WDMT **06**03....	2,0	0,403
MSX **08**000	WDMT **08**04....	2,5	0,593
MSX **12**000	WDMT **12**05....	3,0	1,030
MSX **14**000	WDMT **14**06....	3,5	1,219

■ Plunging and Helical Boring



Cutter Ø	WDMT0603ZDTR a_p: max 1,0 Ramping α max.	Helical boring min. øB	Helical boring max. øB	WDMT0804ZDTR a_p: max 1,5 Ramping α max.	Helical boring min. øB	Helical boring max. øB	WDMT1205ZDTR a_p: max 2,0 Ramping α max.	Helical boring min. øB	Helical boring max. øB	WDMT1406ZDTR a_p: max 2,5 Ramping α max.	Helical boring min. øB	Helical boring max. øB
16	**6°00'**	**21**	**31**									
17	5°00'	23	33									
18	4°30'	25	35									
20	**3°30'**	**29**	**39**	**7°30'**	**25**	**38**						
22	3°00'	33	43	5°30'	29	42						
25	**2°00'**	**39**	**48**	**4°00'**	**35**	**48**						
28				3°00'	41	54						
32				**2°30'**	**49**	**62**	**6°30'**	**42**	**63**			
35				2°00'	55	68	5°00'	48	69			
40				**1°30'**	**65**	**78**	**4°00'**	**58**	**79**	**6°00'**	**53**	**78**
50							**2°30'**	**78**	**99**	**3°30'**	**73**	**98**
63							**2°00'**	**103**	**124**	**2°00'**	**99**	**124**
66							1°30'	109	130	1°45'	105	130
80										**1°30'**	**133**	**158**
100										**1°00'**	**173**	**198**

WFXH - M Type

General Features

WaveMill WFXH type is a high efficiency, multi-purpose cutter, that uses the WFX series inserts for high-feed roughing and a variety of processes.

Characteristics

Stable, high-efficiency milling with superior cutting edge sharpness.
Supports various types of processes (ramping and helical milling).
Able to use the selection of inserts from the WFX series.

Notes on Corner Finishing - Remaining Material

Actual machined corners will have uncut and overcut portions due to the shape of the inserts.

Fig. 1



Fig. 2



WFXH 08000 Type

Programmed Corner R	SOMT 08○○04-□			SOMT 08○○08-□			SOMT 08○○12-□		
	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape
2,0	1,41	0	Fig. 1	1,30	0	Fig. 1	1,21	0	Fig. 1
2,5	1,30	0,02	Fig. 2	1,19	0,01	Fig. 2	1,09	0	Fig. 2
3,0	-	-	-	-	-	-	0,98	0,05	Fig. 2

WFXH 12000 Type

Programmed Corner R	SOMT 12○○04-□			SOMT 12○○08-□			SOMT 12○○12-□			SOMT 12○○16-□		
	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape	Uncut Portion	Overcut Portion	Shape
2,0	2,58	0	Fig. 1	2,48	0	Fig. 1	2,37	0	Fig. 1	2,25	0	Fig. 1
2,5	2,47	0	Fig. 1	2,37	0	Fig. 1	2,25	0	Fig. 1	2,14	0	Fig. 1
3,0	2,36	0	Fig. 1	2,26	0	Fig. 1	2,14	0	Fig. 1	2,11	0	Fig. 1
3,5	2,24	0,01	Fig. 2	2,14	0	Fig. 1	2,03	0	Fig. 1	1,91	0	Fig. 1
4,0	-	-	-	2,03	0,04	Fig. 2	1,91	0,03	Fig. 2	1,8	0,01	Fig. 2

Minimum Cutting Diameter

Minimum cutting diameter (DCN) will depend on the insert that is used. Using an insert with a large nose radius is recommended for the WFXH type.





Body Cat. No.	DC	DCN based on insert nose			
		R0,4	R0,8	R1,2	R1,6
WFXH 08025 M	25	9,69	9,48	9,27	-
08032 M	32	16,6	16,4	16,2	-
WFXH 12040 M	40	15,8	15,5	15,3	15,1

Taper Cutting and Helical Milling



Minimum and Maximum Diameters



Ramping Angle

Insert Cat. No.	DC	Helical Millilng		Taper Cutting
		Min.	Max.	Max. Ramping Angle
SOMT 08○○04-□	25	35	49	1°30‘
	32	49	63	0°30‘
SOMT 08○○08-□	25	35	48	3°
	32	49	62	1°30‘
SOMT 08○○12-□	25	34	47	4°30‘
	32	48	61	2°30‘
SOMT 12○○04-□	40	56	79	1°
SOMT 12○○08-□	40	56	78	1°30‘
SOMT 12○○12-□	40	55	77	2°30‘
SOMT 12○○16-□	40	55	76	3°30‘

● = Euro stock
❍ = Japan stock

☞ G54

Recommended Tightening Torque (N·m)

Modular Type

Rake Angle		
	Radial	-6°
	Axial	6°



(08000M Type)



(12000M Type)



Head

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H		
WFXH08025M12Z2	❍	25	12,5	M12	56	35	5	21	10	19	2	0,1
08032M12Z3	❍	32	17,0	M16	63	40	5	23	10	24	3	0,2

Inserts are not included.

Head

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H		
WFXH12040M12Z3	❍	40	17,0	M16	63	40	5	23	10	24	3	0,2

Inserts are not included.

Identification Details

WFX	08	020	M10	Z2
Cutter Series	Insert Size	Cutter Diameter	Screw Size	No. of Teeth

Inserts

Application	Coated Carbide							Carbide	DLC		
High Speed / Light cut	P			K		MS		KN			
General Purpose		PM	PM	K		MS	MS		N		
Roughing		PM	PM		K		MS		N		
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius (mm) RE	Fig.
SOMT 080304 PZER L	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1
080308 PZER L	❍	❍	❍	❍	❍	❍	●	–	–	0,8	1
SOMT 080304 PZER G	❍	●	●	●	❍	❍	❍	–	–	0,4	1
080308 PZER G	❍	●	●	●	●	❍	●	–	–	0,8	1
080312 PZER G	❍	●	❍	❍	❍	❍	❍	–	–	1,2	1
SOMT 080308 PZER H	❍	●	●	❍	●	❍	❍	–	–	0,8	1
080312 PZER H	❍	❍	●	❍	❍	❍	❍	–	–	1,2	1
SOET 080304 PZER G	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1
080308 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	0,8	1
080312 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	1,2	1
SOET 080302 PZFR S	–	–	–	–	–	–	–	●	●	0,2	1
080304 PZFR S	–	–	–	–	–	–	–	●	●	0,4	1
080308 PZFR S	–	–	–	–	–	–	–	●	●	0,8	1
SOMT 120408 PDER L	●	●	●	❍	❍	❍	●	–	–	0,8	2
SOMT 120404 PDER G	❍	❍	●	❍	●	❍	●	–	–	0,4	2
120408 PDER G	●	●	●	●	❍	●	●	–	–	0,8	2
120412 PDER G	❍	❍	❍	❍	❍	❍	●	–	–	1,2	2
120416 PDER G	❍	●	❍	❍	❍	❍	❍	–	–	1,6	2
SOMT 120408 PDER H	❍	●	❍	●	●	❍	❍	–	–	0,8	2
SOET 120408 PDFR S	–	–	–	–	–	–	–	●	●	0,8	2

Fig. 1



Fig. 2



Spare Parts

Applicable Cutter	Screw		Insert Wrench
		N·m	
WFXH08000M	BFTX0306IP	2,0	TRDR08IP
WFXH12000M	BFTX03512IP	3,0	TRDR15IP

Recommended Cutting Conditions

ISO	Work Material	Grade	Cutting Speed (vc (m/min)	Insert Cat. No.	Ø 25		Ø 32		Ø 40	
					ap (mm)	ft (mm/t)	ap (mm)	ft (mm/t)	ap (mm)	ft (mm/t)
P	General Steel <200HB	ACP200	100–**150**–200	SOMT08	0,8	0,8	0,8	0,8	-	-
				SOMT12	-	-	-	-	1,0	1,0
	Alloy Steel <HRC45	ACP200	80–**130**–180	SOMT08	0,7	0,8	0,7	0,8	-	-
				SOMT12	-	-	-	-	0,8	1,0
M	Stainless Steel (X5CrNiS18 10, other)	ACM300	80–**120**–150	SOMT08	0,8	0,7	0,8	0,7	-	-
				SOMT12	-	-	-	-	1,0	0,8
K	Cast Iron FC, FCD	ACK300	100–**150**–200	SOMT08	0,8	1,0	0,8	1,0	-	-
				SOMT12	-	-	-	-	1,0	1,2
H	Hardened Steel <HRC50	ACK300	40–**80**–100	SOMT08	0,5	0,5	0,5	0,5	-	-
				SOMT12	-	-	-	-	0,6	0,8

The above recommended cutting conditions may require adjustment according to machine rigidity and work rigidity. The above figures are guidelines for use with the BT50 machine tool.
The above conditions assume a tool overhang length of L/D = 3 (i.e. overhang length is 3 times tool diameter) or less.
When tool overhang is more than L/D = 3 and less or equal L/D = 5, settings should be adjusted to approximately 70 % to 80 % of those indicated in the above cutting conditions (i.e. ap and ft).
When tool overhang is more than L/D = 5 and less or equal L/D = 8, settings should be adjusted to approximately 50 % to 60 % of those indicated in the above cutting conditions (i.e. ap and ft).

General Features

The Sumi Dual Mill DFC type employs cost effective double-sided inserts for high toughness and enhanced accuracy.
The double-side inserts are flexible and reduces costs.

Large Line-up

- Diameter from Ø 25 mm to Ø 200 mm
- Available as standard, fine and extra-fine pitch
- Bore diameter: metric
- Insert geometry: L, G, H

Cutter Body

Type		Cat. No.	Diameter (mm)	No. of Teeth	Image
Shank ☞ G24	Standard Pitch	DFC 09000 E	Ø 25 – Ø 80	2–5	
	Fine Pitch	DFCM 09000 E	Ø 32 – Ø 80	3–7	
Shell	Standard Pitch	DFC 09000 RS	Ø 50 – Ø 200	4–8	
	Fine Pitch	DFCM 09000 RS	Ø 50 – Ø 200	5–12	
	Extra-Fine Pitch	DFCF 09000 RS	Ø 50 – Ø 200	6–16	

New Insert Design Provides Excellent Machining Accuracy

Inserts

Cat. No.	RE0,4	RE0,8	RE1,2	RE1,6
XNMU0606__PNER-L	●	●	●	●
XNMU0606__PNER-G	●	●	●	●
XNMU0606__PNER-H	●	●	●	●

Chipbreaker Selection Map



Work Material	Steel, Cast Iron		
	L type	G type	H type
Chipbreaker			
Feature	Low cutting force	General purpose	Strong edge
Cutting edge geometry	 30°	 25°	 20°
Application	Light cut, low rigidity milling and reduced burrs	Main breaker for general purpose applications	Roughing, heavy interrupted and hardness steel milling

Stable and High Cutting Performance Combined with High Toughness



● = Euro stock
❑ = Delivery on request

Recommended Tightening Torque (N·m)

Body – Shank Type

Rake Angle	Radial	-9°
	Axial	-5°

Max. a_p: 6 mm



Body – Dimensions

DFC type, Standard Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth
		DC	DMM	LH	LS	LF	
DFC 09025E	●	25	25	40	80	120	2
DFC 09032E	●	32	32	50	80	130	2
09040E	●	40	32	50	80	130	3
09050E	●	50	32	50	80	130	3
DFC 09050E-42		50	42	50	100	150	3
DFC 09063E	❑	63	32	50	80	130	4
DFC 09063E-42		63	42	50	100	150	4
DFC 09080E	❑	80	32	50	80	130	5
DFC 09080E-42		80	42	50	100	150	5

DFCM type, Medium Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth
		DC	DMM	LH	LS	LF	
DFCM 09032E	●	32	32	50	80	130	3
09040E	●	40	32	50	80	130	4
09050E	●	50	32	50	80	130	5
DFCM 09050E-42		50	42	50	100	150	5
DFCM 09063E	❑	63	32	50	80	130	6
DFCM 09063E-42		63	42	50	100	150	6
DFCM 09080E	❑	80	32	50	80	130	7
DFCM 09080E-42		80	42	50	100	150	7

Identification Details

DFC	M	09	050	E
Cutter Series	M: Medium	Insert Size	Cutter Diameter	Shank Type

Inserts

Application	Coated Carbide						
High Speed / Light Cutting	PM			K		MS	
General Purpose Cutting		PM	PM	K		MS	MS
Rough Cutting		PM	PM		K		MS
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	Radius RE
XNMU 060604 PNER-L		●	●		●		●	0,4
060608 PNER-L		●	●		●		●	0,8
XNMU 060604 PNER-G	●	●	●	●	●	●	●	0,4
060608 PNER-G	●	●	●	●	●	●	●	0,8
060612 PNER-G	●	●	●	●	●	●	●	1,2
060616 PNER-G	●	●	●	●	●	●	●	1,6
XNMU 060608 PNER-H	●	●	●	●	●	●	●	0,8
060612 PNER-H	●	●	●	●	●	●	●	1,2
060616 PNER-H	●	●	●	●	●	●	●	1,6



Spare Parts

Screw	Wrench
BFTX03512IP	TRDR15IP 5,0 (N·m)

Recommemded Cutting Conditions

ISO	Work-material	Hardness (HB)	Cutting Speed (m/min) Min. - Optimum - Max.	Feed Rate Min. - Optimum - Max.	Depth of Cut (mm)	Grade
P	General Steel	180–280	150–**200**–250	0,10–**0,20**–0,30	< 6	ACP200 ACP300
P	Soft Steel	≤ 180	180–**250**–350	0,15–**0,25**–0,35	< 6	ACP200 ACP300
P	Die Steel	200–220	100–**150**–200	0,10–**0,18**–0,25	< 4	ACP200 ACP300
M	Stainless Steel	-	160–**205**–250	0,12–**0,18**–0,25	< 6	ACM200 ACM300
K	Cast Iron	250	100–**175**–250	0,10–**0,20**–0,30	< 6	ACK200 ACK300

Suitable Applications

Face milling



Shoulder milling

Shot milling

Side face milling

"Sumi Wave" Shoulder Mill
WFX (M) 08000 E Type

Body - Shank Type

WFX08000E



Body - WFX_E, Standard Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth
		DC	DMM	LH	LS	LF	
WFX 08020 E-16	●	20	16	30	80	110	2
WFX 08020 E	●	20	20	30	80	110	2
08022 E	●	22	20	30	90	120	2
WFX 08025 E-20	●	25	20	30	90	120	2
WFX 08025 E	●	25	25	30	90	120	2
08028 E	●	28	25	30	90	120	2
08030 E	●	30	25	30	90	120	3
WFX 08032 E	●	32	32	30	90	120	3
08033 E	●	33	32	30	90	120	3
08040 E	●	40	32	30	90	120	3
08050 E	●	50	32	30	90	120	4
08063 E	●	63	32	30	90	120	5

Inserts are not included.

Body - WFXM_E, Medium Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth
		DC	DMM	LH	LS	LF	
WFXM 08025 E	●	25	25	30	90	120	3
WFXM 08032 E	●	32	32	30	90	120	4
08040 E	●	40	32	30	90	120	4
08050 E	●	50	32	30	90	120	5
08063 E	●	63	32	30	90	120	6

Inserts are not included.

Identification Details

WFX	M	08	025	E
Cutter Series	M: Medium	Insert Size	Cutter Diameter	Endmill Type

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed	Feed Rate	DOC	Grades
P	General Steel	180–280	150–**200**–250	0,08–**0,12**–0,18	<6	ACP200 ACP300
P	Soft Steel	≤180	180–**250**–350	0,10–**0,15**–0,20	<6	ACP200 ACP300
P	Die Steel	200–220	100–**150**–200	0,08–**0,12**–0,18	<4	ACP200 ACP300
M	Stainless Steel	-	160–**200**–250	0,10–**0,15**–0,20	<6	ACM300
K	Cast Iron	250	100–**175**–250	0,10–**0,15**–0,20	<6	ACK200 ACK300
N	Non Ferrous Metal	-	300–**500**–1000	0,10–**0,15**–0,20	<6	H1 DL1000

Min. - **Optimum** - Max.

"Sumi Wave" Shoulder Mill
WFX 08000 M Type

Modular Type

Rake Angle		
	Radial	-6°
	Axial	12°

6 mm, 90°

WFX08000M



Head

Cat. No.	Stock	Dimensions (mm)									No. of Teeth
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
WFX 08020 M10Z2	●	20	10,5	M10	49	30	5	19	8	15	2
08022 M10Z2	●	22	10,5	M10	49	30	5	19	8	15	2
WFX 08025 M12Z2	●	25	12,5	M12	56	35	5	21	10	19	2
08028 M10Z2	●	28	12,5	M12	56	35	5	21	10	19	2
WFX 08030 M16Z3	●	30	17,0	M16	63	40	5	23	10	24	3
08032 M16Z3	●	32	17,0	M16	63	40	5	23	10	24	3
08040 M16Z3	●	40	17,0	M16	63	40	5	23	10	24	3

Identification Details

WFX	08	020	M10	Z2
Cutter Series	Insert Size	Cutter Diameter	Screw Size	No. of Teeth

Inserts

Fig. 1



Fig. 2 Wiper Insert



Application	Coated Carbide							Carbide	DLC		
High Speed / Light cut	P			K		MS		KN	N		
General Purpose		PM	PM	K		MS	MS		N		
Roughing		PM	PM		K		MS				
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE	Fig.
SOMT 080304 PZER L	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1
080308 PZER L	❍	❍	❍	❍	❍	❍	●	–	–	0,8	1
SOMT 080304 PZER G	❍	●	●	●	❍	❍	❍	–	–	0,4	1
080308 PZER G	❍	●	●	●	●	❍	●	–	–	0,8	1
080312 PZER G	❍	●	❍	❍	❍	❍	❍	–	–	1,2	1
SOMT 080308 PZER H	❍	●	●	❍	●	❍	❍	–	–	0,8	1
080312 PZER H	❍	❍	●	❍	❍	❍	❍	–	–	1,2	1
SOET 080304 PZER G	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1
080308 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	0,8	1
080312 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	1,2	1
SOET 080302 PZFR S	–	–	–	–	–	–	–	●	●	0,2	1
080304 PZFR S	–	–	–	–	–	–	–	●	●	0,4	1
080308 PZFR S	–	–	–	–	–	–	–	●	●	0,8	1
XOEW 080308 PZTR W	–	–	–	–	❍	–	–	–	–	–	2

Spare Parts

Screw		Wrench
		
BFTX0306IP	2,0	TRDR08IP

● = Euro stock
❍ = Japan stock

☞ G30/G31

Recommended Tightening Torque (N·m)

"Sumi Wave" Shoulder Mill
WFX (F) 12000 E Type

Body - Shank Type

Rake Angle		
	Radial	-8°
	Axial	8°

10 mm, 90°

WFX12000E



Body - WFX_E, Standard Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth
		DC	DMM	LH	LS	LF	
WFX 12040 E	●	40	32	30	90	120	3
12050 E	●	50	32	30	90	120	3
12063 E	●	63	32	30	90	120	4
12080 E	●	80	32	30	90	120	4

Inserts are not included.

Body - WFXF_E, Fine Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth
		DC	DMM	LH	LS	LF	
WFXF 12050 E	●	50	32	30	90	120	4
12063 E	●	63	32	30	90	120	5
12080 E	●	80	32	30	90	120	6

Inserts are not included.

Identification Details

WFX	F	12	050	E
Cutter Series	F: Fine	Insert Size	Cutter Diameter	Endmill Type

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed	Feed Rate	DOC	Grades
P	General Steel	180–280	150–**200**–250	0,10–**0,15**–0,20	<10	ACP200 ACP300
P	Soft Steel	≤180	180–**250**–350	0,10–**0,15**–0,20	<10	ACP200 ACP300
P	Die Steel	200–220	100–**150**–200	0,10–**0,15**–0,20	<6	ACP200 ACP300
M	Stainless Steel	-	160–**200**–250	0,10–**0,15**–0,20	<10	ACM300
K	Cast Iron	250	100–**175**–250	0,10–**0,15**–0,20	<10	ACK200 ACK300
N	Non Ferrous Metal	-	300–**500**–1000	0,10–**0,15**–0,20	<10	H1 DL1000

Min. - **Optimum** - Max.

Inserts

Fig. 1



Fig. 2 Wiper Insert



Application	Coated Carbide							Carbide	DLC		
High Speed / Light cut	P			K		M S		K N	N		
General Purpose		P M	P M	K		M S	M S		N		
Roughing		P M	P M		K		M S				
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE	Fig.
SOMT 120408 PDER L	●	●	●	○	○	○	●	–	–	0,8	1
SOMT 120404 PDER G	○	○	●	○	●	○	●	–	–	0,4	1
120408 PDER G	●	●	●	●	○	●	●	–	–	0,8	1
120412 PDER G	○	○	○	○	○	○	●	–	–	1,2	1
120416 PDER G	○	●	○	○	○	○	○	–	–	1,6	1
SOMT 120408 PDER H	○	●	○	●	●	○	○	–	–	0,8	1
SOET 120408 PDFR S	–	–	–	–	–	–	–	●	●	0,8	1
XOEW 120408 PDTR W	–	–	–	–	○	–	–	–	–	–	2

Spare Parts

Shim	Shim Screw	Insert Screw		Insert Wrench	Seat Wrench
			N·m		
WFXS4R	BW0507F	BFTX03512IP	**3,0**	TRDR15IP	LH035



TSX Type

General Features

High-efficient and high precision tangential shoulder milling cutter with tangentially mounted carbide inserts.

Characteristics

- Tough & Sharp cutting edge
- Very accurate and excellent surface finish
- Wide product range

Product Range

Type		Cat. No.	Diameter Range	No. of Teeth	Shape
Shank Type	Standard Pitch	TSX 08000 E	Ø16 – Ø40	2–4	
	Fine Pitch	TSXF 08000 E	Ø20 – Ø40	3–6	
	Standard Pitch	TSX 13000 E	Ø25 – Ø50	2–4	
	Medium Pitch	TSXM 13000 E	Ø32 – Ø50	3–6	
Shell Type	Standard Pitch	TSX 08000 RS	Ø40 – Ø63	4–6	
	Fine Pitch	TSXF 08000 RS	Ø40 – Ø63	6–10	
	Standard Pitch	TSX 13000 RS	Ø40 – Ø160	2–4	
	Medium Pitch	TSXM 13000 RS	Ø40 – Ø160	3–6	☞ G32

Chipbreaker Selection



Inserts

Cat. No.	RE0,4	RE0,8	RE1,2	RE1,6	RE2,4	RE3,2
LNEX0804__PNER-L	●	●				
LNEX0804__PNER-G	●	●	●	●		
LNEX1306__PNER-L	●	●				
LNEX1306__PNER-G		●		●	●	●
LNEX1306__PNER-H	●	●		●	●	●

Chipbreaker Lineup

Work Material	P M K S		
	L type	G type	H type
Chipbreaker			
Feature	Low cutting force	General purpose	Strong edge
LNEX08 Cutting edge geometry			–
LNEX13 Cutting edge geometry			
Application	Light cut, low rigidity milling and reduced burrs	Main breaker for general purpose applications	Roughing, heavy interrupted and hardness steel milling

Recommended Cutting Conditions

Min. - **Optimum** - Max.

ISO	Work Material	Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/t)	Grade
P	Carbon Steel	180–280	150–**225**–300	0,08–**0,20**–0,30	ACP100, ACP200, ACP300
		> 280	75–**150**–230	0,08–**0,20**–0,30	
	Alloy Steel	180–280	100–**175**–250	0,08–**0,15**–0,25	
M	Stainless Steel	220–280	90–**135**–180	0,08–**0,15**–0,25	ACM200, ACM300
		> 280	75–**125**–170	0,08–**0,15**–0,25	
K	Cast Iron, Ductile Cast Iron	250	100–**175**– 250	0,08–**0,20**–0,30	ACK200, ACK300
S	Exotic Material	-	30–**60**–90	0,05–**0,10**–0,15	ACM200, ACM300

● = Euro stock

Recommended Tightening Torque (N·m)

"Sumi Dual Mill" Series
TSX(F) 08000 E Type

Shank Type

Rake Angle	Radial	-20°
	Axial	-6°

8 mm 90°



Body - TSX, Standard Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
TSX 08016 E	●	16	16	25	75	100	2	0,13
08020 E	●	20	20	30	80	110	2	0,22
08025 E	●	25	25	30	90	120	3	0,40
08032 E	●	32	32	30	90	120	3	0,67
08040 E	●	40	32	30	90	120	4	0,72

Inserts are not included.

Body - TSXF, Fine Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
TSXF 08020 E	●	20	20	30	80	110	3	0,22
08025 E	●	25	25	30	90	120	4	0,40
08032 E	●	32	32	30	90	120	5	0,67
08040 E	●	40	32	30	90	120	6	0,73

Inserts are not included.

Spare Parts

Insert Screw		Insert Wrench	Applicable Cutters
BFTX0306IP	2,0	TRDR08IP	TSX08016E, TSX08020E, TSXF08020E
BFTX0308IP			TSX08025E – 40E, TSXF08025E – 40E
BFTX03510IP	3,0	TRDR15IP	TSX13000E, TSXM13000E

"Sumi Dual Mill" Series
TSX(M) 13000 E Type

Shank Type

Rake Angle	Radial	-15°
	Axial	-6°

12 mm 90°



Body - TSX, Standard Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
TSX 13025 E	●	25	25	35	85	120	2	0,38
13032 E	●	32	32	35	85	120	2	0,66
13040 E	●	40	32	30	90	120	3	0,71
13050 E	●	50	32	30	90	120	4	0,81

Inserts are not included.

Body - TSXM, Medium Pitch

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
TSXM 13032 E	●	32	32	35	85	120	3	0,65
13040 E	●	40	32	30	90	120	4	0,71
13050 E	●	50	32	30	90	120	5	0,80

Inserts are not included.

Identification Details

TSX	F	08	032	E
Cutter Series	F: Fine Pitch M: Medium Pitch	Insert Size	Cutter Diameter	Endmill Type

Inserts

Grade		Coated Carbide						
Application	High Speed / Light Cutting	PM			K		MS	
	General Purpose Cutting	PM	PM		K		MS	MS
	Rough Cutting		PM	PM		K		MS
Applicable Cutters	Inserts Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	Radius RE
TSX(F) 08000E	LNEX 080404 PNER-L	●	●	●	●	●	●	●	0,4
	080408 PNER-L	●	●	●	●	●	●	●	0,8
	LNEX 080404 PNER-G	●	●	●	●	●	●	●	0,4
	080408 PNER-G	●	●	●	●	●	●	●	0,8
	080412 PNER-G	●	●	●	●	●	●	●	1,2
	080416 PNER-G	●	●	●	●	●	●	●	1,6
TSX(M) 13000E	LNEX 130604 PNER-L	●	●	●	●	●	●	●	0,4
	130608 PNER-L	●	●	●	●	●	●	●	0,8
	LNEX 130604 PNER-G	●	●	●	●	●	●	●	0,4
	130608 PNER-G	●	●	●	●	●	●	●	0,8
	130616 PNER-G	●	●	●	●	●	●	●	1,6
	130624 PNER-G	●	●	●	●	●	●	●	2,4
	130632 PNER-G	●	●	●	●	●	●	●	3,2
	LNEX 130608 PNER-H	●	●	●	●	●			0,8
	130616 PNER-H		●	●	●	●			1,6
	130624 PNER-H		●	●	●	●			2,4
	130632 PNER-H		●	●	●	●			3,2

LNEX 08000 type



LNEX 13000 type



Recommended Cutting Conditions

☞ H18

"Wave Mill" Series
WEZ Type

New

General Features

- Supports various machining operations
- Excellent machining quality
- Excellent sharpness with low resistance
- General-purpose grade applicable to any work material

Product Range

Type	Cat. No.	Diameter Range (mm) / No of Teeth															
		Ø14	Ø16	Ø18	Ø20	Ø22	Ø25	Ø28	Ø30	Ø32	Ø35	Ø40	Ø50	Ø63	Ø80	Ø100	Ø125	Ø160
Shell	WEZ 11000RS ☞ G44											4, 6	5,7	6, 8	7, 10	9, 12		
	WEZ 11000R (Inch)														7, 10	9, 12		
	WEZ 17000RS ☞ G46											3, 4	3, 5	4, 6	4, 7	5, 8	6, 9, 11	8, 10 12
	WEZ 17000R (Inch)														4, 7	5, 8	6, 9, 11	8, 10 12
Shank	WEZ 11000E	1	2*	2	2*, 3*	3	2, 3*, 4*	4	4	2, 3, 4, 5*	5	2, 4, 6	5, 7	8	10			
	WEZ 11000EL	1	2*	2	2*	2	2*, 3	2	2	2*, 3	2, 3	2	3					
	WEZ 17000E						2*	2	3	2, 3*	3	3, 4	3*, 5*	4*, 6*	7			
	WEZ 17000EL						2	2	2	2*, 3	2	2, 3, 4	3*, 5*	4*, 6*				

* Different shank diameters in stock

Suitable Applications

- Supports Ramping, Helical Milling, Plunge Cutting

Face milling



Shoulder milling



Side face milling

Groove milling

Hole expansion milling



Ramping



Helical milling



Plunge cutting



Optimised Body Design

Wide guide face for stable insert clamping.



WEZ11 type

Chipbreaker Lineup

Work Material	P M K S H					N
	L Type	G Type	H Type	F Type	P Type	S Type
Chipbreaker						
AO_T11 Cutting edge geometry		 28°	 20°	 28°	 28°	 28°
AO_T17 Cutting edge geometry	 28°	 20°	 10°	 28°	 28°	 28°
Applications	Light cut, low rigidity machining	Main breaker for general purpose to interrupted machining	Heavy cut, heavy interrup-ted machining, hardened steel	Light cut, finishing, low-burr design	Light cut, high-precision machining, high surface wall quality	For non-ferrous metals



● = Euro stock
❍ = Japan stock

Product Range Inserts

Main Grade: ACU2500

Cat. No.	Nose Radius (mm)											
	R0,2	R0,4	R0,8	R1,2	R1,6	R2,0	R2,4	R3,0	R3,2	R4,0	R5,0	R6,4
AOMT 11T3_ _PEER-G	●	●	●	●	●	●	●	●	●			
AOMT 11T3_ _PEER-H		●	●	●	●							
AOET 11T3_ _PEER-F	❍	●	●	❍								
AOET 11T3_ _PEER-P16	❍	❍	❍	❍								
AOET 11T3_ _PEER-P20	❍	❍	❍	❍								
AOET 11T3_ _PEER-P25	❍	❍	❍	❍								
AOET 11T3_ _PEFR-S	❍	●	●	❍								
AOMT 1705_ _PEER-L	●	●	●	●	●							
AOMT 1705_ _PEER-G	●	●	●	●	●	●	●	●	●	●	●	●
AOMT 1705_ _PEER-H		●	●	❍	●							
AOET 1705_ _PEER-F	❍	●	●	❍								
AOET 1705_ _PEER-P25	❍	❍	❍	❍								
AOET 1705_ _PEER-P32	❍	❍	❍	❍								
AOET 1705_ _PEFR-S	❍	●	●	❍								

Lineup of Chipbreakers for Ground Inserts

F Type

Cutting edge specialized for sharpness and machining accuracy

Sharpness from ground finish enables burr control.

Excellent squareness with all diameters.



Machine:	Vertical Machining Centre BT50,
Work Material	X5CrNiS18 9
Tool:	WEZ 11050 RS07 (Ø 50, 7 teeth)
Insert:	AOET11T308PEER-F (ACU2500)
Cutting Conditions:	v_c = 120 m/min, f_z = 0,12 mm/t, a_p = 1 mm, a_e = 30 mm, dry

P Type

Chipbreaker for wall surface squareness equivalent to solid endmills

Premium item with cutting edge shape optimised for each cutter diameter while maintaining the F type chipbreaker's sharpness.

Enables wall surface squareness equal to solid endmills through a blade shape optimised for each tool diameter.





P Type Chipbreaker Selection

Cat. No.	Cutter Diameter (mm)										
	Ø14	Ø16	Ø18	Ø20	Ø22	Ø25	Ø28	Ø30	Ø32	Ø35	=> Ø40
AOET11T3_ _PEER-P_ _	-P16		-P20		–	-P25		–			
AOET1705_ _PEER-P_ _	–					-P25		-P32			–

Machine:	Vertical Machining Centre BT50,
Work Material:	C50
Tool:	WEZ 11020 E03 (Ø 20, 3 teeth)
Insert:	AOET11T308PEER-P20 (ACU2500)
Cutting Conditions:	v_c = 150 m/min, f_z = 0,1 mm/t, a_p = 8 mm x 3 passes, a_e = 1 mm, dry

S Type

Sharp edge chipbreaker for non-ferrous metals, with excellent adhesion resistance

Suppresses adhesion with rake face lapping.

DLC coat inserts available for further improved adhesion resistance.

WEZ

No Adhesion

Competitor A

Adhesion

Competitor B

Adhesion

Machine:	Vertical Machining Centre BT50,
Work Material:	AlSi12Cu
Tool:	WEZ 11020 E03 (Ø 20, 3 teeth)
Insert:	AOET11T308PEER-S (H20)
Cutting Conditions:	v_c = 350 m/min, f_z = 0,1 mm/t, a_p = 3 mm, a_e = 10 mm, dry

Recommended Cutting Conditions

WEZ11 Type

Cutter: WEZ 11020 E03
Insert: AO_T11T3 type
Cutting Data: a_p = 3 mm, a_e = 10 mm, dry



Min. - **Optimum** - Max.

ISO	Material	HB	Chipbreaker	Grade								
				ACU2500	ACP2000	ACP3000	T2500A	ACK2000	ACK3000	ACM200	ACM300	DL2000
				Feed Rate (mm/tooth)								
				0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,18	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,08–**0,15**–0,20	0,05–**0,10**–0,15
				Cutting Speed v_c (m/min)								
P	Unalloyed steel, <0, 15%C, annealed	125	G	270–**320**–370	300–**350**–400	250–**300**–350	230–**280**–330					
	" , <0, 45%C, annealed	190	G	170–**220**–270	200–**250**–300	150–**200**–250	130–**180**–230					
	" , <0, 45%C, tempered	250	G	140–**180**–220	160–**200**–245	120–**160**–200	105–**145**–185					
	" , <0, 75%C, annealed	270	G	110–**145**–175	130–**165**–195	100–**130**–165	85–**115**–150					
	" , <0, 75%C, tempered	300	G	70–**90**–110	80–**100**–120	60–**80**–100	50–**70**–90					
	Low alloyed steel, annealed	180	G	160–**205**–255	190–**235**–280	140–**190**–235	120–**170**–215					
	" , tempered	275	G	90–**120**–150	110–**135**–165	80–**110**–140	70–**100**–125					
	" , tempered	300	G	85–**110**–130	100–**125**–150	75–**100**–125	65–**90**–115					
	" , tempered	350	G	60–**80**–100	70–**90**–110	50–**70**–90	45–**65**–85					
	High alloyed and tool steel, annealed	200	G	140–**180**–220	160–**200**–245	120–**160**–205						
	" , tempered	325	G	55–**70**–85	60–**80**–100	50–**65**–80						
M	Stainless steel, ferritic/martensitic, annealed	200	G	110–**140**–170						140–**170**–190	90–**110**–140	
	" , martensitic, tempered	240	G	100–**125**–150						125–**150**–170	80–**100**–125	
	" , austenitic, plunged	180	G	120–**150**–180						150–**180**–200	100–**120**–150	
K	Grey cast iron		G	150–**200**–250				250–**300**–350	170–**220**–270			
	Nodular cast iron		G	90–**120**–150				150–**180**–210	100–**130**–160			
S	High tempered resist. alloys, Fe based, annealed		G	30–**40**–55						35–**45**–60	25–**35**–50	
	" , hardened		G	60–**80**–100						70–**90**–110	50–**70**–90	
N	Aluminium alloy, Si < 12,6%		S									500–**750**–100
	" , Si > 12,6%		S									170–**200**–250
	Copper alloy		S									300–**330**–350

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

WEZ17 Type

Cutter: WEZ 17032 E03
Insert: AO_T1705 type
Cutting Data: a_p = 5 mm, a_e = 16 mm, dry



Min. - **Optimum** - Max.

ISO	Material		Chipbreaker	Grade								
				ACU2500	ACP2000	ACP3000	T2500A	ACK2000	ACK3000	ACM200	ACM300	DL2000
				Feed Rate (mm/tooth)								
				0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,15**–0,22	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,10–**0,20**–0,28	0,05–**0,10**–0,15
				Cutting Speed v_c (m/min)								
P	Unalloyed steel, <0, 15%C, annealed	125	G	285–**335**–390	315–**360**–420	265–**315**–370	240–**295**–345					
	" , <0, 45%C, annealed	190	G	180–**230**–285	210–**265**–315	160–**210**–265	135–**190**–240					
	" , <0, 45%C, tempered	250	G	145–**190**–230	170–**210**–255	130–**170**–215	110–**155**–195					
	" , <0, 75%C, annealed	270	G	115–**150**–185	135–**170**–205	100–**135**–170	90–**125**–155					
	" , <0, 75%C, tempered	300	G	70–**90**–115	85–**105**–125	65–**85**–105	55–**75**–95					
	Low alloyed steel, annealed	180	G	170–**220**–265	200–**245**–295	150–**200**–250	130–**180**–225					
	" , tempered	275	G	100–**130**–155	115–**145**–175	85–**115**–145	75–**105**–135					
	" , tempered	300	G	90–**115**–140	105–**130**–155	75–**105**–130	65–**90**–120					
	" , tempered	350	G	65–**85**–100	75–**95**–115	55–**75**–95	50–**70**–85					
	High alloyed and tool steel, annealed	200	G	145–**185**–230	170–**215**–255	130–**170**–215						
	" , tempered	325	G	55–**75**–90	65–**85**–100	50–**65**–85						
M	Stainless steel, ferritic/martensitic, annealed	200	G	115–**145**–175						145–**175**–195	100–**115**–145	
	" , martensitic, tempered	240	G	105–**130**–155						130–**155**–175	85–**105**–130	
	" , austenitic, plunged	180	G	125–**155**–190						160–**190**–210	105–**125**–160	
K	Grey cast iron		G	160–**210**–265				265–**315**–370	180–**230**–285			
	Nodular cast iron		G	95–**125**–160				160–**190**–220	105–**140**–170			
S	High tempered resist. alloys, Fe based, annealed		G	30–**40**–60						35–**45**–60	25–**35**–50	
	" , hardened		G	60–**85**–105						75–**95**–115	50–**75**–95	
N	Aluminium alloy, Si < 12,6%		S									500–**750**–100
	" , Si > 12,6%		S									170–**200**–250
	Copper alloy		S									300–**330**–350

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.
For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

■ Ramping / Helical Milling Upper Limits

Ramping



Flat Bottom Machining



Machining with Prepared Hole



● WEZ11 Type

DC Ø (mm)	Max.Ramping Angle	Flat Bottom Machining				Machining with Prepared Hole	
	RPMX (°)	Max. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)
14	13,2	25,3	8,4	23,1	5,9	19,0	1,9
16	10,5	29,3	7,6	27,0	5,6	21,7	1,5
18	8,1	33,3	6,7	30,9	5,0	25,2	1,4
20	6,5	37,3	6,0	34,9	4,6	29,1	1,3
22	5,3	41,3	5,4	38,8	4,3	32,9	1,3
25	4,1	47,3	4,8	44,8	3,9	38,9	1,3
28	3,4	53,3	4,4	50,7	3,6	44,9	1,3
30	3,0	57,3	4,2	54,7	3,5	48,8	1,3
32	2,7	61,3	4,0	58,7	3,3	52,8	1,2
35	2,3	67,3	3,8	64,6	3,1	58,8	1,2
40	1,8	77,3	3,4	74,6	2,9	68,8	1,2
50	1,2	97,3	3,0	94,6	2,6	88,8	1,1
63	0,8	123,3	2,8	120,5	2,5	114,7	1,1

● WEZ17 Type

DC Ø (mm)	Max.Ramping Angle	Flat Bottom Machining				Machining with Prepared Hole	
	RPMX (°)	Max. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)	Min. Machining Diam. (mm)	Max. Pitch (mm/rev)
25	10,8	47,3	13,0	41,0	8,3	33,1	1,8
28	8,1	53,3	11,1	46,9	7,5	39,0	1,8
30	7,0	57,3	10,2	50,9	7,0	43,0	1,8
32	6,1	61,3	9,5	54,9	6,7	47,0	1,7
35	5,1	67,3	8,7	60,8	6,2	53,0	1,7
40	4,0	77,3	7,7	70,8	5,7	63,0	1,7
50	2,5	97,3	6,5	90,7	5,0	83,0	1,6
63	1,8	123,3	5,6	116,7	4,5	109,0	1,6

* The table above shows values with nose radius 0,8 mm

■ Plunge Cutting - Upper Limit for Radial Width a_e



Type	Max. a_e (mm)
WEZ11	3
WEZ17	5

"Wave Mill" Series
WEZ 11000 E

New

Rake Angle		
	Radial	-7° – -18°
	Axial	6° – 15°

10 mm 90°

Fig. 1



Fig. 2



Body - WEZ (Shank Type)

Dimensions (mm)

Cat. No.	Stock	DC	DMM	LH	LS	LF	No. of Teeth	Weight (kg)	Fig.
WEZ 11014E01	●	14	16	25	55	80	1	0,10	1
11016E02	●	16	16	25	75	100	2	0,13	1
11016E02-12	●	16	12	25	75	100	2	0,07	2
11018E02	●	18	16	25	75	100	2	0,13	2
11020E02	●	20	20	30	80	110	2	0,23	1
11020E02-16	●	20	16	30	80	110	2	0,15	2
11020E03	●	20	20	30	80	110	3	0,22	1
11020E03-16	●	20	16	30	80	110	3	0,14	2
11022E03	●	22	20	30	80	110	3	0,23	1
11025E02	●	25	25	35	85	120	2	0,40	1
11025E03	●	25	25	35	85	120	3	0,40	1
11025E03-20	●	25	20	35	85	120	3	0,26	2
11025E04	●	25	25	35	85	120	4	0,39	2
11025E04-20	●	25	20	35	85	120	4	0,26	2
11028E04	●	28	25	35	85	120	4	0,41	1
11030E04	●	30	25	40	90	130	4	0,46	1
11032E02	●	32	32	40	90	130	2	0,74	1
11032E03	●	32	32	40	90	130	3	0,73	1
11032E04	●	32	32	40	90	130	4	0,73	2
11032E05	●	32	32	40	90	130	5	0,72	2
11032E05-25	●	32	25	40	90	130	5	0,46	2
11035E05	●	35	32	40	90	130	5	0,75	2
11040E02	●	40	32	30	120	150	2	0,96	2
11040E04	●	40	32	30	120	150	4	0,94	2
11040E06	●	40	32	30	120	150	6	0,93	2
11050E05	●	50	32	30	120	150	5	1,04	2
11050E07	●	50	32	30	120	150	7	1,04	2
11063E08	●	63	32	30	120	150	8	1,24	2
11080E10	●	80	32	30	120	150	10	1,52	2

Inserts are sold separately.

Spare Parts

Applicable Cutters	Insert Screw		Wrench
		N·m	
WEZ 11014E01 11016E02(-12) 11018E02	BFTX0305IP	2,0	TRDR08IP
11020E02(-16) 11020E03(-16) 11022E03 11025E02 11025E03(-20) 11025E04(-20) 11028E04 11030E04 11032E02 11032E03 11032E04 11032E05(-25) 11035E05 11040E02 11040E04 11040E06 11050E05 11050E07 11063E08 11080E10	BFTX0306IP	1,5	

Identification Details

WEZ	11	025	E	02	-	22
Cutter Series	Insert Size	Cutter Diameter	Round Shank	Number of Teeth		Shank Diameter

Recommended Cutting Conditions

☞ H22

Indexable Endmills

● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide							Carbide	DLC	Cermet	
High Speed / Light Cut		P		K		M S			N	P	
General Purpose	K P M S		P		K	M S	M S	N	N		
Roughing	K P M S		P		K		M S				
Cat. No.	ACU2500	ACP2000	ACP3000	ACK2000	ACK3000	ACM200	ACM300	H20	DL2000	T2500A	RE (mm)
AOMT 11T302PEER-G	●	●	●	●	●	●	●	–	–	●	0,2
11T304PEER-G	●	●	●	●	●	●	●	–	–	●	0,4
11T308PEER-G	●	●	●	●	●	●	●	–	–	●	0,8
11T312PEER-G	●	●	●	●	●	●	●	–	–	●	1,2
11T316PEER-G	●	●	●	●	●	●	●	–	–	●	1,6
11T320PEER-G	●	●	●	●	●	●	●	–	–	●	2,0
11T324PEER-G	●	●	●	●	●	●	●	–	–	●	2,4
11T330PEER-G	●	●	●	●	●	●	●	–	–	●	3,0
11T332PEER-G	●	●	●	●	●	●	●	–	–	●	3,2
AOMT 11T304PEER-H	●	●	●	●	●	●	●	–	–	–	0,4
11T308PEER-H	●	●	●	●	●	●	●	–	–	–	0,8
11T312PEER-H	●	●	●	●	●	●	●	–	–	–	1,2
11T316PEER-H	●	●	●	●	●	●	●	–	–	–	1,6
AOET 11T302PEER-F	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-F	●	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-F	●	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-F	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 11T302PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P16	❍	–	–	–	–	–	–	–	–	–	1,2
11T302PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P20	❍	–	–	–	–	–	–	–	–	–	1,2
11T302PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P25	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 11T302PEFR-S	–	–	–	–	–	–	–	❍	❍	–	0,2
11T304PEFR-S	–	–	–	–	–	–	–	●	●	–	0,4
11T308PEFR-S	–	–	–	–	–	–	–	●	●	–	0,8
11T312PEFR-S	–	–	–	–	–	–	–	❍	❍	–	1,2



L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P16 is applicable to cutter diameters Ø 14 mm and Ø 16 mm.
*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

– = Not available

Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.



*When mounting inserts with nose radius of ≥ 3,0 mm, modification of the body is required.



Reworking guidelines
Nose radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Nose radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

"Wave Mill" Series
WEZ 11000 EL

New

Rake Angle		
	Radial	-7° – -18°
	Axial	6° – 15°

10 mm 90°

Fig. 1



Fig. 2



Body - WEZ (Long Type)

Dimensions (mm)

Cat. No.	Stock	DC	DMM	LH	LS	LF	No. of Teeth	Weight (kg)	Fig.
WEZ 11014EL01	●	14	16	25	95	120	1	0,16	1
11016EL02	●	16	16	25	120	145	2	0,19	1
11016EL02-14	●	16	14	25	120	145	2	0,15	2
11018EL02	●	18	16	25	120	145	2	0,20	2
11020EL02	●	20	20	40	110	150	2	0,31	1
11020EL02-18	●	20	18	25	125	150	2	0,26	2
11022EL02	●	22	20	30	120	150	2	0,32	2
11025EL02	●	25	25	50	120	170	2	0,57	1
11025EL02-22	●	25	22	30	140	170	2	0,46	2
11025EL03	●	25	25	50	120	170	3	0,57	1
11028EL02	●	28	25	30	140	170	2	0,60	2
11030EL02	●	30	25	30	140	170	2	0,62	2
11032EL02	●	32	32	60	110	170	2	0,97	1
11032EL02-30	●	32	30	30	140	170	2	0,88	2
11032EL03	●	32	32	60	110	170	3	0,96	1
11035EL02	●	35	32	30	140	170	2	1,02	2
11035EL03	●	35	32	30	140	170	3	1,00	2
11040EL02	●	40	32	30	140	170	2	1,08	2
11050EL03	●	50	32	30	140	170	3	1,19	2

Inserts are sold separately.

Spare Parts

Applicable Cutters	Insert Screw	N·m	Wrench
WEZ 11014EL01		2,0	
11016EL02(-14)	BFTX0305IP		
11018EL02			
11020EL02(-18)			
11022EL02			
11025EL02(-22)			
11025EL03			
11028EL02		1,5	TRDR08IP
11030EL02			
11032EL02(-30)	BFTX0306IP		
11032EL03			
11035EL02			
11035EL03			
11040EL02			
11050EL03			

Identification Details

WEZ	11	025	E	L	02	-	22
Cutter Series	Insert Size	Cutter Diameter	Round Shank	Long Type	Number of Teeth		Shank Diameter

Recommended Cutting Conditions

☞ H22

● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide							Carbide	DLC	Cermet	
High Speed / Light Cut		P		K		M S			N	P	
General Purpose	K P M S		P		K	M S	M S	N	N		
Roughing	K P M S		P		K		M S				
Cat. No.	ACU2500	ACP2000	ACP3000	ACK2000	ACK3000	ACM200	ACM300	H20	DL2000	T2500A	RE (mm)
AOMT 11T302PEER-G	●	●	●	●	●	●	●	–	–	●	0,2
11T304PEER-G	●	●	●	●	●	●	●	–	–	●	0,4
11T308PEER-G	●	●	●	●	●	●	●	–	–	●	0,8
11T312PEER-G	●	●	●	●	●	●	●	–	–	●	1,2
11T316PEER-G	●	●	●	●	●	●	●	–	–	●	1,6
11T320PEER-G	●	●	●	●	●	●	●	–	–	●	2,0
11T324PEER-G	●	●	●	●	●	●	●	–	–	●	2,4
11T330PEER-G	●	●	●	●	●	●	●	–	–	●	3,0
11T332PEER-G	●	●	●	●	●	●	●	–	–	●	3,2
AOMT 11T304PEER-H	●	●	●	●	●	●	●	–	–	–	0,4
11T308PEER-H	●	●	●	●	●	●	●	–	–	–	0,8
11T312PEER-H	●	●	●	●	●	●	●	–	–	–	1,2
11T316PEER-H	●	●	●	●	●	●	●	–	–	–	1,6
AOET 11T302PEER-F	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-F	●	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-F	●	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-F	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 11T302PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P16	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P16	❍	–	–	–	–	–	–	–	–	–	1,2
11T302PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P20	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P20	❍	–	–	–	–	–	–	–	–	–	1,2
11T302PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,2
11T304PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,4
11T308PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,8
11T312PEER-P25	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 11T302PEFR-S	–	–	–	–	–	–	–	❍	❍	–	0,2
11T304PEFR-S	–	–	–	–	–	–	–	●	●	–	0,4
11T308PEFR-S	–	–	–	–	–	–	–	●	●	–	0,8
11T312PEFR-S	–	–	–	–	–	–	–	❍	❍	–	1,2



L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P16 is applicable to cutter diameters Ø 14 mm and Ø 16 mm.
*P20 is applicable to cutter diameters Ø 18 mm, Ø 20 mm.
*P25 is applicable to cutter diameters Ø 25 mm, Ø 28 mm.

– = Not available

Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.



*When mounting inserts with nose radius of ≥ 3,0 mm, modification of the body is required.



Reworking guidelines
Nose radius = 3,0 mm: C = 1 mm (AOMT11T330PEER)
Nose radius = 3,2 mm: C = 1 mm (AOMT11T332PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

WEZ 17000 E

New

Rake Angle		
	Radial	-6° – -12°
	Axial	6° – 15°

15 mm 90°

Fig. 1



Fig. 2



Body - WEZ (Shank Type)

Dimensions (mm)

Cat. No.	Stock	DC	DMM	LH	LS	LF	No. of Teeth	Weight (kg)	Fig.
WEZ 17025E02	●	25	25	35	85	120	2	0,38	1
17025E02-20	●	25	20	35	85	120	2	0,25	2
17028E02	●	28	25	35	85	120	2	0,40	2
17030E03	●	30	25	40	90	130	3	0,43	2
17032E02	●	32	32	40	90	130	2	0,71	1
17032E03	●	32	32	40	90	130	3	0,69	1
17032E03-25	●	32	25	40	90	130	3	0,44	2
17035E03	●	35	32	40	90	130	3	0,72	2
17040E03	●	40	32	30	105	135	3	0,81	2
17040E04	●	40	32	30	105	135	4	0,79	2
17050E03	●	50	32	30	105	135	3	0,93	2
17050E03-42	●	50	42	30	105	135	3	1,41	2
17050E05	●	50	32	30	105	135	5	0,89	2
17050E05-42	●	50	42	30	105	135	5	1,37	2
17063E04	●	63	32	30	105	135	4	1,10	2
17063E04-42	●	63	42	30	105	135	4	1,58	2
17063E06	●	63	32	30	105	135	6	1,08	2
17063E06-42	●	63	42	30	105	135	6	1,56	2
17080E07	●	63	32	30	105	135	7	1,39	2

Inserts are sold separately.

Spare Parts

Applicable Cutters	Insert Screw		Wrench
			
WEZ 17025E02(-20)	BFTX0407IP	3,0	TRDR15IP
17028E02			
17030E03			
17032E02	BFTX0409IP		
17032E03(-25)			
17035E03			
17040E03			
17040E04			
17050E03(-42)			
17050E05(-42)			
17063E04(-42)			
17063E06(-42)			
17080E07			

Identification Details

WEZ	17	032	E	02	-	30
Cutter Series	Insert Size	Cutter Diameter	Round Shank	Number of Teeth		Shank Diameter

Recommended Cutting Conditions

☞ H22

● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide							Carbide	DLC	Cermet	
High Speed / Light Cut		P		K		MS			N	P	
General Purpose	KPMS		P		K	MS	MS	N	N		
Roughing	KPMS		P		K		MS				
Cat. No.	ACU2500	ACP2000	ACP3000	ACK2000	ACK3000	ACM200	ACM300	H20	DL2000	T2500A	RE (mm)
AOMT 170502PEER-L	●	–	●	–	●	●	●	–	–	●	0,2
170504PEER-L	●	–	●	–	●	●	●	–	–	●	0,4
170508PEER-L	●	–	●	–	●	●	●	–	–	●	0,8
170512PEER-L	●	–	●	–	●	●	●	–	–	●	1,2
170516PEER-L	●	–	●	–	●	●	●	–	–	●	1,6
AOMT 170502PEER-G	●	●	●	●	●	●	●	–	–	●	0,2
170504PEER-G	●	●	●	●	●	●	●	–	–	●	0,4
170508PEER-G	●	●	●	●	●	●	●	–	–	●	0,8
170512PEER-G	●	●	●	●	●	●	●	–	–	●	1,2
170516PEER-G	●	●	●	●	●	●	●	–	–	●	1,6
170520PEER-G	●	●	●	●	●	●	●	–	–	●	2,0
170524PEER-G	●	●	●	●	●	●	●	–	–	●	2,4
170530PEER-G	●	●	●	●	●	●	●	–	–	●	3,0
170532PEER-G	●	●	●	●	●	●	●	–	–	●	3,2
170540PEER-G	●	●	●	●	●	●	●	–	–	●	4,0
170550PEER-G	●	●	●	●	●	●	●	–	–	●	5,0
170564PEER-G	●	●	●	●	●	●	●	–	–	●	6,4
AOMT 170504PEER-H	●	●	●	●	●	●	●	–	–	–	0,4
170508PEER-H	●	●	●	●	●	●	●	–	–	–	0,8
170512PEER-H	❍	●	●	●	●	●	●	–	–	–	1,2
170516PEER-H	●	●	●	●	●	●	●	–	–	–	1,6
AOET 170502PEER-F	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-F	●	–	–	–	–	–	–	–	–	–	0,4
170508PEER-F	●	–	–	–	–	–	–	–	–	–	0,8
170512PEER-F	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 170502PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,4
170508PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,8
170512PEER-P25	❍	–	–	–	–	–	–	–	–	–	1,2
170502PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,4
170508PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,8
170512PEER-P32	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 170502PEFR-S	–	–	–	–	–	–	–	❍	❍	–	0,2
170504PEFR-S	–	–	–	–	–	–	–	●	●	–	0,4
170508PEFR-S	–	–	–	–	–	–	–	●	●	–	0,8
170512PEFR-S	–	–	–	–	–	–	–	❍	❍	–	1,2



L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P25 is applicable to cutter diameters Ø 25 mm and Ø 28 mm.
*P32 is applicable to cutter diameters Ø 30 mm, Ø 32 mm and Ø 35 mm.

– = Not available

Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between he surfaces.



*When mounting inserts with nose radius of ≥ 3,0 mm, modification of the body is required.



Reworking guidelines
Nose radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Nose radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Nose radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Nose radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Nose radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

WEZ 17000 EL

New

Rake Angle		
	Radial	-6° – -12°
	Axial	6° – 15°

15 mm 90°

Fig. 1



Fig. 2



Body - WEZ (Long Type)

Dimensions (mm)

Cat. No.	Stock	DC	DMM	LH	LS	LF	No. of Teeth	Weight (kg)	Fig.
WEZ 17025EL02	●	25	25	50	120	170	2	0,55	1
17028EL02	●	28	25	50	120	170	2	0,57	2
17030EL02	●	30	25	50	120	170	2	0,59	2
17032EL02	●	32	32	60	110	170	2	0,94	1
17032EL02-30	●	32	30	50	120	170	2	0,85	2
17032EL03	●	32	32	60	110	170	3	0,92	1
17035EL02	●	35	32	50	120	170	2	0,98	2
17040EL02	●	40	32	50	120	170	2	1,09	2
17040EL03	●	40	32	50	120	170	3	1,08	2
17040EL04	●	40	32	50	120	170	4	1,05	2
17050EL03	●	50	32	50	120	170	3	1,29	2
17050EL03-42	●	50	42	50	120	170	3	1,83	2
17050EL05	●	50	32	50	120	170	5	1,25	2
17050EL05-42	●	50	42	50	120	170	5	1,79	2
17063EL04	●	63	32	50	120	170	4	1,61	2
17063EL04-42	●	63	42	50	120	170	4	2,16	2
17063EL06	●	63	32	50	120	170	6	1,58	2
17063EL06-42	●	63	42	50	120	170	6	2,13	2

Inserts are sold separately.

Spare Parts

Applicable Cutters	Insert Screw		Wrench
		N·m	
WEZ 17025EL02	BFTX0407IP	3,0	TRDR15IP
17028EL02			
17030EL02			
17032EL02(-30)	BFTX0409IP		
17032EL03			
17035EL02			
17040EL02			
17040EL03			
17040EL04			
17050EL03(-42)			
17050EL05(-42)			
17063EL04(-42)			
17063EL06(-42)			

Identification Details

WEZ	11	025	E	L	02	-	22
Cutter Series	Insert Size	Cutter Diameter	Round Shank	Long Type	Number of Teeth		Shank Diameter

Recommended Cutting Conditions

☞ H22

● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

Inserts

Application	Coated Carbide							Carbide	DLC	Cermet	
High Speed / Light Cut		P		K		M S			N	P	
General Purpose	K P M S		P		K	M S	M S	N	N		
Roughing	K P M S		P		K		M S				
Cat. No.	ACU2500	ACP2000	ACP3000	ACK2000	ACK3000	ACM200	ACM300	H20	DL2000	T2500A	RE (mm)
AOMT 170502PEER-L	●	–	●	–	●	●	●	–	–	●	0,2
170504PEER-L	●	–	●	–	●	●	●	–	–	●	0,4
170508PEER-L	●	–	●	–	●	●	●	–	–	●	0,8
170512PEER-L	●	–	●	–	●	●	●	–	–	●	1,2
170516PEER-L	●	–	●	–	●	●	●	–	–	●	1,6
AOMT 170502PEER-G	●	●	●	●	●	●	●	–	–	●	0,2
170504PEER-G	●	●	●	●	●	●	●	–	–	●	0,4
170508PEER-G	●	●	●	●	●	●	●	–	–	●	0,8
170512PEER-G	●	●	●	●	●	●	●	–	–	●	1,2
170516PEER-G	●	●	●	●	●	●	●	–	–	●	1,6
170520PEER-G	●	●	●	●	●	●	●	–	–	●	2,0
170524PEER-G	●	●	●	●	●	●	●	–	–	●	2,4
170530PEER-G	●	●	●	●	●	●	●	–	–	●	3,0
170532PEER-G	●	●	●	●	●	●	●	–	–	●	3,2
170540PEER-G	●	●	●	●	●	●	●	–	–	●	4,0
170550PEER-G	●	●	●	●	●	●	●	–	–	●	5,0
170564PEER-G	●	●	●	●	●	●	●	–	–	●	6,4
AOMT 170504PEER-H	●	●	●	●	●	●	●	–	–	–	0,4
170508PEER-H	●	●	●	●	●	●	●	–	–	–	0,8
170512PEER-H	❍	●	●	●	●	●	●	–	–	–	1,2
170516PEER-H	●	●	●	●	●	●	●	–	–	–	1,6
AOET 170502PEER-F	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-F	●	–	–	–	–	–	–	–	–	–	0,4
170508PEER-F	●	–	–	–	–	–	–	–	–	–	0,8
170512PEER-F	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 170502PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,4
170508PEER-P25	❍	–	–	–	–	–	–	–	–	–	0,8
170512PEER-P25	❍	–	–	–	–	–	–	–	–	–	1,2
170502PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,2
170504PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,4
170508PEER-P32	❍	–	–	–	–	–	–	–	–	–	0,8
170512PEER-P32	❍	–	–	–	–	–	–	–	–	–	1,2
AOET 170502PEFR-S	–	–	–	–	–	–	–	❍	❍	–	0,2
170504PEFR-S	–	–	–	–	–	–	–	●	●	–	0,4
170508PEFR-S	–	–	–	–	–	–	–	●	●	–	0,8
170512PEFR-S	–	–	–	–	–	–	–	❍	❍	–	1,2



L: Low cutting force
G: General purpose
H: Strong edge
F: Finishing
P: High-precision machining
S: Non ferrous metals

*P25 is applicable to cutter diameters Ø 25 mm and Ø 28 mm.
*P32 is applicable to cutter diameters Ø 30 mm, Ø 32 mm and Ø 35 mm.

❍ = Available from April 2020

– = Not available

Precautions for Mounting

(1) Clean the mounting seat and contact parts.

(2) Apply screw lubrication to the screw thread as well as the screw head face to prevent seizure.

(3) While pressing the insert solidly against the seat surface, tighten at the screws with the included wrench.

(4) After tightening, check that there are no gaps between the surfaces.



*When mounting inserts with nose radius of ≥ 3,0 mm, modification of the body is required.



Reworking guidelines
Nose radius = 3,0 mm: C = 1 mm (AOMT170530PEER)
Nose radius = 3,2 mm: C = 1 mm (AOMT170532PEER)
Nose radius = 4,0 mm: C = 2 mm (AOMT170540PEER)
Nose radius = 5,0 mm: C = 5 mm (AOMT170550PEER)
Nose radius = 6,4 mm: C = 5 mm (AOMT170564PEER)
Standard: R = 1 mm

C: Chamfer
R: Radius

■ General Features

Wide Application Range



■ Ramping (Slant Milling)

Tool Diam. Ø D	Max. Ramping Angle		
	Type 1000	Type 2000	Type 3000
10	2°30'		
12	1°45'		
14	1°25'	1°40‘	
16	1°00	1°20‘	
18	0°45'	1°10‘	
20	0°30'	1°00‘	
25	0°30'	0°45‘	1°30‘
32	0°25‘	0°35‘	1°00‘
40	0°20‘	0°25‘	0°45‘
50	0°15‘	0°20‘	0°30‘
63	0°10‘	0°15‘	0°20'
80			0°15'
100			–

Maximum ramping angle (α max. max.) depends on cutter diameter.

● Precision insert with strong cutting edge and low cutting force

Wave shaped cutting edge design lowers cutting resistance yet improves cutting edge strength.
Achieving high quality finish with high precision cutting edge.
Smooth cutting even for deep grooves and low rigidity machines.

High precision curved cutting edge



High rake wave cutting edge



● Internal Coolant Holes

Improved chip evacuation with air or coolant supply.

● Wide Variety of Inserts

6 types of chipbreaker design
(L, G, H, E, EH and S)
9 milling grades for a wide range of work materials and applications.
- ACP100, ACP200, ACP300
  (steel milling grades)
- ACK200, ACK300
  (cast iron milling grades)
- ACM200, ACM300
  (stainless steel, exotic alloy milling grades)
- DL1000, H1
  (aluminium milling grades)

● High Durable Body

Special surface treatment improves corrosion resistance as well as scratch resistance.
Increased screw size improves clamping force and durability.

■ Product Range

Type	Cat. No.	Series	Diameter Range (mm) Ø 10 Ø 20 Ø 40 Ø 60	Image
Shank	WEX 1000E	Short Type	10 – 25	 WEX3000 WEX2000 WEX1000
	WEX 1000EL	Long Type	10 – 20	
	WEX 2000E	Short Type	14 – 63	
	WEX 2000EL	Long Type	14 – 40	
	WEX 2000EW	Weldon Shank Short Type	16 – 20	
	WEX 3000E	Short Type	25 – 63	
	WEX 3000EL	Long Type	25 – 40	
	WEX 3000EW	Weldon Shank Short Type	25 – 32	
Shell	WEX 1000F	Shell Type	32 – 63	  ☞ G48
	WEX 2000F	Shell Type	40 – 63	
	WEX 3000F	Shell Type	40 – 63	
Modular	WEX 2000M	ModularType	16 – 40	
	WEX 3000M	Modular Type	25 – 40	

Inserts for WEX Type

WEX1000 Type Expansion

- Efficient machining via high number of inserts
- Precise insert change tolerance provides high surface roughness qualitiy
- High shoulder accuracy due to optimized cutting edge
- Stable cutting conditions when utilising low rigidity machines
- Economic advantages using small AXMT06 inserts

WEX3000 WEX2000 WEX1000

Application Range

Shoulder Milling



Chipbreaker Selection



Characteristics

Work Material	Steel, Cast Iron			Stainless Steel, Exotic Alloy		Aluminium
	L	G	H	E	EH	S
Chipbreaker						
Features	Low Cutting Force	General Purpose	Strong Edged	General Purpose	Strong Edged	High Rake
Chipbreaker Profile for 1000 Series Insert						
Chipbreaker Profile for 2000 Series Insert						
Chipbreaker Profile for 3000 Series Insert						
Application	Light cut, low rigidity milling and reduced burrs	**Main chipbreaker** general purpose to interrupted milling	Roughing, heavy interrupted and hardened steel milling	Light cutting to general purpose	Heavy interrupted machining	Aluminium, non-ferrous metal

Grade Selection





WEX 1000 E/EL

Shank Type

Rake Angle		
	Radial	8°–15°
	Axial	16°–24°

5 mm, 90°



● Body (Short Type „E“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 1010 E	●	10	10	17	33	50	2	0,03
1012 E	●	12	12	20	60	80	3	0,06
1014 E	●	14	16	22	59	80	3	0,10
1016 E	●	16	16	20	72	90	4	0,12
1018 E	●	18	20	20	80	100	4	0,21
WEX 1020 E	●	20	20	22	78	100	5	0,22
1025 E	●	25	20	25	90	115	7	0,27

● Body (Long Type „EL“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 1010 EL	●	10	8	17	83	100	2	0,03
1012 EL	●	12	10	20	100	120	2	0,06
1014 EL	●	14	12	20	125	145	3	0,11
1016 EL	●	16	14	20	140	160	3	0,17
1016 EL15	●	16	15	20	140	160	3	0,19
1018 EL	●	18	16	20	160	180	3	0,25
WEX 1020 EL	●	20	18	25	175	200	4	0,36
1020 EL19	●	20	19	25	175	200	4	0,38

Inserts are not included.

Inserts for WEX1000 Type



Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		M S		K N	N	
General Purpose		P		K		M S	M S		N	
Roughing		P	P		K		M S			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 060204 PDER-L	❍	●	❍	❍	●	●	●	–	–	0,4
060208 PDER-L	❍	❍	❍	❍	❍	❍	❍	–	–	0,8
060212 PDER-L	❍	❍	❍	❍	❍	❍	❍	–	–	1,2
AXMT 060204 PDER-G	❍	●	●	❍	❍	❍	●	–	–	0,4
060208 PDER-G	❍	●	●	❍	❍	●	●	–	–	0,8
060212 PDER-G	❍	●	❍	❍	❍	❍	●	–	–	1,2
AXMT 060204 PDER-H	❍	●	●	❍	●	❍	●	–	–	0,4
060208 PDER-H	❍	●	●	❍	●	●	●	–	–	0,8
060212 PDER-H	❍	❍	❍	❍	❍	❍	❍	–	–	1,2
AXMT 060202 PDFR-S	–	–	–	–	–	–	–	❍	❍	0,2

L - Low cutting force
G - General type
H - Strong cutting edge
S - For aluminium alloy

Identification Details

WEX	1	016	EL	15
Cutter Series	1000 Series	Cutter Diameter	Shank Type	Shank Diameter

Spare Parts

Screw	Wrench	Applicable Endmill
0,5 N·m		
BFTX 01804 IP	TRX 06 IP	WEX 1000

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
N·m Recommended Tightening Torque (N·m)

WEX 2000 E/EL

Shank Type

Rake Angle: Radial 8°–15°, Axial 16°–24°

10 mm 90°



Body (Short Type „E“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 2014 E	●	14	16	25	55	80	1	0,10
2016 E	●	16	16	25	75	100	2	0,13
2018 E	●	18	16	25	75	100	2	0,14
WEX 2020 E	●	20	20	30	80	110	3	0,22
2022 E	●	22	20	30	80	110	3	0,23
WEX 2025 E	●	25	25	35	85	120	4	0,38
2028 E	❑	28	25	35	85	120	4	0,39
2030 E	●	30	25	35	85	120	4	0,40
WEX 2032 E	●	32	32	40	90	130	5	0,70
2040 E	❍	40	32	30	120	150	6	0,91
WEX 2050 E	❍	50	32	30	120	150	7	1,02
2063 E	❍	63	32	30	120	150	8	1,22

Body (Long Type „EL“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 2014 EL	●	14	16	25	95	120	1	0,14
2016 EL	●	16	16	25	120	145	2	0,19
2018 EL	❑	18	16	25	120	145	2	0,19
WEX 2020 EL	●	20	20	40	110	150	2	0,32
2022 EL	❑	22	20	30	120	150	2	0,33
WEX 2025 EL	●	25	25	50	120	170	2	0,55
2028 EL	❍	28	25	30	140	170	2	0,59
2030 EL	❍	30	25	30	140	170	2	0,60
WEX 2032 EL	❍	32	32	60	120	180	2	0,99
2040 EL	❑	40	32	30	150	180	2	1,12

Body (Long Type „E“ + Small Shank)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 2016 EL15	❑	16	15	25	120	145	2	0,17
2020 EL19	●	20	19	40	110	150	2	0,30
2025 EL24	●	25	24	50	120	170	2	0,53
2025 EL24Z3	❑	25	24	50	120	170	3	0,50
2032 EL30Z4	❑	32	30	60	120	180	2	0,95

Body (Weldon Shank Short Type „EW“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 2016 EW	●	16	16	25	75	100	2	0,12
2020 EW	●	20	20	30	80	110	3	0,21

Inserts are not included.

Identification Details

WEX	2	016	EL	15
Cutter Series	2000 Series	Cutter Diameter	Shank Type	Shank Diameter

Spare Parts

Screw	Wrench	Applicable Endmill
2,0 N·m		
BFTX 0305 IP	TRDR 08 IP	WEX 2014 – WEX 2018
BFTX 0306 IP		WEX 2020 – WEX 2063

WEX 2000 M

Modular Type

Rake Angle: Radial 10°–18°, Axial 14°–25°

10mm 90°



Head

Cat. No.	Stock	Dimensions (mm)									No. of Teeth
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
WEX 2016M08Z2	●	16	8,5	M8	42	25	5	17	8	13	2
2018M08Z2	❑	18	8,5	M8	42	25	5	17	8	13	2
WEX 2020M10Z3	●	20	10,5	M10	49	30	5	19	8	15	3
2022M10Z3	❑	22	10,5	M10	49	30	5	19	8	15	3
WEX 2025M12Z4	●	25	12,5	M12	56	35	5	21	10	19	4
2028M12Z4	❑	28	12,5	M12	56	35	5	21	10	19	4
WEX 2030M16Z4	❑	30	17,0	M16	63	40	5	23	10	24	4
2032M16Z5	●	32	17,0	M16	63	40	5	23	10	24	5
2040M16Z6	❑	40	17,0	M16	63	40	5	23	10	24	6

Inserts are not included.

Inserts for WEX2000 Type



Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		M S		K N	N	
General Purpose		P		K		M S	M S		N	
Roughing		P	P		K		M S			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 123504 PEER-G	●	●	●	●	●			–	–	0,4
123508 PEER-G	●	●	●	●	●			–	–	0,8
123512 PEER-G	●	●	●	●	●			–	–	1,2
AXMT 123504 PEER-H	●	●	●	●	●			–	–	0,4
123508 PEER-H	●	●	●	●	●			–	–	0,8
123512 PEER-H	●	●	●	❍	●			–	–	1,2
AXMT 123504 PEER-E						●	●	–	–	0,4
123508 PEER-E			▲			●	●	–	–	0,8
123512 PEER-E						●	●	–	–	1,2
AXMT 123508 PEER-EH			▲			●	●	–	–	0,8
AXET 123502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
123504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
123508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

G - General type
H - Strong cutting edge
E - For stainless steel / exotic alloy
EH - Strong edge for stainless steel / exotic alloy
S - For aluminium alloy

– Unable to produce

Identification Details

WEX	2	016	M08	Z2
Cutter Series	2000 Series	Cutter Diameter	Mounting Screw Size	No. of Teeth

Spare Parts

Screw	Wrench	N·m	Applicable Endmill
BFTX 0305 IP	TRDR 08 IP	2,0	WEX 2016M, WEX 2018M
BFTX 0306 IP		2,0	WEX 2020M – WEX 2040M
BFTX 0407 IP	TRDR 15 IP	3,0	WEX 3025M – WEX 3030M
BFTX 0409 IP		3,0	WEX 3032M – WEX 3040M

WEX 3000 E/EL

Shank Type

Rake Angle: Radial 8°–15°, Axial 16°–24°

14 mm 90°



Body (Short Type „E“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 3025 E	●	25	25	35	85	120	2	0,37
3028 E	❑	28	25	35	85	120	2	0,39
3030 E	❑	30	25	40	90	130	3	0,42
WEX 3032 E	●	32	32	40	90	130	3	0,67
3035 E	❑	35	32	40	90	130	3	0,69
3040 E	●	40	32	50	120	170	4	1,01
3050 E	❑	50	32	50	120	170	5	1,23
3063 E	❑	63	32	50	120	170	6	1,58

Body (Short Type „E“ + Small Shank)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 3025 E20	❑	25	20	35	85	120	2	0,25
3032 E25	❑	32	25	40	90	130	3	0,43

Body (Long Type „EL“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 3025 EL	●	25	25	50	120	170	2	0,54
3028 EL	❑	28	25	50	120	170	2	0,56
3030 EL	❑	30	25	60	120	180	2	0,60
WEX 3032 EL	●	32	32	60	120	180	2	0,95
3035 EL	❑	35	32	60	120	180	2	0,98
3040 EL	●	40	32	80	140	220	2	1,38

Body (Weldon Shank Short Type „EW“)

Cat. No.	Stock	Dimensions (mm)					No. of Teeth	Weight (kg)
		DC	DMM	LH	LS	LF		
WEX 3025 EW	●	25	25	35	85	120	2	0,36
3032 EW	●	32	32	40	90	130	3	0,65

Inserts are not included.

✻ **ATTENTION**: If nose radius of inserts is 2,0 mm or more please modify cutter body as indicated.

Standard Chamfer is 0,5 mm by 45 degrees

Increase Chamfer to 1 mm x 45 degrees when using 2,0 mm radius inserts AXMT 170520PEER

Increase chamfer to 1,5 mm x 45 degrees when using 3,0 mm radius inserts AXMT 170530 PEER

Spare Parts

Screw	Wrench	Applicable Endmill
3,0 N·m		
BFTX 0407 IP BFTX 0409 IP	TRDR 15 IP	WEX 3025 – WEX 3030 WEX 3032 – WEX 3063

WEX 3000 M

Modular Type

Rake Angle: Radial 8°–15°, Axial 16°–24°

14 mm 90°



Head

Cat. No.	Stock	Dimensions (mm)									No. of Teeth
		DC	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
WEX 3025M12Z2	●	25	12,5	M12	56	35	5	21	10	19	2
3028M12Z2	❑	28	12,5	M12	56	35	5	21	10	19	2
WEX 3030M16Z3	❑	30	17,0	M16	63	40	5	23	10	24	3
3032M16Z3	●	32	17,0	M16	63	40	5	23	10	24	3
3035M16Z3	❑	35	17,0	M16	63	40	5	23	10	24	3
3040M16Z4	❑	40	17,0	M16	63	40	5	23	10	24	4

Inserts are not included.

Inserts for WEX3000 Type



Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		M S		K N	N	
General Purpose		P		K		M S	M S		N	
Roughing		P	P		K		M S			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 170508 PEER-L	●	●	●	❍	●			–	–	0,8
AXMT 170504 PEER-G	❍	●	●	●	●			–	–	0,4
170508 PEER-G	●	●	●	●	●			–	–	0,8
170512 PEER-G	❍	●	●	❍	●			–	–	1,2
170516 PEER-G	❍	●	●	❍	●			–	–	1,6
170520 PEER-G*	❍	●	●	●	●			–	–	2,0
170530 PEER-G*	●	●	●	●	●			–	–	3,0
AXMT 170508 PEER-H	●	●	●	●	●			–	–	0,8
170512 PEER-H	●	●	●	●	●			–	–	1,2
AXMT 170504 PEER-E						●	●	–	–	0,4
170508 PEER-E			▲			●	●	–	–	0,8
170512 PEER-E						●	●	–	–	1,2
170516 PEER-E						❍	●	–	–	1,6
170520 PEER-E*						❍	●	–	–	2,0
170530 PEER-E*						●	●	–	–	3,0
AXMT 170508 PEER-EH			▲			●	●	–	–	0,8
AXET 170502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
170504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
170508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

L - Low cutting force
G - General type
H - Strong cutting edge
E - For stainless steel / exotic alloy
EH - Strong edge for stainless steel / exotic alloy
S - For aluminium alloy

– Unable to produce
* Cutter body modification is required

Identification Details

WEX	3	025	M12	Z2
Cutter Series	3000 Series	Cutter Diameter	Mounting Screw Size	No. of Teeth

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
N·m Recommended Tightening Torque (N·m)

■ Recommended Cutting Conditions



● WEX1000 Series

Cutter: WEX1012E Insert: AXMT060208PDER - □

Cutting Data: a_p = 4 mm, a_e = 1 mm, dry

ISO	Material	HB	Chipbreaker	Coated Carbide																						„Diamond like Carbon" Coated Carbide		
				ACP100			ACP200			ACP300			ACK200			ACK300			ACM200			ACM300					
				Feed Rate (mm/tooth)																								
				0,08	0,12	0,16	0,08	0,12	0,16	0,08	0,12	0,16	0,10	0,15	0,20	0,10	0,15	0,20	0,08	0,10	0,12	0,08	0,10	0,12			
				Cutting Speed v_c (m/min)																								
P	Unalloyed steel, <0, 15%C, annealed	125	G	280	240	220	240	220	200	220	200	180																
	" , <0, 45%C, annealed	190	G	200	180	160	180	160	140	180	160	140																
	" , <0, 45%C, tempered	250	G	180	120	140	160	140	120	150	130	110																
	" , <0, 75%C, annealed	270	G	160	140	120	150	130	110	130	110	110																
	" , <0, 75%C, tempered	300	G	100	80	70	90	70	60	70	60	50																
	Low alloyed steel, annealed	180	G	200	180	160	180	160	150	160	150	130																
	" , tempered	275	G	130	110	90	120	100	90	100	90	80																
	" , tempered	300	G	120	100	80	100	90	80	90	80	60																
	" , tempered	350	G	90	80	60	80	70	60	70	60	40																
	High alloyed and tool steel, annealed	200	G	180	170	160	170	160	130	150	140	120																
	" , tempered	325	G	100	80	60	80	60	50	60	50	30																
M	Stainless steel, ferritic/martensitic, annealed	200	E																175	150	120	140	130	110			
	Martensitic, tempered	240	E																140	120	100	120	100	90			
	Austenitic, plunged	180	E																180	160	140	160	140	130			
K	Grey cast iron		G										240	220	200	220	200	180									
	Nodular cast iron		G										160	140	120	140	120	100									
S	High tempered resist. alloys, Fe based, annealed		E																50	35		45	25				

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.

For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

● WEX2000 Series

Cutter: WEX2025E Insert: AXMT123508PEER - □

Cutting Data: a_p = 3 mm, a_e = 12,5 mm, dry



ISO	Material	HB	Chipbreaker	Coated Carbide																							„Diamond like Carbon" Coated Carbide		
				ACP100			ACP200			ACP300			ACK200			ACK300			ACM200			ACM300						DL1000		
				Feed Rate (mm/tooth)																										
				0,08	0,15	0,20	0,08	0,15	0,20	0,08	0,15	0,20	0,08	0,15	0,20	0,08	0,15	0,20	0,08	0,15	0,20	0,08	0,15	0,20				0,05	0,15	0,22
				Cutting Speed v_c (m/min)																										
P	Unalloyed steel, <0, 15%C, annealed	125	G	380	350	330	350	330	315	330	315	295																		
	" , <0, 45%C, annealed	190	G	285	255	235	255	235	220	235	220	220																		
	" , <0, 45%C, tempered	250	G	235	210	190	210	190	170	190	170	150																		
	" , <0, 75%C, annealed	270	G	190	162	143	171	152	133	152	133	115																		
	" , <0, 75%C, tempered	300	G	145	115	95	115	95	75	95	75	55																		
	Low alloyed steel, annealed	180	G	265	235	220	235	220	200	220	200	180																		
	" , tempered	275	G	170	145	125	150	130	115	130	115	95																		
	" , tempered	300	G	150	125	105	135	115	95	115	95	75																		
	" , tempered	350	G	125	95	75	105	85	65	85	65	45																		
	High alloyed and tool steel, annealed	200	G	235	210	190	210	190	170	190	170	150																		
	" , tempered	325	G	125	95	75	95	75	55	75	55	35																		
M	Stainless steel, ferritic/martensitic, annealed	200	E																175	155	125	155	140	110						
	Martensitic, tempered	240	EH																160	140	110	145	125	100						
	Austenitic, plunged	180	E																190	170	140	170	150	125						
K	Grey cast iron		G										285	255	235	255	235	220												
	Nodular cast iron		G										190	160	140	160	140	125												
S	High tempered resist. alloys, Fe based, annealed	300	E																50	40		45	35							
	" , hardened	330	E																35	25		30	20							
N	Aluminium alloy, Si < 13%		S																								1000	750	500
	Aluminium alloy, Si > 13%		S																								250	200	170
	Copper alloy		S																								350	330	300

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.

For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

■ Recommended Cutting Conditions

● WEX3000 Series



Cutter: WEX30325E Insert: AXMT170508PEER - □

Cutting Data: a_p = 5 mm, a_e = 16 mm, dry

ISO	Material	HB	Chipbreaker	Coated Carbide																					„Diamond like Carbon" Coated Carbide		
				ACP100			ACP200			ACP300			ACK200			ACK300			ACM200			ACM300			DL1000		
				Feed Rate (mm/tooth)																							
				0,12	0,25	0,35	0,12	0,25	0,35	0,12	0,25	0,35	0,12	0,25	0,35	0,12	0,25	0,35	0,12	0,25	0,35	0,12	0,25	0,35	0,05	0,15	0,25
				Cutting Speed v_c (m/min)																							
P	Unalloyed steel, <0, 15%C, annealed	125	G	400	370	350	370	350	330	350	330	310															
	" , <0, 45%C, annealed	190	G	300	270	250	270	250	230	250	230	210															
	" , <0, 45%C, tempered	250	G	250	220	200	220	200	180	200	180	160															
	" , <0, 75%C, annealed	270	G	200	170	150	180	160	140	160	140	120															
	" , <0, 75%C, tempered	300	G	150	120	100	120	100	80	100	80	60															
	Low alloyed steel, annealed	180	G	280	250	230	250	230	210	230	210	190															
	" , tempered	275	G	180	150	130	160	140	120	140	120	100															
	" , tempered	300	G	160	130	110	140	120	100	120	100	80															
	" , tempered	350	G	130	100	80	110	90	70	90	70	50															
	High alloyed and tool steel, annealed	200	G	250	220	200	220	200	180	200	180	160															
	" , tempered	325	G	130	100	80	100	80	60	80	60	40															
M	Stainless steel, ferritic/martensitic, annealed	200	E																185	165	135	165	150	120			
	Martensitic, tempered	240	EH																170	150	120	150	135	110			
	Austenitic, plunged	180	E																200	180	150	180	160	135			
K	Grey cast iron		G										300	270	250	270	250	230									
	Nodular cast iron		G										200	170	150	170	150	130									
S	High tempered resist. alloys, Fe based, annealed	300	E																50	30		45	25				
	" , hardened	330	E																50	30		45	25				
N	Aluminium alloy, Si < 13%		S																						1000	750	500
	Aluminium alloy, Si > 13%		S																						250	200	170
	Copper alloy		S																						350	330	300

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine, work shape and clamping. They will need to be adjusted according to machine rigidity, work clamp rigidity, cutting depth and other factors.

For groove milling, reduce the feed rate approximately 70 % of the corresponding value shown above.

■ Recommended Values for Helical Milling and Ramping

● Helical Boring

≤ Min. Diameter



Center uncut portion cannot be removed by traverse cutting with the same cutter.

≥ Max. Diameter



Center uncut portion can be removed by traverse cutting with the same cutter.

● Plunging

Use at ≤ RMPX



● Recommended Values for Helical and Plunging

Cutter External Diameter DC	WEX1000 (AXMT06...)			WEX2000 (AX□T12...)			WEX3000 (AX□T17...)		
	Helical		Plunging	Helical		Plunging	Helical		Plunging
	Work Diameter		Max. Ramping Angle	Work Diameter		Max. Ramping Angle	Work Diameter		Max. Ramping Angle
	Min.	Max.		Min.	Max.		Min.	Max.	
10	16,0	18,0	2°30'						
12	20,0	22,0	1°45'						
14	24,0	26,0	1°25'	25,0	27,0	1°40'			
16	28,0	30,0	1°00'	29,0	31,0	1°20'			
18	32,0	34,0	0°45'	33,0	35,0	1°10'			
20	36,0	38,0	0°30'	37,0	39,0	1°00'			
22				41,0	43,0	0°50'			
25	46,0	48,0	0°30'	47,0	49,0	0°45'	44,5	48,0	1°30'
28				53,0	55,0	0°45'	50,5	54,0	1°10'
30				57,0	59,0	0°40'	54,5	58,0	1°10'
32	60,0	62,0	0°25'	61,0	63,0	0°35'	58,5	62,0	1°00'
35							64,5	68,0	0°50'
40	76,0	78,0	0°20'	77,0	79,0	0°25'	74,5	78,0	0°45'
50	96,0	98,0	0°15'	97,0	99,0	0°20'	94,5	98,0	0°30'
63	122,0	124,0	0°10'	123,0	125,0	0°15'	120,5	124,0	0°20'
80							154,5	158,0	0°15'
100									
125									

The above recommended values are for a nose radius of 0,8 mm.

"Wave Mill" Series
WAX Type

Overview

Based on our proven Wavemill design this new range of WAX cutters is capable of rough and finishing Aluminium Alloys and other Non Ferrous Metals. It is ideal for high productivity Aluminium machining to exacting tolerances in the Aircraft, Electronics, and Automotive industries. The award winning Auroracoat DLC (diamond like carbon) inserts resist chip adhesion and substantially increase both tool life and productivity when dry machining Aluminium helping customers boost compliance with ISO14001 accreditation standards

Advantages

- High Productivity
- Dry machining capability with MQL system
- DLC (diamond like carbon) inserts
- True 90 degree shoulder milling
- Chip adhesion resistance
- Wide range of nose radius



Ramping (Slant Milling)

Maximum ramping angle (α max. max.) depends on cutter diameter.
Minimum milling length (L min) is the ramping distance required to reach the maximum cutting depth (a_p max) at the maximum ramping angle of that cutter.
Minimum milling length (L) for any depth can be calculated by the equation below:



WAX3000 E/EL Type

(mm)

Cutter Diameter DC	Ramping Angle RMPX max.	Depth- of Cut a_p max.	Milling Distance L min
20	8°	10	72
25	17°	10	33
32	12°	10	47
40	9°	10	64

WAX3000 RS Type

(mm)

Cutter Diameter DC	Ramping Angle RMPX max.	Depth- of Cut a_p max.	Milling Distance L min
50	7°	10	82
60	5°	10	115
80	3°	10	191
100	3°	10	191
125	2°	10	287

Helical Milling



Helical Milling Diameter

(mm)

Cutter Diameter DC	Milling Diameter øD	
	Min.	Max.
20	22	33
25	29	43
32	43	57
40	59	73
50	79	93
63	105	119
80	139	153
100	179	193
125	229	243

Maximum Allowable Spindle Speed

Cutter Diameter DC	Spindle Revolution n (min^{-1})	Cutting Speed v_c (m/min)
20	14.000	880
25	29.000	2.200
32	25.000	2.500
40	23.000	2.900
50	20.000	3.100
63	18.000	3.500
80	16.000	4.000
100	14.000	4.400
125	13.000	5.100

Recommended Cutting Conditions

Work Material	Aluminum Alloy
Cutting Speed	600–1.200 m/min
Feed Rate	0,05–0,25 mm/tooth

"Wave Mill" Series
WAX 3000 E/EL Type

16–18mm 90°

Axial rake angle	6°
Radial rake angle	19–25°

(Endmill)

Short Type "E"
Long Type "EL"



Body

(For inserts with nose radius ≤ 3,2 mm)

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Weight (Kg)
		DC	DMM	LF	LH	LS		
WAX 3020 E -3.2	●	20	20	130	60	70	1	0,25
WAX 3025 E -3.2	●	25	25	140	60	80	2	0,42
3025 EL-3.2	●	25	25	200	60	140	2	0,63
WAX 3032 E -3.2	●	32	32	150	70	80	2	0,75
3032 EL-3.2	●	32	32	220	70	150	2	1,2
WAX 3040 E -3.2	●	40	32	160	70	90	3	1,0
3040 EL-3.2	●	40	32	220	70	150	3	1,4

Body

(For inserts with nose radius ≥ 4,0 mm)

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Weight (Kg)
		DC	DMM	LF	LH	LS		
WAX 3020 E -4.0	●	20	20	130	60	70	1	0,25
WAX 3025 E -4.0	●	25	25	140	60	80	2	0,42
3025 EL-4.0	●	25	25	200	60	140	2	0,63
WAX 3032 E -4.0	●	32	32	150	70	80	2	0,75
3032 EL-4.0	●	32	32	220	70	150	2	1,2
WAX 3040 E -4.0	●	40	32	160	70	90	3	1,0
3040 EL-4.0	●	40	32	220	70	150	3	1,4

Inserts for WAX 3000 Type



Application	DLC Coated	Carbide
High Speed / Light cut	K N	N
General Purpose		N
Roughing		

Cat. No.	DL1000	H1	Dimensions (mm)					
			APMX	INSL	BS	RE	S	D1
AECT 160404 PEFRA	●	●	18	16,4	1,4	0,4	5	4,4
160408 PEFRA	●	●	18	16,4	1,0	0,8	5	4,4
160412 PEFRA	●	●	18	16,4	0,6	1,2	5	4,4
160416 PEFRA	●	●	17,5	16,4	0,5	1,6	5	4,4
160420 PEFRA	●	●	17,5	16,4	0,5	2,0	5	4,4
160430 PEFRA	●	●	17	16,4	0,7	3,0	5	4,4
160432 PEFRA	●	●	17	16,4	0,5	3,2	5	4,4
AECT 160440 PEFRA	●	●	16,5	16,4	0,5	4,0	5	4,4
160450 PEFRA	●	●	16	16,4	0,4	5,0	5	4,4

Spare Parts

Insert Screw		Insert Wrench	Applicable Endmill
			
BFTX 0408	3,0	TRD 15	WAX 3000 E/EL

● = Euro stock
❑ = Delivery on request

☞ G58

Recommended Tightening Torque (N·m)

WAX 4000 E/EL Type

22–24mm 90°

Axial rake angle	6°
Radial rake angle	19–25°

(Endmill)

Short Type "E"
Long Type "EL"



Body

(For inserts with nose radius ≤ 3,2 mm)

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Weight (Kg)
		DC	DMM	LF	LH	LS		
WAX 4025E -3.2	❑	25	25	140	60	80	1	0,41
4025EL-3.2	❑	25	25	200	60	140	1	0,63
WAX 4032E -3.2	❑	32	32	150	70	80	1	0,72
4032EL-3.2	❑	32	32	220	70	150	1	1,2
WAX 4040E -3.2	❑	40	32	160	70	90	2	0,88
4040EL-3.2	❑	40	32	220	70	150	2	1,2

Body

(For inserts with nose radius ≥ 4,0 mm)

Cat. No.	Stock	Dimensions (mm)					No.of teeth	Weight (Kg)
		DC	DMM	LF	LH	LS		
WAX 4025E -4.0	❑	25	25	140	60	80	1	0,41
4025EL-4.0	❑	25	25	200	60	140	1	0,63
WAX 4032E -4.0	❑	32	32	150	70	80	1	0,72
4032EL-4.0	❑	32	32	220	70	150	1	1,2
WAX 4040E -4.0	❑	40	32	160	70	90	2	0,88
4040EL-4.0	❑	40	32	220	70	150	2	1,2

Inserts for WAX 4000 Type



Application	DLC Coated	Carbide
High Speed / Light cut	K N	N
General Purpose		N
Roughing		

Cat. No.	DL1000	H1	Dimensions (mm)					
			APMX	INSL	BS	RE	S	D1
AECT 220604 PEFRA	❑	❑	24	21,8	1,5	0,4	6,35	6,0
220608 PEFRA	❑	❑	24	21,8	1,2	0,8	6,35	6,0
220612 PEFRA	❑	❑	24	21,8	0,8	1,2	6,35	6,0
220616 PEFRA	❑	❑	24	21,8	0,4	1,6	6,35	6,0
220620 PEFRA	❑	❑	24	21,8	0,5	2,0	6,35	6,0
220630 PEFRA	❑	❑	23	21,8	0,6	3,0	6,35	6,0
220632 PEFRA	❑	❑	23	21,8	0,4	3,2	6,35	6,0
AECT 220640 PEFRA	❑	❑	22	21,8	1,2	4,0	6,35	6,0
220650 PEFRA	❑	❑	22	21,8	0,4	5,0	6,35	6,0

Spare Parts

Insert Screw		Insert Wrench	Applicable Endmill
	N·m		
BFTX 0509 N	5,0	TRD 20	Ø 25 – Ø 32
BFTX 0511 N		TRD 20	Ø 40 – Ø 125

Indexable Endmills

☞ G59

WMM Type

Features

Utilising some of the design features, which made the Wave-Mill so successful, this multi-functional cutter, which utilizes standard wavy shaped inserts mounted radially and axially, performs a variety of operations.
These include slotting, shoulder milling, ramping, pocketing, drilling, helical cutting etc and eliminates the need to stock a variety of application specific tools.

Advantages

- Multi-functional cutter efficiently performs a number of cutting operations.
- Excellent for ramping, helical cutting, and pocketing.
- Uses standard inserts interchangeable with those used on other Wave-Mill cutters
- Strong high rake inserts gives smooth cutting action.
- Good dimensional stability thanks to long life inserts

● Insert Orientation of WMM Type Cutter



Multi-purpose Applications

● Shoulder Cutting	● Slotting	● Ramping (Slant Milling)
DIN X5CrNi810 Cutting of stainless steel tool 	GG25 Deep grooving can be performed easily. Easy chip removal 	C50 Capable of tapered recess cutting of a prepared hole 
Tool Dia. : 25 mm Insert : APMT103504PDER (Grade : ACZ350) v_c = 200 m/min, f_t = 0,1 mm/tooth Axial a_p: 15 mm, Radial a_e: 25 mm, Air blow	Tool Dia. : 25 mm Insert : APMT 103504PDER (Grade : ACZ310) v_c = 180 m/min, f_t =0,12 mm/tooth Axial a_p: 15 mm, R adial a_e: 25 mm, Air blow	Tool Dia. : 25 mm Insert : APMT103504PDER (Grade : ACZ310) v_c = 180 m/min, f_t = 0,12 mm/tooth Axial a_p: 15 mm, Radial a_e: 25 mm, Air blow
● Pocketing	**● Drilling**	**● Helical Cutting**
C50 Capable of pocketing with continuous lateral feed from initial drilling or taper cutting process 	C50 Capable of easy chip removal and drilling without tool damage 	C50 Capable of large boring in diameter of 1,2–1,8 times the cutter diameter without prepared hole 
Tool Dia. : 25 mm Insert : APMT103504PDER (Grade : ACZ350) v_c = 200 m/min, f_t = 0.1 mm/tooth Axial a_p : 15 mm, Radial a_e : 2 5mm Air blow	Tool Dia. : 25 mm Insert : APMT103504PDER (Grade : ACZ350) Bore size : 25 mm, Depth : d=15 mm v_c = 200 m/min, f = 0.1 mm/rev Step feed : 0,5 mm, Air blow	Tool Dia. : 25 mm Insert : APMT103504PDER (Grade : ACZ350) Bore size : 40 mm, Depth : d=30 mm v_c = 300 m/min, f = 0.1 mm/rev Axial feed : t = 15 mm/pitch, Air blow

Recommended Cutting Conditions for WMM(H)2000

øD (mm) \ Material			Carbon steel (ex. C50)	Stainless steel (ex. 10CrNiS189)	Cast iron (ex. GG20)	Aluminium alloy
20 ~ 26	v_c	—	80-**120**-160	80-**100**-120	70-**150**-180	200-**300**-500
	f_t	Shoulder milling	0,05-0,20	0,05-0,15	0,05-0,20	0,1-0,15-0,2
		Slotting	0,05-0,12	0,05-0,10	0,05-0,12	0,05-0,10
		Drilling	0,05-0,18	0,05-0,12	0,05-0,18	0,05-0,10
Grade			ACZ330	ACZ350	ACZ310	DL1000 (H1)

[v_c =m/min, f_t =mm/tooth] [min.– optimum – max.]

Recommended Cutting Conditions for WMM(H)3000

øD (mm) \ Material			Carbon steel (ex. C50)	Stainless steel (ex. 10CrNiS189)	Cast iron (ex. GG20)	Aluminium alloy
32 ~ 40	v_c	—	80-**120**-160	80-**100**-120	70-**150**-180	200-**300**-500
	f_t	Shoulder milling	0,05-0,25	0,05-0,20	0,05-0,25	0,1-0,15-0,2
		Slotting	0,05-0,15	0,05-0,12	0,05-0,15	0,05-0,10
		Drilling	0,05-0,20	0,05-0,18	0,05-0,20	0,05-0,10
Grade			ACZ330	ACZ350	ACZ310	DL1000 (H1)

[v_c =m/min, f_t =mm/tooth] [min.– optimum – max.]

▲ = To be replaced by new item

Recommended Tightening Torque (N·m)

"Wave Mill" Series
WMM (H) 2000 E/EL EW/ELW Type



Body

Cat. No.	Stock	Dimensions (mm)						Total teeth	Effective teeth
		DC	DMM	APMX	LF	LH	LS		
WMM 2020 E	▲	20	20	17	130	35	95	3	1
WMM 2025 E	▲	25	25	26	140	40	100	4	1
(Long type)									
WMM 2020 EL	▲	20	20	17	185	60	125	3	1
WMM 2025 EL	▲	25	25	26	220	75	145	4	1
(Weldon shank type)									
WMM 2020 EW	▲	20	20	17	130	35	95	3	1
WMM 2025 EW	▲	25	25	26	140	40	100	4	1
(Long type with weldon shank)									
WMM 2020 ELW	▲	20	20	17	185	60	125	3	1
WMM 2025 ELW	▲	25	25	26	220	75	145	4	1
(**WMMH** Standard type with coolant holes and weldon shank)									
WMMH 2020 EW	▲	20	20	17	130	35	95	3	1
WMMH 2025 EW	▲	25	25	26	140	40	100	4	1
(**WMMH** Long type with coolant holes and weldon shank)									
WMMH 2020 ELW	▲	20	20	17	185	60	125	3	1
WMMH 2025 ELW	▲	25	25	26	220	75	145	4	1

Inserts for WMM 2000 Series



Application	Coated			Diamond coated	Un-coated
High Speed / Light cut				K N	N
General Purpose	M	P	K		N
Roughing					

Cat. No.	ACZ350	ACZ330	ACZ310	DL1000	H1	Radius RE
APMT 103504 PDER	▲	▲	▲	–	–	0,4
103508 PDER	▲	▲	▲	–	–	0,8
103512 PDER	▲	▲		–	–	1,2
APMT 103504 PDER-H	▲	▲	▲	–	–	0,4
103508 PDER-H	▲	▲	▲	–	–	0,8
103512 PDER-H	▲	▲	▲	–	–	1,2
APET 103504 PDER-F	▲	▲	▲	–	–	0,4
APET 103504 PDFR-S	–	–	–	▲	▲	0,4

PDER-H : Stronger cutting edge
PDER-F : Ground insert for finishing
PDFR-S : Round honed sharp cutting edge for aluminium

Spare Parts

Screw		Wrench
	N·m	
BFTX 02506 N	1,5	TRD 08

"Wave Mill" Series
WMM (H) 3000 E/EL EW/ELW Type



Body

Cat. No.	Stock	Dimensions (mm)						Total teeth	Effective teeth
		DC	DMM	APMX	LF	LH	LS		
WMM 3032 E	▲	32	32	39	150	50	100	4	1
WMM 3040 E	▲	40	32	39	160	55	105	4	1
(Long type)									
WMM 3032 EL	▲	32	32	39	230	90	140	4	1
WMM 3040 EL	▲	40	32	39	230	55	185	4	1
(Weldon shank type)									
WMM 3032 EW	▲	32	32	39	150	50	100	4	1
WMM 3040 EW	▲	40	32	39	160	55	105	4	1
(Long type with weldon shank)									
WMM 3032 ELW	▲	32	32	39	230	90	140	4	1
WMM 3040 ELW	▲	40	32	39	230	55	185	4	1
(**WMMH** Standard type with coolant holes and weldon shank)									
WMMH 3032 EW	▲	32	32	39	150	50	100	4	1
WMMH 3040 EW	▲	40	32	39	160	55	105	4	1
(**WMMH** Long type with coolant holes and weldon shank)									
WMMH 3032 ELW	▲	32	32	39	230	90	140	4	1
WMMH 3040 ELW	▲	40	32	39	230	55	185	4	1

Inserts for WMM 3000 Series



Application	Coated			Diamond coated	Un-coated
High Speed / Light cut				K N	N
General Purpose	M	P	K		N
Roughing					

Cat. No.	ACZ350	ACZ330	ACZ310	DL1000	H1	Radius RE
APMT 160508 PDER	▲	▲	▲	–	–	0,8
160512 PDER		▲		–	–	1,2
160516 PDER	▲	▲	▲	–	–	1,6
APMT 160508 PDER-H	▲	▲	▲	–	–	0,8
160512 PDER-H	▲	▲	▲	–	–	1,2
160516 PDER-H	▲	▲		–	–	1,6
APMT 160520 PDER-H	▲	▲	▲	–	–	2,0
160530 PDER-H	▲	▲	▲	–	–	3,0
160540 PDER-H	▲			–	–	4,0
160550 PDER-H	▲			–	–	5,0
160560 PDER-H	▲	▲	▲	–	–	6,0
APET 160508 PDER-F	▲	▲	▲	–	–	0,8
APET 160504 PDFR-S	–	–	–	▲	▲	0,4
160508 PDFR-S	–	–	–	▲	▲	0,8

Spare Parts

Screw		Wrench
	N·m	
BFTX 03584	3,0	TRD 15

● APET--- S, uncoated grade "H1" for Aluminium

WRX Type

General Features

The WRX Wave repeater end mill system features AXMT style inserts vertically mounted and positioned to provide a long continuous cutting edge suitable for deep shoulder milling. Designed to run at elevated feed rates the soft cutting action reduces cutting resistance, vibration and noise to substantially improve tool life and surface finish.

Available with our new generation Super FF and Super ZX coated inserts for unbeatable performance.

Product Range

- WRX 2000 series with 12 mm inserts
- WRX 3000 series with 17 mm inserts
- Cutter Diameters - 20 mm (a_p = 18 mm) to 100 mm (a_p = 53 mm)
- Special Order Options – WRX Cutter with integrated arbor
  Shell type with detachable head
- Wide ISO Application Range – P/M/K/N classification

Advantages

- Optimised insert positions reduce cutting resistance and vibration
- Integral coolant improves chip flow
- Primary chip slot for smooth and fast chip evacuation
- Optimised insert pocket maximises rigidity
- Bottom edge support improves tool life and cutting performance



Cutting Resistance Comparison



Work Material: C50
Tool: WRX2025RH27E25
Cutting Conditions: v_c = 100 m/min, f_t = 0,15 mm/tooth
a_p = 25 mm, a_e = 10 mm, Dry

Vibration Comparison



Work Material: C50
Tool: WRX3080RH53F32
Cutting Conditions: v_c = 150 m/min, f_t = 0,15 mm/tooth
a_p = 25 mm, a_e = 10 mm, Dry

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item
Recommended Tightening Torque (N·m)

WRX 2000 Series with AXMT 12 mm inserts



Body (Cylindrical Shank Type)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	No. of rows	Effective teeth
		DC	APMX	DMM	LF	LH	LS			
WRX2020RH18E20	●	20	18	20	120	40	80	4	2	2
WRX2020RH36E20	❑	20	36	20	130	45	85	4	4	1
WRX2025RH18E25	●	25	18	25	130	45	85	6	2	3
WRX2025RH27E25	●	25	27	25	130	45	85	6	3	2
WRX2032RH18E32	●	32	18	32	140	50	90	8	2	4
WRX2032RH27E32	●	32	27	32	130	45	85	9	3	3
WRX2040RH18E40	❑	40	18	40	160	40	120	10	2	5
WRX2040RH36E40	●	40	36	40	130	45	85	16	4	4

Body (Weldon Shank Type)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	No. of rows	Effective teeth
		DC	APMX	DMM	LF	LH	LS			
WRX2020RH18W20	●	20	18	20	120	40	80	4	2	2
WRX2020RH36W20	❑	20	36	20	130	45	85	4	4	1
WRX2025RH18W25	●	25	18	25	130	45	85	6	2	3
WRX2025RH27W25	●	25	27	25	130	45	85	6	3	2
WRX2032RH18W32	●	32	18	32	140	50	90	8	2	4
WRX2032RH27W32	●	32	27	32	130	45	85	9	3	3
WRX2040RH18W40	❑	40	18	40	160	40	120	10	2	5
WRX2040RH36W40	●	40	36	40	130	45	85	16	4	4

Inserts (Same as for Wavemill WEX 2000 Type)



Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		MS		KN	N	
General Purpose		P		K		MS	MS		N	
Roughing		P	P		K		MS			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 123504 PEER-G	●	●	●	●	●			–	–	0,4
123508 PEER-G	●	●	●	●	●			–	–	0,8
123512 PEER-G	●	●	●	●	●			–	–	1,2
AXMT 123504 PEER-H	●	●	●	●	●			–	–	0,4
123508 PEER-H	●	●	●	●	●			–	–	0,8
123512 PEER-H	●	●	●	❍	●			–	–	1,2
AXMT 123504 PEER-E						●	●	–	–	0,4
123508 PEER-E			▲			●	●	–	–	0,8
123512 PEER-E						●	●	–	–	1,2
AXMT 123508 PEER-EH			▲			●	●	–	–	0,8
AXET 123502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
123504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
123508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

– Unable to produce

G - General type
H - Strong cutting edge
E - For stainless steel / exotic alloy
EH - Strong edge for stainless steel / exotic alloy
S - For aluminium alloy

Spare Parts (WRX 2000)

Screw	Wrench
 2,0 Nm	
BFTX 0306 IP	TRDR 08 IP

Identification Details

WRX 20 25 R H 27 W 25

- 20 — Insert Size
- 25 — Tool øD
- R — Cutting Direction
- H — Inner coolant
- 27 — Cutting Edge Lengh
- W — Arbor Type
  - **E** - Straight Shank
  - **W** - Weldon Shank
  - **F** - Shell Type
- 25 — Arbor Diameter

Application Examples

Example

Work Material	Construction Machine Parts (USt.42-2)		
		Sumitomo	Competitor
Tool	Body	WRX2000 Weldon shank	Ø 38,1
	Insert	AXMT	18 mm
	Insert grade	ACP200	PVD Type
	Tool dia. (mm)	38,1	38,1
	Total teeth	24	16
	Effective teeth	4	4
Cutting Data	Cutting speed (m/min)	180	137
	Feed (mm/t)	0,09	0,1
	Axial depth of cut (mm)	38,1	38,1
	Radial width of cut (mm)	3,2	3,2
	Coolant	Wet	Wet
Result	Tool life / Cutting edge	60	40
Benefits	1,5 times longer tool life 30 % increased productivity		

G49

WRX 3000 Series with AXMT 17 mm inserts



Body (Cylindrical Shank Type)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	No. of rows	Effective teeth
		DC	APMX	DMM	LF	LH	LS			
WRX3032RH40E32	●	32	40	32	150	65	85	6	3	2
WRX3040RH27E40	❑	40	27	40	180	60	120	6	2	3
WRX3040RH40E40	●	40	40	40	150	65	85	9	3	3
WRX3050RH27E40	❑	50	27	40	180	60	120	8	2	4
WRX3050RH53E40	●	50	53	40	165	75	90	12	4	3

Body (Weldon Shank Type)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	No. of rows	Effective teeth
		DC	APMX	DMM	LF	LH	LS			
WRX3040RH27W40	❑	40	27	40	180	60	120	6	2	3
WRX3040RH40W40	●	40	40	40	150	65	85	9	3	3
WRX3050RH27W40	❑	50	27	40	180	60	120	8	2	4
WRX3050RH53W40	●	50	53	40	165	75	90	12	4	3

Spare Parts (WRX 3000)

Screw	Wrench
 3,0	
BFTX 0409 IP	TRDR 15 IP

Inserts (Same as for Wavemill WEX 3000 Type)



Application	Coated Carbide							Carbide	DLC	
High Speed / Light cut	P			K		MS		KN	N	
General Purpose		P		K		MS	MS		N	
Roughing		P	P		K		MS			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius RE
AXMT 170508 PEER-L	●	●	●	❍	●			–	–	0,8
AXMT 170504 PEER-G	❍	●	●	●	●			–	–	0,4
170508 PEER-G	●	●	●	●	●			–	–	0,8
170512 PEER-G	❍	●	●	❍	●			–	–	1,2
170516 PEER-G	❍	●	●	❍	●			–	–	1,6
170520 PEER-G*	❍	●	●	●	●			–	–	2,0
170530 PEER-G*	●	●	●	●	●			–	–	3,0
AXMT 170508 PEER-H	●	●	●	●	●			–	–	0,8
170512 PEER-H	●	●	●	●	●			–	–	1,2
AXMT 170504 PEER-E						●	●	–	–	0,4
170508 PEER-E			▲			●	●	–	–	0,8
170512 PEER-E						●	●	–	–	1,2
170516 PEER-E						❍	●	–	–	1,6
170520 PEER-E*						❍	●	–	–	2,0
170530 PEER-E*						●	●	–	–	3,0
AXMT 170508 PEER-EH			▲			●	●	–	–	0,8
AXET 170502 PEFR-S	–	–	–	–	–	–	–	●	●	0,2
170504 PEFR-S	–	–	–	–	–	–	–	●	●	0,4
170508 PEFR-S	–	–	–	–	–	–	–	●	●	0,8

– Unable to produce

L – Low cutting force
G – General type
H – Strong cutting edge
E – For stainless steel
EH– Strong edge for stainless steel
S – For aluminium
* Cutter body modification is required.

Application Examples

Example 1

Work Material	Automotive Component / Cast Iron		
Tool	Body	Sumitomo	Competitor
		WRX3000 Type Integrated Arbor	Ø 50
	Insert	AXMT	18 mm
	Insert grade	ACK300	PVD Type
	Tool dia. (mm)	50	50
	Total teeth	15	12
	Effective teeth	3	3
Cutting Data	Cutting speed (m/min)	78	78
	Feed (mm/t)	0,13	0,13
	Axial depth of cut (mm)	45	45
	Radial width of cut (mm)	5	5
	Coolant	Dry	Dry
Result	Tool life / Cutting edge	500 min	300 min
Benefits	1,7 times longer tool life		

Example 2

Work Material	Machine Parts / Stainless Steel		
Tool	Body	Sumitomo	Competitor
		WRX3040RH40E40	Ø 40
	Insert	AXMT	18 mm
	Insert grade	ACP300	PVD Type
	Tool dia. (mm)	40	40
	Total teeth	9	6
	Effective teeth	3	2
Cutting Data	Cutting speed (m/min)	125	125
	Feed (mm/t)	0,2	0,2
	Axial depth of cut (mm)	40	40
	Radial width of cut (mm)	5	5
	Coolant	Wet	Wet
Result	Tool life / Cutting edge	20	5 ~ 10
Benefits	Stable machining, double tool life with no breakage		

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item

☞ G49

Recommended Tightening Torque (N·m)

Chipbreaker Selection

Work Material	Steel, Cast Iron			Stainless Steel		Aluminium
Chipbreaker Type	L	G	H	E	EH	S
						
Feature	Low cutting force	General purpose	Strong cutting edge	E type for smooth cutting	Strong cutting edge	Sharp cutting edge
2000 Type Figure	–					
3000 Type Figure						
Application	Light cut, low rigidity milling and less burrs	General to Interrupted milling	Roughing, heavy interrupted and hardened steel milling	Light cutting to general purpose	Heavy interrupted machining	Aluminium alloy and non-ferrous metal

Ramping (Slant Milling)

Tool Diameter	Max. Ramping Angle	
	WRX 2000 Typ	WRX 3000 Typ
20	4°	
25	2°	
32	1°30'	
40	1°	2°
50	0°30'	1°
63		0°30'
80		0°30'
100		Not possible

Recommended Cutting Conditions

Tool: WRX 3050 RH53 F22, DC = 50 mm, a_p = 50 mm

ISO	Work Material	Property, Condition	Hardness (HB)	Grades (optimum grade in bold letters)			Chip Breaker	Recommended cutting speed and feed / tooth according to width of cut (a_e /DC) - must be adjusted to actual machine and workpiece conditions.					
								10%		25%		>50%	
								v_c	f_t	v_c	f_t	v_c	f_t
								min. **Optimum** max.	min. **Optimum** max.	min. **Optimum** max.	min. **Optimum** max.	min. **Optimum** max.	min. **Optimum** max.
P	Steel, carbon steel	< 0,15% C, annealed	125	ACP 100	**ACP 200**	ACP 300	L - **G**	170 – **215** – 240	0,21 – **0,28** – 0,35	160 – **195** – 220	0,16 – **0,21** – 0,26	130 – **160** – 180	0,08 – **0,10** – 0,13
		< 0,45% C, annealed	190	ACP 100	**ACP 200**	ACP 300	L - **G**	160 – **195** – 220	0,21 – **0,28** – 0,35	140 – **175** – 190	0,16 – **0,21** – 0,26	110 – **140** – 160	0,08 – **0,10** – 0,13
		< 0,45% C, tempered	250	ACP 100	**ACP 200**	ACP 300	L - **G** - H	140 – **180** – 200	0,19 – **0,26** – 0,32	130 – **165** – 180	0,14 – **0,19** – 0,24	100 – **130** – 140	0,08 – **0,10** – 0,13
		< 0,75% C, annealed	270	ACP 100	**ACP 200**	ACP 300	L - **G** - H	140 – **170** – 190	0,19 – **0,26** – 0,32	120 – **155** – 170	0,14 – **0,19** – 0,24	100 – **130** – 140	0,07 – **0,10** – 0,12
		< 0,75% C, tempered	300	ACP 100	**ACP 200**	ACP 300	L - **G** - H	130 – **165** – 180	0,19 – **0,26** – 0,32	120 – **150** – 170	0,14 – **0,19** – 0,24	100 – **120** – 130	0,07 – **0,10** – 0,12
	Low alloyed steel	annealed	180	ACP 100	**ACP 200**	ACP 300	**G** - H	130 – **165** – 180	0,18 – **0,24** – 0,30	120 – **150** – 170	0,13 – **0,18** – 0,22	100 – **120** – 130	0,07 – **0,09** – 0,11
		tempered	275	ACP 100	**ACP 200**	ACP 300	**G** - H	130 – **160** – 180	0,17 – **0,23** – 0,28	120 – **145** – 160	0,12 – **0,16** – 0,20	100 – **120** – 130	0,07 – **0,09** – 0,11
		tempered	300	ACP 100	**ACP 200**	ACP 300	**G** - H	110 – **140** – 160	0,16 – **0,22** – 0,27	100 – **130** – 140	0,11 – **0,15** – 0,19	90 – **110** – 120	0,07 – **0,09** – 0,11
		tempered	350	ACP 100	**ACP 200**	ACP 300	**G** - H	100 – **130** – 140	0,16 – **0,21** – 0,26	100 – **120** – 130	0,11 – **0,15** – 0,19	80 – **100** – 110	0,06 – **0,08** – 0,10
	High alloyed and tool steel	annealed	200	**ACP 100**	ACP 200		G - **H**	70 – **85** – 90	0,15 – **0,21** – 0,26	60 – **80** – 90	0,11 – **0,14** – 0,18	60 – **70** – 80	0,06 – **0,08** – 0,10
		tempered	325	**ACP 100**	ACP 200		G - **H**	30 – **35** – 40	0,14 – **0,19** – 0,24	30 – **35** – 40	0,10 – **0,14** – 0,17	20 – **30** – 30	0,06 – **0,08** – 0,10
M	Stainless steel, ferritic/martensitic	annealed	200		ACP 200	**ACP 300**	L - **G** - H	120 – **150** – 170	0,15 – **0,20** – 0,25	110 – **135** – 150	0,11 – **0,14** – 0,18	90 – **110** – 120	0,07 – **0,09** – 0,11
	Stainless, martensitic	tempered	240		ACP 200	**ACP 300**	L - **G** - H	100 – **125** – 140	0,16 – **0,22** – 0,27	90 – **115** – 130	0,12 – **0,16** – 0,20	80 – **100** – 110	0,07 – **0,10** – 0,12
	Stainless, austenitic	plunged	180		ACM 200	**ACM 300**	L - **G**	80 – **95** – 110	0,15 – **0,20** – 0,25	70 – **85** – 90	0,11 – **0,14** – 0,18	60 – **70** – 80	0,06 – **0,08** – 0,10
K	Gray cast iron	GG	180	**ACK 200**	ACK 300		**G** - H	190 – **240** – 270	0,19 – **0,26** – 0,32	180 – **220** – 240	0,14 – **0,19** – 0,24	140 – **170** – 190	0,09 – **0,12** – 0,15
	Nodular cast iron	GGG	250	**ACK 200**	ACK 300		**G** - H	140 – **170** – 190	0,16 – **0,21** – 0,26	120 – **155** – 170	0,12 – **0,16** – 0,20	100 – **130** – 140	0,07 – **0,10** – 0,12
S	Exotic alloys (Resistant alloys, Ti + Ni alloys)	Fe based, annelaed	200	ACK 200	**ACK 300**		L - **G**	40 – **45** – 50	0,12 – **0,16** – 0,21	30 – **40** – 45	0,08 – **0,11** – 0,14	30 – **35** – 40	0,07 – **0,09** – 0,11
		hardened	280	ACK 200	**ACK 300**		L - **G**	15 – **20** – 25	0,10 – **0,14** – 0,17	10 – **15** – 20	0,07 – **0,10** – 0,12	10 – **15** – 20	0,05 – **0,07** – 0,09
N	Aluminum alloy	Si < 13%			**DL 1000**	H1	**S**	510 – **635** – 710	0,23 – **0,31** – 0,38	460 – **580** – 640	0,17 – **0,22** – 0,28	390 – **485** – 540	0,08 – **0,12** – 0,14
		Si ≥ 13%			**DL 1000**	H1	**S**	150 – **190** – 210	0,19 – **0,25** – 0,32	140 – **175** – 190	0,14 – **0,18** – 0,23	130 – **165** – 180	0,08 – **0,10** – 0,13
	Copper alloy				**DL 1000**	H1	**S**	320 – **405** – 450	0,15 – **0,21** – 0,26	300 – **370** – 410	0,13 – **0,16** – 0,22	240 – **300** – 330	0,07 – **0,10** – 0,12

- Dry machining is recommended (air cooling) - if lubricant is used, we recommend CVD coated grades (ACP100 / ACK200) or tough PVD grades (ACP300 / ACK300).
- Insert geometry: L type for low cutting forces, thinly coated components. G type for general application, H type offers high cutting edge stability for rough and heavy cutting conditions.

WBMR Type

Features

Particularly suitable for die mold machining the WBMR replaceable insert ball nose endmill efficiently roughs complex profiles.

Its high feed rate capability is a direct result of a sharp cutting edge which is maintained during the cutting cycle by the special cemented carbide substrate working in parallel with the ultra hard ZX coating.

Advantages

- Wave shaped cutting edge
- Economical M class insert
- Precise clamping
- High feed rate capability



Chipbreaker
(Nick type)
for r = 25
radial insert

ZNMT 4310250-N

Performance

● Cutting Resistance



Cutting Conditions (Shoulder milling, downcut)
v_c = 200 m/min, f_t = 0.15 mm/tooth
Axial a_p: 5 mm, Radial a_e: 5 mm
Work Material : C50

● Anti-Rotational Mechanism



Circumferential movement of the insert caused by cutting forces is controlled by guide faces A, B & C, so as to allow stable cutting.

● Insert Life



Cutting Conditions (Shoulder milling, downcut)
v_c = 100 m/min, f_t = 0.15 mm/tooth
Axial a_p: 5mm, Radial a_e: 5 mm
Work Material : X 40 CrMoV 5-1(HRC45)

Application Example

● Cold Molding Die

Work Material :
X 155 CrVMo 12 1



<Results>
Flank wear after continuous cutting for seven hours was less than other manufacturer's product.
Stable cutting was observed.

WBMR 2200S (ø 20 mm)
Insert Grade : ACZ350

Cutting Conditions :
n = 2200 rpm, v_f = 500 mm/min
Depth of Cut : 0,3–2 mm
Non-water soluble cutting oil

● Injection Molded Part

(Cr-Mo steel + Stellite-overlay)



<Results>
Wave ball (ø30mm) could cut without chattering while other manufacturer's products could not cut at all due to chattering.

WBMR 2300M (ø 30 mm)
Insert Grade : ACZ350

Cutting Conditions :
n = 500 rpm, v_f = 35 mm/min
Depth of Cut : 5 mm
Dry cut

Recommended Cutting Conditions (2 teeth)

Condition		Carbon steel (Below HRC25)	Alloy steel (Below HRC45)	Stainless, Die steel etc.	Cast iron
(A)	v_c	200-**250**-300	100-**150**-200	50-**80**-100	100-**120**-150
	f_t	0,1-**0,2**-0,3	0,1-**0,2**-0,3	0,1-**0,15**-0,2	0,2-**0,3**-0,4



[v_c =m/min, f_t =mm/tooth] [min.– optimum – max.]

Recommended Cutting Conditions (4 teeth)

Condition		Carbon steel (Below HRC25)	Alloy steel (Below HRC45)	Stainless, Die steel etc.	Cast iron
(A)	v_c	200-**250**-300	100-**150**-200	50-**80**-100	100-**120**-150
	f_t	0,1-**0,2**-0,3	0,1-**0,2**-0,3	0,1-**0,15**-0,2	0,2-**0,3**-0,4
(B)	v_c	160-**200**-240	80-**120**-160	40-**60**-80	80-**100**-120
	f_t	0,1-**0,2**-0,3	0,1-**0,2**-0,3	0,1-**0,15**-0,2	0,2-**0,3**-0,4



[v_c =m/min, f_t =mm/tooth] [min.– optimum – max.]

● = Euro stock
○ = Japan stock

❑ = Delivery on request

Recommended Tightening Torque (N·m)

Wave Ball Mill" for Roughing
WBMR 2000 Type

Rake Angle		
	Radial	–
	Axial	-10°

20–47mm



Body (Short and middle length type, 2 teeth)

Cat. No.	Stock	Dimensions (mm)						
		DC	DMM	APMX	LH	LS	LU	LF
WBMR 2200 S	●	20	25	20	60	80	40	140
2200 M	●	20	25	20	60	140	40	200
2200 MW	●	20	25	20	60	140	40	200
WBMR 2250 S	●	25	32	23	70	80	50	150
2250 M	●	25	32	23	73	147	50	220
2250 MW	●	25	32	23	73	147	50	220
WBMR 2320 S	●	32	32	31	80	80	60	160
2320 M	●	32	32	31	85	155	60	240
2320 MW	●	32	32	31	85	155	60	240
WBMR 2400 S	❑	40	42	35	100	100	-	200
2400 M	❑	40	42	35	180	100	-	280
WBMR 2500 S	❑	50	42	47	100	100	-	200
2500 M	❑	50	42	47	180	100	-	280

S: **S**hort type with cylindrical shank
M: **M**iddle length type with cylindrical shank

MW: **M**iddle length type with Weldon shank

Wave Ball Mill" for Roughing
WBMR 2000 L Type

Rake Angle		
	Radial	–
	Axial	-10°

30–69mm



Body (Extra long type, 4 teeth)

Cat. No.	Stock	Dimensions (mm)						
		DC	DMM	APMX	LH	LS	LU	LF
WBMR 2200 LL	●	20	25	30	80	170	40	250
2200 LLW	●	20	25	30	80	170	40	250
WBMR 2250 LL	●	25	32	38	100	200	50	300
2250 LLW	●	25	32	38	100	200	50	300
WBMR 2320 LL	●	32	32	44	120	230	60	350
2320 LLW	●	32	32	44	120	230	60	350
WBMR 2400 LL	❑	40	42	50	250	100	-	350
2400 LLW		40	42	50	250	100	-	350
WBMR 2500 LL	❑	50	42	69	250	100	-	350
2500 LLW		50	42	69	250	100	-	350

LL: Extra long type with cylindrical shank

LLW: Extra long type with Weldon shank

Inserts

Application	Coated Carbide		
High Speed / Light cut			
General Purpose	PM	PM	
Roughing	PM	PM	K

Cat. No.	ACP200	ACP300	ACK300	Dimensions (mm) L	W1	S	RE	Fig.	No. of teeth	Applicable Endmill
ZNMT 1804100-C	●	●	●	18,00	9,76	4,76	10,0	1	1	WBMR 2200
2004100-S	●	●	●	20,00	7,50	4,37	10,0	2	1	
SPMT 070308	❍	❍		7,94	-	3,18	-	3	2	
ZNMT 2205125-C	●	●	●	22,50	12,20	5,70	12,5	1	1	WBMR 2250
2305125-S	●	●	●	23,00	9,38	5,56	12,5	2	1	
SPMT 09T308	●	●	●	9,53	-	3,97	-	3	2	
ZNMT 2907160-C	●	●	●	29,00	15,62	7,15	16,0	1	1	WBMR 2320
3006160-S	●	●	●	30,00	12,00	6,70	16,0	2	1	
SPMT 09T308	●	●	●	9,53	-	3,97	-	3	2	
ZNMT 3608200	❍	❍	❍	36,00	19,50	6,70	20,0	4	2	WBMR 2400
SPMT 09T308	●	●	●	9,53	-	3,97	-	3	2	
ZNMT 4310250	❍		❍	43,00	25,70	10,15	25	4	2	WBMR 2500
4310250-N	❍		❍	43,00	25,70	10,15	25	5	2	
SPMT 120408	❍	❍	❍	12,7	-	4,76	-	3	2	

Fig. 1



Fig. 2



Fig. 3

Fig. 4



Fig. 5



Spare Parts

Screw		Wrench	Wrench	Applicable Endmill
	(N·m)			
BFTX 0307N	2,0	TRX10	–	WBMR 2200, WBMR 2200 LL
BFTX 0409N	3,4	–	TRD15	WBMR 2250, WBMR 2250LL
BFTX 0511N	5,0	–	TRD20	WBMR 2320, WBMR 2320LL
BFTX 0407N	3,0	–	TRD15	WBMR 2320LL
BFTX0619N	7,5	–	TRD25	WBMR 2400, WBMR 2500, WBMR 2400LL, WBMR 2500LL
BFTX 0409N	3,4	–	TRD15	WBMR 2500LL

Wave Ball Mill for Finishing
WBMF Type

Features

The outstanding results obtained from this finishing cutter are due to the combination of its large sigmoid blade and precise clamping system making it extremely rigid !

The WBMF achieves an excellent machined finish greatly reducing hand finishing and polishing operations.

Advantages

- Unique rigid clamping system
- Large sigmoid blade
- Smooth cutting action
- High quality machined surface
- Ultra hard ZX coated cutting edge



Application Example

● Bumper Moulding Die

Work Material :
C55



<Results>
Surface roughness after continuous cutting for twelve hours was better than other manufacturer's product.
Less width of flank wear was observed.

WBMF1200M (ø20mm) Insert : ZPGU2471100 Grade : ACZ120	Cutting Conditions v_c = 88 m/min v_f = 700 mm/min (f_t = 0,25 mm/tooth) Width of Cut : 0,5 mm Depth of Cut : 0,5 mm Dry

● Bumper Moulding Die

Work Material :
C50



<Results>
Smooth cutting and good surface finish after continuous cutting for eight hours

WBMF1200M (ø20mm) Insert : ZPGU2471100 Grade : ACZ120	Cutting Conditions v_c = 190 m/min v_f = 1200 mm/min (f_t = 0,21 mm/tooth) Width of Cut : 0,2 mm Depth of Cut : 0,2 mm Dry

● = Euro stock
❑ = Delivery on request

Recommended Tightening Torque (N·m)

Rake Angle		
	Radial	–
	Axial	0°



Body

Cat. No.		Stock	Dimensions (mm)						
			DC	DMM	APMX	LH	LS	LU	LF
WBMF	1100 S	❑	10	16	9	30	70	17	100
	1100 M	●	10	16	9	35	95	17	130
	1100 L	❑	10	16	9	50	130	17	180
WBMF	1120 S	❑	12	16	10,5	40	70	19,5	110
	1120 M	●	12	16	10,5	40	110	19,5	150
	1120 MM12N		12	12	10,5	40	110	19,5	150
	1120 L	❑	12	16	10,5	60	140	19,5	200
WBMF	1160 S	❑	16	20	12	50	80	25,5	130
	1160 M	●	16	20	12	50	130	25,5	180
	1160 MM12N		16	16	12	50	130	25,5	180
	1160 L	❑	16	20	12	70	150	25,5	220
WBMF	1200 S	❑	20	25	15	60	80	32	140
	1200 M	●	20	25	15	60	140	32	200
	1200 MM20N		20	20	15	60	140	32	200
	1200 L	❑	20	25	15	80	170	32	250
WBMF	1250 S		25	32	18,5	70	80	36	150
	1250 M	●	25	32	18,5	73	147	36	220
	1250 L	❑	25	32	18,5	100	200	36	300
WBMF	1300 S		30	32	22,5	80	80	43	160
	1300 M	●	30	32	22,5	85	155	43	240
	1300 L		30	32	22,5	120	230	43	350

S : **S**hort type
M : **M**iddle length type
L : **L**ong type

Inserts

Application	Coated
High Speed / Light cut	P
General Purpose	
Roughing	



Cat. No.	ACZ120	Dimensions (mm)					Applicable Endmill
		DC	L	APMX	S	RE	
ZPGU 1551050	●	10	15,6	9	5,1	5,0	WBMF1100
ZPGU 1856060	●	12	18	10,5	5,6	6,0	WBMF1120
ZPGU 2061080	●	16	20,5	12	6,1	8,0	WBMF1160
ZPGU 2471100	●	20	24,5	15	7,1	10,0	WBMF1200
ZPGU 2876125	●	25	28,5	18,5	7,6	12,5	WBMF1250
ZPGU 3486150	●	30	34,4	22,5	8,6	15,0	WBMF1300

Spare Parts

Screw		Wrench	Applicable Endmill
BFTG0408F	3,4	TRD15	WBMF1100
BFTG0409F	3,4	TRD15	WBMF1120
BFTG0513F	5,0	TRD20	WBMF1160
BFTG0617F	7,5	TRD25	WBMF1200
BFTG0621F	7,5	TRD25	WBMF1250
BFTG0825F	7,5	TRD25	WBMF1300

Recommended Cutting Conditions

Material / Condition		Carbon steel (Below HRC25)	Alloy steel (Below HRC45)	Stainless, Die steel etc.	Cast iron
øD 10~30	v_c	200–**250**–300	100–**150**–200	50–**80**–100	100–**120**–150
	f_t	0,1–**0,2**–0,3	0,1–**0,2**–0,3	0,1–**0,15**–0,2	0,2–**0,3**–0,4

Wave Radius Mill
WRCX 08000/10000 E Type

Shank Type with Small Diameter Inserts

4,0 mm (WRCX 08000) 5,0 mm (WRCX 10000)

E_ : Cylindrical straight shank type

ES : **S**hort type with straight shank
EM : **M**iddle length type with straight shank
EL : **L**ong type with straight shank



Axial rake angle: – 3°
Radial rake angle: 0 – 35°

■ Body

■ Spare Parts

Cat. No.	Stock	Dimensions (mm) DCX	DMM	DN	APMX	LF	LH	LS	No. of teeth	Axial Rake	Radial Rake	Helical Boring øB Standard	Plunging α max.	Spare Parts	N·m	
WRCX 08012 ES	●	12	12	9,4	4	110	40	70	1	-3°	-35°	-	0°30'	BFTX 02505 IP	1,5	TRDR 08 IP
08012 EM	●	12	12	9,4	4	150	70	80	1							
WRCX 08016 ES	●	16	16	14	4	120	50	70	1	-3°	-10°	24^{+7}_{-4}	5°30'	BFTX 02506 IP	1,5	TRDR 08 IP
08016 EM	●	16	16	14	4	150	70	80	1							
WRCX 08020 ES	●	20	20	18	4	130	50	80	2	-3°	-3°	$32^{\pm7}$	13°			
08020 EM	●	20	20	18	4	180	100	80	2							
08020 EL	●	20	20	18	4	250	130	120	2							
WRCX 08025 ES	●	25	25	21	4	130	50	80	3	-3°	0°	$42^{\pm7}$	8°20'			
08025 EM	●	25	25	21	4	180	100	80	3							
08025 EL	●	25	25	21	4	250	130	120	3							
WRCX 10025 ES	●	25	25	21	5	130	50	80	2	-3°	0°	$40^{\pm8}$	13°10'	BFTX 03584 IP	3,0	TRDR 15 IP
10025 EM	●	25	25	21	5	180	100	80	2							
10025 EL	●	25	25	21	5	250	130	120	2							
WRCX 10032 ES	●	32	32	28	5	130	50	80	3	-3°	0°	$54^{\pm8}$	8°			
10032 EM	●	32	32	28	5	200	120	80	3							
10032 EL	●	32	32	28	5	300	180	120	3							

■ Inserts

Application	Coated Carbide					Uncoated Carbide	Diamond Coated
High Speed / Light cut	P			K		K N	N
General Purpose		P M	P M	K			N
Roughing		P M	P M		K		

Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	H1	DL1000	Dimensions (mm) IC	RE	S	Fig.	Applicable Endmill
QPMT 080330 PPEN	●	●	●	●	●			8	3,0	3,18	1	WRCX 08000 E
080330 PPEN-H	●	●	●	●	●			8	3,0	3,18	1	
QPMT 10T335 PPEN	●	●	●	●	●			10	3,5	3,97	1	WRCX 10000 E
10T335 PPEN-H	●	●	●	●	●			10	3,5	3,97	1	
QPET 10T350 PPFR-S						●	●	10	5,0	3,97	2	

Fig. 1



Fig. 2



QPMT... : Standard 16 cornered polygon type
QPMT...-H: Stronger cutting edge type

QPET...-S: Polished round insert for non-ferrous material

■ Recommended Cutting Conditions

[v_c = m/min, f_t = mm/tooth] [min.– **optimum** – max.]

Material / Grade / øD (mm)		Carbon steel (ex. C40 ~ C50)	Alloy steel (Below HRC40)	Stainless steel (ex. X10CrNiS18-9)	Cast iron (ex. GG20)	Non-ferrous material
		ACP100, ACP200	ACP100, ACP200	ACP200, ACP300	ACK200, ACK300	DL1000, H1
12–32	v_c	80–**120**–160	60–**100**–140	60–**100**–120	60–**80**–120	200–**500**–1000
	f_t	0,1–**0,3**–0,4	0,1–**0,2**–0,3	0,1–**0,15**–0,2	0,1–**0,2**–0,3	0,1–**0,2**–0,3

● = Euro stock
❑ = Delivery on request

☞ G19

Recommended Tightening Torque (N·m)

Exchangeable Head Endmills
WRCX 08000 M Type

4,0 mm (WRCX 08000M)

Modular Type

High efficiency multi purpose endmills



Axial rake angle: 0°
Radial rake angle: -3°

Heads

For insert type : QPMT 0803

Cat. No.	Stock	Dimensions (mm)									No. of teeth
		DCX	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
WRCX 08020M10Z2	●	20	10,5	M10	49	30	5	19	8	15	2
WRCX 08025M12Z3	●	25	12,5	M12	56	35	5	21	10	19	3

Inserts are not included.

Exchangeable Head Endmills
WRCX 10000/12000 M Type

5,0 mm (WRCX 10000M) 6,0 mm (WRCX 12000M)

High efficiency multi purpose endmills



Axial rake angle: 0°
Radial rake angle: -3°

Heads

For insert type : QPOT 10T3

Cat. No.	Stock	Dimensions (mm)									No. of teeth
		DCX	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
WRCX 10025M12Z2	●	25	12,5	M12	56	35	5	21	10	19	2
10028M12Z3		28	12,5	M12	56	35	5	21	10	19	2
WRCX 10030M16Z3		30	17,0	M16	63	40	5	23	10	24	3
10032M16Z3	●	32	17,0	M16	63	40	5	23	10	24	3

Inserts are not included.

Heads

For insert type : QPOT 1204

Cat. No.	Stock	Dimensions (mm)									No. of teeth
		DCX	DCON	CRKS	OAL	LF	LS2	LS	L11	H	
WRCX 12040M16Z4	❑	40	17,0	M16	63	40	5	23	10	24	4

Inserts are not included.

Inserts

Application	Coated Carbide					Uncoated carbide	Diamond Coated
High Speed / Light cut	P			K		K N	N
General Purpose		P M	P M	K			N
Roughing		P M	P M		K		

Cat. No.		ACP100	ACP200	ACP300	ACK200	ACK300	H1	DL1000	Dimensions (mm) IC	RE	S	Fig.	Applicable Endmill
QPMT	080330 PPEN	●	●	●	●	●			8	3,0	3,18	1	WRCX 08000 M
	080330 PPEN-H	●	●	●	●	●			8	3,0	3,18	1	
QPMT	10T335 PPEN	●	●	●	●	●			10	3,5	3,97	1	WRCX 10000 M
	10T335 PPEN-H	●	●	●	●	●			10	3,5	3,97	1	
QPET	10T350 PPFR-S						●	●	10	5,0	3,97	2	
QPMT	120440 PPEN	●	●	●	●	●			12	4,0	4,76	1	WRCX 12000 M
	120440 PPEN-H	●	●	●	●	●			12	4,0	4,76	1	
QPET	120460 PPFR-S						●	●	12	6,0	4,76	2	

Fig. 1



Fig. 2



QPMT... : 16 corner insert for general purpose application
QPMT...-H: 16 corner insert with strong cutting edge

QPET...-S: Round insert with sharp cutting edge for aluminium

Identification Details

WRCX	08	020	M10	Z2
Cutter Type	Insert Size	Diameter	Mounting Screw	No. of Teeth

Spare Parts

Screw		Wrench	Applicable Endmill
	N·m		
BFTX 02506 IP	1,5	TRDR 08 IP	WRCX 08020M – WRCX 08025M

Spare Parts

Screw		Wrench	Applicable Endmill
	N·m		
BFTX 03584 IP	3,0	TRDR 15 IP	WRCX 10025M – WRCX 10032M
BFTX 0409 IP	3,0	TRDR 15 IP	WRCX 12040M

Wave Radius Mill
RSX(F)08000/10000/12000ES

Milling of steel, stainless steel, cast iron and exotic alloys

Shank Type

Rake Angle		
	Radial	-5°– -8°
	Axial	10°

4,0 mm (08000ES) 5,0 mm (10000ES) 6,0 mm (12000ES)



Body (RSX...ES, Standard)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	Weight (kg)
		DCX	DMM	DN	LH	LS	LF		
RSX 08020 ES	●	20	20	16,9	30	70	100	2	0,3
08025 ES	●	25	25	21,9	40	80	120	3	0,4
RSX 10025 ES	●	25	25	20,3	50	80	130	2	0,4
10032 ES	●	32	32	27,1	50	80	130	3	0,7
RSX 12032 ES	●	32	32	25,6	50	80	130	2	0,7

Body (RSXF...ES, Fine Pitch)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	Weight (kg)
		DCX	DMM	DN	LH	LS	LF		
RSXF 08020 ES	●	20	20	16,9	30	70	100	3	0,3
08025 ES	●	25	25	21,9	40	80	120	4	0,4
RSXF 10025 ES	●	25	25	20,3	50	80	130	3	0,4
10032 ES	●	32	32	27,1	50	80	130	4	0,7
RSX 12032 ES	●	32	32	25,6	50	80	130	3	0,7

Inserts

Application	Grade							
High Speed/Light Cut			MS	MS				
General Purpose	PM		MS	MS	MS			
Roughing	PM	K			MS			
Cat. No.	ACP200	ACK300	ACM100	ACM200	ACM300	Dimens. IC	Dimens. S	Applicable Cutters
RDET 0803M0EN G	●	●	●	●	●	8	3,18	RSX(F) 08000ES
0803M0EN H	❍	●	●	●	●	8	3,18	
RDET 10T3M0EN G	●	●	●	●	●	10	3,97	RSX(F) 10000ES
10T3M0EN H	●	●	●	●	●	10	3,97	
RDET 1204M0EN G	●	●	●	●	●	12	4,76	RSX(F) 12000ES
1204M0EN H	●	●	●	●	●	12	4,76	



Cutting Edge Cross Section

G - Type **H** - Type

M0: IC is metric

Spare Parts

Applicable Cutters	Wrench	Screw	N·m
RSX(F) 08000ES	TRDR08IP	BFTX02506IP	**1,5**
RSX(F) 10000ES	TRDR15IP	BFTX03584IP	**3,0**
RSX(F) 12000ES		BFTX0409IP	**3,0**

Identification Details

RSX	F	10	025	ES
Cutter Series	Fine Pitch Type	Insert Size	Cutter Diameter	Endmill Type

Recommended Cutting Conditions

Min.-**Optimum**-Max.

ISO	Work Material			Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/t)	Grade
P	Carbon Steel			180–280	100–**160**–200	0,20–**0,40**–0,60	ACP200
	Alloy Steel			180–280	100–**140**–180	0,20–**0,30**–0,40	ACP200
M	Stain-less Steel	Cr Based	Ferritic	200	150–**180**–200	0,15–**0,25**–0,35	ACM300
			Martensitic	200–330	80–**120**–180	0,15–**0,25**–0,35	ACM300
		Cr-Ni Based	Austenitic	200	150–**180**–200	0,15–**0,25**–0,35	ACM300
			Austenitic, ferritic	230–270	80–**120**–180	0,15–**0,25**–0,35	ACM200
			Precipitation hardening	330	60–**100**–160	0,15–**0,25**–0,35	ACM200
K	Cast Iron			250	80–**120**–160	0,10–**0,30**–0,40	ACK300
S	Heat resistant alloy		Ni based material	250–350	20–**30**– 40	0,10–**0,20**–0,30	ACM100 ACM200
	Titanium		Pure Titanium	(Rm400)	60–**80**–100	0,10–**0,20**–0,30	
			$\alpha + \beta$ alloy system	(Rm1050)	40–**50**–60	0,10–**0,20**–0,30	

● = Euro stock
❍ = Japan stock

☞ G20/G21

N·m Recommended Tightening Torque (N·m)

Modular Type

Rake Angle		
	Radial	-5°– -8°
	Axial	10°

4,0 mm (08000ES) 5,0 mm (10000ES) 6,0 mm (12000ES)



Body (RSX...M, Standard)

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DCX	DCON	CRKS	OAL	LF	LS2	LS	L11	H		
RSX 08020M10Z2	●	20	10,5	M10	49	30	5	19	8	15	2	0,1
08025M12Z3	●	25	12,5	M12	56	35	5	21	10	19	3	0,1
08032M16Z4	●	32	17,0	M16	63	40	5	23	10	24	4	0,2
RSX 10025M12Z2	●	25	12,5	M12	56	35	5	21	10	19	2	0,1
10032M16Z3	●	32	17,0	M16	63	40	5	23	10	24	3	0,2
RSX 12032M16Z2	●	32	17,0	M16	63	40	5	23	10	24	2	0,2
12040M16Z3	●	40	17,0	M16	63	40	5	23	10	24	3	0,3

Body (RSXF...M, Fine Pitch)

Cat. No.	Stock	Dimensions (mm)									No. of Teeth	Weight (kg)
		DCX	DCON	CRKS	OAL	LF	LS2	LS	L11	H		
RSXF 08020M10Z3	●	20	10,5	M10	49	30	5	19	8	15	3	0,1
08025M12Z4	●	25	12,5	M12	56	35	5	21	10	19	4	0,1
08032M16Z5	●	32	17,0	M16	63	40	5	23	10	24	5	0,2
RSXF 10025M12Z3	●	25	12,5	M12	56	35	5	21	10	19	3	0,1
10032M16Z4	●	32	17,0	M16	63	40	5	23	10	24	4	0,2
RSXF 12032M16Z3	●	32	17,0	M16	63	40	5	23	10	24	3	0,2
12040M16Z4	●	40	17,0	M16	63	40	5	23	10	24	4	0,3

Inserts

Application	Grade				
High Speed/Light Cut			MS	MS	
General Purpose	PM		MS	MS	MS
Roughing	PM	K			MS

Cat. No.	ACP200	ACK300	ACM100	ACM200	ACM300	Dimens. IC	Dimens. S	Applicable Cutters
RDET 0803M0EN G	●	●	●	●	●	8	3,18	RSX(F) 08000ES
0803M0EN H	○	●	●	●	●	8	3,18	
RDET 10T3M0EN G	●	●	●	●	●	10	3,97	RSX(F) 10000ES
10T3M0EN H	●	●	●	●	●	10	3,97	
RDET 1204M0EN G	●	●	●	●	●	12	4,76	RSX(F) 12000ES
1204M0EN H	●	●	●	●	●	12	4,76	



Cutting Edge Cross Section

G - Type **H** - Type

M0: IC is metric

Spare Parts

Applicable Cutters	Wrench	Screw	N·m
RSX(F) 08000M	TRDR08IP	BFTX02506IP	**1,5**
RSX(F) 10000M	TRDR15IP	BFTX03584IP	**3,0**
RSX(F) 12000M		BFTX0409IP	**3,0**

Identification Details

RSX	F	10	025	M12	Z3
Cutter Series	Fine Pitch Type	Insert Size	Cutter Diameter	Mounting Screw Size	No. of Teeth

Recommended Cutting Conditions

Min.-**Optimum**-Max.

ISO	Work Material		Hardness (HB)	Cutting Speed v_c (m/min)	Feed Rate f_t (mm/t)	Grade
P	Carbon Steel		180–280	100–**160**–200	0,20–**0,40**–0,60	ACP200
	Alloy Steel		180–280	100–**140**–180	0,20–**0,30**–0,40	ACP200
M	Stain-less Steel	Cr Based	Ferritic	200	150–**180**–200	0,15–**0,25**–0,35	ACM300
			Martensitic	200–330	80–**120**–180	0,15–**0,25**–0,35	ACM300
		Cr-Ni Based	Austenitic	200	150–**180**–200	0,15–**0,25**–0,35	ACM300
			Austenitic, ferritic	230–270	80–**120**–180	0,15–**0,25**–0,35	ACM200
			Precipitation hardening	330	60–**100**–160	0,15–**0,25**–0,35	ACM200
K	Cast Iron			250	80–**120**–160	0,10–**0,30**–0,40	ACK300
S	Heat resistant alloy		Ni based material	250–350	20–**30**–40	0,10–**0,20**–0,30	ACM100 ACM200
	Titanium		Pure Titanium	(Rm 400)	60–**80**–100	0,10–**0,20**–0,30	
			$\alpha + \beta$ alloy system	(Rm 1050)	40–**50**–60	0,10–**0,20**–0,30	

WFXC Type

General Features

The WaveMill WFXC type is a chamfering tool that uses inserts for the WFX series. This allows the WFXC type to support many types of work materials using a variety of grades.

Grade Selection





Application Notes

Since chamfering uses the straight cutting edge portion of the insert, the range that can be chamfered will change depending on the corner radius (RE) of the insert that is attached to the body.
Work diameter: Use in a range grater or equal to DC1 and less than or equal to DC2.
Depth: The workpiece can be chamfered from „a“, which is the distance from the tip of the tool to the straight cutting edge at the depth indicated by „b“.

Body	Insert		Min. Work Diameter	Max. Work Diameter	Min. Depth	Max. Depth	Max. Diameter
	Cat. No.	RE	DC1	DC2	a	b	DCX
WFXC 08008E	SOMT 080304	0,4	7,5	15,8	0,1	4,1	17,8
	SOMT 080308	0,8	8,0	15,8	0,2	3,9	17,5
	SOMT 080312	1,2	8,5	15,8	0,4	3,6	17,2
WFXC 08016E	SOMT 080304	0,4	15,5	23,8	0,1	4,1	25,8
	SOMT 080308	0,8	16,0	23,8	0,2	3,9	25,5
	SOMT 080312	1,2	16,5	23,8	0,3	3,6	25,2
WFXC 12025E	SOMT 120404	0,4	24,6	38,3	0,1	6,8	41,3
	SOMT 120408	0,8	25,0	38,3	0,2	6,6	41,0
	SOMT 120412	1,2	25,6	38,3	0,4	6,3	40,7
	SOMT 120416	1,6	26,1	38,3	0,5	6,1	40,4
WFXC 12032E	SOMT 120404	0,4	31,6	45,3	0,1	6,8	48,3
	SOMT 120408	0,8	32,0	45,3	0,2	6,6	48,0
	SOMT 120412	1,2	32,6	45,3	0,4	6,3	47,7
	SOMT 120416	1,6	33,1	45,3	0,5	6,1	47,4

Dimensions (mm)



● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

WFXC 08000/12000 E

Rake Angle		
	Radial	0°
	Axial	0°





Body WFXC 08000E (Standard Type)

Cat. No.	Stock	Dimensions (mm)						No. of Teeth	Weight (kg)
		DC1	DCX	LF	LH	LS	DMM		
WFXC 08008E	❍	8	17,5	120	30	90	10	1	0,1
08016E	❍	16	25,5	120	30	90	16	2	0,2

Body WFXC 12000E (Standard Type)

Cat. No.	Stock	Dimensions (mm)						No. of Teeth	Weight (kg)
		DC1	DCX	LF	LH	LS	DMM		
WFXC 12025E	❍	25	41,0	150	40	110	25	3	0,6
12032E	❍	32	48,0	150	40	110	32	3	1,0

Identification Details

WFX	C	08	016	E
Cutter Series	Chamfering	Insert Size	Cutter Diameter	Endmill Type

Inserts

Application	Coated Carbide							Carbide	DLC			
High Speed / Light cut	P			K		MS		KN				
General Purpose		PM	PM	K		MS	MS		N			
Roughing		PM	PM		K		MS		N			
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius (mm) RE	Fig.	Applicable Cutters
SOMT 080304 PZER L	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1	WFXC08000E
080308 PZER L	❍	❍	❍	❍	❍	❍	●	–	–	0,8	1	
SOMT 080304 PZER G	❍	●	●	●	❍	❍	❍	–	–	0,4	1	
080308 PZER G	❍	●	●	●	●	❍	●	–	–	0,8	1	
080312 PZER G	❍	●	❍	❍	❍	❍	❍	–	–	1,2	1	
SOMT 080308 PZER H	❍	●	●	❍	●	❍	❍	–	–	0,8	1	
080312 PZER H	❍	❍	●	❍	❍	❍	❍	–	–	1,2	1	
SOET 080304 PZER G	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1	
080308 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	0,8	1	
080312 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	1,2	1	
SOET 080302 PZFR S	–	–	–	–	–	–	–	●	●	0,2	1	
080304 PZFR S	–	–	–	–	–	–	–	●	●	0,4	1	
080308 PZFR S	–	–	–	–	–	–	–	●	●	0,8	1	
SOMT 120408 PDER L	●	●	●	❍	❍	❍	●	–	–	0,8	2	WFXC12000E
SOMT 120404 PDER G	❍	❍	●	❍	●	❍	●	–	–	0,4	2	
120408 PDER G	●	●	●	●	❍	●	●	–	–	0,8	2	
120412 PDER G	❍	❍	❍	❍	❍	❍	●	–	–	1,2	2	
120416 PDER G	❍	●	❍	❍	❍	❍	❍	–	–	1,6	2	
SOMT 120408 PDER H	❍	●	❍	●	●	❍	❍	–	–	0,8	2	
SOET 120408 PDFR S	–	–	–	–	–	–	–	●	●	0,8	2	

Fig. 1



Fig. 2



Spare Parts

Applicable Cutter	Screw		Wrench
		(N-m)	
WFXC08000E	BFTX0306IP	2,0	TRDR08IP
WFXC12000E	BFTX03512IP	3,0	TRDR15IP

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed	Feed Rate
P	General Steel	180–280	150–**200**–250	0,05–**0,10**–0,15
	Soft Steel	≤180	180–**265**–350	0,10–**0,15**–0,20
	Die Steel	200–220	100–**150**–200	0,05–**0,10**–0,15
M	Stainless Steel	-	150–**200**–250	0,05–**0,10**–0,15
K	Cast Iron	250	100–**175**–250	0,05–**0,10**–0,15

Min. - **Optimum** - Max.

Modular Type



Rake Angle		
	Radial	0°
	Axial	0°

45°

Head (WFXC 08000M)

Cat. No.	Stock	Dimensions (mm)										No. of Teeth	Weight (kg)
		DC1	DCX	DCON	CRKS	OAL	LF	LS2	LS	L11	H		
WFXC 08016M08Z2	❍	16	25,5	8,5	M8	42	25	5	17	8	13	2	0,1

Identification Details

WFX	C	08	016	M08	Z2
Cutter Series	Chamfe-ring	Insert Size	Cutter Diameter	Screw Size	No. of Teeth

Head (WFXC 12000M)

Cat. No.	Stock	Dimensions (mm)										No. of Teeth	Weight (kg)
		DC1	DCX	DCON	CRKS	OAL	LF	LS2	LS	L11	H		
WFXC 12025M12Z3	❍	25	41,0	12,5	M12	56	32	5	21	10	19	3	0,1
12032M16Z3	❍	32	48,0	17,0	M16	63	40	5	23	10	24	3	0,2

Inserts

Application	Coated Carbide							Carbide	DLC		
High Speed / Light cut	P			K		MS		KN			
General Purpose		PM	PM	K		MS	MS		N		
Roughing		PM	PM		K		MS		N		
Cat. No.	ACP100	ACP200	ACP300	ACK200	ACK300	ACM200	ACM300	H1	DL1000	Radius (mm) RE	Fig.
SOMT 080304 PZER L	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1
080308 PZER L	❍	❍	❍	❍	❍	❍	●	–	–	0,8	1
SOMT 080304 PZER G	❍	●	●	●	❍	❍	❍	–	–	0,4	1
080308 PZER G	❍	●	●	●	●	❍	●	–	–	0,8	1
080312 PZER G	❍	●	❍	❍	❍	❍	❍	–	–	1,2	1
SOMT 080308 PZER H	❍	●	●	❍	●	❍	❍	–	–	0,8	1
080312 PZER H	❍	❍	●	❍	❍	❍	❍	–	–	1,2	1
SOET 080304 PZER G	❍	❍	❍	❍	●	❍	❍	–	–	0,4	1
080308 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	0,8	1
080312 PZER G	❍	❍	❍	❍	❍	❍	❍	–	–	1,2	1
SOET 080302 PZFR S	–	–	–	–	–	–	–	●	●	0,2	1
080304 PZFR S	–	–	–	–	–	–	–	●	●	0,4	1
080308 PZFR S	–	–	–	–	–	–	–	●	●	0,8	1
SOMT 120408 PDER L	●	●	●	❍	❍	❍	●	–	–	0,8	2
SOMT 120404 PDER G	❍	❍	●	❍	●	❍	●	–	–	0,4	2
120408 PDER G	●	●	●	●	❍	●	●	–	–	0,8	2
120412 PDER G	❍	❍	❍	❍	❍	❍	●	–	–	1,2	2
120416 PDER G	❍	●	❍	❍	❍	❍	❍	–	–	1,6	2
SOMT 120408 PDER H	❍	●	❍	●	●	❍	❍	–	–	0,8	2
SOET 120408 PDFR S	–	–	–	–	–	–	–	●	●	0,8	2

Fig. 1



Fig. 2



Spare Parts

Applicable Cutter	Screw		Wrench
		N·m	
WFXC08000M	BFTX0306IP	2,0	TRDR08IP
WFXC12000M	BFTX03512IP	3,0	TRDR15IP

Recommended Cutting Conditions

ISO	Work Material	Hardness (HB)	Cutting Speed	Feed Rate
P	General Steel	180–280	150–**200**–250	0,05–**0,10**–0,15
P	Soft Steel	≤180	180–**265**–350	0,10–**0,15**–0,20
P	Die Steel	200–220	100–**150**–200	0,05–**0,10**–0,15
M	Stainless Steel	-	150–**200**–250	0,05–**0,10**–0,15
K	Cast Iron	250HB	100–**175**–250	0,05–**0,10**–0,15

Min. - **Optimum** - Max.

● = Euro stock
❍ = Japan stock

N·m Recommended Tightening Torque (N·m)

New

Features

Drastically Reduced Runout Adjustment Time
Simple screw-fastening structure enables fine adjustments to be made easily.

Blade Through Coolant
Secures a supply of coolant to the cutting edge and breaks chips thoroughly.

Lightweight Aluminum Alloy Body
Utilizing aluminum alloy to achieve a total weight of less than 1,3 kg for a Ø 125 mm cutter with 22 teeth.

Product Range

Type	Cat. No.	Body Material	Diameter Range (mm) / No of Teeth							
			Ø32	Ø40	Ø50	Ø63	Ø80	Ø100	Ø125	Ø160
Shell	ANXA 16000RS	Aluminum Alloy					10, 14	12, 18	14, 22	20, 28
	ANXA 16000R (Inch)	Aluminum Alloy					10, 14	12, 18	14, 22	20, 28
	ANXS 16000RS	Steel		6	6, 9	8, 12	10, 14	12, 18	14, 22	
	ANXS 16000R (Inch)	Steel				8, 12	10, 14	12, 18	14, 22	
Shank	ANXS 16000E ☞ G60	Steel	4	6						

Inch Inch Bore

Blade Selection Guide

Work Material	N					
Type	L	G	GX	H	—	W
Cutting Edge Shape						
Features	Low Cutting Force	Standard	Long Edge	High Strength	Corner Radius	Wiper
Applications	Finishing / Light Cutting	General Purpose	Roughing			
Edge Length*	6,0 mm	6,0 mm	9,0 mm	6,0 mm		



*Edge length
GX type = 9,0 mm

Edge Selection Guide



Reduces Running Costs by Drastically Increasing Blade, Insert Regrinding Allowance (to 1,0 mm)

Assuming 0,2 mm of regrinding each time, an edge can be used up to 6 times.
(Peripheral edge cannot be reground.)





If you wish to use reground blades you shall use sets of blades with matching size of the same level in order to keep the balance.

Performances

High-Speed / High-Efficiency Cutting

Realizes ultra-high efficiency machining with v_f = 30.000 mm/min



Comparison: Cutter Diameter Ø 100 mm

	Spindle Speed min^{-1}	Number of Teeth	Feed Rate v_f (mm/min)
ANX Series	18.000	18	32.400
Competitor	9.500	12	11.400

Drastically Reduces Runout Adjustment Time

– Simple screw-fastening structure
– Enables fine adjustments to be made easily
– High-rigidity body





Chip Control

Blade-Through Coolant Chip Breaking

ALNEX ANX Series | Competitor

Work Material:	G-AlSi12Cu
Cutting Conditions:	v_c = 2500 m/min, f_z = 0,05 mm/t, a_p = 0,5 mm, wet

❍ = Japan stock

Recommended Tightening Torque (N·m)

ANXS 16000 E

New

Rake Angle	Radial	-2 – 0°
	Axial	+5°

3 mm | 90°



Body - ANXS (Steel)

Dimensions (mm)

Cat. No.	Stock	DC	DCX	DMM	LH	LS	LF	No. of Teeth	Weight (kg)
ANXS 16032E04	❍	30	32	20	35	60	95	4	0,3
16040E06	❍	38	40	20	40	60	100	6	0,5

Blades are sold separately.
If using a blade for corner radius machining (ANB1604R), DC = DCX.

Identification Details

ANX	S	16	032	E	04
Cutter Series	Steel Body	Blade Size	Cutter Diameter	Round Shank	Number of Teeth

Spare Parts

Sold separately.

Applicable Cutters	Clamp Screw		Adjustment Screw	Wrench	Adjustment Wrench	Assembly Wrench
						
ANXS 16032E04 16040E06	BXA0310IP	2,0	HFJ	TRXW10IP	ANT	HFVT

Max. Allowable Spindle Speed

Cat. No.	n max (min^{-1})
ANXS 16032E04	10.000
16040E06	10.000

Blades

Application	SUMIDIA
High Speed / Light Cut	N
General Purpose	N
Roughing	N

Cat. No.	DA1000	Cutting Edge Length	Wiper Edge Shape	Applications	Fig.
ANB 1600R-L	❍	6,0	Linear	Low Cutting Force	1
1600R-G	❍	6,0	Arc-Shaped	General Purpose	1
1600R-H	❍	6,0	Arc-Shaped	Strong Edge	1
1600R-GX	❍	9,0	Arc-Shaped	Long Edge	2
1604R	❍	6,0	Linear	Corner Radius	3
1600R-W	❍	–	Arc-Shaped	Wiper	4

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Wiper Blade

Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

ISO	Work Material	Hard-ness	Cutting Speed v_c (m/min)	Feed Rate f_z (mm/t)	Grade
N	Aluminium Alloy	–	2.000–**2.500**–3.000	0,05–**0,13**–0,20	DA1000

Si content ≥ 12,6 %

Min. - **Optimum** - Max.

ISO	Work Material	Hard-ness	Cutting Speed v_c (m/min)	Feed Rate f_z (mm/t)	Grade
N	Aluminium Alloy	–	400–**600**–800	0,05–**0,13**–0,20	DA1000

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

■ ALNEX Series Usage Manual

● Adjustment of the Blades, Runout Alignment

① Before inserting the blade, make sure that the seat and screws are free of debris by cleaning those areas.

② Insert the blade into its seat.

③ While holding the blade against the seat, install the clamping bolt using the provided wrench, pre-tightening the bolt (recommended pre-torque is 1 N·m).

④ Using the provided wrench for the height adjustment screw, set the height to your predetermined value.

⑤ Fully tighten the clamp bolt (recommended torque is 2 N·m).

⑥ Use 1 blade as a datum point and adjust all blade heights to match.

⑦ After tightening, verify that there is no gap between the seat and blade.

② 

③ 
Pre-tighten (1N·m)

④ 
Adjust height

⑤ 
Final tighten (2N·m)

● Balance Adjustments

The cutter comes pre-balanced to a G 6,3 specification.
Under normal circumstances, it is not necessary to adjust the balance of the cutter.



● Clamp Bolts for Arbor

Work Material	Dim.			Max. Torque	Applicable Cutters
	M	L	D		
BXH0825-D13	8	25	13	15	ANXS16040RS_ _
BXH1030-D16	10	30	16	25	ANXS16040RS_ _ , ANXS16063RS_ _
BXH1235-D18	12	35	18	40	ANXS16063R_ _
BXH1235-D33	12	35	33	50	ANXS16080R(S)_ _ , ANXA16080/100/125R(S)_ _
BXH1635-D40	16	35	40	100	ANXS16100R(S)_ _
BXH2036-D50	20	36	50	200	ANXS16125R(S)_ _ , ANXA16160R(S)_ _



● Other Precautions

- Please use only Sumitomo genuine parts.
- Please regularly replace clamp bolts.
- If you wish to reduce the # of effective blades in use, to maintain balance and protect the body, please use dummy blades (set height well below effective blades).
- Please do not operate after releasing the interlock or opening the cover.
- Please avoid use and consult with Sumitomo if you mistakenly crash the body.
- As the blades are very sharp, it is very easy to get hurt when touching the blades with your hands directly, so please wear gloves when taking the blade out of the case to set into the cutter or when setting the cutter into machine tool.

J

Coated & Solid Endmills

J1–J44

Selection Guide

● According to Work Materials

Square Type

Legend: Grade | Edge Type | Usage

General Steel (Common Use)

Coated | Sharp | General

Global Endmills
Standard
GSX Type
ø 1–25 mm
•2 Flutes
•3 Flutes
•4 Flutes



⇨ J7–19

Anti-Vibration
Radius Corner
Endmills
GSXVL Type
ø 2–25 mm
•4 Flutes

⇨ J20–21

General Steel (Special Use)

Plunge Cut
Multi-Purpose

Coated | Sharp | General

GSX MILL
GSXSLT Type
ø 1–16 mm
•3 Flutes



⇨ J14

High Efficiency

Coated | Strong | High Efficiency

UPMILL
SSUP-ZX Type
ø 2–20 mm
•4 Flutes

⇨ J30–31

High Efficiency

Coated | Strong | High Efficiency

ROUGHING ENDMILL
GSRE-SFType
ø 6–20 mm
•4 Flutes

⇨ J25

Hardened Steel

High performance Type

Coated | Strong | High Efficiency

GS-MILL-HARD
GSH-SF Type
ø 1–20 mm
•4 Flutes
•6 Flutes
•8 Flutes

⇨ J26

High Rigidity Type

Coated | Strong | High Efficiency

HARD ENDMILL
LHHM...ZX
EHHM...ZX
ø 3–32 mm
•4 Flutes
•6 Flutes
•8 Flutes

⇨ J29

SumiBoron Endmill

CBN

"Helical Master"
BNES Type
ø 6–16 mm
•1 Flute

⇨ J40, M50

Exotic Metals

For Heat Resistive Steel

Coated | Sharp | General

Radius Endmills
Standard
SSEH Type
ø 4,5–25 mm
•4 Flutes



Anti-Vibration
Radius Endmills
SSEHVL Type
ø 4,5–25 mm
•4 Flutes

⇨ J22, J24, J35

⇨ J22–23, J35

Non-ferrous Metal

SumiDia Endmill

PCD

SUMIDIA brazed
DFE Type
ø 4–13 mm
•1 Flute
•2 Flutes
•4 Flutes



⇨ Stock in Japan

DLC-Coated Endmill

Coated | Sharp | General

AURORA COATED
ASM-DL Type
ø 2–16 mm
•2 Flutes
•4 Flutes

⇨ J27–28

● According to Work Materials

Ballnose Type

General Steel (Common Use)

Coated | General

GSX MILL BALL
GSXB Type
R 0,2–12,5 mm
•2 Flutes

⇨ J32

General Steel (Short Series)

Coated | Short | General

NEOBALL SHORT FLUTE
S-SNB-ZX Type
R 1,5–15 mm
•2 Flutes



⇨ Stock in Japan

Coated | Short | General

ZX-COATED SHORT FLUTE
S-SSB-ZX Type
R 1,5–4 mm
•2 Flutes

⇨ Stock in Japan

Hardened Steel

High Rigidity Type

Coated | Strong | High Efficiency

HARDBALL
SHB-ZX Type
R 0,5–10 mm
•2 Flutes

⇨ Stock in Japan

Hardened Steel

CBN | MOULD FINISH MASTER | PCD

SUMIBORON brazed
BNBP Type
R 0,2–1,0 mm
•2 Flutes



⇨ J41, M51

SUMIDIA binderless
NPDRS Type
R 0,2–2,0 mm
•1 Flute
Radius Endmill

NPDB(S) Type
R 0,1–1,0 mm
•1 Flute
Ballnose Endmill



⇨ J42–43, M52–53

Non-ferrous Metal

DLC-Coated Endmill

Coated | General

AURORA COATED
SNB-DL Type
R 1–8 mm
•2 Flutes



⇨ J34

GSX MILL Series

Characteristics and Applications

- Wide variation of three flute types and four flute lengths enable use in a wide variety of applications.
- Fine carbide substrate provides high transverse rupture strength and excellent thermal shock resistance improving reliability in wet cutting applications.
- GSX Coating provides improved reliability and longer tool life.
- Large rake angle and unique flute design improve sharpness and chip evacuation.
- Cutting teeth with gash land improves corner flute strength.
- Sharper edge S type and fracture resistant C type added to the 2D size series.

● Wear Resistance



● Thermal Resistance



● Improved Chip Evacuation



Large rake angle combined with our unique flute design improves sharpness and chip evacuation.

2 cutting edge designs expand machining applications

Sharper edge S type and fracture resistant C type added to the 2D size series.

S Type Sharp Corner: Sharper Edge Design



C Type Gash Land: Fracture Resistant Design



Note: In gash land drilling, some material remains as shown on the right. If you need sharp corners, use the S Type.



Ex.: Corner on a ø 10 mm hole

Application Range

P					H			M	S		K	N		
General Structure Rolled Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45 ~ 55 HRC	Hardened Steel 55 ~ 60 HRC	Hardened Steel 60 ~ 65 HRC	Stainless Steel	Ti Alloy	Heat Resistant Alloy	Cast Iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎ *1			◎	○	○	○			

◎ : Best
○ : Good

Blank : Not recommended
*1: GSXSLT30000C is recommended for 50 HRC or less

Recommended Milling Examples

Application	Surface Milling		Grooving		Groove Finishing	
Form						
	Rough	Finishing	Rough	Finishing	Rough	Finishing
S Type		◎		○		◎
C Type	◎	○	◎	◎	◎	○

S Type is best for removing inside corners.

*2: Use with small depth of cut.

GSX MILL Series

Large rake angle and unique flute design improve sharpness and excellent chip evacuation.

Product Range

Application	No. of Teeth	Flute Length				
		1,5 D	2 D		3 D	4 D
		C Type	S Type	C Type	C Type	C Type
General Purpose	2 Flutes	GSX20000C-1.5D ⇨ J 7	GSX20000S-2D ⇨ J 8	GSX20000C-2D ⇨ J 9	GSX20000C-3D ⇨ J 10	GSX20000C-4D ⇨ J 11
	3 Flutes	GSX30000C-1.5D ⇨ J 12		GSX30000C-2D ⇨ J 13		
	4 Flutes	GSX40000C-1.5D ⇨ J 15	GSX40000S-2D ⇨ J 16	GSX40000C-2D ⇨ J 17	GSX40000C-3D ⇨ J 18	GSX40000C-4D ⇨ J 19
Compound Endmilling	3 Flutes	GSXSLT30000C-1.5D ⇨ J 14				

Multi-Purpose "GSX-SLT" Slot Type

- Optimized flute design of slotted 3 flute (1.5D) short type reduces cutting resistance.

① Allows drilling and slot milling and other continuous (compound) applications.
② Perfect for use with thin sheets and small machining centres



Application Examples

● Carbon Steel Grooving with GSX20000C

GSX 20000C | Competitor

Gash land for stronger cutting edge.

Tool dimension	ø 6 (2 Flutes)
Work material	C50
Cutting speed	v_c = 87 m/min
	n = 4615 rpm
Feed rate	f_t = 0,06 mm/teeth
	v_f = 553 mm/min
Depth of cut	a_p = 3 mm
Wide of cut	a_e = 6 mm
Cooland	Dry
Vertical machining centre (BT50)	

● Cast Iron Grooving with GSX20000C

GSX 20000C | Competitor

GSX coating for improved wear resistance.

Tool dimension	ø 10 (2 Flutes)
Work material	GGG60
Cutting speed	v_c = 66 m/min
	n = 2100 rpm
Feed rate	f_t = 0,072 mm/teeth
	v_f = 302 mm/min
Depth of cut	a_p = 5 mm, 5 passes
Wide of cut	a_e = 10 mm
Cooland	Dry
Vertical machining centre (BT40)	

● Stainless Steel Machining with GSX20000C

GSX 20000C | Competitor

Improved reliability even under wet machining.

Tool dimension	ø 10 (2 Flutes)
Work material	X5 CrNi 1812
Cutting speed	v_c = 50 m/min
	n = 1591 rpm
Feed rate	f_t = 0,04 mm/teeth
	v_f = 27 mm/min
Depth of cut	a_p = 10 mm
Wide of cut	a_e = 0,5 mm
Cooland	Wet
Vertical machining centre (BT50)	

● Surface Milling C50 with GSX20000S

GSX 20000S | Competitor



S type delivers optimum cutting performance.

Tool dimension	ø 6 (2 Flutes)
Work material	C50
Cutting speed	v_c = 87 m/min
	n = 4615 rpm
Feed rate	f_t = 0,06 mm/teeth
	v_f = 553 mm/min
Depth of cut	a_p = 10 mm
Wide of cut	a_e = 0,3 mm
Cooland	Dry
Vertical machining centre (BT50)	

GSX MILL Series

☞ J 20, J 21

GSX MILL Anti-vibration Type (Square/Radius)

■ Characteristics and Applications

- Optimized irregular pitch and lead affords:
  - Drastically improved chattering and fracture resistance !
  - Less cutting force Allows high-speed, high-feed cutting.
- Rounded lands greatly improve machined surface quality (from ø 4 and up).
- New fine-grained carbide substrate and special coating for better rigidity and thermal and wear resistance.

■ Product Range

GSX MILL Anti-vibration Square Type

Series	No. of Teeth	Serie	DC (mm)
GSXVL4000-2.5D	4 Flutes	 ⇨ J 20	ø 2 – ø 20

GSX MILL Anti-vibration Corner Radius Type

Series	No. of Teeth	Serie	DC (mm)
GSXVL4000-R-2.5D	4 Flutes	 ⇨ J 21	ø 3 – ø 20

■ Cutting Range



■ Cutting Resistance



■ Application Range

● Surface Finish Quality

GSX Anti-vibration | Competitor's Anti-vibration | Conventional Design



No Chattering Clean Surface | Minute Chattering Poor Surface | Heavy Chattering Poor Surface

Work material:	C50	Cutting Conditions:	n = 4.800 rpm v_f = 800 mm/min
Grooving: Tool dimension:	ø 10	Depth of cut Equipment:	a_p = 10 mm BT50



+ J 34

GSX MILL Ball

■ Characteristics and Applications

- New coating combined with a fine-grained carbide substrate affords better thermal and wear resistance.
- Large helix angle on cutting edge reduces cutting resistance.
- Unique pocket design and expanded pocket area promotes better chip evacuation.

➡ Expands the range of machineable material from soft to hardened steels, and offers reliability and longer tool life.

■ Product Range

Series	No. of Teeth	Serie	DC (mm)
GSX-B 20000	2 Flutes	 ⇨ J 36	R=ø0,2 – ø15 (DC=0,2 – 30)

■ Application Range



■ Application Examples

● Flank Wear



GSX Ball (Cutting Length 140 m)

Able to continue

Conventional Tool (Cutting Length 80 m)

Unable to continue

Work Material : X40CrVMo5-1 (50HRC)
Tool Dimensions : R3 (2 Flutes)
Cutting Conditions : v_c= 179 m/min (n = 9.500 rpm)
v_f= 2.250 mm/min (f_t = 0,12 mm/t)
a_p = 0,2 ~ 1,0 mm, a_e =0,3 mm, Wet
Equipment Vertical Machining Centre BT40

Chipping in centre
Heavy wear on flank face

● = Euro stock

GSX MILL Endmills
GSX 20000C-1.5D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 20100C-1.5D	●	1,0	1,5	2,5	40	4
GSX 20150C-1.5D	●	1,5	2,3	3,3	40	4
GSX 20200C-1.5D	●	2,0	3,0	4,0	40	4
GSX 20250C-1.5D	●	2,5	3,8	4,8	40	4
GSX 20300C-1.5D	●	3,0	4,5	6,0	45	6
GSX 20350C-1.5D	●	3,5	5,3	6,8	45	6
GSX 20400C-1.5D	●	4,0	6,0	7,5	45	6
GSX 20450C-1.5D	●	4,5	6,8	8,3	50	6
GSX 20500C-1.5D	●	5,0	7,5	9,5	50	6
GSX 20550C-1.5D	●	5,5	8,3	10,3	50	6
GSX 20600C-1.5D	●	6,0	9,0	–	50	6
GSX 20700C-1.5D	●	7,0	11,0	13,0	60	8
GSX 20800C-1.5D	●	8,0	12,0	–	60	8
GSX 20900C-1.5D	●	9,0	14,0	16,0	70	10
GSX 21000C-1.5D	●	10,0	15,0	–	70	10
GSX 21200C-1.5D	●	12,0	18,0	–	75	12
GSX 21400C-1.5D		14,0	21,0	24,5	90	16
GSX 21500C-1.5D		15,0	23,0	26,5	90	16
GSX 21600C-1.5D		16,0	24,0	–	90	16
GSX 22000C-1.5D		20,0	30,0	–	100	20

Endmill Identification (GSX MILL Series)

GSX 2 0100 C - 1.5D

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



Shoulder Milling

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		19.600	250	19.600	250	19.600	250	18.300	180	12.700	100	9.000	60	11.000	70	9.000	50
2,0		11.200	340	11.200	340	11.200	340	10.500	240	7.300	130	5.300	80	6.400	90	5.300	70
4,0		6.400	460	6.400	460	6.400	460	6.000	320	4.200	180	3.000	110	3.600	120	3.000	90
6,0		4.600	560	4.600	560	4.600	560	4.300	400	3.000	210	2.200	130	2.700	140	2.200	100
8,0		3.400	560	3.400	560	3.400	560	3.200	400	2.200	210	1.600	130	2.000	140	1.600	100
10,0		2.800	560	2.800	560	2.800	560	2.600	400	1.800	210	1.300	130	1.600	140	1.300	100
12,0		2.300	560	2.300	560	2.300	560	2.200	400	1.500	210	1.100	130	1.300	140	1.100	100
16,0		1.700	450	1.700	450	1.700	450	1.600	320	1.100	180	800	100	1.000	110	800	85
20,0		1.350	380	1.350	380	1.350	380	1.300	280	900	160	650	90	800	100	650	75
Shoulder cutting	a_p	1,5 DC										1,0 DC					
	a_e	0,05 DC										0,02 DC					

Grooving

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		19.600	200	19.600	250	19.600	250	18.300	180	12.700	100	9.000	60	11.000	50	4.500	20
2,0		11.200	270	11.200	340	11.200	340	10.500	240	7.300	130	5.300	80	6.400	65	2.650	25
4,0		6.400	370	6.400	460	6.400	460	6.000	320	4.200	180	3.000	110	3.600	80	1.500	35
6,0		4.600	450	4.600	560	4.600	560	4.300	400	3.000	210	2.200	130	2.700	100	1.100	40
8,0		3.400	450	3.400	560	3.400	560	3.200	400	2.200	210	1.600	130	2.000	100	800	40
10,0		2.800	450	2.800	560	2.800	560	2.600	400	1.800	210	1.300	130	1.600	100	650	40
12,0		2.300	450	2.300	560	2.300	560	2.200	400	1.500	210	1.100	130	1.300	100	500	40
16,0		1.700	360	1.700	450	1.700	450	1.600	320	1.100	180	800	100	1.000	80	400	35
20,0		1.350	300	1.350	380	1.350	380	1.300	280	900	160	650	90	800	70	320	30
Grooving	a_p	0,2 DC		0,5 DC						0,2 DC		0,05 DC		0,2 DC			

GSX 20000S-2D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 20030S-2D	❍	0,3	0,6	1,0	40	4
GSX 20040S-2D	❍	0,4	0,8	1,2	40	4
GSX 20050S-2D	●	0,5	1,3	1,7	40	4
GSX 20080S-2D	❍	0,8	1,6	2,1	40	4
GSX 20100S-2D	●	1,0	2,5	3,5	40	4
GSX 20150S-2D	●	1,5	3,8	4,8	40	4
GSX 20200S-2D	●	2,0	5,0	6,0	40	4
GSX 20250S-2D	●	2,5	6,3	7,3	40	4
GSX 20300S-2D	●	3,0	7,5	9,0	45	6
GSX 20350S-2D	●	3,5	8,8	10,3	45	6
GSX 20400S-2D	●	4,0	11,0	14,0	45	6
GSX 20450S-2D	●	4,5	11,3	12,8	50	6
GSX 20500S-2D	●	5,0	13,0	19,6	50	6
GSX 20550S-2D	●	5,5	13,0	19,6	50	6
GSX 20600S-2D	●	6,0	13,0	–	50	6
GSX 20700S-2D	●	7,0	16,0	21,1	60	8
GSX 20800S-2D	●	8,0	19,0	–	60	8
GSX 20900S-2D	●	9,0	19,0	24,1	70	10
GSX 21000S-2D	●	10,0	22,0	–	70	10
GSX 21200S-2D	●	12,0	26,0	–	75	12
GSX 21600S-2D	●	16,0	32,0	–	90	16
GSX 22000S-2D	●	20,0	40,0	–	100	20

Endmill Identification (GSX MILL Series)

GSX **2** **0050** **S** **-** **2D**

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. This series is not recommended for grooving.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



● Shoulder Milling

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	16.600	180	16.600	180	16.600	180	15.500	130	10.500	70	7.500	45	9.400	50	7.500	35
2,0	9.500	250	9.500	250	9.500	250	9.000	200	6.200	100	4.500	60	5.400	70	4.500	50
4,0	5.400	330	5.400	330	5.400	330	5.000	250	3.400	120	2.500	75	3.000	90	2.500	65
6,0	4.000	400	4.000	400	4.000	400	3.700	300	2.550	150	1.900	100	2.300	110	1.900	80
8,0	3.000	400	3.000	400	3.000	400	2.800	300	1.900	150	1.400	100	1.700	110	1.400	80
10,0	2.400	400	2.400	400	2.400	400	2.200	300	1.500	150	1.100	100	1.300	110	1.100	80
12,0	2.000	400	2.000	400	2.000	400	1.850	300	1.300	150	950	100	1.100	110	950	80
16,0	1.500	330	1.500	330	1.500	330	1.400	250	950	120	700	75	850	85	700	60
20,0	1.200	280	1.200	280	1.200	280	1.100	220	750	110	550	65	650	75	550	55
Shoulder cutting ap	1,5 DC										1,0 DC					
Shoulder cutting ae	0,05 DC										0,02 DC					

● Groove Finishing

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	16.600	180	16.600	180	16.600	180	15.500	130	10.500	70	7.500	45	9.400	50	7.500	35
2,0	9.500	250	9.500	250	9.500	250	9.000	200	6.200	100	4.500	60	5.400	70	4.500	50
4,0	5.400	330	5.400	330	5.400	330	5.000	250	3.400	120	2.500	75	3.000	90	2.500	65
6,0	4.000	400	4.000	400	4.000	400	3.700	300	2.550	150	1.900	100	2.300	110	1.900	80
8,0	3.000	400	3.000	400	3.000	400	2.800	300	1.900	150	1.400	100	1.700	110	1.400	80
10,0	2.400	400	2.400	400	2.400	400	2.200	300	1.500	150	1.100	100	1.300	110	1.100	80
12,0	2.000	400	2.000	400	2.000	400	1.850	300	1.300	150	950	100	1.100	110	950	80
16,0	1.500	330	1.500	330	1.500	330	1.400	250	950	120	700	75	850	85	700	60
20,0	1.200	280	1.200	280	1.200	280	1.100	220	750	110	550	65	650	75	550	55
Groove finishing ap	1,5 DC															
Groove finishing ae	–0,02 DC															

● = Euro stock
❍ = Japan stock

GSX MILL Endmills
GSX 20000C-2D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 20050C-2D	●	0,5	1,0	1,4	40	4
GSX 20100C-2D	●	1,0	2,0	3,0	40	4
GSX 20150C-2D	●	1,5	3,0	4,0	40	4
GSX 20200C-2D	●	2,0	4,0	5,0	40	4
GSX 20250C-2D	●	2,5	5,0	6,0	40	4
GSX 20300C-2D	●	3,0	6,0	7,5	45	6
GSX 20350C-2D	●	3,5	7,0	8,5	45	6
GSX 20400C-2D	●	4,0	8,0	9,5	45	6
GSX 20450C-2D	●	4,5	9,0	10,5	50	6
GSX 20500C-2D	●	5,0	10,0	12,0	50	6
GSX 20550C-2D	●	5,5	11,0	13,0	50	6
GSX 20600C-2D	●	6,0	12,0	—	50	6
GSX 20700C-2D	●	7,0	14,0	16,0	60	8
GSX 20800C-2D	●	8,0	16,0	—	60	8
GSX 20900C-2D	●	9,0	18,0	20,0	70	10
GSX 21000C-2D	●	10,0	20,0	—	70	10
GSX 21200C-2D	●	12,0	24,0	—	75	12
GSX 21400C-2D		14,0	28,0	31,5	90	16
GSX 21500C-2D		15,0	30,0	33,5	90	16
GSX 21600C-2D	●	16,0	32,0	—	90	16
GSX 22000C-2D	●	20,0	40,0	—	100	20

Endmill Identification (GSX MILL Series)

GSX 2 0050 C - 2D

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



Shoulder Milling

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		19.600	250	19.600	250	19.600	250	18.300	180	12.700	100	9.000	60	11.000	70	9.000	50
2,0		11.200	340	11.200	340	11.200	340	10.500	240	7.300	130	5.300	80	6.400	90	5.300	70
4,0		6.400	460	6.400	460	6.400	460	6.000	320	4.200	180	3.000	110	3.600	120	3.000	90
6,0		4.600	560	4.600	560	4.600	560	4.300	400	3.000	210	2.200	130	2.700	140	2.200	100
8,0		3.400	560	3.400	560	3.400	560	3.200	400	2.200	210	1.600	130	2.000	140	1.600	100
10,0		2.800	560	2.800	560	2.800	560	2.600	400	1.800	210	1.300	130	1.600	140	1.300	100
12,0		2.300	560	2.300	560	2.300	560	2.200	400	1.500	210	1.100	130	1.300	140	1.100	100
16,0		1.700	450	1.700	450	1.700	450	1.600	320	1.100	180	800	100	1.000	110	800	85
20,0		1.350	380	1.350	380	1.350	380	1.300	280	900	160	650	90	800	100	650	75
Shoulder cutting	a_p	1,5 DC										1,0 DC					
	a_e	0,05 DC										0,02 DC					

Grooving

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		19.600	200	19.600	250	19.600	250	18.300	180	12.700	100	9.000	60	11.000	50	4.500	20
2,0		11.200	270	11.200	340	11.200	340	10.500	240	7.300	130	5.300	80	6.400	65	2.650	25
4,0		6.400	370	6.400	460	6.400	460	6.000	320	4.200	180	3.000	110	3.600	80	1.500	35
6,0		4.600	450	4.600	560	4.600	560	4.300	400	3.000	210	2.200	130	2.700	100	1.100	40
8,0		3.400	450	3.400	560	3.400	560	3.200	400	2.200	210	1.600	130	2.000	100	800	40
10,0		2.800	450	2.800	560	2.800	560	2.600	400	1.800	210	1.300	130	1.600	100	650	40
12,0		2.300	450	2.300	560	2.300	560	2.200	400	1.500	210	1.100	130	1.300	100	500	40
16,0		1.700	360	1.700	450	1.700	450	1.600	320	1.100	180	800	100	1.000	80	400	35
20,0		1.350	300	1.350	380	1.350	380	1.300	280	900	160	650	90	800	70	320	30
Grooving	a_p	0,2 DC		0,5 DC						0,2 DC		0,05 DC		0,2 DC			

GSX 20000C-3D Type

Coated Carbide Grades | GSX Coating

Structual Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 20100C-3D	●	1,0	3,0	4,0	40	4
GSX 20150C-3D	●	1,5	4,5	5,5	40	4
GSX 20200C-3D	●	2,0	6,0	7,0	40	4
GSX 20250C-3D	●	2,5	7,5	8,5	40	4
GSX 20300C-3D	●	3,0	9,0	10,5	50	6
GSX 20400C-3D	●	4,0	12,0	13,5	50	6
GSX 20500C-3D	●	5,0	15,0	17,0	50	6
GSX 20600C-3D	●	6,0	18,0	—	50	6
GSX 20800C-3D	●	8,0	24,0	—	70	8
GSX 21000C-3D	●	10,0	30,0	—	90	10
GSX 21200C-3D	●	12,0	36,0	—	90	12
GSX 21600C-3D	●	16,0	48,0	—	110	16
GSX 22000C-3D		20,0	60,0	—	120	20

Endmill Identification (GSX MILL Series)

GSX **2** **0100** **C** **-** **3D**

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rare cases, chattering may occur in early milling stages, dissipating after 2m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



● Shoulder Milling

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	16.600	190	16.600	190	16.600	190	15.500	140	10.500	70	7.500	45	9.400	50	7.500	35
2,0	9.500	250	9.500	250	9.500	250	9.000	200	6.200	120	4.500	60	5.200	70	4.500	50
4,0	5.200	330	5.200	330	5.200	330	4.800	200	3.400	150	2.250	75	2.600	90	2.250	65
6,0	3.500	360	3.500	360	3.500	360	3.200	250	2.550	170	1.500	90	1.700	100	1.500	80
8,0	2.600	320	2.600	320	2.600	320	2.400	240	1.900	170	1.100	90	1.300	105	1.100	80
10,0	2.100	300	2.100	300	2.100	300	1.900	230	1.500	170	900	90	1.000	100	900	80
12,0	1.750	280	1.750	280	1.750	280	1.600	230	1.250	170	750	90	850	100	750	80
16,0	1.300	240	1.300	240	1.300	240	1.200	200	950	150	550	75	650	85	550	65
20,0	1.050	220	1.050	220	1.050	220	950	180	750	140	450	70	500	75	450	60
Shoulder cutting ap	2,5 DC								2,0 DC							
Shoulder cutting ae	< ø3: 0,05 DC , ≤ ø3: 0,1 DC								0,02 DC							

● Grooving

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	16.600	70	16.600	80	16.600	80	15.500	50	10.500	50	7.500	35	9.400	30	3.750	10
2,0	9.500	80	9.500	100	9.500	100	9.000	90	6.200	60	4.500	45	5.200	40	2.250	15
4,0	5.200	120	5.200	150	5.200	150	4.800	120	3.400	80	2.200	50	2.600	50	1.250	20
6,0	3.500	140	3.500	170	3.500	170	3.200	130	2.550	100	1.500	50	1.700	60	950	25
8,0	2.600	140	2.600	160	2.600	160	2.400	130	1.900	100	1.100	50	1.300	60	700	25
10,0	2.100	130	2.100	150	2.100	150	1.900	120	1.500	90	900	50	1.000	60	550	25
12,0	1.750	130	1.750	150	1.750	150	1.600	120	1.250	90	750	50	850	60	450	25
16,0	1.300	110	1.300	130	1.300	130	1.200	110	950	80	550	45	650	50	350	20
20,0	1.050	100	1.050	120	1.050	120	950	100	750	70	450	40	500	40	280	15
Grooving ap	0,1 DC		0,2 DC								0,05 DC		0,1 *D*			
Grooving ae																

● = Euro stock

GSX MILL Endmills
GSX 20000C-4D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 20100C-4D	●	1,0	4,0	5,0	40	4
GSX 20150C-4D	●	1,5	6,0	7,0	40	4
GSX 20200C-4D	●	2,0	8,0	9,0	40	4
GSX 20250C-4D	●	2,5	10,0	11,0	50	4
GSX 20300C-4D	●	3,0	12,0	13,5	50	6
GSX 20400C-4D	●	4,0	16,0	17,5	50	6
GSX 20500C-4D	●	5,0	20,0	22,0	60	6
GSX 20600C-4D	●	6,0	24,0	–	60	6
GSX 20800C-4D	●	8,0	32,0	–	80	8
GSX 21000C-4D	●	10,0	40,0	–	90	10
GSX 21200C-4D	●	12,0	48,0	–	100	12
GSX 21600C-4D		16,0	64,0	–	120	16
GSX 22000C-4D		20,0	80,0	–	140	20

Endmill Identification (GSX MILL Series)

GSX 2 0100 C - 4D

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length
			S: Sharp Edge C: Gash Land Drilling	

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rear cases, chattering may occur in early milling stages, dissipating after 2 m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. This series is not recommended for grooving.
7. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



Shoulder Milling

Work Material / Cond. / DC (mm)		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		9.000	130	9.000	130	9.000	130	7.000	95	6.500	50	4.500	30	5.400	40	4.500	25
2,0		4.500	180	4.500	180	4.500	180	3.500	120	3.200	70	2.300	40	2.700	50	2.300	35
4,0		2.250	240	2.250	240	2.250	240	1.750	160	1.600	95	1.200	60	1.350	65	1.200	40
6,0		1.500	300	1.500	300	1.500	300	1.150	170	1.050	110	800	70	900	70	800	50
8,0		1.100	260	1.100	260	1.100	260	850	170	800	110	600	70	660	70	600	50
10,0		900	250	900	250	900	250	700	160	650	110	460	70	540	70	460	50
12,0		750	240	750	240	750	240	580	160	520	110	400	70	450	70	400	50
16,0		550	200	550	200	550	200	440	140	400	95	300	55	330	60	300	45
20,0		450	180	450	180	450	180	350	120	320	85	240	45	270	50	240	40
Shoulder cutting	a_p	3,5 DC										3,0 DC					
	a_e	0,08 DC						0,04 DC									

GSX 30000C-1.5D Type

Coated Carbide Grades | GSX Coating

Structual Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎			◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 30100C-1.5D	●	1,0	1,5	2,5	40	4
GSX 30150C-1.5D	●	1,5	2,3	3,3	40	4
GSX 30200C-1.5D	●	2,0	3,0	4,0	40	4
GSX 30250C-1.5D	●	2,5	3,8	4,8	40	4
GSX 30300C-1.5D	●	3,0	4,5	6,0	45	6
GSX 30400C-1.5D	●	4,0	6,0	7,5	45	6
GSX 30500C-1.5D	●	5,0	7,5	9,5	50	6
GSX 30600C-1.5D	●	6,0	9,0	–	50	6
GSX 30700C-1.5D	●	7,0	11,0	13,0	60	8
GSX 30800C-1.5D	●	8,0	12,0	–	60	8
GSX 30900C-1.5D	●	9,0	14,0	16,0	70	10
GSX 31000C-1.5D	●	10,0	15,0	–	70	10
GSX 31200C-1.5D	●	12,0	18,0	–	75	12
GSX 31600C-1.5D		16,0	24,0	–	90	16
GSX 32000C-1.5D		20,0	30,0	–	100	20

Endmill Identification (GSX MILL Series)

GSX **3** **0100** **C** **-** **1.5D**

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



● Shoulder Milling

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	19.600	300	19.600	300	19.600	300	18.300	210	12.700	130	9.000	80	11.000	90	9.000	65
2,0	11.200	410	11.200	410	11.200	410	10.500	280	7.300	170	5.300	100	6.400	120	5.300	90
4,0	6.400	550	6.400	550	6.400	550	6.000	370	4.200	230	3.000	140	3.600	150	3.000	120
6,0	4.600	670	4.600	670	4.600	670	4.300	460	3.000	270	2.200	170	2.700	180	2.200	130
8,0	3.400	670	3.400	670	3.400	670	3.200	460	2.200	270	1.600	170	2.000	180	1.600	130
10,0	2.800	670	2.800	670	2.800	670	2.600	460	1.800	270	1.300	170	1.600	180	1.300	130
12,0	2.300	670	2.300	670	2.300	670	2.200	460	1.500	270	1.100	170	1.300	180	1.100	130
16,0	1.700	550	1.700	550	1.700	550	1.600	370	1.100	230	800	140	1.000	150	800	100
20,0	1.350	490	1.350	490	1.350	490	1.300	330	900	210	650	120	800	130	650	90
Shoulder cutting ap	1,5 DC								1,0 DC							
Shoulder cutting ae	0,05 DC								0,02 DC							

● Grooving

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	19.600	240	19.600	300	19.600	300	18.300	210	12.700	130	9.000	80	11.000	65	4.500	25
2,0	11.200	320	11.200	410	11.200	410	10.500	280	7.300	170	5.300	100	6.400	85	2.650	35
4,0	6.400	450	6.400	550	6.400	550	6.000	370	4.200	230	3.000	140	3.600	100	1.500	50
6,0	4.600	540	4.600	670	4.600	670	4.300	460	3.000	270	2.200	170	2.650	130	1.150	55
8,0	3.400	540	3.400	670	3.400	670	3.200	460	2.200	270	1.600	170	2.000	130	800	55
10,0	2.800	540	2.800	670	2.800	670	2.600	460	1.800	270	1.300	170	1.600	130	650	55
12,0	2.300	540	2.300	670	2.300	670	2.200	460	1.500	270	1.100	170	1.300	130	500	55
16,0	1.700	440	1.700	550	1.700	550	1.600	370	1.100	230	800	140	1.000	110	400	45
20,0	1.350	390	1.350	490	1.350	490	1.300	330	900	210	650	120	800	90	320	40
Grooving ap	0,2 DC		0,5 DC								0,05 DC		0,2 DC			
Grooving ae																

● = Euro stock

GSX MILL Endmills
GSX 30000C-2D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎			◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 30100C-2D	●	1,0	2,5	3,5	40	4
GSX 30150C-2D	●	1,5	3,8	4,8	40	4
GSX 30200C-2D	●	2,0	5,0	6,0	40	4
GSX 30250C-2D	●	2,5	6,3	7,3	40	4
GSX 30300C-2D	●	3,0	7,5	9,0	45	6
GSX 30400C-2D	●	4,0	11,0	12,5	45	6
GSX 30500C-2D	●	5,0	13,0	15,0	50	6
GSX 30600C-2D	●	6,0	13,0	–	50	6
GSX 30700C-2D	●	7,0	16,0	18,0	60	8
GSX 30800C-2D	●	8,0	19,0	–	60	8
GSX 30900C-2D	●	9,0	19,0	21,0	70	10
GSX 31000C-2D	●	10,0	22,0	–	70	10
GSX 31200C-2D	●	12,0	26,0	–	75	12
GSX 31600C-2D		16,0	32,0	–	90	16
GSX 32000C-2D		20,0	40,0	–	100	20

Endmill Identification (GSX MILL Series)

GSX 3 0100 C - 2D

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



Shoulder Milling

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	19.600	300	19.600	300	19.600	300	18.300	210	12.700	130	9.000	80	11.000	90	9.000	65
2,0	11.200	410	11.200	410	11.200	410	10.500	280	7.300	170	5.300	100	6.400	120	5.300	90
4,0	6.400	550	6.400	550	6.400	550	6.000	370	4.200	230	3.000	140	3.600	150	3.000	120
6,0	4.600	670	4.600	670	4.600	670	4.300	460	3.000	270	2.200	170	2.700	180	2.200	130
8,0	3.400	670	3.400	670	3.400	670	3.200	460	2.200	270	1.600	170	2.000	180	1.600	130
10,0	2.800	670	2.800	670	2.800	670	2.600	460	1.800	270	1.300	170	1.600	180	1.300	130
12,0	2.300	670	2.300	670	2.300	670	2.200	460	1.500	270	1.100	170	1.300	180	1.100	130
16,0	1.700	550	1.700	550	1.700	550	1.600	370	1.100	230	800	140	1.000	150	800	100
20,0	1.350	490	1.350	490	1.350	490	1.300	330	900	210	650	120	800	130	650	90
Shoulder cutting a_p	1,5 DC										1,0 DC					
Shoulder cutting a_e	0,05 DC										0,02 DC					

Grooving

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	19.600	240	19.600	300	19.600	300	18.300	210	12.700	130	9.000	80	11.000	65	4.500	25
2,0	11.200	320	11.200	410	11.200	410	10.500	280	7.300	170	5.300	100	6.400	85	2.650	35
4,0	6.400	450	6.400	550	6.400	550	6.000	370	4.200	230	3.000	140	3.600	100	1.500	50
6,0	4.600	540	4.600	670	4.600	670	4.300	460	3.000	270	2.200	170	2.650	130	1.150	55
8,0	3.400	540	3.400	670	3.400	670	3.200	460	2.200	270	1.600	170	2.000	130	800	55
10,0	2.800	540	2.800	670	2.800	670	2.600	460	1.800	270	1.300	170	1.600	130	650	55
12,0	2.300	540	2.300	670	2.300	670	2.200	460	1.500	270	1.100	170	1.300	130	500	55
16,0	1.700	440	1.700	550	1.700	550	1.600	370	1.100	230	800	140	1.000	110	400	45
20,0	1.350	390	1.350	490	1.350	490	1.300	330	900	210	650	120	800	90	320	40
Grooving a_p	0,2 DC		0,5 DC						0,2 DC		0,05 DC		0,2 DC			

GSXSLT 30000C-1.5D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎			◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSXSLT 30100C-1.5D	●	1,0	1,5	2,5	40	4
GSXSLT 30150C-1.5D	●	1,5	2,3	3,3	40	4
GSXSLT 30200C-1.5D	❍	2,0	3,0	4,0	40	4
GSXSLT 30250C-1.5D	❍	2,5	3,8	4,8	40	4
GSXSLT 30300C-1.5D	●	3,0	4,5	6,0	45	6
GSXSLT 30400C-1.5D	●	4,0	6,0	7,5	45	6
GSXSLT 30500C-1.5D	●	5,0	7,5	9,5	50	6
GSXSLT 30600C-1.5D	●	6,0	9,0	–	50	6
GSXSLT 30700C-1.5D	●	7,0	11,0	13,0	60	8
GSXSLT 30800C-1.5D	●	8,0	12,0	–	60	8
GSXSLT 30900C-1.5D	●	9,0	14,0	16,0	70	10
GSXSLT 31000C-1.5D	●	10,0	15,0	–	70	10
GSXSLT 31200C-1.5D	●	12,0	18,0	–	75	12
GSXSLT 31600C-1.5D		16,0	24,0	–	90	16

■ Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. Use step machining of 0.1Dc when drilling stainless steel, heat resistant alloy, and titanium alloy.
5. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



● Shoulder Milling

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	19.600	300	19.600	300	19.600	300	18.300	210	12.700	130	9.000	80	11.000	90	9.000	65
2,0	11.200	410	11.200	410	11.200	410	10.500	280	7.300	170	5.300	100	6.400	120	5.300	90
4,0	6.400	550	6.400	550	6.400	550	6.000	370	4.200	230	3.000	140	3.600	150	3.000	120
6,0	4.600	670	4.600	670	4.600	670	4.300	460	3.000	270	2.200	170	2.700	180	2.200	130
8,0	3.400	670	3.400	670	3.400	670	3.200	460	2.200	270	1.600	170	2.000	180	1.600	130
10,0	2.800	670	2.800	670	2.800	670	2.600	460	1.800	270	1.300	170	1.600	180	1.300	130
12,0	2.300	670	2.300	670	2.300	670	2.200	460	1.500	270	1.100	170	1.300	180	1.100	130
16,0	1.700	550	1.700	550	1.700	550	1.600	370	1.100	230	800	140	1.000	150	800	100
Shoulder cutting ap	1.5 DC										1.0 DC					
Shoulder cutting ae	0.05 DC										0.02 DC					

● Grooving

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	19.600	240	19.600	300	19.600	300	18.300	210	12.700	130	9.000	80	11.000	65	4.500	25
2,0	11.200	320	11.200	410	11.200	410	10.500	280	7.300	170	5.300	100	6.400	85	2.650	35
4,0	6.400	450	6.400	550	6.400	550	6.000	370	4.200	230	3.000	140	3.600	100	1.500	50
6,0	4.600	540	4.600	670	4.600	670	4.300	460	3.000	270	2.200	170	2.650	130	1.150	55
8,0	3.400	540	3.400	670	3.400	670	3.200	460	2.200	270	1.600	170	2.000	130	800	55
10,0	2.800	540	2.800	670	2.800	670	2.600	460	1.800	270	1.300	170	1.600	130	650	55
12,0	2.300	540	2.300	670	2.300	670	2.200	460	1.500	270	1.100	170	1.300	130	500	55
16,0	1.700	440	1.700	550	1.700	550	1.600	370	1.100	230	800	140	1.000	110	400	45
Grooving ap	0,2 DC		0,5 DC						0,2 DC		0,05 DC		0,2 DC			

● Drilling

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	19.600	70	19.600	90	19.600	90	18.300	60	12.700	40	9.000	25	11.000	20	4.500	10
2,0	11.200	90	11.200	120	11.200	120	10.500	80	7.300	50	5.300	30	6.400	25	2.650	15
4,0	6.400	130	6.400	160	6.400	160	6.000	110	4.200	70	3.000	40	3.600	30	1.500	20
6,0	4.600	160	4.600	200	4.600	200	4.300	130	3.000	80	2.200	50	2.650	40	1.150	20
8,0	3.400	160	3.400	200	3.400	200	3.200	130	2.200	80	1.600	50	2.000	40	800	20
10,0	2.800	160	2.800	200	2.800	200	2.600	130	1.800	80	1.300	50	1.600	40	650	20
12,0	2.300	160	2.300	200	2.300	200	2.200	130	1.500	80	1.100	50	1.300	40	500	20
16,0	1.700	130	1.700	160	1.700	160	1.600	110	1.100	70	800	40	1.000	35	400	15

● = Euro stock
❍ = Japan stock

GSX MILL Endmills
GSX 40000C-1.5D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 40100C-1.5D	●	1,0	1,5	2,5	40	4
GSX 40150C-1.5D	●	1,5	2,3	3,3	40	4
GSX 40200C-1.5D	●	2,0	3,0	4,0	40	4
GSX 40250C-1.5D	●	2,5	3,8	4,8	40	4
GSX 40300C-1.5D	●	3,0	4,5	6,0	45	6
GSX 40350C-1.5D	●	3,5	5,3	6,8	45	6
GSX 40400C-1.5D	●	4,0	6,0	7,5	45	6
GSX 40450C-1.5D	●	4,5	6,8	8,3	50	6
GSX 40500C-1.5D	●	5,0	7,5	9,5	50	6
GSX 40550C-1.5D	●	5,5	8,3	10,3	50	6
GSX 40600C-1.5D	●	6,0	9,0	–	50	6
GSX 40700C-1.5D	●	7,0	11,0	13,0	60	8
GSX 40800C-1.5D	●	8,0	12,0	–	60	8
GSX 40900C-1.5D	●	9,0	14,0	16,0	70	10
GSX 41000C-1.5D	●	10,0	15,0	–	70	10
GSX 41200C-1.5D	●	12,0	18,0	–	75	12
GSX 41400C-1.5D		14,0	21,0	24,5	90	16
GSX 41500C-1.5D		15,0	23,0	26,5	90	16
GSX 41600C-1.5D		16,0	24,0	–	90	16
GSX 42000C-1.5D		20,0	30,0	–	100	20

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



Shoulder Milling

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		24.000	470	24.000	470	24.000	470	21.000	290	14.500	180	10.500	120	12.600	120	10.500	85
2,0		12.800	570	12.800	570	12.800	570	12.000	380	8.300	230	6.000	150	7.200	160	6.000	110
4,0		6.800	730	6.800	730	6.800	730	6.400	490	4.400	300	3.200	200	3.800	210	3.200	130
6,0		4.600	780	4.600	780	4.600	780	4.300	520	3.000	320	2.200	210	2.650	220	2.200	150
8,0		3.400	780	3.400	780	3.400	780	3.200	520	2.200	320	1.600	210	2.000	220	1.600	150
10,0		2.800	780	2.800	780	2.800	780	2.600	520	1.800	320	1.300	210	1.500	220	1.300	150
12,0		2.300	780	2.300	780	2.300	780	2.200	520	1.500	320	1.100	210	1.300	220	1.100	150
16,0		1.700	650	1.700	650	1.700	650	1.600	420	1.100	280	800	170	1.000	180	800	120
20,0		1.350	600	1.350	600	1.350	600	1.300	380	900	260	650	150	800	160	650	100
Shoulder cutting	a_p	1,5 DC										1,0 DC					
	a_e	0,05 DC										0,02 DC					

Shoulder Milling (High Speed Machining Centre)

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		60.000	1.200	60.000	1.200	60.000	1.200	60.000	850	60.000	720	48.000	500	32.000	300	–	–
2,0		47.800	2.200	47.800	2.200	47.800	2.200	47.800	1.600	39.800	1.200	31.800	900	15.900	400	–	–
4,0		23.900	2.600	23.900	2.600	23.900	2.600	23.900	1.900	19.900	1.400	15.900	1.100	8.000	490	–	–
6,0		16.000	2.700	16.000	2.700	16.000	2.700	16.000	2.000	13.300	1.500	10.600	1.200	5.300	520	–	–
8,0		12.000	2.700	12.000	2.700	12.000	2.700	12.000	2.000	10.000	1.500	8.000	1.200	4.000	520	–	–
10,0		9.600	2.700	9.600	2.700	9.600	2.700	9.600	2.000	8.000	1.500	6.400	1.200	3.200	520	–	–
12,0		8.000	2.700	8.000	2.700	8.000	2.700	8.000	2.000	6.700	1.500	5.300	1.200	2.700	520	–	–
16,0		6.000	2.200	6.000	2.200	6.000	2.200	6.000	1.600	5.000	1.200	4.000	900	2.000	450	–	–
20,0		4.800	2.000	4.800	2.000	4.800	2.000	4.800	1.400	4.000	1.100	3.200	750	1.600	380	–	–
Shoulder cutting	a_p	1,5 DC										1,0 DC					
	a_e	0,05 DC										0,02 DC					

Grooving

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		24.000	380	24.000	470	24.000	470	21.000	290	14.500	180	10.500	120	12.600	85	5.200	30
2,0		12.800	460	12.800	570	12.800	570	12.000	380	8.300	230	6.000	150	7.200	110	3.000	40
4,0		6.800	580	6.800	730	6.800	730	5.400	490	4.400	300	3.200	200	3.800	130	1.600	55
6,0		4.600	620	4.600	780	4.600	780	4.300	520	3.000	320	2.200	210	2.650	160	1.100	65
8,0		3.400	620	3.400	780	3.400	780	3.200	520	2.200	320	1.600	210	2.000	160	800	65
10,0		2.800	620	2.800	780	2.800	780	2.600	520	1.800	320	1.300	210	1.600	160	650	65
12,0		2.300	620	2.300	780	2.300	780	2.200	520	1.500	320	1.100	210	1.300	160	550	65
16,0		1.700	520	1.700	560	1.700	560	1.600	420	1.100	280	800	170	1.000	130	400	55
20,0		1.350	480	1.350	600	1.350	600	1.300	380	900	260	650	150	800	110	320	50
Grooving	a_p	0,2 DC		0,5 DC						0,2 DC		0,05 DC		0,2 DC			

GSX 40000S-2D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 40100S-2D	●	1,0	2,5	3,5	40	4
GSX 40150S-2D	●	1,5	3,8	4,8	40	4
GSX 40200S-2D	●	2,0	5,0	6,0	40	4
GSX 40250S-2D	●	2,5	6,3	7,3	40	4
GSX 40300S-2D	●	3,0	7,5	9,0	45	6
GSX 40350S-2D	●	3,5	8,8	10,0	45	6
GSX 40400S-2D	●	4,0	11,0	14,0	45	6
GSX 40450S-2D	●	4,5	11,3	12,8	50	6
GSX 40500S-2D	●	5,0	13,0	19,6	50	6
GSX 40550S-2D	●	5,5	13,0	19,6	50	6
GSX 40600S-2D	●	6,0	13,0	–	50	6
GSX 40700S-2D	●	7,0	16,0	21,1	60	8
GSX 40800S-2D	●	8,0	19,0	–	60	8
GSX 40900S-2D	●	9,0	19,0	24,1	70	10
GSX 41000S-2D	●	10,0	22,0	–	70	10
GSX 41200S-2D	●	12,0	26,0	–	75	12
GSX 41600S-2D	●	16,0	32,0	–	90	16
GSX 42000S-2D	●	20,0	40,0	–	100	20

Endmill Identification (GSX MILL Series)

GSX 4 1000 S - 2D

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. This series is not recommended for grooving.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



● Shoulder Milling

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	22.000	360	22.000	360	22.000	360	19.000	220	13.000	140	9.500	90	11.300	90	9.500	65
2,0	11.500	440	11.500	440	11.500	440	11.000	290	7.500	180	5.400	110	6.500	120	5.400	85
4,0	6.000	560	6.000	560	6.000	560	5.800	370	4.000	230	2.900	150	3.400	160	2.900	100
6,0	4.200	600	4.200	600	4.200	600	4.000	400	2.700	240	2.000	160	2.400	170	2.000	120
8,0	3.000	600	3.000	600	3.000	600	2.800	400	2.000	240	1.450	160	1.800	170	1.450	120
10,0	2.500	600	2.500	600	2.500	600	2.350	400	1.600	240	1.200	160	1.450	170	1.200	120
12,0	2.100	600	2.100	600	2.100	600	2.000	400	1.350	240	1.000	160	1.200	170	1.000	120
16,0	1.500	500	1.500	500	1.500	500	1.450	320	1.000	210	750	130	900	140	750	90
20,0	1.200	460	1.200	460	1.200	460	1.150	290	800	200	600	110	700	120	600	75
Shoulder cutting ap	2,0 DC															
Shoulder cutting ae	0,03 DC										0,01 DC					

● Groove Finishing

Work Material / Cond. / DC (mm)	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	22.000	360	22.000	360	22.000	360	19.000	220	13.000	140	9.500	90	11.300	90	9.500	65
2,0	11.500	440	11.500	440	11.500	440	11.000	290	7.500	180	5.400	110	6.500	120	5.400	85
4,0	6.000	560	6.000	560	6.000	560	5.800	370	4.000	230	2.900	150	3.400	160	2.900	100
6,0	4.200	600	4.200	600	4.200	600	4.000	400	2.700	240	2.000	160	2.400	170	2.000	120
8,0	3.000	600	3.000	600	3.000	600	2.800	400	2.000	240	1.450	160	1.800	170	1.450	120
10,0	2.500	600	2.500	600	2.500	600	2.350	400	1.600	240	1.200	160	1.450	170	1.200	120
12,0	2.100	600	2.100	600	2.100	600	2.000	400	1.350	240	1.000	160	1.200	170	1.000	120
16,0	1.500	500	1.500	500	1.500	500	1.450	320	1.000	210	750	130	900	140	750	90
20,0	1.200	460	1.200	460	1.200	460	1.150	290	800	200	600	110	700	120	600	75
Groove finishing ap	1,5 DC															
Groove finishing ae	–0,02 DC															

● = Euro stock

GSX MILL Endmills
GSX 40000C-2D Type

Coated Carbide Grades — GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 40100C-2D	●	1,0	2,0	3,0	40	4
GSX 40150C-2D	●	1,5	3,0	4,0	40	4
GSX 40200C-2D	●	2,0	4,0	5,0	40	4
GSX 40250C-2D	●	2,5	5,0	6,0	40	4
GSX 40300C-2D	●	3,0	6,0	7,5	45	6
GSX 40350C-2D	●	3,5	7,0	8,5	45	6
GSX 40400C-2D	●	4,0	8,0	9,5	45	6
GSX 40450C-2D	●	4,5	9,0	10,5	50	6
GSX 40500C-2D	●	5,0	10,0	12,0	50	6
GSX 40550C-2D	●	5,5	11,0	13,0	50	6
GSX 40600C-2D	●	6,0	12,0	–	50	6
GSX 40700C-2D	●	7,0	14,0	16,0	60	8
GSX 40800C-2D	●	8,0	16,0	–	60	8
GSX 40900C-2D	●	9,0	18,0	20,0	70	10
GSX 41000C-2D	●	10,0	20,0	–	70	10
GSX 41200C-2D	●	12,0	24,0	–	75	12
GSX 41400C-2D		14,0	28,0	31,5	90	16
GSX 41500C-2D		15,0	30,0	33,5	90	16
GSX 41600C-2D	●	16,0	32,0	–	90	16
GSX 42000C-2D	●	20,0	40,0	–	100	20

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
5. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



● Shoulder Milling

Work Material / Cond.	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	24.000	470	24.000	470	24.000	470	21.000	290	14.500	180	10.500	120	12.600	120	10.500	85
2,0	12.800	570	12.800	570	12.800	570	12.000	380	8.300	230	6.000	150	7.200	160	6.000	110
4,0	6.800	730	6.800	730	6.800	730	6.400	490	4.400	300	3.200	200	3.800	210	3.200	130
6,0	4.600	780	4.600	780	4.600	780	4.300	520	3.000	320	2.200	210	2.650	220	2.200	150
8,0	3.400	780	3.400	780	3.400	780	3.200	520	2.200	320	1.600	210	2.000	220	1.600	150
10,0	2.800	780	2.800	780	2.800	780	2.600	520	1.800	320	1.300	210	1.500	220	1.300	150
12,0	2.300	780	2.300	780	2.300	780	2.200	520	1.500	320	1.100	210	1.300	220	1.100	150
16,0	1.700	650	1.700	650	1.700	650	1.600	420	1.100	280	800	170	1.000	180	800	120
20,0	1.350	600	1.350	600	1.350	600	1.300	380	900	260	650	150	800	160	650	100
Shoulder cutting ap	1,5 DC										1,0 DC					
Shoulder cutting ae	0,05 DC										0,02 DC					

● Shoulder Milling (High Speed Machining Centre)

Work Material / Cond.	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	60.000	1.200	60.000	1.200	60.000	1.200	60.000	850	60.000	720	48.000	500	32.000	300	–	–
2,0	47.800	2.200	47.800	2.200	47.800	2.200	47.800	1.600	39.800	1.200	31.800	900	15.900	400	–	–
4,0	23.900	2.600	23.900	2.600	23.900	2.600	23.900	1.900	19.900	1.400	15.900	1.100	8.000	490	–	–
6,0	16.000	2.700	16.000	2.700	16.000	2.700	16.000	2.000	13.300	1.500	10.600	1.200	5.300	520	–	–
8,0	12.000	2.700	12.000	2.700	12.000	2.700	12.000	2.000	10.000	1.500	8.000	1.200	4.000	520	–	–
10,0	9.600	2.700	9.600	2.700	9.600	2.700	9.600	2.000	8.000	1.500	6.400	1.200	3.200	520	–	–
12,0	8.000	2.700	8.000	2.700	8.000	2.700	8.000	2.000	6.700	1.500	5.300	1.200	2.700	520	–	–
16,0	6.000	2.200	6.000	2.200	6.000	2.200	6.000	1.600	5.000	1.200	4.000	900	2.000	450	–	–
20,0	4.800	2.000	4.800	2.000	4.800	2.000	4.800	1.400	4.000	1.100	3.200	750	1.600	380	–	–
Shoulder cutting ap	1,5 DC										1,0 DC					
Shoulder cutting ae	0,05 DC										0,02 DC					

● Grooving

Work Material / Cond.	Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0	24.000	380	24.000	470	24.000	470	21.000	290	14.500	180	10.500	120	12.600	85	5.200	30
2,0	12.800	460	12.800	570	12.800	570	12.000	380	8.300	230	6.000	150	7.200	110	3.000	40
4,0	6.800	580	6.800	730	6.800	730	5.400	490	4.400	300	3.200	200	3.800	130	1.600	55
6,0	4.600	620	4.600	780	4.600	780	4.300	520	3.000	320	2.200	210	2.650	160	1.100	65
8,0	3.400	620	3.400	780	3.400	780	3.200	520	2.200	320	1.600	210	2.000	160	800	65
10,0	2.800	620	2.800	780	2.800	780	2.600	520	1.800	320	1.300	210	1.600	160	650	65
12,0	2.300	620	2.300	780	2.300	780	2.200	520	1.500	320	1.100	210	1.300	160	550	65
16,0	1.700	520	1.700	560	1.700	560	1.600	420	1.100	280	800	170	1.000	130	400	55
20,0	1.350	480	1.350	600	1.350	600	1.300	380	900	260	650	150	800	110	320	50
Grooving ap	0,2 DC		0,5 DC						0,2 DC		0,05 DC		0,2 DC			

GSX 40000C-3D Type

Coated Carbide Grades | GSX Coating

Structual Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 40100C-3D	●	1,0	3,0	4,0	40	4
GSX 40150C-3D	●	1,5	4,5	5,5	40	4
GSX 40200C-3D	●	2,0	6,0	7,0	40	4
GSX 40250C-3D	●	2,5	7,5	8,5	40	4
GSX 40300C-3D	●	3,0	9,0	10,5	50	6
GSX 40400C-3D	●	4,0	12,0	13,5	50	6
GSX 40500C-3D	●	5,0	15,0	17,0	50	6
GSX 40600C-3D	●	6,0	18,0	–	50	6
GSX 40800C-3D	●	8,0	24,0	–	70	8
GSX 41000C-3D	●	10,0	30,0	–	90	10
GSX 41200C-3D	●	12,0	36,0	–	90	12
GSX 41600C-3D	●	16,0	48,0	–	110	16
GSX 42000C-3D		20,0	60,0	–	120	20

Endmill Identification (GSX MILL Series)

GSX **4** **0100** **C** - **2D / 3D**

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rear cases, chattering may occur in early milling stages, dissipating after 2 m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



● Shoulder Milling

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		21.000	360	21.000	360	21.000	360	19.000	220	13.000	140	9.000	90	10.500	90	9.000	65
2,0		10.500	360	10.500	360	10.500	360	9.600	290	7.500	180	4.500	110	5.200	120	4.500	85
4,0		5.200	500	5.200	500	5.200	500	4.800	370	4.000	280	2.250	150	2.600	160	2.250	100
6,0		3.500	560	3.500	560	3.500	560	3.200	400	2.700	300	1.500	160	1.700	170	1.500	120
8,0		2.600	520	2.600	520	2.600	520	2.400	400	2.000	300	1.100	160	1.300	170	1.100	120
10,0		2.100	500	2.100	500	2.100	500	1.900	400	1.600	300	900	160	1.000	160	900	120
12,0		1.750	500	1.750	500	1.750	500	1.600	400	1.350	300	750	150	850	160	750	120
16,0		1.300	420	1.300	420	1.300	420	1.200	330	1.000	260	550	120	650	140	550	100
20,0		1.050	380	1.050	380	1.050	380	950	290	800	230	450	110	500	120	450	90
Shoulder cutting	a_p	2,5 DC										2,0 DC					
	a_e	< ø3: 0,05 DC , ≤ ø3< ø8: 0,1 DC , ≤ ø8: 0,15 DC								0,02 DC							

● Grooving

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		16.600	140	16.600	140	16.600	140	15.500	100	10.500	100	7.500	70	9.400	60	3.750	20
2,0		9.500	160	9.500	160	9.500	160	9.000	180	6.200	120	4.500	90	5.200	80	2.250	30
4,0		5.200	160	5.200	180	5.200	180	4.800	160	3.400	110	2.200	65	2.600	70	1.250	25
6,0		3.500	160	3.500	200	3.500	200	3.200	160	2.550	120	1.500	65	1.700	70	950	25
8,0		2.600	160	2.600	200	2.600	200	2.400	160	1.900	120	1.100	65	1.300	70	700	25
10,0		2.100	160	2.100	200	2.100	200	1.900	160	1.500	120	900	65	1.000	70	550	25
12,0		1.750	160	1.750	200	1.750	200	1.600	160	1.250	120	750	65	850	70	450	25
16,0		1.300	160	1.300	200	1.300	200	1.200	160	950	120	550	65	650	70	350	25
20,0		1.050	160	1.050	200	1.050	200	950	160	750	120	450	65	500	70	280	25
Grooving	a_p	0,1 DC		0,2 DC								0,05 DC		0,1 DC			

● = Euro stock

GSX MILL Endmills
GSX 40000C-4D Type

Coated Carbide Grades | GSX Coating

Structural Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



DC	Tolerance
D ≤ 3,0	0 – 0,015
3,0 < D ≤ 12	0 – 0,020
12,0 < D	0 – 0,030

Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSX 40100C-4D	●	1,0	4,0	5,0	40	4
GSX 40150C-4D	●	1,5	6,0	7,0	40	4
GSX 40200C-4D	●	2,0	8,0	9,0	40	4
GSX 40250C-4D	●	2,5	10,0	11,0	50	4
GSX 40300C-4D	●	3,0	12,0	13,5	50	6
GSX 40400C-4D	●	4,0	16,0	17,5	50	6
GSX 40500C-4D	●	5,0	20,0	22,0	60	6
GSX 40600C-4D	●	6,0	24,0	–	60	6
GSX 40800C-4D	●	8,0	32,0	–	80	8
GSX 41000C-4D	●	10,0	40,0	–	90	10
GSX 41200C-4D	●	12,0	48,0	–	100	12
GSX 41600C-4D	●	16,0	64,0	–	120	16
GSX 42000C-4D		20,0	80,0	–	140	20

Endmill Identification (GSX MILL Series)

GSX 4 0100 C - 4D

Series Code	No. of Teeth	Diameter	Cutting Edge	Cutting Edge Length

S: Sharp Edge
C: Gash Land Drilling

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. In rear cases, chattering may occur in early milling stages, dissipating after 2m of cutting.
5. If chattering is a problem, reduce the spindle speed and feed rate indicated in the table below by the same ratio, or reduce the depth of cut.
6. This series is not recommended for grooving.
7. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



Shoulder Milling

Work Material / Cond.		Structural Steel		Carbon Steel (150 to 250HB)		Cast Iron		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (35 to 45HRC)		Hardened Steel (45 to 55HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
1,0		9.000	140	9.000	140	9.000	140	7.000	80	6.500	60	4.500	40	5.400	40	4.500	40
2,0		4.500	140	4.500	140	4.500	140	3.500	100	3.200	80	2.300	55	2.700	55	2.300	40
4,0		2.250	200	2.250	200	2.250	200	1.750	120	1.600	100	1.200	60	1.350	50	1.200	35
6,0		1.500	250	1.500	250	1.500	250	1.150	160	1.050	140	800	65	900	45	800	35
8,0		1.100	220	1.100	220	1.100	220	850	160	800	130	600	65	660	45	600	35
10,0		900	210	900	210	900	210	700	140	650	120	460	65	540	45	460	35
12,0		750	200	750	200	750	200	580	140	520	110	400	65	450	45	400	35
16,0		550	170	550	170	550	170	440	120	400	95	300	55	330	45	300	35
20,0		450	150	450	150	450	150	350	100	320	80	240	50	270	45	240	35
Shoulder cutting	a_p	3,5 DC										3,0 DC					
	a_e	< ø3: 0,04 DC , 3 ≤ øD< 8: 0,08 DC , 8 ≤ øD: 0,1 DC										0,02 DC					

GSXVL 4000-2.5D Type

Coated Carbide Grades | GSX Coating

Structual Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



Grade: ACF20

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSXVL 4020-2.5D	●	2,0	5	6,5	50	4
GSXVL 4030-2.5D	●	3,0	8	9,5	50	6
GSXVL 4040-2.5D	●	4,0	10	11,5	50	6
GSXVL 4050-2.5D	●	5,0	13	14,5	60	6
GSXVL 4060-2.5D	●	6,0	15	–	60	6
GSXVL 4070-2.5D	❍	7,0	18	20,0	70	8
GSXVL 4080-2.5D	●	8,0	20	–	80	8
GSXVL 4090-2.5D	●	9,0	23	25,0	90	10
GSXVL 4100-2.5D	●	10,0	25	–	90	10
GSXVL 4110-2.5D	❍	11,0	28	30,5	90	12
GSXVL 4120-2.5D	●	12,0	30	–	90	12
GSXVL 4140-2.5D	●	14,0	35	37,5	110	16
GSXVL 4150-2.5D	❍	15,0	38	41,0	110	16
GSXVL 4160-2.5D	●	16,0	40	–	115	16
GSXVL 4180-2.5D	●	18,0	45	48,0	120	20
GSXVL 4200-2.5D	●	20,0	50	–	125	20
GSXVL 4250-2.5D	❍	25,0	63	–	140	25

SAFE-LOCK™ Applicable Endmills

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
GSXVL 4120S-2.5D	❍	12,0	30	–	90	12
GSXVL 4140S-2.5D	❍	14,0	35	37,5	110	16
GSXVL 4150S-2.5D	❍	15,0	38	41,0	110	16
GSXVL 4160S-2.5D	❍	16,0	40	–	115	16
GSXVL 4180S-2.5D	❍	18,0	45	48,0	120	20
GSXVL 4200S-2.5D	❑	20,0	50	–	125	20
GSXVL 4250S-2.5D	❑	25,0	63	–	140	25

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.

● Shoulder Milling

Work Material / Cond. / DC (mm)	Carbon Steel, Cast Iron (150 to 250HB)		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (40 to 50HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy (20 to 45HRC)	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
2,0	13.000	1.000	10.000	800	8.000	700	10.000	580	5.000	200
4,0	9.600	1.200	8.000	1.000	6.000	800	5.500	650	3.000	230
6,0	6.800	1.500	5.600	1.200	4.200	900	3.800	680	2.100	240
8,0	5.200	1.600	4.400	1.300	3.200	950	2.800	650	1.600	250
10,0	4.200	1.500	3.500	1.200	2.600	800	2.300	600	1.300	210
12,0	3.500	1.400	3.000	1.200	2.200	700	1.900	550	1.100	180
14,0	3.000	1.200	2.600	1.100	1.800	600	1.600	500	900	150
16,0	2.700	1.100	2.200	1.000	1.600	600	1.400	480	760	130
18,0	2.400	1.000	2.000	900	1.400	570	1.300	450	680	120
20,0	2.200	900	1.700	800	1.200	550	1.100	400	600	100
25,0	1.700	680	1.400	630	1.000	450	890	310	480	82
Shoulder cutting a_p	1,5 DC									
Shoulder cutting a_e	0,1 DC				0,05 DC		0,1 DC		0,05 DC	



● Shoulder Milling

Work Material / Cond. / DC (mm)	Carbon Steel, Cast Iron (150 to 250HB)		Alloy Steel (25 to 35HRC)		Tempered Steel, Hardened Steel (40 to 50HRC)		Stainless Steel		Heat Resistive Steel, Titanium Alloy (20 to 45HRC)	
	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
2,0	13.000	750	10.000	550	8.400	500	6.500	300	4.000	140
4,0	8.200	800	6.000	600	5.200	500	4.000	330	2.000	130
6,0	6.100	1.100	4.000	600	3.500	580	2.700	350	1.350	150
8,0	4.600	1.000	3.000	580	2.600	570	2.000	330	1.000	140
10,0	3.600	1.000	2.400	550	2.100	510	1.600	200	800	130
12,0	3.100	920	2.000	500	1.700	450	1.300	280	660	110
14,0	2.600	750	1.700	450	1.500	400	1.100	250	570	100
16,0	2.300	670	1.500	420	1.300	350	1.000	230	500	90
18,0	2.000	620	1.300	380	1.100	330	900	200	430	80
20,0	1.900	600	1.200	360	1.000	320	800	180	380	70
25,0	1.500	470	1.000	300	790	250	640	140	300	55
Grooving a_p	1,0 DC				0,2 DC		0,3 DC		0,2 DC	

● = Euro stock
❍ = Japan stock
❑ = Delivery on request

Anti-Vibration MILL with R. Corner
GSXVL 4000-R-2.5D Type

Coated Carbide Grades | GSX Coating

Structal Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	◎	◎	◎	◎	◎	○		◎	○	○			



Endmills

(mm)

Cat. No.	Stock	DC	RE	APMX	LU	LF	DMM
GSXVL 4030-R02-2.5D	●	3,0	0,2	8	9,5	50	6
GSXVL 4030-R05-2.5D	❍	3,0	0,5	8	9,5	50	6
GSXVL 4040-R02-2.5D	❍	4,0	0,2	10	11,5	50	6
GSXVL 4040-R05-2.5D	●	4,0	0,5	10	11,5	50	6
GSXVL 4040-R10-2.5D	❍	4,0	1,0	10	11,5	50	6
GSXVL 4050-R02-2.5D	●	5,0	0,2	13	14,5	60	6
GSXVL 4050-R05-2.5D	❍	5,0	0,5	13	14,5	60	6
GSXVL 4050-R10-2.5D	❍	5,0	1,0	13	14,5	60	6
GSXVL 4060-R03-2.5D	❍	6,0	0,3	15	–	60	6
GSXVL 4060-R05-2.5D	●	6,0	0,5	15	–	60	6
GSXVL 4060-R10-2.5D	●	6,0	1,0	15	–	60	6
GSXVL 4060-R15-2.5D	❍	6,0	1,5	15	–	60	6
GSXVL 4080-R03-2.5D	❍	8,0	0,3	20	–	80	8
GSXVL 4080-R05-2.5D	●	8,0	0,5	20	–	80	8
GSXVL 4080-R10-2.5D	●	8,0	1,0	20	–	80	8
GSXVL 4080-R15-2.5D	●	8,0	1,5	20	–	80	8
GSXVL 4080-R20-2.5D	❍	8,0	2,0	20	–	80	8
GSXVL 4100-R03-2.5D	●	10,0	0,3	25	–	90	10
GSXVL 4100-R05-2.5D	●	10,0	0,5	25	–	90	10
GSXVL 4100-R10-2.5D	●	10,0	1,0	25	–	90	10
GSXVL 4100-R15-2.5D	❍	10,0	1,5	25	–	90	10
GSXVL 4100-R20-2.5D	❍	10,0	2,0	25	–	90	10
GSXVL 4120-R05-2.5D	●	12,0	0,5	30	–	90	12
GSXVL 4120-R10-2.5D	●	12,0	1,0	30	–	90	12
GSXVL 4120-R15-2.5D	●	12,0	1,5	30	–	90	12
GSXVL 4120-R20-2.5D	●	12,0	2,0	30	–	90	12
GSXVL 4120-R30-2.5D	❍	12,0	3,0	30	–	90	12
GSXVL 4160-R10-2.5D	●	16,0	1,0	40	–	115	16
GSXVL 4160-R15-2.5D	●	16,0	1,5	40	–	115	16
GSXVL 4160-R20-2.5D	●	16,0	2,0	40	–	115	16
GSXVL 4160-R30-2.5D	❍	16,0	3,0	40	–	115	16
GSXVL 4200-R10-2.5D	●	20,0	1,0	50	–	125	20
GSXVL 4200-R15-2.5D	❍	20,0	1,5	50	–	125	20
GSXVL 4200-R20-2.5D	❍	20,0	2,0	50	–	125	20
GSXVL 4200-R30-2.5D	●	20,0	3,0	50	–	125	20
GSXVL 4250-R10-2.5D	❍	25,0	1,0	63	–	140	25
GSXVL 4250-R15-2.5D	❍	25,0	1,5	63	–	140	25
GSXVL 4250-R20-2.5D	❍	25,0	2,0	63	–	140	25
GSXVL 4250-R30-2.5D	❍	25,0	3,0	63	–	140	25

Grade: ACF20

Endmills

SAFE-λOCK™

Applicable Endmills

(mm)

Cat. No.	Stock	DC	RE	APMX	LU	LF	DMM
GSXVL 4120S-R05-2.5D	❍	12,0	0,5	30	–	90	12
GSXVL 4120S-R10-2.5D	❑	12,0	1,0	30	–	90	12
GSXVL 4120S-R15-2.5D	❑	12,0	1,5	30	–	90	12
GSXVL 4120S-R20-2.5D	❑	12,0	2,0	30	–	90	12
GSXVL 4120S-R30-2.5D	❑	12,0	3,0	30	–	90	12
GSXVL 4160S-R10-2.5D	❑	16,0	1,0	40	–	115	16
GSXVL 4160S-R15-2.5D	❑	16,0	1,5	40	–	115	16
GSXVL 4160S-R20-2.5D	❑	16,0	2,0	40	–	115	16
GSXVL 4160S-R30-2.5D	❑	16,0	3,0	40	–	115	16
GSXVL 4200S-R10-2.5D	❑	20,0	1,0	50	–	125	20
GSXVL 4200S-R15-2.5D	❑	20,0	1,5	50	–	125	20
GSXVL 4200S-R20-2.5D	❑	20,0	2,0	50	–	125	20
GSXVL 4200S-R30-2.5D	❑	20,0	3,0	50	–	125	20
GSXVL 4250S-R10-2.5D	❑	25,0	1,0	63	–	140	25
GSXVL 4250S-R15-2.5D	❑	25,0	1,5	63	–	140	25
GSXVL 4250S-R20-2.5D	❑	25,0	2,0	63	–	140	25
GSXVL 4250S-R30-2.5D	❍	25,0	3,0	63	–	140	25

Grade: ACF20

Recommended Cutting Conditions

1. For stable machining performance use rigid, high-precision machines and holders.
2. Use air blowing when dry machining.
3. Use wet machining for stainless steel, heat resistant alloy, and titanium alloy applications.
4. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.



Shoulder Milling and Grooving

Work Material / Cond. / DC (mm)		Carbon Steel, Cast Iron (150 to 250HB) Spindle Speed (rpm)	Carbon Steel, Cast Iron (150 to 250HB) Feed Rate (mm/min)	Alloy Steel (25 to 35HRC) Spindle Speed (rpm)	Alloy Steel (25 to 35HRC) Feed Rate (mm/min)	Tempered Steel, Hardened Steel (40 to 50HRC) Spindle Speed (rpm)	Tempered Steel, Hardened Steel (40 to 50HRC) Feed Rate (mm/min)	Stainless Steel Spindle Speed (rpm)	Stainless Steel Feed Rate (mm/min)	Heat Resistive Steel, Titanium Alloy (20 to 45HRC) Spindle Speed (rpm)	Heat Resistive Steel, Titanium Alloy (20 to 45HRC) Feed Rate (mm/min)
2,0		9.000	720	6.000	430	4.000	320	5.500	320	2.600	120
4,0		6.600	800	4.500	450	3.000	380	4.000	320	2.000	120
6,0		4.800	960	3.000	480	2.500	380	3.000	480	1.200	120
8,0		3.600	1.000	2.200	610	2.000	400	2.000	520	1.000	140
10,0		2.800	1.000	1.800	610	1.500	400	1.700	550	800	160
12,0		2.400	950	1.500	550	1.200	380	1.500	500	700	140
14,0		2.200	880	1.300	490	1.000	360	1.200	430	600	130
16,0		1.800	650	1.100	420	800	300	1.000	360	500	120
18,0		1.600	580	1.000	360	750	270	900	340	450	110
20,0		1.400	500	900	330	700	250	820	300	400	100
Shoulder cutting	a_p	1,5 DC									
	a_e	0,1 DC				0,05 DC		0,1 DC		0,05 DC	
Grooving	a_p	1,0 DC				0,2 DC		0,3 DC		0,2 DC	

Corner Radius Selection

DC	RE0,2	RE0,3	RE0,5	RE1,0	RE1,5	RE2,0	RE3,0
3	❑		❑				
4	❑		❑	❑			
5	❑		❑	❑			
6		❑	❑	❑	❑		
8		❑	❑	❑	❑	❑	
10		❑	❑	❑	❑	❑	
12			❑	❑	❑	❑	❑
16				❑	❑	❑	❑
20				❑	❑	❑	❑
25				❑	❑	❑	❑

SSEH Series

☞ J 24, J 39

SSEH Radius

■ Characteristics and Applications

- Steep helix (45° helix) improves sharpness.
- Combination of unique flute design and semi-mirrored surface improves chip evacuation and adhesion resistance.
- Ultra-smooth coating with improved hardness and heat resistance combined with tough carbide substrate improves tool life when working with heat resistant alloys.
- Unique, smooth radius shape mitigates cutting impact and improves fracture resistance.
- Both coated and uncoated types are available in stock to meet various conditions.

■ Application Examples

- Inconel 718 (Side Milling)



Tool Diameter: ø 6 × R1
Cutting Conditions: v_c = 20 m/min, f_t = 0,025 mm/t, a_p = 5 mm, a_e = 0,5 mm, wet

- Inconel 713 (Side Milling)

SSEH 4100W-R10	Competitor's Product
	
Tool Diameter : ø 10 x R1 Cutting Conditions : v_c= 32 m/min, f_t = 0,018 mm/t a_p = 20 mm, a_e = 0,8 m, Dry	



In Sumitomo Electric Hardmetal tests, the special coating with excellent adhesion resistance provided less cutting edge adhesion than the competitor's product and enabled fracturefree machining.
The competitor's product suffered from edge adhesion leading to breakage.





☞ J 23, J 39

SSEH Radius Anti-vibration Type

■ Characteristics and Applications

- New anti-vibration type added to the SSEH type endmill for exotic alloys.
- Builds on the same features of existing endmills by adding an irregular lead for exceptionally good anti-vibration performance.
- Compatible with wide range of milling for exotic alloys including SUS, Inconel, and titanium.
- Reduces chattering for high-speed, high-feed cutting.
- Both coated and uncoated types are available in stock to meet various conditions.

Irregular Pitch + Irregular Lead



■ Application Examples

- Surface Roughness Comparison

SSEH Anti-vibration Type

Good Surface Quality
Ra 0,37 µm Rz 1,86 µm



Conventional Tool

Surface shows chattering
Ra 1,52 µm Rz 6,45 µm

Work Material: X5CrNi1810 (Surface Milling)
Tool Diameter: ø 12 mm
Cutting Conditions: n = 1.300 rpm, v_f = 300 mm/min
a_p = 18 mm, a_e = 1,2 mm
Equipment: BT50

● = Euro stock
❑ = Delivery on request

Anti-Vibration MILL with R. Corner
SSEHVL 4000W-R Type

Coated Carbide Grades | GS HARD Coating

Structual Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
○	○	○	○	○				◎	◎				



Grade: ACW52

■ Endmills

(mm)

Cat. No.	Stock	DC	RE	LU	LF	DMM
SSEHVL 4045W-R05	●	4,5	0,5	12	50	6
SSEHVL 4045W-R10	●	4,5	1,0	12	50	6
SSEHVL 4050W-R05	●	5,0	0,5	13	60	6
SSEHVL 4050W-R10	●	5,0	1,0	13	60	6
SSEHVL 4060W-R10	●	6,0	1,0	13	60	6
SSEHVL 4080W-R10	●	8,0	1,0	19	80	8
SSEHVL 4100W-R10	●	10,0	1,0	22	90	10
SSEHVL 4100W-R30	●	10,0	3,0	22	90	10
SSEHVL 4120W-R10	●	12,0	1,0	26	90	12
SSEHVL 4120W-R30	●	12,0	3,0	26	90	12
SSEHVL 4160W-R10	●	16,0	1,0	32	115	16
SSEHVL 4160W-R30	●	16,0	3,0	32	115	16
SSEHVL 4200W-R10	❑	20,0	1,0	40	125	20
SSEHVL 4200W-R30	❑	20,0	3,0	40	125	20
SSEHVL 4250W-R10	❑	25,0	1,0	50	140	25
SSEHVL 4250W-R30	❑	25,0	3,0	50	140	25

SAFE-λOCK™

Applicable Endmills

■ Endmills

(mm)

Cat. No.	Stock	DC	RE	LU	LF	DMM
SSEHVL 4120WS-R10	❑	12,0	1,0	26	90	12
SSEHVL 4120WS-R30	❑	12,0	3,0	26	90	12
SSEHVL 4160WS-R10	❑	16,0	1,0	32	115	16
SSEHVL 4160WS-R30	❑	16,0	3,0	32	115	16
SSEHVL 4200WS-R10	❑	20,0	1,0	40	125	20
SSEHVL 4200WS-R30	❑	20,0	3,0	40	125	20
SSEHVL 4250WS-R10	❑	25,0	1,0	50	140	25
SSEHVL 4250WS-R30	❑	25,0	3,0	50	140	25

■ Diameter and Corner Radius Selection Range

DC	RE0,5	RE1,0	RE3,0
4,5	●	●	
5	●	●	
6		●	
8		●	
10		●	●
12		●	●
16		●	●
20		❑	❑
25		❑	❑

■ Recommended Cutting Conditions

1. For stable machining, a more rigid machine is recommended.
2. Wet machining is recommended for stainless steel and heat resistant alloy applications.
3. If cutting noise and vibration are present, please change the cutting conditions accordingly.



● Shoulder Milling

Work Material / Cond.		Stainless Steel		Titanium Alloy		Heat Resistive Steel	
DC (mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
4,5		3.500	350	3.500	280	2.100	170
5,0		3.200	380	3.200	320	1.900	190
6,0		2.700	430	2.700	320	1.600	190
8,0		2.000	400	2.000	280	1.200	170
10,0		1.600	380	1.600	260	1.000	160
12,0		1.300	360	1.300	230	800	140
16,0		1.000	320	1.000	200	600	120
20,0		800	260	800	160	480	100
25,0		640	200	640	130	380	80
Shoulder cutting	a_p	1,5 DC					
	a_e	0,1 DC		0,05 DC		0,05 DC	

● Grooving

Work Material / Cond.		Stainless Steel		Titanium Alloy		Heat Resistive Steel	
DC(mm)		Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)	Spindle Speed (rpm)	Feed Rate (mm/min)
4,5		4,200	200	3,900	270	1,400	100
5,0		3,800	240	3,500	300	1,300	120
6,0		3,200	260	2,900	300	1,100	140
8,0		2,400	240	2,200	270	800	120
10,0		1,900	220	1,700	250	650	110
12,0		1,600	200	1,400	230	550	100
16,0		1,200	130	1,100	200	400	80
20,0		950	95	890	90	320	60
25,0		760	75	700	70	250	50
Grooving	a_p	0,3 DC		0,2 DC		0,15 DC	

SSEH 4000W-R Type

4 Flutes Endmills with Radius Corner and HAIMER's SAFE-LOCK™ Applicable Endmills

Coated Carbide Grades	GS HARD Coating	Structual Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
		○	○	○	○	○				◎	◎				



Grade: ACW52

SAFE-LOCK™

Applicable Endmills

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
SSEH 4045W-R05	●	4,5	0,5	12	50	6
SSEH 4050W-R05	●	5,0	0,5	13	60	6
SSEH 4060W-R10	●	6,0	1,0	13	60	6
SSEH 4080W-R10	●	8,0	1,0	19	80	8
SSEH 4100W-R10	●	10,0	1,0	22	90	10
SSEH 4100W-R30	●	10,0	3,0	22	90	10
SSEH 4120W-R10	●	12,0	1,0	26	90	12
SSEH 4120W-R30	●	12,0	3,0	26	90	12
SSEH 4160W-R10	●	16,0	1,0	32	115	16
SSEH 4160W-R30	●	16,0	3,0	32	115	16
SSEH 4200W-R10	❍	20,0	1,0	40	125	20
SSEH 4200W-R30	❍	20,0	3,0	40	125	20
SSEH 4250W-R10	❍	25,0	1,0	50	140	25
SSEH 4250W-R30	❍	25,0	3,0	50	140	25

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
SSEH 4120WS-R10	❍	12,0	1,0	26	90	12
SSEH 4120WS-R30	❍	12,0	3,0	26	90	12
SSEH 4160WS-R10	❍	16,0	1,0	32	115	16
SSEH 4160WS-R30	❍	16,0	3,0	32	115	16
SSEH 4200WS-R10	❍	20,0	1,0	40	125	20
SSEH 4200WS-R30	❍	20,0	3,0	40	125	20
SSEH 4250WS-R10	❍	25,0	1,0	50	140	25
SSEH 4250WS-R30	❍	25,0	3,0	50	140	25

■ Diameter and Corner Radius Selection Range

DC	RE0,5	RE1,0	RE3,0
4,5	●		
5	●		
6		●	
8		●	
10		●	●
12		●	●
16		●	●
20		❍	❍
25		❍	❍



■ Recommended Cutting Conditions

1. For stable machining, a more rigid machine is recommended.
2. Wet machining is recommended for stainless steel and heat resistant alloy applications.
3. If cutting noise and vibration are present, please change the cutting conditions accordingly.

● Shoulder Milling

Work Material / Cond. / DC (mm)	Stainless Steel Spindle Speed (rpm)	Stainless Steel Feed Rate (mm/min)	Titanium Alloy Spindle Speed (rpm)	Titanium Alloy Feed Rate (mm/min)	Heat Resistive Steel Spindle Speed (rpm)	Heat Resistive Steel Feed Rate (mm/min)
4,5	3.500	350	3.500	280	2.100	170
5,0	3.200	380	3.200	320	1.900	190
6,0	2.700	430	2.700	320	1.600	190
8,0	2.000	400	2.000	280	1.200	170
10,0	1.600	380	1.600	260	1.000	160
12,0	1.300	360	1.300	230	800	140
16,0	1.000	320	1.000	200	600	120
20,0	800	260	800	160	480	100
25,0	640	200	640	130	380	80
Shoulder cutting ap	1,5 DC					
Shoulder cutting ae	0,1 DC		0,05 DC		0,05 DC	

● Grooving

Work Material / Cond. / DC (mm)	Stainless Steel Spindle Speed (rpm)	Stainless Steel Feed Rate (mm/min)	Titanium Alloy Spindle Speed (rpm)	Titanium Alloy Feed Rate (mm/min)	Heat Resistive Steel Spindle Speed (rpm)	Heat Resistive Steel Feed Rate (mm/min)
4,5	4,200	200	3,900	270	1,400	100
5,0	3,800	240	3,500	300	1,300	120
6,0	3,200	260	2,900	300	1,100	140
8,0	2,400	240	2,200	270	800	120
10,0	1,900	220	1,700	250	650	110
12,0	1,600	200	1,400	230	550	100
16,0	1,200	130	1,100	200	400	80
20,0	950	95	890	90	320	60
25,0	760	75	700	70	250	50
Grooving ap	0,3 DC		0,2 DC		0,15 DC	

● = Euro stock
❍ = Japan stock

GS MILL Series
GSRE 4000SF Type

Coated carbide grade: **ACZ20W**



Helix angle : 40°

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	CHW	DMM
GSRE 4060 SF	●	6,0	13	50	0,3	6
4070 SF	●	7,0	16	60	0,3	8
4080 SF	●	8,0	19	60	0,4	8
4090 SF	●	9,0	19	70	0,4	10
4100 SF	●	10,0	22	70	0,5	10
GSRE 4110 SF	●	11,0	22	75	0,5	12
4120 SF	●	12,0	26	75	0,6	12
4140 SF	●	14,0	26	90	0,6	16
4160 SF	●	16,0	32	90	0,8	16
4180 SF	●	18,0	32	100	0,8	20
GSRE 4200 SF	●	20,0	38	100	1,0	20

Recommended :

(1) Cutting performance is improved when using a high rigidity machine.

(2) Speeds and feeds should be reduced when there is any excessive vibration or strange noise during the operation.



Recommended Cutting Conditions

● Shoulder cutting

Material / Cutting data / Tool Dia. (mm)	Carbon steel (HB150–250)		Cast iron		Alloy steel, Prehardened steel (HRC25–35)		Hardened steel (HRC40–50)		Stainless steel		Heat resistant alloys Titanium alloy	
	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)
1	4.800	1.200	5.800	1.500	3.200	380	2.600	400	4.300	250	1.600	90
2	4.100	1.200	5.000	1.500	2.700	380	2.200	400	4.500	250	1.350	90
3	3.600	1.200	4.500	1.500	2.400	380	2.000	400	4.000	250	1.250	90
4	3.200	1.200	4.000	1.500	2.100	380	1.800	400	3.500	250	1.050	90
5	2.800	1.200	2.500	1.500	1.900	380	1.600	400	3.200	250	1.000	100
6	2.600	1.200	3.000	1.400	1.700	380	1.500	400	2.900	250	900	100
8	2.400	1.200	2.900	1.400	1.600	400	1.300	400	2.600	250	800	100
10	2.200	1.100	2.600	1.300	1.300	380	1.100	350	2.200	200	700	100
12	1.800	900	2.200	1.100	1.200	380	1.000	350	2.000	180	600	100
16	1.400	700	1.800	900	1.000	380	900	350	1.800	150	550	100
20	1.400	700	1.700	800	850	380	800	350	1.600	150	500	100
Shoulder cutting a_p	1,5 DC						1,5 DC					
Shoulder cutting a_e	0,5 DC						0,3 DC					



● Slotting

Material / Cutting data / Tool Dia. (mm)	Carbon steel (HB150–250)		Cast iron		Alloy steel, Prehardened steel (HRC25–35)		Hardened steel (HRC40–50)		Stainless steel		Heat resistant alloys Titanium alloy	
	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)
1	3.600	900	4.300	1.100	2.400	300	1.700	260	4.200	250	1.100	60
2	3.000	900	3.700	1.100	2.000	280	1.500	260	3.600	250	900	60
3	2.700	900	3.400	1.100	1.800	280	1.350	260	3.200	250	800	60
4	2.400	900	3.000	1.100	1.600	280	1.200	260	2.800	250	700	60
5	2.100	900	2.600	1.100	1.400	280	1.100	270	2.500	250	650	65
6	2.000	900	2.300	1.100	1.300	280	1.000	270	2.300	250	600	70
8	1.800	900	2.200	1.100	1.200	300	900	270	2.100	250	550	70
10	1.600	800	2.000	1.100	1.000	290	750	240	1.800	180	450	65
12	1.350	650	1.650	850	900	280	700	240	1.600	160	400	65
16	1.200	550	1.500	750	800	280	600	230	1.400	140	350	60
20	1.050	500	1.350	700	700	280	550	210	1.250	125	300	60
Slotting a_p	1,0 DC						0,5 DC					

Coated carbide grade: **ACF07C**



Helix angle : 50˚
Corner : Edge with honing

DC	Tolerance (mm)
D ≤ 3,0	0 – - 0,015
3,0 < D	0 – - 0,030

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
GSH 4010 SF	●	1,0	3	50	6
4015 SF	●	1,5	4	50	6
4020 SF	●	2,0	6	50	6
GSH 6030 SF	●	3,0	8	50	6
6040 SF	●	4,0	11	50	6
6050 SF	●	5,0	12	50	6
6060 SF	●	6,0	13	50	6
6080 SF	●	8,0	19	60	8
6100 SF	●	10,0	22	70	10
6120 SF	●	12,0	26	75	12
GSH 8160 SF	●	16,0	32	90	16
8200 SF	●	20,0	38	100	20

Recommended :
(1) Cutting performance is improved when using a high rigidity machine.
(2) Speeds and feeds should be reduced when there is any excessive vibration or strange noise during the operation.

Recommended Cutting Conditions

● Conventional Milling Operations

Material / Cutting data / Tool Dia. (mm)	Alloy steel, Prehardened steel (–HRC35)		Heat treated alloy steel, hardened steel (HRC35–45)		Hardened steel (HRC45–55)		Hardened steel (HRC55–60)		Hardened steel (HRC60–65)		Hardened steel (HRC65–)	
	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)
1	20.000	540	20.000	390	15.600	260	12.300	160	11.100	140	7.800	95
2	19.000	1.100	17.200	770	13.400	530	10.500	320	9.500	270	6.700	190
3	15.000	2.150	13.400	1.540	10.400	1.050	8.200	650	7.400	540	5.200	380
4	11.200	2.400	10.000	1.740	7.800	1.180	6.100	730	5.600	600	3.900	420
5	9.000	2.700	8.000	1.930	6.200	1.300	4.900	810	4.400	670	3.100	470
6	7.500	2.700	6.700	1.930	5.200	1.300	4.100	810	3.700	670	2.600	470
8	5.600	2.700	5.000	1.930	3.900	1.300	3.050	810	2.800	670	1.950	470
10	4.500	2.700	4.000	1.930	3.100	1.300	2.450	810	2.200	670	1.550	470
12	3.750	2.700	3.350	1.930	2.600	1.300	2.050	810	1.850	670	1.300	470
16	2.800	2.500	2.500	1.800	1.950	1.220	1.530	760	1.400	630	980	440
20	2.250	2.100	2.000	1.540	1.550	1.050	1.230	650	1.100	540	780	380
Shoulder cutting a_p	1–1,5 DC				1–1,5 DC				1–1,5 DC			
Shoulder cutting a_e	0,1 DC				0,05 DC				0,02 DC			
Slotting a_p	0,1 DC				0,05 DC				–0,05 DC (Max 0,5)			

● HSC Machining Centre Operations

Material / Cutting data / Tool Dia. (mm)	Alloy steel, Prehardened steel (–HRC35)		Heat treated alloy steel, hardened steel (HRC35–45)		Hardened steel (HRC45–55)		Hardened steel (HRC55–60)		Hardened steel (HRC60–65)	
	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)
1	48.000	1.250	48.000	1.250	48.000	1.250	48.000	930	38.000	700
2	48.000	2.850	48.000	2.850	48.000	2.850	36.000	1.600	24.000	1.000
3	32.000	4.900	32.000	4.900	32.000	4.900	24.000	2.740	16.000	1.700
4	24.000	5.200	24.000	5.200	24.000	5.200	18.000	2.900	12.000	1.800
5	19.200	5.800	19.200	5.800	19.200	5.800	14.300	3.200	9.600	2.000
6	16.000	5.800	16.000	5.800	16.000	5.800	12.000	3.200	8.000	2.000
8	12.000	5.800	12.000	5.800	12.000	5.800	9.000	3.200	6.000	2.000
10	9.600	5.800	9.600	5.800	9.600	5.800	7.200	3.200	4.800	2.000
12	8.000	5.800	8.000	5.800	8.000	5.800	6.000	3.200	4.000	2.000
16	6.000	5.400	6.000	5.400	6.000	5.400	4.500	3.000	3.000	1.900
20	4.800	4.600	4.800	4.600	4.800	4.600	3.600	2.580	2.400	1.600
Shoulder cutting a_p	1–1,5 DC		1–1,5 DC				1–1,5 DC		1–1,5 DC	
Shoulder cutting a_e	0,1 DC		0,05 DC				0,02 DC		0,12 DC	



● = Euro stock

AURORA COAT Series



Features

Sumitomo Electric's "AURORA" COAT is a high hardness, low coefficient layer of "Diamond Like Carbon" (DLC).

Other than producing excellent surface finish for machining of Aluminium and non-ferrous metals, DLC coat can be used for dry cutting and is environmental friendly.

Characteristics / Application

- Very smooth AURORA COAT results in low adhesion as well as good surface finish
- With lower cutting forces and high rigidity, this series is suitable for low rigidity machine
- Available in 2 and 4 flutes square type as well as ballnose type endmills

Product Range

Series	No. of teeth	Shape	Diameter
ASM2000DL	2	Square 	ø 2 – ø 16
ASM4000DL	4	Square 	ø 2 – ø 16
SNB2000DL	2	Ballnose 	ø 2 – ø 16 (R1 – R8)

Efficiency



● Performance Comparison



Work Material: A5052
Tool: ASM4100DL, ø 10 mm 4 teeth
Cutting Conditions: v_c = 200 m/min, n = 6,300 rpm, v_f = 1300 mm/min
f_t = 0,05 mm/tooth, a_p = 10 mm, a_e = 1,0 mm
Down Cut

● Surface Finish Comparison



Work Material: A5052
Tool: ASM4100DL, ø 10 mm 4 teeth
Cutting Conditions: v_c = 200 m/min, n = 6,300 rpm, v_f = 1300 mm/min
f_t = 0,05 mm/tooth, a_p = 10 mm, a_e = 1,0 mm
Down Cut

AURORA Coated Spiral Endmills
ASM 2000/4000 DL Type

2 4

DLC coated carbide grade: DL1000



■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
ASM 2020 DL	●	2,0	6	40	4
2030 DL	●	3,0	10	45	6
2040 DL	●	4,0	12	45	6
2050 DL	●	5,0	15	50	6
ASM 2060 DL	●	6,0	15	50	6
2080 DL	●	8,0	18	60	8
2100 DL	●	10,0	22	71	10
ASM 2120 DL	●	12,0	25	75	12
2160 DL	●	16,0	32	90	16

ASM 4020 DL	●	2,0	6	40	4
4030 DL	●	3,0	10	45	6
4040 DL	●	4,0	12	45	6
4050 DL	●	5,0	15	50	6
ASM 4060 DL	●	6,0	15	50	6
4080 DL	●	8,0	18	60	8
4100 DL	●	10,0	22	71	10
ASM 4120 DL	●	12,0	25	75	12
4160 DL	●	16,0	32	90	16

AURORA Coated Spiral Endmills
ASM 2000/4000 DL-R Type

With Radius Corner -R

2 4

DLC coated carbide grade: DL1000



■ Endmills

(mm)

Cat. No.	Stock	DC	RE	APMX	LF	DMM
ASM 2080 DL-R10	❑	8,0	1,0	18	60	8
2080 DL-R20	❑	8,0	2,0	18	60	8
ASM 2100 DL-R10	❑	10,0	1,0	22	71	10
2100 DL-R20	❑	10,0	2,0	22	71	10
ASM 2120 DL-R20	❑	12,0	2,0	25	75	12
2120 DL-R30	❑	12,0	3,0	25	75	12
ASM 2160 DL-R30	❑	16,0	3,0	32	90	16

ASM 4080 DL-R10	❑	8,0	1,0	18	60	8
4080 DL-R20	❑	8,0	2,0	18	60	8
ASM 4100 DL-R10	❑	10,0	1,0	22	71	10
4100 DL-R20	❑	10,0	2,0	22	71	10
ASM 4120 DL-R20	❑	12,0	2,0	25	75	12
4120 DL-R30	❑	12,0	3,0	25	75	12
ASM 4160 DL-R30	❑	16,0	3,0	32	90	16



■ Recommended Cutting Conditions

Recommended :

(1) Cutting performance is improved when using a high rigidity machine.

(2) Speeds and feeds should be reduced when there is any excessive vibration or strange noise during the operation.

(3) In case of chatter first check the cutting conditions.

Work Material		Aluminium Alloy							
Cutting data / DC (mm)		Wet (Emulsion)				Dry			
		Side Milling (4 teeth)		Groove Milling (4 teeth)		Side Milling (4 teeth)		Groove Milling (4 teeth)	
		Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)
2,0		40.000	1.400	28.000	280	40.000	980	28.000	200
3,0		32.000	2.000	22.000	400	32.000	1.400	22.000	280
4,0		26.000	2.600	18.000	520	26.000	1.800	18.000	360
5,0		20.000	2.600	14.000	520	20.000	1.800	14.000	360
6,0		17.000	2.700	12.000	540	17.000	1.900	12.000	370
8,0		13.000	2.700	9.000	540	13.000	1.900	9.000	370
10,0		11.000	2.800	7.200	560	11.000	2.000	7.200	390
12,0		8.500	2.800	6.000	560	8.500	2.000	6.000	390
16,0		6.400	2.800	4.500	560	6.400	2.000	4.500	390
Depth and wide of cut	a_p	1,5 DC		1,0 DC		1,5 DC		0,5 DC	
	a_e	0,2 DC		(DC)		0,2 DC		(DC)	

● = Euro stock ❑ = Delivery on request

ZX Coated Long Fast Helix Endmills
LHHM 4000/6000/8000 ZX Type

4 6 8

Coated carbide grade: ACZ10M



Helix angle : 45°
Corner : Edge with honing

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
LHHM 4030 ZX	❑	3,0	12	55	6
4040 ZX	❑	4,0	15	60	6
4050 ZX	❑	5,0	18	60	6
LHHM 6060 ZX	❑	6,0	18	60	6
6080 ZX	❑	8,0	25	75	8
6100 ZX	❑	10,0	30	80	10
6120 ZX	❑	12,0	30	100	12
LHHM 8160 ZX	❑	16,0	50	105	16
8200 ZX	❑	20,0	55	120	20
8250 ZX	❑	25,0	65	140	25
8300 ZX	❑	30,0	75	160	32



Recommended conditions

(Shoulder processing) a_p = 1,5 x øD

a_e =0,025(HRC56~65) ~ 0,2(below HRC25) x øD

DC \ Material		Carbon steel, Alloy steel (BelowHRC25)	Carbon steel, Alloy steel (BelowHRC45)	Hardened steel (BelowHRC65)	Cast iron
3,0–5,0	v_c	200–**250**–300	100–**150**–200	80–**100**–120	60–**75**–90
	f_t	0,030–0,060	0,022–0,037	0,007–0,015	0,030–0,060
6,0–12,0	v_c	200–**250**–300	100–**150**–200	80–**100**–120	40–**50**–60
	f_t	0,061–0,090	0,037–0,067	0,015–0,028	0,060–0,165
16,0–32,0	v_c	200–**250**–300	100–**150**–200	80–**100**–120	40–**50**–60
	f_t	0,090–0,098	0,067–0,075	0,028–0,038	0,187–0,262



v_c =m/min f_t =mm/tooth

ZX Coated Extra Long Fast Helix Endmills
EHHM 4000/6000/8000 ZX Type

4 6 8

Coated carbide grade: ACZ10M



Helix angle : 45°
Corner : Edge with honing

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
EHHM 4030 ZX	❑	3,0	20	60	6
4040 ZX	❑	4,0	25	65	6
4050 ZX	❑	5,0	30	70	6
EHHM 6060 ZX	❑	6,0	30	70	6
6080 ZX	❑	8,0	40	90	8
6100 ZX	❑	10,0	50	100	10
6120 ZX	❑	12,0	50	120	12
EHHM 8160 ZX	❑	16,0	70	140	16
8200 ZX	❑	20,0	85	165	20
8250 ZX	❑	25,0	100	185	25
8300 ZX	❑	30,0	110	205	32
8320 ZX	❑	32,0	110	205	32



Recommended conditions

(Shoulder processing) a_p = 1,5 x øD

a_e =0,025(HRC56~65) ~ 0,2(below HRC25) x øD

DC \ Material		Carbon steel, Alloy steel (BelowHRC25)	Carbon steel, Alloy steel (BelowHRC45)	Hardened steel (BelowHRC65)	Cast iron
3,0–5,0	v_c	200–**250**–300	100–**150**–200	80–**100**–120	100–**120**–150
	f_t	0,020–0,040	0,015–0,025	0,005–0,010	0,020–0,040
6,0–12,0	v_c	200–**250**–300	100–**150**–200	80–**100**–120	100–**120**–150
	f_t	0,041–0,060	0,025–0,045	0,01 0–0,019	0,040–0,110
16,0–32,0	v_c	200–**250**–300	100–**150**–200	80–**100**–120	100–**120**–150
	f_t	0,060–0,065	0,045–0,050	0,019–0,025	0,125–0,175



v_c =m/min f_t =mm/tooth

SSUP MILL Series

Features

ZX coated general use endmill for high efficient slotting and side cutting of steels, stainless steels, high temperature alloys and cast irons.

Unique flute design and strong cutting edge ensure excellent chip control even when rough machining slots.

Feed rate up to 2000 mm/min with and without coolant

Advantages

- Unique flute design for excellent chip removal
- Extra strong cutting edge
- 40° high helix angle for high feed rates
- New ZX coating for excellent wear resistance
- Smooth cutting
- Excellent rigid wide cutting land

SSUP 4000ZX-R Series
Diameter and Corner Radius Range

DC \ RE	RE0,2	RE0,3	RE0,5	RE1,0	RE1,5	RE2.0	RE3.0
3	●		●				
4	●		●	●			
5	●		●	●			
6		●	●	●	●		
8		●	●	●	●		
10		●	●	●	●	●	
12			●	●	●	●	●
16				●	●	●	●
20				●	●	●	●

Performance

● Feed rate comparisons

<Results>
Stable milling at double the feed rate



Work material: X155CrVMo12 1 (HB220) Tool : ø 10 mm, 4 flute Cutting length: 10m	Cutting conditions : n = 2250 rpm, v_c = 80 m/min a_p =10 mm, a_e =10mm Dry

● Chip control



<Results>
Excellent chip control



Work material: X155CrVMo12 1 (HB220) Tool : ø 10 mm, 4 flute	Cutting conditions : n = 2250 rpm, v_c = 80 m/min f_t = 0,147 mm/tooth (v_f = 1500 mm/min) a_p = 10 mm, a_e = 10 mm, Dry

● Wear resistance comparison - slotting

<Results>
Half the edge wear - double the tool life



Work material: 40CrMoV5 H_RC40 Tool : ø 10 mm, 4 flute Cutting length: 7,5 m	Cutting conditions : n = 1600 rpm, v_c = 50m/min f_t = 0,04 mm/tooth (v_f = 500 mm/min) a_p = 5mm, a_e = 10 mm, Dry

● Wear resistance comparison - shoulder cutting

<Results>
Half the edge wear - double the tool life



Work material: X155CrVMo12 1 (HB220) Tool : ø 10mm, 4 flute Cutting length: 15 m	Cutting conditions : n = 1750 rpm, v_c = 55 m/min f_t = 0,086 mm/tooth (v_f = 600 mm/min) a_p =15 mm, a_e = 1 mm, Dry

● = Euro stock
❑ = Delivery on request

ZX Coated SSUP MILL
SSUP 4000ZX Type

Coated carbide grade: ACZ50M



Helix angle : 40°
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 3,0	– 0,014 – 0,028
3,0 < D ≤ 6,0	– 0,020 – 0,038
6,0 < D	– 0,025 – 0,047

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
SSUP 4020 ZX	●	2,0	6	50	4
4030 ZX	●	3,0	8	50	6
4040 ZX	●	4,0	11	50	6
4050 ZX	●	5,0	13	60	6
SSUP 4060 ZX	●	6,0	13	60	6
4070 ZX	●	7,0	16	70	8
4080 ZX	●	8,0	19	80	8
4090 ZX	●	9,0	19	90	10
4100 ZX	●	10,0	22	90	10
SSUP 4110 ZX	●	11,0	22	90	12
4120 ZX	●	12,0	26	90	12
4140 ZX	●	14,0	26	110	16
4150 ZX	❑	15,0	26	110	16
SSUP 4160 ZX	●	16,0	32	115	16
4180 ZX	❑	18,0	32	120	20
4200 ZX	●	20,0	38	125	20

ZX Coated SSUP MILL
SSUP 4000ZX-R Type

With Radius Corner

Coated carbide grade: ACZ50M



Helix angle : 40°
Corner : Sharp edge

-R

DC	Tolerance (mm)
D ≤ 3,0	– 0,014 – 0,028
3,0 < D ≤ 6,0	– 0,020 – 0,038
6,0 < D	– 0,025 – 0,047

Endmills

(mm)

Cat. No.	Stock	DC	RE	APMX	LF	DMM
SSUP 4030 ZX-R02	●	3,0	0,2	8	50	6
4030 ZX-R05	❑	3,0	0,5	8	50	6
SSUP 4040 ZX-R02	●	4,0	0,2	11	50	6
4040 ZX-R05	●	4,0	0,5	11	50	6
4040 ZX-R10	❑	4,0	1,0	11	50	6
SSUP 4050 ZX-R02	●	5,0	0,2	13	60	6
4050 ZX-R05	●	5,0	0,5	13	60	6
4050 ZX-R10	❑	5,0	1,0	13	60	6
SSUP 4060 ZX-R03	●	6,0	0,3	13	60	6
4060 ZX-R05	●	6,0	0,5	13	60	6
4060 ZX-R10	●	6,0	1,0	13	60	6
4060 ZX-R15	❑	6,0	1,5	13	60	6
SSUP 4080 ZX-R03	●	8,0	0,3	13	80	8
4080 ZX-R05	●	8,0	0,5	13	80	8
4080 ZX-R10	●	8,0	1,0	19	80	8
4080 ZX-R15	❑	8,0	1,5	19	80	8
4080 ZX-R20	❑	8,0	2,0	19	80	8
SSUP 4100 ZX-R03	●	10,0	0,3	22	90	10
4100 ZX-R05	●	10,0	0,5	22	90	10
4100 ZX-R10	●	10,0	1,0	22	90	10
4100 ZX-R15	❑	10,0	1,5	22	90	10
4100 ZX-R20	❑	10,0	2,0	22	90	10
SSUP 4120 ZX-R05	●	12,0	0,5	26	90	12
4120 ZX-R10	●	12,0	1,0	26	90	12
4120 ZX-R15	●	12,0	1,5	26	90	12
4120 ZX-R20	❑	12,0	2,0	26	90	12
4120 ZX-R30	❑	12,0	3,0	26	90	12
SSUP 4160 ZX-R10	●	16,0	1,0	32	115	16
4160 ZX-R15	●	16,0	1,5	32	115	16
4160 ZX-R20	❑	16,0	2,0	32	115	16
4160 ZX-R30	❑	16,0	3,0	32	115	16
SSUP 4200 ZX-R10	●	20,0	1,0	38	125	20
4200 ZX-R15	❑	20,0	1,5	38	125	20
4200 ZX-R20	❑	20,0	2,0	38	125	20
4200 ZX-R30	❑	20,0	3,0	38	125	20

Recommended Cutting Conditions

Material / Cutting data / DC (mm)		Carbon steel, Cast iron (HB150–250) Speed (rpm)	Feed (mm/min)	Alloy steel, Prehardened steel (HRC25–35) Speed (rpm)	Feed (mm/min)	Hardened steel (HRC40–50) Speed (rpm)	Feed (mm/min)	Stainless steel Speed (rpm)	Feed (mm/min)	Heat resistant alloys Titanium alloy (HRC20–45) Speed (rpm)	Feed (mm/min)
2		9000	720	6000	430	4000	320	5500	320	2600	120
4		6600	800	4500	450	3000	380	4000	320	2000	120
6		4800	960	3000	480	2500	380	3000	480	1200	120
8		3600	1000	2200	610	2000	400	2000	520	1000	140
10		2800	1000	1800	610	1500	400	1700	550	800	160
12		2400	950	1500	550	1200	380	1500	500	700	140
14		2200	880	1300	490	1000	360	1200	430	600	130
16		1800	650	1100	420	800	300	1000	360	500	120
18		1600	580	1000	360	750	270	900	340	450	110
20		1400	500	900	330	700	250	820	300	400	100
Shoulder cutting	a_p	1,5 DC									
	a_e	0,1 DC				0,05 DC		0,1 DC		0,05 DC	
Slotting	a_p	1,0 DC				0,2 DC		0,3 DC		0,2 DC	



(1) Cutting performance is improved when using a high rigidity machine.
(2) Speeds and feeds should be reduced when slotting some stainless steels.
(3) In case of chatter first check the cutting conditions.

GSX MILL Ball Endmills
GSXB 20000 Type

Coated Carbide Grades | GSX Coating

Structual Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
◎	◎	◎	◎	◎	◎	○		◎	○	○			



Coated carbide grade: **ACB20**

Endmill Identification (GSXB Type)

GSXB 2 0200

- GSXB: Series Code
- 2: No. of Teeth
- 0200: Radius of Ballnose

Endmills

(mm)

Cat. No.	Stock	RE	DC	APMX	LU	LF	DMM
GSXB 20020	●	0,20	0,4	0,6	0,8	50	4
GSXB 20030	●	0,30	0,6	0,9	1,2	50	4
GSXB 20050	●	0,50	1,0	1,5	2,0	50	4
GSXB 20075	●	0,75	1,5	2,5	3,0	50	4
GSXB 20100	●	1,00	2,0	3,0	4,0	60	6
GSXB 20125	●	1,25	2,5	4,0	5,0	60	6
GSXB 20150	●	1,50	3,0	4,5	6,0	60	6
GSXB 20200	●	2,00	4,0	6,0	8,0	70	6
GSXB 20250	●	2,50	5,0	7,5	10,0	80	6
GSXB 20300	●	3,00	6,0	9,0	–	80	6
GSXB 20350	●	3,50	7,0	11,0	20,0	90	8
GSXB 20400	●	4,00	8,0	12,0	–	90	8
GSXB 20500	●	5,00	10,0	15,0	–	100	10
GSXB 20600	●	6,00	12,0	18,0	–	110	12
GSXB 20700	●	7,00	14,0	21,0	38,0	110	16
GSXB 20800	●	8,00	16,0	24,0	–	140	16
GSXB 20900	●	9,00	18,0	27,0	50,0	140	20
GSXB 21000	●	10,00	20,0	30,0	–	160	20
GSXB 21250		12,50	25,0	38,0	–	180	25
GSXB 21500		15,00	30,0	45,0	80,0	180	32

New "Global Standard" Mills
Ball nose type with 2 teeth

Recommended Cutting Conditions

(1) If cutting noise and vibration are present, please change the cutting conditions accordingly.
(2) If the machine is not designed to achieve the recommended spindle speed, please use the max. spindle speed available.



●Radius Milling

Work Material / Cutting Conditions / RE (mm)	Carbon Steel, Alloy Steel (Below 25HRC) Spindle Speed (rpm)	Carbon Steel, Alloy Steel (Below 25HRC) Feed Rate (mm/min)	Carbon Steel, Alloy Steel (Below 50HRC) Spindle Speed (rpm)	Carbon Steel, Alloy Steel (Below 50HRC) Feed Rate (mm/min)	Cast Iron Special Cast Iron Spindle Speed (rpm)	Cast Iron Special Cast Iron Feed Rate (mm/min)	Stainless Steel Titanium Alloy Spindle Speed (rpm)	Stainless Steel Titanium Alloy Feed Rate (mm/min)
0,20	50.000	2.100	35.000	1.150	50.000	2.100	50.000	1.750
0,30	50.000	2.500	35.000	1.350	50.000	2.500	50.000	2.100
0,50	50.000	3.000	35.000	1.600	50.000	3.000	50.000	2.500
0,75	35.000	3.000	24.000	1.650	35.000	3.200	34.000	2.500
1,00	27.500	3.000	19.000	1.700	35.000	3.900	26.000	2.500
1,25	22.500	3.000	15.500	1.700	28.000	3.900	21.000	2.500
1,50	19.000	3.000	13.000	1.700	24.000	3.900	17.500	2.500
2,00	17.000	3.800	12.000	2.100	20.000	4.100	15.000	2.700
2,50	15.500	4.300	11.000	2.200	18.000	4.600	12.000	2.500
3,00	14.000	4.700	10.500	2.500	16.500	5.300	10.500	2.500
3,50	12.500	4.200	9.000	2.100	14.000	4.500	9.000	2.200
4,00	11.000	3.500	7.900	1.900	12.500	4.000	7.800	1.900
5,00	9.000	2.800	6.300	1.500	10.500	3.300	6.300	1.500
6,00	7.500	2.400	5.200	1.250	8.700	2.800	5.200	1.250
7,00	6.400	2.100	4.500	1.100	7.400	2.400	4.500	1.100
8,00	5.600	1.800	3.900	950	6.500	2.100	3.900	950
9,00	5.000	1.600	3.500	850	5.800	1.900	3.500	850
10,00	4.500	1.450	3.100	750	5.200	1.700	3.150	750
12,50	3.600	1.150	2.500	600	4.200	1.350	2.500	600
15,00	3.000	960	2.100	500	3.500	1.150	2.100	500
Depth and wide of cut a_p	0,02 DC		0,02 DC		0,02 DC		0,02 DC	
Depth and wide of cut a_e	0,05 DC		0,05 DC		0,05 DC		0,05 DC	

● = Euro stock

DLC (Diamond Like Carbon) Coating

2

DLC coated carbide grade: DL1200



Helix angle : 30°

Endmills

(mm)

Cat. No.	Stock	RE	DC	APMX	LU	LF	DMM
SNB 2020 DL	●	1,0	2,0	3	5	60	6
2030 DL	●	1,5	3,0	4,5	8	80	6
SNB 2040 DL	●	2,0	4,0	6	12	80	6
2050 DL	●	2,5	5,0	7,5	14	90	6
SNB 2060 DL	●	3,0	6,0	9	-	100	6
2080 DL	●	4,0	8,0	12	-	100	8
2100 DL	●	5,0	10,0	15	-	120	10
SNB 2120 DL	●	6,0	12,0	18	-	120	12
2160 DL	●	8,0	16,0	24	-	160	16

Characteristics / Application

- Very smooth AURORA COAT results in low adhesion as well as good surface finish
- With lower cutting forces and high rigidity, this series is suitable for low rigidity machine



Recommended Cutting Conditions

Work Material		Aluminum Alloy			
Cutting data / RE (mm)		Wet (Emulsion)		Dry	
		Speed (rpm)	Feed (mm/min)	Speed (rpm)	Feed (mm/min)
1,0		48.000	1.500	48.000	1.000
1,5		48.000	2.100	48.000	1.500
2,0		31.000	2.800	31.000	2.000
2,5		24.000	2.800	24.000	2.000
3,0		20.000	2.800	20.000	2.000
4,0		15.000	2.800	15.000	2.000
5,0		13.000	3.000	13.000	2.100
6,0		10.000	3.000	10.000	2.100
8,0		7.700	3.000	7.700	2.100
Depth and wide of cut	a_p	1,5 DC		1,0 DC	
	a_e	0,2 DC		(DC)	

● = Euro stock

ASM 2000 Type

2

Carbide grade: H1 (Micrograin)



Helix angle : 30˚
Corner : Sharp edge

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
ASM 2020	❑	2,0	6	40	4
2030	❑	3,0	10	45	6
2040	❑	4,0	12	45	6
2050	❑	5,0	15	50	6
ASM 2060	❑	6,0	15	50	6
2080	❑	8,0	18	60	8
2100	❑	10,0	22	71	10
ASM 2120	❑	12,0	25	75	12
2160		16,0	32	90	16

Recommended Conditions

(Shoulder processing) a_p =1,5 x DC
a_e =0,1 x DC

DC \ Material		Al-alloy	Cast iron
1 – 2,5	v_c	100-**200**-300	100-**120**-150
	f_t	0,004–0,017	0,008–0,020
3 – 5	v_c	100-**200**-300	100-**120**-150
	f_t	0,018–0,036	0,027–0,060
6 – 12	v_c	100-**200**-300	100-**120**-150
	f_t	0,038–0,070	0,065–0,157
14 – 16	v_c	100-**200**-300	100-**120**-150
	f_t	0,075–0,125	0,160–0,250



v_c =m/min f_t =mm/tooth

❑ = Delivery on request

Anti-Vibration Type Radius Endmills for Exotic Alloys

SSEHVL 4000-R Type

Uncoated Carbide | 4

Structal Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
								○	◎				



Helix Angle

DC	Tolerance (mm)
D ≤ 6,0	– 0,028 – 0,043
6,0 < D	– 0,033 – 0,052

Carbide grade: EH520

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
SSEHVL 4045-R05	●	4,5	0,5	12	50	6
SSEHVL 4045-R10	●	4,5	1,0	12	50	6
SSEHVL 4050-R05	●	5,0	0,5	13	60	6
SSEHVL 4050-R10	●	5,0	1,0	13	60	6
SSEHVL 4060-R10	●	6,0	1,0	13	60	6
SSEHVL 4080-R10	●	8,0	1,0	19	80	8
SSEHVL 4100-R10	●	10,0	1,0	22	90	10
SSEHVL 4100-R30	●	10,0	3,0	22	90	10
SSEHVL 4120-R10	●	12,0	1,0	26	90	12
SSEHVL 4120-R30	●	12,0	3,0	26	90	12
SSEHVL 4160-R10	●	16,0	1,0	32	115	16
SSEHVL 4160-R30	●	16,0	3,0	32	115	16

Radius Endmills for Exotic Alloys

SSEH 4000-R Type

Uncoated Carbide | 4

Structal Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45~55 HRC	Hardened Steel 55~60 HRC	Hardened Steel 60~65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	Graphite
								○	◎				



Helix Angle

DC	Tolerance (mm)
D ≤ 6,0	– 0,028 – 0,043
6,0 < D	– 0,033 – 0,052

Carbide grade: EH520

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LU	LF	DMM
SSEH 4045-R05	●	4,5	0,5	12	50	6
SSEH 4045-R10	●	4,5	1,0	12	50	6
SSEH 4050-R05	●	5,0	0,5	13	60	6
SSEH 4050-R10	●	5,0	1,0	13	60	6
SSEH 4060-R10	●	6,0	1,0	13	60	6
SSEH 4080-R10	●	8,0	1,0	19	80	8
SSEH 4100-R10	●	10,0	1,0	22	90	10
SSEH 4100-R30	●	10,0	3,0	22	90	10
SSEH 4120-R10	●	12,0	1,0	26	90	12
SSEH 4120-R30	●	12,0	3,0	26	90	12
SSEH 4160-R10	●	16,0	1,0	32	115	16
SSEH 4160-R30	●	16,0	3,0	32	115	16

■ Characteristics / Application

1. For stable machining, a more rigid machine is recommended.
2. Wet machining is recommended for stainless steel and heat resistant alloy applications.
3. If cutting noise and vibration are present, please change the cutting conditions accordingly.



● Shoulder Milling

Work Material / Cond. / DC (mm)	Stainless Steel Spindle Speed (rpm)	Stainless Steel Feed Rate (mm/min)	Titanium Alloy Spindle Speed (rpm)	Titanium Alloy Feed Rate (mm/min)	Heat Resistive Steel Spindle Speed (rpm)	Heat Resistive Steel Feed Rate (mm/min)
4.5	2.300	120	4.600	370	1.600	130
5.0	2.000	130	4.100	410	1.500	150
6.0	1.700	130	3.400	400	1.200	140
8.0	1.300	130	2.600	360	900	130
10.0	1.000	130	2.100	340	700	110
12.0	800	110	1.700	300	600	100
16.0	600	90	1.300	260	500	100
Shoulder cutting a_p	1,5 DC					
Shoulder cutting a_e	0,1 DC		0,05 DC		0,05 DC	

● Grooving

Work Material / Cond. / DC (mm)	Stainless Steel Spindle Speed (rpm)	Stainless Steel Feed Rate (mm/min)	Titanium Alloy Spindle Speed (rpm)	Titanium Alloy Feed Rate (mm/min)	Heat Resistive Steel Spindle Speed (rpm)	Heat Resistive Steel Feed Rate (mm/min)
4,5	1.800	50	3.200	250	1.300	110
5,0	1.600	50	2.900	290	1.200	120
6,0	1.400	50	2.400	290	1.000	120
8,0	1.000	50	1.800	250	700	90
10,0	800	50	1.400	230	600	100
12,0	600	50	1.200	210	500	90
16,0	500	40	900	180	400	80
Grooving a_p	0,3 DC		0,2 DC		0,15 DC	

● Shoulder Milling

Work Material / Cond. / DC (mm)	Stainless Steel Spindle Speed (rpm)	Stainless Steel Feed Rate (mm/min)	Titanium Alloy Spindle Speed (rpm)	Titanium Alloy Feed Rate (mm/min)	Heat Resistive Steel Spindle Speed (rpm)	Heat Resistive Steel Feed Rate (mm/min)
4,5	1.800	90	3.500	280	1.400	110
5,0	1.600	100	3.200	320	1.300	130
6,0	1.300	100	2.700	320	1.100	130
8,0	1.000	100	2.000	280	800	110
10,0	800	100	1.600	260	600	100
12,0	700	100	1.300	230	500	90
16,0	500	80	1.000	200	400	80
Shoulder cutting a_p	1,5 DC					
Shoulder cutting a_e	0,1 DC		0,05 DC		0,05 DC	

● Grooving

Work Material / Cond. / DC (mm)	Stainless Steel Spindle Speed (rpm)	Stainless Steel Feed Rate (mm/min)	Titanium Alloy Spindle Speed (rpm)	Titanium Alloy Feed Rate (mm/min)	Heat Resistive Steel Spindle Speed (rpm)	Heat Resistive Steel Feed Rate (mm/min)
4,5	1.400	40	2.500	200	1.100	90
5,0	1.300	40	2.200	220	1.000	100
6,0	1.100	40	1.900	230	800	100
8,0	800	40	1.400	200	600	80
10,0	600	40	1.100	180	500	80
12,0	500	40	900	160	400	70
16,0	400	30	700	140	300	60
Grooving a_p	0,3 DC		0,2 DC		0,15 DC	

Solid Carbide Spiral Endmills
SSM 2000 Type (ø0,2–ø4,3)

2

Carbide grade: A1 (Micrograin)



Helix angle : 30˚
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
SSM 2002	❑	0,2	0,5	40	3
2003	●	0,3	1,0	40	3
2004	●	0,4	1,0	40	3
2005	❍	0,5	1,5	40	3
SSM 2006	●	0,6	1,5	40	3
2007	❍	0,7	1,5	40	3
2008	●	0,8	2,0	40	3
2009	❑	0,9	2,0	40	3
2010	●	1,0	3,0	40	4
SSM 2011	❑	1,1	3,0	40	4
2012	❑	1,2	3,0	40	4
2013		1,3	3,0	40	4
2014	❑	1,4	3,0	40	4
2015	●	1,5	5,0	40	4
SSM 2016		1,6	5,0	40	4
2017		1,7	5,0	40	4
2018	❑	1,8	5,0	40	4
2019	❑	1,9	5,0	40	4
2020	●	2,0	6,0	40	4
SSM 2021		2,1	6,0	40	4
2022	❑	2,2	6,0	40	4
2023	❑	2,3	6,0	40	4
2024	❑	2,4	6,0	40	4
2025	●	2,5	8,0	40	4
SSM 2026	❑	2,6	8,0	40	4
2027	❑	2,7	8,0	40	4
2028	❑	2,8	8,0	40	4
2029		2,9	8,0	40	4
2030	●	3,0	8,0	45	6
SSM 2031	❑	3,1	8,0	45	6
2032	●	3,2	8,0	45	6
2033		3,3	8,0	45	6
2034	❑	3,4	8,0	45	6
2035	●	3,5	8,0	45	6
SSM 2036		3,6	10,0	45	6
2037		3,7	10,0	45	6
2038	❑	3,8	10,0	45	6
2039	❑	3,9	10,0	45	6
2040	●	4,0	10,0	45	6
SSM 2041	❑	4,1	10,0	45	6
2042	❑	4,2	10,0	45	6
2043		4,3	10,0	45	6

Recommended Conditions

(Slotting) DC < ø 3; a_p =0,5 x DC
DC ≥ ø 3; a_p =1,0 x DC

DC		Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
0,2–0,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	–0,002	–0,002	–0,001	0,002–0,004
1,0–2,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,003–0,010	0,003–0,010	0,002–0,005	0,005–0,017
3,0–4,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,012–0,024	0,012–0,024	0,006–0,011	0,018–0,040



v_c =m/min f_t =mm/tooth

Solid Carbide Spiral Endmills
SSM 2000 Type (ø4,4–ø8,5)

2

Carbide grade: A1 (Micrograin)



Helix angle : 30˚
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030

Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
SSM 2044	❑	4,4	10	45	6
2045	❑	4,5	10	45	6
SSM 2046		4,6	12	50	6
2047		4,7	12	50	6
2048	❑	4,8	12	50	6
2049	❑	4,9	12	50	6
2050	●	5,0	12	50	6
SSM 2051	❑	5,1	12	50	6
2052	❑	5,2	12	50	
2053		5,3		50	
2054		5,4	12	50	6
2055	❑	5,5	12	50	6
SSM 2056		5,6	12	50	6
2057		5,7	12	50	6
2058		5,8	12	50	6
2059		5,9	12	50	6
2060	●	6,0	12	50	6
SSM 2061		6,1	12	50	6
2062	❍	6,2	12	50	6
2063	❑	6,3	12	50	6
2064	❑	6,4	12		6
2065	❑	6,5	12	50	8
SSM 2066	❑	6,6		55	8
2067		6,7	15	55	8
2068		6,8	15	55	8
2069		6,9	15	55	8
2070	●	7,0	15	55	8
SSM 2071	❑	7,1	15	55	8
2072		7,2	15	55	8
2073		7,3	15	55	8
2074		7,4	15	55	8
2075	❍	7,5	15	55	8
SSM 2076		7,6	15	55	8
2077		7,7	15	55	8
2078	❑	7,8	15	55	8
2079		7,9	15	55	8
2080	●	8,0	15	55	8
SSM 2081	❑	8,1	15	55	8
2082	❍	8,2	15	55	8
2083		8,3	15	55	8
2084		8,4	15	55	8
2085	❍	8,5	15	55	10

Recommended Conditions

(Slotting) DC ≥ ø3; a_p =1,0 x DC

DC		Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
5–5,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,012–0,024	0,012–0,024	0,006–0,011	0,018–0,040
6–8,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,025–0,050	0,025–0,050	0,013–0,025	0,045–0,105



v_c =m/min f_t =mm/tooth

● = Euro stock
❍ = Japan stock
❑ = Delivery on request

Solid Carbide Spiral Endmills
SSM 2000 Type (ø8,6–ø30)

2

Carbide grade: A1 (Micrograin)



Helix angle : 30°
Corner : Sharp edge

DC	Tolerance (mm)
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
SSM 2086	❍	8,6	15	55	10
2087		8,7	15	55	10
2088	❑	8,8	15	55	10
2089		8,9	15	55	10
2090	❑	9,0	15	55	10
SSM 2091		9,1	15	55	10
2092		9,2	15	55	10
2093		9,3	15	55	10
2094		9,4	15	55	10
2095		9,5	15	55	10
SSM 2096		9,6	18	65	10
2097		9,7	18	65	10
2098		9,8	18	65	10
2099		9,9	18	65	10
2100	●	10,0	18	65	10
SSM 2105		10,5	18	70	12
2110	❑	11,0	18	70	12
2115	❑	11,5	18	70	12
2120	●	12,0	18	70	12
2125		12,5	20	80	16
SSM 2130	❑	13,0	20	80	16
2135		13,5		80	16
2140	❍	14,0	20	80	16
2145		14,5	25	80	16
2150	❑	15,0	25	80	16
SSM 2155		15,5	35	90	16
2160	❍	16,0	35	90	16
2165		16,5	35	90	20
2170	❍	17,0	35	90	20
2175	❑	17,5	40	105	20
SSM 2180	❑	18,0	40	105	20
2185		18,5	40	105	20
2190		19,0	40	105	20
2195		19,5	40	105	20
2200	❍	20,0	40	105	20
SSM 2210	❑	21,0	40	105	25
2220	❑	22,0	40		25
2230	❑		45	115	25
2240		24,0	45	115	25
2250	❑		50		25
SSM 2300			55	130	32

Recommended Conditions

(Slotting) DC ≥ ø3; a_p =1,0 x DC

DC		Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
9–12,5	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,025–0,050	0,025–0,050	0,013–0,025	0,045–0,105
13–19,5	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,055–0,085	0,055–0,085	0,030–0,050	0,110–0,170
20–30	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,095–0,120	0,095–0,120	0,055–0,070	0,185–0,260



v_c =m/min f_t =mm/tooth

Solid Carbide Spiral Endmills
SSM 4000 Type (ø1,5–ø25)

4

Carbide grade: A1 (Micrograin)



Helix angle : 30°
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
SSM 4015	❍	1,5	5	40	4
4020	●	2,0	6	40	4
4025	❑	2,5	8	40	4
4030	●	3,0	8	45	6
4035	❑	3,5	8	45	6
SSM 4040	●	4,0	10	45	6
4045	❑	4,5	10	45	6
4050	●	5,0	12	50	6
4055	❑	5,5	12	50	6
4060	●	6,0	12	50	6
SSM 4065	❑	6,5	12	50	8
4070	❑	7,0	15	55	8
4075	❍	7,5	15	55	8
4080	●	8,0	15	55	8
4085	❑	8,5	15	55	10
SSM 4090	❍	9,0	15	55	10
4095	❍	9,5	15	55	10
4100	●	10,0	18	65	10
4105		10,5	18	65	12
4110	❑	11,0	18	70	12
SSM 4120	●	12,0	18	70	12
4130		13,0	20	80	16
4140	❍	14,0	20	80	16
4150	❑	15,0	25	80	16
4160	●	16,0	35	90	16
SSM 4170	❑	17,0	35	90	20
4180	❑	18,0	40	105	20
4190		19,0	40	105	20
4200	●	20,0	40	105	20
4210		21,0	40	105	25
SSM 4220		22,0	40	105	25
4230		23,0	45	115	25
4240		24,0	45	115	25
4250	❑	25,0	50	120	25

Recommended Conditions

(Shoulder processing) a_p =1,5 x DC
a_e =0,1 x DC

DC		Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
1 ~ 2,9	v_c	40–**50**–60	30–**0**–50	20–**30**–40	40–**50**–60
	f_t	0,004–0,017	0,004–0,017	0,002–0,008	0,008–0,020
3 ~ 5,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,018–0,036	0,018–0,036	0,009–0,018	0,027–0,060
6 ~ 12,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,038–0,070	0,038–0,070	0,019–0,035	0,065–0,157
13 ~ 19,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,075–0,125	0,075–0,125	0,040–0,075	0,160–0,250
20 ~	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,135–0,170	0,135–0,170	0,085–0,110	0,257–0,390



v_c =m/min f_t =mm/tooth

Long Spiral Endmills
LSM 2000 Type

2

Carbide grade: A1 (Micrograin)



Helix angle : 30˚
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

Cat. No.	Stock	DC	APMX	LF	DMM
LSM 2030	▲	3,0	12	50	6
2035	▲	3,5	12	50	6
2040	▲	4,0	15	50	6
2045	▲	4,5	15	50	6
2050	▲	5,0	18	55	6
LSM 2055	▲	5,5	18	55	6
2060	▲	6,0	18	55	6
2065	▲	6,5	18	55	8
2070	▲	7,0	25	65	8
2075	▲	7,5	25	65	8
LSM 2080	▲	8,0	25	65	8
2085	▲	8,5	25	65	10
2090	▲	9,0	25	65	10
2095	▲	9,5	25	65	10
2100	▲	10,0	30	75	10
LSM 2105		10,5	30	80	12
2110	▲	11,0	30	80	12
2120	▲	12,0	30	80	12
2130	▲	13,0	35	95	16
2140	▲	14,0	40	95	16
LSM 2150	▲	15,0	40	95	16
2160	▲	16,0	50	105	16
2170		17,0	50	105	20
2180	▲	18,0	50	115	20
2190		19,0	55	120	20
LSM 2200	▲	20,0	55	120	20
2210		21,0	60	125	25
2220		22,0	60	135	25
2230		23,0	60	135	25
2240		24,0	65	140	25

Recommended Conditions

(Slotting) DC ≥ ø3; a_p =1,0 x DC

DC	Material	Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
3–5,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,009–0,018	0,009–0,018	0,005–0,008	0,014–0,030
6–12,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,019–0,038	0,019–0,038	0,009–0,019	0,034–0,079
13–19,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,041–0,064	0,041–0,064	0,023–0,038	0,083–0,128
20–	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,071–0,090	0,071–0,090	0,041–0,052	0,139–0,195



v_c =m/min f_t =mm/tooth

▲ = To be replaced by new item

Long Spiral Endmills
LSM 4000 Type

4

Carbide grade: A1 (Micrograin)



Helix angle : 30˚
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
LSM 4030	▲	3,0	12	50	6
4035	▲	3,5	12	50	6
4040	▲	4,0	15	50	6
4045		4,5	15	50	6
4050	▲	5,0	18	55	6
LSM 4055	▲	5,5	18	55	6
4060	▲	6,0	18	55	6
4065	▲	6,5	18	55	8
4070	▲	7,0	25	65	8
4075	▲	7,5	25	65	8
LSM 4080	▲	8,0	25	65	8
4085	▲	8,5	25	65	10
4090	▲	9,0	25	65	10
4095	▲	9,5	25	65	10
4100	▲	10,0	30	75	10
LSM 4105		10,5	30	80	12
4110	▲	11,0	30	80	12
4120	▲	12,0	30	80	12
4130	▲	13,0	35	95	16
4140	▲	14,0	40	95	16
LSM 4150	▲	15,0	40	95	16
4160	▲	16,0	50	105	16
4170		17,0	50	105	20
4180	▲	18,0	50	115	20
4190		19,0	55	120	20
LSM 4200	▲	20,0	55	120	20
4210		21,0	60	125	25
4220		22,0	60	135	25
4230		23,0	60	135	25
4240		24,0	65	140	25
4250	▲	25,0	65	140	25

Recommended Conditions

(Shoulder processing) a_p =1,5 x DC
a_e = 0,1 x DC

DC	Material	Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
3–5,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,014–0,027	0,014–0,027	0,007–0,014	0,020–0,045
6–12,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,028–0,053	0,028–0,053	0,014–0,026	0,048–0,118
13–19,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,056–0,094	0,056–0,094	0,030–0,056	0,120–0,188
20–	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,101–0,127	0,101–0,127	0,064–0,082	0,193–0,292



v_c =m/min f_t =mm/tooth

Extra Long Spiral Endmills
ELSM 2000 Type

2

Carbide grade: A1 (Micrograin)



Helix angle : 30°
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

(mm)

Cat. No.	Stock	DC	APMX	LF	DMM
ELSM 2030	▲	3,0	20	55	6
2040	▲	4,0	25	60	6
2050	▲	5,0	30	65	6
2060	▲	6,0	30	65	6
2070	▲	7,0	40	85	8
ELSM 2080	▲	8,0	40	85	8
2090	▲	9,0	40	85	10
2100	▲	10,0	50	100	10
2110	▲	11,0	50	100	12
2120	▲	12,0	50	100	12
ELSM 2130		13,0	70	140	16
2140	▲	14,0	70	140	16
2150		15,0	70	140	16
2160	▲	16,0	70	140	16
2180	▲	18,0	80	160	20
ELSM 2200	▲	20,0	85	165	20
2220		22,0	95	180	25
2250		25,0	100	185	25

Extra Long Spiral Endmills
ELSM 4000 Type

4

Carbide grade: A1 (Micrograin)



Helix angle : 30°
Corner : Sharp edge

DC	Tolerance (mm)
D ≤ 6,0	– 0,010 – 0,030
6,0 < D ≤ 10,0	– 0,015 – 0,040
10,0 < D	– 0,020 – 0,050

■ Endmills

Cat. No.	Stock	DC	APMX	LF	DMM
ELSM 4030	▲	3,0	20	55	6
4040	▲	4,0	25	60	6
4050	▲	5,0	30	65	6
4060	▲	6,0	30	65	6
4070	▲	7,0	40	85	8
ELSM 4080	▲	8,0	40	85	8
4090	▲	9,0	40	85	10
4100	▲	10,0	50	100	10
4110		11,0	50	100	12
4120	▲	12,0	50	100	12
ELSM 4130		13,0	70	140	16
4140	▲	14,0	70	140	16
4150		15,0	70	140	16
4160	▲	16,0	70	140	16
4170		17,0	80	160	20
ELSM 4180	▲	18,0	80	160	20
4190		19,0	85	165	20
4200	▲	20,0	85	165	20
4210		21,0	95	180	25
4220		22,0	95	180	25
ELSM 4230		23,0	95	180	25
4240		24,0	100	180	25
4250	▲	25,0	100	180	25

Recommended Conditions

(Slotting) DC ≥ ø3; a_p =1,0 x DC

DC \ Material		Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
3–5,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,006–0,012	0,006–0,012	0,003–0,006	0,009–0,020
6–12,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,013–0,025	0,013–0,025	0,006–0,013	0,023–0,053
13–19,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,028–0,043	0,028–0,043	0,015–0,025	0,055–0,085
20–	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40-**50**-60
	f_t	0,048–0,060	0,048–0,060	0,027–0,035	0,092–0,130



v_c =m/min f_t =mm/tooth

Recommended Conditions

(Shoulder processing) a_p =1,5 x DC
a_e =0,05 x DC

DC \ Material		Carbon steel, Alloy steel (BelowHRC30)	Carbon steel, Alloy steel (BelowHRC40)	Carbon steel, Alloy steel (BelowHRC45)	Cast iron
3–5,9	v_c	40–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,009–0,018	0,009–0,018	0,005–0,009	0,014–0,030
6–12,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,019–0,035	0,019–0,035	0,010–0,018	0,033–0,079
13–19,9	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,038–0,063	0,038–0,063	0,020–0,038	0,080–0,125
20–	v_c	40–**50**–60	30–**40**–50	20–**30**–40	40–**50**–60
	f_t	0,067–0,085	0,067–0,085	0,042–0,055	0,128–0,195



v_c =m/min f_t =mm/tooth

BNES Type

Spiral CBN Endmill for Hardened Steel



■ Endmills BNES Type with 1 Spiral Flute



Helix angle : 15°
right-hand cut, right-hand helix

Cat. No.	Stock	Dimensions (mm)				
	BN350	DC	DMM	APMX	LU	LF
BNES 1060	❍	6,0	10	7,0	11	60
1080	❍	8,0	10	10,0	14	70
1100	❍	10,0	12	12,0	17	75
1120	❍	12,0	12	14,0	20	80
1140	❍	14,0	16	16,0	21,5	80

■ Recommended Cutting Conditions

Cutting speed: v_c (m/min), Spindle revolutions: n (rpm), Feed per tooth: f_t (mm/tooth), Feed speed: v_f (mm/min)



Depth of cut : $a_p \leq D$

Tooling example	DC	Hardened steel (H_RC 50–57) v_c = 100–170 m/min			Hardened steel (H_RC 58–65) v_c = 80–150 m/min		
	6–8	$a_e \leq$ 0,1 mm	n = 4000–9000	v_f (mm/min) = 240–540	$a_e \leq$ 0,08 mm	n = 3200–8000	v_f (mm/min) = 150–370
	10–12	$a_e \leq$ 0,15 mm	n = 2700–5400	v_f (mm/min) = 180–360	$a_e \leq$ 0,12 mm	n = 2100–4800	v_f (mm/min) 120–270
	14–16	$a_e \leq$ 0,2 mm	n = 2000–3800	v_f (mm/min) = 140–260	$a_e \leq$ 0,15 mm	n = 1600–3400	v_f (mm/min) = 110–230

Recommendation: Dry cutting (Air coolant)
Down-cut milling
Minimise the overhang
Use a rigid machine

■ Performance

● Long Tool Life and High Efficiency





Work material: X155CrVMo12-1
Hardness: H_RC 60

Cutting data:
v_c = 100 m/min (**Helical Master**)
v_c = 40 m/min (Competitor's coated solid carbide endmill)
v_f = 186 mm/min

Down-cut milling
Dry cutting

● Excellent Surface Roughness

"Helical Master" BNES 1080 ø 8,0



Conventional straight flute CBN endmill, ø 8,0





Work material: 15Cr3
Hardness: H_RC 55–58
Cutting data: v_c = 130 m/min
v_f = 310 mm/min

Down-cut milling
Dry cutting

● = Euro stock
❍ = Japan stock

SUMIBORON "MOULD Finish Master"

BNBP Type

Characteristics / Application

- High precision machining of hardened steels < HRC70 with long tool life
- Super tough grade SUMIBORON BN350 prevents chipping of the cutting edge
- RE accuracy : ±0,005 mm

Endmills



※ Endmill Identification

BNBP 2 R020 - 012 4

- Shank Diam.
- Neck length (LU)
- Number of teeth
- Radius of ball nose

Cat. No.	Stock	Dimensions (mm)						
	BN350	RE	DC	LF	DN	DMM	APMX	LU
BNBP 2 R020-012 4	●	0,2	0,4	50	0,37	4	0,3	1,2
2 R030-015 4	●	0,3	0,6	50	0,57	4	0,4	1,5
2 R050-025 4	●	0,5	1,0	50	0,97	4	0,6	2,5
2 R075-040 4	●	0,75	1,5	50	1,47	4	0,9	4,0
2 R100-055 4	●	1,0	2,0	50	1,97	4	1,4	5,5
BNBP 2 R020-012 6	●	0,2	0,4	50	0,37	6	0,3	1,2
2 R030-015 6	●	0,3	0,6	50	0,57	6	0,4	1,5
2 R050-025 6	●	0,5	1,0	50	0,97	6	0,6	2,5
2 R075-040 6	●	0,75	1,5	50	1,47	6	0,9	4,0
2 R100-055 6	●	1,0	2,0	50	1,97	6	1,4	5,5

Performance

Wear Resistance



Machined Surface



R1,0 Ball endmill, Work material: X155CrVMo12-1 (H_RC60)
Cutting data: n = 20.000 rpm, f_t = 0,05 mm/tooth (v_f = 2.000 mm/min)
a_p = 0,05 mm, a_e = 0,05 mm, Air blast

High Speed Machining



R1,0 Ball endmill, Work material: X155CrVMo12-1 (H_RC60)
Cutting data: n = 40.000 rpm, f_t = 0,05 mm/tooth (v_f = 4.000 mm/min)
a_p = 0,05 mm, a_e = 0,05 mm, Oil mist

Excellent surface finish compared with competitor's CBN and coated carbide endmills

Recommended Cutting Conditions

Spindle revolutions: n (rpm), Feed rate per tooth: f_t (mm/tooth), Depth of cut: a_p (mm), Wide of cut: a_e (mm)

Material / Cutting data / Radius (mm)	Pre-hardened steel, Die steel (–HRC52)				Die steel (–HRC62)				High speed tool steel (–HRC70)			
	n (rpm)	f_t (mm/tooth)	a_p (mm)	a_e (mm)	n (rpm)	f_t (mm/tooth)	a_p (mm)	a_e (mm)	n (rpm)	f_t (mm/tooth)	a_p (mm)	a_e (mm)
0,2	20.000–50.000	0,02	0,03	0,03	20.000–50.000	0,02	0,01	0,02	20.000–50.000	0,015	0,01	0,02
0,3	20.000–50.000	0,02	0,03	0,03	20.000–50.000	0,02	0,01	0,02	20.000–50.000	0,015	0,01	0,02
0,5	20.000–50.000	0,03	0,05	0,05	20.000–50.000	0,03	0,03	0,04	20.000–50.000	0,02	0,02	0,03
0,75	20.000–50.000	0,04	0,08	0,1	20.000–50.000	0,04	0,05	0,05	20.000–50.000	0,03	0,02	0,05
1,0	20.000–50.000	0,05	0,1	0,1	17.000–50.000	0,05	0,05	0,05	17.000–50.000	0,03	0,03	0,05

Important Notes

(1) For stable machining, a more rigid machine is recommended.
(2) Air blast or oil mist coolant is recommended.
(3) Shorten overhang as much as possible.

NPDRS Type

SUMIDIA Binderless Radius Endmill **NPDRS** Type





NPDRS Type Body (for Standard Finishing)

Cat. No.	Stock	Dimensions (mm)							Real effective length with respect to work material gradient angle				
	NPD10	DC	RE	APMX	LU	LF	DN	DMM	0,5°	1°	1,5°	2°	3°
NPDRS 1020 R002-006	❍	0,2	0,02	0,10	0,6	40	0,175	4	0,61	0,62	0,63	0,64	0,66
1020 R005-006	❍	0,2	0,05	0,10	0,6	40	0,175	4	0,61	0,62	0,63	0,64	0,66
1030 R002-010	❍	0,3	0,02	0,15	1,0	40	0,27	4	1,01	1,03	1,04	1,06	1,09
1030 R005-010	❍	0,3	0,05	0,15	1,0	40	0,27	4	1,01	1,03	1,04	1,06	1,09
1050 R005-015	❍	0,5	0,05	0,25	1,5	40	0,47	4	1,61	1,66	1,72	1,78	1,92
NPDRS 1050 R010-015	❍	0,5	0,10	0,25	1,5	40	0,47	4	1,61	1,66	1,71	1,77	1,91
1100 R005-030	❍	1,0	0,05	0,55	3,0	40	0,95	4	3,40	3,52	3,65	3,78	4,08
1100 R010-030	❍	1,0	0,10	0,55	3,0	40	0,95	4	3,40	3,52	3,64	3,77	4,07
1100 R020-030	❍	1,0	0,20	0,55	3,0	40	0,95	4	3,40	3,51	3,63	3,76	4,05
1200 R005-040	❍	2,0	0,05	0,55	4,0	40	1,95	4	4,44	4,59	4,75	4,93	5,33
NPDRS 1200 R010-040	❍	2,0	0,10	0,55	4,0	40	1,95	4	4,43	4,59	4,75	4,92	5,31
1200 R020-040	❍	2,0	0,20	0,55	4,0	40	1,95	4	4,43	4,58	4,74	4,91	5,29

Identification Details

NPDR	S	1	020	R002	-	006
Series Code	For standard finishing	No. of flutes	Cutting diameter	Corner radius		Length below neck

Cutting Diameter and Nose Radius Combinations

DC	RE 0,02	RE 0,05	RE 0,1	RE 0,2
0,2	❍	❍		
0,3	❍	❍		
0,5		❍	❍	
1,0		❍	❍	❍
2,0		❍	❍	❍

Recommended Cutting Conditions

- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.

Work Material		Carbide			
DC (mm)	LU (mm)	Spindle Speed (min^{-1})	Feed Rate (mm/min)	a_p (mm)	p_f (mm)
0,2	0,10	40.000	100	0,001	0,001
0,3	0,15	40.000	150	0,002	0,001
0,5	0,25	40.000	200	0,003	0,001
1,0	0,55	40.000	400	0,005	0,003
2,0	0,55	40.000	600	0,010	0,005

❍ = Japan stock

NPDB(S) Type

SUMIDIA Binderless Ballnose Endmill **NPDBS** Type / **NPDB** Type





■ NPDBS Type Body (for Standard Finishing)

Cat. No.	Stock	Dimensions (mm)							Real effective length with respect to work material gradient angle				
	NPD10	RE	DC	APMX	LU	LF	DN	DMM	0,5°	1°	1,5°	2°	3°
NPDBS 1010-004	❍	0,1	0,2	0,1	0,4	40	0,18	4	0,44	0,45	0,46	0,47	0,49
1020-008	❍	0,2	0,4	0,2	0,8	40	0,38	4	0,83	0,84	0,85	0,86	0,89
1030-010	❍	0,3	0,6	0,3	1,0	40	0,58	4	1,05	1,08	1,10	1,13	1,20
1050-020	❍	0,5	1,0	0,5	2,0	40	0,95	4	2,08	2,13	2,19	2,24	2,38
1100-030	❍	1,0	2,0	1,0	3,0	40	1,95	4	3,13	3,20	3,27	3,35	3,53

■ NPDB Type Body (for Precision Finishing)

Cat. No.	Stock	Dimensions (mm)							Real effective length with respect to work material gradient angle				
	NPD10	RE	DC	APMX	LU	LF	DN	DMM	0,5°	1°	1,5°	2°	3°
NPDB 1010-004	❍	0,1	0,2	0,1	0,4	40	0,18	4	0,44	0,45	0,46	0,47	0,49
1020-008	❍	0,2	0,4	0,2	0,8	40	0,38	4	0,83	0,84	0,85	0,86	0,89
1030-010	❍	0,3	0,6	0,3	1,0	40	0,58	4	1,05	1,08	1,10	1,13	1,20
1050-020	❍	0,5	1,0	0,5	2,0	40	0,95	4	2,08	2,13	2,19	2,24	2,38
1100-030	❍	1,0	2,0	1,0	3,0	40	1,95	4	3,13	3,20	3,27	3,35	3,53

■ Identification Details

NPDB	**(S)**	**1**	**030**	**-**	**010**
Series Code	For standard finishing	No. of flutes	Ballnose radius		Length below neck

■ Recommended Cutting Conditions

- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.

● Flat Surface Finishing

Work Material		Carbide			
RE (mm)	LU (mm)	Spindle Speed (min^{-1})	Feed Rate (mm/min)	a_p (mm)	p_f (mm)
0,1	0,4	40.000	100	0,001	0,001
0,2	0,8	40.000	150	0,001	0,001
0,3	1,0	40.000	200	0,001	0,001
0,5	2,0	40.000	400	0,001	0,003
1,0	3,0	40.000	600	0,001	0,005

● Copy Finishing

Work Material		Carbide			
RE (mm)	LU (mm)	Spindle Speed (min^{-1})	Feed Rate (mm/min)	a_p (mm)	p_f (mm)
0,1	0,4	40.000	100	0,001	0,001
0,2	0,8	40.000	150	0,002	0,001
0,3	1,0	40.000	200	0,003	0,001
0,5	2,0	40.000	400	0,005	0,003
1,0	3,0	40.000	600	0,010	0,005

Multi-Drills

K

K1–K72

Multi-Drill Series

General Features

MultiDrill series is Sumitomo's original brand of high performance drills that have a special cutting edge design coupled with an advance carbide substrate.
The series has a comprehensive selection of diameters and drill lengths to cover a wide range of work materials and require-ments, providing high efficiency, high precision and cost effectiveness.

Solid Carbide Type Multi-Drills Selection

	SDP ...	SDM ...	MDW ...	MDS ...	MDF ...	MDW ... ○○○			MLDH	MDUS / MDSS	MDS ...
Type	...U3/5/7 **-HAK** (DIN)	...U3/5 **-HAK** (DIN)	**GS** 2/4	S/M **K-HAK** (DIN)	...S2D, L2D ...H3D, H5D	... **PHT**	... **XHGS** ... **XHTA**	... **NHGS**	... P / L	–	... **SDC**
Page	⇨ K 6–11	⇨ K 12–17	⇨ K18–21	⇨ K22–23	⇨ K24–31	⇨ K32–35		⇨ K36–37	⇨ K38–39	⇨ K40	⇨ K41
						Pilot drill			Pilot drill		
Application	P K	P M	P	P M K	P	P M K N		N	P M K	P M K H	N
Form	m7 drill DIN type		h8 drill cylindric	m7 drill DIN type	h8 drill cylindric	Extra long DIN type		Super Multi-Drill	Long Micro Drill	Mini Multi-Drill	Diamond Coated
Length (The ratio to øD)	3D/5D/7D	3D / 5D	2 / 4D	3D / 5D	S2D/ L2D	H3D/ H5D	3D	10D–30D	3D / 5D / 10D	5/12/20/30 D	10D	3D
Coolant holes	Yes		No	Yes	No	Yes	Yes		Yes	Yes	No	No
Coating	AlCrTiN		DEX (TiAlCr/TiSi)	TiAlN	PVD		TiAlN	–	DLC	TiAlN	TiAlN / ZX	SUMIDIA
Diameter range	3,0–16,0		2,0–16,0	4,0–12,0	0,3–20,0	3,0–16,0	4,0–8,0	3,0–12,0	3,0–16,0	0,8–2,0	0,03–1,0	2,0–10,0

Advantages

- Unique curved flute design with proven enhanced chip formation and removal, resulting in better hole accuracy.
- High speed and high efficient drilling is made possible with the combination of a special substrate with an advanced PVD coating. (10x tool life of HSS drills, 5x the efficiency)
- Wide selection range (Diameter: 0,03–65 mm, Drilling depths L/D: 2–30)
- Other diameters and length can be asked and offered

Brazed Carbide Type and Insert Type Multi-Drills Selection

	KDS ... ○○○ ⇨ K43				SMD ... ⇨ K51,K56, K58	WDX ...○○ WAS ....-.. ⇨ K70	PDL ...○○	PCT ...○○
Type	MAK	LAK	DAK	FA	SMDT ...(D) MTL ⇨ K53, K59			
Page	⇨ K44–45	⇨ K45–46	⇨ K48–49	⇨ K50	SMDT ...D MEL ⇨ K54–55	⇨ K60–69	⇨ K70–72	⇨ K71–72
					SMDT ... MFS ⇨ K57			
					SMDH ...M-3/5/8 ⇨ K52, K56 SMDH ...M / L / D ⇨ K59			
								
Application	P M K S			K N	P M K	P M K N		
Form	h7 drill			h8 drill	SMDT type carbide head	Indexable insert drill	Straight flute insert drill	Insert mill
Length (The ratio to øD)	3D	5D	7D	10D	1.5D / 3D / 5D / 8D / 12D	2D / 3D / 4D / 5D	2D / 3D	3D / 5D
Coolant holes	Yes			Yes	Yes	Yes		
Coating	TiAlN			–	TiAlN	WDXT type insert		
Diameter range	9,5–40,5			8,0–30,5	12,0–42,5	3,0–65,0	16,0–40,0	

Selection Guide

● According to Drill Types / Applications

Application		General ⟷		Special
Solid Type	"Super Multi-Drill" **MDS / MDW** Type	m7 DIN Type "Super Multi-Drill" **SDP...U HAK Type** AlCrTiN coated general purpose drill with coolant holes  Ø 3,0–16 mm L/D: 3, 5, 7 ➪ K6–11	"Super Multi-Drill" **MDW...GS Type** DEX (TiAlCr/TiSi) coated general purpose drill without coolant holes  Ø 2,0–16 mm L/D:–2, –4 ➪ K18–21	—
		m7 DIN Type "Super Multi-Drill" **MDS...K-HAK Type** TiAlN coated general purpose drill with coolant holes  Ø 2,0–12 mm L/D: –2, –4 ➪ K22–23	—	"Super Multi-Drill" **MDS...D Type** Hardened Steel Exotic Metals  Ø 1,0–16,1 mm L/D: –3 (Stock in Japan)
Brazed Type	"Super Multi-Drill" **KDS** Type	"Super Multi-Drill" **KDS... MAK Type** General Purpose Drill  Ø 12–26 mm L/D: –3 ➪ K44–45	Long Type "Super Multi-Drill" **KDS... LAK Type** Deep Hole Drilling  Ø 12–26 mm L/D: –5 ➪ K46–47	—
		—	Long Type "Super Multi-Drill" **KDS... DAK Type** Good Chip Removal  Ø 9–22 mm L/D: –7 ➪ K48–49	Extra Long Typ "Super Multi-Drill" **KDS... FA Type** For Cast Irons and Aluminium Alloys  Delivery on request Ø 9–22 mm L/D: –7 ➪ K50

■ Recommended Cutting Conditions by Work Materials

Drill \ Work		Steel	Stainless Steel	Cast Iron	Non-ferrous Metalls
Solid Type	**SDP...U HAK** **MDW...GS**	50–120 0,2–0,35	15–70 0,1–0,2	50–110 0,2–0,35	—
Brazed Type	**KDS...AK** (MAK/LAK/DAK)	50–90 0,15–0,35	35–50 0,15–0,25	60–100 0,2–0,35	—
	KDS...FA	—	—	30–70 0,2–0,5	60–150 0,2–0,5

▬ Cutting speed v_c (m/min)
├─┤ Feed f (mm/rev)

● According to Drill Types / Applications

Application	General ⟷ Special		
Indexable Drills	Insert Type Drills **WDX Type** High Efficiency and Deep Holes  Ø 13,0–65,0 mm L/D: 2, 3, 4, 5 ➪ K60–69	Replaceable Head Type Drills **SMD Type**  Ø 12,0–42,5 mm L/D: 3, 5, 8 ➪ K51–59	"Multi-Function" Types **PDL & PCT** Plunge Drills and Plunge Mills  Ø 16,0–40,0 mm L/D: 2, 3, 5 ➪ K70–72

Application	Deep Hole	Very Small Hole	Precision Hole
Special Purpose Drills	"Super Long Multi-Drill" **MDW...XHGS/XHTA Type** New General Purpose Deep Hole Drill  Ø 4,0–12,0 mm L/D: 10/15/20/25/30 ➪ K32–35	"Long Micro Drill" **MLDH... P/L Type** "P" type for pilot hole  Ø 0,8–2,0 mm L/D: 5/12/20/30 ➪ K38–39	AURORA-Coat Drill **MDW...NHGS Type** For Aluminium Alloy  Ø 3,0–16,0 mm L/D: 3 / 5 / 10 ➪ K36–37
	—	"Mini-MultiDrill" **MDSS Type**  Ø 0,20–1,00 mm L/D: 10 ➪ K40	"SUMI-DIA" coaed Drill **MDS...SDC Type** For Aluminium & CFRP*  CFRP* (Carbon FibreReinforced Plastic) Ø 2–10 mm L/D: –3 ➪ K41
	—	"Micro Drill" **MDUS Type** For Printed Circuit Boards High precision holes  Ø 0,05–0,19 mm L/D: –8 ➪ K40	—

■ Recommended Cutting Conditions by Work Materials

Drill \ Work	Steel	Stainless Steel	Cast Iron	Non-ferrous Metalls
SMD (Ø 20)	50 ▬ 120 0,12 ⊢ 0,35	50 ▬ 90 0,1 ⊢ 0,25	50 ▬ 100 0,2 ⊢ 0,45	100 ▬ 180 0,2 ⊢ 0,4
WDX (Ø 18)	100 ▬ 220 0,15 ⊢ 0,25	80 ▬ 180 0,06 ⊢ 0,18	120 ▬ 200 0,1 ⊢ 0,32	100 ▬ 200 0,1 ⊢ 0,25
MDW...XHT (Ø 5)	80 ▬ 120 0,15 ⊢ 0,25	30 ▬ 60 0,08 ⊢ 0,15	50 ▬ 90 0,15 ⊢ 0,3	80 ▬ 160 0,12 ⊢ 0,35

▬ Cutting speed v_c (m/min)
⊢ Feed f (mm/rev)

SDP Type (DIN)

General Features



Stock Size

Ø 3,0 – Ø 12,0
Increment 0,1 mm

Ø 12,1 – Ø 16,0
Standard diameter

Coating Structure



Improved anti-adhesion AlCrTiN lubricant layer coating with high Al content improves friction condition.

High wear resistance
Tough and hard
AlCrTiN super multilayer

Substrate

Advantages

- The specific and optimum solution for a wide range of application conditions
- Top performance parameters, maximum feed and stable long tool life
- Double margin design for high-precision holes
- Good balance of high wear resistance and toughness
- Curved cutting edge - ideal for removing chips
- Reliable and high productivity performance

Application Range







Maximum Feed Rate Result

Feed Rate (mm/rev)	0,30	0,40	0,50	0,55	0,60	0,65	0,70	0,75	0,80
SDP Type	OK	OK	OK	OK	OK	OK	OK	OK	
Competitor	OK	Breakage!							

Internal test conditions

Drill:	Ø 4, L/D = 5
Work Material:	Carbon Steel (C50)
Cutting Data:	v_c = 80 m/rev, a_p = 18 mm

Comparison of Tool Life



Cut volume: 950 cm³ Cut volume: 3800 cm³



500 Holes Work: C50, Drill Dia: 8 mm, L/D = 5 2000 Holes

Drill:	Ø 8, L/D = 5
Work Material:	Carbon Steel (C50)
Cutting Data:	v_c=80m/min, f=0,15mm/rev, a_p=38mm, Through hole, Internal coolant

SDP Type

Competitor



Excellent Hole Accuracy

	Hole Accuracy	Chip Shape
SDP Type	 	Compact cutting chips 
Competitor	 	Longer cutting chips 

Drill:	Ø 8, L/D = 5
Workpiece:	Carbon Steel (C50)
Cutting Data:	v_c=80m/min, f=0,25mm/rev, a_p=24mm, Blind-hole, Internal coolant

■ Solid Carbide Drill with Internal Coolant Supply, Ø 3,0–7,5 mm, 3D / 5D /7D



DC (mm)	DMM (mm)	Cat. No. (L/D) 3, 5, 7	3D Type			5D Type			7D Type		
			Stock	Dimensions (mm)		Stock	Dimensions (mm)		Stock	Dimensions (mm)	
			3	OAL	LCF	5	OAL	LCF	7	OAL	LCF
3,0	6	SDP 0300 U □ HAK	●	62	17	●	66	24	●	70	29
3,1		SDP 0310 U □ HAK	●			●			●		
3,2		SDP 0320 U □ HAK	●			●			●		
3,25		SDP 0325 U □ HAK	●			●			●		
3,3		SDP 0330 U □ HAK	●			●			●		
3,4		SDP 0340 U □ HAK	●			●			●	75	33,5
3,5		SDP 0350 U □ HAK	●			●			●		
3,6		SDP 0360 U □ HAK	●			●			●		
3,7		SDP 0370 U □ HAK	●			●			●		
3,8		SDP 0380 U □ HAK	●		21	●	74	33	●		35,5
3,9		SDP 0390 U □ HAK	●			●			●		
4,0		SDP 0400 U □ HAK	●			●			●		
4,1		SDP 0410 U □ HAK	●			●			●		
4,2		SDP 0420 U □ HAK	●			●			●		
4,3		SDP 0430 U □ HAK	●	66		●			●	85	44
4,4		SDP 0440 U □ HAK	●			●			●		
4,5		SDP 0450 U □ HAK	●			●			●		
4,6		SDP 0460 U □ HAK	●			●			●		
4,65		SDP 0465 U □ HAK	●			●			●		
4,7		SDP 0470 U □ HAK	●			●			●		
4,8		SDP 0480 U □ HAK	●		25	●	82	41	●	90	49
4,9		SDP 0490 U □ HAK	●			●			●		
5,0		SDP 0500 U □ HAK	●			●			●		
5,1		SDP 0510 U □ HAK	●			●			●		
5,2		SDP 0520 U □ HAK	●			●			●		
5,3		SDP 0530 U □ HAK	●			●			●		
5,4		SDP 0540 U □ HAK	●			●			●	97	56
5,5		SDP 0550 U □ HAK	●			●			●		
5,55		SDP 0555 U □ HAK	●			●			●		
5,6		SDP 0560 U □ HAK	●			●			●		
5,7		SDP 0570 U □ HAK	●			●			●		
5,8		SDP 0580 U □ HAK	●			●			●		
5,9		SDP 0590 U □ HAK	●			●			●		
6,0		SDP 0600 U □ HAK	●			●			●		
6,1	8	SDP 0610 U □ HAK	●	79	31	●	91	50	●	106	65
6,2		SDP 0620 U □ HAK	●			●			●		
6,3		SDP 0630 U □ HAK	●			●			●		
6,4		SDP 0640 U □ HAK	●			●			●		
6,5		SDP 0650 U □ HAK	●			●			●		
6,6		SDP 0660 U □ HAK	●			●			●		
6,7		SDP 0670 U □ HAK	●			●			●		
6,8		SDP 0680 U □ HAK	●			●			●		
6,9		SDP 0690 U □ HAK	●			●			●	116	75
7,0		SDP 0700 U □ HAK	●			●			●		
7,1		SDP 0710 U □ HAK	●		37	●			●		
7,2		SDP 0720 U □ HAK	●			●			●		
7,3		SDP 0730 U □ HAK	●			●			●		
7,4		SDP 0740 U □ HAK	●			●			●		
7,5		SDP 0750 U □ HAK	●			●			●		

※ Remarks:
❑ Non-Stock Items will be required minimum order quantity for 30 pcs.

● = Euro stock
❑ = Delivery on request

■ Solid Carbide Drill with Internal Coolant Supply, Ø 7,6–12,5 mm, 3D / 5D / 7D



Grade: PCX70
Helix angle: 30°

DC (mm)	DMM (mm)	Cat. No. (L/D) 3, 5, 7	3D Type			5D Type			7D Type		
			Stock	Dimensions (mm)		Stock	Dimensions (mm)		Stock	Dimensions (mm)	
			3	OAL	LCF	5	OAL	LCF	7	OAL	LCF
7,6	8	SDP 0760 U □ HAK	●	79	37	●	91	50	●	116	75
7,7		SDP 0770 U □ HAK	●			●			●		
7,8		SDP 0780 U □ HAK	●			●			●		
7,9		SDP 0790 U □ HAK	●			●			●		
8,0		SDP 0800 U □ HAK	●			●			●		
8,1	10	SDP 0810 U □ HAK	●	89	43	●	103	57	●	131	85
8,2		SDP 0820 U □ HAK	●			●			●		
8,3		SDP 0830 U □ HAK	●			●			❑		
8,4		SDP 0840 U □ HAK	●			●			●		
8,5		SDP 0850 U □ HAK	●			●			●		
8,6		SDP 0860 U □ HAK	●			●			●		
8,7		SDP 0870 U □ HAK	●			●			●		
8,8		SDP 0880 U □ HAK	●			●			●		
8,9		SDP 0890 U □ HAK	●			●			❑		
9,0		SDP 0900 U □ HAK	●			●			●		
9,1		SDP 0910 U □ HAK	●			●			●	139	93
9,2		SDP 0920 U □ HAK	●			●			●		
9,25		SDP 0925 U □ HAK	●			●			❑		
9,3		SDP 0930 U □ HAK	●			●			●		
9,4		SDP 0940 U □ HAK	●			●			●		
9,5		SDP 0950 U □ HAK	●			●			●		
9,6		SDP 0960 U □ HAK	●			●			❑		
9,7		SDP 0970 U □ HAK	●			●			●		
9,8		SDP 0980 U □ HAK	●			●			●		
9,9		SDP 0990 U □ HAK	●			●			●		
10,0		SDP 1000 U □ HAK	●			●			●		
10,1	12	SDP 1010 U □ HAK	●	102	51	●	118	67	❑	155	104
10,2		SDP 1020 U □ HAK	●			●			●		
10,3		SDP 1030 U □ HAK	●			●			❑		
10,4		SDP 1040 U □ HAK	●			●			❑		
10,5		SDP 1050 U □ HAK	●			●			●		
10,6		SDP 1060 U □ HAK	●			●			❑		
10,7		SDP 1070 U □ HAK	●			●			❑		
10,8		SDP 1080 U □ HAK	●			●			●		
10,9		SDP 1090 U □ HAK	●			●			❑		
11,0		SDP 1100 U □ HAK	●			●			●		
11,1		SDP 1110 U □ HAK	●			●			❑	163	112
11,2		SDP 1120 U □ HAK	●			●			●		
11,3		SDP 1130 U □ HAK	●			●			❑		
11,4		SDP 1140 U □ HAK	●			●			❑		
11,5		SDP 1150 U □ HAK	●			●			●		
11,6		SDP 1160 U □ HAK	●			●			❑		
11,7		SDP 1170 U □ HAK	●			●			❑		
11,8		SDP 1180 U □ HAK	●			●			●		
11,9		SDP 1190 U □ HAK	●			●			❑		
12,0		SDP 1200 U □ HAK	●			●			●		
12,1	14	SDP 1210 U □ HAK	❑	107	56	❑	124	73	❑	182	131
12,2		SDP 1220 U □ HAK	●			●			●		
12,3		SDP 1230 U □ HAK	❑			❑			❑		
12,4		SDP 1240 U □ HAK	❑			❑			❑		
12,5		SDP 1250 U □ HAK	●			●			●		

※ Remarks:
❑ Non-Stock Items will be required minimum order quantity for 30 pcs.

■ Solid Carbide Drill with Internal Coolant Supply, Ø 12,6–16,0 mm, 3D / 5D / 7D



DC (mm)	DMM (mm)	Cat. No. (L/D) 3, 5, 7	3D Type			5D Type			7D Type		
			Stock	Dimensions (mm)		Stock	Dimensions (mm)		Stock	Dimensions (mm)	
			3	OAL	LCF	**5**	OAL	LCF	**7**	OAL	LCF
12,6	14	SDP 1260 U □ HAK	❑	107	56	❑	124	73	❑	182	131
12,7		SDP 1270 U □ HAK	❑			❑			❑		
12,8		SDP 1280 U □ HAK	❑			❑			❑		
12,9		SDP 1290 U □ HAK	❑			❑			❑		
13,0		SDP 1300 U □ HAK	●			●			●		
13,1		SDP 1310 U □ HAK	❑			❑			❑		
13,2		SDP 1320 U □ HAK	❑			❑			❑		
13,3		SDP 1330 U □ HAK	❑			❑			❑		
13,4		SDP 1340 U □ HAK	❑			❑			❑		
13,5		SDP 1350 U □ HAK	●			●			●		
13,6		SDP 1360 U □ HAK	❑			❑			❑		
13,7		SDP 1370 U □ HAK	●			●			●		
13,8		SDP 1380 U □ HAK	❑			❑			❑		
13,9		SDP 1390 U □ HAK	❑			❑			❑		
14,0		SDP 1400 U □ HAK	●			●			●		
14,1	16	SDP 1410 U □ HAK	❑	115	60	❑	133	78	❑	204	149
14,2		SDP 1420 U □ HAK	●			●			●		
14,3		SDP 1430 U □ HAK	❑			❑			❑		
14,4		SDP 1440 U □ HAK	❑			❑			❑		
14,5		SDP 1450 U □ HAK	●			●			●		
14,6		SDP 1460 U □ HAK	❑			❑			❑		
14,7		SDP 1470 U □ HAK	●			●			●		
14,8		SDP 1480 U □ HAK	❑			❑			❑		
14,9		SDP 1490 U □ HAK	❑			❑			❑		
15,0		SDP 1500 U □ HAK	●			●			●		
15,1		SDP 1510 U □ HAK	❑			❑			❑		
15,2		SDP 1520 U □ HAK	●			●			●		
15,3		SDP 1530 U □ HAK	❑			❑			❑		
15,4		SDP 1540 U □ HAK	❑			❑			❑		
15,5		SDP 1550 U □ HAK	●			●			●		
15,6		SDP 1560 U □ HAK	❑			❑			❑		
15,7		SDP 1570 U □ HAK	●			●			●		
15,8		SDP 1580 U □ HAK	❑			❑			❑		
15,9		SDP 1590 U □ HAK	❑			❑			❑		
16,0		SDP 1600 U □ HAK	●			●			●		

※ Remarks:
❑ Non-Stock Items will be required minimum order quantity for 30 pcs.

● = Euro stock
❑ = Delivery on request

Recommended Cutting Conditions

Material Group						SDP_____U_HAK PCX70					
						Ø 3,0–6,0 mm		Ø 6,1–10,0 mm		Ø 10,1–16,0 mm	
ISO 513	Work Material	Type/ Structure	R_m N/mm²	Hardness HB30	Fitness	v_c=m/min	Feed rate (mm/rev)	v_c=m/min	Feed rate (mm/rev)	v_c=m/min	Feed rate (mm/rev)
P	Carbon steel Cast steel	free cutting steel construction steel case-hardened steel heat-treatable steel spring steel	420	125	◎	50–**80**–120	0,15–**0,20**–0,31	70–**110**–140	0,20–**0,25**–0,42	80–**120**–160	0,25–**0,30**–0,53
			650	190	◎	50–**80**–120	0,15–**0,20**–0,31	70–**110**–140	0,20–**0,25**–0,42	80–**120**–160	0,25–**0,30**–0,53
			850	250	◎	50–**80**–120	0,15–**0,20**–0,31	70–**110**–140	0,20–**0,25**–0,42	80–**120**–160	0,25–**0,30**–0,53
			750	270	◎	50–**80**–120	0,15–**0,20**–0,31	70–**110**–140	0,20–**0,25**–0,42	80–**120**–160	0,25–**0,30**–0,50
			1000	300	◎	10–**20**–30	0,05–**0,06**–0,11	15–**22**–30	0,08–**0,09**–0,14	20–**28**–35	0,08–**0,09**–0,16
	Low alloy steel Cast steel	case-hardened steel heat-treatable steel bearing steel nitriding steel cold work steel	600	180	◎	50–**70**–90	0,10–**0,14**–0,24	60–**80**–110	0,15–**0,20**–0,32	70–**100**–120	0,20–**0,25**–0,40
			930	275	◎	45–**65**–85	0,10–**0,14**–0,24	60–**80**–110	0,15–**0,22**–0,34	65–**95**–120	0,20–**0,25**–0,37
			1000	300	○	40–**60**–80	0,10–**0,15**–0,26	60–**80**–110	0,15–**0,20**–0,32	60–**90**–120	0,20–**0,25**–0,37
			1200	350	◎	35–**55**–75	0,10–**0,15**–0,26	55–**75**–110	0,15–**0,22**–0,32	55–**80**–110	0,20–**0,27**–0,38
	High alloy steel	tool steel hot work steel	680	200	○	30–**40**–50	0,10–**0,15**–0,25	30–**40**–50	0,12–**0,20**–0,28	30–**40**–50	0,12–**0,20**–0,32
			1100	325	○	20–**30**–40	0,10–**0,12**–0,23	20–**30**– 40	0,12–**0,15**–0,27	20–**30**–40	0,14–**0,18**–0,32
M	Stainless steel Cast steel	martensitic/ferritic	680	200	○	40–**55**–70	0,08–**0,10**–0,21	40–**60**–75	0,10–**0,12**–0,25	50–**70**–80	0,10–**0,12**–0,25
		martensitic	820	240	⊙	30–**45**–60	0,08–**0,10**–0,20	40–**60**–70	0,10–**0,12**–0,24	50–**60**–80	0,10–**0,12**–0,24
		austenitic	600	180	⊙	30–**45**–60	0,08–**0,10**–0,20	40–**60**–70	0,10–**0,12**–0,24	50–**60**–80	0,10–**0,12**–0,24
		Duplex	740	230	⊙	30–**45**–60	0,06–**0,08**–0,18	40–**60**–70	0,08–**0,10**–0,23	50–**60**–80	0,10–**0,10**–0,23
K	Cast iron GG	ferritic/pearlitic		180	◎	50–**70**–90	0,15–**0,20**–0,36	60–**80**–100	0,20–**0,25**–0,40	70–**100**–120	0,25–**0,30**–0,42
		pearlitic		260	◎	40–**60**–80	0,15–**0,20**–0,36	50–**70**–90	0,20–**0,25**–0,40	60–**80**–100	0,25–**0,30**–0,42
	Cast iron GGG	ferritic		160	◎	50–**70**–90	0,15–**0,18**–0,31	60–**80**–100	0,20–**0,25**–0,40	70–**100**–120	0,25–**0,30**–0,42
		pearlitic		250	◎	40–**60**–80	0,15–**0,18**–0,31	50–**70**–90	0,20–**0,25**–0,40	70–**80**–100	0,25–**0,30**–0,42
S	Heat resisting alloys	Fe-based			○	10–**20**–30	0,08–**0,09**–0,13	15–**22**–32	0,08–**0,10**–0,15	20–**28**–35	0,10–**0,12**–0,19
		Ni / Co-based			○	10–**20**–30	0,08–**0,09**–0,13	15–**22**–32	0,08–**0,10**–0,15	20–**28**–35	0,10–**0,12**–0,19
	Titanium Titanium alloys	pure Titanium	430								
		Ti-Basis			○	10–**20**–30	0,05–**0,06**–0,12	15–**22**–32	0,08–**0,09**–0,17	20–**28**–35	0,08–**0,09**–0,17
N	Aluminium Al-wrought alloys	pure aluminium									
		wrought alloys									
	Aluminium Cast alloys	Si ≤ 12%									
		Si ≥ 12%			⊙	70–**90**–100	0,15–**0,20**–0,25	80–**100**–120	0,20–**0,25**–0,30	100–**120**–140	0,25–**0,30**–0,35
		Al - Mg alloys									
	Zinc die-cast	Zn alloys									
	Copper alloys	Copper									
		Brass			○	80–**100**–120	0,15–**0,20**–0,25	110–**130**–180	0,20–**0,25**–0,30	160–**180**–200	0,25–**0,30**–0,35
		Bronze									
H	Hardened steel	45 HRC			○	10–**20**–30	0,08–**0,09**–0,10	15–**22**–32	0,08–**0,10**–0,12	20–**28**–35	0,12–**0,15**–0,20
		55 HRC									
		60 HRC									
		> 60 HRC									

◎ Preferred choice ○ Suitable ⊙ Possible

SDP-Identification

SDP **0800** **U** **3** **HAK** PCX70

- **S**umi-**D**rill **P**ower Type
- Drill Diameter 8,0 mm
- **U**: Universal
- Drilling Depth 3D/5D/7D
- DIN 6535 Form HAK
- Grade

SDM Type

General Features



Stock Size

Ø 3,0 – Ø 12,0
Increment 0,1 mm

Ø 12,1 – Ø 16,0
Standard diameter

Advantages

- High process reliability in stainless steel and low carbon steel
- Can be used on low-performance machines! (→avoids overload!)
- High surface quality in the bore
- Sharp cutting edge
- High adhesion resistance by Sumi-Power Coating



Chip Control

Drill:	Ø 8 mm, L/D = 5
Work Material:	X5CrNiS18 10 (1.4301)
Cutting D ata:	v_c=60m/min, f=0,10mm/rev, a_p=19mm Internal coolant (2,0MPa)

SDM

Short chips,
good chip evacuation

Competitor A



Partial long chips,
risk of tool breakage
by poor chip evacuation

Optimal Cutting Forces

Drill:	Ø 8 mm, L/D = 5
Work Material:	X5CrNiS18 10 (1.4301)
Cutting Data:	v_c=60m/min, f=0,20mm/rev, a_p=40mm Internal coolant (2,0MPa)

10 % lower than competitor A

SDM



Competitor



Low Burr Formation

Drill:	Ø 8 mm, L/D = 5
Work Material:	X5CrNiS18 10 (1.4301)
Cutting Data:	v_c=60m/min, f=0,20mm/rev, a_p=40mm Internal coolant (2,0MPa)



SDM Competitor A Competitor B

Recommended Cutting Conditions

Material Group						SDM_____U_HAK PCX70					
ISO 513	Work Material	Type/ Structure	R_m N/mm²	Hardness HB30	Fitness	Ø 3,0–6,0 mm		Ø 6,1–10,0 mm		Ø 10,1–16,0 mm	
						v_c=m/min	Feed rate (mm/rev)	v_c=m/min	Feed rate (mm/rev)	v_c=m/min	Feed rate (mm/rev)
P	Carbon steel Cast steel	free cutting steel construction steel case-hardened steel heat-treatable steel spring steel	420	125	○	80–**100**–120	0,08–**0,11**–0,14	80–**100**–120	0,10–**0,15**–0,20	80–**100**–120	0,20–**0,25**–0,30
			650	190	○	80–**100**–120	0,08–**0,11**–0,14	80–**100**–120	0,10–**0,15**–0,20	80–**100**–120	0,20–**0,25**–0,30
			850	250	○	80–**100**–120	0,08–**0,11**–0,14	80–**100**–120	0,10–**0,15**–0,20	80–**100**–120	0,20–**0,25**–0,30
			750	270	○	40–**60**–100	0,08–**0,10**–0,12	40–**60**–100	0,10–**0,12**–0,16	40–**60**–100	0,15–**0,17**–0,20
			1000	300							
	Low alloy steel Cast steel	case-hardened steel heat-treatable steel bearing steel nitriding steel cold work steel	600	180	○	80–**100**–120	0,08–**0,11**–0,14	80–**100**–120	0,10–**0,15**–0,20	80–**100**–120	0,20–**0,25**–0,30
			930	275	○	40–**60**–100	0,08–**0,10**–0,12	40–**60**–100	0,10–**0,12**–0,16	40–**60**–100	0,15–**0,17**–0,20
			1000	300							
			1200	350							
	High alloy steel / Cast steel	tool steel hot work steel	680	200	○	40–**60**–100	0,08–**0,10**–0,12	40–**60**–100	0,10–**0,12**–0,16	40–**60**–100	0,15–**0,17**–0,20
			1100	325							
M	Stainless steel Cast steel	martensitic/ferritic	680	200	◉	40–**60**–100	0,08–**0,10**–0,12	40–**60**–100	0,10–**0,14**–0,18	40–**60**–100	0,15–**0,20**–0,25
		martensitic/ferritic		>200	◉	30–**50**–80	0,08–**0,10**–0,12	30–**50**–80	0,10–**0,14**–0,18	30–**50**–80	0,15–**0,20**–0,25
		martensitic	820	240	◉	30–**50**–80	0,08–**0,10**–0,12	30–**50**–80	0,10–**0,14**–0,18	30–**50**–80	0,15–**0,20**–0,25
		austenitic	600	180	◉	40–**60**–100	0,08–**0,10**–0,12	40–**60**–100	0,10–**0,14**–0,18	40–**60**–100	0,15–**0,20**–0,25
		austenitic		>200	◉	30–**50**–80	0,08–**0,10**–0,12	30–**50**–80	0,10–**0,14**–0,18	30–**50**–80	0,15–**0,20**–0,25
		Duplex	740	230	◉	30–**45**–70	0,08–**0,10**–0,12	30–**45**–70	0,10–**0,14**–0,18	30–**45**–70	0,15–**0,20**–0,25
		Precipation hardened		≤450	◉	30–**45**–70	0,08–**0,10**–0,12	30–**45**–70	0,10–**0,14**–0,18	30–**45**–70	0,15–**0,20**–0,25
K	Cast iron GG	ferritic/pearlitic		180							
		pearlitic		260							
	Cast iron GGG	ferritic		160							
		pearlitic		250							
S	Heat resisting alloys	Fe-based			○	20–**30**–40	0,06–**0,08**–0,10	20–**30**–40	0,08–**0,10**–0,12	20–**30**–40	0,10–**0,12**–0,15
		Ni / Co-based			○	20–**30**–40	0,06–**0,08**–0,10	20–**30**–40	0,08–**0,10**–0,12	20–**30**–40	0,10–**0,12**–0,15
	Titanium Titanium alloys	pure Titanium	430								
		Ti-Basis			○	20–**30**–40	0,06–**0,08**–0,10	20–**30**–40	0,08–**0,10**–0,12	20–**30**–40	0,10–**0,12**–0,15
N	Aluminium	pure aluminium									
		wrought alloys									
	Aluminium Cast alloys	Si ≤ 12%									
		Si ≥ 12%									
		Al - Mg alloys									
	Zinc die-cast	Zn alloys									
	Copper alloys	Copper									
		Brass									
		Bronze									
H	Hardened steel	45 HRC									
		55 HRC									
		60 HRC									
		>60 HRC									

◉ Preferred choice ○ Possible

SDM-Identification

SDM **0800** **U** **3** **HAK** PCX70

- **SDM**: **S**umi-**D**rill **M** (ISO-Code)
- **0800**: Drill Diameter 8,0 mm
- **U**: Universal
- **3**: Drilling Depth 3D/5D
- **HAK**: DIN 6535 Form HAK
- PCX70: Grade

● = Euro stock
❑ = Delivery on request

■ Solid Carbide Drill with Internal Coolant Supply, Ø 3,0–7,5 mm, 3D / 5D



DC (mm)	DMM (mm)	Cat. No. (L/D) 3/5	3D Type			5D Type		
			Stock	Dimensions (mm)		Stock	Dimensions (mm)	
			3	OAL	LCF	5	OAL	LCF
3,0	6	SDM 0300 U □ HAK	●	62	17	●	66	24
3,1		SDM 0310 U □ HAK	●			●		
3,2		SDM 0320 U □ HAK	●			●		
3,25		SDM 0325 U □ HAK	❑			❑		
3,3		SDM 0330 U □ HAK	●			●		
3,4		SDM 0340 U □ HAK	●			●		
3,5		SDM 0350 U □ HAK	●			●		
3,6		SDM 0360 U □ HAK	●			●		
3,7		SDM 0370 U □ HAK	●			●		
3,8		SDM 0380 U □ HAK	●	66	21	●	74	33
3,9		SDM 0390 U □ HAK	●			●		
4,0		SDM 0400 U □ HAK	●			●		
4,1		SDM 0410 U □ HAK	●			●		
4,2		SDM 0420 U □ HAK	●			●		
4,3		SDM 0430 U □ HAK	●			●		
4,4		SDM 0440 U □ HAK	●			●		
4,5		SDM 0450 U □ HAK	●			●		
4,6		SDM 0460 U □ HAK	●			●		
4,65		SDM 0465 U □ HAK	❑			❑		
4,7		SDM 0470 U □ HAK	●			●		
4,8		SDM 0480 U □ HAK	●		25	●	82	41
4,9		SDM 0490 U □ HAK	●			●		
5,0		SDM 0500 U □ HAK	●			●		
5,1		SDM 0510 U □ HAK	●			●		
5,2		SDM 0520 U □ HAK	●			●		
5,3		SDM 0530 U □ HAK	●			●		
5,4		SDM 0540 U □ HAK	●			●		
5,5		SDM 0550 U □ HAK	●			●		
5,55		SDM 0555 U □ HAK	❑			❑		
5,6		SDM 0560 U □ HAK	●			●		
5,7		SDM 0570 U □ HAK	●			●		
5,8		SDM 0580 U □ HAK	●			●		
5,9		SDM 0590 U □ HAK	●			●		
6,0		SDM 0600 U □ HAK	●			●		
6,1	8	SDM 0610 U □ HAK	●	79	31	●	91	50
6,2		SDM 0620 U □ HAK	●			●		
6,3		SDM 0630 U □ HAK	●			●		
6,4		SDM 0640 U □ HAK	●			●		
6,5		SDM 0650 U □ HAK	●			●		
6,6		SDM 0660 U □ HAK	●			●		
6,7		SDM 0670 U □ HAK	●			●		
6,8		SDM 0680 U □ HAK	●			●		
6,9		SDM 0690 U □ HAK	●			●		
7,0		SDM 0700 U □ HAK	●			●		
7,1		SDM 0710 U □ HAK	●		37	●		
7,2		SDM 0720 U □ HAK	●			●		
7,3		SDM 0730 U □ HAK	●			●		
7,4		SDM 0740 U □ HAK	●			●		
7,5		SDM 0750 U □ HAK	●			●		

SDM Type

■ Solid Carbide Drill with Internal Coolant Supply, Ø 7,6–12,0 mm, 3D / 5D



DC (mm)	DMM (mm)	Cat. No. (L/D) 3/5	3D Type			5D Type		
			Stock	Dimensions (mm)		Stock	Dimensions (mm)	
			3	OAL	LCF	5	OAL	LCF
7,6	8	SDM 0760 U □ HAK	●	79	37	●	91	50
7,7		SDM 0770 U □ HAK	●			●		
7,8		SDM 0780 U □ HAK	●			●		
7,9		SDM 0790 U □ HAK	●			●		
8,0		SDM 0800 U □ HAK	●			●		
8,1	10	SDM 0810 U □ HAK	●	89	43	●	103	57
8,2		SDM 0820 U □ HAK	●			●		
8,3		SDM 0830 U □ HAK	●			●		
8,4		SDM 0840 U □ HAK	●			●		
8,5		SDM 0850 U □ HAK	●			●		
8,6		SDM 0860 U □ HAK	●			●		
8,7		SDM 0870 U □ HAK	●			●		
8,8		SDM 0880 U □ HAK	●			●		
8,9		SDM 0890 U □ HAK	●			●		
9,0		SDM 0900 U □ HAK	●			●		
9,1		SDM 0910 U □ HAK	●			●		
9,2		SDM 0920 U □ HAK	●			●		
9,25		SDM 0925 U □ HAK	❑			❑		
9,3		SDM 0930 U □ HAK	●			●		
9,4		SDM 0940 U □ HAK	●			●		
9,5		SDM 0950 U □ HAK	●			●		
9,6		SDM 0960 U □ HAK	●			●		
9,7		SDM 0970 U □ HAK	●			●		
9,8		SDM 0980 U □ HAK	●			●		
9,9		SDM 0990 U □ HAK	●			●		
10,0		SDM 1000 U □ HAK	●			●		
10,1	12	SDM 1010 U □ HAK	●	102	51	●	118	67
10,2		SDM 1020 U □ HAK	●			●		
10,3		SDM 1030 U □ HAK	●			●		
10,4		SDM 1040 U □ HAK	●			●		
10,5		SDM 1050 U □ HAK	●			●		
10,6		SDM 1060 U □ HAK	●			●		
10,7		SDM 1070 U □ HAK	●			●		
10,8		SDM 1080 U □ HAK	●			●		
10,9		SDM 1090 U □ HAK	●			●		
11,0		SDM 1100 U □ HAK	●			●		
11,1		SDM 1110 U □ HAK	●			●		
11,2		SDM 1120 U □ HAK	●			●		
11,3		SDM 1130 U □ HAK	●			●		
11,4		SDM 1140 U □ HAK	●			●		
11,5		SDM 1150 U □ HAK	●			●		
11,6		SDM 1160 U □ HAK	●			●		
11,7		SDM 1170 U □ HAK	●			●		
11,8		SDM 1180 U □ HAK	●			●		
11,9		SDM 1190 U □ HAK	●			●		
12,0		SDM 1200 U □ HAK	●			●		

● = Euro stock
❑ = Delivery on request

SDM Type

■ Solid Carbide Drill with Internal Coolant Supply, Ø 12,0–16,0 mm, 3D / 5D



DC (mm)	DMM (mm)	Cat. No. (L/D) 3/5	3D Type			5D Type		
			Stock	Dimensions (mm)		Stock	Dimensions (mm)	
			3	OAL	LCF	5	OAL	LCF
12,1	14	SDM 1210 U □ HAK	❑	107	56	❑	124	73
12,2		SDM 1220 U □ HAK	❑			❑		
12,3		SDM 1230 U □ HAK	❑			❑		
12,4		SDM 1240 U □ HAK	❑			❑		
12,5		SDM 1250 U □ HAK	●			●		
12,6		SDM 1260 U □ HAK	❑			❑		
12,7		SDM 1270 U □ HAK	❑			❑		
12,8		SDM 1280 U □ HAK	❑			❑		
12,9		SDM 1290 U □ HAK	❑			❑		
13,0		SDM 1300 U □ HAK	●			●		
13,1		SDM 1310 U □ HAK	❑			❑		
13,2		SDM 1320 U □ HAK	❑			❑		
13,3		SDM 1330 U □ HAK	❑			❑		
13,4		SDM 1340 U □ HAK	❑			❑		
13,5		SDM 1350 U □ HAK	●			●		
13,6		SDM 1360 U □ HAK	❑			❑		
13,7		SDM 1370 U □ HAK	❑			❑		
13,8		SDM 1380 U □ HAK	❑			❑		
13,9		SDM 1390 U □ HAK	❑			❑		
14,0		SDM 1400 U □ HAK	●			●		
14,1	16	SDM 1410 U □ HAK	❑	115	60	❑	133	78
14,2		SDM 1420 U □ HAK	❑			❑		
14,3		SDM 1430 U □ HAK	❑			❑		
14,4		SDM 1440 U □ HAK	❑			❑		
14,5		SDM 1450 U □ HAK	●			●		
14,6		SDM 1460 U □ HAK	❑			❑		
14,7		SDM 1470 U □ HAK	❑			❑		
14,8		SDM 1480 U □ HAK	❑			❑		
14,9		SDM 1490 U □ HAK	❑			❑		
15,0		SDM 1500 U □ HAK	●			●		
15,1		SDM 1510 U □ HAK	❑			❑		
15,2		SDM 1520 U □ HAK	❑			❑		
15,3		SDM 1530 U □ HAK	❑			❑		
15,4		SDM 1540 U □ HAK	❑			❑		
15,5		SDM 1550 U □ HAK	●			●		
15,6		SDM 1560 U □ HAK	❑			❑		
15,7		SDM 1570 U □ HAK	❑			❑		
15,8		SDM 1580 U □ HAK	❑			❑		
15,9		SDM 1590 U □ HAK	❑			❑		
16,0		SDM 1600 U □ HAK	●			●		

DEX Coating

General Features

- Sumitomo Electric Hardmetal's next-generation drill coating utilises nano-coating technology to provide more than double the tool life of conventional coatings.
- Silicon and chrome improve usure, heat, and adhesion resistance.
- New super multi-layered structure offers significantly improved chip resistance (coating strength).

Characteristics

- Coating Design
  World's first combined super multi-layered coating is made from alternate layers of super multilayered substrates.



- Characteristics of Films



DEX Coat Application Examples

- MultiDrill GS Type Drilling Examples

Comparison of Usure Resistance

Edge Usure Comparison for 70 m Drilling

Shoulder and rake face feature improved usure resistance enabling long tool life.

DEX Coating MultiDrill GS Type

Concurrent A Dril





Tool:	MDW 0800 GS4
Work Material:	C50 (HB200)
Cutting Conditions:	v_c = 70 m/min, f = 0,25 mm/rev, a_p = 32 mm External coolant (Water soluble)

Comparison of Adhesion Resistance

Edge Usure Comparison for 100 m Drilling

Offers significantly improved fracture resistance to counter problems caused by shoulder and flute adhesion in soft steel drilling.

DEX Coating MultiDrill GS Type

Competitor B Dril



Tool:	MDW 0600 GS4
Work Material:	15CrMo5 (HB120)
Cutting Conditions:	v_c = 60 m/min, f = 0,18 mm/rev, a_p = 18 mm External coolant (Water soluble)

- Long MultiDrill XHT Type Drilling Examples

Reduced margin usure during deep hole MQL drilling increases number of regrinds.

DEX Coating



Conventional Coating

Tool:	MDW 0497 XHT20 (Ø 4,97 L/D = 29)
Work Material:	42CrMo4 (HB275) Crank Shaft
Cutting Conditions:	v_c= 70 m/min, f = 0,23 mm/rev, a_p = 75 mm MQL

- MultiDrill SMD Type Drilling Examples

Offers longer tool life with SEC MultiDrills as well.



Tool:	SMDH 210 M (Ø 21,0)
Work Material:	36Mn5 (HB350) Construction Mashine Componemt
Cutting Conditions:	v_c = 60 m/min, f = 0,25 mm/rev, a_p = 25 mm Water soluble Coolant

SUPER MULTI-DRILLS
GS Type

General Features

Super MultiDrill GS types are solid carbide drills that employ a new flute design and wide chip pocket to achieve excellent chip management and evacuation.
DEX coating enables stable and long tool life over a wide range of work materials and applications.

Characteristics and Applications

- **Long tool life**
  New cutting edge design and special DEX coating provide long tool life with a wide variety of work materials.
- **Stable chip evacuation**
  New flute shape significantly improves chip management and evacuation.
- **Quiet cutting and stable cutting resistance**
  Stable drilling with little wobble even in small machine applications.
- **Environmentally-friendly**
  Compatible with the MQL (Minimum Quantity Lubrication) system.

Series

Coolant Supply	Type	Diameter Range (mm)	Hole Depth (L/D)
External (GS Type)	MDW □□□□ GS2	Ø 0,8 – 16,0	–2
	MDW □□□□ GS4		–4

Performance

Chip Management

MDW … **GS** | Conventional Type



Performance Comparison

MDW … **GS** | Conventional Type



GS type provides stable drill behaviour throughout the drilling process.

Tool: MDW 0800 GS4
Work Material: C50 (HB200)
Cutting Conditions: v_c = 80 m/min, f = 0,25 mm/rev, a_p = 24 mm
External Coolant (Water Soluble)

Application Examples

● Automotive Component
C43 (HB250)

Drill: MDW 0970 GS4 (Ø 9,7 mm)
Cutting Data: v_c = 80 m/min, f = 0,25 mm/rev
a_p = 25 mm
External Coolant (Water Soluble)



● Boron Steel Machine Component
(HRC30)

Drill: MDW 0980 GS2 (Ø 9,8 mm)
Cutting Data: v_c = 70 m/min, f = 0,15 mm/rev
a_p = 7 mm
External Coolant (Water Soluble)



● Machine Component
USt.42-2

Drill: MDW 0800 GS4 (Ø 8,0 mm)
Cutting Data: v_c = 80 m/min, f = 0,25 mm/rev
a_p =25 mm
Internal Coolant (Water Soluble)



MDW ... GS Type

Without Coolant Holes (2D/4D)

"Super Multi-Layer" DEX (TiAlCr/TiSi) Coated Solid Carbide Drills



Helix angle: 30°
ℓ_1 = Effective drilling length

● Diameter Ø 2,0–6,0 mm

(mm)

Dimensions DC	ød	Cat. No. 2, 4	Short Type (2D) Stock 2	Short Type (2D) Dimensions L	ℓ_1	ℓ_2	Long Type (4D) Stock 4	Long Type (4D) Dimensions L	ℓ_1	ℓ_2
2,0	3,0	MDW 0200 GS□	●	45,4	6,0	8,4	○	49,4	13,0	15,4
2,1	3,0	MDW 0210 GS□	○	45,6	7,3	10,5	○	49,6	14,5	17,5
2,2		MDW 0220 GS□	○				○			
2,3		MDW 0230 GS□	○				○			
2,4		MDW 0240 GS□	○				●			
2,5		MDW 0250 GS□	●				○			
2,6		MDW 0260 GS□	●		9,8	13,6	●		16,0	19,6
2,7		MDW 0270 GS□	○				○			
2,8		MDW 0280 GS□	○				○			
2,9		MDW 0290 GS□	○				○			
3,0		MDW 0300 GS□	○				○			
3,1	4,0	MDW 0310 GS□	○	54,8	15,5	19,7	○	60,8	20,5	24,7
3,2		MDW 0320 GS□	○				○			
3,3		MDW 0330 GS□	○				○			
3,4		MDW 0340 GS□	○				○			
3,5		MDW 0350 GS□	○				○			
3,6		MDW 0360 GS□	○		17,0	21,8	○		23,0	27,8
3,7		MDW 0370 GS□	○				○			
3,8		MDW 0380 GS□	○				○			
3,9		MDW 0390 GS□	○				○			
4,0		MDW 0400 GS□	○				○			
4,1	5,0	MDW 0410 GS□	○	62,0	18,5	23,9	○	77,0	25,5	31,9
4,2		MDW 0420 GS□	○				○			
4,3		MDW 0430 GS□	○				○			
4,4		MDW 0440 GS□	○				○			
4,5		MDW 0450 GS□	○				○			
4,6		MDW 0460 GS□	○		20,0	26,0	○		33,0	39,0
4,7		MDW 0470 GS□	○				○			
4,8		MDW 0480 GS□	○				○			
4,9		MDW 0490 GS□	○				○			
5,0		MDW 0500 GS□	○				○			
5,1	6,0	MDW 0510 GS□	○	66,2	19,5	26,1	○	82,2	33,5	40,1
5,2		MDW 0520 GS□	○				○			
5,3		MDW 0530 GS□	○				○			
5,4		MDW 0540 GS□	○				○			
5,5		MDW 0550 GS□	○				●			
5,6		MDW 0560 GS□	○		21,0	28,2	○		35,0	42,2
5,7		MDW 0570 GS□	○				○			
5,8		MDW 0580 GS□	○				○			
5,9		MDW 0590 GS□	○				○			
6,0		MDW 0600 GS□	○				○			

● Diameter Ø 6,1–10,0 mm

(mm)

Dimensions DC	ød	Cat. No. 2, 4	Short Type (2D) Stock 2	Short Type (2D) Dimensions L	ℓ_1	ℓ_2	Long Type (4D) Stock 4	Long Type (4D) Dimensions L	ℓ_1	ℓ_2
6,1	7,0	MDW 0610 GS□	○	74,5	24,5	32,3	○	84,3	35,5	43,3
6,2		MDW 0620 GS□	○				○			
6,3		MDW 0630 GS□	○				○			
6,4		MDW 0640 GS□	○				○			
6,5		MDW 0650 GS□	○				○			
6,6		MDW 0660 GS□	○		26,1	34,5	○		36,1	44,5
6,7		MDW 0670 GS□	○				○			
6,8		MDW 0680 GS□	○				○			
6,9		MDW 0690 GS□	○				○			
7,0		MDW 0700 GS□	○				○			
7,1	8,0	MDW 0710 GS□	○	79,7	25,6	34,6	○	91,7	37,6	46,6
7,2		MDW 0720 GS□	○				○			
7,3		MDW 0730 GS□	○				○			
7,4		MDW 0740 GS□	○				○			
7,5		MDW 0750 GS□	○				○			
7,6		MDW 0760 GS□	○		28,1	37,7	○		40,1	49,7
7,7		MDW 0770 GS□	○				○			
7,8		MDW 0780 GS□	○				○			
7,9		MDW 0790 GS□	○				○			
8,0		MDW 0800 GS□	○				●			
8,1	9,0	MDW 0810 GS□	○	83,9	27,4	37,8	○	99,9	34,4	54,8
8,2		MDW 0820 GS□	○				○			
8,3		MDW 0830 GS□	○				○			
8,4		MDW 0840 GS□	○				○			
8,5		MDW 0850 GS□	○				○			
8,6		MDW 0860 GS□	○		29,1	39,9	○		46,1	56,9
8,7		MDW 0870 GS□	○				○			
8,8		MDW 0880 GS□	○				○			
8,9		MDW 0890 GS□	○				○			
9,0		MDW 0900 GS□	○				○			
9,1	10,0	MDW 0910 GS□	○	89,0	28,6	40,0	○	107,0	48,6	60,0
9,2		MDW 0920 GS□	○				○			
9,3		MDW 0930 GS□	○				○			
9,4		MDW 0940 GS□	○				○			
9,5		MDW 0950 GS□	○				○			
9,6		MDW 0960 GS□	○		30,0	42,0	○		50,0	62,0
9,7		MDW 0970 GS□	○				○			
9,8		MDW 0980 GS□	○				○			
9,9		MDW 0990 GS□	○				○			
10,0		MDW 1000 GS□	○				○			

■ Recommended Cutting Conditions for Multi-Drills GS Type

Diameter (mm)		Soft Steels (–200 HB)	General Steels (–300 HB)	Stainless Steels (–200 HB)	Grey Cast Irons	Ductile Cast Irons
–Ø 3	v_c	30–**50**–70	30–**45**–60	10–**30**–40	40–**70**–90	35–**55**–75
	f	0,12–0,20	0,10–0,20	0,06–0,12	0,15–0,30	0,12–0,20
–Ø 5	v_c	40–**70**–100	40–**60**–80	15–**40**–55	40–**70**–90	40–**60**–80
	f	0,15–0,25	0,15–0,25	0,08–0,15	0,15–0,30	0,15–0,25
–Ø 10	v_c	50–**80**–130	50–**70**–110	15–**45**–60	50–**80**–120	50–**70**–100
	f	0,20–0,35	0,20–0,35	0,10–0,20	0,20–0,35	0,20–0,35
–Ø 16	v_c	60–**90**–140	60–**80**–120	20–**50**–60	60–**90**–120	50–**70**–100
	f	0,25–0,35	0,25–0,35	0,10–0,20	0,25–0,35	0,25–0,35

(v_c : Cutting Speed (m/min), f : Feed Rate (mm/rev)) (Min – **Standard** – Max)

● = Euro stock
○ = Japan stock

MDW ... GS Type

GS Type for General Purpose Drilling of Steels

● GS Type



Grade: ACX70

● Diameter Ø 10,1–13,0 mm

(mm)

Dimensions		Cat. No.	Short Type (2D)				Long Type (4D)			
DC (mm)	ød		Stock	Dimensions			Stock	Dimensions		
		2, 4 ↘	2	L	ℓ_1	ℓ_2	4	L	ℓ_1	ℓ_2
10,1	11,0	MDW 1010 GS□	❍	95,3	30,6	43,2	❍	116,2	55,6	68,2
10,2		MDW 1020 GS□	❍				❍			
10,3		MDW 1030 GS□	❍				❍			
10,4		MDW 1040 GS□	❍				❍			
10,5		MDW 1050 GS□	❍				❍			
10,6		MDW 1060 GS□	❍		34,1	47,3	❍		57,1	70,3
10,7		MDW 1070 GS□	❍				❍			
10,8		MDW 1080 GS□	❍				❍			
10,9		MDW 1090 GS□	❍				❍			
11,0		MDW 1100 GS□	❍				❍			
11,1	12,0	MDW 1110 GS□	❍	102,5	33,6	47,4	❍	123,5	59,6	73,4
11,2		MDW 1120 GS□	❍				❍			
11,3		MDW 1130 GS□	❍				❍			
11,4		MDW 1140 GS□	❍				❍			
11,5		MDW 1150 GS□	❍				❍			
11,6		MDW 1160 GS□	❍		35,1	49,5	❍		61,1	75,5
11,7		MDW 1170 GS□	❍				❍			
11,8		MDW 1180 GS□	❍				❍			
11,9		MDW 1190 GS□	❍				❍			
12,0		MDW 1200 GS□	❍				❍			
12,1	13,0	MDW 1210 GS□	❍	102,7	34,6	49,6	❍	139,7	63,6	78,6
12,2		MDW 1220 GS□	❍				❍			
12,3		MDW 1230 GS□	❍				❍			
12,4		MDW 1240 GS□	❍				❍			
12,5		MDW 1250 GS□	❍				❍			
12,6		MDW 1260 GS□	❍		36,1	51,7	❍		65,1	80,7
12,7		MDW 1270 GS□	❍				❍			
12,8		MDW 1280 GS□	❍				❍			
12,9		MDW 1290 GS□	❍				❍			
13,0		MDW 1300 GS□	❍				❍			

● Diameter Ø 13,1–16,0 mm

(mm)

Dimensions		Cat. No.	Short Type (2D)				Long Type (4D)			
DC (mm)	ød		Stock	Dimensions			Stock	Dimensions		
		2, 4 ↘	2	L	ℓ_1	ℓ_2	4	L	ℓ_1	ℓ_2
13,1	14,0	MDW 1310 GS□	❍	107,9	36,6	52,8	❍	149,9	70,2	86,8
13,2		MDW 1320 GS□	❍				❍			
13,3		MDW 1330 GS□	❍				❍			
13,4		MDW 1340 GS□	❍				❍			
13,5		MDW 1350 GS□	❍				❍			
13,6		MDW 1360 GS□	❍		38,1	54,9	❍		72,1	88,9
13,7		MDW 1370 GS□	❍				❍			
13,8		MDW 1380 GS□	❍				❍			
13,9		MDW 1390 GS□	❍				❍			
14,0		MDW 1400 GS□	❍				❍			
14,1	15,0	MDW 1410 GS□	❍	111,1	37,6	55,0	❍	156,1	74,6	92,0
14,2		MDW 1420 GS□	❍				❍			
14,3		MDW 1430 GS□	❍				❍			
14,4		MDW 1440 GS□	❍				❍			
14,5		MDW 1450 GS□	❍				❍			
14,6		MDW 1460 GS□	❍		38,1	56,1	❍		76,1	94,1
14,7		MDW 1470 GS□	❍				❍			
14,8		MDW 1480 GS□	❍				❍			
14,9		MDW 1490 GS□	❍				❍			
15,0		MDW 1500 GS□	❍				❍			
15,1	16,0	MDW 1510 GS□	❍	115,5	37,6	56,2	❍	169,3	78,6	97,2
15,2		MDW 1520 GS□	❍				❍			
15,3		MDW 1530 GS□	❍				❍			
15,4		MDW 1540 GS□	❍				❍			
15,5		MDW 1550 GS□	❍				❍			
15,6		MDW 1560 GS□	❍		39,1	58,3	❍		80,1	99,3
15,7		MDW 1570 GS□	❍				❍			
15,8		MDW 1580 GS□	❍				❍			
15,9		MDW 1590 GS□	❍				❍			
16,0		MDW 1600 GS□	❍				❍			

■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs.
Please specify the Cat. No. For example, if the diameter of the drill is 10,2 mm, please indicate as follow.

E.g., **MDW 1020 GS 2/4,** ACX70 (Grade)

- **MDW**: SUPER MULTI-DRILLs
- **1020**: Drill diameter **10,2** mm
- **GS**: **GS** type MULTI-DRILLs
- **2/4**: Drilling depth (The ratio to ØD): –2 / –4

MDS ... SK-HAK Type

Short Type

TiAlN Coated Solid Carbide Drills to DIN6537 (Ø-Tolerance: m7)





Helix angle: 30°
ℓ_1 = Effective drilling length
Grade: ACW70

●Diameter Ø 4,0–8,0 mm

Dimensions (mm)			Cat. No.	DIN 6537 K (Short Type)			
øD (mm)	Shank			Stock	Dimensions (mm)		
	ød	ℓ_3		SK-HAK	L	ℓ_1	ℓ_2
4,0	6	36	MDS 040 SKHAK	●	66	17	24
4,1			MDS 041 SKHAK	❐			
4,2			MDS 042 SKHAK	●			
4,3			MDS 043 SKHAK	❐			
4,4			MDS 044 SKHAK	❐			
4,5			MDS 045 SKHAK	●			
4,6			MDS 046 SKHAK	❐			
4,7			MDS 047 SKHAK	❐			
4,8	6	36	MDS 048 SKHAK	❐	66	20	28
4,9			MDS 049 SKHAK	❐			
5,0			MDS 050 SKHAK	●			
5,1			MDS 051 SKHAK	●			
5,2			MDS 052 SKHAK	❐			
5,3			MDS 053 SKHAK	❐			
5,4			MDS 054 SKHAK	❐			
5,5			MDS 055 SKHAK	●			
5,6			MDS 056 SKHAK	❐			
5,7			MDS 057 SKHAK	❐			
5,8			MDS 058 SKHAK	❐			
5,9			MDS 059 SKHAK	❐			
6,0			MDS 060 SKHAK	●			
6,1	8	36	MDS 061 SKHAK	❐	79	24	34
6,2			MDS 062 SKHAK	❐			
6,3			MDS 063 SKHAK	❐			
6,4			MDS 064 SKHAK	❐			
6,5			MDS 065 SKHAK	●			
6,6			MDS 066 SKHAK	❐			
6,7			MDS 067 SKHAK	❐			
6,8			MDS 068 SKHAK	●			
6,9			MDS 069 SKHAK	❐			
7,0			MDS 070 SKHAK	●			
7,1	8	36	MDS 071 SKHAK	❐	79	29	41
7,2			MDS 072 SKHAK	❐			
7,3			MDS 073 SKHAK	❐			
7,4			MDS 074 SKHAK	❐			
7,5			MDS 075 SKHAK	●			
7,6			MDS 076 SKHAK	❐			
7,7			MDS 077 SKHAK	❐			
7,8			MDS 078 SKHAK	❐			
7,9			MDS 079 SKHAK	❐			
8,0			MDS 080 SKHAK	●			

●Diameter Ø 8,1–12,0 mm

Dimensions (mm)			Cat. No.	DIN 6537 K (Short Type)			
øD (mm)	Shank			Stock	Dimensions (mm)		
	ød	ℓ_3		SK-HAK	L	ℓ_1	ℓ_2
8,1	10	40	MDS 081 SKHAK	❐	89	35	47
8,2			MDS 082 SKHAK	❐			
8,3			MDS 083 SKHAK	❐			
8,4			MDS 084 SKHAK	❐			
8,5			MDS 085 SKHAK	●			
8,6			MDS 086 SKHAK	❐			
8,7			MDS 087 SKHAK	❐			
8,8			MDS 088 SKHAK	❐			
8,9			MDS 089 SKHAK	❐			
9,0			MDS 090 SKHAK	●			
9,1			MDS 091 SKHAK	❐	89	35	47
9,2			MDS 092 SKHAK	❐			
9,3			MDS 093 SKHAK	❐			
9,4			MDS 094 SKHAK	❐			
9,5			MDS 095 SKHAK	●			
9,6			MDS 096 SKHAK	❐			
9,7			MDS 097 SKHAK	❐			
9,8			MDS 098 SKHAK	❐			
9,9			MDS 099 SKHAK	❐			
10,0			MDS 100 SKHAK	●			
10,1	12	45	MDS 101 SKHAK	❐	102	40	55
10,2			MDS 102 SKHAK	❐			
10,3			MDS 103 SKHAK	❐			
10,4			MDS 104 SKHAK	❐			
10,5			MDS 105 SKHAK	●			
10,6			MDS 106 SKHAK	❐			
10,7			MDS 107 SKHAK	❐			
10,8			MDS 108 SKHAK	❐			
10,9			MDS 109 SKHAK	❐			
11,0			MDS 110 SKHAK	●			
11,1			MDS 111 SKHAK	❐	102	40	55
11,2			MDS 112 SKHAK	❐			
11,3			MDS 113 SKHAK	❐			
11,4			MDS 114 SKHAK	❐			
11,5			MDS 115 SKHAK	●			
11,6			MDS 116 SKHAK	❐			
11,7			MDS 117 SKHAK	❐			
11,8			MDS 118 SKHAK	❐			
11,9			MDS 119 SKHAK	❐			
12,0			MDS 120 SKHAK	●			

■ Recommended Cutting Conditions for K-HAK Type Multi-Drills

Diameter (mm)		Steels (<200 HB)	Steels (200–300 HB)	Alloy Steels (>200 HB)	Hardened Steels (45 HRC)	Stainless Steels (<200 HB)	Ductile Cast Irons	Grey Cast Irons	Titanium Alloys (Ti-6Al-4V)	Inconel (Inconel 718)
–Ø 5	v_c	50–**80**–120	50–**75**–100	40–**65**–80	20–**35**–50	30–**45**–60	40–**60**–100	80–**100**–120	20–**30**–40	10–**20**–30
	f	0,15–0,25	0,15–0,25	0,10–0,20	0,08–0,10	0,10–0,20	0,15–0,25	0,15–0,30	0,08–0,10	0,05–0,08
–Ø 10	v_c	50–**120**–140	70–**110**–140	40–**70**–80	30–**40**–60	50–**70**–90	70–**90**–120	100–**130**–140	25–**30**–40	15–**25**–30
	f	0,20–0,35	0,20–0,35	0,10–0,25	0,10–0,15	0,10–0,25	0,20–0,35	0,20–0,35	0,08–0,12	0,08–0,10
–Ø 16	v_c	90–**140**–170	80–**120**–150	40–**80**–100	30–**45**–60	50–**80**–110	80–**100**–130	100–**150**–160	25–**35**–40	20–**30**–35
	f	0,25–0,35	0,25–0,35	0,15–0,30	0,12–0,20	0,15–0,30	0,25–0,35	0,25–0,40	0,10–0,15	0,08–0,10
–Ø 20	v_c	100–**150**–180	80–**130**–160	50–**90**–120	30–**45**–60	50–**80**–110	80–**110**–140	100–**150**–160	25–**35**–40	20–**30**–35
	f	0,30–0,40	0,25–0,40	0,15–0,30	0,15–0,25	0,15–0,30	0,25–0,40	0,25–0,40	0,10–0,15	0,08–0,10

(v_c : Cutting Speed (m/min), f : Feed Rate (mm/rev)) (Min – **Standard** – Max)

● = Euro stock
❑ = Delivery on request

MDS ... MK-HAK Type

Long Type

TiAlN Coated Solid Carbide Drills to DIN6537 (Ø-Tolerance: m7)





Helix angle: 30°
ℓ_1 = Effective drilling length
Grade: ACW70

●Diameter Ø 4,0–8,0 mm

Dimensions (mm)			Cat. No.	DIN 6537 L (Long Type)			
øD (mm)	Shank			Stock	Dimensions (mm)		
	ød	ℓ_3		MK-HAK	L	ℓ_1	ℓ_2
4,0	6	36	MDS 040 MKHAK	●	74	29	36
4,1			MDS 041 MKHAK	❐			
4,2			MDS 042 MKHAK	●			
4,3			MDS 043 MKHAK	❐			
4,4			MDS 044 MKHAK	❐			
4,5			MDS 045 MKHAK	●			
4,6			MDS 046 MKHAK	❐			
4,7			MDS 047 MKHAK	❐			
4,8	6	36	MDS 048 MKHAK	❐	82	35	44
4,9			MDS 049 MKHAK	❐			
5,0			MDS 050 MKHAK	●			
5,1			MDS 051 MKHAK	❐			
5,2			MDS 052 MKHAK	❐			
5,3			MDS 053 MKHAK	❐			
5,4			MDS 054 MKHAK	❐			
5,5			MDS 055 MKHAK	●			
5,6			MDS 056 MKHAK	❐			
5,7			MDS 057 MKHAK	❐			
5,8			MDS 058 MKHAK	❐			
5,9			MDS 059 MKHAK	❐			
6,0			MDS 060 MKHAK	●			
6,1	8	36	MDS 061 MKHAK	❐	91	43	53
6,2			MDS 062 MKHAK	❐			
6,3			MDS 063 MKHAK	❐			
6,4			MDS 064 MKHAK	❐			
6,5			MDS 065 MKHAK	●			
6,6			MDS 066 MKHAK	❐			
6,7			MDS 067 MKHAK	❐			
6,8			MDS 068 MKHAK	●			
6,9			MDS 069 MKHAK	❐			
7,0			MDS 070 MKHAK	●			
7,1	8	36	MDS 071 MKHAK	❐	91	43	53
7,2			MDS 072 MKHAK	❐			
7,3			MDS 073 MKHAK	❐			
7,4			MDS 074 MKHAK	❐			
7,5			MDS 075 MKHAK	❐			
7,6			MDS 076 MKHAK	❐			
7,7			MDS 077 MKHAK	❐			
7,8			MDS 078 MKHAK	❐			
7,9			MDS 079 MKHAK	❐			
8,0			MDS 080 MKHAK	●			

●Diameter Ø 8,1–12,0 mm

Dimensions (mm)			Cat. No.	DIN 6537 L (Long Type)			
øD (mm)	Shank			Stock	Dimensions (mm)		
	ød	ℓ_3		MK-HAK	L	ℓ_1	ℓ_2
8,1	10	40	MDS 081 MKHAK	❐	103	49	61
8,2			MDS 082 MKHAK	❐			
8,3			MDS 083 MKHAK	❐			
8,4			MDS 084 MKHAK	❐			
8,5			MDS 085 MKHAK	●			
8,6			MDS 086 MKHAK	❐			
8,7			MDS 087 MKHAK	❐			
8,8			MDS 088 MKHAK	❐			
8,9			MDS 089 MKHAK	❐			
9,0			MDS 090 MKHAK	●			
9,1			MDS 091 MKHAK	❐	103	49	61
9,2			MDS 092 MKHAK	❐			
9,3			MDS 093 MKHAK	❐			
9,4			MDS 094 MKHAK	❐			
9,5			MDS 095 MKHAK	●			
9,6			MDS 096 MKHAK	❐			
9,7			MDS 097 MKHAK	❐			
9,8			MDS 098 MKHAK	❐			
9,9			MDS 099 MKHAK	❐			
10,0			MDS 100 MKHAK	●			
10,1	12	45	MDS 101 MKHAK	❐	118	56	71
10,2			MDS 102 MKHAK	●			
10,3			MDS 103 MKHAK	❐			
10,4			MDS 104 MKHAK	❐			
10,5			MDS 105 MKHAK	●			
10,6			MDS 106 MKHAK	❐			
10,7			MDS 107 MKHAK	❐			
10,8			MDS 108 MKHAK	❐			
10,9			MDS 109 MKHAK	❐			
11,0			MDS 110 MKHAK	●			
11,1			MDS 111 MKHAK	❐	118	56	71
11,2			MDS 112 MKHAK	❐			
11,3			MDS 113 MKHAK	❐			
11,4			MDS 114 MKHAK	❐			
11,5			MDS 115 MKHAK	●			
11,6			MDS 116 MKHAK	❐			
11,7			MDS 117 MKHAK	❐			
11,8			MDS 118 MKHAK	❐			
11,9			MDS 119 MKHAK	❐			
12,0			MDS 120 MKHAK	●			

■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs.
Please specify the Cat. No.
For example, if the diameter of the drill is 10,2 mm, please indicate as follow.

E.g., **MDS 102 MK-HAK**, ACW70 (Grade)

Multi-
Drill
Solid type

Drill diameter
10,2 mm

Cylindrical shank and spiral coolant holes to: DIN6535 Form HAK

S : 3–3,5 D
M : –5 D

General Features

The flat MultiDrill MDF type is a solid carbide drill that can be used for various purposes including high-efficiency spot facing and drilling in inclined and curved surfaces.

Advantages

- Can be used in a variety of drilling applications thanks to its point angle of 180°
  Applicable to high-efficiency spot facing, drilling in non-horizontal surfaces such as inclined and cylindrical surfaces and interrupted drilling. It also reduces burrs at hole exits.
- Improved machining stability
  Achieves high rigidity by employing RS THINNING, which ensures web thickness on the bottom face.
- Excellent chip evacuation performance
  Achieves excellent chip evacuation thanks to its wide chip pocket and high-quality rake face shape.
- Excellent cutting edge strength
  Achieves excellent cutting edge strength thanks to optimized cutting edge design.
- Expanded lineup of long type
  An expanded lineup of long type drills with diameters between Ø 3,0 and Ø 20,0 mm that are capable of drilling with an overhang length up to L/D = 10.
- Expanded lineup of types with oil hole
  Supports internal coolant. For deeper drilling (3D, 5D).

Improves drilling stability by ensuring web thickness.

Reduction of Burrs at Hole Exit



Work Material: 15CrMo5
Drill: MDF0500S2D (Ø 5,0 mm, 2D)
Cutting Conditions: v_c = 65 m/min, f = 0,12 mm/rev
H = 10 mm, 150 holes, wet
Equipment: Vertical machining center

Reduces exit burrs by more than half compared to general-purpose drills


Burr height: 0,18 mm
Flat MultiDrill MDF type


Burr height: 0,44 mm
Conventional general type

Applications


High-efficient spot facing


Hole expansion drilling


Drilling in non-horizontal surfaces (such as inclined and cylindrical)


Interrupted drilling


Cross drilling



Pre-tap hole drilling in thin sheets



Deep spot facing



Avoiding interference with work materials

Flat MultiDrill
MDF Type

Long Type (L2D)

For flat base drilling in long overhang conditions, hole expansion, burr prevention.
For deep flat base drilling and to avoid interference with workpiece.
Drilling that uses the long shank type requires a guide hole of the same diameter or a centering hole larger than the tool diameter.

Two types
Ⓐ ØDC < 6 mm Stepped Shank Products
Ⓑ ØDC ≥ 6 mm Relief Shank Products



With Oil Hole (H3D Type / H5D Type)

Support for internal coolant allows for deeper flat hole drilling.
Drilling that uses oil hole L/D = 5 requires a guide hole of the same diameter or a centering hole larger than the tool diameter.

Deep Spot Facing



Tool: MDF0600H5D
Work Material: C50, Ø 6 mm
Cutting Conditions: v_c = 140 m/min,
f = 0,15 mm/rev
H = 30 mm (5D)
Internal Coolant
Overhang 45 mm
Prepared Hole 3 mm (0,5D)

Long Overhang Spot Facing



Tool: MDF0600H3D
Work Material: C50,
Cutting Conditions: v_c = 90 m/min,
f = 0,1 mm/rev
H = 18mm (3D)
Internal Coolant
Overhang 35 mm

① Entrance ② Hole Bottom

Inclined Surface Drilling

Tool: MDF0500S2D
Work Material: 15CrMo5
Cutting Conditions: v_c = 65 m/min,
f = 0,08 mm/rev
H = 10mm
External MQL

Controlling Burrs and Chips when Withdrawn

Tool: MDF1000S2D
Work Material: St 42-3
Cutting Conditions: v_c = 75 m/min,
f = 0,12 mm/rev
H = 5mm
External MQL

Using Flat Drills, General-Purpose Drills and Endmills

Tool	Flat Drill **MDF Type**		General Purpose Drill GS/HGS Type		Endmill for Spot Facing GSX MILL Slot	
Hole Bottom Shape						
Drilling in horizontal surfaces	⊙	Feed rate approximately half of a general-purpose drill	○	Optimal	X	Within 1D, limited to low feed rate Feed rate one-fifth or lower of a general-purpose drill
Drilling in non-horizontal surfaces	○	Optimal (within 2D is recommended)	X	Unusable	⊙	Within 1D, limited to low feed rate Feed rate half or lower of a flat drill
Traversing	X	Unusable	X	Unusable	○	Optimal

Series

Application	Series	Diameter Range (mm)	Hole Depth (L/D)
External	MDF □□□□ S2D	Ø 0,3 – 20,0	≤ 2,0
	MDF □□□□ L2D	Ø 0,3 – 20,0	≤ 2,0
Internal	MDF □□□□ H3D	Ø 0,3 – 16,0	≤ 3,0
	MDF □□□□ H5D	Ø 0,3 – 16,0	≤ 5,0

External Coolant Supply (MDF S2D Type)

Carbon Steel <0,28%	Alloy Steel >0,28%	Tempered Steel	Hardened Steel <45HRC	Hardened Steel >45HRC	Stainless-Steel	Cast Iron	Ductile Cast Iron	Aluminium Alloy
◎	◎	◎	○		○	○	○	○

PVD 2D

● MDF Type



● Diameter Ø 0,3–7,0 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Cat. No.	Stock	Dimensions (mm) L	ℓ1	ℓ2
0,3*	3,0	MDF 0030S2D	❍	40	1,0	1,3
0,4*		0040S2D	❍		1,4	1,8
0,5	3,0	MDF 0050S2D	❍	40	2,0	2,2
0,6		0060S2D	❍		2,4	2,6
0,7		0070S2D	❍		2,8	3,1
0,8		0080S2D	❍		3,2	3,5
0,9		0090S2D	❍		3,6	4,0
1,0	3,0	MDF 0100S2D	●	45	4,0	4,4
1,1		0110S2D	❍		4,4	4,8
1,2		0120S2D	❍		4,8	5,3
1,3		0130S2D	❍		5,2	5,7
1,4		0140S2D	❍		5,6	6,2
1,5	3,0	MDF 0150S2D	●	45	6,0	6,6
1,6		0160S2D	❍		6,4	7,0
1,7		0170S2D	❍		6,8	7,5
1,8		0180S2D	❍		7,2	7,9
1,9		0190S2D	❍		7,6	8,4
2,0	4,0	MDF 0200S2D	●	50	8,0	8,8
2,1		0210S2D	●		8,4	9,2
2,2		0220S2D	●		8,8	9,7
2,3		0230S2D	●		9,2	10,1
2,4		0240S2D	●		9,6	10,6
2,5	4,0	MDF 0250S2D	●	50	10,0	11,0
2,6		0260S2D	●		10,4	11,4
2,7		0270S2D	●		10,8	11,9
2,8		0280S2D	●		11,2	12,3
2,9		0290S2D	●		11,6	12,8
3,0	6,0	MDF 0300S2D	●	50	12,0	13,2
3,1		0310S2D	●		12,4	13,6
3,2		0320S2D	●		12,8	14,1
3,3		0330S2D	●		13,2	14,5
3,4		0340S2D	●		13,6	15,0
3,5		0350S2D	●		14,0	15,4
3,6	6,0	MDF 0360S2D	●	50	14,4	15,8
3,7		0370S2D	●		14,8	16,3
3,8		0380S2D	●		15,2	16,7
3,9		0390S2D	●		15,6	17,2
4,0		0400S2D	●		16,0	17,6
4,1	6,0	MDF 0410S2D	●	60	16,4	18,0
4,2		0420S2D	●		16,8	18,5
4,3		0430S2D	●		17,2	18,9
4,4		0440S2D	●		17,6	19,4
4,5		0450S2D	●		18,0	19,8
4,6	6,0	MDF 0460S2D	●	60	18,4	20,2
4,7		0470S2D	●		18,8	20,7
4,8		0480S2D	●		19,2	21,1
4,9		0490S2D	●		19,6	21,6
5,0		0500S2D	●		20,0	22,0
5,1	6,0	MDF 0510S2D	●	60	20,4	22,4
5,2		0520S2D	●		20,8	22,9
5,3		0530S2D	●		21,2	23,3
5,4		0540S2D	●		21,6	23,8
5,5		0550S2D	●		22,0	24,2
5,6	6,0	MDF 0560S2D	●	60	22,4	24,6
5,7		0570S2D	●		22,8	25,1
5,8		0580S2D	●		23,2	25,5
5,9		0590S2D	●		23,6	26,0
6,0		0600S2D	●		24,0	26,4
6,1	8,0	MDF 0610S2D	●	70	24,4	26,8
6,2		0620S2D	●		24,8	27,3
6,3		0630S2D	●		25,2	27,7
6,4		0640S2D	●		25,6	28,2
6,5		0650S2D	●		26,0	28,6
6,6	8,0	MDF 0660S2D	●	70	26,4	29,0
6,7		0670S2D	●		26,8	29,5
6,8		0680S2D	●		27,2	29,9
6,9		0690S2D	●		27,6	30,4
7,0		0700S2D	●		28,0	30,8

● Diameter Ø 7,1–20,0 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Cat. No.	Stock	Dimensions (mm) L	ℓ1	ℓ2
7,1	8,0	MDF 0710S2D	●	70	28,4	31,2
7,2		0720S2D	●		28,8	31,7
7,3		0730S2D	●		29,2	32,1
7,4		0740S2D	●		29,6	32,6
7,5		0750S2D	●		30,0	33,0
7,6	8,0	MDF 0760S2D	●	70	30,4	33,4
7,7		0770S2D	●		30,8	33,9
7,8		0780S2D	●		31,2	34,3
7,9		0790S2D	●		31,6	34,8
8,0		0800S2D	●		32,0	35,2
8,1	10,0	MDF 0810S2D	❍	80	32,4	35,6
8,2		0820S2D	❍		32,8	36,1
8,3		0830S2D	❍		33,2	36,5
8,4		0840S2D	❍		33,6	37,0
8,5		0850S2D	●		34,0	37,4
8,6	10,0	MDF 0860S2D	❍	80	34,4	37,8
8,7		0870S2D	❍		34,8	38,3
8,8		0880S2D	❍		35,2	38,7
8,9		0890S2D	❍		35,6	39,2
9,0		0900S2D	●		36,0	39,6
9,1	10,0	MDF 0910S2D	❍	80	36,4	40,0
9,2		0920S2D	❍		36,8	40,5
9,3		0930S2D	❍		37,2	40,9
9,4		0940S2D	❍		37,6	41,4
9,5		0950S2D	●		38,0	41,8
9,6	10,0	MDF 0960S2D	❍	80	38,4	42,2
9,7		0970S2D	●		38,8	42,7
9,8		0980S2D	❍		39,2	43,1
9,9		0990S2D	❍		39,6	43,6
10,0		1000S2D	●		40,0	44,0
10,1	12,0	MDF 1010S2D	❍	90	40,4	44,4
10,2		1020S2D	❍		40,8	44,9
10,3		1030S2D	❍		41,2	45,3
10,4		1040S2D	❍		41,6	45,8
10,5		1050S2D	●		42,0	46,2
10,6	12,0	MDF 1060S2D	❍	90	42,4	46,6
10,7		1070S2D	❍		42,8	47,1
10,8		1080S2D	❍		43,2	47,5
10,9		1090S2D	❍		43,6	48,0
11,0		1100S2D	●		44,0	48,4
11,1	12,0	MDF 1110S2D	❍	90	44,4	48,8
11,2		1120S2D	❍		44,8	49,3
11,3		1130S2D	❍		45,2	49,7
11,4		1140S2D	❍		45,6	50,2
11,5		1150S2D	●		46,0	50,6
11,6	12,0	MDF 1160S2D	❍	90	46,4	51,0
11,7		1170S2D	❍		46,8	51,5
11,8		1180S2D	●		47,2	51,9
11,9		1190S2D	❍		47,6	52,4
12,0		1200S2D	●		48,0	52,8
12,5	14,0	MDF 1250S2D	❍	100	50,0	54,0
13,0		1300S2D	❍		52,0	56,8
13,5		1350S2D	❍	110	54,0	59,6
14,0		1400S2D	❍		56,0	62,4
14,5	16,0	MDF 1450S2D	❍	110	58,0	65,2
15,0		1500S2D	❍		60,0	68,0
15,5		1550S2D	❍	115	62,0	70,8
16,0		1600S2D	❍		64,0	73,6
16,5	18,0	MDF 1650S2D	❍	125	66,0	72,4
17,0		1700S2D	❍		68,0	75,2
17,5		1750S2D	❍	130	70,0	78,0
18,0		1800S2D	❍		72,0	80,8
18,5	20,0	MDF 1850S2D	❍	140	74,0	83,6
19,0		1900S2D	❍		76,0	86,4
19,5		1950S2D	❍		78,0	89,2
20,0		2000S2D	❍		80,0	92,0

*RS Thinning is used for ØDc ≥ 0,5mm.

Grade: ACF75

● = Euro stock
❍ = Japan stock

Flat MultiDrill
MDF Type

External Coolant Supply (L2D Type, Long Type)

Carbon Steel, Alloy Steel <0,28%	Carbon Steel, Alloy Steel >0,28%	Tempered Steel	Hardened Steel <45HRC	Hardened Steel >45HRC	Stainless-Steel	Cast Iron	Ductile Cast Iron	Aluminium Alloy
◎	◎	◎	○		○	○	○	○

PVD 2D

● ø DC ≤ ø DMM



● ø DC > ø DMM



● Diameter Ø 3,0–9,5 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Cat. No.	Stock	Dimensions (mm)		
				L	ℓ1	ℓ2
3,0	6,0	MDF 0300L2D	❍	100	13,5	30,0
3,1		0310L2D	❍		14,0	31,0
3,2		0320L2D	❍		14,4	32,0
3,3		0330L2D	❍		14,9	33,0
3,4		0340L2D	❍		15,3	34,0
3,5		0350L2D	❍		15,8	35,0
3,6	6,0	MDF 0360L2D	❍	100	16,2	36,0
3,7		0370L2D	❍		16,7	37,0
3,8		0380L2D	❍		17,1	38,0
3,9		0390L2D	❍		17,6	39,0
4,0		0400L2D	❍		18,0	40,0
4,1	6,0	MDF 0410L2D	❍	100	18,5	41,0
4,2		0420L2D	❍		18,9	42,0
4,3		0430L2D	❍		19,4	43,0
4,4		0440L2D	❍		19,8	44,0
4,5		0450L2D	❍		20,3	45,0
4,6	6,0	MDF 0460L2D	❍	100	20,7	46,0
4,7		0470L2D	❍		21,2	47,0
4,8		0480L2D	❍		21,6	48,0
4,9		0490L2D	❍		22,1	49,0
5,0		0500L2D	❍		22,5	50,0
5,1	6,0	MDF 0510L2D	❍	110	23,0	51,0
5,2		0520L2D	❍		23,4	52,0
5,3		0530L2D	❍		23,9	53,0
5,4		0540L2D	❍		24,3	54,0
5,5		0550L2D	❍		24,8	55,0
5,6	6,0	MDF 0560L2D	❍	110	25,2	56,0
5,7		0570L2D	❍		25,7	57,0
5,8		0580L2D	❍		26,1	58,0
5,9		0590L2D	❍		26,6	59,0
6,0	5,0	MDF 0600L2DS5	❍	110	27,0	30,0
6,0	6,0	MDF 0600L2D	❍	110	27,0	60,0
6,1	6,0	MDF 0610L2D	❍	120	27,5	30,5
6,2		0620L2D	❍		27,9	30,9
6,3		0630L2D	❍		28,4	31,4
6,4		0640L2D	❍		28,8	31,8
6,5		0650L2D	❍		29,3	32,3
6,6	6,0	MDF 0660L2D	❍	120	29,7	32,7
6,7		0670L2D	❍		30,2	33,2
6,8		0680L2D	❍		30,6	33,6
6,9		0690L2D	❍		31,1	34,1
7,0		0700L2D	❍		31,5	34,5
7,1	6,0	MDF 0710L2D	❍	130	32,0	35,0
7,2		0720L2D	❍		32,4	35,4
7,3		0730L2D	❍		32,9	35,9
7,4		0740L2D	❍		33,3	36,3
7,5		0750L2D	❍		33,8	36,8
7,6	6,0	MDF 0760L2D	❍	130	34,2	37,2
7,7		0770L2D	❍		34,7	37,7
7,8		0780L2D	❍		35,1	38,1
7,9		0790L2D	❍		35,6	38,6
8,0	6,0	MDF 0800L2DS6	❍	130	36,0	39,0
8,0	8,0	MDF 0800L2D	❍	130	36,0	80,0
8,1	8,0	MDF 0810L2D	❍	140	36,5	39,5
8,2		0820L2D	❍		36,9	39,9
8,3		0830L2D	❍		37,4	40,4
8,4		0840L2D	❍		37,8	40,8
8,5		0850L2D	❍		38,3	41,3
8,6	8,0	MDF 0860L2D	❍	140	38,7	41,7
8,7		0870L2D	❍		39,2	42,2
8,8		0880L2D	❍		39,6	42,6
8,9		0890L2D	❍		40,1	43,1
9,0		0900L2D	❍		40,5	43,5
9,1	8,0	MDF 0910L2D	❍	150	41,0	41,0
9,2		0920L2D	❍		41,4	41,4
9,3		0930L2D	❍		41,9	41,9
9,4		0940L2D	❍		42,3	42,3
9,5		0950L2D	❍		42,8	42,8

● Diameter Ø 9,6–20,0 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Cat. No.	Stock	Dimensions (mm)		
				L	ℓ1	ℓ2
9,6	8,0	MDF 0960L2D	❍	150	43,2	46,2
9,7		0970L2D	❍		43,7	46,7
9,8		0980L2D	❍		44,1	47,1
9,9		0990L2D	❍		44,6	47,6
10,0	8,0	MDF 1000L2DS8	❍	150	45,0	48,0
10,0	10,0	MDF 1000L2D	❍	150	45,0	100,0
10,1	10,0	MDF 1010L2D	❍	160	45,5	48,5
10,2		1020L2D	❍		45,9	48,9
10,3		1030L2D	❍		46,4	49,4
10,4		1040L2D	❍		46,8	49,8
10,5		1050L2D	❍		47,3	50,3
10,6	10,0	MDF 1060L2D	❍	160	47,7	50,7
10,7		1070L2D	❍		48,2	51,2
10,8		1080L2D	❍		48,6	51,6
10,9		1090L2D	❍		49,1	52,1
11,0		1100L2D	❍		49,5	52,5
11,1	10,0	MDF 1110L2D	❍	170	50,0	53,0
11,2		1120L2D	❍		50,4	53,4
11,3		1130L2D	❍		50,9	53,9
11,4		1140L2D	❍		51,3	54,3
11,5		1150L2D	❍		51,8	54,8
11,6	10,0	MDF 1160L2D	❍	170	52,2	55,2
11,7		1170L2D	❍		52,7	55,7
11,8		1180L2D	❍		53,1	56,1
11,9		1190L2D	❍		53,6	56,6
12,0	10,0	MDF 1200L2DS10	❍	170	54,0	57,0
12,0	12,0	MDF 1200L2D	❍	170	54,0	120,0
12,5	12,0	MDF 1250L2D	❍	180	56,3	59,3
13,0		1300L2D	❍		58,5	61,5
13,5		1350L2D	❍	190	60,8	63,8
14,0	12,0	MDF 1400L2DS12	❍	190	63,0	66,0
14,0	14,0	MDF 1400L2D	❍	190	63,0	140,0
14,5	14,0	MDF 1450L2D	❍	200	65,3	68,3
15,0		1500L2D	❍		67,5	70,5
15,5		1550L2D	❍	210	69,8	72,8
16,0	14,0	MDF 1600L2DS14	❍	210	72,0	75,0
16,0	16,0	MDF 1600L2D	❍	210	72,0	160,0
16,5	16,0	MDF 1650L2D	❍	220	74,3	77,3
17,0		1700L2D	❍		76,5	79,5
17,5		1750L2D	❍	230	78,8	81,8
18,0	16,0	MDF 1800L2DS16	❍	230	81,0	84,0
18,0	18,0	MDF 1800L2D	❍	230	81,0	180,0
18,5	18,0	MDF 1850L2D	❍	240	83,3	86,3
19,0		1900L2D	❍		85,5	88,5
19,5		1950L2D	❍	250	87,8	90,8
20,0	18,0	MDF 2000L2DS18	❍	250	90,0	93,0
20,0	20,0	MDF 2000L2D	❍	250	90,0	200,0

Grade: ACF75

Drilling that uses this tool requires a guide hole of the same diameter or a centering hole larger than the tool diameter.

■ Recommended Cutting Conditions

● MDF S2D Type

1. The recommended hole depth is 2 x DC. The depth shall be the depth from the highest point of the hole when drilling inclined surfaces.
2. The recommended cutting conditions are those for drilling in flat horizontal surfaces.
3. Adjust the feed rate according to the inclination angle when drilling in an inclined surface.
3.1 Set the feed rate at ≤ 70% when the inclination angle is ≤ 30°
3.2 Set the feed rate at ≤ 50% when the inclination angle is:> 30°
4. This product is a drilling tool. Do not use it for traversing or helical milling

(v_c: Cutting Speed m/min f: Feed Rate mm/rev)

Drill Diam. ØDC (mm)	Cutting Conditions	Soft Steel / General Steel (–250 HB)	Alloy Steel (–300 HB)	Hardened Steel (–50 HRC)	Stainless Steel (–200 HB)	Gray Cast Iron FC250	Ductile Cast Iron	Aluminium Alloy
–Ø 0,5	v_c	30–**40**–50	30–**35**–40	15–**20**–25	15–**20**–25	30–**40**–50	20–**30**–40	60–**80**–100
	f	0,004–**0,005**–0,006	0,004–**0,005**–0,006	0,001–**0,002**–0,003	0,003–**0,004**–0,005	0,004–**0,005**–0,006	0,001–**0,003**–0,005	0,003–**0,005**–0,007
–Ø 1,0	v_c	45–**55**–65	35–**45**–55	20–**30**–40	20–**25**–30	45–**55**–65	30–**40**–50	80–**100**–120
	f	0,01–**0,03**–0,05	0,01–**0,03**–0,05	0,002–**0,006**–0,01	0,005–**0,007**–0,01	0,01–**0,03**–0,05	0,005–**0,01**–0,015	0,01–**0,02**–0,03
–Ø 2,0	v_c	50–**60**–70	40–**50**–60	20–**30**–40	20–**30**–40	50–**60**–70	45–**55**–65	90–**110**–130
	f	0,02–**0,04**–0,06	0,02–**0,04**–0,06	0,01–**0,018**–0,025	0,01–**0,015**–0,02	0,02–**0,04**–0,06	0,015–**0,03**–0,045	0,03–**0,05**–0,07
–Ø 4,0	v_c	60–**75**–90	50–**65**–80	20–**30**–40	20–**30**–40	60–**75**–90	55–**65**–75	90–**110**–130
	f	0,06–**0,08**–0,10	0,05–**0,08**–0,10	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,06–**0,08**–0,10
–Ø 6,0	v_c	60–**75**–90	50–**65**–80	20–**30**–40	20–**30**–50	60–**75**–90	60–**70**–80	90–**110**–130
	f	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,04–**0,06**–0,08	0,03–**0,04**–0,05	0,05–**0,10**–0,15	0,06–**0,09**–0,12	0,05–**0,10**–0,15
–Ø 8,0	v_c	60–**75**–90	50–**65**–80	20–**30**–40	20–**30**–50	60–**75**–90	60–**70**–80	90–**110**–130
	f	0,10–**0,15**–0,20	0,10–**0,15**–0,20	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,10–**0,15**–0,20	0,10–**0,12**–0,15	0,10–**0,15**–0,20
–Ø 10,0	v_c	60–**75**–90	50–**65**–80	20–**30**–40	20–**30**–50	60–**75**–90	60–**70**–80	90–**110**–130
	f	0,12–**0,17**–0,22	0,12–**0,17**–0,22	0,08–**0,10**–0,12	0,06–**0,08**–0,10	0,12–**0,17**–0,22	0,12–**0,15**–0,18	0,12–**0,17**–0,22
–Ø 12,0	v_c	60–**75**–90	50–**65**–80	20–**30**–40	20–**30**–50	60–**75**–90	60–**70**–80	90–**110**–130
	f	0,15–**0,20**–0,25	0,15–**0,20**–0,25	0,12–**0,15**–0,18	0,08–**0,10**–0,12	0,15–**0,20**–0,25	0,15–**0,18**–0,20	0,15–**0,20**–0,25
–Ø 16,0	v_c	60–**75**–90	50–**65**–80	20–**30**–40	20–**30**–50	60–**75**–90	60–**70**–80	90–**110**–130
	f	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,14–**0,17**–0,20	0,10–**0,15**–0,20	0,17–**0,22**–0,27	0,15–**0,20**–0,25	0,20–**0,25**–0,30
–Ø 20,0	v_c	60–**75**–90	50–**65**–80	20–**30**–40	20–**30**–50	60–**75**–90	60–**70**–80	90–**110**–130
	f	0,25–**0,30**–0,35	0,25–**0,30**–0,35	0,16–**0,19**–0,22	0,15–**0,20**–0,25	0,25–**0,30**–0,35	0,20 - **0,25** - 0,30	0,25–**0,30**–0,35

Min. - **Optimum** - Max.

● MDF L2D Type, Long Type

1. Drilling that uses this tool requires a guide hole of the same diameter.
2. The cutting conditions are the recommended conditions with a guide hole.
3. The recommended hole depth is 5 x DC. The depth is measured from the highest point of the hole on drilling in inclined surfaces.
4. This product is a drilling tool. Do not use it for traversing or helical milling.

(v_c: Cutting Speed m/min f: Feed Rate mm/rev)

Drill Diam. ØDC (mm)	Cutting Conditions	Soft Steel / General Steel (–250 HB)	Alloy Steel (–300 HB)	Hardened Steel (–50 HRC)	Stainless Steel (–200 HB)	Gray Cast Iron FC250	Ductile Cast Iron	Aluminium Alloy
–Ø 4,0	v_c	60–**80**–100	50–**70**–90	20–**30**–40	20–**30**–40	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,06–**0,08**–0,10	0,05–**0,08**–0,10	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,06–**0,08**–0,10
–Ø 6,0	v_c	60–**80**–100	50–**70**–90	20–**30**–40	20–**30**–50	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,04–**0,06**–0,08	0,03–**0,04**–0,05	0,05–**0,10**–0,15	0,06–**0,09**–0,12	0,05–**0,10**–0,15
–Ø 8,0	v_c	60–**80**–100	50–**70**–90	20–**30**–40	20–**30**–50	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,10–**0,15**–0,20	0,10–**0,15**–0,20	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,10–**0,15**–0,20	0,10–**0,12**–0,15	0,10–**0,15**–0,20
–Ø 10,0	v_c	60–**80**–100	50–**70**–90	20–**30**–40	20–**30**–50	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,15–**0,20**–0,25	0,15–**0,20**–0,25	0,08–**0,10**–0,12	0,06–**0,08**–0,10	0,15–**0,20**–0,25	0,12–**0,15**–0,18	0,15–**0,20**–0,25
–Ø 12,0	v_c	60–**80**–100	50–**70**–90	20–**30**–40	20–**30**–50	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,12–**0,15**–0,18	0,08–**0,10**–0,12	0,17–**0,22**–0,27	0,15–**0,20**–0,25	0,20–**0,25**–0,30
–Ø 16,0	v_c	60–**80**–100	50–**70**–90	20–**30**–40	20–**30**–50	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,14–**0,17**–0,20	0,10–**0,15**–0,20	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,25–**0,30**–0,35
–Ø 20,0	v_c	60–**80**–100	50–**70**–90	20–**30**–40	20–**30**–50	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,25–**0,30**–0,35	0,25–**0,30**–0,35	0,16–**0,19**–0,22	0,15–**0,20**–0,25	0,30–**0,35**–0,40	0,25–**0,30**–0,35	0,35–**0,40**–0,45

Min. - **Optimum** - Max.

● = Euro stock
❍ = Japan stock

Flat MultiDrill
MDF Type

Carbon Steel <0,28%	Alloy Steel >0,28%	Tempered Steel	Hardened Steel <45HRC	Hardened Steel >45HRC	Stainless-Steel	Cast Iron	Ductile Cast Iron	Aluminium Alloy
◎	◎	◎	○		○	○	○	○

PVD 3D 5D

■ Internal Coolant Supply (MDF H3D/H5D Type)

● MDF Type 3D Single Margin



● MDF Type 5D Double Margin



● Diameter Ø 3,0–6,0 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Hole Depth (L/D)	Cat. No.	Stock	Dimensions (mm) L	ℓ1	ℓ2
3,0	3	3	MDF 0300H3D	●	68	13,5	16,5
		5	0300H5D	●	78	20,1	23,1
3,1	4	3	MDF 0310H3D	❍	72	14,0	17,0
		5	0310H5D	❍	86	20,8	23,8
3,2	4	3	0320H3D	❍	72	14,4	17,4
		5	0320H5D	❍	86	21,4	24,4
3,3	4	3	0330H3D	❍	72	14,9	17,9
		5	0330H5D	❍	86	22,1	25,1
3,4	4	3	0340H3D	❍	72	15,3	18,3
		5	0340H5D	❍	86	22,8	25,8
3,5	4	3	0350H3D	●	72	15,8	18,8
		5	0350H5D	●	86	23,5	26,5
3,6	4	3	MDF 0360H3D	❍	72	16,2	19,2
		5	0360H5D	❍	86	24,1	27,1
3,7	4	3	0370H3D	❍	72	16,7	19,7
		5	0370H5D	❍	86	24,8	27,8
3,8	4	3	0380H3D	❍	72	17,1	20,1
		5	0380H5D	❍	86	25,5	28,5
3,9	4	3	0390H3D	❍	72	17,6	20,6
		5	0390H5D	❍	86	26,1	29,1
4,0	4	3	0400H3D	●	72	18,0	21,0
		5	0400H5D	●	86	26,8	29,8
4,1	5	3	MDF 0410H3D	❍	80	18,5	21,5
		5	0410H5D	❍	98	27,5	30,5
4,2	5	3	0420H3D	❍	80	18,9	21,9
		5	0420H5D	❍	98	28,1	31,1
4,3	5	3	0430H3D	❍	80	19,4	22,4
		5	0430H5D	❍	98	28,8	31,8
4,4	5	3	0440H3D	❍	80	19,8	22,8
		5	0440H5D	❍	98	29,5	32,5
4,5	5	3	0450H3D	●	80	20,3	23,3
		5	0450H5D	●	98	30,2	33,2
4,6	5	3	MDF 0460H3D	❍	80	20,7	23,7
		5	0460H5D	❍	98	30,8	33,8
4,7	5	3	0470H3D	❍	80	21,2	24,2
		5	0470H5D	❍	98	31,5	34,5
4,8	5	3	0480H3D	❍	80	21,6	24,6
		5	0480H5D	❍	98	32,2	35,2
4,9	5	3	0490H3D	❍	80	22,1	25,1
		5	0490H5D	❍	98	32,8	35,8
5,0	5	3	0500H3D	●	80	22,5	25,5
		5	0500H5D	●	98	33,5	36,5
5,1	6	3	MDF 0510H3D	❍	82	23,0	26,0
		5	0510H5D	❍	100	34,2	37,2
5,2	6	3	0520H3D	❍	82	23,4	26,4
		5	0520H5D	❍	100	34,8	37,8
5,3	6	3	0530H3D	❍	82	23,9	26,9
		5	0530H5D	❍	100	35,5	38,5
5,4	6	3	0540H3D	❍	82	24,3	27,3
		5	0540H5D	❍	100	36,2	39,2
5,5	6	3	0550H3D	●	82	24,8	27,8
		5	0550H5D	●	100	36,9	39,9
5,6	6	3	MDF 0560H3D	❍	82	25,2	28,2
		5	0560H5D	❍	100	37,5	40,5
5,7	6	3	0570H3D	❍	82	25,7	28,7
		5	0570H5D	❍	100	38,2	41,2
5,8	6	3	0580H3D	❍	82	26,1	29,1
		5	0580H5D	❍	100	38,9	41,9
5,9	6	3	0590H3D	❍	82	26,6	29,6
		5	0590H5D	❍	100	39,5	42,5
6,0	6	3	0600H3D	●	82	27,0	30,0
		5	0600H5D	●	100	40,2	43,2

● Diameter Ø 6,1–9,0 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Hole Depth (L/D)	Cat. No.	Stock	Dimensions (mm) L	ℓ1	ℓ2
6,1	7	3	MDF 0610H3D	❍	88	27,5	30,5
		5	0610H5D	❍	109	40,9	43,9
6,2	7	3	0620H3D	❍	88	27,9	30,9
		5	0620H5D	❍	109	41,5	44,5
6,3	7	3	0630H3D	❍	88	28,4	31,4
		5	0630H5D	❍	109	42,2	45,2
6,4	7	3	0640H3D	❍	88	28,8	31,8
		5	0640H5D	❍	109	42,9	45,9
6,5	7	3	0650H3D	●	88	29,3	32,3
		5	0650H5D	●	109	43,6	46,6
6,6	7	3	MDF 0660H3D	❍	88	29,7	32,7
		5	0660H5D	❍	109	44,2	47,2
6,7	7	3	0670H3D	❍	88	30,2	33,2
		5	0670H5D	❍	109	44,9	47,9
6,8	7	3	0680H3D	❍	88	30,6	33,6
		5	0680H5D	❍	109	45,6	48,6
6,9	7	3	0690H3D	❍	88	31,1	34,1
		5	0690H5D	❍	109	46,2	49,2
7,0	7	3	0700H3D	●	88	31,5	34,5
		5	0700H5D	●	109	46,9	49,9
7,1	8	3	MDF 0710H3D	❍	94	32,0	35,0
		5	0710H5D	❍	118	47,6	50,6
7,2	8	3	0720H3D	❍	94	32,4	35,4
		5	0720H5D	❍	118	48,2	51,2
7,3	8	3	0730H3D	❍	94	32,9	35,9
		5	0730H5D	❍	118	48,9	51,9
7,4	8	3	0740H3D	❍	94	33,3	36,3
		5	0740H5D	❍	118	49,6	52,6
7,5	8	3	0750H3D	●	94	33,8	36,8
		5	0750H5D	●	118	50,3	53,3
7,6	8	3	MDF 0760H3D	❍	94	34,2	37,2
		5	0760H5D	❍	118	50,9	53,9
7,7	8	3	0770H3D	❍	94	34,7	37,7
		5	0770H5D	❍	118	51,6	54,6
7,8	8	3	0780H3D	❍	94	35,1	38,1
		5	0780H5D	❍	118	52,3	55,3
7,9	8	3	0790H3D	❍	94	35,6	38,6
		5	0790H5D	❍	118	52,9	55,9
8,0	8	3	0800H3D	●	94	36,0	39,0
		5	0800H5D	●	118	53,6	56,6
8,1	9	3	MDF 0810H3D	❍	100	36,5	39,5
		5	0810H5D	❍	127	54,3	57,3
8,2	9	3	0820H3D	❍	100	36,9	39,9
		5	0820H5D	❍	127	54,9	57,9
8,3	9	3	0830H3D	❍	100	37,4	40,4
		5	0830H5D	❍	127	55,6	58,6
8,4	9	3	0840H3D	❍	100	37,8	40,8
		5	0840H5D	❍	127	56,3	59,3
8,5	9	3	0850H3D	●	100	38,3	41,3
		5	0850H5D	●	127	57,0	60,0
8,6	9	3	MDF 0860H3D	❍	100	38,7	41,7
		5	0860H5D	❍	127	57,6	60,6
8,7	9	3	0870H3D	❍	100	39,2	42,2
		5	0870H5D	❍	127	58,3	61,3
8,8	9	3	0880H3D	❍	100	39,6	42,6
		5	0880H5D	❍	127	59,0	62,0
8,9	9	3	0890H3D	❍	100	40,1	43,1
		5	0890H5D	❍	127	59,6	62,6
9,0	9	3	0900H3D	●	100	40,5	43,5
		5	0900H5D	●	127	60,3	63,3

Grade: ACF75

Internal Coolant Supply (MDF H3D/H5D Type)

Carbon Steel, Alloy Steel <0,28%	Carbon Steel, Alloy Steel >0,28%	Tempered Steel	Hardened Steel <45HRC	Hardened Steel >45HRC	Stainless-Steel	Cast Iron	Ductile Cast Iron	Aluminium Alloy
◎	◎	◎	○		○	○	○	○

PVD 3D 5D

● MDF Type 3D Single Margin



● MDF Type 5D Double Margin



ØDsh6

● Diameter Ø 9,1–12,0 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Hole Depth (L/D)	Cat. No.	Stock	Dimensions (mm)		
					L	*ℓ1*	*ℓ2*
9,1	10	3	MDF 0910H3D	❍	106	41,0	44,0
		5	0910H5D	❍	136	61,0	64,0
9,2	10	3	0920H3D	❍	106	41,4	44,4
		5	0920H5D	❍	136	61,6	64,6
9,3	10	3	0930H3D	❍	106	41,9	44,9
		5	0930H5D	❍	136	62,3	65,3
9,4	10	3	0940H3D	❍	106	42,3	45,3
		5	0940H5D	❍	136	63,0	66,0
9,5	10	3	0950H3D	●	106	42,8	45,8
		5	0950H5D	●	136	63,7	66,7
9,6	10	3	MDF 0960H3D	❍	106	43,2	46,2
		5	0960H5D	❍	136	64,3	67,3
9,7	10	3	0970H3D	❍	106	43,7	46,7
		5	0970H5D	❍	136	65,0	68,0
9,8	10	3	0980H3D	❍	106	44,1	47,1
		5	0980H5D	❍	136	65,7	68,7
9,9	10	3	0990H3D	❍	106	44,6	47,6
		5	0990H5D	❍	136	66,3	69,3
10,0	10	3	1000H3D	●	106	45,0	48,0
		5	1000H5D	●	136	67,0	70,0
10,1	11	3	MDF 1010H3D	❍	116	45,5	48,5
		5	1010H5D	❍	149	67,7	70,7
10,2	11	3	1020H3D	❍	116	45,9	48,9
		5	1020H5D	❍	149	68,3	71,3
10,3	11	3	1030H3D	❍	116	46,4	49,4
		5	1030H5D	❍	149	69,0	72,0
10,4	11	3	1040H3D	❍	116	46,8	49,8
		5	1040H5D	❍	149	69,7	72,7
10,5	11	3	1050H3D	●	116	47,3	50,3
		5	1050H5D	●	149	70,4	73,4
10,6	11	3	MDF 1060H3D	❍	116	47,7	50,7
		5	1060H5D	❍	149	71,0	74,0
10,7	11	3	1070H3D	❍	116	48,2	51,2
		5	1070H5D	❍	149	71,7	74,7
10,8	11	3	1080H3D	❍	116	48,6	51,6
		5	1080H5D	❍	149	72,4	75,4
10,9	11	3	1090H3D	❍	116	49,1	52,1
		5	1090H5D	❍	149	73,0	76,0
11,0	11	3	1100H3D	●	116	49,5	52,5
		5	1100H5D	●	149	73,7	76,7
11,1	12	3	MDF 1110H3D	❍	122	50,0	53,0
		5	1110H5D	❍	158	74,4	77,4
11,2	12	3	1120H3D	❍	122	50,4	53,4
		5	1120H5D	❍	158	75,0	78,0
11,3	12	3	1130H3D	❍	122	50,9	53,9
		5	1130H5D	❍	158	75,7	78,7
11,4	12	3	1140H3D	❍	122	51,3	54,3
		5	1140H5D	❍	158	76,4	79,4
11,5	12	3	1150H3D	●	122	51,8	54,8
		5	1150H5D	●	158	77,1	80,1
11,6	12	3	MDF 1160H3D	❍	122	52,2	55,2
		5	1160H5D	❍	158	77,7	80,7
11,7	12	3	1170H3D	❍	122	52,7	55,7
		5	1170H5D	❍	158	78,4	81,4
11,8	12	3	1180H3D	❍	122	53,1	56,1
		5	1180H5D	❍	158	79,1	82,1
11,9	12	3	1190H3D	❍	122	53,6	56,6
		5	1190H5D	❍	158	79,7	82,7
12,0	12	3	1200H3D	●	122	54,0	57,0
		5	1200H5D	●	158	80,4	83,4

● Diameter Ø 12,5–16,0 mm

Diameter ØDc (mm)	Shank ØDs (mm)	Hole Depth (L/D)	Cat. No.	Stock	Dimensions (mm)		
					L	*ℓ1*	*ℓ2*
12,5	13	3	MDF 1250H3D	❍	128	56,3	59,3
		5	1250H5D	❍	167	83,8	86,8
13,0	13	3	1300H3D	❍	128	58,5	61,5
		5	1300H5D	❍	167	87,1	90,1
13,5	14	3	MDF 1350H3D	❍	134	60,8	63,8
		5	1350H5D	❍	176	90,5	93,5
14,0	14	3	1400H3D	❍	134	63,0	66,0
		5	1400H5D	❍	176	93,8	96,8
14,5	15	3	MDF 1450H3D	❍	140	65,3	68,3
		5	1450H5D	❍	185	97,2	100,2
15,0	15	3	1500H3D	❍	140	67,5	70,5
		5	1500H5D	❍	185	100,5	103,5
15,5	16	3	MDF 1550H3D	❍	146	69,8	72,8
		5	1550H5D	❍	194	103,9	106,9
16,0	16	3	1600H3D	❍	146	72,0	75,0
		5	1600H5D	❍	194	107,2	110,2

Grade: ACF75

● = Euro stock
❍ = Japan stock

■ Recommended Cutting Conditions

● MDF H3D Type with Oil Hole

1. The recommended hole depth is 3 x DC. The depth is measured from the highest point of the hole on drilling in inclined surfaces.
2. The recommended cutting conditions are those for drilling on flat horizontal surfaces.
3. Adjust the feed rate according to the inclination angle when drilling in an inclined surface.
3.1 Set the feed rate at ≤ 70 % when the inclination angle is ≤ 30°.
3.2 Set the feed rate at ≤ 50 % when the inclination angle is > 30°.
4. This product is a drilling tool. Do not use it for traversing or helical milling.
5. A guide hole of the same diameter is recommended when drilling stainless steel.

(v_c: Cutting Speed m/min f: Feed Rate mm/rev)

Drill Diam. ØDC(mm)	Cutting Conditions	Soft Steel / General Steel (–250 HB)	Alloy Steel (–300 HB)	Hardened Steel (–50 HRC)	Stainless Steel (–200 HB)	Gray Cast Iron FC250	Ductile Cast Iron	Aluminium Alloy
–Ø 4,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,06–**0,08**–0,10	0,05–**0,08**–0,10	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,06–**0,08**–0,10
–Ø 6,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	70–**80**–90	90–**120**–150
	f	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,04–**0,06**–0,08	0,03–**0,04**–0,05	0,05–**0,10**–0,15	0,06–**0,09**–0,12	0,05–**0,10**–0,15
–Ø 8,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	70–**80**–90	90–**120**–150
	f	0,10–**0,15**–0,20	0,10–**0,15**–0,20	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,10–**0,15**–0,20	0,10–**0,12**–0,15	0,10–**0,15**–0,20
–Ø 10,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	70–**80**–90	90–**120**–150
	f	0,12–**0,17**–0,22	0,12–**0,17**–0,22	0,08–**0,10**–0,12	0,06–**0,08**–0,10	0,12–**0,17**–0,22	0,12–**0,15**–0,18	0,15–**0,20**–0,25
–Ø 12,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	70–**80**–90	90–**120**–150
	f	0,15–**0,20**–0,25	0,15–**0,20**–0,25	0,12–**0,15**–0,18	0,08–**0,10**–0,12	0,15–**0,20**–0,25	0,15–**0,18**–0,20	0,20–**0,25**–0,30
–Ø 16,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	70–**80**–90	90–**120**–150
	f	0,15–**0,20**–0,25	0,15–**0,20**–0,25	0,12–**0,15**–0,18	0,10–**0,15**–0,20	0,17–**0,22**–0,27	0,15–**0,20**–0,25	0,25–**0,30**–0,40

Min. - **Optimum** - Max.

● MDF H5D Type with Oil Hole

1. Drilling that uses this tool requires a guide hole of the same diameter.
2. The cutting conditions are the recommended conditions with a guide hole.
3. The recommended hole depth is 5 x DC. The depth is measured from the highest point of the hole on drilling in inclined surfaces.
4. This product is a drilling tool. Do not use it for traversing or helical milling.

(v_c: Cutting Speed m/min f: Feed Rate mm/rev)

Drill Diam. ØDC(mm)	Cutting Conditions	Soft Steel / General Steel (–250 HB)	Alloy Steel (–300 HB)	Hardened Steel (–50 HRC)	Stainless Steel (–200 HB)	Gray Cast Iron FC250	Ductile Cast Iron	Aluminium Alloy
–Ø 4,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,06–**0,08**–0,10	0,05–**0,08**–0,10	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,06–**0,08**–0,10
–Ø 6,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70– **85**–100	65–**75**–85	90–**120**–150
	f	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,04–**0,06**–0,08	0,03–**0,04**–0,05	0,05–**0,10**–0,15	0,06–**0,09**–0,12	0,05–**0,10**–0,15
–Ø 8,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,10–**0,15**–0,20	0,10–**0,15**–0,20	0,06–**0,08**–0,10	0,04–**0,06**–0,08	0,10–**0,15**–0,20	0,10–**0,12**–0,15	0,10–**0,15**–0,20
–Ø 10,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,15–**0,20**–0,25	0,15–**0,20**–0,25	0,08–**0,10**–0,12	0,06–**0,08**–0,10	0,15–**0,20**–0,25	0,12–**0,15**–0,18	0,15–**0,20**–0,25
–Ø 12,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,12–**0,15**–0,18	0,08–**0,10**–0,12	0,17–**0,22**–0,27	0,15–**0,20**–0,25	0,20–**0,25**–0,30
–Ø 16,0	v_c	70–**85**–100	60–**75**–90	30–**40**–50	25–**35**–45	70–**85**–100	65–**75**–85	90–**120**–150
	f	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,14–**0,17**–0,20	0,10–**0,15**–0,20	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,25–**0,30**–0,35

Min. - **Optimum** - Max.

XGHS Series

Applications	Series	Diameter Range (mm)	Hole Depth (L/D)
Deep Hole Drilling	MDW□□□□XHGS12	Ø 3,0 – 12,0	–12
	MDW□□□□XHGS15	Ø 3,0 – 12,0	–15
	MDW□□□□XHGS20	Ø 3,0 – 12,0	–20
	MDW□□□□XHGS25	Ø 3,0 – 12,0	–25
	MDW□□□□XHGS30	Ø 3,0 – 10,0	–30
Pilot Hole Drilling	MDW□□□□PHT	Ø 3,0 – 12,0	–2

General Features

Super MultiDrill XHGS series is a next-generation drill for deep hole drilling, features stable chip control and improved strength to further enhance efficiency of deep hole drilling.

Characteristics and Applications

Low Cutting Resistance

The application of a new special thinning shape „RX thinning“ reduces cutting resistance during high efficiency drilling.

RX THINNING

Conventional Drill



XHGS Series



Work Material: C45
Tools: MDW050XHT20 (conventional), MDW0500XHGS20 (Ø 5,0 mm, 20D)
Cutting Cond.: v_c = 80 m/min, f = 0,35 mm/rev, (⇨ at the time of entry penetration f = 0,08 mm/rev), H = 90 mm
Coolant: MQL

Chip Control

New groove shape „J flute“ with improved chip control stability when drilling deep holes.

J-flute

Improved chip evacuation makes it possible to reduce spindle load fluctuation, ensuring stable, long tool life.

Consistant Chips

XHGS Series

Conv. Drill

f = 0,35 mm/rev | f = 0,40 mm/rev | f = 0,45 mm/rev

Work Material: C45
Tools: MDW050XHT20 (conventional), MDW0500XHGS20 (Ø 5,0 mm, 20D)
Cutting Cond.: v_c = 80 m/min, H = 90 mm
Coolant: MQL

High Precision & Stability

The XHGS series provides excellent guide performance due to the unique design when compared to the conventional drill.

Conventional Drill

Excellent Guide Performance

XHGS Series

Recommended Cutting Conditions

Min. - **Optimum** - Max.

Drill Diameter DC (mm)	Cutting Conditions	Soft Steel (–200 HB)	General Steel (–250 HB)	Alloy Steel (–300 HB)	Hardened Steel (–40 HRC)	Cast Iron FC FCD
–Ø 3,0	v_c	50–**60**–80	60–**80**–100	40–**55**–70	30–**40**–50	40–**55**–70
	f	0,12–**0,15**–0,20	0,12–**0,15**–0,20	0,10–**0,13**–0,16	0,06–**0,08**–0,12	0,15–**0,18**–0,23
–Ø 5,0	v_c	50–**60**–80	60–**80**–100	50–**60**–70	30–**45**–55	50–**60**–70
	f	0,15–**0,20**–0,25	0,15–**0,23**–0,30	0,12–**0,15**–0,20	0,08–**0,10**–0,14	0,17–**0,25**–0,35
–Ø 10,0	v_c	50–**70**–90	60–**80**–110	50–**65**–80	30–**50**–60	50–**65**–80
	f	0,20–**0,25**–0,30	0,20–**0,25**–0,32	0,15–**0,20**–0,25	0,10–**0,15**–0,20	0,25–**0,28**–0,35
–Ø 12,0	v_c	60–**80**–100	60–**90**–120	50–**65**–80	40–**55**–70	50–**65**–80
	f	0,25–**0,30**–0,35	0,25–**0,30**–0,35	0,15–**0,23**–0,27	0,12–**0,15**–0,23	0,25–**0,30**–0,35

Note: Use lower speed when using MQL coolant and higher speed when using internal coolant. Vc: Cutting speed (m/min), f: Feed Rate (mm/rev)

Recommended Drilling Method

1. Drill a pilot hole using the dedicated PHT

Select the same nominal diameter for the dedicated pilot hole drill PHT type as the deep hole drill XHGS type.
(The pilot drill diameter is designed +0,02 mm to +0,05 mm larger than the long drill diameter)



2. Enter the pilot hole at reduced cutting data

Rotation speed: 500 min^{-1}
Feed rate: 1000 to 2000 mm/min



Important:
DO NOT enter pilot hole at higher cutting data, this will cause damage to the drill.

3. Increase rotation speed until the set cutting speed is reached, and start normal drilling operation



When using a NC machine, only begin drilling operation once full rotation speed is reached.

4. After drilling rotation speed is reduced and the drill is retracted from the work material

Rotation speed: 500 min^{-1}
Feed rate: 1.000 to 2.000 mm/min



Retracting a drill from the work material at a high rotation speed is dangerous as doing so may result in breakage due to run-out.

5. Other Notes

A flat base should be prepared when the surface for the pilot tool is slanted. Spot face using:

☑ MultiDrill MDF type

☑ Flat endmill

When the deep hole drill exits through an angle surface, decrease the feed rate to f = 0,05 mm/rev just before drilling through.

Coolant

1. Internal coolant supply

Use suitable coolant / emulsion
Pump pressure: Steel: 1,5 to 2,0 MPa (cooling effect increases at higher pressure, affecting chips/wear)
Cast iron & aluminium alloy: 4,0 to 6,0 MPa (priority on cooling)

2. Internal MQL

Airpressure: 0,5 MPa or higher
Discharge volume: It is recommended to set the maximum discharge volume possible on the machine.
*Consult the manufacturer before using with aluminium alloy.

● MDW … XHG S … HAK



Coated grade: ACX70

P ●MDW…XHG S Type for Deep Hole Drilling, Diameter Ø 3,0–12,0 mm

(mm)

Dimensions		Cat. No. 12, 15, 20, 25, 30 →	For 12 x D			For 15 x D			For 20 x D			For 25 x D			For 30 x D		
			Stock	Dimensions		Stock	Dimensions		Stock	Dimensions		Stock	Dimensions		Stock	Dimensions	
				L	ℓ		L	ℓ		L	ℓ		L	ℓ		L	ℓ
3,0	4,0	MDW 0300XHGS □□ HAK	●	85	57	●	94	66	●	109	81	●	124	96	●	139	111
3,5		0350XHGS □□ HAK	●	89	61	●	100	72	●	117	89	●	135	107	●	152	124
4,0		0400XHGS □□ HAK	●	95	67	●	107	79	●	127	99	●	147	119	●	167	139
4,5	5,0	MDW 0450XHGS □□ HAK	●	104	76	●	118	90	●	140	112	●	163	135	●	184	156
5,0		0500XHGS □□ HAK5*	●	108	80	●	123	95	●	148	120	●	173	145	●	198	170
5,0	6,0	MDW 0500XHGS □□ HAK	●	116	80	●	131	95	●	156	120	●	181	145	●	206	170
5,5		0550XHGS □□ HAK	●	124	88	●	141	105	●	168	132	●	196	160	●	223	187
6,0		0600XHGS □□ HAK	●	130	94	●	148	112	●	178	142	●	208	172	●	238	202
6,5	8,0	MDW 0650XHGS □□ HAK	●	138	102	●	158	122	●	190	154	●	223	187	●	255	219
6,8		0680XHGS □□ HAK	●	144	108	●	164	128	●	198	162	●	236	200	●	266	230
7,0		0700XHGS □□ HAK	●	145	109	●	166	130	●	201	165	●	236	200	●	271	235
7,5		0750XHGS □□ HAK	●	151	115	●	174	138	●	211	175	●	249	213	●	286	250
8,0		0800XHGS □□ HAK	●	157	121	●	181	145	●	221	185	●	261	225	●	301	265
8,5	10,0	MDW 0850XHGS □□ HAK	●	171	131	●	197	157	●	239	199	●	282	242	●	324	284
9,0		0900XHGS □□ HAK	●	177	137	●	204	164	●	249	209	●	294	254	●	339	299
9,5		0950XHGS □□ HAK	●	183	143	●	212	172	●	259	219	●	305	265	●	352	312
10,0		1000XHGS □□ HAK	●	187	147	●	217	177	●	267	227	●	317	277	●	367	327
10,5	12,0	MDW 1050XHGS □□ HAK	●	202	157	●	234	189	●	286	241	●	339	294	–	–	–
11,0		1100XHGS □□ HAK	●	208	163	●	241	196	●	296	251	●	351	306	–	–	–
11,5		1150XHGS □□ HAK	●	213	168	●	248	203	●	305	260	●	363	318	–	–	–
12,0		1200XHGS □□ HAK	●	219	174	●	255	210	●	315	270	●	375	330	–	–	–

(*) Cat. No. description: Drill-Ø = 5 mm, shank-Ø = 5 mm (E.g. for 20 x D: MDW050XHGS20HAK5)
Non-standard diamters and lengths on request (Ø 2,5–16,0 mm possible)

● MDW…PHT Type for Pilot Hole



Dimensions		Cat. No.	For Pilot Hole				
DC (mm)	ød (mm)		Stock	L	ℓ1	ℓ2	ℓ3
3,03	4,0	MDW 0303 PHT	●	52	9	22	28
3,53		0353 PHT	●	52	9	22	28
4,03	5,0	MDW 0403 PHT	●	59	12	29	28
4,53		0453 PHT	●	59	12	29	28
5,03	6,0	MDW 0503 PHT	●	71	15	33	36
5,53		0553 PHT	●	71	15	33	36
6,03	8,0	MDW 0603 PHT	●	76	18	38	36
6,53		0653 PHT	●	76	18	38	36
6,83		0683 PHT	●	76	18	38	36
7,03		0703 PHT	●	82	21	43	36
7,53		0753 PHT	●	82	21	43	36
8,03	10,0	MDW 0803 PHT	●	88	24	46	40
8,53		0853 PHT	●	88	24	46	40
9,03		0903 PHT	●	88	24	46	40
9,53		0953 PHT	●	88	24	46	40
10,03	12,0	MDW 1003 PHT	●	104	30	55	45
10,53		1053 PHT	●	104	30	55	45
11,03		1103 PHT	●	104	30	55	45
11,53		1153 PHT	●	104	30	55	45
12,03	14,0	MDW 1203 PHT	●	117	42	68	45

■ How to Order

Non stock items – minimum order 6 pieces
Always specify the catalogue number and drill diameter as shown
- eg drill diameter 5,0 mm = MDW 050

E.g., **MDW 050 X H G S 30 HAK ACX70** (Grade)

- Super MULTI-DRILL
- DC = 5,0 mm
- Extra long type
- With spiral coolant holes
- Special shape (RX thinning) + J flute
- Cutting edges for steel with double margin
- Drilling depth (L/D ratio)
- Shank type to DIN6535

● = Euro stock

Extra Long SUPER MULTI-DRILLs
MDW ... XHTA/PHT Type

● MDW ... XHT A ... HAK



Helix angle: 30°
Uncoated grade: KH03

N ●MDW...XHT A Type for Aluminium and Copper Alloys

(mm)

Dimensions		Cat. No.	For 20 x D			For 30 x D		
DC (mm)	ød (mm)	20, 30	Stock	Dimensions		Stock	Dimensions	
			20	L	ℓ_1	30	L	ℓ_1
4,0	4,0	MDW 040XHT A□□ HAK	●	127	97	●	167	137
5,0	6,0	MDW 050XHT A□□ HAK	●	156	118	●	206	168
6,0		060XHT A□□ HAK	●	178	138	●	238	198
7,0	8,0	MDW 070XHT A□□ HAK	●	201	162	●	271	232
8,0		080XHT A□□ HAK	●	221	182	●	301	262
9,0	10,0	MDW 090XHT A□□ HAK	●	249	205	●	339	295
10,0		100XHT A□□ HAK	●	267	225	●	367	325

⇨ All Long Drill series include an allowance to accomodate regrinding!
⇨ Uncoated carbide grade: KH03

■ How to Order

Non stock items – minimum order 6 pieces
Always specify the catalogue number and drill diameter as shown
- eg drill diameter 5,0 mm = MDW 050

E.g.,

MDW 050 X H T A 30 HAK (KH03) (Grade)

- Super MULTI-DRILL
- DC = 5,0 mm
- Extra long type
- with spiral coolant holes
- Shank type to DIN6535
- Drilling depth (L/D ratio)
- Cutting edges for Al and Cu alloys
- Special shape of clearance face

■ Recommended Cutting Conditions

Vc: Cutting speed (m/min), f: Feed Rate (mm/rev)

Drill Ø (mm) \ Work material		Aluminium Alloy
–Ø 5,0	v_c	80–160
	f	0,08–0,30
–Ø 6,0	v_c	80–160
	f	0,12–0,35
–Ø 8,0	v_c	80–180
	f	0,15–0,40
–Ø 10,0	v_c	80–180
	f	0,20–0,50
–Ø 12,0	v_c	80–180
	f	0,20–0,45

● MDW...PHT Type for Pilot Hole



Helix angle: 30°
ℓ_1 = Effective drilling length
Coated grade: ACW70

Dimensions		Cat. No.	For Pilot Hole				
DC (mm)	ød (mm)		Stock	Dimensions (mm)			
				L	ℓ_1	ℓ_2	ℓ_3
3,03	4,0	MDW 0303 PHT	●	52	9	22	28
3,53		0353 PHT	●	52	9	22	28
4,03	5,0	MDW 0403 PHT	●	59	12	29	28
4,53		0453 PHT	●	59	12	29	28
5,03	6,0	MDW 0503 PHT	●	71	15	33	36
5,53		0553 PHT	●	71	15	33	36
6,03	8,0	MDW 0603 PHT	●	76	18	38	36
6,53		0653 PHT	●	76	18	38	36
6,83		0683 PHT	●	76	18	38	36
7,03		0703 PHT	●	82	21	43	36
7,53		0753 PHT	●	82	21	43	36
8,03	10,0	MDW 0803 PHT	●	88	24	46	40
8,53		0853 PHT	●	88	24	46	40
9,03		0903 PHT	●	88	24	46	40
9,53		0953 PHT	●	88	24	46	40
10,03	12,0	MDW 1003 PHT	●	104	30	55	45
10,53		1053 PHT	●	104	30	55	45
11,03		1103 PHT	●	104	30	55	45
11,53		1153 PHT	●	104	30	55	45
12,03	14,0	MDW 1203 PHT	●	117	42	68	45

■ How to Order

Non stock items – minimum order 6 pieces
Always specify the catalogue number and drill diameter as shown -
eg. drill diameter 5,03 mm = MDW 0503

E.g.,

MDW 0503 PHT, ACW70

- Super MULTI-DRILL
- DC = 5,03 mm
- TiAlN coated grade
- Pilot drill with spiral coolant holes

MDW ... NHGS Type

DLC (Diamond Like Carbon) Coated Multi-Drills

With Coolant Holes (3D/5D/10D)



Characteristics

- **High efficiency drilling**
  AURORA COAT and strong helix design reduces cutting forces and improves edge sharpness.
- **Precision drilling**
  Special cutting edge design improves hole precision and quality.
- **Longer tool life**
  With AURORA COAT coupled with the cutting edge design, long and stable tool life can be achieved.
- **Deep hole (L/D = 20) drilling**
  Drills for deep hole drilling can be custom-made.
  Production range: Ø 3,0–16,0 mm
  total length: 50 times drill diameter (max. 290 mm)

Applicable Work Materials

- Aluminium Die Casting
- Aluminium Alloy
- Aluminium Alloy Casting
- Brass Casting
- Bronze Casting

Comparison of Cutting Force (Thrust Force)



Recommended Cutting Conditions

Diameter (mm)		Aluminium Alloy	Aluminium Die Casting	Copper Alloy
–Ø 5	v_c	80–160	80–180	80–160
	f	0,08–0,30	0,10–0,30	0,08–0,15
–Ø 10	v_c	80–180	80–200	60–180
	f	0,10–0,30	0,10–0,35	0,10–0,20
–Ø 16	v_c	80–200	80–200	80–200
	f	0,15–0,40	0,10–0,40	0,10–0,25

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev), Min–Max)

Diameter Ø 3,0–8,0 mm

(mm)

Dimensions		Cat. No.	3D Type			5D Type			10D Type		
			Stock	Dimensions		Stock	Dimensions		Stock	Dimensions	
øD	ød	3, 5, 10 ↘	3	L	ℓ	5	L	ℓ	10	L	ℓ
3,0	3,0	MDW 0300 NHGS□□	❐	68,6	18,1	❐	78,6	28,6	❐	92,6	42,6
3,1		MDW 0310 NHGS□□				❐					
3,2		MDW 0320 NHGS□□	❐			❐			❐		
3,3		MDW 0330 NHGS□□	❐		20,7	❐		32,7			49,7
3,4		MDW 0340 NHGS□□				❐			❐		
3,5		MDW 0350 NHGS□□	❐			❐			❐		
3,6		MDW 0360 NHGS□□				❐			❐		
3,65	4,0	MDW 0365 NHGS□□	❐	72,8		❐	86,8			106,8	
3,66		MDW 0366 NHGS□□				❐					
3,7		MDW 0370 NHGS□□			23,3	❐		36,8			56,8
3,8		MDW 0380 NHGS□□				❐					
3,9		MDW 0390 NHGS□□				❐			❐		
4,0		MDW 0400 NHGS□□	❐			❐			❐		
4,1		MDW 0410 NHGS□□	❐			❐					
4,2		MDW 0420 NHGS□□	❐			❐					
4,3		MDW 0430 NHGS□□			25,9	❐		40,9			63,9
4,4		MDW 0440 NHGS□□				❐					
4,5		MDW 0450 NHGS□□	❐			❐			❐		
4,6	5,0	MDW 0460 NHGS□□	❐	81,0		❐	99,0			125,0	
4,7		MDW 0470 NHGS□□				❐					
4,8		MDW 0480 NHGS□□			28,5	❐		45,0			71,0
4,9		MDW 0490 NHGS□□				❐			❐		
5,0		MDW 0500 NHGS□□	❐			❐			❐		
5,1		MDW 0510 NHGS□□				❐			❐		
5,2		MDW 0520 NHGS□□	❐			❐					
5,3		MDW 0530 NHGS□□	❐		28,6	❐		45,1			88,1
5,4		MDW 0540 NHGS□□				❐					
5,5		MDW 0550 NHGS□□	❐			❐			❐		
5,6	6,0	MDW 0560 NHGS□□		83,2		❐	101,2			137,2	
5,7		MDW 0570 NHGS□□				❐					
5,8		MDW 0580 NHGS□□			31,2	❐		49,2			85,2
5,9		MDW 0590 NHGS□□	❐			❐					
6,0		MDW 0600 NHGS□□	❐			❐			❐		
6,1		MDW 0610 NHGS□□				❐			❐		
6,2		MDW 0620 NHGS□□				❐					
6,3		MDW 0630 NHGS□□			33,8	❐		53,3			92,3
6,4		MDW 0640 NHGS□□				❐					
6,5		MDW 0650 NHGS□□	❐			❐			❐		
6,6	7,0	MDW 0660 NHGS□□		89,5		❐	110,5			152,5	
6,7		MDW 0670 NHGS□□	❐			❐			❐		
6,8		MDW 0680 NHGS□□	❐		36,5	❐		57,5	❐		99,5
6,9		MDW 0690 NHGS□□				❐					
7,0		MDW 0700 NHGS□□	❐			❐			❐		
7,1		MDW 0710 NHGS□□				❐					
7,2		MDW 0720 NHGS□□				❐			❐		
7,3		MDW 0730 NHGS□□			39,1	❐		61,6			116,6
7,35		MDW 0735 NHGS□□	❐			❐					
7,4		MDW 0740 NHGS□□	❐			❐					
7,5	8,0	MDW 0750 NHGS□□	❐	95,7		❐	119,7		❐	167,7	
7,6		MDW 0760 NHGS□□				❐					
7,7		MDW 0770 NHGS□□				❐					
7,8		MDW 0780 NHGS□□	❐		41,7	❐		65,7	❐		113,7
7,9		MDW 0790 NHGS□□				❐					
8,0		MDW 0800 NHGS□□	❐			❐			❐		

AURORA Coated NHGS Type, Grade: DL1300

❑ = Delivery on request

AURORA COAT SERIES
MDW ... NHGS Type

● NHGS 3/5 Type (Ø 3,0–16,0 mm)



● NHGS 10 Type (Ø 3,0–16,0 mm)



●Diameter Ø 8,1–13,0 mm

(mm)

Dimensions		Cat. No.	3D Type			5D Type			10D Type		
			Stock	Dimensions		Stock	Dimensions		Stock	Dimensions	
øD	ød	3, 5, 10 ↘	3	L		5	L	ℓ	10	L	ℓ
8,1	9,0	MDW 0810 NHGS□□		101,9	44,3	❒	128,9	69,8		182,9	118,8
8,2		MDW 0820 NHGS□□				❒					
8,3		MDW 0830 NHGS□□				❒					
8,4		MDW 0840 NHGS□□				❒					
8,5		MDW 0850 NHGS□□	❒			❒			❒		
8,6		MDW 0860 NHGS□□	❒		46,9	❒		73,9			127,9
8,7		MDW 0870 NHGS□□				❒					
8,8		MDW 0880 NHGS□□	❒			❒					
8,9		MDW 0890 NHGS□□				❒					
9,0		MDW 0900 NHGS□□	❒			❒			❒		
9,1	10,0	MDW 0910 NHGS□□		108,0	49,5	❒	138,0	78,0		198,0	135,0
9,2		MDW 0920 NHGS□□				❒					
9,21		MDW 0921 NHGS□□	❒			❒					
9,3		MDW 0930 NHGS□□				❒					
9,4		MDW 0940 NHGS□□	❒			❒					
9,5		MDW 0950 NHGS□□	❒			❒			❒		
9,6		MDW 0960 NHGS□□			52,0	❒		82,0			142,0
9,7		MDW 0970 NHGS□□				❒					
9,8		MDW 0980 NHGS□□				❒			❒		
9,9		MDW 0990 NHGS□□				❒					
10,0		MDW 1000 NHGS□□	❒			❒			❒		
10,1	11,0	MDW 1010 NHGS□□	❒	168,3	54,7		151,3	86,2		217,3	149,2
10,2		MDW 1020 NHGS□□									
10,3		MDW 1030 NHGS□□	❒			❒					
10,4		MDW 1040 NHGS□□				❒					
10,5		MDW 1050 NHGS□□	❒			❒			❒		
10,6		MDW 1060 NHGS□□	❒		57,3	❒		90,3			156,3
10,7		MDW 1070 NHGS□□									
10,8		MDW 1080 NHGS□□									
10,9		MDW 1090 NHGS□□									
11,0		MDW 1100 NHGS□□	❒			❒			❒		
11,08	12,0	MDW 1108 NHGS□□	❒	124,5	59,9	❒	160,5	94,4		232,5	163,4
11,1		MDW 1110 NHGS□□	❒			❒					
11,2		MDW 1120 NHGS□□	❒			❒					
11,3		MDW 1130 NHGS□□									
11,4		MDW 1140 NHGS□□	❒			❒					
11,5		MDW 1150 NHGS□□	❒			❒			❒		
11,6		MDW 1160 NHGS□□			62,5			98,5			170,5
11,7		MDW 1170 NHGS□□									
11,8		MDW 1180 NHGS□□									
11,9		MDW 1190 NHGS□□									
12,0		MDW 1200 NHGS□□	❒			❒			❒		
12,1	13,0	MDW 1210 NHGS□□	❒	130,7	65,1	❒	169,7	102,6		247,7	177,6
12,2		MDW 1220 NHGS□□									
12,3		MDW 1230 NHGS□□	❒			❒					
12,4		MDW 1240 NHGS□□									
12,5		MDW 1250 NHGS□□	❒			❒			❒		
12,6		MDW 1260 NHGS□□			67,7			106,7			184,7
12,7		MDW 1270 NHGS□□									
12,8		MDW 1280 NHGS□□									
12,9		MDW 1290 NHGS□□									
12,96		MDW 1296 NHGS□□	❒			❒					
13,0		MDW 1300 NHGS□□	❒			❒			❒		

●Diameter Ø 13,1–16,0 mm

(mm)

Dimensions		Cat. No.	3D Type			5D Type			10D Type		
			Stock	Dimensions		Stock	Dimensions		Stock	Dimensions	
øD	ød	3, 5, 10 ↘	3	L	ℓ	5	L	ℓ	10	L	ℓ
13,1	14,0	MDW 1310 NHGS□□		136,9	70,8		178,9	110,8		262,9	191,8
13,2		MDW 1320 NHGS□□									
13,3		MDW 1330 NHGS□□									
13,4		MDW 1340 NHGS□□									
13,5		MDW 1350 NHGS□□	❒			❒					
13,6		MDW 1360 NHGS□□			72,9			114,9			198,9
13,7		MDW 1370 NHGS□□									
13,8		MDW 1380 NHGS□□									
13,9		MDW 1390 NHGS□□									
14,0		MDW 1400 NHGS□□	❒			❒					
14,1	15,0	MDW 1410 NHGS□□	❒	141,1	75,5	❒	188,1	119,0		278,1	206
14,2		MDW 1420 NHGS□□									
14,3		MDW 1430 NHGS□□									
14,4		MDW 1440 NHGS□□									
14,5		MDW 1450 NHGS□□	❒			❒					
14,6		MDW 1460 NHGS□□			78,1			123,1			213,1
14,7		MDW 1470 NHGS□□									
14,8		MDW 1480 NHGS□□									
14,9		MDW 1490 NHGS□□	❒			❒					
14,96		MDW 1496 NHGS□□	❒			❒					
15,0		MDW 1500 NHGS□□	❒			❒					
15,1	16,0	MDW 1510 NHGS□□		149,3	80,7		197,3	127,2		293,3	220,2
15,2		MDW 1520 NHGS□□									
15,3		MDW 1530 NHGS□□									
15,4		MDW 1540 NHGS□□									
15,5		MDW 1550 NHGS□□	❒			❒					
15,6		MDW 1560 NHGS□□			83,3			131,3			227,3
15,7		MDW 1570 NHGS□□									
15,8		MDW 1580 NHGS□□									
15,9		MDW 1590 NHGS□□									
16,0		MDW 1600 NHGS□□	❒			❒					

AURORA Coated NHGS Type, Grade: DL1300

■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs.
Please specify the Cat. No.
For example, if the diameter of the drill is 10,3 mm and the ratio to øD is 5, please indicate as follow.

E.g.,

MDW 1030 NHGS 5 , DL1300 (Grade)

- MDW: Super MULTI-DRILL
- 1030: DC = 10,3 mm
- H: Applicable work materials
- GS: with spiral coolant holes
- 5: Drilling depth (The ratio to øD): –3 / –**5** / –10
- NHGS: NHGS type Multi-Drills

Micro Long Drills
MLDH ....L/P Type

General Features

Micro Long Drills are oil-hole drills for high efficiency drilling that were developed for drilling deep, small-diameter holes. These next-generation, small-diameter hole drills feature improved strength - often a problem area with small-diameter drills.

Characteristics and Applications

● Deep-hole drilling
New groove shape ensures good drill rigidity and chip evacuation.
High efficiency drilling to depths of over 20 x drill diameter at over v_f = 500 mm/min (drill diameter 1,3 mm, X12CrS13 equivalent).
Optimal thinning and edge balance for stable chip control.

● Long tool life
Special coating provides long tool life with a wide variety of work materials.
Improved chip evacuation makes it possible to reduce spindle load fluctuation, ensuring stable tool life.

Series

Application	Type	Diameter Range (mm)	Hole Depth (L/D)
Guide Hole Drilling	MLDH □□□□ P	Ø 0,8 – 2,0	–2
Deep Hole Drilling	MLDH □□□□ L5	Ø 0,8 – 2,0	–5
	MLDH □□□□ L12	Ø 0,8 – 2,0	–12
	MLDH □□□□ L20	Ø 0,8 – 2,0	–20
	MLDH □□□□ L30	Ø 0,8 – 2,0	–30

Recommended Cutting Conditions

● MLDH .... P / L5

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max)

Drill-ø (mm)	Cutting Cond.	Soft Steel (–200 HB)	General Steel (200–250 HB)	Alloy Steel (250–300 HB)	Stainless Steel (–200 HB)	Cast Iron	Aluminium Alloy	Heat-Resistant Steels
–Ø 1,0	v_c	40–**50**–60	40–**50**–60	40–**50**–60	20–**30**–40	40–**50**–60	50–**60**–70	5–**10**–15
	f	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,02–**0,03**–0,04	0,03–**0,04**–0,06	0,005–**0,01**–0,02
–Ø 1,5	v_c	40–**50**–60	40–**50**–60	40–**50**–60	20–**30**–40	40–**50**–60	50–**60**–70	5–**10**–15
	f	0,04–**0,08**–0,12	0,04–**0,08**–0,12	0,04–**0,08**–0,12	0,02–**0,05**–0,10	0,04–**0,08**–0,12	0,05–**0,10**–0,15	0,01–**0,03**–0,05
–Ø 2,0	v_c	40–**50**–60	40–**50**–60	40–**50**–60	20–**30**–40	40–**50**–60	50–**60**–70	5–**10**–15
	f	0,06–**0,08**–0,12	0,06–**0,08**–0,12	0,06–**0,08**–0,12	0,04–**0,06**–0,10	0,06–**0,08**–0,12	0,08–**0,12**–0,15	0,01–**0,03**–0,05

● MLDH .... L12 / L20 / L30

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max)

Drill-ø (mm)	Cutting Cond.	Soft Steel (–200 HB)	General Steel (200–250 HB)	Alloy Steel (250–300 HB)	Stainless Steel (–200 HB)	Cast Iron	Aluminium Alloy	Heat-Resistant Steels
–Ø 1,0	v_c	40–**50**–60	40–**50**–60	40–**50**–60	20–**30**–40	40–**50**–60	50–**60**–70	5–**10**–15
	f	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,01–**0,02**–0,03	0,02–**0,03**–0,04	0,03–**0,04**–0,06	0,005–**0,01**–0,02
–Ø 1,5	v_c	40–**50**–60	40–**50**–60	40–**50**–60	20–**30**–40	40–**50**–60	50–**60**–70	5–**10**–15
	f	0,03–**0,05**–0,07	0,03–**0,05**–0,07	0,03–**0,05**–0,07	0,02–**0,04**–0,07	0,04–**0,07**–0,10	0,05–**0,08**–0,12	0,01–**0,02**–0,03
–Ø 2,0	v_c	40–**50**–60	40–**50**–60	40–**50**–60	20–**30**–40	40–**50**–60	50–**60**–70	5–**10**–15
	f	0,04–**0,06**–0,08	0,04–**0,06**–0,08	0,04–**0,06**–0,08	0,04–**0,06**–0,08	0,04–**0,07**–0,10	0,05–**0,08**–0,12	0,01–**0,02**–0,03

○ = Japan stock

Micro Long Drills
MLDH ....L/P Type

Internal Coolant Supply

● MLDH-P For Pilot Hole Drilling



● MLDH-L For Deep Hole Drilling



■ Stock

(mm)

ØD (mm)	P Type for Pilot Hole Drilling				L Type for Deep Hole Drilling											
	Cat. No.	Stock	Dimensions		Cat. No. 5,12,20,30	5x D			12x D			20x D			30x D		
						Stock	Dimensions		Stock	Dimensions		Stock	Dimensions		Stock	Dimensions	
			L	ℓ		5	L	ℓ	1 2	L	ℓ	2 0	L	ℓ	3 0	L	ℓ
0,80	MLDH 0800P	❍	45	3,2	MLDH 0800L□□	❍	50	8	❍	60	14	❍	65	19	❍	75	28
0,81	0810P	❍			0810L□□	❍		9	❍			❍			❍		
0,82	MLDH 0820P	❍		3,3	MLDH 0820L□□	❍			❍			❍		20	❍		
0,83	0830P	❍			0830L□□	❍			❍			❍			❍		
0,84	MLDH 0840P	❍		3,4	MLDH 0840L□□	❍			❍			❍			❍		29
0,85	0850P	❍			0850L□□	❍			❍	55		❍			❍		
0,86	0860P	❍			0860L□□	❍			❍		15	❍		21	❍		
0,87	MLDH 0870P	❍		3,5	MLDH 0870L□□	❍			❍			❍			❍		30
0,88	0880P	❍			0880L□□	❍			❍			❍			❍		
0,89	MLDH 0890P	❍		3,6	MLDH 0890L□□	❍			❍			❍			❍		
0,90	0900P	❍			0900L□□	❍			❍			❍		22	❍		31
0,91	0910P	❍			0910L□□	❍		10	❍			❍			❍		
0,92	MLDH 0920P	❍		3,7	MLDH 0920L□□	❍			❍	60	16	❍			❍		
0,93	0930P	❍			0930L□□	❍			❍			❍			❍		32
0,94	MLDH 0940P	❍		3,8	MLDH 0940L□□	❍			❍			❍		23	❍	75	
0,95	0950P	❍			0950L□□	❍			❍			❍			❍		
0,96	0960P	❍			0960L□□	❍			❍			❍			❍		33
0,97	MLDH 0970P	❍		3,9	MLDH 0970L□□	❍			❍			❍			❍		
0,98	0980P	❍			0980L□□	❍			❍		17	❍		24	❍		
0,99	MLDH 0990P	❍		4,0	MLDH 0990L□□	❍			❍			❍			❍		34
1,00	1000P	❍			1000L□□	❍			❍			❍			❍		
1,05	MLDH 1050P	❍		4,2	MLDH 1050L□□	❍	55	12	❍		18	❍	70	25	❍	80	36
1,10	MLDH 1100P	❍		4,4	MLDH 1100L□□	❍			❍		19	❍		26	❍		37
1,15	MLDH 1150P	❍		4,6	MLDH 1150L□□	❍			❍		20	❍		28	❍		39
1,20	MLDH 1200P	❍		4,8	MLDH 1200L□□	❍			❍			❍		29	❍	85	41
1,25	MLDH 1250P	❍		5,0	MLDH 1250L□□	❍		14	❍	65	21	❍	75	30	❍		43
1,30	MLDH 1300P	❍		5,2	MLDH 1300L□□	❍			❍		22	❍		31	❍		44
1,35	MLDH 1350P	❍		5,4	MLDH 1350L□□	❍			❍		23	❍		32	❍	90	46
1,40	MLDH 1400P	❍		5,6	MLDH 1400L□□	❍			❍		24	❍		34	❍		48
1,45	MLDH 1450P	❍		5,8	MLDH 1450L□□	❍		16	❍		25	❍		35	❍		49
1,50	MLDH 1500P	❍		6,0	MLDH 1500L□□	❍			❍		26	❍		36	❍		51
1,55	MLDH 1550P	❍		6,2	MLDH 1550L□□	❍			❍			❍	80	37	❍	95	53
1,60	MLDH 1600P	❍		6,4	MLDH 1600L□□	❍			❍	70	27	❍		38	❍		54
1,65	MLDH 1650P	❍	50	6,6	MLDH 1650L□□	❍	60	18	❍		28	❍		40	❍		56
1,70	MLDH 1700P	❍		6,8	MLDH 1700L□□	❍			❍		29	❍		41	❍	100	58
1,75	MLDH 1750P	❍		7,0	MLDH 1750L□□	❍			❍		30	❍		42	❍		60
1,80	MLDH 1800P	❍		7,2	MLDH 1800L□□	❍			❍		31	❍	85	43	❍		61
1,85	MLDH 1850P	❍		7,4	MLDH 1850L□□	❍		20	❍			❍		44	❍	103	63
1,90	MLDH 1900P	❍		7,6	MLDH 1900L□□	❍			❍	75	32	❍		46	❍		65
1,95	MLDH 1950P	❍		7,8	MLDH 1950L□□	❍			❍		33	❍		47	❍		66
2,00	MLDH 2000P	❍		8,0	MLDH 2000L□□	❍			❍		34	❍	90	48	❍		68

PVD Coated Grade: ACV70

MDUS / MDSS Type



●Diameter Ø 0,03–0,19 mm

øD (mm)	Cat. No.	Stock	Dimensions ℓ_1	Dimensions ℓ_2	Fig.	Pcs./Packing
0,030	MDUS 0030-30C	❍	0,3	28	1	5
0,035	MDUS 0035-30C		0,4			
0,040	MDUS 0040-30C	❍				
0,045	MDUS 0045-30C		0,5			
0,050	MDUS 0050-30C	❍				
0,055	MDUS 0055-30C		0,6			
0,060	MDUS 0060-30C					
0,065	MDUS 0065-30C		0,7			
0,070	MDUS 0070-30C					
0,075	MDUS 0075-30C	❍	0,8			
0,080	MDUS 0080-30C					
0,085	MDUS 0085-30C		1,0			
0,090	MDUS 0090-30C					
0,095	MDUS 0095-30C	❍				
0,100	MDUS 0100-30C					
0,110	MDUS 0110-30C	❍	1,2			1
0,120	MDUS 0120-30C					
0,120	MDUS 0130-30C	❍	1,5			
0,140	MDUS 0140-30C					
0,150	MDUS 0150-30C					
0,160	MDUS 0160-30C	❍	1,8			
0,170	MDUS 0170-30C					
0,180	MDUS 0180-30C					
0,190	MDUS 0190-30C		1,9			

●Diameter Ø 0,20–0,59 mm

øD (mm)	Cat. No.	Stock	Dimensions ℓ_1	Dimensions ℓ_2	Fig.	Pcs./Packing
0,20	MDSS 0020	❒	2,5	28	2	1
0,21	MDSS 0021	❒				
0,22	MDSS 0022	❒				
0,23	MDSS 0023	❒				
0,24	MDSS 0024	❒				
0,25	MDSS 0025	❒				
0,26	MDSS 0026	❒				
0,27	MDSS 0027	❒				
0,28	MDSS 0028	❒				
0,29	MDSS 0029	❒				
0,30	MDSS 0030	❒	3			
0,31	MDSS 0031	❒				
0,32	MDSS 0032	❒				
0,33	MDSS 0033	❒				
0,34	MDSS 0034	❒				
0,35	MDSS 0035	❒	4		3	
0,36	MDSS 0036	❒				
0,37	MDSS 0037	❒				
0,38	MDSS 0038	❒				
0,39	MDSS 0039	❒				
0,40	MDSS 0040	❒	5			
0,41	MDSS 0041	❒				
0,42	MDSS 0042	❒				
0,43	MDSS 0043	❒				
0,44	MDSS 0044	❒				
0,45	MDSS 0045	❒				
0,46	MDSS 0046	❒				
0,47	MDSS 0047	❒				
0,48	MDSS 0048	❒				
0,49	MDSS 0049	❒				
0,50	MDSS 0050	❒	6	27		
0,51	MDSS 0051	❒				
0,52	MDSS 0052	❒				
0,53	MDSS 0053	❒				
0,54	MDSS 0054	❒				
0,55	MDSS 0055	❒				
0,56	MDSS 0056	❒				
0,57	MDSS 0057	❒				
0,58	MDSS 0058	❒				
0,59	MDSS 0059	❒				

●Diameter Ø 0,60–1,00 mm

øD (mm)	Cat. No.	Stock	Dimensions ℓ_1	Dimensions ℓ_2	Fig.	Pcs./Packing
0,60	MDSS 0060	❒	7	26	3	1
0,61	MDSS 0061	❒				
0,62	MDSS 0062	❒				
0,63	MDSS 0063	❒				
0,64	MDSS 0064	❒				
0,65	MDSS 0065	❒				
0,66	MDSS 0066	❒				
0,67	MDSS 0067	❒				
0,68	MDSS 0068	❒				
0,69	MDSS 0069	❒				
0,70	MDSS 0070	❒	9	24		
0,71	MDSS 0071	❒				
0,72	MDSS 0072	❒				
0,73	MDSS 0073	❒				
0,74	MDSS 0074	❒				
0,75	MDSS 0075	❒				
0,76	MDSS 0076	❒				
0,77	MDSS 0077	❒				
0,78	MDSS 0078	❒				
0,79	MDSS 0079	❒				
0,80	MDSS 0080	❒	10	23		
0,81	MDSS 0081	❒				
0,82	MDSS 0082	❒				
0,83	MDSS 0083	❒				
0,84	MDSS 0084	❒				
0,85	MDSS 0085	❒				
0,86	MDSS 0086	❒				
0,87	MDSS 0087	❒				
0,88	MDSS 0088	❒				
0,89	MDSS 0089	❒				
0,90	MDSS 0090	❒	11	22		
0,91	MDSS 0091	❒				
0,92	MDSS 0092	❒				
0,93	MDSS 0093	❒				
0,94	MDSS 0094	❒				
0,95	MDSS 0095	❒				
0,96	MDSS 0096	❒				
0,97	MDSS 0097	❒				
0,98	MDSS 0098	❒				
0,99	MDSS 0099	❒				
1,00	MDSS 0100	❒	12	21		

■ MDSS Recommended Cutting Conditions (Wet)

Work / Cond. / Drill-ø (mm)	Alloy Steel, Pre-hardened Steel: Spindle (rpm)	Feed rate (mm/min)	Step-feed (mm)	Die Steel, Tempered Steel (H_RC 30–40): Spindle (rpm)	Feed rate (mm/min)	Step-feed (mm)	Stainless Steel: Spindle (rpm)	Feed rate (mm/min)	Step-feed (mm)
Ø 0,2	26500	50	0,1D	21200	40	0,1D	10600	20	0,1D
Ø 0,3	26500	80		21200	60		10600	30	
Ø 0,4	25900	100		19900	80		9500	40	
Ø 0,5	25500	150		19100	110		9500	50	
Ø 1,0	15900	240	0,2D–0,5D※	12700	190	0,2D–0,5D※	5600	80	

1. The above conditions are recommended under wet conditions, using water-soluble coolant.
2. If machine noises and vibrations are present, please adjust the cutting conditions accordingly.
3. If the machine cannot achieve the recommended spindle speed, please use the max. spindle speed available.

※ Step feed is recommended for drilling of holes deeper than 3xD.

○ = Japan stock
❑ = Delivery on request

SUMIDIA Coated Drills
SDC Type

General Features

SUMIDIA Coated SDC type drills for Carbon Fibre Reinforced Plastic (CFRP) employ Sumitomo Electric Hardmetal's proprietary multi-step point angle.
Combined with a diamond coating, this technology improves the quality of machined surfaces and extends tool life.

Characteristics and Applications

- Excellent drilled-hole quality
  - Sharp cutting edge shape reduces delamination of fibre layers and burrs.
  - Continuously changing point angle disperses load placed on cutting edge and prevents breakage.
- Long tool life
  - Use of high-strength diamond coating with excellent adhesion delivers high quality and long tool life.

Performance

Comparison of Machined Surface Finish

Excellent Machined Face Quality
(Prevents Delamination And Burrs)



Tool:	SUMIDIA coated drill SDC type, Ø 6,375 Competitor A B C´s drill Ø 6,35 & Ø 6,5
Work Material:	CFRP
Cutting Conditions:	n = 6.000 rpm, f=0,1 mm/rev, a_p =28 mm (Through) Dry

Tool Life Comparison

Effects of Diamond Coating

SDC type (After drilling 600 holes)	Competitor's product (After drilling 50 holes)
	
No delamination Low flank wear	More delamination from cutting edge to flank

Stable diamond layer adhesion prevents delamination.
Excellent wear resistance enables high-quality drilling with long tool life.



Tool:	SUMIDIA coated drill SDC type, Ø 6,375 Competitor A B C´s drill Ø 6,35 & Ø 6,5
Work Material:	CFRP
Cutting Conditions:	n = 6.000 rpm, f=0,1 mm/rev, a_p =28 mm (Through) Dry

Series

Type	Diameter Range (mm)	Point angle	Hole Depth ($^L/_D$)
MDS□□□□□SDC3	Ø 2,0 – 4,0	90°	–3
	Ø 4,851 – 10,0	130°	

DCX20	SUMI-DIA
Grade	Coating

Structal Steel	Carbon Steel	Alloy Steel	Pre-hardened Steel	Tempered Die Steel	Hardened Steel 45–55 HRC	Hardened Steel 55–60 HRC	Hardened Steel 60–65 HRC	Stainless Steel	Ti Alloy / Heat Resistant Alloy	Cast iron	Al Alloy	Cu Alloy	CFRP *
											○		◎

* CFRP (Carbon Fibre Reinforced Plastic)

● Diameter Ø 2,0–4,0 mm



● Diameter Ø 4,851–10,0 mm



●Diameter ø 2,0–10,0 mm

(mm)

Dimensions DC (mm)	Dimensions Ød (mm)	Cat. No.	3D Type Stock	3D Type Dimensions L	3D Type Dimensions ℓ
2,0	3,0	MDS 02000SDC3	❍	49	12,5
2,489		02489SDC3	❍		15,0
3,0		03000SDC3	❍		17,5
3,3	3,3	MDS 03300SDC3	❍	60	20,0
4,0	4,0	04000SDC3	❍		22,5
4,851	4,851	MDS 04851SDC3	❍	76	27,5
5,0	5,0	05000SDC3	❍		
5,6	5,6	MDS 05600SDC3	❍	81	30,0
6,0	6,0	06000SDC3	❍		
6,375	6,375	MDS 06375SDC3	❍	83	32,5
7,0	7,0	07000SDC3	❍		35,0
7,938	7,938	MDS 07938SDC3	❍	90	40,0
8,0	8,0	08000SDC3	❍		
9,0	9,0	MDS 09000SDC3	❍	98	45,0
9,550	9,550	MDS 09550SDC3	❍	105	50,0
10,0	10,0	10000SDC3	❍		

Recommended Cutting Conditions

ØD \ Work Cond.		CFRP Only (Dry Machining)	Stacked Plates of CFRP, Aluminium Alloys (Dry Machining)
–Ø 6,0	v_c	80–**120**–150	40–**60**–80
	f	0,05–**0,08**–0,10	0,05–**0,05**–0,10
–Ø10,0	v_c	80–**100**–120	40–**60**–80
	f	0,05–**0,08**–0,10	0,05–**0,05**–0,10

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max)

KDS Type



Description

The new AK type drill features an extra long carbide drill head, new cutting geometry, coolant holes and ultra hard TiAlN coating for reliable high productivity drilling.

Advantages

- General purpose drill for steels, stainless steels, cast irons
- High productivity drilling even on deep holes up to 7 x D
- Twice the tool life of conventionally coated drills
- Self centering
- Surface finish and tolerances comparable to solid carbide
- Regrindable extra long carbide head halves drill replacement costs

Series

Type	Diameter range (mm)	Hole depth (L/D)	Remark
Short type (MAK Type)	Ø 9,5–40,5	–3	First choice general purpose drill
Long type (LAK Type)	Ø 9,5–40,5	–5	
Extra long type (DAK Type)	Ø 9,5–40,5	–7	Helix angle: 25° ---> 0°

Series

Performance

● High efficiency drilling

Comparison of coating damage when high speed drilling



Drill dia.: 18,0 mm
Work material: C50 (HB230)
f = 0,3 mm/rev
a_p = 50 mm

● Optimized drill geometry

Comparison of damage to drill margin After 40 min. cut length



Drill dia.: 18,0 mm
Work material: C50 (HB230)
v_c = 50 m/min
f = 0,25 mm/rev
a_p = 38 mm

● Comparison of cutting power (chip removal capability)



Drill dia.: 18,0 mm
Work material: C50 (HB230)
v_c = 50 m/min
f = 0,3 mm/rev
a_p = 90 mm (L/D = 5)

Application examples

● Workpiece material

- General steel and alloy steel
- Low carbon steel
- Die steel
- Stainless steel
- Ductile cast iron
- Grey cast iron

● Automotive parts
Work material: C50 (HB250)



Drill: KDS 180 LAK (Ø 18,0 mm)
Conditions: v_c = 55 m/min, f = 0,25 mm/rev
a_p = 70 mm

● Automotive parts
Work material: 42CrMo4 (HB250)



Drill: KDS 250 MAK (Ø 25,0 mm)
Conditions: v_c = 60 m/min, f = 0,25 mm/rev
a_p = 65 mm

KDS ... MAK Type

Short Type (3 x D)

Brazed Carbide Drills with Coolant Holes



Helix angle: 20°
ℓ_2 = Effective drilling length

●Diameter Ø 9,5–15,5 mm

Dimensions (mm)				Cat. No.	Short Series (3D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		MAK	OAL	LU	LUX
9,5~				KDS 095 MAK	❑			
10,0	16	48	1,8	100 MAK	❑	96,8	32	37
~10,5				105 MAK	❑			
10,6~				KDS 106 MAK	❑			
11,0	16	48	2	110 MAK	❑	102,0	35	40
~11,5				115 MAK	❑			
11,6				KDS 116 MAK	❑			
11,7				117 MAK	❑			
11,8				118 MAK	❑			
11,9				119 MAK	❑			
12,0	16	48	2,2	120 MAK	❑	107,2	38	44
12,1				121 MAK	❑			
12,2				122 MAK	❑			
12,3				123 MAK	❑			
12,4				124 MAK	❑			
12,5				125 MAK	❑			
12,6				KDS 126 MAK	❑			
12,7				127 MAK	❑			
12,8				128 MAK	❑			
12,9				129 MAK	❑			
13,0	16	48	2,4	130 MAK	❑	112,4	41	47
13,1				131 MAK	❑			
13,2				132 MAK	❑			
13,3				133 MAK	❑			
13,4				134 MAK	❑			
13,5				135 MAK	❑			
13,6				KDS 136 MAK	❑			
13,7				137 MAK	❑			
13,8				138 MAK	❑			
13,9				139 MAK	❑			
14,0	16	48	2,5	140 MAK	❑	117,5	44	51
14,1				141 MAK	❑			
14,2				142 MAK	❑			
14,3				143 MAK	❑			
14,4				144 MAK	❑			
14,5				145 MAK	❑			
14,6				KDS 146 MAK	❑			
14,7				147 MAK	❑			
14,8				148 MAK	❑			
14,9				148 MAK	❑			
15,0	20	50	2,7	150 MAK	❑	127,7	47	54
15,1				151 MAK	❑			
15,2				152 MAK	❑			
15,3				153 MAK	❑			
15,4				154 MAK	❑			
15,5				155 MAK	❑			

●Diameter Ø 15,6–20,0 mm

Dimensions (mm)				Cat. No.	Short Series (3D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		MAK	OAL	LU	LUX
15,6				KDS 156 MAK	❑			
15,7				157 MAK	❑			
15,8				158 MAK	❑			
15,9				159 MAK	❑			
16,0	20	50	2,9	160 MAK	❑	132,9	50	58
16,1				161 MAK	❑			
16,2				162 MAK	❑			
16,3				163 MAK	❑			
16,4				164 MAK	❑			
16,5				165 MAK	❑			
16,6				KDS 166 MAK	❑			
16,7				167 MAK	❑			
16,8				168 MAK	❑			
16,9				169 MAK	❑			
17,0	20	50	3,1	170 MAK	❑	138,1	53	61
17,1				171 MAK	❑			
17,2				172 MAK	❑			
17,3				173 MAK	❑			
17,4				174 MAK	❑			
17,5				175 MAK	❑			
17,6				KDS 176 MAK	❑			
17,7				177 MAK	❑			
17,8				178 MAK	❑			
17,9				179 MAK	❑			
18,0	20	50	3,3	180 MAK	❑	143,3	56	65
18,1				181 MAK	❑			
18,2				182 MAK	❑			
18,3				183 MAK	❑			
18,4				184 MAK	❑			
18,5				185 MAK	❑			
18,6				KDS 186 MAK	❑			
18,7				187 MAK	❑			
18,8				188 MAK	❑			
18,9				189 MAK	❑			
19,0	25	56	3,5	190 MAK	❑	158,5	59	68
19,1				191 MAK	❑			
19,2				192 MAK	❑			
19,3				193 MAK	❑			
19,4				194 MAK	❑			
19,5				195 MAK	❑			
19,6				KDS 196 MAK	❑			
19,7				197 MAK	❑			
19,8	25	56	3,6	198 MAK	❑	158,6	62	72
19,9				199 MAK	❑			
20,0				200 MAK	❑			

■ Recommended Cutting Conditions

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev)) (Min – **Standard** – Max)

Diameter (mm)		Steels (<250 HB)	Steels (250–320 HB)	Hardened Steels (45 HRC)	Stainless Steels (<200 HB)	Ductile Cast Irons	Cast Irons	Aluminium Alloys	Titanium Alloys (Ti–6Al–4V)	Inconel (Inconel 718)
–Ø 15	v_c	50–**65**–75	50–**60**–70	30–**35**–45	35–**45**–50	55–**65**–75	60–**80**–100	70–**85**–100	20–**25**–35	10–**20**–30
	f	0,15–0,3	0,15–0,3	0,1–0,2	0,1–0,2	0,15–0,3	0,2–0,3	0,25–0,35	0,1–0,15	0,08–0,1
–Ø 20	v_c	50–**65**–75	50–**60**–70	35–**40**–50	35–**45**–50	60–**70**–80	60–**80**–100	70–**90**–110	20–**30**–40	10–**20**–30
	f	0,15–0,35	0,15–0,35	0,15–0,25	0,15–0,25	0,15–0,35	0,2–0,35	0,25–0,4	0,1–0,15	0,08–0,1
–Ø 30,5	v_c	55–**70**–90	55–**65**–90	35–**40**–50	35–**45**–50	60–**70**–90	60–**90**–110	75–**100**–120	25–**35**–40	15–**25**–35
	f	0,2–0,4	0,2–0,4	0,15–0,25	0,15–0,25	0,2–0,4	0,25–0,4	0,3–0,4	0,1–0,2	0,08–0,12

If the drilling operation is completely satisfactory with the above condition and the rigidity of the machine is sufficient, the cutting data can be raised. For more guidance, please contact our technical representative.

❑ = Delivery on request

KDS ... MAK Type

TiAlN Coated Brazed Carbide Multi-Drills for General Steels, Cast Iron & Ductile Cast Iron

Specification:
- Brazed carbide drill TiAlN coated (Grade: ACW30) with coolant holes
- Shank with whistle notch

●Diameter Ø 20,1–24,5 mm

Dimensions (mm)				Cat. No.	Short Series (3D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		MAK	OAL	LU	LUX
20,1	25	56	3,6	KDS 201 MAK	❑	158,6	62	72
20,2				202 MAK	❑			
20,3				203 MAK	❑			
20,4				204 MAK	❑			
20,5				205 MAK	❑			
20,6	25	56	3,8	KDS 206 MAK	❑	158,8	65	75
20,7				207 MAK	❑			
20,8				208 MAK	❑			
20,9				209 MAK	❑			
21,0				210 MAK	❑			
21,1				211 MAK	❑			
21,2				212 MAK	❑			
21,3				213 MAK	❑			
21,4				214 MAK	❑			
21,5				215 MAK	❑			
21,6	25	56	4,0	KDS 216 MAK	❑	164,0	68	79
21,7				217 MAK	❑			
21,8				218 MAK	❑			
21,9				219 MAK	❑			
22,0				220 MAK	❑			
22,1				221 MAK	❑			
22,2				222 MAK	❑			
22,3				223 MAK	❑			
22,4				224 MAK	❑			
22,5				225 MAK	❑			
22,6	25	56	4,2	KDS 226 MAK	❑	164,2	71	82
22,7				227 MAK	❑			
22,8				228 MAK	❑			
22,9				229 MAK	❑			
23,0				230 MAK	❑			
23,1				231 MAK	❑			
23,2				232 MAK	❑			
23,3				233 MAK	❑			
23,4				234 MAK	❑			
23,5				235 MAK	❑			
23,6	32	60	4,4	KDS 236 MAK	❑	174,4	74	86
23,7				237 MAK	❑			
23,8				238 MAK	❑			
23,9				239 MAK	❑			
24,0				240 MAK	❑			
24,1				241 MAK	❑			
24,2				242 MAK	❑			
24,3				243 MAK	❑			
24,4				244 MAK	❑			
24,5				245 MAK	❑			

●Diameter Ø 24,6– 40,5 mm

Dimensions (mm)				Cat. No.	Short Series (3D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		MAK	OAL	LU	LUX
24,6	32	60	4,5	KDS 246 MAK	❑	174,5	76	88
24,7				247 MAK	❑			
24,8				248 MAK	❑			
24,9				249 MAK	❑			
25,0				250 MAK	❑			
25,1				251 MAK	❑			
25,2				252 MAK	❑			
25,3				253 MAK	❑			
25,4				254 MAK	❑			
25,5				255 MAK	❑			
25,6	32	60	4,7	KDS 256 MAK	❑	179,9	79	92
25,7				257 MAK	❑			
25,8				258 MAK	❑			
25,9				259 MAK	❑			
26,0				260 MAK	❑			
26,1 –26,5				261 MAK –265 MAK	❑			
26,6 –27,5	32	60	4,9	KDS 266 MAK –275 MAK	❑	179,9	81	94
27,6 –28,5	32	60	5,1	KDS 276 MAK –285 MAK	❑	185,1	83	97
28,6 –29,5	32	60	5,3	KDS 286 MAK –295 MAK	❑	190,3	86	100
29,6 –30,5	32	60	5,5	KDS 296 MAK –305 MAK	❑	190,5	89	104
30,6 –31,5	40	70	5,6	KDS 306 MAK –315 MAK	❑	210,6	95	112
31,6 –32,5	40	70	5,8	KDS 316 MAK –325 MAK	❑	215,8	98	115
32,6 –33,5	40	70	6,0	KDS 326 MAK –335 MAK	❑	221,0	101	119
33,6 –34,5	40	70	6,2	KDS 336 MAK –345 MAK	❑	226,2	104	122
34,6 –35,5	40	70	6,4	KDS 346 MAK –355 MAK	❑	231,4	107	125
35,6 –36,5	40	70	6,6	KDS 356 MAK –365 MAK	❑	231,6	110	128
36,6 –37,5	40	70	6,7	KDS 366 MAK –375 MAK	❑	236,7	113	132
37,6 –38,5	40	70	6,9	KDS 376 MAK –385 MAK	❑	241,9	116	163
38,6 –39,5	40	70	7,1	KDS 386 MAK –395 MAK	❑	247,1	119	168
39,6 –40,5	40	70	7,3	KDS 396 MAK –405 MAK	❑	252,3	122	173

■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs. Please specify the Cat. No.
For example, if the diameter of the drill is 10,2 mm, please indicate as follow.

E.g., **KDS 102 MAK**, ACW30 (Grade)

KDS series: Brazed carbide drill with coolant holes

Drill diameter **10,2** mm

M : 3 x D

AK: Brazed carbide and TiAlN coated drill

KDS ... LAK Type

Long Type (5 x D)

Brazed Carbide Drills with Coolant Holes



Helix angle: 20° ---> 6°
ℓ_2 = Effective drilling length

●Diameter Ø 9,5–15,5 mm

Dimensions (mm)				Cat. No.	Long Series (5D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		LAK	OAL	LU	LUX
9,5~	16	48	1,8	KDS 095 LAK	❑	116,8	52	57
10,0				100 LAK	❑			
~10,5				105 LAK	❑			
10,6~	16	48	2	KDS 106 LAK	❑	127,0	57	63
11,0				110 LAK	❑			
~11,5				115 LAK	❑			
11,6	16	48	2,2	KDS 116 LAK	❑	132,2	63	69
11,7				117 LAK	❑			
11,8				118 LAK	❑			
11,9				119 LAK	❑			
12,0				120 LAK	❑			
12,1				121 LAK	❑			
12,2				122 LAK	❑			
12,3				123 LAK	❑			
12,4				124 LAK	❑			
12,5				125 LAK	❑			
12,6	16	48	2,4	KDS 126 LAK	❑	142,4	67	74
12,7				127 LAK	❑			
12,8				128 LAK	❑			
12,9				129 LAK	❑			
13,0				130 LAK	❑			
13,1				131 LAK	❑			
13,2				132 LAK	❑			
13,3				133 LAK	❑			
13,4				134 LAK	❑			
13,5				135 LAK	❑			
13,6	16	48	2,5	KDS 136 LAK	❑	147,5	73	80
13,7				137 LAK	❑			
13,8				138 LAK	❑			
13,9				139 LAK	❑			
14,0				140 LAK	❑			
14,1				141 LAK	❑			
14,2				142 LAK	❑			
14,3				143 LAK	❑			
14,4				144 LAK	❑			
14,5				145 LAK	❑			
14,6	20	50	2,7	KDS 146 LAK	❑	157,7	77	85
14,7				147 LAK	❑			
14,8				148 LAK	❑			
14,9				149 LAK	❑			
15,0				150 LAK	❑			
15,1				151 LAK	❑			
15,2				152 LAK	❑			
15,3				153 LAK	❑			
15,4				154 LAK	❑			
15,5				155 LAK	❑			

●Diameter Ø 15,6–20,0 mm

Dimensions (mm)				Cat. No.	Long Series (5D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		LAK	OAL	LU	LUX
15,6	20	50	2,9	KDS 156 LAK	❑	167,9	83	91
15,7				157 LAK	❑			
15,8				158 LAK	❑			
15,9				159 LAK	❑			
16,0				160 LAK	❑			
16,1				161 LAK	❑			
16,2				162 LAK	❑			
16,3				163 LAK	❑			
16,4				164 LAK	❑			
16,5				165 LAK	❑			
16,6	20	50	3,1	KDS 166 LAK	❑	173,1	87	96
16,7				167 LAK	❑			
16,8				168 LAK	❑			
16,9				169 LAK	❑			
17,0				170 LAK	❑			
17,1				171 LAK	❑			
17,2				172 LAK	❑			
17,3				173 LAK	❑			
17,4				174 LAK	❑			
17,5				175 LAK	❑			
17,6	20	50	3,3	KDS 176 LAK	❑	178,3	93	102
17,7				177 LAK	❑			
17,8				178 LAK	❑			
17,9				179 LAK	❑			
18,0				180 LAK	❑			
18,1				181 LAK	❑			
18,2				182 LAK	❑			
18,3				183 LAK	❑			
18,4				184 LAK	❑			
18,5				185 LAK	❑			
18,6	25	56	3,5	KDS 186 LAK	❑	193,5	97	107
18,7				187 LAK	❑			
18,8				188 LAK	❑			
18,9				189 LAK	❑			
19,0				190 LAK	❑			
19,1				191 LAK	❑			
19,2				192 LAK	❑			
19,3				193 LAK	❑			
19,4				194 LAK	❑			
19,5				195 LAK	❑			
19,6	25	56	3,6	KDS 196 LAK	❑	198,6	103	113
19,7				197 LAK	❑			
19,8				198 LAK	❑			
19,9				199 LAK	❑			
20,0				200 LAK	❑			

■ Recommended Cutting Conditions

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev)) (Min – **Standard** – Max)

Diameter (mm)		Steels (<250 HB)	Steels (250–320 HB)	Hardened Steels (45 HRC)	Stainless Steels (<200 HB)	Ductile Cast Irons	Cast Irons	Aluminium Alloys	Titanium Alloys (Ti–6Al–4V)	Inconel (Inconel 718)
–Ø 15	v_c	50–**65**–75	50–**60**–70	30–**35**–45	35–**45**–50	55–**65**–75	60–**80**–100	70–**85**–100	20–**25**–35	10–**20**–30
	f	0,15–0,3	0,15–0,3	0,1–0,2	0,1–0,2	0,15–0,3	0,2–0,3	0,25–0,35	0,1–0,15	0,08–0,1
–Ø 20	v_c	50–**65**–75	50–**60**–70	35–**40**–50	35–**45**–50	60–**70**–80	60–**80**–100	70–**90**–110	20–**30**–40	10–**20**–30
	f	0,15–0,35	0,15–0,35	0,15–0,25	0,15–0,25	0,15–0,35	0,2–0,35	0,25–0,4	0,1–0,15	0,08–0,1
–Ø 30,5	v_c	55–**70**–90	55–**65**–90	35–**40**–50	35–**45**–50	60–**70**–90	60–**90**–110	75–**100**–120	25–**35**–40	15–**25**–35
	f	0,2–0,4	0,2–0,4	0,15–0,25	0,15–0,25	0,2–0,4	0,25–0,4	0,3–0,4	0,1–0,2	0,08–0,12

If the drilling operation is completely satisfactory with the above condition and the rigidity of the machine is sufficient, the cutting data can be raised. For more guidance, please contact our technical representative.

❑ = Delivery on request

KDS ... LAK Type

TiAlN Coated Brazed Carbide Multi-Drills for General Steels, Cast Iron & Ductile Cast Iron

Specification:
- Brazed carbide drill TiAlN coated (Grade: ACW30) with coolant holes
- Shank with whistle notch

●Diameter Ø 20,1–24,5 mm

Dimensions (mm)				Cat. No.	Long Series (5D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		LAK	OAL	LU	LUX
20,1	25	56	3,6	KDS 201 LAK	❑	198,6	103	113
20,2				202 LAK	❑			
20,3				203 LAK	❑			
20,4				204 LAK	❑			
20,5				205 LAK	❑			
20,6	25	56	3,8	KDS 206 LAK	❑	198,8	107	118
20,7				207LAK	❑			
20,8				208 LAK	❑			
20,9				209 LAK	❑			
21,0				210 LAK	❑			
21,1				211 LAK	❑			
21,2				212 LAK	❑			
21,3				213 LAK	❑			
21,4				214 LAK	❑			
21,5				215 LAK	❑			
21,6	25	56	4,0	KDS 216 LAK	❑	204,0	113	124
21,7				217 LAK	❑			
21,8				218 LAK	❑			
21,9				219 LAK	❑			
22,0				220 LAK	❑			
22,1				221 LAK	❑			
22,2				222 LAK	❑			
22,3				223 LAK	❑			
22,4				224 LAK	❑			
22,5				225 LAK	❑			
22,6	25	56	4,2	KDS 226 LAK	❑	214,2	117	129
22,7				227 LAK	❑			
22,8				228 LAK	❑			
22,9				229 LAK	❑			
23,0				230 LAK	❑			
23,1				231 LAK	❑			
23,2				232 LAK	❑			
23,3				233 LAK	❑			
23,4				234 LAK	❑			
23,5				235 LAK	❑			
23,6	32	60	4,4	KDS 236 LAK	❑	224,4	123	135
23,7				237 LAK	❑			
23,8				238 LAK	❑			
23,9				239 LAK	❑			
24,0				240 LAK	❑			
24,1				241 LAK	❑			
24,2				242 LAK	❑			
24,3				243 LAK	❑			
24,4				244 LAK	❑			
24,5				245 LAK	❑			

●Diameter Ø 24,6–40,5 mm

Dimensions (mm)				Cat. No.	Long Series (5D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		LAK	OAL	LU	LUX
24,6	32	60	4,5	KDS 246 LAK	❑	229,5	127	140
24,7				247 LAK	❑			
24,8				248 LAK	❑			
24,9				249 LAK	❑			
25,0				250 LAK	❑			
25,1				251 LAK	❑			
25,2				252 LAK	❑			
25,3				253 LAK	❑			
25,4				254 LAK	❑			
25,5				255 LAK	❑			
25,6	32	60	4,7	KDS 256 LAK	❑	234,7	133	146
25,7				257 LAK	❑			
25,8				258 LAK	❑			
25,9				259 LAK	❑			
26,0				260 LAK	❑			
26,1 –26,5				261 LAK –265 LAK	❑			
26,6 –27,5	32	60	4,9	KDS 266 LAK –275 LAK	❑	239,9	137	151
27,6 –28,5	32	60	5,1	KDS 276 LAK –285 LAK	❑	245,1	143	157
28,6 –29,5	32	60	5,3	KDS 286 LAK –295 LAK	❑	250,3	147	162
29,6 –30,5	32	60	5,5	KDS 296 LAK –305 LAK	❑	260,5	152	167
30,6 –31,5	40	70	5,6	KDS 306 LAK –315 LAK	❑	280,6	166	187
31,6 –32,5	40	70	5,8	KDS 316 LAK –325 LAK	❑	285,8	172	190
32,6 –33,5	40	70	6,0	KDS 326 LAK –335 LAK	❑	291,0	175	194
33,6 –34,5	40	70	6,2	KDS 336 LAK –345 LAK	❑	296,2	177	197
34,6 –35,5	40	70	6,4	KDS 346 LAK –355 LAK	❑	301,4	180	200
35,6 –36,5	40	70	6,6	KDS 356 LAK –365 LAK	❑	306,6	183	203
36,6 –37,5	40	70	6,7	KDS 366 LAK –375 LAK	❑	311,7	188	207
37,6 –38,5	40	70	6,9	KDS 376 LAK –385 LAK	❑	321,9	193	243
38,6 –39,5	40	70	7,1	KDS 386 LAK –395 LAK	❑	327,1	198	248
39,6 –40,5	40	70	7,3	KDS 396 LAK –405 LAK	❑	332,3	203	253

■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs. Please specify the Cat. No.
For example, if the diameter of the drill is 10,2 mm, please indicate as follow.

E.g., **KDS 102 L AK** , ACW30 (Grade)

KDS series: Brazed carbide drill with coolant holes

Drill diameter **10,2** mm

L : 5 x D

AK: Brazed carbide and TiAlN coated drill

KDS ... DAK Type

Extra Long Type (7 x D) Brazed Carbide Drills with Coolant Holes



Helix angle: 20° ---> 0°
ℓ_2 = Effective drilling length

●Diameter Ø 9,5–15,5 mm

Dimensions (mm)				Cat. No.	Extra Long Series (7D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		DAK	OAL	LU	LUX
9,5~				KDS 095 DAK	❑			
10,0	16	48	1,8	100 DAK	❑	141,8	75	80
~10,5				105 DAK	❑			
10,6~				KDS 106 DAK	❑			
11,0	16	48	2	110 DAK	❑	152,0	81	87
~11,5				115 DAK	❑			
11,6				KDS 116 DAK	❑			
11,7				117 DAK	❑			
11,8				118 DAK	❑			
11,9				119 DAK	❑			
12,0	16	48	2,2	120 DAK	❑	162,2	91	97
12,1				121 DAK	❑			
12,2				122 DAK	❑			
12,3				123 DAK	❑			
12,4				124 DAK	❑			
12,5				125 DAK	❑			
12,6				KDS 126 DAK	❑			
12,7				127 DAK	❑			
12,8				128 DAK	❑			
12,9				129 DAK	❑			
13,0	16	48	2,4	130 DAK	❑	177,4	99	106
13,1				131 DAK	❑			
13,2				132 DAK	❑			
13,3				133 DAK	❑			
13,4				134 DAK	❑			
13,5				135 DAK	❑			
13,6				KDS 136 DAK	❑			
13,7				137 DAK	❑			
13,8				138 DAK	❑			
13,9				139 DAK	❑			
14,0	16	48	2,5	140 DAK	❑	182,5	106	113
14,1				141 DAK	❑			
14,2				142 DAK	❑			
14,3				143 DAK	❑			
14,4				144 DAK	❑			
14,5				145 DAK	❑			
14,6				KDS 146 DAK	❑			
14,7				147 DAK	❑			
14,8				148 DAK	❑			
14,9				149 DAK	❑			
15,0	20	50	2,7	150 DAK	❑	197,7	114	122
15,1				151 DAK	❑			
15,2				152 DAK	❑			
15,3				153 DAK	❑			
15,4				154 DAK	❑			
15,5				155 DAK	❑			

●Diameter Ø 15,6–20,0 mm

Dimensions (mm)				Cat. No.	Extra Long Series (7D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		DAK	OAL	LU	LUX
15,6				KDS 156 DAK	❑			
15,7				157 DAK	❑			
15,8				158 DAK	❑			
15,9				159 DAK	❑			
16,0	20	50	2,9	160 DAK	❑	207,9	121	129
16,1				161 DAK	❑			
16,2				162 DAK	❑			
16,3				163 DAK	❑			
16,4				164 DAK	❑			
16,5				165 DAK	❑			
16,6				KDS 166 DAK	❑			
16,7				167 DAK	❑			
16,8				168 DAK	❑			
16,9				169 DAK	❑			
17,0	20	50	3,1	170 DAK	❑	218,1	129	138
17,1				171 DAK	❑			
17,2				172 DAK	❑			
17,3				173 DAK	❑			
17,4				174 DAK	❑			
17,5				175 DAK	❑			
17,6				KDS 176 DAK	❑			
17,7				177 DAK	❑			
17,8				178 DAK	❑			
17,9				179 DAK	❑			
18,0	20	50	3,3	180 DAK	❑	223,3	136	145
18,1				181 DAK	❑			
18,2				182 DAK	❑			
18,3				183 DAK	❑			
18,4				184 DAK	❑			
18,5				185 DAK	❑			
18,6				KDS 186 DAK	❑			
18,7				187 DAK	❑			
18,8				188 DAK	❑			
18,9				189 DAK	❑			
19,0	25	56	3,5	190 DAK	❑	243,5	144	154
19,1				191 DAK	❑			
19,2				192 DAK	❑			
19,3				193 DAK	❑			
19,4				194 DAK	❑			
19,5				195 DAK	❑			
19,6				KDS 196 DAK	❑			
19,7				197 DAK	❑			
19,8	25	56	3,6	198 DAK	❑	248,6	151	161
19,9				199 DAK	❑			
20,0				200 DAK	❑			

■ Recommended Cutting Conditions

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev)) (Min – **Standard** – Max)

Diameter (mm)		Steels (<250 HB)	Steels (250–320 HB)	Die Steels (about 250 HB)	Ductile Cast Irons	Remarks
–Ø 15	v_c	40–**65**–90	40–**60**–90	40–**50**–70	50–**70**–100	To avoid the drill bending, which can cause breakage, please pre-drill or reduce the cutting conditions at the entrance of hole: RPM: 100–300 f: 0,05–0,08 mm/rev
	f	0,15–**0,2**–0,3	0,1–**0,2**–0,25	0,1–**0,2**–0,25	0,2–**0,3**–0,35	
–Ø 20	v_c	40–**65**–90	40–**60**–90	40–**50**–70	50–**70**–100	
	f	0,2–**0,3**–0,4	0,15–**0,25**–0,35	0,15–**0,25**–0,3	0,2–**0,35**–0,4	
–Ø 30,5	v_c	40–**70**–90	40–**65**–90	40–**55**–70	50–**70**–100	
	f	0,2–**0,35**–0,45	0,2–**0,3**–0,4	0,2–**0,3**–0,35	0,25–**0,4**–0,5	

❑ = Delivery on request

KDS ... DAK Type

TiAlN Coated Brazed Carbide Multi-Drills for General Steels & Ductile Cast Iron

Specification:
- Brazed carbide drill TiAlN coated (Grade: ACW30) with coolant holes
- Shank with whistle notch

●Diameter Ø 20,1–24,5 mm

Dimensions (mm)				Cat. No.	Extra Long Series (7D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		DAK	OAL	LU	LUX
20,1	25	56	3,6	KDS 201 DAK	❑	248,6	151	161
20,2				202 DAK	❑			
20,3				203 DAK	❑			
20,4				204 DAK	❑			
20,5				205 DAK	❑			
20,6	25	56	3,8	KDS 206 DAK	❑	248,8	155	166
20,7				207 DAK	❑			
20,8				208 DAK	❑			
20,9				209 DAK	❑			
21,0				210 DAK	❑			
21,1				211 DAK	❑			
21,2				212 DAK	❑			
21,3				213 DAK	❑			
21,4				214 DAK	❑			
21,5				215 DAK	❑			
21,6	25	56	4,0	KDS 216 DAK	❑	259,0	166	177
21,7				217 DAK	❑			
21,8				218 DAK	❑			
21,9				219 DAK	❑			
22,0				220 DAK	❑			
22,1				221 DAK	❑			
22,2				222 DAK	❑			
22,3				223 DAK	❑			
22,4				224 DAK	❑			
22,5				225 DAK	❑			
22,6	25	56	4,2	KDS 226 DAK	❑	274,2	174	186
22,7				227 DAK	❑			
22,8				228 DAK	❑			
22,9				229 DAK	❑			
23,0				230 DAK	❑			
23,1				231 DAK	❑			
23,2				232 DAK	❑			
23,3				233 DAK	❑			
23,4				234 DAK	❑			
23,5				235 DAK	❑			
23,6	32	60	4,4	KDS 236 DAK	❑	284,4	178	190
23,7				237 DAK	❑			
23,8				238 DAK	❑			
23,9				239 DAK	❑			
24,0				240 DAK	❑			
24,1				241 DAK	❑			
24,2				242 DAK	❑			
24,3				243 DAK	❑			
24,4				244 DAK	❑			
24,5				245 DAK	❑			

●Diameter Ø 24,6–40,5 mm

Dimensions (mm)				Cat. No.	Extra Long Series (7D)			
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)		
	DCON	LS	PL		DAK	OAL	LU	LUX
24,6	32	60	4,5	KDS 246 DAK	❑	294,5	187	200
24,7				247 DAK	❑			
24,8				248 DAK	❑			
24,9				249 DAK	❑			
25,0				250 DAK	❑			
25,1				251 DAK	❑			
25,2				252 DAK	❑			
25,3				253 DAK	❑			
25,4				254 DAK	❑			
25,5				255 DAK	❑			
25,6	32	60	4,7	KDS 256 DAK	❑	304,7	197	210
25,7				257 DAK	❑			
25,8				258 DAK	❑			
25,9				259 DAK	❑			
26,0				260 DAK	❑			
26,1 –26,5				261 DAK –265 DAK	❑			
26,6 –27,5	32	60	4,9	KDS 266 DAK –275 DAK	❑	309,9	201	215
27,6 –28,5	32	60	5,1	KDS 276 DAK –285 DAK	❑	315,1	206	200
28,6 –29,5	32	60	5,3	KDS 286 DAK –295 DAK	❑	325,3	215	230
29,6 –30,5	32	60	5,5	KDS 296 DAK –305 DAK	❑	335,5	225	240
30,6 –31,5	40	70	5,6	KDS 306 DAK –315 DAK	❑	350,6	229	245
31,6 –32,5	40	70	5,8	KDS 316 DAK –325 DAK	❑	360,8	234	250
32,6 –33,5	40	70	6,0	KDS 326 DAK –335 DAK	❑	371,0	243	260
33,6 –34,5	40	70	6,2	KDS 336 DAK –345 DAK	❑	381,2	253	270
34,6 –35,5	40	70	6,4	KDS 346 DAK –355 DAK	❑	391,4	257	275
35,6 –36,5	40	70	6,6	KDS 356 DAK –365 DAK	❑	396,6	262	280
36,6 –37,5	40	70	6,7	KDS 366 DAK –375 DAK	❑	406,7	271	290
37,6 –38,5	40	70	6,9	KDS 376 DAK –385 DAK	❑	416,9	292	338
38,6 –39,5	40	70	7,1	KDS 386 DAK –395 DAK	❑	422,1	296	343
39,6 –40,5	40	70	7,3	KDS 396 DAK –405 DAK	❑	427,3	300	348

■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs. Please specify the Cat. No.
For example, if the diameter of the drill is 10,2 mm, please indicate as follow.

E.g., **KDS 102 D AK** , ACW30 (Grade)

KDS series: Brazed carbide drill with coolant holes

Drill diameter **10,2** mm

AK: Brazed carbide and TiAlN coated drill

D : 7 x D

Brazed Carbide MULTI-DRILLs
KDS ... FA Type

(Available on Request)

Extra Long Type (10 x D) Brazed Carbide Drills with Coolant Holes



Helix angle: 25° ---> 0°
ℓ_2 = Effective drilling length



Specification:
- Brazed carbide (Grade: G10E) drill with coolant holes
- Shank with whistle notch

●Diameter Ø 8,0–15,0 mm

Dimensions (mm)				Cat. No.	Extra Long Series (10D)		
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)	
	DCON	LS	PL		FA10	OAL	LUX
8,0 –8,5	16	48	1,5	KDS 080 FA10 –085 FA10	❑	156,5	93
8,6 –9,5	16	48	1,6	KDS 086 FA10 –095 FA10	❑	171,6	104
9,6 –10,5	16	48	1,8	KDS 096 FA10 –105 FA10	❑	181,8	115
10,6 –11,5	16	48	2,0	KDS 106 FA10 –115 FA10	❑	197,0	126
11,6 –12,5	16	48	2,2	KDS 116 FA10 –125 FA10	❑	207,2	137
12,6 –13,5	16	48	2,4	KDS 126 FA10 –135 FA10	❑	222,4	148
13,6 –14,5	16	48	2,5	KDS 136 FA10 –145 FA10	❑	232,5	159
14,6 –15,5	20	50	2,7	KDS 146 FA10 –155 FA10	❑	247,7	170
15,6 –16,5	20	50	2,9	KDS 156 FA10 –165 FA10	❑	262,9	181
16,6 –17,5	20	50	3,1	KDS 166 FA10 –175 FA10	❑	273,1	192
17,6 –18,5	20	50	3,3	KDS 176 FA10 –185 FA10	❑	288,3	203
18,6 –19,5	25	56	3,5	KDS 186 FA10 –195 FA10	❑	303,5	214

●Diameter Ø 15,1–19,5 mm

Dimensions (mm)				Cat. No.	Extra Long Series (10D)		
DC (mm)	Shank		Drill Head		Stock	Dimensions (mm)	
	DCON	LS	PL		FA10	OAL	LUX
19,6 –20,5	25	56	3,6	KDS 196 FA10 –205 FA10	❑	318,6	225
20,6 –21,5	25	56	3,8	KDS 206 FA10 –215 FA10	❑	328,8	236
21,6 –22,5	25	56	4,0	KDS 216 FA10 –225 FA10	❑	344,0	247
22,6 –23,5	25	56	4,2	KDS 226 FA10 –235 FA10	❑	354,2	258
23,6 –24,5	32	60	4,4	KDS 236 FA10 –245 FA10	❑	374,4	269
24,6 –25,5	32	60	4,5	KDS 246 FA10 –255 FA10	❑	384,5	280
25,6 –26,5	32	60	4,7	KDS 256 FA10 –265 FA10	❑	399,7	291
26,6 –27,5	32	60	4,9	KDS 266 FA10 –275 FA10	❑	409,9	302
27,6 –28,5	32	60	5,1	KDS 276 FA10 –285 FA10	❑	425,1	313
28,6 –29,5	32	60	5,3	KDS 286 FA10 –295 FA10	❑	435,3	324
29,6 –30,5	32	60	5,5	KDS 296 FA10 –305 FA10	❑	450,5	335

Brazed Carbide Multi-Drills for Cast Irons and Aluminium Alloys

■ How to Order

Non-Stock Items will be required minimum order quantity for 6 pcs. Please specify the Cat. No.
For example, if the diameter of the drill is 10,2 mm, please indicate as follow.

E.g., **KDS 102 FA 10** ,G10E (Grade)

KDS series: Brazed carbide drill with coolant holes

Drill diameter **10,2** mm

10: Effective drilling length

FA: Extra long type brazed carbide drill with special flutes (Helix angle: 25° ⇨ 0°)

■ Recommended Cutting Conditions

(v_c : Cutting Speed (m/min), f : Feed rate (mm/rev)) (Min – **Standard** – Max)

Diameter (mm)		Cast Irons	Aluminium Alloys	Remarks
–Ø 12		30–**55**–60	50–**70**–90	To avoid the drill bending, which can cause breakage, please pre-drill or reduce the cutting conditions at the entrance of hole; RPM: 100–300, f : 0,05–0,08 mm/rev. Higher feed rates and deep holes require high coolant pressure. Cutting fluid : Water soluble oil Cutting fluid pressure : 4–10 bar
		0,1–**0,2**–0,25	0,1–**0,2**–0,3	
–Ø 20		40–**60**–70	60–**70**–100	
		0,2–**0,3**–0,4	0,3–**0,35**–0,5	
–Ø 30		40–**60**–70	70–**100**–150	
		0,3–**0,4**–0,5	0,3–**0,4**–0,5	

❑ = Delivery on request

SMD Type

General Features

Fast accurate and ideal for drilling steels, this newly developed drill from SUMITOMO gives similar hole accuracy to that of regrindable drills renowned within the industry as being the ultimate hole making tool.

Advantages

- Available in diameters ranging from 12,0–42,5 mm
- Drilling Depths 1,5–12 x Diameter
- Optimised heat dissipation via precisely located coolant holes
- Maximised rigidity from newly developed clamping system
- High performance drilling of precision holes from solid
- 3 different types of head for general and smooth cutting (MTL type, MEL type) and new MFS type for drilling in non-flat surfaces.

The newly developed tungsten carbide substrate with it's ultra hard smooth coating proved that against competition users can expect to see holes with tolerances similar to that of reaming and tool life almost doubled.

Edge security comes from replaceable drilling heads bolted to fixed radial serrations which provide a rigid and precise clamping platform.

Specially treated toughened steel body to resist wear and rust

Through coolant holes positioned to optimise coolant pressure and direction.



Drilling Precision



Drill: Ø 18,0 mm
Work material: C50
Conditions: v_c = 70 m/min, f = 0,25 mm/rev
a_p = 38 mm (through), Water soluble

Application Example



Work material: 34CrMo4 (H_B235–302)
Drill: Ø 18,0 mm
Conditions: v_c = 70 m/min, f = 0,25 mm/rev
a_p = 38 mm (through), Water soluble

SMDH Type

● Holder 3D / 5D / 8D

Shank Type:
Whistle notch type



● Holder **1,5D**

Shank Type:
Weldon type



● Holder **12D**

Shank Type:
Cylindrical type



ℓ_2 = Effective drilling length

■ Holder

(mm)

Dimensions				Cat. No.	Series (1,5D)				Series (3D)			Series (5D)			Series (8D)			Series (12D)				Related Drill Heads DMTL / DMEL
Drill Head		Shank			Stock	Dimensions			Stock	Dimensions		Stock	Dimensions		Stock	Dimensions		Stock	Dimensions			
Ø D	ℓ_1	Ød	ℓ_3		**S**	L	ℓ_2	Ød2	**M3**	L	ℓ_2	**M5**	L	ℓ_2	**M8**	L	ℓ_2	**12D**	L	ℓ_2	Ød2	
12,0	2,2	16	48	SMDH 120□□	●	91	25,5	20	●	107,2	43,5	●	132,2	68,5								1200–1249
12,5	2,3			SMDH 125□□	●	91	25,5	20	●	107,3	43,5	●	132,3	68,5								1250–1299
13,0	2,4			SMDH 130□□	●	92	27,5	20	●	112,4	46,5	●	142,4	73,5								1300–1349
14,0	2,5			SMDH 140□□□	●	96	31,5	20	●	119,0	52,5	●	149,0	81,5	●	194,0	124,5	●	238,5	168,5	20	1350–1450
15,0	2,7	20	50	SMDH 150□□□	●	100	32,0	25	●	129,2	55,0	●	159,2	86,0	●	204,2	133,0	●	253,0	180,0	25	1451–1550
16,0	2,9			SMDH 160□□□	●	103	35,0	25	●	134,4	59,0	●	169,4	92,0		214,4	141,0	●	265,5	192,0	25	1551–1650
17,0	3,1			SMDH 170□□□	●	105	35,5	25	●	139,6	62,5	●	174,6	97,5	●	224,6	150,5	●	278,1	203,5	25	1651–1750
18,0	3,3			SMDH 180□□□	●	107	39,7	25	●	144,8	66,5	●	179,8	103,5	●	229,8	158,5	●	290,5	215,5	25	1751–1850
19,0	3,5	25	56	SMDH 190□□□	●	115	40,5	30	●	160,1	69,5	●	195,0	108,5	●	255,0	167,5	●	309,1	228,5	30	1851–1950
20,0	3,6			SMDH 200□□□	●	118	43,0	30	●	160,1	73,0	●	200,1	114,0	●	265,1	175,0	●	321,4	240,0	30	1951–2050
21,0	3,8			SMDH 210□□□	●	119	44,0	30	●	160,3	76,0	●	200,3	119,0	●	270,3	184,0	●	333,9	252,0	30	2051–2150
22,0	4,0			SMDH 220□□□	●	121	47,0	30	●	165,1	80,0	●	205,1	125,0	●	275,1	192,0	●	347,0	264,0	30	2151–2280
23,0	4,2			SMDH 230□□□	●	122	46,5	30	●	164,8	82,5	●	214,8	129,5	●	284,8	200,5	●	359,0	275,5	30	2281–2380
24,0	4,4	32	60	SMDH 240□□□	●	129	49,5	37	●	174,6	86,5	●	224,6	135,5	●	299,6	208,5	●	376,1	284,5	37	2381–2480
25,0	4,6			SMDH 250□□□	●	129	49,0	37	●	174,6	88,0	●	229,6	140,0	●	304,6	217,0	●	388,4	300,0	37	2481–2580
26,0	4,7			SMDH 260□□	●	132	52,0	37	●	179,7	92,0	●	234,7	146,0	●	314,7	225,0					2581–2680
27,0	4,9			SMDH 270□□	●	133	53,0	37	●	179,9	94,0	●	239,9	151,0	●	324,9	234,0					2681–2780
28,0	5,1			SMDH 280□□	●	135	54,5	37	●	185,1	96,5	●	245,1	156,5	●	330,1	241,5					2781–2880
29,0	5,3			SMDH 290□□	●	136	55,5	37	●	190,3	99,5	●	250,3	161,5	●	340,3	250,5					2881–2980
30,0	5,5			SMDH 300□□	●	139	58,5	37	●	190,5	104,5	●	260,5	167,5	●	350,5	259,5					2981–3050

Drill order description example: SMDH210M3, drill heads ➪ K59/H60

■ Recommended Torque

Screw		Applicable Insert
	N·m	
BXD 02208 IP	0,8–1,0	SMDT 1200 – 1550 D M□L
BXD 02509 IP	0,9–1,2	SMDT 1551 – 1850 D M□L
BXD 03011 IP	1,8–2,4	SMDT 1851 – 2150 D M□L
BXD 03512 IP	2,8–3,7	SMDT 2151 – 2480 D M□L
BXD 04014 IP	4,1–5,5	SMDT 2481 – 2780 D M□L
BXD 04515 IP	5,0–6,6	SMDT 2781 – 3050 D M□L

■ Spare Parts

Screw	Wrench	Applicable Holder
BXD 02208 IP	TRDR 08 IP	SMDT 120 – 150 M□
BXD 02509 IP	TRDR 10 IP	SMDT 160 – 180 M□
BXD 03011 IP	TRDR 15 IP	SMDT 190 – 210 M□
BXD 03512 IP	TRDR 15 IP	SMDT 220 – 240 M□
BXD 04014 IP	TRDR 20 IP	SMDT 250 – 270 M□
BXD 04515 IP	TRDR 25 IP	SMDT 280 – 300 M□

● = Euro stock

Regrindable Drill Head Insert
SMDT... D MTL Type

PVD coated grade: **ACX70**

Type MTL



Drill Head (Insert)

● Ø 12,0–15,3 mm

DC (mm)	Cat. No.	Stock	PL	LF
12,0	SMDT 1200 D MTL	●	2,2	6,9
12,1	1210 D MTL	●	2,2	
12,2	1220 D MTL	●	2,2	
12,3	1230 D MTL	●	2,2	
12,4	1240 D MTL	●	2,3	
12,5	SMDT 1250 D MTL	●	2,3	7,1
12,6	1260 D MTL	●	2,3	
12,7	1270 D MTL	●	2,3	
12,8	1280 D MTL	●	2,3	
12,9	1290 D MTL	●	2,3	
13,0	SMDT 1300 D MTL	●	2,4	7,3
13,1	1310 D MTL	●	2,4	
13,2	1320 D MTL	●	2,4	
13,3	1330 D MTL	●	2,4	
13,4	1340 D MTL	●	2,4	
13,5	SMDT 1350 D MTL	●	2,5	7,8
13,6	1360 D MTL	●	2,5	
13,7	1370 D MTL	●	2,5	
13,8	1380 D MTL	●	2,5	
13,9	1390 D MTL	●	2,5	
14,0	1400 D MTL	●	2,5	
14,1	1410 D MTL	●	2,6	
14,2	1420 D MTL	●	2,6	
14,3	1430 D MTL	●	2,6	
14,4	1440 D MTL	●	2,6	
14,5	1450 D MTL	●	2,6	
14,6	SMDT 1460 D MTL	●	2,7	8,3
14,7	1470 D MTL	●	2,7	
14,8	1480 D MTL	●	2,7	
14,9	1490 D MTL	●	2,7	
15,0	1500 D MTL	●	2,7	
15,1	1510 D MTL	●	2,7	
15,2	1520 D MTL	●	2,8	
15,3	1530 D MTL	●	2,8	

● Ø 15,4–18,7 mm

DC (mm)	Cat. No.	Stock	PL	LF
15,4	SMDT 1540 D MTL	●	2,8	8,3
15,5	1550 D MTL	●	2,8	
15,6	SMDT 1560 D MTL	●	2,8	8,7
15,7	1570 D MTL	●	2,9	
15,8	1580 D MTL	●	2,9	
15,9	1590 D MTL	●	2,9	
16,0	1600 D MTL	●	2,9	
16,1	1610 D MTL	●	2,9	
16,2	1620 D MTL	●	2,9	
16,3	1630 D MTL	●	3,0	
16,4	1640 D MTL	●	3,0	
16,5	1650 D MTL	●	3,0	
16,6	SMDT 1660 D MTL	●	3,0	9,2
16,7	1670 D MTL	●	3,0	
16,8	1680 D MTL	●	3,1	
16,9	1690 D MTL	●	3,1	
17,0	1700 D MTL	●	3,1	
17,1	1710 D MTL	●	3,1	
17,2	1720 D MTL	●	3,1	
17,3	1730 D MTL	●	3,1	
17,4	1740 D MTL	●	3,2	
17,5	1750 D MTL	●	3,2	
17,6	SMDT 1760 D MTL	●	3,2	9,6
17,7	1770 D MTL	●	3,2	
17,8	1780 D MTL	●	3,2	
17,9	1790 D MTL	●	3,3	
18,0	1800 D MTL	●	3,3	
18,1	1810 D MTL	●	3,3	
18,2	1820 D MTL	●	3,3	
18,3	1830 D MTL	●	3,3	
18,4	1840 D MTL	●	3,3	
18,5	1850 D MTL	●	3,4	
18,6	SMDT 1860 D MTL	●	3,4	10,1
18,7	1870 D MTL	●	3,4	

● Ø 18,8–30,5 mm

DC (mm)	Cat. No.	Stock	PL	LF
18,8	SMDT 1880 D MTL	●	3,4	10,1
18,9	1890 D MTL	●	3,4	
19,0	1900 D MTL	●	3,5	
19,1	1910 D MTL	●	3,5	
19,2	1920 D MTL	●	3,5	
19,3	1930 D MTL	●	3,5	
19,4	1940 D MTL	●	3,5	
19,5	1950 D MTL	●	3,5	
19,6	SMDT 1960 D MTL	●	3,6	10,5
19,7	1970 D MTL	●	3,6	
19,8	1980 D MTL	●	3,6	
19,9	1990 D MTL	●	3,6	
20,0	2000 D MTL	●	3,6	
20,5	SMDT 2050 D MTL	●	3,7	
21,0	SMDT 2100 D MTL	●	3,8	11,0
21,5	2150 D MTL	●	3,9	
22,0	SMDT 2200 D MTL	●	4,0	11,0
22,5	2250 D MTL	●	4,1	
23,0	SMDT 2300 D MTL	●	4,2	11,0
23,5	2350 D MTL	●	4,3	
24,0	SMDT 2400 D MTL	●	4,4	11,0
24,5	2450 D MTL	●	4,5	
25,0	SMDT 2500 D MTL	●	4,5	11,3
25,5	2550 D MTL	●	4,6	
26,0	SMDT 2600 D MTL	●	4,7	11,7
26,5	2650 D MTL	●	4,8	
27,0	SMDT 2700 D MTL	●	4,9	12,2
27,5	2750 D MTL	●	5,0	
28,0	SMDT 2800 D MTL	●	5,1	12,6
28,5	2850 D MTL	●	5,2	
29,0	SMDT 2900 D MTL	●	5,3	13,1
29,5	2950 D MTL	●	5,4	
30,0	SMDT 3000 D MTL	●	5,5	13,5
30,5	3050 D MTL	●	5,6	

Recommended Cutting Conditions

● For using **3 x D** and **5 x D** type drills

Drill Ø (mm) \ Work material		General steel (HB250–320)	Harden steel (HRC45)	Nodular cast iron
~ 16,0	v_c	70 – **100** – 120	40 – **60** – 90	50 – **60** – 80
	f	0,15 – **0,2** – 0,3	0,1 – **0,15** – 0,2	0,2 – **0,25** – 0,3
~ 20,0	v_c	70 – **100** – 120	40 – **70** – 90	50 – **70** – 90
	f	0,15 – **0,25** – 0,35	0,15 – **0,2** – 0,25	0,2 – **0,25** – 0,35
~ 30,8	v_c	70 – **100** – 120	40 – **60** – 90	50 – **70** – 90
	f	0,2 – **0,25** – 0,35	0,15 – **0,2** – 0,25	0,25 – **0,3** – 0,35

Note: High cutting performance is enhanced when using a high quality machine and rigid set up.

● For using **8 x D** and **12 x D** type drills

Drill Ø (mm) \ Work material		General steel (HB250–320)	Harden steel (HRC45)	Nodular cast iron
~ 16,0	v_c	50 – **70** – 80	30 – **50** – 70	40 – **50** – 70
	f	0,15 – **0,2** – 0,3	0,1 – **0,15** – 0,2	0,2 – **0,25** – 0,3
~ 20,0	v_c	50 – **70** – 80	30 – **50** – 70	40 – **60** – 80
	f	0,15 – **0,25** – 0,35	0,15 – **0,2** – 0,25	0,2 – **0,25** – 0,35
~ 25,0 (12D) ~ 30,5 (8D)	v_c	50 – **70** – 80	30 – **50** – 70	40 – **60** – 80
	f	0,2 – **0,25** – 0,35	0,15 – **0,2** – 0,25	0,25 – **0,3** – 0,35

[v_c : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max]

Regrindable Drill Head Insert
SMDT... D MEL Type

MEL Type for Smooth Cutting

(Soft Steel, Stainless Steel, Grey Cast Iron)

PVD coated grade: **ACX80**

Type MEL



Drill Head (Insert)

● Ø 12,0–15,3 mm

DC (mm)	Cat. No.	Stock	PL	LF
12,0	SMDT 1200 D MEL	●	2,2	
12,1	1210 D MEL	●	2,2	
12,2	1220 D MEL	●	2,2	6,9
12,3	1230 D MEL	●	2,2	
12,4	1240 D MEL	●	2,3	
12,5	SMDT 1250 D MEL	●	2,3	
12,6	1260 D MEL	●	2,3	
12,7	1270 D MEL	●	2,3	7,1
12,8	1280 D MEL	●	2,3	
12,9	1290 D MEL	●	2,3	
13,0	SMDT 1300 D MEL	●	2,4	
13,1	1310 D MEL	●	2,4	
13,2	1320 D MEL	●	2,4	7,3
13,3	1330 D MEL	●	2,4	
13,4	1340 D MEL	●	2,4	
13,5	SMDT 1350 D MEL	●	2,5	
13,6	1360 D MEL	●	2,5	
13,7	1370 D MEL	●	2,5	
13,8	1380 D MEL	●	2,5	
13,9	1390 D MEL	●	2,5	
14,0	1400 D MEL	●	2,5	7,8
14,1	1410 D MEL	●	2,6	
14,2	1420 D MEL	●	2,6	
14,3	1430 D MEL	●	2,6	
14,4	1440 D MEL	●	2,6	
14,5	1450 D MEL	●	2,6	
14,6	SMDT 1460 D MEL	●	2,7	
14,7	1470 D MEL	●	2,7	
14,8	1480 D MEL	●	2,7	
14,9	1490 D MEL	●	2,7	
15,0	1500 D MEL	●	2,7	8,3
15,1	1510 D MEL	●	2,7	
15,2	1520 D MEL	●	2,8	
15,3	1530 D MEL	●	2,8	

● Ø 15,4–18,7 mm

DC (mm)	Cat. No.	Stock	PL	LF
15,4	SMDT 1540 D MEL	●	2,8	8,3
15,5	1550 D MEL	●	2,8	
15,6	SMDT 1560 D MEL	●	2,8	
15,7	1570 D MEL	●	2,9	
15,8	1580 D MEL	●	2,9	
15,9	1590 D MEL	●	2,9	
16,0	1600 D MEL	●	2,9	8,7
16,1	1610 D MEL	●	2,9	
16,2	1620 D MEL	●	2,9	
16,3	1630 D MEL	●	3,0	
16,4	1640 D MEL	●	3,0	
16,5	1650 D MEL	●	3,0	
16,6	SMDT 1660 D MEL	●	3,0	
16,7	1670 D MEL	●	3,0	
16,8	1680 D MEL	●	3,1	
16,9	1690 D MEL	●	3,1	
17,0	1700 D MEL	●	3,1	9,2
17,1	1710 D MEL	●	3,1	
17,2	1720 D MEL	●	3,1	
17,3	1730 D MEL	●	3,1	
17,4	1740 D MEL	●	3,2	
17,5	1750 D MEL	●	3,2	
17,6	SMDT 1760 D MEL	●	3,2	
17,7	1770 D MEL	●	3,2	
17,8	1780 D MEL	●	3,2	
17,9	1790 D MEL	●	3,3	
18,0	1800 D MEL	●	3,3	9,6
18,1	1810 D MEL	●	3,3	
18,2	1820 D MEL	●	3,3	
18,3	1830 D MEL	●	3,3	
18,4	1840 D MEL	●	3,3	
18,5	1850 D MEL	●	3,4	
18,6	SMDT 1860 D MEL	●	3,4	10,1
18,7	1870 D MEL	●	3,4	

● Ø 18,8–30,5 mm

DC (mm)	Cat. No.	Stock	PL	LF
18,8	SMDT 1880 D MEL	●	3,4	
18,9	1890 D MEL	●	3,4	
19,0	1900 D MEL	●	3,5	
19,1	1910 D MEL	●	3,5	10,1
19,2	1920 D MEL	●	3,5	
19,3	1930 D MEL	●	3,5	
19,4	1940 D MEL	●	3,5	
19,5	1950 D MEL	●	3,5	
19,6	SMDT 1960 D MEL	●	3,6	
19,7	1970 D MEL	●	3,6	
19,8	1980 D MEL	●	3,6	10,5
19,9	1990 D MEL	●	3,6	
20,0	2000 D MEL	●	3,6	
20,5	SMDT 2050 D MEL	●	3,7	
21,0	SMDT 2100 D MEL	●	3,8	11,0
21,5	2150 D MEL	●	3,9	
22,0	SMDT 2200 D MEL	●	4,0	11,0
22,5	2250 D MEL	●	4,1	
23,0	SMDT 2300 D MEL	●	4,2	11,0
23,5	2350 D MEL	●	4,3	
24,0	SMDT 2400 D MEL	●	4,4	11,0
24,5	2450 D MEL	●	4,5	
25,0	SMDT 2500 D MEL	●	4,5	11,3
25,5	2550 D MEL	●	4,6	
26,0	SMDT 2600 D MEL	●	4,7	11,7
26,5	2650 D MEL	●	4,8	
27,0	SMDT 2700 D MEL	●	4,9	12,2
27,5	2750 D MEL	●	5,0	
28,0	SMDT 2800 D MEL	●	5,1	12,6
28,5	2850 D MEL	●	5,2	
29,0	SMDT 2900 D MEL	●	5,3	13,1
29,5	2950 D MEL	●	5,4	
30,0	SMDT 3000 D MEL	●	5,5	13,5
30,5	3050 D MEL	●	5,6	

Recommended Cutting Conditions

● For using **3 x D** and **5 x D** type drills

Drill Ø (mm) \ Work material		Soft steel (–HB250)	Stainless steel (–HB200)	Grey cast iron
~ 16,0	v_c	80 – **100** – 120	50 – **60** – 80	50 – **70** – 90
	f	0,15 – **0,2** – 0,35	0,1 – **0,15** – 0,2	0,2 – **0,25** – 0,3
~ 20,0	v_c	80 – **100** – 120	60 – **70** – 90	60 – **80** – 100
	f	0,15 – **0,25** – 0,35	0,15 – **0,2** – 0,25	0,25 – **0,3** – 0,35
~ 30,8	v_c	80 – **100** – 120	60 – **70** – 90	60 – **80** – 100
	f	0,2 – **0,3** – 0,35	0,15 – **0,2** – 0,25	0,2 – **0,35** – 0,40

Note: High cutting performance is enhanced when using a high quality machine and rigid set up.

● For using **8 x D** and **12 x D** type drills

Drill Ø (mm) \ Work material		Soft steel (–HB250)	Stainless steel (–HB200)	Grey cast iron
~ 16,0	v_c	50 – **70** – 80	40 – **50** – 60	40 – **60** – 80
	f	0,15 – **0,2** – 0,35	0,1 – **0,15** – 0,2	0,2 – **0,25** – 0,3
~ 20,0	v_c	50 – **70** – 80	40 – **60** – 70	50 – **70** – 90
	f	0,15 – **0,25** – 0,35	0,15 – **0,2** – 0,25	0,25 – **0,3** – 0,35
~ 25,0 (12D) ~ 30,5 (8D)	v_c	60 – **70** – 80	40 – **60** – 70	50 – **70** – 90
	f	0,2 – **0,3** – 0,35	0,15 – **0,2** – 0,25	0,2 – **0,35** – 0,4

[v_c : Cutting Speed (m/min), f : Feed rate (mm/rev), Min - **Optimum** - Max]

● = Euro stock

Advantages

- Replaceable and regrindable drill head
- New design decreases cutting force by 25 %
- Ideal for stainless steels - soft steels etc
- Excellent tool life when drilling cast iron
- Improves drilling performance on low powered machines
- Increases productivity

Performance (Stainless steel machinig)

Comparison of cutting force



Work Material: X5CrNi1810 (1.4301)
Drill Diameter: Ø 16,5 x 5D
Conditions: v_c = 60 m/min

Chip comparison



Work Material: X5CrNi1810 (1.4301)
Drill Diameter: Ø 16,5 x 5D
Conditions: v_c = 60 m/min, f = 0,15 mm/rev

Performance (Cast iron machinig)

Comparison of cutting force



Work Material: GGG45
Drill Diameter: Ø 18 x 5D
Conditions: v_c = 80 m/min

Comparison of wear resistance



Work Material: GG25
Drill Diameter: Ø 14 x 5D
Cutting Length: 34,7 m

Conditions: v_c = 100 m/min
f = 0,2 mm/rev
Wet

MFS Type Ideal for Drilling in Non-Flat Surfaces and Less Burr



Advantages

- **Various Drilling Operations Thanks to a Point Angle of 180°**
  Applicable to high-efficiency spot facing, drilling in non-flat surfaces such as inclined and cylindrical surfaces and interrupted drilling.
  Also reduces burrs st the hole exit.

- **Improves Machining Stability**
  Achieves high rigidity by employing RS Thinning, which ensures thick web at the bottom.

● Holder



No flat face for side lock clamping on the shank of 12D holders.

Holder

Dimensions			Cat. No.	Series (1,5D)				Series (3D)			Series (5D)			Series (8D)			Series (12D)				Related Drill Heads MFS
Drill Head	Shank			Stock	Dimensions			Stock	Dimensions		Stock	Dimensions		Stock	Dimensions		Stock	Dimensions			
DC	DCON	LS		S	OAL	LU	DCSFMS	M3	OAL	LU	M5	OAL	LU	M8	OAL	LU	12D	OAL	LU	DCSFMS	
12,0	16	48	SMDH 120□□	●	91	25,5	20	●	107,2	43,5	●	132,2	68,5								1200–1249
12,5			SMDH 125□□	●	91	25,5	20	●	107,3	43,5	●	132,3	68,5								1250–1299
13,0			SMDH 130□□	●	92	27,5	20	●	112,4	46,5	●	142,4	73,5								1300–1349
14,0			SMDH 140□□□	●	96	31,5	20	●	119,0	52,5	●	149,0	81,5	●	194,0	124,5	●	238,5	168,5	20	1350–1450
15,0	20	50	SMDH 150□□□	●	100	32,0	25	●	129,2	55,0	●	159,2	86,0	●	204,2	133,0	●	253,0	180,0	25	1451–1550
16,0			SMDH 160□□□	●	103	35,0	25	●	134,4	59,0	●	169,4	92,0	●	214,4	141,0	●	265,5	192,0	25	1551–1650
17,0			SMDH 170□□□	●	105	35,5	25	●	139,6	62,5	●	174,6	97,5	●	224,6	150,5	●	278,1	203,5	25	1651–1750
18,0			SMDH 180□□□	●	107	39,7	25	●	144,8	66,5	●	179,8	103,5	●	229,8	158,5	●	290,5	215,5	25	1751–1850
19,0	25	56	SMDH 190□□□	●	115	40,5	30	●	160,1	69,5	●	195,0	108,5	●	255,0	167,5	●	309,1	228,5	30	1851–1950
20,0			SMDH 200□□□	●	118	43,0	30	●	160,1	73,0	●	200,1	114,0	●	265,1	175,0	●	321,4	240,0	30	1951–2050
21,0			SMDH 210□□□	●	119	44,0	30	●	160,3	76,0	●	200,3	119,0	●	270,3	184,0	●	333,9	252,0	30	2051–2150
22,0			SMDH 220□□□	●	121	47,0	30	●	165,1	80,0	●	205,1	125,0	●	275,1	192,0	●	347,0	264,0	30	2151–2280
23,0			SMDH 230□□□	●	122	46,5	30	●	164,8	82,5	●	214,8	129,5	●	284,8	200,5	●	359,0	275,5	30	2281–2380
24,0	32	60	SMDH 240□□□	●	129	49,5	37	●	174,6	86,5	●	224,6	135,5	●	299,6	208,5	●	376,1	284,5	37	2381–2480
25,0			SMDH 250□□□	●	129	49,0	37	●	174,6	88,0	●	229,6	140,0	●	304,6	217,0	●	388,4	300,0	37	2481–2580
26,0			SMDH 260□□	●	132	52,0	37	●	179,7	92,0	●	234,7	146,0	●	314,7	225,0					2581–2680
27,0			SMDH 270□□	●	133	53,0	37	●	179,9	94,0	●	239,9	151,0	●	324,9	234,0					2681–2780
28,0			SMDH 280□□	●	135	54,5	37	●	185,1	96,5	●	245,1	156,5	●	330,1	241,5					2781–2880
29,0			SMDH 290□□	●	136	55,5	37	●	190,3	99,5	●	250,3	161,5	●	340,3	250,5					2881–2980
30,0			SMDH 300□□	●	139	58,5	37	●	190,5	104,5	●	260,5	167,5	●	350,5	259,5					2981–3050

Drill order description example: SMDH210M3, drill heads ⇨ K63

Recommended Torque

Screw		Applicable Insert
	N·m	
BXD 02208 IP	0,8–1,0	SMDT 1200 – 1550 MFS
BXD 02509 IP	0,9–1,2	SMDT 1551 – 1850 MFS
BXD 03011 IP	1,8–2,4	SMDT 1851 – 2150 MFS
BXD 03512 IP	2,8–3,7	SMDT 2151 – 2480 MFS
BXD 04014 IP	4,1–5,5	SMDT 2481 – 2780 MFS
BXD 04515 IP	5,0–6,6	SMDT 2781 – 3050 MFS

Spare Parts

Screw	Wrench	Applicable Holder
		
BXD 02208 IP	TRDR 08 IP	SMDT 120 – 150 □□
BXD 02509 IP	TRDR 10 IP	SMDT 160 – 180 □□
BXD 03011 IP	TRDR 15 IP	SMDT 190 – 210 □□
BXD 03512 IP	TRDR 15 IP	SMDT 220 – 240 □□
BXD 04014 IP	TRDR 20 IP	SMDT 250 – 270 □□
BXD 04515 IP	TRDR 25 IP	SMDT 280 – 300 □□

● = Euro stock

N·m Recommended Tightening Torque (N·m)

Drill Head Insert
SMDT... MFS Type

Type MFS





PVD coated grade: **ACX70**

■ Drill Head (Insert)

● ø 12,0 ~ 21,5 mm

DC (mm)	Cat. No.	Stock	LF (mm)	Applicable Holders
12,0	SMDT 1200 MFS	●	7,1	SMDH120 □□
12,5	SMDT 1250 MFS	●	7,2	SMDH125 □□
13,0	SMDT 1300 MFS	●	7,5	SMDH130 □□
13,5	SMDT 1350 MFS	●	7,9	SMDH140 □□
14,0	SMDT 1400 MFS	●		
14,5	SMDT 1450 MFS	●		
15,0	SMDT 1500 MFS	●	8,3	SMDH150 □□
15,5	SMDT 1550 MFS	●		
16,0	SMDT 1600 MFS	●	8,8	SMDH160 □□
16,5	SMDT 1650 MFS	●		
17,0	SMDT 1700 MFS	●	9,3	SMDH170 □□
17,5	SMDT 1750 MFS	●		
18,0	SMDT 1800 MFS	●	9,8	SMDH180 □□
18,5	SMDT 1850 MFS	●		
19,0	SMDT 1900 MFS	●	10,2	SMDH190 □□
19,5	SMDT 1950 MFS	●		
20,0	SMDT 2000 MFS	●	10,7	SMDH200 □□
20,5	SMDT 2050 MFS	●		
21,0	SMDT 2100 MFS	●	11,2	SMDH210 □□
21,5	SMDT 2150 MFS	●		

● ø 22,0 ~ 30,0 mm

DC (mm)	Cat. No.	Stock	LF (mm)	Applicable Holders
22,0	SMDT 2200 MFS	●	11,2	SMDH220 □□
22,5	SMDT 2250 MFS	●		
23,0	SMDT 2300 MFS	●	11,2	SMDH230 □□
23,5	SMDT 2350 MFS	●		
24,0	SMDT 2400 MFS	●	11,3	SMDH240 □□
24,5	SMDT 2450 MFS	●		
25,0	SMDT 2500 MFS	●	11,7	SMDH250 □□
25,5	SMDT 2550 MFS	●		
26,0	SMDT 2600 MFS	●	12,2	SMDH260 □□
26,5	SMDT 2650 MFS	●		
27,0	SMDT 2700 MFS	●	12,7	SMDH270 □□
27,5	SMDT 2750 MFS	●		
28,0	SMDT 2800 MFS	●	13,2	SMDH280 □□
28,5	SMDT 2850 MFS	●		
29,0	SMDT 2900 MFS	●	13,6	SMDH290 □□
29,5	SMDT 2950 MFS	●		
30,0	SMDT 3000 MFS	●	14,1	SMDH300 □□

■ MFS Type Head Important Notes

	No Guide Hole (Solid Workpiece Hole Drilling)	With Guide Hole	Flat Finishing of Hole Bottom
Application			
1,5D Holder	○	○ (Guide Hole not required)	○
3D–12D Holder	X	X	○

■ Recommended Cutting Conditions

v_c: Cutting speed (m/min)
f: Feed rate (mm/rev)

Work Material		Soft Steel (<250 HB)	General Steel (250–320HB)	Hardened Steel (45HRC)	Stainless Steel (<200 HB)	Gray Cast Iron	Ductile Cast Iron	Aluminum Alloy (*)
Drill Diameter DC (mm)	Cutting Conditions	Min.-**Optimum**-Max.	Min.-**Optimum**-Max.	Min.-**Optimum**-Max.	Min.-**Optimum**-Max.	Min.-**Optimum**-Max.	Min.-**Optimum**-Max.	Min.-**Optimum**-Max.
–Ø 16,0	v_c	60–**100**–120	70–**100**–120	40–**60**–90	50–**60**–80	50–**70**–90	50–**60**–80	200–**240**–260
	f	0,15–**0,20**–0,35	0,15–**0,20**–0,30	0,10–**0,15**–0,20	0,10–**0,15**–0,20	0,20–**0,25**–0,30	0,20–**0,25**–0,30	0,35–**0,45**–0,55
–Ø 20,0	v_c	80–**100**–120	70–**100**–120	40–**60**–90	60–**70**–90	60–**80**–100	50–**70**–90	200–**240**–260
	f	0,15–**0,25**–0,35	0,15–**0,25**–0,35	0,15–**0,20**–0,25	0,15–**0,20**–0,25	0,20–**0,30**–0,35	0,20–**0,25**–0,35	0,35–**0,50**–0,60
–Ø 30,8	v_c	80–**100**–120	70–**100**–120	40–**60**–90	60–**70**–90	60–**80**–100	50–**70**–90	200–**240**–260
	f	0,20–**0,30**–0,35	0,20–**0,25**–0,35	0,15–**0,20**–0,25	0,15–**0,20**–0,25	0,20–**0,30**–0,40	0,25–**0,30**–0,35	0,35–**0,50**–0,60

Note: The recommended hole depth is 2 x DC. The depth is measured from the highest point of the hole when drilling on inclined surfaces. The recommended cutting conditions above are for drilling on flat horizontal surfaces.
Adjust the feed rate according to the inclination angle when drilling on an inclined surface. Set the feed rate at 70 % ot lower when inclination angle is 30° or less. Set the feed rate at 50 % or lower when the inclination angle is larger than 30°. This product is a drilling tool. Do not use it for traverse or helical milling.

(*) Inquire about drills specifically for aluminum alloy.

SMD Type

Large Hole MTL Type

For Large Holes

Tool edge design ideal for malleable material used for large casings, etc.
Edge design suitable for malleable material commonly used for large hole drilling.



Improved chip management
for highly malleable materials
Large Helix Angle Design



Machined Surface Accuracy

Work Material: St 52-3 (Base substrate for construction use)
Drill Size: Ø 33,0 mm x 5D
Cutting Conditions: v_c = 120 m/min, f = 0,25 mm/rev
Cutting Environment: Emulsion Type

High drilling accuracy with large diameters



Cutting Force Comparison (Thrust)

Work Material: St 42-2 (Laminated plates)
Drill Size: Ø 37,5 mm x 5D
Cutting Conditions: v_c = 90 m/min, f = 0,35 mm/rev
Cutting Environment: Emulsion Type

Stable even when machining laminated plates



Recommended Cutting Conditions

v_C=Cutting Speed (m/min) f=Feed Rate (mm/rev)

Work Material		Soft Steel (–250 HB)	General Steel (250–320 HB)	Hardened Steel (45 HRC)	Stainless Steel (–200 HB)	Grey Cast Iron	Ductil Cast Iron
Recommended Head		**MTL** Type	**MTL** Type	**MTL** Type	**MTL** Type	**MTL** Type	**MTL** Type
Drill Ø (mm)	Cutt. Conditions						
–36,5	v_c	**60–120** (40–80)	**60–120** (40–80)	**40–80** (30–60)	**40–80** (30–60)	**50–100** (40–90)	**50–90** (40–70)
	f	0,25–0,4	0,2–0,35	0,15– 0,3	0,15–0,25	0,25–0,45	0,25–0,35
–42,5	v_c	**60–120** (40–80)	**60–120** (40–80)	**40–80** (30–60)	**40–80** (30–60)	**50–100** (40–90)	**50–90** (40–70)
	f	0,25–0,4	0,2–0,35	0,15–0,3	0,15–0,25	0,25–0,45	0,25–0,35

Note: Where machining and work clamp rigidity are good, conditions may be increased up to the maximum.
For 8D drills, please use feed rates stated within the ( ). Before drilling 8D holes, a guide hole of similar diameter must be made.

○ = Japan stock
❑ = Delivery on request

Regrindable Drill Head Insert
SMDT... MTL Type

● Indexable Head MTL Type



● Toolholder



■ Drill Head (Ø 31,0–42,5 mm), Grade MTL Type - ACX80

■ Holders M (3D), L (5D), D (8D)

Drill Diameter ØD	Heads			Toolholder					
	MTL Type		h1	M (3D)		L (5D)		D (8D)	
	Cat. No.	Stock		Cat. No.	Stock	Cat. No.	Stock	Cat. No.	Stock
31,0	**SMDT 3100 MTL**	❍	15,2	**SMDH 320 M**	❍	**SMDH 320 L**	❍	**SMDH 320 D**	❍
31,5	**SMDT 3150 MTL**	❒							
32,0	**SMDT 3200 MTL**	❍							
32,5	**SMDT 3250 MTL**	❒	15,2	**SMDH 335 M**	❍	**SMDH 335 L**	❍	**SMDH 335 D**	❍
33,0	**SMDT 3300 MTL**	❍							
33,5	**SMDT 3350 MTL**	❒							
34,0	**SMDT 3400 MTL**	❍	16,6	**SMDH 350 M**	❍	**SMDH 350 L**	❍	**SMDH 350 D**	❍
34,5	**SMDT 3450 MTL**	❒							
35,0	**SMDT 3500 MTL**	❍							
35,5	**SMDT 3550 MTL**	❒	16,4	**SMDH 365 M**	❍	**SMDH 365 L**	❍	**SMDH 365 D**	❍
36,0	**SMDT 3600 MTL**	❍							
36,5	**SMDT 3650 MTL**	❒							
37,0	**SMDT 3700 MTL**	❍	18,1	**SMDH 380 M**	❍	**SMDH 380 L**	❍	**SMDH 380 D**	❍
37,5	**SMDT 3750 MTL**	❍							
38,0	**SMDT 3800 MTL**	❍							
38,5	**SMDT 3850 MTL**	❒	17,8	**SMDH 395 M**	❍	**SMDH 395 L**	❍	**SMDH 395 D**	❍
39,0	**SMDT 3900 MTL**	❍							
39,5	**SMDT 3950 MTL**	❒							
40,0	**SMDT 4000 MTL**	❍	19,5	**SMDH 410 M**	❍	**SMDH 410 L**	❍	**SMDH 410 D**	❍
40,5	**SMDT 4050 MTL**	❍							
41,0	**SMDT 4100 MTL**	❍							
41,5	**SMDT 4150 MTL**	❒	19,3	**SMDH 425 M**	❍	**SMDH 425 L**	❍	**SMDH 425 D**	❍
42,0	**SMDT 4200 MTL**	❍							
42,5	**SMDT 4250 MTL**	❒							

● Mounted Figure



Only use the special MTL Type head with a M, L or D type holder

Dimensions (mm)		M (3D)		L (5D)		D (8D)		Shank		Cap Screw	Wrench	N·m
Drill Head		Dimensions (mm)		Dimensions (mm)		Dimensions (mm)		Dimensions (mm)				
øD	ℓ_1	ℓ_2	L	ℓ_2	L	ℓ_2	L	ℓ_3	ød			
31,0												
31,5	5,7	97,9	200,7	163	265,7	257,9	360,7	60	32,0	BXD04515IP	TRDR25IP	5–6,6
32,0												
32,5												
33,0	6,0	103,3	206,0	171,5	276,0	273,3	376,0	60	32,0			
33,5												
34,0												
34,5	6,3	106,8	221,3	182	296,3	287	401,3	70	40,0			
35,0												
35,5												
36,0	6,6	112,3	226,6	187,5	301,6	297,3	411,6	70	40,0			
36,5												
37,0												
37,5	6,8	115,8	231,8	195,8	311,8	310,8	426,8	70	40,0			
38,0												
38,5												
39,0	7,1	121,3	237,1	206,3	322,1	321,3	437,1	70	40,0			
39,5												
40,0												
40,5	7,4	129,8	252,4	209,8	332,4	334,8	457,4	70	40,0			
41,0												
41,5												
42,0	7,6	135,3	257,6	220,3	342,6	345,3	467,6	70	40,0			
42,5												

BX0515 | HD040 | 7,2

WDX Type

ECONOMICAL - FAST - ACCURATE - RIGID

High Feed Drilling - 4 Edge Inserts

General Features

The newly designed WDX drill features indexable inserts with 4 cutting edges and a range of optimised chipbreakers;
light (L) - general purpose (G) - heavy (H) for rapid chip removal.

The balanced cut design maximises feed rates and accuracy whilst the super ZX ultra hard coated inserts double the tool life.

Advantages

● Rigid - Economical - Multi-function

Drills - Bores - External Turns
Diameter range 13,0–55,0 mm
Drilling depth –2D, –3D, –4D, –5D

● Excellent chip control

Wide application suitability - choose from 3 styles of chipbreaker

L Type
- Excellent chip control under low feed rate conditions
- Excellent hole accuracy
- Excellent surface finish

G Type
- General purpose chipbreaker
- Excellent chip control
- Low cutting force
- Low / medium feed rates



H Type
- Strong cutting edge at higher feed rates
- Stable machining – eliminates vibration and noise

● One insert style for both pockets

4 Edge insert provides both Inner and Outer cutting edges
Newly designed insert style simplifies insert management.

● Ultra hard Super ZX inserts double tool life

ACP300 for steels - stainless steels - difficult to cut materials
ACK300 for cast irons

● Excellent hole accuracy

Improved cutting force balance and insert design for optimum performance



Features of Super ZX Coating

- Super-multi layered coating with ultra-thin (nanometer) layers of TiAlN and AlCrN, alternately stacked up to 1.000 layers.
- 40 % increase in coating hardness and 200 % increase in oxidation temperature as compared with conventional grades

● Oxidation Temperature



● Coating Structure



"AURORA" Coating DLC (Diamond Like Carbon)

Coated Grade **DL1500** for Aluminium

G Type

● Super smooth surface and low coefficient of friction

Achieving beautiful finishing on Aluminium and non-ferrous metalls with its high resistance to build-up edge.

Peripheral Insert	
DL1500	ACK300
	

Central Insert	
DL1500	ACK300
	

● = Euro stock
○ = Japan stock

Recommended Tightening Torque (N·m)

WDX Type (2D)

Max. Depth: 2 D

Fig. 1



Fig. 2



Fig. 3



Holder

DC (mm)	Cat. No.	Stock	Dimensions (mm) OAL	LUX	LPR	DCON	DCSFMS	LS	Applicable Insert	Fig.
13,0	WDX 130D2S20	●	88	29	44					
13,5	WDX 135D2S20	●	89	30	45					
14,0	WDX 140D2S20	●	90	31	46	20	28	44	WDXT 042004	
14,5	WDX 145D2S20	●	91	32	47					
15,0	WDX 150D2S20	●	92	33	48					
15,5	WDX 155D2S20	●	93	34	49					
16,0	WDX 160D2S20	●	94	35	50	20	30	44		
16,5	WDX 165D2S20	●	95	36	51				WDXT 052504	
17,0	WDX 170D2S20	●	96	37	52					
17,5	WDX 175D2S25	●	109	38	53	25	32	56		
18,0	WDX 180D2S25	●	110	39	54					
18,5	WDX 185D2S25	●	111	40	55					
19,0	WDX 190D2S25	●	112	41	56					
19,5	WDX 195D2S25	●	113	42	57					
20,0	WDX 200D2S25	●	114	43	58					
20,5	WDX 205D2S25	●	115	44	59	25	33	56	WDXT 063006	1
21,0	WDX 210D2S25	●	116	45	60					
21,5	WDX 215D2S25	●	117	46	61					
22,0	WDX 220D2S25	●	118	47	62					
22,5	WDX 225D2S25	●	119	48	63					
23,0	WDX 230D2S25	●	123	49	67					
23,5	WDX 235D2S25	●	124	50	68					
24,0	WDX 240D2S25	●	125	51	69	25	37	56		
24,5	WDX 245D2S25	●	126	52	70					
25,0	WDX 250D2S25	●	127	53	71					
25,5	WDX 255D2S32	●	134	54	74				WDXT 073506	
26,0	WDX 260D2S32	●	135	55	75					
26,5	WDX 265D2S32	●	136	56	76					
27,0	WDX 270D2S32	●	137	57	77	32	41	60		
27,5	WDX 275D2S32	●	138	58	78					
28,0	WDX 280D2S32	●	139	59	79					
28,5	WDX 285D2S32	●	140	60	80					
29,0	WDX 290D2S32	●	143	62	83	32	50	60		
29,5	WDX 295D2S32	●	144	63	84					
30,0	WDX 300D2S40	●	158	64	88					
31,0	WDX 310D2S40	●	160	66	90					
32,0	WDX 320D2S40	●	162	68	92					
33,0	WDX 330D2S40	●	164	70	94	40	54	70	WDXT 094008	
34,0	WDX 340D2S40	●	166	72	96					
35,0	WDX 350D2S40	●	168	74	98					
36,0	WDX 360D2S40	●	170	76	100					2
37,0	WDX 370D2S40	●	179	79	109					
38,0	WDX 380D2S40	●	181	81	111					
39,0	WDX 390D2S40	●	183	83	113					
40,0	WDX 400D2S40	●	185	85	115					
41,0	WDX 410D2S40	●	187	87	117	40	49,5	70	WDXT 125012	
42,0	WDX 420D2S40	●	189	89	119					
43,0	WDX 430D2S40	●	191	91	121					
44,0	WDX 440D2S40	●	193	93	123					
45,0	WDX 450D2S40	●	195	95	125					
46,0	WDX 460D2S40	●	197	97	127					
47,0	WDX 470D2S40	●	199	99	129					
48,0	WDX 480D2S40	●	201	101	131		49,5			
49,0	WDX 490D2S40	●	203	103	133					
50,0	WDX 500D2S40	●	205	105	135	40		70	WDXT 156012	
51,0	WDX 510D2S40	●	207	107	137		50,5			
52,0	WDX 520D2S40	●	209	109	139		51,5			
53,0	WDX 530D2S40	●	211	111	141		52,5			
54,0	WDX 540D2S40	●	213	113	143		53,5			
55,0	WDX 550D2S40	●	215	115	145					
56,0	WDX 560D2S40	❍	222	120	152		54			3
57,0	WDX 570D2S40	❍	224	122	154		55			
58,0	WDX 580D2S40	❍	226	124	156		56			
59,0	WDX 590D2S40	❍	228	126	158		57			
60,0	WDX 600D2S40	❍	230	128	160	40	58	70	WDXT 186012	
61,0	WDX 610D2S40	❍	232	130	162		59			
62,0	WDX 620D2S40	❍	234	132	164		60			
63,0	WDX 630D2S40	❍	236	134	166		61			
64,0	WDX 640D2S40	❍	238	136	168		62			
65,0	WDX 650D2S40	❍	240	138	170		63			

Inserts

(mm)

Fig. 4



L Type
Excellent chip control at low feed rates

Fig. 5



G Type
General purpose chipbreaker

Fig. 6



H Type
Strong cutting edge at higher feed rates

Cat. No.	Coated ACP100	ACP300	ACK300	DL1500	Fig.	Dimensions (mm) W1	Thickness	RE	Applicable Holder
WDXT 042004-L	❍	●	●		4				
WDXT 042004-G	●	●	●	●	5	4,2	2,0	0,4	WDX 130 ~ 150
WDXT 042004-H	❍	●	●		6				
WDXT 052504-L	❍	●	●		4				
WDXT 052504-G	●	●	●	●	5	5,0	2,5	0,4	WDX 155 ~ 180
WDXT 052504-H	❍	●	●		6				
WDXT 063006-L	●	●	●		4				
WDXT 063006-G	●	●	●	●	5	6,0	3,0	0,6	WDX 185 ~ 225
WDXT 063006-H	❍	●	●		6				
WDXT 073506-L	●	●	●		4				
WDXT 073506-G	●	●	●	●	5	7,5	3,5	0,6	WDX 230 ~ 285
WDXT 073506-H	●	●	●		6				
WDXT 094008-L	●	●	●		4				
WDXT 094008-G	●	●	●	●	5	9,6	4,0	0,8	WDX 290 ~ 360
WDXT 094008-H	●	●	●		6				
WDXT 125012-L	●	●	●		4				
WDXT 125012-G	●	●	●	●	5	12,4	5,0	1,2	WDX 370 ~ 450
WDXT 125012-H	●	●	●		6				
WDXT 156012-L	●	●	●		4				
WDXT 156012-G	●	●	●	●	5	15,2	6,0	1,2	WDX 460 ~ 550
WDXT 156012-H	●	●	●		6				
WDXT 186012-G	●	●	●		5	18,0	6,0	1,2	WDX 560 ~ 650

Spare Parts

Screw	Wrench	Wrench	Applicable Holders	N·m
BFTX 01604 N	TRX 06	–	WDX 130D_S20 – 150D_S20	0,3
BFTX 0204 N	TRX 06	–	WDX 155D_S20 – 180D_S25	0,5
BFTX 02206	–	TRX 07	WDX 185D_S25 – 225D_S25	1,0
BFTX 02506 N	–	TRX 08	WDX 230D_S25 – 285D_S32	1,5
BFTX 03584	–	TRX 15	WDX 290D_S32 – 360D_S40	3,5
BFTX 0511 N	–	TRX 20	WDX 370D_S40 – 450D_S40	5,0
BFTX 0615 N	–	TRX 25	WDX 460D_S40 – 550D_S40	7,5

Identification of Drill Body

WDX 200 D2 S25

- 200: Drill Diameter (Ø 20,0 mm)
- D2: Flute Length L/D (2 x D)
- S25: Shank Size (Ø 25,0 mm)

Identification of Indexable Insert

WDXT 06 30 06 -G

- 06: Width Across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Corner Radius (0,6 mm)
- -G: Breaker Type

WDX Type (3D)



Max. Depth: 3 D

Fig. 1



Fig. 2



Fig. 3



Holder

DC (mm)	Cat. No.	Stock	Dimensions (mm) OAL	LUX	LPR	DCON	DCSFMS	LS	Applicable Insert	Fig.
13,0	WDX 130D3S20	●	101,0	42,0	57,0					
13,5	WDX 135D3S20	●	102,5	43,5	58,5					
14,0	WDX 140D3S20	●	104,0	45,0	60,0	20	28	44	WDXT 042004	
14,5	WDX 145D3S20	●	105,5	46,5	61,5					
15,0	WDX 150D3S20	●	107,0	58,0	63,0					
15,5	WDX 155D3S20	●	108,5	49,5	64,5					
16,0	WDX 160D3S20	●	110,0	51,0	66,0	20	30	44		
16,5	WDX 165D3S20	●	111,5	52,5	67,5				WDXT 052504	
17,0	WDX 170D3S20	●	113,0	54,0	69,0					
17,5	WDX 175D3S25	●	126,5	55,5	70,5	25	32	56		
18,0	WDX 180D3S25	●	128,0	57,0	72,0					
18,5	WDX 185D3S25	●	129,5	58,5	73,5					
19,0	WDX 190D3S25	●	131,0	60,0	75,0					
19,5	WDX 195D3S25	●	132,5	61,5	76,5					
20,0	WDX 200D3S25	●	134,0	63,0	78,0					
20,5	WDX 205D3S25	●	135,5	64,5	79,5	25	33	56	WDXT 063006	1
21,0	WDX 210D3S25	●	137,0	66,0	81,0					
21,5	WDX 215D3S25	●	138,5	67,5	82,5					
22,0	WDX 220D3S25	●	140,0	69,0	84,0					
22,5	WDX 225D3S25	●	141,5	70,5	85,5					
23,0	WDX 230D3S25	●	146,0	72,0	90,0					
23,5	WDX 235D3S25	●	147,5	73,5	91,5					
24,0	WDX 240D3S25	●	149,0	75,0	93,0	25	37	56		
24,5	WDX 245D3S25	●	150,5	76,5	94,5					
25,0	WDX 250D3S25	●	152,0	78,0	96,0					
25,5	WDX 255D3S32	●	159,5	79,5	97,5					
26,0	WDX 260D3S32	●	161,0	81,0	101,0					
26,5	WDX 265D3S32	●	162,5	82,5	102,5					
27,0	WDX 270D3S32	●	164,0	84,0	104,0	32	41	60	WDXT 073506	
27,5	WDX 275D3S32	●	165,5	85,5	105,5					
28,0	WDX 280D3S32	●	167,0	87,0	107,0					
28,5	WDX 285D3S32	●	168,5	88,5	108,5					
29,0	WDX 290D3S32	●	172,0	91,0	112,0	32	50	60		
29,5	WDX 295D3S32	●	173,5	92,5	113,5					
30,0	WDX 300D3S40	●	188,0	94,0	118,0					
31,0	WDX 310D3S40	●	191,0	97,0	121,0					
32,0	WDX 320D3S40	●	194,0	100,0	124,0					
33,0	WDX 330D3S40	●	197,0	103,0	127,0	40	54	70	WDXT 094008	
34,0	WDX 340D3S40	●	200,0	106,0	130,0					
35,0	WDX 350D3S40	●	203,0	109,0	133,0					
36,0	WDX 360D3S40	●	206,0	112,0	136,0					2
37,0	WDX 370D3S40	●	216,0	116,0	146,0					
38,0	WDX 380D3S40	●	219,0	119,0	149,0					
39,0	WDX 390D3S40	●	222,0	122,0	152,0					
40,0	WDX 400D3S40	●	225,0	125,0	155,0					
41,0	WDX 410D3S40	●	228,0	128,0	158,0	40	49,5	70	WDXT 125012	
42,0	WDX 420D3S40	●	231,0	131,0	161,0					
43,0	WDX 430D3S40	●	234,0	134,0	164,0					
44,0	WDX 440D3S40	●	237,0	137,0	167,0					
45,0	WDX 450D3S40	●	240,0	140,0	170,0					
46,0	WDX 460D3S40	●	243,0	143,0	173,0					
47,0	WDX 470D3S40	●	246,0	146,0	176,0					
48,0	WDX 480D3S40	●	249,0	149,0	179,0		49,5			
49,0	WDX 490D3S40	●	252,0	152,0	182,0					
50,0	WDX 500D3S40	●	255,0	155,0	185,0					
51,0	WDX 510D3S40	●	258,0	158,0	188,0	40		70	WDXT 156012	
52,0	WDX 520D3S40	●	261,0	161,0	191,0		50,5			
53,0	WDX 530D3S40	●	264,0	164,0	194,0		51,5			
54,0	WDX 540D3S40	●	267,0	167,0	197,0		52,5			
55,0	WDX 550D3S40	●	270,0	170,0	200,0		53,5			
56,0	WDX 560D3S40	○	278,0	176,0	208,0		54			
57,0	WDX 570D3S40	○	281,0	179,0	211,0		55			
58,0	WDX 580D3S40	○	284,0	182,0	214,0		56			3
59,0	WDX 590D3S40	○	287,0	185,0	217,0		57			
60,0	WDX 600D3S40	○	290,0	188,0	220,0	40	58	70	WDXT 186012	
61,0	WDX 610D3S40	○	293,0	191,0	223,0		59			
62,0	WDX 620D3S40	○	296,0	194,0	226,0		60			
63,0	WDX 630D3S40	○	299,0	197,0	229,0		61			
64,0	WDX 640D3S40	○	302,0	200,0	232,0		62			
65,0	WDX 650D3S40	○	305,0	203,0	235,0		63			

Inserts

(mm)

Fig. 4



L Type
Excellent chip control at low feed rates

Fig. 5



G Type
General purpose chipbreaker

Fig. 6



H Type
Strong cutting edge at higher feed rates

Cat. No.	Coated ACP100	ACP300	ACK300	DL1500	Fig.	Dimensions (mm) W1	Thickness	RE	Applicable Holder
WDXT 042004-L	○	●	●		4				
WDXT 042004-G	●	●	●	●	5	4,2	2,0	0,4	WDX 130 ~ 150
WDXT 042004-H	○	●	●		6				
WDXT 052504-L	○	●	●		4				
WDXT 052504-G	●	●	●	●	5	5,0	2,5	0,4	WDX 155 ~ 180
WDXT 052504-H	○	●	●		6				
WDXT 063006-L	●	●	●		4				
WDXT 063006-G	●	●	●	●	5	6,0	3,0	0,6	WDX 185 ~ 225
WDXT 063006-H	○	●	●		6				
WDXT 073506-L	●	●	●		4				
WDXT 073506-G	●	●	●	●	5	7,5	3,5	0,6	WDX 230 ~ 285
WDXT 073506-H	●	●	●		6				
WDXT 094008-L	●	●	●		4				
WDXT 094008-G	●	●	●	●	5	9,6	4,0	0,8	WDX 290 ~ 360
WDXT 094008-H	●	●	●		6				
WDXT 125012-L	●	●	●		4				
WDXT 125012-G	●	●	●	●	5	12,4	5,0	1,2	WDX 370 ~ 450
WDXT 125012-H	●	●	●		6				
WDXT 156012-L	●	●	●		4				
WDXT 156012-G	●	●	●	●	5	15,2	6,0	1,2	WDX 460 ~ 550
WDXT 156012-H	●	●	●		6				
WDXT 186012-G	●	●	●		5	18,0	6,0	1,2	WDX 560 ~ 650

Spare Parts

Screw	Wrench	Wrench	Applicable Holders	N·m
				
BFTX 01604 N	TRX 06	–	WDX 130D_S20 – 150D_S20	0,3
BFTX 0204 N	TRX 06	–	WDX 155D_S20 – 180D_S25	0,5
BFTX 02206	–	TRX 07	WDX 185D_S25 – 225D_S25	1,0
BFTX 02506 N	–	TRX 08	WDX 230D_S25 – 285D_S32	1,5
BFTX 03584	–	TRX 15	WDX 290D_S32 – 360D_S40	3,5
BFTX 0511 N	–	TRX 20	WDX 370D_S40 – 450D_S40	5,0
BFTX 0615 N	–	TRX 25	WDX 460D_S40 – 550D_S40	7,5

Identification of Drill Body

WDX 200 D3 S25

- 200: Drill Diameter (Ø 20,0 mm)
- D3: Flute Length L/D (3 x D)
- S25: Shank Size (Ø 25,0 mm)

Identification of Indexable Insert

WDXT 06 30 06 -G

- 06: Width Across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Corner Radius (0,6 mm)
- -G: Breaker Type

N·m Recommended Tightening Torque (N·m)

● = Euro stock
○ = Japan stock

WDX Type (4D)

Max. Depth: 4 D

Fig. 1



Fig. 2



Fig. 3



Holder

DC (mm)	Cat. No.	Stock	Dimensions (mm) OAL	LUX	LPR	DCON	DCSFMS	LS	Applicable Insert	Fig.
13,0	WDX 130D4S20	●	114	55	70					
13,5	WDX 135D4S20	●	116	57	72					
14,0	WDX 140D4S20	●	118	59	74	20	28	44	WDXT 042004	
14,5	WDX 145D4S20	●	120	61	76					
15,0	WDX 150D4S20	●	122	63	78					
15,5	WDX 155D4S20	●	124	65	80					
16,0	WDX 160D4S20	●	126	67	82	20	30	44		
16,5	WDX 165D4S20	●	128	69	84				WDXT 052504	
17,0	WDX 170D4S20	●	130	71	86					
17,5	WDX 175D4S25	●	144	73	88	25	32	56		
18,0	WDX 180D4S25	●	146	75	90					
18,5	WDX 185D4S25	●	148	77	92					
19,0	WDX 190D4S25	●	150	79	94					
19,5	WDX 195D4S25	●	152	81	96					
20,0	WDX 200D4S25	●	154	83	98					
20,5	WDX 205D4S25	●	156	85	100	25	33	56	WDXT 063006	1
21,0	WDX 210D4S25	●	158	87	102					
21,5	WDX 215D4S25	●	160	89	104					
22,0	WDX 220D4S25	●	162	91	106					
22,5	WDX 225D4S25	●	164	93	108					
23,0	WDX 230D4S25	●	169	95	113					
23,5	WDX 235D4S25	●	171	97	115					
24,0	WDX 240D4S25	●	173	99	117	25	37	56		
24,5	WDX 245D4S25	●	175	101	119					
25,0	WDX 250D4S25	●	177	103	121					
25,5	WDX 255D4S32	●	185	105	125				WDXT 073506	
26,0	WDX 260D4S32	●	187	107	127					
26,5	WDX 265D4S32	●	189	109	129					
27,0	WDX 270D4S32	●	191	111	131	32	41	60		
27,5	WDX 275D4S32	●	193	113	133					
28,0	WDX 280D4S32	●	195	115	135					
28,5	WDX 285D4S32	●	197	117	137					
29,0	WDX 290D4S32	●	201	120	141	32	50	60		
29,5	WDX 295D4S32	●	203	122	143					
30,0	WDX 300D4S40	●	218	124	148					
31,0	WDX 310D4S40	●	222	128	152					
32,0	WDX 320D4S40	●	226	132	156					
33,0	WDX 330D4S40	●	230	136	160	40	54	70	WDXT 094008	
34,0	WDX 340D4S40	●	234	140	164					
35,0	WDX 350D4S40	●	238	144	168					
36,0	WDX 360D4S40	●	242	148	172					2
37,0	WDX 370D4S40	●	253	153	183					
38,0	WDX 380D4S40	●	257	157	187					
39,0	WDX 390D4S40	●	261	161	191					
40,0	WDX 400D4S40	●	265	165	195					
41,0	WDX 410D4S40	●	269	169	199	40	49,5	70	WDXT 125012	
42,0	WDX 420D4S40	●	273	173	203					
43,0	WDX 430D4S40	●	277	177	207					
44,0	WDX 440D4S40	●	281	181	211					
45,0	WDX 450D4S40	●	285	185	215					
46,0	WDX 460D4S40	●	289	189	219					
47,0	WDX 470D4S40	●	293	193	223					
48,0	WDX 480D4S40	●	297	197	227					
49,0	WDX 490D4S40	●	301	201	231		49,5			
50,0	WDX 500D4S40	●	305	205	235	40		70	WDXT 156012	
51,0	WDX 510D4S40	●	309	209	239					
52,0	WDX 520D4S40	●	313	213	243		50,5			
53,0	WDX 530D4S40	●	317	217	247		51,5			
54,0	WDX 540D4S40	●	321	221	251		52,5			
55,0	WDX 550D4S40	●	325	225	255		53,5			3
56,0	WDX 560D4S40	❍	334	232	264		54			
57,0	WDX 570D4S40	❍	338	236	268		55			
58,0	WDX 580D4S40	❍	342	240	272	40	56	70	WDXT 186012	
59,0	WDX 590D4S40	❍	346	244	276		57			
60,0	WDX 600D4S40	❍	350	248	280		58			

Inserts

(mm)

Fig. 4



L Type
Excellent chip control at low feed rates

Fig. 5



G Type
General purpose chipbreaker

Fig. 6



H Type
Strong cutting edge at higher feed rates

Cat. No.	Coated ACP100	ACP300	ACK300	DL1500	Fig.	Dimensions (mm) W1	Thickness	RE	Applicable Holder
WDXT 042004-L	❍	●	●		4				
WDXT 042004-G	●	●	●	●	5	4,2	2,0	0,4	WDX 130 ~ 150
WDXT 042004-H	❍	●	●		6				
WDXT 052504-L	❍	●	●		4				
WDXT 052504-G	●	●	●	●	5	5,0	2,5	0,4	WDX 155 ~ 180
WDXT 052504-H	❍	●	●		6				
WDXT 063006-L	●	●	●		4				
WDXT 063006-G	●	●	●	●	5	6,0	3,0	0,6	WDX 185 ~ 225
WDXT 063006-H	❍	●	●		6				
WDXT 073506-L	●	●	●		4				
WDXT 073506-G	●	●	●	●	5	7,5	3,5	0,6	WDX 230 ~ 285
WDXT 073506-H	●	●	●		6				
WDXT 094008-L	●	●	●		4				
WDXT 094008-G	●	●	●	●	5	9,6	4,0	0,8	WDX 290 ~ 360
WDXT 094008-H	●	●	●		6				
WDXT 125012-L	●	●	●		4				
WDXT 125012-G	●	●	●	●	5	12,4	5,0	1,2	WDX 370 ~ 450
WDXT 125012-H	●	●	●		6				
WDXT 156012-L	●	●	●		4				
WDXT 156012-G	●	●	●	●	5	15,2	6,0	1,2	WDX 460 ~ 550
WDXT 156012-H	●	●	●		6				
WDXT 186012-G	●	●	●		5	18,0	6,0	1,2	WDX 560 ~ 650

Spare Parts

Screw	Wrench	Wrench	Applicable Holders	N·m
BFTX 01604 N	TRX 06	–	WDX 130D_S20 – 150D_S20	0,3
BFTX 0204 N	TRX 06	–	WDX 155D_S20 – 180D_S25	0,5
BFTX 02206	–	TRX 07	WDX 185D_S25 – 225D_S25	1,0
BFTX 02506 N	–	TRX 08	WDX 230D_S25 – 285D_S32	1,5
BFTX 03584	–	TRX 15	WDX 290D_S32 – 360D_S40	3,5
BFTX 0511 N	–	TRX 20	WDX 370D_S40 – 450D_S40	5,0
BFTX 0615 N	–	TRX 25	WDX 460D_S40 – 550D_S40	7,5

Identification of Drill Body

WDX 200 D4 S25

- 200: Drill Diameter (Ø 20,0 mm)
- D4: Flute Length L/D (4 x D)
- S25: Shank Size (Ø 25,0 mm)

Identification of Indexable Insert

WDXT 06 30 06 -G

- 06: Width Across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Corner Radius (0,6 mm)
- -G: Breaker Type

WDX Type (5D)

Max. Depth: 5 D



Holder

DC (mm)	Cat. No.	Stock	Dimensions (mm) OAL	LUX	LPR	DCON	DCSFMS	LS	Applicable Insert	Fig.
13,0	WDX 130D5S20	●	127,0	68,0	83,0					
13,5	WDX 135D5S20	●	129,5	70,5	85,5					
14,0	WDX 140D5S20	●	132,0	73,0	88,0	20	28	44	WDXT 042004	
14,5	WDX 145D5S20	●	134,5	75,5	90,5					
15,0	WDX 150D5S20	●	137,0	78,0	93,0					
15,5	WDX 155D5S20	●	139,5	80,5	95,5					
16,0	WDX 160D5S20	●	142,0	83,0	98,0	20	30	44	WDXT 052504	
16,5	WDX 165D5S20	●	144,5	85,5	100,5					
17,0	WDX 170D5S20	●	147,0	88,0	103,0					
17,5	WDX 175D5S20	●	161,5	90,5	105,5	25	32	56		
18,0	WDX 180D5S25	●	164,0	93,0	108,0					
18,5	WDX 185D5S25	●	166,5	95,5	110,5					
19,0	WDX 190D5S25	●	169,0	98,0	113,0					
19,5	WDX 195D5S25	●	171,5	100,5	115,5					
20,0	WDX 200D5S25	●	174,0	103,0	118,0					
20,5	WDX 205D5S25	●	176,5	105,5	120,5	25	33	56	WDXT 063006	1
21,0	WDX 210D5S25	●	179,0	108,0	123,0					
21,5	WDX 215D5S25	●	181,5	110,5	125,5					
22,0	WDX 220D5S25	●	184,0	113,0	128,0					
22,5	WDX 225D5S25	●	186,5	115,5	130,5					
23,0	WDX 230D5S25	●	192,0	118,0	136,0					
23,5	WDX 235D5S25	●	194,5	120,5	138,5					
24,0	WDX 240D5S25	●	197,0	123,0	141,0	25	37	56	WDXT 073506	
24,5	WDX 245D5S25	●	199,5	125,5	143,5					
25,0	WDX 250D5S25	●	202,0	128,0	146,0					
26,0	WDX 260D5S32	●	213,0	133,0	153,0					
27,0	WDX 270D5S32	●	218,0	138,0	158,0	32	41	60		
28,0	WDX 280D5S32	●	223,0	143,0	163,0					
29,0	WDX 290D5S32	●	230,0	149,0	170,0	32	50	60		
30,0	WDX 300D5S40	●	248,0	154,0	178,0					
31,0	WDX 310D5S40	●	253,0	159,0	183,0					
32,0	WDX 320D5S40	●	258,0	164,0	188,0					
33,0	WDX 330D5S40	●	263,0	169,0	193,0	40	54	70	WDXT 094008	2
34,0	WDX 340D5S40	●	268,0	174,0	198,0					
35,0	WDX 350D5S40	●	273,0	179,0	203,0					
36,0	WDX 360D5S40	●	278,0	184,0	208,0					
37,0	WDX 370D5S40	❍	290,0	190,0	220,0					
38,0	WDX 380D5S40	❍	295,0	195,0	225,0					
39,0	WDX 390D5S40	❍	300,0	200,0	230,0					
40,0	WDX 400D5S40	❍	305,0	205,0	235,0					
41,0	WDX 410D5S40	❍	310,0	210,0	240,0	40	49,5	70	WDXT 125012	2
42,0	WDX 420D5S40	❍	315,0	215,0	245,0					
43,0	WDX 430D5S40	❍	320,0	220,0	250,0					
44,0	WDX 440D5S40	❍	325,0	225,0	255,0					
45,0	WDX 450D5S40	❍	330,0	230,0	260,0					
46,0	WDX 460D5S40	❍	335,0	235,0	265,0					
47,0	WDX 470D5S40	❍	340,0	240,0	270,0					
48,0	WDX 480D5S40	❍	345,0	245,0	275,0		49,5			2
49,0	WDX 490D5S40	❍	350,0	250,0	280,0					
50,0	WDX 500D5S40	❍	355,0	255,0	285,0	40		70	WDXT 156012	
51,0	WDX 510D5S40	❍	360,0	260,0	290,0					
52,0	WDX 520D5S40	❍	365,0	265,0	295,0		50,5			3
53,0	WDX 530D5S40	❍	370,0	270,0	300,0		51,5			
54,0	WDX 540D5S40	❍	375,0	275,0	305,0		52,5			
55,0	WDX 550D5S40	❍	380,0	280,0	310,0		53,5			

Inserts

(mm)

Fig. 4 / Fig. 5 / Fig. 6



L Type
Excellent chip control at low feed rates

G Type
General purpose chipbreaker

H Type
Strong cutting edge at higher feed rates

Cat. No.	Coated ACP100	ACP300	ACK300	DL1500	Fig.	Dimensions (mm) W1	Thickness	RE	Applicable Holder
WDXT 042004-L	❍	●	●		4				
WDXT 042004-G	●	●	●	●	5	4,2	2,0	0,4	WDX 130 ~ 150
WDXT 042004-H	❍	●	●		6				
WDXT 052504-L	❍	●	●		4				
WDXT 052504-G	●	●	●	●	5	5,0	2,5	0,4	WDX 155 ~ 180
WDXT 052504-H	❍	●	●		6				
WDXT 063006-L	●	●	●		4				
WDXT 063006-G	●	●	●	●	5	6,0	3,0	0,6	WDX 185 ~ 225
WDXT 063006-H	❍	●	●		6				
WDXT 073506-L	●	●	●		4				
WDXT 073506-G	●	●	●	●	5	7,5	3,5	0,6	WDX 230 ~ 285
WDXT 073506-H	●	●	●		6				
WDXT 094008-L	●	●	●		4				
WDXT 094008-G	●	●	●	●	5	9,6	4,0	0,8	WDX 290 ~ 360
WDXT 094008-H	●	●	●		6				
WDXT 125012-L	●	●	●		4				
WDXT 125012-G	●	●	●	●	5	12,4	5,0	1,2	WDX 370 ~ 450
WDXT 125012-H	●	●	●		6				
WDXT 156012-L	●	●	●		4				
WDXT 156012-G	●	●	●	●	5	15,2	6,0	1,2	WDX 460 ~ 550
WDXT 156012-H	●	●	●		6				

Spare Parts

Screw	Wrench	Wrench	Applicable Holders	N·m
BFTX 01604 N	TRX 06	–	WDX 130D_S20 – 150D_S20	0,3
BFTX 0204 N	TRX 06	–	WDX 155D_S20 – 180D_S25	0,5
BFTX 02206	–	TRX 07	WDX 185D_S25 – 225D_S25	1,0
BFTX 02506 N	–	TRX 08	WDX 230D_S25 – 285D_S32	1,5
BFTX 03584	–	TRX 15	WDX 290D_S32 – 360D_S40	3,5
BFTX 0511 N	–	TRX 20	WDX 370D_S40 – 450D_S40	5,0
BFTX 0615 N	–	TRX 25	WDX 460D_S40 – 550D_S40	7,5

Identification Details

Drill Body

WDX 200 D5 S25

- 200: Drill Diameter (Ø 20,0 mm)
- D5: Flute Length L/D (5 x D)
- S25: Shank Size (Ø 25,0 mm)

Indexable Insert

WDXT 06 30 06 -G

- 06: Width Across Flats (6,0 mm)
- 30: Thickness (3,0 mm)
- 06: Corner Radius (0,6 mm)
- -G: Breaker Type

● = Euro stock
○ = Japan stock

N·m Recommended Tightening Torque (N·m)

Indexable Insert Type "SumiDrill"
WDX Type

Multi-Purpose Functionality

Applications for machining centre



Recommended conditions - reduce feed rate to 70 %

Hole profile



Drill Diameter (mm)	a (mm)
Ø13,0–18,0	0,4
Ø18,5–28,5	0,6
Ø29,0–36,0	0,8
Ø37,0–55,0	1,2

Applications for Lathes

Setting Instruction

Ensure the face of the drill flange is hard against the face of the tool holder.
Align the centreline of the drill to the centreline of the lathes Y axis



Drilling Over Holes

Offset the lathes X axis within the maximum amount stated in the table

Drill description	Max. Offset (mm)	Drill description	Max. Offset (mm)
WDX130...	0,35	WDX280...	0,15
WDX135...	0,30	WDX285...	0,10
WDX140...	0,25	WDX290...	1,00
WDX145...	0,20	WDX295...	0,95
WDX150...	0,15	WDX300...	0,90
WDX155...	0,40	WDX310...	0,80
WDX160...	0,40	WDX320...	0,70
WDX165...	0,35	WDX330...	0,55
WDX170...	0,30	WDX340...	0,45
WDX175...	0,25	WDX350...	0,35
WDX180...	0,20	WDX360...	0,20
WDX185...	0,50	WDX370...	1,00
WDX190...	0,45	WDX380...	1,00
WDX195...	0,40	WDX390...	0,90
WDX200...	0,30	WDX400...	0,80
WDX205...	0,30	WDX410...	0,70
WDX210...	0,20	WDX420...	0,60
WDX215...	0,15	WDX430...	0,50
WDX220...	0,10	WDX440...	0,50
WDX225...	0,06	WDX450...	0,40
WDX230...	0,70	WDX460...	1,50
WDX235...	0,70	WDX470...	1,40
WDX240...	0,60	WDX480...	1,30
WDX245...	0,50	WDX490...	1,20
WDX250...	0,50	WDX500...	1,10
WDX255...	0,45	WDX510...	1,00
WDX260...	0,40	WDX520...	0,90
WDX265...	0,35	WDX530...	0,80
WDX270...	0,25	WDX540...	0,60
WDX275...	0,20	WDX550...	0,50

Recommended conditions - reduce feed rate to 30 %

Turning by lathes

Recommended conditions - reduce feed rate to 50 %

Eccentric Sleeve WAS Type

The Eccentric Sleeve WAS Type, exclusively designed for "SumiDrill" WDX Type, provides up to ± 0,3 mm of hole size adjustment.



■ Dimensions

(mm)

Cat. No.	Stock	DCB	DMM	BDX	LS	L2	L3	L4	Diameter Adjustment Range (max.)
WAS 2025-48	●	20	25	33	43	5	32	5	+0,3 – -0,2
WAS 2532-60	●	25	32	42	60	7	46	6	+0,3 – -0,3
WAS 3240-70	●	32	40	55	70	7	57	6	+0,3 – -0,3
WAS 4050-85	●	40	50	60	70	7	54	6	+0,3 – -0,3

■ Diameter Adjustment



Note 1: The dial is for reference purposes. Always measure the actual drilling diameter and adjust accordingly.
Note 2: Not usable with collet chuck type holders. Only use with a side-locking holder like Weldon.

● = Euro stock

■ Application Examples

"SumiDrill" WDX type


Normal wear


Good chip control

Competitor


Breakage


Long chips

Automotive Component (SUS304)
Drill Body: WDX220D2S25
Drill Insert: WDXT063006-L (ACP300)
Conditions: v_c = 125 m/min, f = 0,07 mm/rev, H = 5 mm, through, Wet

Insert breakage was eliminated with improved chip control and better surface finish.

"SumiDrill" WDX type


Good chip form

Competitor


Entangled chips

Structural Steel
Drill Body: WDX190D4S25
Drill Insert: WDXT063006-L (ACP300)
Conditions: v_c = 100 m/min, f = 0,06 mm/rev, H = 40 mm, through, Wet

Eliminated the problem of entangled chips.



Machine Component (SCM440)
Drill Body: WDX220D3S25
Drill Insert: WDXT063006-G (ACP300)
Conditions (Sumitomo): v_c= 157 m/min, f = 0,19 mm/rev, H= 19 mm, through, Wet
Conditions (Comp.): v_c= 157 m/min, f = 0,15 mm/rev, H= 19 mm, through, Wet

Good chip control even under high efficiency conditions.
Better stability through lower cutting force, resulting in 25 % higher efficiency and 20 % higher tool life.



Plate (S48C)
Drill Body: WDX600D3S40
Drill Insert: WDXT186012-G (ACP300)
Conditions (Sumitomo): v_c= 150 m/min, f = 0,16 mm/rev, H= 60 mm, through, Wet
Conditions (Comp.): v_c= 30 m/min, f = 0,20 mm/rev, H= 60 mm, through, Wet

Stable drilling performance.
4 times higher efficiency.



Automotive Component (SCM415)
Drill Body: WDX200D5S25
Drill Insert: WDXT063006-G (ACP300)
Conditions: v_c = 185 m/min, f = 0,12 mm/rev, H = 87 mm, through, Wet

Good surface roughness.
Stable hole diameter.

Bearing Component for Windmill (42CrMo)
Drill Body: WDX330D5S40
Drill Insert: WDXT094008-L (ACP300)
Conditions: v_c = 146 m/min, f = 0,10 mm/rev, H = 158 mm, through, Wet

WDX shows stable drilling performance, no cutting edge breakage.

Recommended Cutting Conditions (2D)

[min. - **optimal** - max.]

ISO	Work material	Hardness (HB)	Chip breaker & Grade		Cutting Speed Vc (m/min)	Feed rate (mm/rev) Ø 13,0–18,0	Ø 18,5–29,0	Ø 29,5–36,0	Ø 37,0–55,0	Ø 56,0–65,0
P	Carbon steel	125	L	ACP300	150–**220**–250	0,04–**0,08**–0,12	0,04–**0,08**–0,12	0,04–**0,08**–0,13	0,05–**0,10**–0,15	0,06– **0,11**–0,17
		190	G	ACP300	150–**220**–250	0,08–**0,13**–0,24	0,08–**0,13**–0,24	0,08–**0,14**–0,26	0,09–**0,16**–0,29	0,10–**0,17**–0,32
		250	G	ACP300	125–**170**–230	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22	0,08–**0,14**–0,24
		270	G	ACP300	125–**170**–230	0,08–**0,13**–0,22	0,08–**0,14**–0,24	0,08–**0,14**–0,23	0,09–**0,16**–0,26	0,10–**0,17**–0,29
		300	G	ACP300	100–**130**–170	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22
	Low alloyed steel	180	L	ACP300	150–**180**–220	0,05–**0,08**–0,14	0,05–**0,08**–0,14	0,05–**0,08**–0,16	0,06–**0,09**–0,17	0,07–**0,10**–0,19
		275	G	ACP300	125–**150**–200	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22
		300	G	ACP300	100–**140**–170	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22
		350	G	ACP300	80–**120**–150	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22
	High alloyed steel	200	G	ACP300	100–**150**–200	0,08–**0,13**–0,24	0,08–**0,13**–0,24	0,08–**0,14**–0,26	0,09–**0,16**–0,29	0,10–**0,17**–0,32
		325	G	ACP300	80–**120**–160	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22	0,08–**0,14**–0,24
M	Stainless steel, martensitic / ferritic	200	L/G	ACP300	100–**150**–200	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22	0,08–**0,14**–0,24
	Stainless steel, martensitic / tempered	240	L/G	ACP300	90–**120**–150	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22	0,08–**0,14**– 0,24
	Stainless steel, austenitic / quenched	180	L/G	ACP300	100–**150**–200	0,04–**0,08**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22	0,08–**0,14**–0,24
	Stainless steel, austenitic / ferritic (Duplex)	230	L/G	ACP300	80–**120**–150	0,04–**0,08**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22	0,08–**0,14**–0,24
K	Cast iron (GG)	180	H	ACK300	120–**160**–200	0,09–**0,20**–0,32	0,10–**0,22**–0,36	0,11–**0,24**–0,39	0,12–**0,26**–0,44	0,13–**0,29**–0,48
		260	H	ACK300	120–**160**–200	0,09–**0,20**–0,32	0,10–**0,22**–0,36	0,11–**0,24**–0,39	0,12–**0,26**–0,44	0,13–**0,29**–0,48
	Nodular cast iron (GGG)	160	H	ACK300	90–**120**–250	0,09–**0,20**–0,32	0,10–**0,22**–0,36	0,11–**0,24**–0,39	0,12–**0,26**–0,44	0,13–**0,29**–0,48
		250	H	ACK300	90–**120**–150	0,09–**0,20**–0,32	0,10–**0,22**–0,36	0,11–**0,24**–0,39	0,12–**0,26**–0,44	0,13–**0,29**–0,48
S	Heat resistant alloy	200	L/G	ACP300	25–**50**–70	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22	0,08–**0,14**–0,24
N	Aluminium alloy		G	DL1500	200–**260**–320	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22
	Copper alloy		G	DL1500	180–**230**–280	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22

Recommended Cutting Conditions (3D)

[min. - **optimal** - max.]

ISO	Work material	Hardness (HB)	Chip breaker & Grade		Cutting Speed Vc (m/min)	Feed rate (mm/rev) Ø 13,0–18,0	Ø 18,5– 29,0	Ø 29,5–36,0	Ø 37,0–55,0	Ø 56,0–65,0
P	Carbon steel	125	L	ACP300	150–**220**–250	0,04–**0,07**–0,1	0,04–**0,07**–0,10	0,04–**0,08**–0,11	0,05–**0,09**–0,12	0,06–**0,10**–0,13
		190	G	ACP300	150–**220**–250	0,08–**0,12**–0,2	0,08–**0,12**–0,20	0,08–**0,13**–0,22	0,09–**0,14**–0,24	0,10–**0,16**–0,27
		250	G	ACP300	125–**170**–230	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18	0,08–**0,13**–0,20
		270	G	ACP300	125–**170**–230	0,08–**0,12**–0,18	0,08–**0,12**–0,18	0,08–**0,13**–0,19	0,09–**0,14**–0,22	0,10–**0,16**–0,24
		300	G	ACP300	100–**130**–170	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17	0,08–**0,13**–0,19
	Low alloyed steel	180	L	ACP300	150–**180**–220	0,05–**0,07**–0,12	0,05–**0,07**–0,12	0,05–**0,08**–0,13	0,06–**0,08**–0,15	0,07–**0,09**–0,16
		275	G	ACP300	125–**150**–200	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17	0,08–**0,13**–0,19
		300	G	ACP300	100–**140**–170	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17	0,08–**0,13**–0,19
		350	G	ACP300	80–**120**–150	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17	0,08–**0,13**–0,19
	High alloyed steel	200	G	ACP300	100–**150**–200	0,08–**0,12**–0,2	0,08–**0,12**–0,20	0,08–**0,13**–0,22	0,09–**0,14**–0,24	0,10–**0,16**–0,27
		325	G	ACP300	80–**120**–160	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18	0,08–**0,13**–0,20
M	Stainless steel, martensitic / ferritic	200	L/G	ACP300	100–**150**–200	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18	0,08–**0,13**–0,20
	Stainless steel, martensitic / tempered	240	L/G	ACP300	90–**120**–150	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18	0,08–**0,13**–0,20
	Stainless steel, austenitic / quenched	180	L/G	ACP300	100–**150**–200	0,04–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18	0,08–**0,13**–0,20
	Stainless steel, austenitic / ferritic (Duplex)	230	L/G	ACP300	80–**120**–150	0,04–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18	0,08–**0,13**–0,20
K	Cast iron (GG)	180	H	ACK300	12–**160**–200	0,09–**0,18**–0,27	0,10–**0,20**–0,30	0,11–**0,22**–0,32	0,12–**0,24**–0,36	0,13–**0,26**–0,40
		260	H	ACK300	120–**160**–200	0,09–**0,18**–0,27	0,10–**0,20**–0,30	0,11–**0,22**–0,32	0,12–**0,24**–0,36	0,13–**0,26**–0,40
	Nodular cast iron (GGG)	160	H	ACK300	90–**120**–250	0,09–**0,18**–0,27	0,10–**0,20**–0,30	0,11–**0,22**–0,32	0,12–**0,24**–0,36	0,13–**0,26**–0,40
		250	H	ACK300	90–**120**–150	0,09–**0,18**–0,27	0,10–**0,20**–0,30	0,11–**0,22**–0,32	0,12–**0,24**–0,36	0,13–**0,26**–0,40
S	Heat resistant alloy	200	L/G	ACP300	25–**50**–70	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18	0,08–**0,13**–0,20
N	Aluminium alloy		G	DL1500	200–**260**–320	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22
	Copper alloy		G	DL1500	180–**230**–280	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20	0,08–**0,14**–0,22

Indexable Insert Type "SumiDrill"
WDX Type

Recommended Cutting Conditions (4D)

[min. - **optimal** - max.]

Material Group ISO	Work material	Hardness (HB)	Chip breaker & Grade		Cutting Speed Vc (m/min)	Feed rate (mm/rev) Ø 13,0–18,0	Ø 18,5–29,0	Ø 29,5–36,0	Ø 37,0–55,0	Ø 56,0–65,0
P	Carbon steel	125	L	ACP300	150–**220**–250	0,04–**0,07**–0,09	0,04–**0,07** – 0,09	0,04–**0,07**–0,09	0,05–**0,08**–0,10	0,05–**0,08**–0,10
		190	G	ACP300	150–**220**–250	0,08–**0,11**–0,17	0,08–**0,11**–0,17	0,08–**0,12**–0,18	0,09–**0,14**–0,21	0,09–**0,14**–0,21
		250	G	ACP300	125–**170**–230	0,06–**0,10**–0,13	0,06–**0,10**–0,13	0,06–**0,10**–0,14	0,07–**0,11**–0,15	0,07–**0,11**–0,15
		270	G	ACP300	125–**170**–230	0,08–**0,11**–0,15	0,08–**0,11**–0,15	0,08–**0,12**–0,17	0,09–**0,14**–0,19	0,09–**0,14**–0,19
		300	G	ACP300	100–**130**–170	0,06–**0,10**–0,12	0,06–**0,10**–0,12	0,06–**0,10**–0,13	0,07–**0,11**–0,14	0,07–**0,11**–0,14
	Low alloyed steel	180	L	ACP300	150–**180**–220	0,05–**0,07**–0,10	0,05–**0,07**–0,10	0,05–**0,07**–0,11	0,06–**0,08**–0,12	0,06–**0,08**–0,12
		275	G	ACP300	125–**150**–200	0,06–**0,10**–0,12	0,06–**0,10**–0,12	0,06–**0,10**–0,13	0,07–**0,11**–0,14	0,07–**0,11**–0,14
		300	G	ACP300	100–**140**–170	0,06–**0,10**–0,12	0,06–**0,10**–0,12	0,06–**0,10**–0,13	0,07–**0,11**–0,14	0,07–**0,11**–0,14
		350	G	ACP300	80–**120**–150	0,06–**0,10**–0,12	0,06–**0,10**–0,12	0,06–**0,10**–0,13	0,07–**0,11**–0,14	0,07–**0,11**–0,14
	High alloyed steel	200	G	ACP300	100–**150**–200	0,08–**0,11**–0,17	0,08–**0,11**–0,17	0,08–**0,12**–0,18	0,09–**0,14**–0,21	0,09–**0,14**–0,21
		325	G	ACP300	80–**120**–160	0,06–**0,10**–0,13	0,06–**0,10**–0,13	0,06–**0,10**–0,14	0,07–**0,11**–0,15	0,07–**0,11**–0,15
M	Stainless steel, martensitic / ferritic	200	L/G	ACP300	100–**150**–200	0,06–**0,10**–0,13	0,06–**0,10**–0,13	0,06–**0,10**–0,14	0,07–**0,11**–0,15	0,07–**0,11**–0,15
	Stainless steel, martensitic / tempered	240	L/G	ACP300	90–**120**–150	0,06–**0,10**–0,13	0,06–**0,10**–0,13	0,06–**0,10**–0,14	0,07–**0,11**–0,15	0,07–**0,11**–0,15
	Stainless steel, austenitic / quenched	180	L/G	ACP300	100–**150**–200	0,04–**0,10**–0,13	0,06–**0,10**–0,13	0,06–**0,10**–0,14	0,07–**0,11**–0,15	0,07–**0,11**–0,15
	Stainless steel, austenitic / ferritic (Duplex)	230	L/G	ACP300	80–**120**–150	0,04–**0,10**–0,13	0,06–**0,10**–0,13	0,06–**0,10**–0,14	0,07–**0,11**–0,15	0,07–**0,11**–0,15
K	Cast iron (GG)	180	H	ACK300	120–**160**–200	0,09–**0,17**–0,23	0,10–**0,19**–0,26	0,11–**0,21**–0,28	0,12–**0,23**–0,31	0,12–**0,23**–0,31
		260	H	ACK300	120–**160**–200	0,09–**0,17**–0,23	0,10–**0,19**–0,26	0,11–**0,21**–0,28	0,12–**0,23**– 0,31	0,12–**0,23**–0,31
	Nodular cast iron (GGG)	160	H	ACK300	90–**120**– 250	0,09–**0,17**–0,23	0,10–**0,19**–0,26	0,11–**0,21**–0,28	0,12–**0,23**–0,31	0,12–**0,23**–0,31
		250	H	ACK300	90–**120**–150	0,09–**0,17**–0,23	0,10–**0,19**–0,26	0,11–**0,21**–0,28	0,12–**0,23**– 0,31	0,12–**0,23**–0,31
S	Heat resistant alloy	200	L/G	ACP300	25–**50**–70	0,06–**0,10**–0,13	0,06–**0,10**–0,13	0,06–**0,10**–0,14	0,07–**0,11**–0,15	0,07–**0,11**–0,15
N	Aluminium alloy		G	DL1500	200–**260**–320	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,06–**0,11**–0,16	0,06–**0,12**–0,18	0,07–**0,13**–0,20
	Copper alloy		G	DL1500	180–**230**–280	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,06–**0,11**–0,16	0,06–**0,12**–0,18	0,07–**0,13**–0,20

Recommended Cutting Conditions (5D)

[min. - **optimal** - max.]

Material Group ISO	Work material	Hardness (HB)	Chip breaker & Grade		Cutting Speed Vc (m/min)	Feed rate (mm/rev) Ø 13,0–18,0	Ø 18,5–29,0	Ø 29,5–36,0	Ø 37,0–55,0	Ø 56,0–65,0
P	Carbon steel	125	L	ACP300	150–**220**–250	0,04–**0,06**–0,09	0,04–**0,06**–0,08	0,04–**0,06**–0,08	0,05–**0,07**–0,09	
		190	G	ACP300	150–**220**–250	0,07–**0,10**–0,15	0,07–**0,10**–0,15	0,08–**0,11**–0,17	0,09–**0,12**–0,19	
		250	G	ACP300	125–**170**–230	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14	
		270	G	ACP300	125–**170**–230	0,07–**0,10**–0,14	0,07–**0,10**–0,14	0,08–**0,11**–0,15	0,09–**0,12**–0,17	
		300	G	ACP300	100–**130**–170	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13	
	Low alloyed steel	180	L	ACP300	150–**180**–220	0,05–**0,06**–0,09	0,05–**0,06**–0,09	0,05–**0,06**–0,10	0,05–**0,07**–0,11	
		275	G	ACP300	125–**150**–200	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13	
		300	G	ACP300	100–**140**–170	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13	
		350	G	ACP300	80–**120**–150	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13	
	High alloyed steel	200	G	ACP300	100–**150**–200	0,07–**0,10**–0,15	0,07–**0,10**–0,15	0,08–**0,11**–0,17	0,09–**0,12**–0,19	
		325	G	ACP300	80–**120**–160	0,05–**0,09**–0,11	0,06–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14	
M	Stainless steel, martensitic / ferritic	200	L/G	ACP300	100–**150**–200	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14	
	Stainless steel, martensitic / tempered	240	L/G	ACP300	90–**120**–150	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14	
	Stainless steel, austenitic / quenched	180	L/G	ACP300	100–**150**–200	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14	
	Stainless steel, austenitic / ferritic (Duplex)	230	L/G	ACP300	80–**120**–150	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,07–**0,12**–0,18	
K	Cast iron (GG)	180	H	ACK300	120–**160**–200	0,08–**0,15**–0,21	0,09–**0,17**–0,23	0,09–**0,18**–0,25	0,11–**0,20**–0,28	
		260	H	ACK300	120–**160**–200	0,08–**0,15**–0,21	0,09–**0,17**–0,23	0,09–**0,18**–0,25	0,11–**0,20**–0,28	
	Nodular cast iron (GGG)	160	H	ACK300	90–**120**–250	0,08–**0,15**–0,21	0,09–**0,17**–0,23	0,09–**0,18**–0,25	0,11–**0,20**–0,28	
		250	H	ACK300	90–**120**–150	0,08–**0,15**–0,21	0,09–**0,17**–0,23	0,09–**0,18**–0,25	0,11–**0,20**–0,28	
S	Heat resistant alloy	200	L/G	ACP300	25–**50**–70	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14	
N	Aluminium alloy		G	DL1500	200–**260**–320	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,06–**0,11**–0,16	0,06–**0,12**–0,18	
	Copper alloy		G	DL1500	180–**230**–280	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,06–**0,11**–0,16	0,06–**0,12**–0,18	

PDL Type / PCT Type

Description

The tool cuts in the Z axis direction where tool rigidity is highest, allowing high efficiency roughing for aeronautic components and dies with long tool overhang must be used to machine deep holes and pockets.

Characteristics

- The flat cutting edge design produces near-flat bottom profiles to reduce depth of cut variation during finishing.
- All sizes come with an air hole for supplying coolant internally to improve chip evacuation.
- Durable body with special surface treatment offers improved tool life and reliability.
- The tools use SumiDrill WDX type inserts for handling a wide range of work materials, from steel to non-ferrous metals and exotic alloys.

- The PDL type has a central insert making it possible to make radial cuts beyond the tool's radius, pitch feed cutting, and drilling. (Pocket milling, etc.)



Keep the value of P_f for PDL type tools to less than 70 % of the tool diameter (DC).

- Although the PCT type has limited radial cutting ability, the tool has many effective teeth enabling it to perform high feed cutting. (Medium finishing of corners, hole expansion, deep grooving, etc.)



Keep the value of P_f for PCT type tools to less than 50 % of the tool diameter (DC).
For a_e refer to the dimension under "a_e max" in the stock / dimensions tables titled "Holders Max, Depth: 3D/5D".

Application examples

PDL Pocketing
Work Material: Ti Alloy



Tool: PDL400D2S40 (Ø 40)
Insert: WDXT125012-G
Grade: ACK300
Cutting Conditions:
v_c = 40 m/min
f = 0,07 mm/rev
(v_f = 22,3 mm/min)
P_f = 25 mm

PCT Corner Finishing
Work Material: Ti Alloy



Tool:
PCT320D3S32 (Ø 32)
PCT250D3S25 (Ø 25)
PCT200D3S20 (Ø 20)
Grade: ACK300
Insert:
WDXT094008-G
WDXT073506-G
WDXT063006-G
Cutting Conditions:
v_c = 50 m/min
f_t = 0,08 mm/tooth
(v_f = 80–127 mm/min)
a_e = 3,2–6,5 mm

PCT Grooving
Work Material: Ti Alloy



Tool: PCT320D5S32 (Ø 32)
Insert: WDXT094008-G
Grade: ACK300
Cutting Conditions:
v_c = 40 m/min
f_t = 0,07 mm/tooth
(v_f = 56 mm/min)
P_f = 5,0 mm

PDL Drilling
Work Material: X4 CrNiMo 17 12 2



Tool: PDL200D3S25 (Ø 20)
Insert: WDXT063006-G
Grade: ACP300
Cutting Conditions:
v_c = 180 m/min
f = 0,10 mm/rev
(v_f = 286 mm/min)
DC = 20 mm

PCT Aeronautic Components
Work Material: X5 CrNi 18 10



Tool: PCT320D3S32 (Ø 32)
Insert: WDXT094008-G
Grade: ACP300
Cutting Conditions:
v_c = 180 m/min
f_t = 0,15 mm/tooth
(v_f = 537 mm/min)
a_e = 7,0 mm, P_f = 5,0 mm

PCT Machine Components
Work Material: 34 Cr Ni 4



Tool: PCT200D5S20 (Ø 20)
Insert: WDXT063006-G
Grade: ACK300
Cutting Conditions:
v_c = 150 m/min
f_t = 0,15 mm/tooth
(v_f = 716 mm/min)
a_e = 3,5 mm

● = Euro stock
❍ = Japan stock

Recommended Tightening Torque (N·m)

Indexable Plunge Drill
PDL Type (2D, 3D)

2D 3D

Carbon Steel, Alloy Steel		Tempered Steel	Hardened Steel		Stainless Steel	Ti Alloy	Heat Resistant Alloy	Cast iron	Ductile Cast Iron	Al Alloy	Cu Alloy	Composite CFRP *
C≤0,28%	C>0,28%		HRC≤45	HRC>45								
W												

Fig 1



Fig 2



Holder (Max a_p: 2D)

Cat. No.	Stock	Dimensions (mm)								Applicable Insert	Fig.
		DC	OAL	LU	LUX	LPR	LS	DCON	DCSFMS		
PDL 160D2S20	●	16,0	94	32	35	50	44	20	28	WDXT052504	
200D2S25	●	20,0	114	40	43	58	56	25	33	WDXT063006	1
250D2S25	●	25,0	127	50	53	71	56	25	37	WDXT073506	
PDL 320D2S40	●	32,0	162	64	68	92	70	40	54	WDXT094008	2
400D2S40	●	40,0	185	80	85	115	70	40	54	WDXT125012	

Holder (Max a_p: 3D)

Cat. No.	Stock	Dimensions (mm)								Applicable Insert	Fig.
		DC	OAL	LU	LUX	LPR	LS	DCON	DCSFMS		
PDL 160D3S20	●	16,0	110	48	51	66	44	20	28	WDXT052504	
200D3S25	●	20,0	134	60	63	78	56	25	33	WDXT063006	1
250D3S25	●	25,0	152	75	78	96	56	25	37	WDXT073506	
PDL 320D3S40	●	32,0	194	96	100	124	70	40	54	WDXT094008	2
400D3S40	●	40,0	225	120	125	155	70	40	54	WDXT125012	

Spare Parts

Screw	Wrench	Wrench	N·m	Applicable Holders
				
BFTX0204N	TRX06	–	**0,5**	PDL 160 D2 S20, PDL 160 D3 S20 PCT 160 D3 S16, PCT 160 D5 S16
BFTY02206	–	TRD07	**1,0**	PDL 200 D2 S25, PDL 200 D3 S25 PCT 200 D3 S20, PCT 200 D5 S20
BFTX02506N	–	TRD08	**1,5**	PDL 250 D2 S25, PDL 250 D3 S25 PCT 250 D3 S25, PCT 250 D5 S25
BFTX03584	–	TRD15	**3,5**	PDL 320 D2 S40, PDL 320 D3 S40 PCT 320 D3 S32, PCT 320 D5 S32
BFTX0511N	–	TRD20	**5,0**	PDL 400 D2 S40, PDL 400 D3 S40 PCT 400 D3 S42, PCT 400 D5 S42

Notes about Mounting Inserts



PDL type: Inserts can be used on either the centre or the outside.
Inserts used on the outside cannot be used in the centre,. Similarly, inserts used in the centre cannot be used on the outside.
PCT type: 2 corners can be used only for the outer inserts.

Indexable Plunge Mill
PCT Type (3D, 5D)

3D 5D

Carbon Steel, Alloy Steel		Tempered Steel	Hardened Steel		Stainless Steel	Ti Alloy	Heat Resistant Alloy	Cast iron	Ductile Cast Iron	Al Alloy	Cu Alloy	Composite CFRP *
C≤0,28%	C>0,28%		HRC≤45	HRC>45								
◎	◎		○		○	◎		◎	◎	◎	○	

* CFRP (Carbon Fibre Reinforced Plastic)

Fig 3



Holder (Max a_p: 3D)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	Applicable Insert	Fig.
		DC	a_e max	OAL	LH	LS	DCON			
PCT 160D3S16	●	16,0	4,0	123	53	70	16	2	WDXT052504	
200D3S20	●	20,0	5,0	145	65	80	20	2	WDXT063006	
250D3S25	●	25,0	6,5	160	80	80	25	2	WDXT073506	3
320D3S32	●	32,0	8,5	191	101	90	32	2	WDXT094008	
400D3S42	●	40,0	11,0	225	125	100	42	3	WDXT125012	

Holder (Max a_p: 5D)

Cat. No.	Stock	Dimensions (mm)						No. of teeth	Applicable Insert	Fig.
		øD	a_e max	OAL	LH	LS	DCON			
PCT 160D5S16	●	16,0	4,0	155	85	70	16	2	WDXT052504	
200D5S20	●	20,0	5,0	185	105	80	20	2	WDXT063006	
250D5S25	●	25,0	6,5	210	130	80	25	2	WDXT073506	3
320D5S32	●	32,0	8,5	255	165	90	32	2	WDXT094008	
400D5S42	●	40,0	11,0	305	205	100	42	3	WDXT125012	

Inserts

(mm)

Fig. 4



L Type
Excellent chip control at low feed rates

Fig. 5



G Type
General purpose chipbreaker

Fig. 6



H Type
Strong cutting edge at higher feed rates

Application	Coated			
High Speed / Light Cutting				N
General Purpose		M		
Roughing		PM	K	

Cat. No.	ACP100	ACP300	ACK300	DL1500	Fig.	Dimensions (mm) W1	Thickness	RE	Applicable Holder
WDXT 052504-L	❍	●	●		4				PDL160D2S20
052504-G	●	●	●	●	5	5,0	2,5	0,4	PDL160D3S20 PCT160D3S16
052504-H	❍	●	●		6				PCT160D5S16
WDXT 063006-L	●	●	●		4				PDL200D2S25
063006-G	●	●	●	●	5	6,0	3,0	0,6	PDL200D3S25 PCT200D3S20
063006-H	❍	●	●		6				PCT200D5S20
WDXT 073506-L	●	●	●		4				PDL250D2S25
073506-G	●	●	●	●	5	7,5	3,5	0,6	PDL250D3S25 PCT250D3S25
073506-H	●	●	●		6				PCT250D5S25
WDXT 094008-L	●	●	●		4				PDL320D2S40
094008-G	●	●	●	●	5	9,6	4,0	0,8	PDL320D3S40 PCT320D3S32
094008-H	●	●	●		6				PCT320D5S32
WDXT 125012-L	●	●	●		4				PDL400D2S40
125012-G	●	●	●	●	5	12,4	5,0	1,2	PDL400D3S40 PCT400D3S42
125012-H	●	●	●		6				PCT400D5S42

Identification Details

PCT, PDL Type

PCT 250 D3 S25

- 250: Tool Diameter (Ø 25,0)
- D3: Max Depth L/D (3D)
- S25: Shank Size (Ø 25,0)

PCT, PDL Type Insert Identification

WDXT 07 35 06 -G

- 07: Width Across Flats (7,5)
- 35: Thickness x 10 (3,5)
- 06: Corner Radius x 10 (R0,6)
- -G: Breaker Type

Recommended Cutting Conditions
PDL Type / PCT Type



Recommended Cutting Conditions (2D)

[min. - **optimal** - max.]

ISO	Work material	Hardness (HB)	Chip breaker & Grade		Cutting Speed Vc (m/min)	PDL Type: f (mm/rev) Ø 16,0	Ø 20,0–25,0	Ø 32,0	Ø 40,0
P	Carbon steel	125	G	ACP300	120–**180**–240	0,05–**0,08**–0,10	0,05–**0,08**–0,10	0,05–**0,08**–0,11	0,05–**0,08**–0,12
		125	L	ACP300	130–**170**–220	0,04–**0,08**–0,12	0,04–**0,08**–0,12	0,04–**0,08**–0,13	0,05–**0,10**–0,15
		190	G	ACP300	100–**150**–200	0,08–**0,13**–0,24	0,08–**0,13**–0,24	0,08–**0,14**–0,26	0,09–**0,16**–0,29
		250	G	ACP300	80–**120**–160	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22
		270	G	ACP300	100–**130**–160	0,08–**0,13**–0,22	0,08–**0,13**–0,22	0,08–**0,14**–0,23	0,09–**0,16**–0,26
		300	G	ACP300	70–**100**–140	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20
	Low alloyed steel	180	L	ACP300	100–**140**–180	0,05–**0,08**–0,14	0,05–**0,08**–0,14	0,05–**0,08**–0,16	0,06–**0,09**–0,17
		275	G	ACP300	80–**120**–160	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20
		300	G	ACP300	75–**110**–140	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20
		350	G	ACP300	60–**85**–110	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20
	High alloyed steel	200	G	ACP300	100–**130**–160	0,08–**0,13**–0,24	0,08–**0,13**–0,24	0,08–**0,14**–0,26	0,09–**0,16**–0,29
		325	G	ACP300	80–**100**–120	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22
M	Stainless steel, martensitic / ferritic	200	G	ACP300	100–**140**–180	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22
	Stainless steel, martensitic / tempered	240	G	ACP300	90–**120**–150	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22
	Stainless steel, austenitic / quenched	180	G	ACP300	100–**140**–180	0,06–**0,08**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22
	Stainless steel, austenitic / ferritic (Duplex)	230	G	ACP300	80–**120**–150	0,04–**0,08**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22
K	Cast iron (GG)	180	H	ACK300	120–**160**–200	0,09–**0,20**–0,32	0,10–**0,22**–0,36	0,11–**0,24**–0,39	0,12–**0,26**–0,44
	Nodular cast iron (GGG)	260	H	ACP300	90–**120**–150	0,09–**0,20**–0,32	0,10–**0,22**–0,36	0,11–**0,24**–0,39	0,12–**0,26**–0,44
S	Heat resistant alloy	200	G	ACP300	25–**50**–70	0,06–**0,11**–0,18	0,06–**0,11**–0,18	0,06–**0,12**–0,19	0,07–**0,13**–0,22
N	Aluminium alloy		G	DL1500	200–**260**–320	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20
	Copper alloy		G	DL1500	180–**230**–280	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20

Recommended Cutting Conditions (3D)

[min. - **optimal** - max.]

ISO	Work material	Hardness (HB)	Chip breaker & Grade		Cutting Speed Vc (m/min)	PDL Type: f (mm/rev) / PCT Type: f_t (mm/tooth) Ø 16,0	Ø 20,0–25,0	Ø 32,0	Ø 40,0
P	Carbon steel	125	G	ACP300	120–**180**–240	0,05–**0,07**–0,10	0,05–**0,07**–0,10	0,05–**0,08**–0,11	0,05–**0,08**–0,12
		125	L	ACP300	130–**170**–220	0,04–**0,07**–0,10	0,04–**0,07**–0,10	0,04–**0,08**–0,11	0,05–**0,09**–0,12
		190	G	ACP300	100–**150**–200	0,08–**0,12**–0,20	0,08–**0,12**–0,20	0,08–**0,13**–0,22	0,09–**0,14**–0,24
		250	G	ACP300	80–**120**–160	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18
		270	G	ACP300	100–**130**–160	0,08–**0,12**–0,18	0,08–**0,12**–0,18	0,08–**0,13**–0,19	0,09–**0,14**–0,22
		300	G	ACP300	70–**100**–140	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17
	Low alloyed steel	180	L	ACP300	100–**140**–180	0,05–**0,07**–0,12	0,05–**0,07**–0,12	0,05–**0,07**–0,13	0,06–**0,07**–0,15
		275	G	ACP300	80–**120**–160	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17
		300	G	ACP300	75–**110**–140	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17
		350	G	ACP300	60–**85**–110	0,06–**0,10**–0,14	0,06–**0,10**–0,14	0,06–**0,11**–0,15	0,07–**0,12**–0,17
	High alloyed steel	200	G	ACP300	100–**130**–160	0,08–**0,12**–0,20	0,08–**0,12**–0,20	0,08–**0,13**–0,22	0,09–**0,14**–0,24
		325	G	ACP300	80–**100**–120	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18
M	Stainless steel, martensitic / ferritic	200	G	ACP300	100–**140**–180	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18
	Stainless steel, martensitic / tempered	240	G	ACP300	90–**120**–150	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18
	Stainless steel, austenitic / quenched	180	G	ACP300	100–**140**–180	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18
	Stainless steel, austenitic / ferritic (Duplex)	230	G	ACP300	80–**120**–150	0,04–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18
K	Cast iron (GG)	180	H	ACK300	120–**160**–200	0,09–**0,18**–0,27	0,10–**0,20**–0,30	0,11–**0,22**–0,32	0,12–**0,24**–0,36
	Nodular cast iron (GGG)	260	H	ACP300	90–**120**–150	0,09–**0,18**–0,27	0,10–**0,20**–0,30	0,11–**0,22**–0,32	0,12–**0,24**–0,36
S	Heat resistant alloy	200	G	ACP300	25–**50**–70	0,06–**0,10**–0,15	0,06–**0,10**–0,15	0,06–**0,11**–0,16	0,07–**0,12**–0,18
N	Aluminium alloy		G	DL1500	200–**260**–320	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20
	Copper alloy		G	DL1500	180–**230**–280	0,06–**0,11**–0,17	0,06–**0,11**–0,17	0,06–**0,12**–0,18	0,07–**0,13**–0,20

Recommended Cutting Conditions (5D)

[min. - **optimal** - max.]

ISO	Work material	Hardness (HB)	Chip breaker & Grade		Cutting Speed Vc (m/min)	PCT Type: f_t (mm/tooth) Ø 16,0	Ø 20,0–25,0	Ø 32,0	Ø 40,0
P	Carbon steel	125	G	ACP300	120–**180**–240	0,05–**0,06**–0,09	0,05–**0,06**–0,09	0,05–**0,06**–0,09	0,05–**0,07**–0,09
		125	L	ACP300	130–**170**–220	0,04–**0,06**–0,08	0,04–**0,06**–0,08	0,04–**0,06**–0,08	0,05–**0,07**–0,09
		190	G	ACP300	100–**150**–200	0,07–**0,10**–0,15	0,07–**0,10**–0,15	0,08–**0,11**–0,17	0,09–**0,12**–0,19
		250	G	ACP300	80–**120**–160	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14
		270	G	ACP300	100–**130**–160	0,07–**0,10**–0,14	0,07–**0,10**–0,14	0,08–**0,11**–0,15	0,09–**0,12**–0,17
		300	G	ACP300	70–**100**–140	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13
	Low alloyed steel	180	L	ACP300	100–**140**–180	0,05–**0,06**–0,09	0,05–**0,06**–0,09	0,05–**0,06**–0,10	0,05–**0,07**–0,11
		275	G	ACP300	80–**120**–160	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13
		300	G	ACP300	75–**110**–140	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13
		350	G	ACP300	60–**85**–110	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,13
	High alloyed steel	200	G	ACP300	100–**130**–160	0,07–**0,10**–0,15	0,07–**0,10**–0,15	0,08–**0,11**–0,17	0,09–**0,12**–0,19
		325	G	ACP300	80–**100**–120	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14
M	Stainless steel, martensitic / ferritic	200	G	ACP300	100–**140**–180	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14
	Stainless steel, martensitic / tempered	240	G	ACP300	90–**120**–150	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14
	Stainless steel, austenitic / quenched	180	G	ACP300	100–**140**–180	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14
	Stainless steel, austenitic / ferritic (Duplex)	230	G	ACP300	80–**120**–150	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14
K	Cast iron (GG)	180	H	ACK300	120–**160**–200	0,08–**0,15**–0,21	0,09–**0,17**–0,23	0,09–**0,18**–0,25	0,11–**0,20**–0,28
	Nodular cast iron (GGG)	260	H	ACP300	90–**120**–150	0,08–**0,15**–0,21	0,09–**0,17**–0,23	0,09–**0,18**–0,25	0,11–**0,20**–0,28
S	Heat resistant alloy	200	G	ACP300	25–**50**–70	0,05–**0,09**–0,11	0,05–**0,09**–0,11	0,06–**0,09**–0,12	0,06–**0,10**–0,14
N	Aluminium alloy		G	DL1500	200–**260**–320	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,06–**0,11**–0,16	0,06–**0,12**–0,18
	Copper alloy		G	DL1500	180–**230**–280	0,05–**0,10**–0,15	0,05–**0,10**–0,15	0,06–**0,11**–0,16	0,06–**0,12**–0,18

SUMIBORON SUMIDIA

L1–L30



New generation Sumiboron inserts – an even better way to machine hardened steels

General

Building on its global success machining hardened steels with Sumiboron inserts the addition of heat and wear resistant coatings to a variety of tough new CBN substrates has resulted in a new generation of high performance grades. With economy in mind the new inserts are multi cornered.

Choose the coated insert suitable for your application and take your hard part machining operations to the new industry standard.

Types and Application

Microstructure

Microstructure

Microstructure

Type	ISO	Grade	Application	Characteristic	Hardness Hv (GPa)	TRS (GPa)
Uncoated CBN	H	BN1000	High speed Continuous cutting	Best wear resistance grade and suitable for high speed continuous cutting	27–31	0,90–1,00
		BN2000	Continuous and Interrupted cutting	Micro-grain CBN with Ceramic binder improves fracture toughness and wear resistance	31–34	1,05–1,15
		BNX25	High efficiency cutting (Continuous–Interrupted)	Binder with high heat resistance improves tool life during high speed machining	31–33	0,95–1,10
		BNX25	High speed Interrupted cutting	Superior fracture toughness in high speed cutting and suitable for high speed interrupted hard turning	29–31	1,00–1,10
		BN350	Interrupted cutting (Heavy)	Micro-grain CBN with higher fracture toughness that improves cutting edge strength	33–35	1,20–1,30
Coated CBN	H	BNC2010	High precision continuous cutting	New generation TiCN layer improves notch wear resistance and provides an excellent surface finish.	30–32	1,10–1,20
		BNC100	High speed continuous and light interrupted cutting	High speed finishing grade for continuous and light interrupted cutting applications	29–32	1,00–1,10
		BNC160	High precision continuous cutting	High precision grade for continuous cutting - ideal when an excellent surface finish is required	31–33	1,10–1,20
		BNC2020	High efficiency general purpose	New coating technology offers excellent adhesion during both continuous and interrupted cut applications.	34–36	1,20–1,30
		BNC200	Continuous and Interrupted cutting (Light–Medium Interrupted)	General purpose grade with low to high speed cutting capability and extended tool life - removes the carburised layer on heat treated components	33–35	1,10–1,20
		BNC300	Interrupted cutting (Heavy)	Tough grade for heavy interrupted cutting applications	33–35	1,15–1,25
		BNC500	GG and GGG machining	For Cast Iron machining with a good balance of wear and fracture resistance	32–34	1,00–1,10
Uncoated CBN	S PM	BN7000	High speed machining of GG Cast Iron machining Iron based products Rolls of high hardness Heat resistant alloy	First choice for high speed finishing of grey cast iron	41–44	1,25–1,35
	PM	BN7500	High efficiency machining of powdered metal	Less burrs when machining sintered parts due to excellent edge sharpness	41–44	1,40–1,50
	K S	BNS800	High speed machining of GG Machining rolls of high hardness Sintered component roughing Special cast Iron machining	High thermal impact resistance with high heat transfer ability and higher CBN content ratio	39–42	0,95–1,10
Binderless CBN	S K	NCB100	New Ultimate CBN grade achieves highly efficient and precise finishing of hard-to-cut materials	Binderless CBN is harder and has better thermal conductivity. Therefore, it enables higher efficiency and longer tool life in machining of hard-to-cut materials, such as titanium alloy and cobalt-chromium alloy.	51–54	1,8–1,9

H

HARDENED STEEL MACHINING

Advantages of using CBN

In terms of cost investment, it is much lower in machine cost and overhead cost due to the fact that a CNC lathe is cheaper than a grinding machine.
As for the quality of finish, inserts can machine different profiles and the finishing is also commendable as compared to grinding.
Environmentally, sludge treatment for grinding is a hazard to the environment but for turning, the chips can be collected and recycled.

■ Application Range





K

CAST IRON MACHINING

Advantages of using CBN

Following charts show merits of using CBN in cast iron machining compared with conventional tools, such as carbide, cermet or ceramics.
SumiBoron performs longer tool life than conventional tools in high speed machining and brings higher efficiency and superior precision.

High Speed Machining



High Speed Machining



High Precision Machining



■ Application Range

Grey Cast Iron



Ductile Cast Iron



Edge Specification of SUMIBORON Inserts

Sumiboron Inserts and Edge Preparation

All SUMIBORON inserts are enhanced with the optimum cutting edge preparation for various grades and geometries (shown on the rigth).
This is to avoid cutting edge fracture caused by the heavy loads generated during the machining of high hardness materials such as Hardened Steel.
As the pioneer of CBN tools „SUMIBORON“, various selection of grades and edge preparation combinations is our strong point for Hardened Steel machining.

Close-up of Cutting Edge



Section A - A'



SUMIBORON Insert Cutting Edge Specification

Series	Work Material	Grade	Negative / Positive	Standard				Low Resistance Type **L** / High Efficiency Type **E**					Strong Edge Type **H**				
				Identification Code	α	W	Honing	Notation	Identification Code	α	W	Honing	Notation	Identification Code	α	W	Honing
Uncoated SUMIBORON	Hardened Steel	**BNX10**	Neg./Pos.	T01225	25°	0,12	No	–	–	–	–	–	–	–	–	–	–
		BNX20	Neg./Pos.	S01225	25°	0,12	Yes	**LT**	T01215*	15°	0,12	No	–	–	–	–	–
		BNX25	Neg./Pos.	S01725	25°	0,17	Yes	–	–				–	–	–	–	–
		BN1000	Neg./Pos.	S01225	25°	0,12	Yes	–	–				–	–	–	–	–
		BN2000	Neg./Pos.	S01225	25°	0,12	Yes	**LT**	T01215	15°	0,12	No	**HS**	S01235	35°	0,12	Yes
		BN350	Neg.	T01225	25°	0,12	No	–	–	–	–	–	**HT**	T01235	35°	0,12	No
			Pos.	T01235	35°	0,12	No						–	–	–	–	–
	Cast Iron	**BN700**	Neg./Pos.	T01215	15°	0,12	No	**LF**	(Sharp edge)	0°	0	No	**HS**	S01225	25°	0,12	Yes
		BN7000	Neg./Pos.	T01215	15°	0,12	No	**LF**	(Sharp edge)	0°	0	No	**HS**	S01225	25°	0,12	Yes
	Exotic Alloy	**BN7500**	Neg./Pos.	T01215	15°	0,12	No	**LF**	(Sharp edge)	0°	0	No	**HS**	S00525	25°	0,05	Yes
								LE	(Sharp edge)	0°	0	Yes					
								LS	S00715	15°	0,07	Yes					
		BNS800	Neg.	T02020	20°	0,20	No	**LF**	(Sharp edge)	0°	0	No	–	–	–	–	–
Coated SUMIBORON	Hardened Steel	**BNC2010**	Neg./Pos.	S01225	25°	0,12	Yes	**LE**	(Sharp edge)	0°	0	Yes	**HS**	S01730	30°	0,17	Yes
		BNC2020	Neg./Pos.	S01225	25°	0,12	Yes	**LT**	T00515	15°	0,05	No	**HS**	S02735	35°	0,27	Yes
								ES	S00535	35°	0,05	Yes					
		BNC100	Neg./Pos.	S01225	25°	0,12	Yes	**LS**	S01715	15°	0,17	Yes	–	–	–	–	–
		BNC160	Neg./Pos.	S01225	25°	0,12	Yes	**LS**	S01020	20°	0,10	Yes	**HS**	S01730	30°	0,17	Yes
		BNC200	Neg./Pos.	S01225	25°	0,12	Yes	**LS**	S01015	15°	0,10	Yes	**HS**	S01735	35°	0,17	Yes
		BNC300	Neg./Pos.	S01225	25°	0,12	Yes	**LS**	S00515	15°	0,05	Yes	**HS**	S01735	35°	0,17	Yes
	Cast Iron	**BNC500**	Neg./Pos.	S01215	15°	0,12	Yes	–	–	–	–	–	**HS**	S01225	25°	0,12	Yes
Binder-less CBN	Cast Iron, Exotic Alloy, Carbide, Cermet	**NCB100**	Neg./Pos.	T01215	15°	0,12	No	–	–	–	–	–	**–**	–	–	–	–

* BNX20 Identification code will be T00715 for insers with inscribed circle of less than Ø 4,76.

Cutting Edge Preparation of Inserts with Wiper / Chipbreakers

Series	Work Material	Grade	Other Types					
			Notation	Identification Code	α	W	Honing	Type
Uncoated SUMIBORON	Hardened Steel	**BN2000**	WG	S01215	15°	0,12	Yes	Wiper
			WH	S01215	15°	0,12	Yes	Wiper
			N-FV	–	0°	0	Yes	With breaker
			N-LV	S00535	35°	0,05	Yes	With breaker
	Cast Iron Exotic Alloy	**BNS800**	W	T02020	20°	0,20	No	Wiper
			LFW	(Sharp edge)	0°	0	No	With sharpe edge
Coated SUMIBORON	Hardened Steel	**BNC2010 BNC2020**	WG	S01215	15°	0,12	Yes	Wiper
			WH	S01215	15°	0,12	Yes	Wiper
			N-FV	–	0°	0	Yes	With breaker
			N-LV	S00535	35°	0,05	Yes	With breaker
			N-SV	S01235	35°	0,12	Yes	With breaker
		BNC100	W	S01715	15°	0,17	Yes	Wiper
		BNC160 BNC200	WG	S01215	15°	0,12	Yes	Wiper
			WH	S01215	15°	0,12	Yes	Wiper
			W	S01215	15°	0,12	Yes	Wiper
			N-FV	–	0°	0	Yes	With breaker
			N-LV	S00535	35°	0,05	Yes	With breaker
			N-SV	S01235	35°	0,12	Yes	With breaker
	Cast Iron	**BNC500**	W	S01215	15°	0,12	Yes	Wiper

Cutting Edge Specification Identification Code

Notation of Edge Preparation				
No.	Standard Type			
L	Low cutting forces	+	F	Sharp edge
E	High efficiency		E	Honing
			T	Negative land
H	Strong edge type		S	Negative land + honing
WG / WH / W	Wiper			
N-FV / N-LV N-SV	With Chipbreaker			

Edge Preparation Identification Code



S **0** **1** **2** **2** **5**

W: Negative land width **α**: Negative land angle

Cutting edge: **T** - Negative land
S - Negative land + **R** - Honing

Example: **S01225**
→ 25°/0,12 mm width negative land with honing

Insert Types and Cutting Edge Geometries

Multi Cornered One-Use Type Inserts



■ Characteristics

- One-use type inserts improve machining efficiency by using each cutting edge to its full potential following the numbering system on each cutting edge then throwing the insert away.
- Multi cornered inserts have a single piece of Sumiboron mounted on every useable corner. Single sided inserts use the top corners whilst double sided inserts use both top and bottom corners. Diamond shaped inserts have 4 corners and triangular inserts have 6 corners.
- A variety of Sumiboron coated grades readily replace expensive grinding operations for high precision tolerances outstanding surface finish, heavy interrupted cutting and efficient cost effective machining of hardened parts.

Cutting Edge Preparation

Machining of Hardened Steel



Sintered Alloy Machining



One-Use Wiper Insert

■ Characteristics

- New lineup includes:
  WG Type ⇨ for low-feed cutting
  WH Type ⇨ for high-feed cutting
- SUMIBORON one-use insert with wiper edge for hardened steel machining
- Excellent surface finish similar to grinding
- Improved efficiency with higher speeds and feeds

Break Master N - FV, N - LV, N - SV



Break Master N-SV Type

■ Characteristics

- N-SV type is perfect for carburised layer removal while N-FV / N-LV types are best suited to finishing of hardened steel.
- First CBN insert to feature an integral chipbreaker
- Ideal for removing carburised layer - can be used on both hardened and unhardened materals.
- Effective chip control solution protects component from swarf damage.

Break Master N-FV /-LV /-SV



Characteristics

- SUMIBORON one-use insert with chipbreaker.
- N-SV type is perfect for carburised layer removal while N-FV/N-LV types are best suited to finishing of hardened steel.
- Breaker included on the CBN edge, chipbreaking effect can be maintained throughout machining process.
- Unique breaker design can be applied to both hardened and non-hardened parts with effective chip control.
- SV type lineup now includes BNC2010/BNC160 for good wear resistance, while SUMIBORON BNC2020/BNC200 allows high efficiency machining.
- In addition to general purpose SUMIBORON BNC2020/BNC200, the N-FV / N-LV type lineup includes BNC2010/BNC160 for excellent wear resistance and general purpose uncoated SUMIBORON BN2000.

Application Range





* When machining heat treated steel harder than H_RC50 the depth of cut should not exceed 0,5 mm.

Application Examples

External Carburised Layer Removal



No constant stopages or incorrect part dimension problem and the chips are small.

Double the tool life of competitor's CBN

Break Master N-SV
Tool life = 200 pcs

BNC200 (no breaker)
Tool life = 200 pcs

Comp. CBN (no breaker)
Tool life = 100 pcs

Work material: 42CrMo4, Carburised steel (shaft)
Insert: CNGG 120408 N-SV NC4 (BNC200)
Conditions: v_c = 150 m/min, f = 0,15 mm/rev, a_p = 0,5mm, x 2 passes, wet

Carburised Face Layer Removal



Break Master N-SV type improves chip control with increased productivity until the pre-set tool life.



Work material: 42CrMo4 (HRC30-62)
Insert: CNGG 120408 N-SV NC4 (BNC200)
Conditions: v_c = 140 m/min, f = 0,15 mm/rev, a_p = 0,3 mm, wet

SUMIBORON
One-Use Wiper Inserts

■ Characteristics

- SUMIBORON one-use insert with wiper edge for hardened steel machining
- Excellent surface finish similar to grinding
- Improved efficiency with higher speeds and feeds
- New lineup includes:
  WG type ⇨ for low-feed cutting
  WH type ⇨ for high-feed cutting

■ Purpose of Wiper Edge



■ Surface Roughness of Wiper Insert

	"Wiper" Insert (RE 0,8)		Standard Insert (RE0,8)	
	Finishing (f = 0,10 mm/rev)	High feed cutting (f = 0,30 mm/rev)	Finishing (f =0,10 mm/rev)	High feed cutting (f = 0,30 mm/rev)
Surface Roughness Profile	**WG** Type	**WH** Type		
Surface Roughness R_z	0,63 µm	1,39 µm	1,98 µm	9,20 µm

■ Recommended Cutting Conditions
(Surface Roughness Standard: R_z = 1,6–3,2 µm)

- For optimum effectiveness, use wiper inserts for continuous cutting.
- For copy turning, inserts with nose-radius is recommended.
- Chattering and undulation may occur, please use work and machine with high rigidity.

Two types are available depending on the feed rate:
WG type: Recommended feed rate: less than f ≤ 0,20 mm/rev
WH type: Recommended feed rate: more than f ≥ 0,20 mm/rev
Range of good surface roughness: R_z = 1,6 µm to 3,2 µm
Available grades: BN2000, BNC2010, BNC160, BNC2020,BNC200



■ Tool-Setup WG / WH Wiper

CNGA / CCGW / WNGA Type Wiper

1. Use a holder with a 95° approach angle.
2. Tool compensation required.

CNGA / CCGW / WNGA type wiper inserts do not follow the ISO standard. Correction of the tool offset of the cutting edge as explained on the right.



Cutting Edge Position Compensation, Outer Processing



Nose Radius	Type	X-Direction	Z-Direction
RE 0,4	WG	-0,02	-0,02
	WH	-0,06	-0,06
RE 0,8/1,2	WG	-0,01	-0,01
	WH	-0,06	-0,06

DNGA / DCGW Type Wiper

1. Use a holder with a 93° approach angle.
2. Tool compensation required.

DNGA / DCGW type wiper inserts do not follow the ISO standard. Correction of the tool offset of the cutting edge as explained on the right.
Note: DNGA/DCGW type wiper inserts are only possible for external and internal turning, not for facing.



Cutting Edge Position Compensation, Outer Processing



Nose Radius	Type	X-Direction	Z-Direction
RE 0,4	WG	-0,17	-0,01
	WH	-0,70	-0,06
RE 0,8	WG	-0,05	0
	WH	-0,58	-0,05

Uncoated CBN grades for hardened steel machining

■ General Features

A new uncoated type of SUMIBORON that has a newly developed high-purity ceramic binder.
Both fracture and wear resistance are combined to achieve a stable tool life in a wide variety of hardened steel machining.

Available in single corner and multi-corner type inserts.

■ Characteristics

● BN1000
- Superior high-speed machining grade with the highest wear resistance of any uncoated SUMIBORON.
  Delivers excellent tool life in continuous cutting to light-interrupted cutting.
- Improved fracture resistance while also emphasizing wear resistance.
  Improved hardness and heat resistance from the high-purity TiCN ceramic binder.

● BN2000
- General purpose grade suitable for typical hardened steel machining applications.
  Provides stable tool life in everything from continuous cutting to light-to-medium interrupted cutting.
- High degrees of both fracture resistance and wear resistance.
  Significant improvements in the performance of both by employing a high-purity ceramic binder.
- Stable surface roughness by increasing sharpness (Figure on right).

Sharpness Comparison



Compared to conventional grades, small cutting edge roundness

■ Newly Developed High-Purity Ceramic Binder

Conventional Grade



The impurities contained in the ceramic binder for conventional grades cause a weakening in the sintered body and a decrease in heat resistance, which becomes the cause of cracks (chipping) and wear.

BN1000/BN2000



With the newly developed high-purity **ceramic binder**, the BN1000 / BN2000 achieve toughness and improved heat resistance by decreasing impurities to an extreme!

■ Recommended Application Range

Continuous Cutting



Interrupted Cutting



■ Cutting Conditions

BN1000

v_c (m/min)	f (mm/rev)	a_p (mm)
100 150 200 250 300 120	0,03–0,15	0,03–0,2

BN2000

v_c (m/min)	f (mm/rev)	a_p (mm)
50 100 150 200 250 80 120	0,03–0,2	0,0–0,3

* Coolant ... Continuous cutting: dry or wet
Interrupted cutting: dry

Uncoated SUMIBORON
BN1000 / BN2000

■ Cutting Performance

BN1000



Wear Resistance Comparison



Work material: 100Cr6 (H_RC58-62), Round Bar
Insert: CNGA 120408 NU-2
Cutting data: v_c = 150 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, dry

BN1000



Chipping Resistance Comparison



Work material: 15CrMo5 (H_RC58-62), 8 Grooves
Insert: CNGA 120408 NU-2
Cutting data: v_c = 150 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, dry

BN2000



Wear Resistance Comparison



Work material: 15CrMo5 (H_RC58-62), Round Bar
Insert: CNGA 120408 NU-2
Cutting data: v_c = 100 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, dry

BN2000



Chipping Resistance Comparison



Work material: 15CrMo5 (H_RC58-62), 8 Grooves
Insert: CNGA 120408 NU-2
Cutting data: v_c = 150 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, dry

■ Machining Precision

BN1000



Accuracy Comparison



Work material: 15CrMo5 (H_RC58-62), Round Bar Ø 130
Insert: CNGA 120408 NU-2
Cutting data: v_c = 200 m/min, f = 0,1 mm/rev, a_p = 0,1 mm, wet

BN2000



Surface Roughness Comparison



Work material: 15CrMo5 (H_RC58-62), Round Bar
Insert: CNGA 120408 NU-2
Cutting data: v_c = 100 m/min, f = 0,08 mm/rev, a_p = 0,2 mm, dry

Characteristics

BNC2010 BNC2020

BNC100 BNC160 BNC200 BNC300 BNC500

New Coated SUMIBORON Series achieving
- higher speed
- higher efficiency and
- higher precision

General Features

Using a high heat resistant and tough CBN substrate coupled with a special ceramic coating, this series caters to a wide variety of applications with improved precision and longer tool life as compared to conventional CBN.

There is a comprehensive lineup of economical and easy-to-use insert selection, such as the cost effective double-sided, multi-cornered, one-use type inserts.

BNC2010 and BNC2020 are the latest additions to the Coated SUMIBORON series, to provide even better stability and longer tool life for hardened steel machining.

Characteristics



Cutting Performance



Cutting Edge Management



The edge numbers are still visible after machining, which makes the management of used cutting edges easy.

BNC2010 and BNC2020 are coated in gold, which makes it easy to distinguish used edges.

Coated SUMIBORON Characteristics



Characteristics of Grades

BNC2010

CBN Content: 50 ~ 55 %
Grain Size: 2 µm
Hardness HV: 30 ~ 32 GPa
TRS: 1,10 ~ 1,20 GPa
Main Coating Components: Multi-layered TiCN
Coating Thickness: 1,5 µm

High Precision Machining

Newly developed CBN substrate with high crater wear resistance coated with special multi-layered TiCN, which exhibits excellent notch wear resistance.
Ideal for finishing of hardened steel requiring excellent accuracy or surface roughness.
Able to stably maintain 1,6 R_z finishing.

BNC2020

CBN Content: 70 ~ 75 %
Grain Size: 5 µm
Hardness HV: 34 ~ 36 GPa
TRS: 1,20 ~ 1,30 GPa
Main Coating Components: Multi-layered TiAlN
Coating Thickness: 1,5 µm

General and High Efficiency Cutting

Newly developed tough CBN substrate with highly wear resistant TiAlN coating. Provides improved stability by inserting a highly adhesive layer between the substrate and the TiAlN layer.
Ideal for general machining including finishing and interrupted cutting as well as high-efficiency machining such as carburised layer removal.

BNC100

CBN Content: 40 ~ 45%
Grain Size: 1 µm
Hardness HV: 29 ~ 32 GPa
TRS: 1,05~1,15GPa
Main Coating Components: TiAlN/TiCN
Coating Thickness: 2,5 µm

High Speed Cutting

BNC160

CBN Content: 60 ~ 65 %
Grain Size: 3 µm
Hardness HV: 31 ~ 33 GPa
TRS: 1,10~1,20GPa
Main Coating Components: TiAlN/TiCN
Coating Thickness: 2,0 µm

High Precision Machining

BNC200

CBN Content: 65 ~ 70 %
Grain Size: 4 µm
Hardness HV: 33 ~ 35 GPa
TRS: 1,15~1,25GPa
Main Coating Components: TiAlN
Coating Thickness: 2,0 µm

General and High Efficiency Cutting

BNC300

CBN Content: 60 ~ 65 %
Grain Size: 1 µm
Hardness HV: 33 ~ 35 GPa
TRS: 1,15~1,25GPa
Main Coating Components: TiAlN
Coating Thickness: 1,0 µm

Heavy Interrupted Cutting

Recommended Cutting Conditions

Grade	Cutting Speed v_c (m/min) 50 100 (120) 150 (180) 200 (220) 250 300
BNC2010	
BNC2020	
BNC300	
BNC100	
BNC160	
BNC200	

Grade	Feed Rate (mm/rev) / Depth of Cut (mm) 0 0,1 0,2 0,3 0,4 0,5
BNC2010	0,03 – 0,25 0,03 – 0,35
BNC2020	0,03 – 0,40 0,03 – 0,50
BNC300	0,03 – 0,20 0,03 – 0,30
BNC100	0,03 – 0,20 0,03 – 0,30
BNC160	0,03 – 0,20 0,03 – 0,35
BNC200	0,05 – 0,35 0,05 – 0,50



Characteristics

BNC2010 - High Precision

A grade for high-precision machining applicable for finishing requiring good surface roughness and dimensional accuracy.
Provides further improved wear resistance thanks to a newly developed CBN substrate coated with a TiCN layer.
Reduces flank wear and achieves excellent surface finish thanks to newly developed special stable multi-layered coating.

BNC2020 - General Purpose & High Efficiency

A general-purpose grade applicable to general hardened steel machining.
A newly developed tough CBN-substrate coated with a highly wear-resistant TiAlN layer.
Achieves more stable machining and longer tool life by employing a highly adhesive layer for high chipping resistance.

CBN-Substrate and Coating Structure of BNC2010 and BNC2020

BNC2010



Achieves excellent flank wear resistance thanks to a laminated structure of a TiCN-layer and special multi-layer coating.

BNC2020



Achieves further stability thanks to TiAlN coating layers with high bonding strength.

Application Range



Recommended Cutting Conditions

BNC2010

Cutting Speed (m/min)	
120 150 200 250 300	
Feed Rate (mm/rev)	Depth of Cut (mm)
0,03–0,25	0,03–0,35

BNC2020

Cutting Speed (m/min)	
50 100 150 200 220	
Feed Rate (mm/rev)	Depth of Cut (mm)
0,03–0,40	0,03–0,50

Coated SUMIBORON BNC2010/BNC2020

Cutting Performance

BNC2010



Work Material:	15CrMo5, 58-62HRC, Continuous
Insert:	DNGA150408NC4 (BNC2010)
Cutting Edge Treatment:	S01225
Cutting Conditions:	v_c = 160 m/min, f = 0,08 mm/rev, a_p = 0,1 mm, wet

BNC2020



Work Material:	SCM415-5V, 58-62HRC, Interrupted
Insert:	CNGA120412NC4 (BNC2020)
Cutting Edge Treatment:	S01225
Cutting Conditions:	v_c = 130 m/min, f = 0,1 mm/rev, a_p = 0,6 mm, dry

Application Example

Continuous External Turning of Main Shaft

BNC2010 provides excellent wear resistance and achieves excellent surface roughness.





Insert:	DNGA150408NC4 (BNC2010)
Cutting Conditions:	v_c = 200 m/min, f = 0,10 mm/rev, a_p = 0,35 mm, dry

Carburised Layer Removal for Sun Gears

BNC2020 achieves a longer tool life in high load cutting.





Insert:	DNGA120408NC4 (BNC2020)
Cutting Conditions:	v_c = 100 m/min, f = 0,15 mm/rev, a_p = 0,5 mm, wet

Facing of CVJ Outer Race

BNC2010 with a WH type wiper insert maintains excellent surface finish for an extended time.





Insert:	CNGA120412NCWH2 (BNC2010)
Cutting Conditions:	v_c = 150 m/min, f = 0,2 mm/rev, a_p = 0,2 mm, dry

Interrupted Machining of CVJ Cage Window

BNC2020 strong edge HS type provides stable performance in interrupted cutting.





Insert:	TNGA160420HSNC3 (BNC2020)
Cutting Conditions:	v_c = 120 m/min, f = 0,10 mm/rev, a_p = 0,15 mm, dry

Cutting Edge Preparation

Grade	General Edge Treatment	Strong Edge Type: HS
	Edge Treatment	Edge Treatment
BNC2010	S01225	S01730
BNC2020	S01225	S02735



Edge Treatment Identification Code

S 0 1 2 2 5

Cutting edge: **T** - Negative land
S - Negative land + **R** - Honing

W: Negative land width

α: Negative land angle

Coated Sumiboron premium grade for high speed machining of hardened steels

General Features

Our copper coloured Sumiboron grade BNC 100 resists premature plastic deformation of the cutting edge by withstanding the high temperatures that occur when machining hardened steels. This new grade features a heat resistant CBN substrate and a special TiCN based ceramic coating to enhance surface finish across a broad range of finishing applications at elevated cutting speeds.

Ideal for higher speed machining and suitable for continuous or light interrupted cuts BNC100 delivers reliable performance and excellent tool life

Advantages

- High speed machining!
  Suitable for continuous to light interrupted high speed cutting with v_c = 150 ~ 300 m/min.
- Extended tool life!
  Wear resistant ceramic coating and tough CBN substrate considerably extends tool life.
- Excellent surface finish!
  A consistent surface finish to values less than 6,3 Rz is easily achieved on both continuous and light interrupted cut applications.

Performance

Flank wear comparison



Work material: 15CrMo5 (Carburised steel) H_RC58-62
Insert type: CNGA 120408 NC-4
Cutting data: v_c = 250 m/min, f = 0,08 mm/rev, a_p = 0,1 mm, dry

Surface roughness comparison



Work material: 15CrMo5 (Carburised steel) H_RC58-62
Insert type: CNGA 120408 NC-4
Cutting data: v_c = 250 m/min, f = 0,1 mm/rev, a_p = 0,1 mm, dry

Application Range

Continuous Cutting



Interrupted Cutting



Recommended Cutting Conditions

v_c (m/min) 100 150 200 250 300	f (mm/rev)	d_{oc} (mm)
	0,03-0,2	0,03-0,3

Coolant ... Continuous cutting: dry or wet
Interrupted cutting: dry

Coated SUMIBORON BNC160

High precision machining with surface finishes down to 1,6 Rz possible thanks to smooth coating!

■ General

Use the copper coloured Sumiboron grade BNC160 to improve surface integrity as well as machining accuracy.
The TiCN based smooth surface ceramic coating and the newly developed Sumiboron substrate enhances edge strength and wear resistance making high precision machining with surface finishes as low as 1,6 Rz readily achievable.

This new grade is ideal for turning components that previously relied on precision grinding machines for final machining.

■ Advantages

- Excellent surface roughness!
  A consistent surface roughness is maintained for hours because wear at the boundary is so gradual.
- High Precision Machining
  High precision work previously ground, can now be turned.
- Enlarged scope of application!
  A wider range of hardened steels can be cut using Sumiboron the result being high productivity on close tolerance machining applications.

■ Performance

Continuous Cutting

Wear Resistance



Work material: 15CrMo5 (H_RC60)
Insert type: CNGA 120408 NC-4
Cutting data: v_c = 200 m/min, f = 0,1 mm/rev, a_p = 0,1 mm, dry

Machining Accuracy



Continuous Cutting

Surface Roughness



Work material: 15CrMo5 (H_RC60)
Insert type: CNGA 120408 NC-4
Cutting data: v_c = 200 m/min, f = 0,1 mm/rev, a_p = 0,1 mm, dry

■ Recommended cutting Conditions

v_c (m/min) 120 150 200 220 250	f (mm/rev)	d_{oc} (mm)
	0,03–0,2	0,03–0,35

Feed rate and nose radius are set such that the theoretical surface roughness is 1/2 to 1/3 of the required surface roughness.

Coolant ... Continuous cutting: Dry or Wet
Interrupted cutting: Dry

Most suitable for high speed finishing !

Excellent wear and fracture resistance!
Predictable tool life on a wide range of applications!

■ General

Our silver coloured Sumiboron insert grade BNC200 offers safe reliable cutting and predictable tool life.

The newly developed cutting material with enhanced edge strength is coated with TiAlN based ceramic for excellent wear resistance and realises extended tool life even when interrupted cutting.
This grade is especially suitable for medium speed machining of carburised surfaces.

■ Advantages

- Predictable tool life!
  Extended tool life is realised even when high speed cutting thanks to excellent wear resistance.
- Wide range of applications!
  Sumiboron is suitable for a wide range of applications eg. from low to high speed interrupted cutting.
- The newly developed brazing technology maximises edge strength making Sumiboron suitable for interrupted and continuous cutting.

■ Performance





- BNC200 features excellent wear resistance comparable with BNX10, plus outstanding fracture resistance.

■ Application Range



■ Recommended Cutting Conditions

v_c (m/min) 50 80 170 220	f (mm/rev)	d_{oc} (mm)
	0,03–0,25	0,05–0,5

Coolant ... Continuous cutting: dry or wet
Interrupted cutting: dry

Can be used in a wide range of applications from low to high speed operation.

Coated / Uncoated SUMIBORON

BNC300 / BN350

The ultimate grades BNC300 and BN350 in interrupted machining of hardened steel



General Features

- BNC300
  CBN substrate that emphasizes on toughness coupled with a highly wear resistant TiAlN based coating layer that has improved adhesion strength. With a good balance of fracture and wear resistance, stable and longer tool life can be achieve in interrupted cut or in a mixture of continuous and interrupted cutting.

- BN350
  SUMIBORON series highest fracture resistance and toughest CBN. Reliable grade for achieving stable tool life in heavy interrupted cutting conditions.

Characteristics

BNC300

- Stable and long tool life in interrupted cutting
  Achieving stable and long tool life in heavy interrupted cutting, with superior fracture resistance.
- Superior dimensional precision
  Good adhesion strength, TiAlN based, high wear resistance coating. Achieving superior dimensional precision even in interrupted cutting.
- Suitable for different types of workpieces
  Achieving significantly longer tool life even on workpieces that have a mixture of continuous and interrupted cutting.

BN350

- Stable and long tool life in interrupted cutting
  Stable and long tool life with superior fracture resistance, that prevents fractures which commonly occurs during interrupted cutting.

Performance

Continuous ~ Light Interrupted Machining
(Frequency of Interruption 50%)



Work material: 15CrMo5 (H_RC58-62)
Insert type: CNGA 120408 NC-4
Cutting data: v_c = 120 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, dry

Heavy Interrupted Machining
(Frequency of Interruption 100%)



Work material: 15CrMo5 (H_RC58-62)
Insert type: CNGA 120408 NU-2
Cutting data: v_c = 100 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, dry

Recommended Application Range

Coated SUMIBORON



Uncoated SUMIBORON



Recommended Cutting Conditions (BNC300, BN350)

v_c (m/min)	f (mm/rev)	d_{oc} (mm)
50 100 150 200 80 120	0,03–0,2	0,03–0,3

Coolant ... Interrupted cutting: dry

Coated CBN grade for ductile cast iron machining



General Features

Further improvements in the toughness of the sintered CBN and wear resistance from the application of a newly developed high-purity TiC binder. In addition, it demonstrates exceptional wear resistance by combining a ceramic coating with excellent heat resistance. High-speed and high-precision machining is achieved when finishing ductile cast iron. It also provides a long, stable tool life in machining high-strength ductile cast iron, special cast irons such as vermicular cast iron, and centrifugally cast iron.

Characteristics

- Achieves a Long, Stable Tool Life at v_c = 400 m/min
  Superior wear resistance, makes stable machining possible under high-speed conditions.
- Supports High-precision Machining
  Can maintain excellent dimensional tolerance and surface roughness.



Cutting Performance





Application Range



High Precision Machining



Recommended Cutting Conditions



f (mm/rev)	a_p (mm)
0,1–0,4	0,03–0,5

❋ Coolant ... Wet

Uncoated SUMIBORON BN7000

Uncoated CBN grade for high-speed finishing of cast iron, powdered metals, and difficult-to-machine materials!



■ General Features

Medium-grain CBN sintered to a high density to achieve the maximum content percentage.
Also delivers superior fracture resistance by increasing the binding strength between CBN particles. Provides stable, long tool life for high-speed finishing work with cast iron, powdered metals, and difficult-to-machine materials.



■ Characteristics

● Excellent for high speed finishing of Cast Iron!
Good wear and fracture resistance in high speed machining of Grey Cast Iron.

● High efficiency machining of powdered metal
With 4 different types of edge treatment, stable and long tool life can be achieved from machining of Sintered Alloys of any shape or hardness.

● Able to machine any Exotic Metals.
Long tool life can also be achieved for the machining of exotic materials such as Roll, HSS and Heat-Resistive Alloy etc.

■ Cutting Performance

Cast Iron Milling



Work material: GG25 (Pearlite)
Insert (Cutter): SNEW 1203 ADTR, (FMU 4100 R)
Cutting data: v_c = 500 ~ 2.000 m/min, f = 0,2 mm/rev
a_p = 0,3 mm, Wet

Turning of Powdered Metal



Work material: Sintered ferrous alloy, SMF4040 equivalent (HRB70, Interrupted Machining)
Insert type: CNGA 120408
Cutting data: v_c = 250 m/min, f = 0,1 mm/rev, a_p = 0,3 mm, Wet

Cast Iron Turning



Work material: GG30 (Pearlite)
Insert type: CNGA 120408 NU-2
Cutting data: v_c = 800 m/min, f = 0,15 mm/rev, a_p = 0,2 mm, Wet

■ Recommended Edge Treatment



● Negative Land

	α	w	r
Standard	15°	0,12	No
LF type	–	–	No
HS type	25°	0,12	Yes

Uncoated CBN grade for high precision and high efficiency machining of powdered metal

■ General Features

High density sintered material made of micro-grained CBN grains provide excellent sharpness and wear resistance for high quality surfaces in sintered alloy finishing.



The previous CBN left white blemishes on the finished surface whereas the BN7500 leaves a better, glossy surface finish.

■ Characteristics

- Excellent for finishing of powdered metal
  Excellent machined surface finish and surface appearance.

- Available with 5 different types of edge treatment for machining sintered alloys of any shape or hardness
  The LF type has a sharper edge designed specifically for machining sintered alloys with minimal burr and improved machining precision.
  The HS Type has a strengthened cutting edge for stable chipping resistance during interrupted cutting and finishing.

■ Cutting Performance

Surface Roughness Comparison



Work Material: Sintered ferrous alloy, SMF4040 equivalent (HRB70, Continuous cut)
Insert: CNGA 120408 LF-NU2
Cutting Data: v_c = 200 m/min, f = 0,1 mm/rev, a_p = 0,1 mm, wet

Burr Comparison (Average Height)



Work Material: Sintered ferrous alloy, SMF4040 equivalent (HRB70, Continuous cut)
Insert: CNGA 120408 LF-NU2
Cutting data: v_c = 200 m/min, f = 0,1 mm/rev, a_p = 0,1 mm, wet

● Feed and Burr Relationship



The LF Type without negative land has a cutting edge sharpness superior to the standard type and can control burrs better.

Work Material: VVT Facing
Insert: TNGA 160404 NU3
Cutting Data: v_c = 200 m/min, f = 0,1 mm/rev, a_p = 0,1 mm, wet

■ Recommended Edge Treatment



	α	w	R
Standard	15°	0,12 mm	No
LF type	α = 0°		
LE type	(No neg. Land)		
LS type	15°	0,07 mm	Yes
HS type	25°	0,05 mm	



Round honing cutting edge

Uncoated SUMIBORON BNS800

Solid CBN grade for high speed rough and finish machining of cast iron



General

Solid CBN grade with high content CBN and special binder phase provide high fracture toughness and high thermal conductivity.

Solid inserts for roughing with high depth of cut and also for finishing of cast iron and alloyed cast iron at wet and dry conditions.

Advantages

- High wear resistance !
  High CBN-content and special binder phase provide a excellent wear resistance and a tight dimensional control in finish machining.
- High edge stability !
  High thermal conductivity of BNS800 and high edge stability provide a long tool life at wet and dry machining.

Performance

Continuous Cutting



Work Material: Round Bar (GG30)
Insert: SNGN 090308
Cutting Data: v_c = 800 m/min, f = 0,2 mm/rev, a_p = 0,5 mm, dry

Interrupted Cutting



Work Material: Round Bar- 6V, grooved (GG30)
Insert: SNGN 090308
Cutting Data: v_c = 600 m/min, f = 0,3 mm/rev, a_p = 0,5 mm, dry

Application Example

Cylinder Bore	Brake Disc	Carbide Roll	Sprayed Face Bore
			
Tool life criteria: Finishing 	Tool life criteria: Breakage 	Tool life criteria: Breakage 	Tool life criteria: Breakage 

Tooling	Light Cut	Finishing
Grade	BNS800	
Insert	SNGN090308	
v_c	1000 m/min	
f	0,3 mm/rev	0,25 mm/rev
a_p	0,2 mm	
Coolant	wet	

Tooling	Finishing
Grade	BNS800
Insert	DNGN110312
v_c	600 m/min
f	0,3 mm/rev
a_p	0,5 mm
Coolant	dry

Tooling	Finishing
Grade	
Insert	RNGN090300
v_c	40 m/min
f	0,15 mm/rev
a_p	0,2 mm
Coolant	wet

Tooling	Roughing	Finishing
Grade	BNS800	
Insert	SNGN090312	SNGN090308
v_c	80 m/min	
f	0,04 mm/rev	0,03 mm/rev
a_p	~3 mm	0,5 mm
Coolant	wet	

SUMIBORON Binderless
NCB100

New

S

Cemented Carbide | Brittle Materials

Featttures

SUMIBORON Binderless is a polycrystalline cubic boron nitrid (CBN) that directly binds nanometer- or sub-micron-level CBN particles without binder materials.
Binderless CBN is harder and has better thermal conductivity. Therefore, it enables higher efficiency and longer tool life in machining of hard-to-cut materials, such as titanium alloy and cobalt-chromium alloy.

Mikrostructure of Sintered Body



Physical Properties

	Binderless CBN	Conventional CBN
CBN Content (%)	100	90–95
Binder Material	–	WC–Co
Hardness (GPa)	51–54	41–44
Thermal Conductivity (W/m·K)	180–200	100–120

SUMIBORON Binderless CBN

Advantages

– Higher efficient machining and longer tool life have been realized by the effects of higher hardness and thermal conductivity than conventional CBN grades.
– Achieves high precise machining and better surface integrity because of less adhesion by not containing any binder materials.
– Ideal tool material for high-efficient finishing of hard-to-cut materials, such as titanium alloy and cobalt-chromium alloy, cemented carbides and cermets.
– NBC100 is able to maintain excellent dimensional accuracy and surface roughness for a long period.
– Shows improved work efficiency and cost reduction by less frequency of exchanging inserts compared to conventional tool grades.

Application Range and Performance

Turning of Titanium Alloy (Ti-6Al-4V)



Turning of Cobalt-Chromium Alloy (Co-Cr)



SUMIBORON Binderless
NCB100

Turning of Titanium Alloy (Ti-6Al-4V)

Wear Resistance



Work Material: Ti-6Al-4V
Insert: CNGA 120408 NU
Cutting Conditions: v_c = 150 m/min, f = 0,15 mm/rev, a_p = 0,5 mm, wet

Surface Roughness



Work Material: Ti-6Al-4V
Insert: CNGA 120408 NU
Cutting Conditions: v_c = 150 m/min, f = 0,15 mm/rev, a_p = 0,5 mm, wet



Turning of Cobalt-Chromium Alloy (Co-Cr)

Wear Resistance



Work Material: Co-Cr
Insert: VNGA 160408 NU
Cutting Conditions: v_c = 60, 150 m/min, f = 0,1 mm/rev, a_p = 0,4 mm, wet

Surface Roughness



Work Material: Co-Cr
Insert: VNGA 160408 NU
Cutting Conditions: v_c = 60, 150 m/min, f = 0,1 mm/rev, a_p = 0,4 mm, wet



■ Recommended Cutting Conditions

Titanium Alloys

Min. - **Optimum** - Max.

Work Material		Grade	Cutting Conditions		
Composition	Hardness (HRC)		Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
Ti-6Al-4V	30–35	NCB100	0,1–**0,3**–0,5	0,05–**0,15**–0,20	50–**200**–300
Ti-5Al-5V-5Mo-3Cr	32–38	NCB100	0,1–**0,3**–0,5	0,05–**0,10**–0,20	50–**150**–250
Ti-10V-2Fe-3Al	32–38	NCB100	0,1–**0,3**–0,5	0,05–**0,10**–0,20	50–**150**–250

Cobalt-Chromium Alloys

Min. - **Optimum** - Max.

Work Material		Grade	Cutting Conditions		
Composition	Hardness (HRC)		Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
Co-30Cr-5Mo	35–45	NCB100	0,10–**0,15**–0,30	0,05–**0,15**–0,20	50–**200**–300

Carbides

Min. - **Optimum** - Max.

Work Material		Grade	Cutting Conditions		
Composition	Hardness (HRC)		Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
WC-20Co	<85	NCB100	0,03–**0,10**–0,20	0,03–**0,10**–0,20	5–**20**–40

SUMIDIA BINDERLESS NPD10 is recommended for: > 85 HRA

Other Work Materials

Min. - **Optimum** - Max.

Work Material		Grade	Cutting Conditions		
Composition	Hardness (HRC)		Depth of Cut (mm)	Feed Rate (mm/rev)	Cutting Speed (m/min)
Pure Titanium	130–230	NCB100	0,1–**0,3**–0,5	0,05–**0,10**–0,20	100–**250**–400
Cermet	1.000–1.500	NCB100	0,1–**0,2**–0,3	0,05–**0,10**–0,20	10–**30**–50

Production Process

General

Since 1970s, Sumitomo has pioneered the development of sintered cubic boron nitride (CBN) and sintered diamond (PCD) tools successfully used in the tool making industries. These tool materials can be epoch-making in a sence of broadening the cutting application range.

Production Process

In the production process of **SUMIBORON / SUMIDIA**, CBN powder / diamond powder is firstly synthesized under the ultra - high pressure, and secondly, the synthesized crystalline grains are sintered.

Fig. 2 shows a diagram of high temperature high pressure apparatus for processing the ultra - high pressure sintering operation.
This apparatus is basically composed of a piston and a cylinder to generate ultra - high pressure as high as 5000 N/mm^2 with a special device. The piston and cylinder are made of cemented carbide.

To manufacture final products round discs of SUMIBORON and SUMIDIA material are cut into specific shapes and brazed on to tool bodies made of cemented carbide, or steel, etc., and after that finished by grinding the edge.
In another process the final product can be obtained only by cutting blanks and finishing them.

Fig. 1



Fig. 2





SumiBoron / SumiDia Grinding Method

Items		SumiBoron	SumiDia
Grinding machine	–	1) Carbide grinding machine is applicable. 2) R Pointer should be used. 3) Should be wet grinding.	1) Special-purpose high rigidity grinding machine is desirable. 2) Be sure of applying with wet system.
Wheel	Abrasive	Diamond	Diamond
	Grain size	D 25 - medium, D20 - fine (#400–800)	Rough grinding: D 35 (#400 mesh) Finish grinding: D 25 (#800–1500 mesh)
	Bond	Resinoid or vitrified	Special-purpose metal bond for diamond sintered tool or vitrified
	Concentration	100	100–125
	Dressing	Use #400 WA stick	Execute dressing with a WA stick of about 400 mesh.
Grinding condition	Wheel speed	800–1000 m/min.	800–1000 m/min.
	Table cycle	30–60 cycles/min.	30–60 cycles/min.
	Grinding oil	Water soluble grinding coolant oil	Water soluble grinding coolant (Solution type)
Others	–	1) Check chipping of the cutting edge with microscope after finishing. 2) Blank surface cut by EDM should be ground more than 0,05 mm	1) Rake surface is lapped generally 2) Inspect with microscope of magnification of 30–50 times if there is edge chipping. 3) Edge treatment of tool should be sharp for cutting non-ferrous metals. 4) Remove the wire-cut surface of blank by 0,05 mm or more in grinding operation.

General Features

SUMIDIA sintered diamond series has 3 grades (DA1000, DA150, DA90) with individual features depending on the optimum combination of diamond particle size and binder, as well as the NPD10 grade (nano-polycrystalline diamond) where nano-order diamond particles are directly bound with high strength without using binders.
This series is suited to a wide range of applications from machining of aluminium alloy to machining of hard brittle materials and cemented carbide.

Series • Features • Application

Grade		Features	Application	Average size of Diamond grains (μm)	Hardness Hv	TRS (GPa)
SUMIDIA	DA1000	High density sintered material made of ultra-fine diamond particles that demonstrates optimum wear resistance and excellent edge sharpness.	• High silicon aluminum alloy cutting • Rough, interrupted and finishing of Al-alloy • Wood or wooden board cutting • Non-ferrous metal finishing (aluminium, copper alloy)	< 0,5	50 ~ 60	≈ 2,60
SUMIDIA	DA150	Micro-grained sintered diamond grade with strong diamond-to-diamond bonding. It is suitable for the machining of non-ferrous metals and other very hard materials.	• Non-ferrous metal finishing (aluminium, copper alloy) • Green or semi-sintered carbide & ceramic roughing • FRP, hard rubber & carbon cutting • Wooden or Inorganic Material Board Cutting	5	50 ~ 60	≈ 1,95
SUMIDIA	New **DA90**	Contains coarser diamond particles than other grades, giving it good wear resistance suitable for the machining of carbides and high-silicon aluminium. Shows the highest diamond content for excellent wear resistance.	• Machining of high-silicon • Machining of aluminium composite (MMC) • Green or semi-sintered carbide & ceramic roughing • Machining of sintered ceramics/stone/rock	< 50	50 ~ 60	≈ 1,10
SUMIDIA Binderless	**NPD10**	A 100% diamond grade made by nano-level diamond grains with direct conversion sintering. Has the highest wear resistance and fracture resistance and the best edge sharpness.	• Surface finishing of carbide • Machining brittle materials (ceramics)	< 0,05	120 ~ 130	≈ 3,15

Application Range

Aluminium

Machinability	Work Material	Turning: Roughing	Turning: Finishing	Milling	Example Part
Good ↓ Difficult	Sintered aluminium	DA1000	DA1000	DA1000	Cylinder liner
	Die cast aluminium (ADC12)	DA1000	DA1000	DA1000	Transmission case, oil pan cylinder block, aluminium wheel
	Low silicon (AC2B-T6, AC4C-T6)	DA1000	DA1000	DA1000	Cylinder head
	High silicon (T6)	DA1000	DA150	DA1000	Cylinder block

Non-Aluminium

Machinability	Work Material	Turning: Roughing	Turning: Finishing	Milling	Example Part
Good ↓ Difficult	Non-ferrous sintered alloy	DA1000	DA1000	DA1000	Bushing
	Gunmetal carbon	DA1000	DA1000	DA1000	Connection rod
	Carbide	DA90	NPD10	NPD10	Punches, dies, rolls
	Iron combined	DA90	DA90	DA150	Cylinder block, bearing cap

Cutting Performance

Continuous Cutting



Work Material: MMC (Al-20% SIC)
Insert: CNMX 120408, Holder: PCLN2525
Cutting Cond.: v_c = 350 m/min, f = 0,2 mm/rev, a_p = 0,18 mm, wet

Continuous Cutting



Work Material: Cemented Carbide (87 HRA)
Insert: DCMW 070204 NF
Cutting Cond.: v_c = 20 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, wet

Continuous Cutting



Work Material: Cemented Carbide (91 HRA)
Insert: DCMW 11T304 RH (NPD10)
DCMW 11T304 NF (DA90)
Cutting Cond.: v_c = 20 m/min, f = 0,05 mm/rev, a_p = 0,05 mm, dry

Recommended Cutting Conditions

Cutting Conditions \ Work Materials		Aluminium Alloys	Copper Alloy	Reinforced Plastics	Wood or Organic Materials	Carbide	Carbon
Cutting Speed	v_c (m/min)	~ 3.000	~ 1.000	~ 1.000	~ 4.000	10 ~ 30	100 ~ 600
Feed rate	f (mm/rev)	~ 0,2	~ 0,2	~ 0,4	~ 0,4	~ 0,2	~ 1,0
Depth of cut	a_p (mm)	~ 3,0	~ 3,0	~ 2,0	–	~ 0,5	~ 2,0

Nano-Polycristalline Diamond

General Features

Nano-polycristalline diamond is a type of polycristalline diamond, produced by directly binding nano-level diamond grains without using any binders.
This material is unique to our company and as compared to conventional diamond grades containing binders, it exhibits higher strength, excellent wear resistance and fracture resistance.
SUMIDIA Binderless is the series of tools with cutting edges made from this high performance nano-polycristalline diamond.

Micro-Structure Comparison

Nano-Polycristalline Diamond
SEM Structure



Diamond particle average grain diameter
(30 - 50 nm)

Conventional PCD
SEM Structure

Diamond particle average grain diameter
(1 - 10 μm)

Hardness



SUMIDIA Binderless

Application Examples

- Ballnose Endmill / Radius Endmill (Carbide Machining)



- Indexable Inserts (Carbide Machining)

General Features

NPD10 is made from high-hardness nano-polycrystalline diamond.
This is a pure diamond material, but unlike single-crystal diamonds, it has no anisotropy.
It achieves extended tool life and machining accuracy superior to conventional diamond tools when machining hard brittle materials such as cemented carbide.
DA90 is a polycrystalline diamond grade in which coarse diamond particles have been sintered to form a dense structure. The high diamond content, with high wear resistance, makes it ideal for roughing of cemented carbide and hard brittle material.
Optimized design and mass production technology have been developed, achieving the same performance as conventional tools with higher cost performance.

Characteristics

- Ideal for Finishing of Hard Brittle Materials Including Cemented Carbide (NPD10)
  High-precision cutting of cemented carbide thanks to the outstanding wear resistance of nano-polycrystalline diamond.
- Superior Dimensional Tolerance Maintained for a Long Time (NPD10)
  Tool replacement count can be drastically reduced compared to conventional diamond tools, enabling work efficiency to be improved and total costs to be reduced.
- Ideal for Roughing of Hard Brittle Materials Including Cemented Carbide (DA90)
  Stable tool life in sintered surface machining of cemented carbide and roughing of hard brittle materials thanks to the outstanding wear resistance of the coarse-grained polycrystalline diamond.
- Uses SUMIDIA NF Insert (DA90)
  Optimized design and mass production technology have been developed, achieving the same performance as conventional tools with higher cost-performance.

Applicable Range (Cemented Carbide)



Applications of NPD10 and DA90 (Cemented Carbide)

Grade	SUMIDIA Binderless NPD10		SUMIDIA DA90	
Dimensional Tolerance	◎	Best	△	The first recommendation is NPD10
Tool Life (Wear Resistance)	◎	Best $a_p \le 0,2$ mm, $f \le 0,1$mm/rev	○	ap ≥ 0,2 mm can also be used
Sintered Surface Machining of Cemented Carbide	×	Impossible	◎	Best
Machined Surface Quality	◎	Best	△	The first recommendation is NPD10

Recommended Cutting Conditions (Carbide Machining)

Work Material				Grade	Cutting Conditions		
Class		Hardness (HRA)	SEI Grades		Cutting Speed v_c (m/min)	Feed Rate f (mm/rev)	Depth of Cut a_p (mm/rev)
VM, VC	40	≥ 88	G5, D2	NPD10	5–**15**–20	0,03–**0,05**–0,07	0,03–**0,05**–0,07
VM, VC	70, 60, 50	83 – <88	G7, G6	NPD10	5–**20**–30	0,03–**0,10**–0,20	0,03–**0,10**–0,20
VM, VC	–	≥ 83	G7, G6, G5, D2	DA90	5–**20**–30	0,03–**0,10**–0,20	0,03–**0,20**–0,50

Min. - **Optimum** - Max., Cutting conditions: NPD10: dry, DA90: wet

Machining Precision of NPD10)

Boring of Carbide VM30 (91HRA)





NPD10 has no dimension variation even with cutting distance of 1.100 m.

Work Material: Carbide VM30 (91HRA)
Insert: DCMW 11T304 RH
Cutting Conditions: v_c = 20 m/min, f = 0,05 mm/rev, a_p = 0,05 mm, dry

Wear Resistance of DA90

External Machining of Cemented Carbide VC50 (87HRA)



Work Material: Carbide VC50 (87HRA)
Insert: DCMW 070204 NF
Cutting Conditions: v_c = 20 m/min, f = 0,1 mm/rev, a_p = 0,2 mm, wet

General Features

SumiDia DA1000 is a high density, ultra fine grained sintered PCD with high toughness similar to that of cemented carbides.

SumiDia DA1000, with its great improvement in fracture resistance, eliminates the breakage problems faced by conventional PCD tools especially during the milling of Aluminium alloys and achieves a longer and more stable tool life.

Furthermore, the NF type inserts makes it even more cost effective.

Cutting Performance



Work Material: 17 % Al-Si alloy
Insert: TPGW 160308
Cutting conditions: v_c= 1.000 m/min, f = 0,15 mm/rev, a_p = 0,2 mm, wet

Wear Resistance in Turning Application



Work Material: 17 % Si-Al alloy
Insert: TPGN 160304
Cutting Conditions: v_c=800 m/min, f = 0,12 mm/rev, a_p=0,5 mm, wet

NF Type Inserts

General Features

- **Total Cost Effectiveness with High Performance and Lower Price**
  - Optimum design utilizing improved mass production techniques provides a relatively lower cost.
  - Regrindable type results in huge total cost reduction.

- **Wide Application Range**
  - Wide range of stocked items for small hole boring, OD turning to milling processes.
  - Negative and positive type inserts that are applicable on standard lever-lock, pin-lock type holders.

Efficiency

SumiDia NF-type inserts preserve the excellent basic performance of DA1000 while achieving high cost performance through optimal design and development of mass production technology. These inserts achieve the high performance of SUMIDIA DA1000, including excellent fracture resistance, wear resistance and smooth work material surface finishing.

● NF-Type Edge



(NF-type is precision ground just like conventional inserts.)

Application Examples

Milling of Aluminum Oil Pump Cover



Work Material: ADC12 (Al-12% Si alloy)
Insert: TEEN32R NF
Cutting conditions: v_c = 3.000 m/min, f_t = 0,06 mm/rev, a_p = 0,2 mm

Boring of Aluminum Valve Bore



Work Material: ADC12 (Al-12% Si alloy)
Insert: TPGN 110304 NF
Cutting conditions: v_c = 530 m/min, f = 0,05 mm/rev, a_p = 0,2 mm

SUMIDIA Inserts
Break Master N-LD / -GD Type

Characteristics

- Provides excellent chip control in semi finishing and finishing of aluminium alloy.
- Solves chip control problems and dramatically improves work efficiency.
- Achieves stable tool life by employing high toughness grade DA1000.

Applications Range

Wrought Aluminium Alloy (A6061)



Casted Aluminium Alloy (ADC12)



NLD Type Chipbreaker

Achieves excellent chip control for finishing.

NGD Type Chipbreaker

Achieves excellent chip control for semi finishing.

Application Examples

Internal Turning of Machine Component

Provides good chip control in small-depth cutting of wrought Al alloy.



Breakmaster **NLD** type

Without chip breaker

Work Material: A6061
Insert: VCMT110302 **NLD** NF (DA1000)
Cutting Conditions: v_c = 200 m/min, f = 0,20 mm/rev, a_p = 0,10 mm, wet

Internal Turning of Transmission Component

Offers good chip control in casted material.
Small chips - easy to remove.



Breakmaster **NGD** type

Without chip breaker

Work Material: ADC12
Insert: TPMT110304 **NGD** NF (DA1000)
Cutting Conditions: v_c = 400 m/min, f = 0,23 mm/rev, a_p = 1,20 mm, wet

General Features

Economy One-Use Insert

- Similar to SumiBoron One-Use type inserts

With Built-in Chipbreaker for Effective Chip Removal

- Solving chip control problems and improving efficiency with DM-type chipbreaker.

Extensive Insert Range for External and Facing Operation

- 80° and 55° diamond shaped inserts are added to expand the application range of this series.

Application Range

Triangular Type Insert (Boring)



(Internal turning, Wet cut, Work material: ADC12)

CCMT/DCMT Type (External Turning & Facing)



(Internal turning, Wet cut, Work material: ADC12)



Chip Control

Break Master

No Chipbreaker

Application

Machining Details	Cutting Conditions	Results
Work Material: AC2A-T6 Operation: Internal Boring	v_c = 300 m/min f = 0,06 mm/rev a_p = 0,35 mm Wet cut	Surface finish of the bore hole was less than Ra = 1 µm. Chips formed was of a uniform curl of about 2 mm in length. There was almost no chips left inside the bore hole.

Recommended Conditions

Boring (Triangular Insert)

Feed Rate	Depth of Cut	Type
–0.15 mm/rev.	−0,7 mm	Wet cut

External Copying (55°, 80° Diamond Shaped Inserts)

Feed Rate	Depth of Cut	Type
–0.15 mm/rev.	−0,5 mm	Wet cut

For facing process, D.O.C. should be less than 0,4 mm

Series

External Turning & Facing		Boring	
	CCMT 0602_ _ L/R-DM NU		TPMT 0802_ _ L/R-DM NU
	CCMT 09T3_ _ L/R-DM NU		TPMT 0902_ _ L/R-DM NU
	DCMT 0702_ _ L/R-DM NU		TPMR 1103_ _ L/R-DM NU(*)
	DCMT 11T3_ _ L/R-DM NU		TPMR 1603_ _ L/R-DM NU(*)

(*) Stock in Japan
Delivery on request

SUMIBORON / SUMIDIA
Indexable Inserts & Tools

M1–M62

M

Insert Identification

Regrindable Type

CNMA 120408 B

① Insert ISO Code: ISO ⇨ C2/C3

② Additional Information: Chart 1

Chart 1

Symbol	Description
B	Full-top CBN insert

One-Use Type

CNGG 120408 N-SV NC WG 4

① Insert ISO Code: ISO ⇨ C2/C3

② Chip Breaker: Chart 2

③ One-Use Type: Chart 3

④ Wiper Insert: Chart 4

⑤ No. of Cutting Edges: Chart 5

Chart 2

Symbol	Description
–	Standard Type
LF LE	Sharp cutting edge
LT	Small edge treatment type
LS	Low cutting force
ES	High efficiency type
HS	Strong cutting edge
N-FV N-LV N-SV	Chipbreaker Type

Chart 3

Symbol	One-Use Type	Grade
NC	Coated SUMIBORON	BNC2010, 2020 BNC100, 160 BNC200, 300 BNC500
NU	Uncoated CBN	BNX10, 20 BN1000, 2000 BN350, BN7000, 7500
NS		BNX25

Chart 4

Symbol	Wiper Insert
WG	Finishing 0,05 ≤ f ≤ 0,20
WH	High feed cutting 0,20 ≤ f < 0,40
W	Surface Roughness Standard: R_z 1,6~3,2µm

f : Feed Rate (mm/rev)

Chart 5

Symbol	No. of Cutting Edges	Type
–	1 cutting edge	Single-corner
2	2 cutting edges	Multi-corner
3	3 cutting edges	
4	4 cutting edges	
6	6 cutting edges	

Regrindable Type

CNMA 120408 RH

① Insert ISO Code: ISO ⇨ C2/C3

② Additional Information: Chart 1

Chart 1

Symbol	Description
RH	Honing specification (treated cutting edge)

One-Use Type

CNMA 120408 N-LD NF

① Insert ISO Code: ISO ⇨ C2/C3

② Additional Information: Chart 2

③ Type: Chart 3

Chart 2

Symbol	Description
N-LD	Chipbreaker type (neutral)
N-GD	
R-DM	Chipbreaker type (right handed)
L-DM	Chipbreaker type (left handed)

Chart 3

Symbol	Description
NF	NF insert ⇨ L26
NU	One use insert

80° Diamond Type | 7° Relief With Insert Hole

Dimensions (mm)				
CC_ _	L	IC	S	D_1
0602--	6,45	6,35	2,38	2,8
09T3--	9,7	9,525	3,97	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

Coated

CCGT / CCGW

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	H Coated CBN BNC2010	H Coated CBN BNC2020	H Coated CBN BNC100	H Coated CBN BNC160	H Coated CBN BNC200	H Coated CBN BNC300	K Coated CBN BNC500	H Uncoated CBN BN1000	H Uncoated CBN BN2000	H Uncoated CBN BNX10	H Uncoated CBN BNX20	H Uncoated CBN BNX25	H Uncoated CBN BN250	H Uncoated CBN BN300	H Uncoated CBN BN350	H Uncoated CBN BN700	K PM Uncoated CBN BN7000	K PM Uncoated CBN BN7500	K Uncoated CBN BNS800	S Binderless CBN NCB100	N Uncoated PCD DA90	N Uncoated PCD DA150	N Uncoated PCD DA1000	N Binderless Sumidia NPD10
Break Master - FV, LV CBN with chipbreaker	with 2 CBN cutting edges	CCGT 060204 N-FV NC2	0,4	●	●		●																			
		CCGT 09T304 N-FV NC2	0,4	●	●		●	●																		
		CCGT 09T308 N-FV NC2	0,8	●	●		●	●																		
		CCGT 09T304 N-LV NC2	0,4	●	●		●	●																		
		CCGT 09T308 N-LV NC2	0,8	●	●		●	●																		
Standard - Normal cut geometry	with 2 CBN cutting edges	CCGW 060202 NC2	0,2	●	●	●	●	●																		
		CCGW 060204 NC2	0,4	●	●	●	●	●	●	●																
		CCGW 060208 NC2	0,8		●			●	●																	
		CCGW 09T302 NC2	0,2		●			●																		
		CCGW 09T304 NC2	0,4	●	●	●	●	●	●	●																
		CCGW 09T308 NC2	0,8	●	●	●	●	●	●	●																
	(Wiper Type)	CCGW 09T304 NC-W2	0,4			●	●	●																		
		CCGW 09T308 NC-W2	0,8			●	●	●																		
		CCGW 09T304 NC-WG2	0,4	●	●		●	●																		
		CCGW 09T308 NC-WG2	0,8	●	●		●	●																		
		CCGW 09T304 NC-WH2	0,4	●	●		●	●																		
		CCGW 09T308 NC-WH2	0,8	●	●		●	●																		
LE - Type Low cutting force	with 2 CBN cutting edges	CCGW 060202 LE-NC2	0,2	●																						
		CCGW 060204 LE-NC2	0,4	●																						
		CCGW 09T302 LE-NC2	0,2	●																						
		CCGW 09T304 LE-NC2	0,4	●																						
		CCGW 09T308 LE-NC2	0,8	●																						
LT - Type Sharp cutting edge	with 2 CBN cutting edges	CCGW 060202 LT-NC2	0,2		●																					
		CCGW 060204 LT-NC2	0,4		●																					
		CCGW 09T302 LT-NC2	0,2		○																					
		CCGW 09T304 LT-NC2	0,4		●																					
		CCGW 09T308 LT-NC2	0,8		●																					
LS - Type Low cutting force	with 2 CBN cutting edges	CCGW 060202 LS-NC2	0,2			●	●	●																		
		CCGW 060204 LS-NC2	0,4			●	●	●																		
		CCGW 09T304 LS-NC2	0,4			●	●	●	●																	
		CCGW 09T308 LS-NC2	0,8				●	●	●																	
HS - Type Strong cutting edge	with 2 CBN cutting edges	CCGW 09T304 HS-NC2	0,4		●			●	●																	
		CCGW 09T308 HS-NC2	0,8		●			●	●																	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

80° Diamond Type — 11° Relief, With Insert Hole

Dimensions (mm)				
CP--	L	IC	S	D_1
0602--	6,45	6,35	2,38	2,8
0802--		7,94	2,38	3,4
0903--		9,525	3,18	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

Coated

CPGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		CPGW 080202 NC2	0,2	❍	❍																					
		CPGW 080204 NC2	0,4	❍	❍																					
		CPGW 090302 NC2	0,2	❍	❍																					
		CPGW 090304 NC2	0,4	❍	❍																					

Uncoated

CPMW ●●●●●●

● M-Class SumiDia (PCD, NF Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		CPMW 060202 NF	0,2																						●	
		CPMW 060204 NF	0,4																						●	
		CPMW 060208 NF	0,8																						●	

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 7° Relief With Insert Hole

Uncoated

Dimensions (mm)				
CC_ _	L	IC	S	D_1
0602--	6,45	6,35	2,38	2,8
09T3--	9,7	9,525	3,97	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

CCGT / CCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	H Coated CBN BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	K Coated CBN BNC500	H Uncoated CBN BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	K Uncoated CBN BN7000	K PM BN7500	BNS800	S Binderless CBN NCB100	N Uncoated PCD DA90	DA150	DA1000	N Binderless Sumidia NPD10
Break Master - FV, LV CBN with chipbreaker	with 2 CBN cutting edges	**CCGT 060204 N-FV NU2**	0,4									●														
		CCGT 09T304 N-FV NU2	0,4									●														
		CCGT 09T308 N-FV NU2	0,8									●														
		CCGT 09T304 N-LV NU2	0,4									●														
		CCGT 09T308 N-LV NU2	0,8									●														
	with 2 CBN cutting edges	**CCGW 060204 NU2**	0,4																		●					
		CCGW 060208 NU2	0,8																		●					
		CCGW 09T304 NU2	0,4								●	●	▲	●		▲	▲	●			●					
		CCGW 09T308 NU2	0,8								●	●		●		▲	▲	●			●					
	(Wiper Type)	**CCGW 09T304 NU-WG2**	0,4									●														
		CCGW 09T308 NU-WG2	0,8									●														
		CCGW 09T304 NU-WH2	0,4									●														
		CCGW 09T308 NU-WH2	0,8									●														
LF - Type Sharp cutting edge	with 2 CBN cutting edges	**CCGW 09T304 LF-NU2**	0,4																		●					
		CCGW 09T308 LF-NU2	0,8																		●					
HS - Type Strong cutting edge	with 2 CBN cutting edges	**CCGW 09T304 HS-NU2**	0,4																		●					
		CCGW 09T308 HS-NU2	0,8																		●					

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 7° Relief / With Insert Hole

Uncoated

Dimensions (mm)				
CC--	L	IC	S	D_1
0602--	6,45	6,35	2,38	2,8
09T3--	9,7	9,525	3,97	4,4
1204--	12,9	12,7	4,76	5,5

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

CCGW ●●●●●●

● G-Class SumiBoron (CBN, Regrindable Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		CCGW 09T304	0,4											●			▲										
		CCGW 09T308	0,8											●													

● G-Class SumiBoron (CBN, One-Use Type)

		CCGW 060204 NS	0,4												●												
		CCGW 060208 NS	0,8												●												
		CCGW 09T304 NS	0,4												●												
		CCGW 09T308 NS	0,8												●												
		CCGW 060202 NU	0,2									●		●					▲	●							
		CCGW 060204 NU	0,4								●	●	▲	●		▲	▲	●	▲	●							
		CCGW 060208 NU	0,8									●		●		▲			▲	●							
		CCGW 09T302 NU	0,2											●													
		CCGW 09T304 NU	0,4								●		▲	●		▲	▲	●	▲	●							
		CCGW 09T308 NU	0,8								●	●	▲	●		▲	▲	●	▲	●							
		CCGW 120408 NU	0,8								●		▲	●													

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

CC_ _ Type 7° pos. Inserts

80° Diamond Type | 7° Relief With Insert Hole

Uncoated

Dimensions (mm)				
CC_ _	L	IC	S	D_1
0602--	6,45	6,35	2,38	2,8
09T3--	9,7	9,525	3,97	4,4

- H Hardened Steel
- K Cast Iron
- N Non-Ferrous Metal
- S Exotic Alloy
- PM Sintered Component
- Carbide/Hard Brittle Material

CCMT / CCMW

Grade groups: H Coated CBN: BNC2010, BNC2020, BNC100, BNC160, BNC200, BNC300; K Coated CBN: BNC500; H Uncoated CBN: BN1000 – BN700; K / PM Uncoated CBN: BN7000, BN7500; S: BNS800; Binderless CBN: NCB100; N Uncoated PCD: DA90, DA150, DA1000; Binderless Sumidia: NPD10

● M-Class SumiDia (PCD, Regrindable Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		CCMT 060202	0,2																						●		
		CCMT 060204	0,4																						●		
		CCMT 09T302	0,2																						●		

● M-Class SumiDia (PCD, NF Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		CCMT 060201 NF	0,1																							●	
		CCMT 060202 NF	0,2																							●	
		CCMT 060204 NF	0,4																							●	
		CCMT 09T301 NF	0,1																							●	
		CCMT 09T302 NF	0,2																							●	
		CCMT 09T304 NF	0,4																							●	
		CCMT 09T308 NF	0,8																							●	

● M-Class SumiDia (PCD, One-Use "Break Master" Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
Break Master - DM 		CCMT 060202 L-DM NU	0,2																								
		CCMT 060204 L-DM NU	0,4																						●		
		CCMT 09T302 L-DM NU	0,2																								
		CCMT 09T304 L-DM NU	0,4																						○		
Break Master - DM 		CCMT 060202 R-DM NU	0,2																						○		
		CCMT 060204 R-DM NU	0,4																						○		
		CCMT 09T302 R-DM NU	0,2																						○		
		CCMT 09T304 R-DM NU	0,4																						●		
Break Master - LD 		CCMT 060202 N-LD NF	0,2																							○	
		CCMT 060204 N-LD NF	0,4																							○	
		CCMT 09T302 N-LD NF	0,2																							○	
		CCMT 09T304 N-LD NF	0,4																							○	
		CCMT 09T308 N-LD NF	0,8																							○	
Break Master - GD 		CCMT 060202 N-GD NF	0,2																							○	
		CCMT 060204 N-GD NF	0,4																							○	
		CCMT 09T302 N-GD NF	0,2																							○	
		CCMT 09T304 N-GD NF	0,4																							○	
		CCMT 09T308 N-GD NF	0,8																							○	

● M-Class SumiDia (PCD, Binderless)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		CCMW 03X102 RH	0,2																								○
		CCMW 03X104 RH	0,4																								○
		CCMW 04X102 RH	0,2																								○
		CCMW 04X104 RH	0,4																								○
		CCMW 060202 RH	0,2																								○
		CCMW 060204 RH	0,4																								○
		CCMW 09T302 RH	0,2																								○
		CCMW 09T304 RH	0,4																								○
		CCMW 09T308 RH	0,8																								○

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

L4, L5 Edge Specification of SUMIBORON Inserts

SUMIBORON / SUMIDIA
Indexable Inserts

80° Diamond Type | 0° Relief, With Insert Hole

Dimensions (mm)				
CN_ _	L	IC	S	D_1
1204--	12,9	12,7	4,76	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

Coated

CNGA / CNGG

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	H Coated CBN BNC2010	H Coated CBN BNC2020	H Uncoated CBN BNC100	H Uncoated CBN BNC160	H Uncoated CBN BNC200	H Uncoated CBN BNC300	K Uncoated CBN BNC500	H Uncoated CBN BN1000	H Uncoated CBN BN2000	H Uncoated CBN BNX10	H Uncoated CBN BNX20	H Uncoated CBN BNX25	H Uncoated CBN BN250	H Uncoated CBN BN300	H Uncoated CBN BN350	H Uncoated CBN BN700	K PM BN7000	K PM BN7500	K PM BNS800	S Binderless CBN NCB100	N Uncoated PCD DA90	N Uncoated PCD DA150	N Uncoated PCD DA1000	N Binderless Sumidia NPD10
 Standard - Normal cut geometry	 with 4 CBN cutting edges	**CNGA 120402 NC4**	0,2	❍	❍																						
		CNGA 120404 NC4	0,4	●	●	●	●	●	●	❍																	
		CNGA 120408 NC4	0,8	●	●	●	●	●	●	❍																	
		CNGA 120412 NC4	1,2	●	●	●	●	●	●	❍																	
	 (Wiper Type)	**CNGA 120404 NC-W4**	0,4			▲	▲	▲		▲																	
		CNGA 120408 NC-W4	0,8				▲	▲		▲																	
		CNGA 120412 NC-W4	1,2																								
		CNGA 120404 NC-WG4	0,4	●	●		●	●																			
		CNGA 120408 NC-WG4	0,8	●	●		●	●																			
		CNGA 120412 NC-WG4	1,2	●	●		●	●																			
		CNGA 120404 NC-WH4	0,4	❍	●		●	●																			
		CNGA 120408 NC-WH4	0,8	●	●		●	●																			
		CNGA 120412 NC-WH4	1,2	●	●		●	●																			
 **LE** - Type Low cutting force	 with 2 CBN cutting edges	**CNGA 120404 LE-NC2**	0,4	●																							
		CNGA 120408 LE-NC2	0,8	●																							
		CNGA 120412 LE-NC2	1,2	❍																							
 **LT** - Type Sharp cutting edge	 with 2 CBN cutting edges	**CNGA 120402 LT-NC2**	0,,2		❍																						
		CNGA 120404 LT-NC2	0,4		●																						
		CNGA 120408 LT-NC2	0,8		●																						
		CNGA 120412 LT-NC2	1,2		●																						
 **LS** - Type Low cutting force	 with 2 CBN cutting edges	**CNGA 120404 LS-NC2**	0,4			●	●	●	❍																		
		CNGA 120408 LS-NC2	0,8			●	●	●	❍																		
		CNGA 120412 LS-NC2	1,2			●	●	●	❍																		
 **ES** - Type Crater wear stability	 with 4 CBN cutting edges	**CNGA 120404 ES-NC4**	0,4		●																						
		CNGA 120408 ES-NC4	0,8		●																						
		CNGA 120412 ES-NC4	1,2		●																						
 **HS** - Type Strong cutting edge	 with 2 CBN cutting edges	**CNGA 120404 HS-NC2**	0,4	●	●		●	●	●																		
		CNGA 120408 HS-NC2	0,8	●	●		●		●																		
		CNGA 120412 HS-NC2	1,2	●	●		●	●	●																		
Break Master - FV, LV, SV  CBN with chipbreaker	 with 4 CBN cutting edges	**CNGG 120404 N-FV NC4**	0,4	●	●		❑	●																			
		CNGG 120408 N-FV NC4	0,8	●	●		❑	●																			
		CNGG 120412 N-FV NC4	1,2	●	❍		❑	●																			
		CNGG 120404 N-LV NC4	0,4	❍	●		❑	●																			
		CNGG 120408 N-LV NC4	0,8	●	●		●	●																			
		CNGG 120412 N-LV NC4	1,2	●	●		●	●																			
		CNGG 120408 N-SV NC4	0,8		●			●																			
		CNGG 120412 N-SV NC4	1,2		●			●																			

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 0° Relief | With Insert Hole

Uncoated

Dimensions (mm)				
CN_ _	L	IC	S	D_1
1204--	12,9	12,7	4,76	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

CNGA / CNGM

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H Coated						K	H Uncoated CBN									K PM			S Binderless CBN	N Uncoated PCD			Binderless Sumidia
	with 2 CBN cutting edges	**CNGA 120404 NS2**	0,4												●												
		CNGA 120408 NS2	0,8												●												
		CNGA 120412 NS2	1,2												●												
		CNGA 120404 NU2	0,4									●		●		▲	▲	●			○						
		CNGA 120408 NU2	0,8								●	●	▲	●		▲	▲	●	▲	●	●						
		CNGA 120412 NU2	1,2								●	●	▲	●			▲	●			○						
		CNGA 120404 NU-W2	0,4								▲	▲															
		CNGA 120408 NU-W2	0,8								▲	▲															
	(Wiper Type)	**CNGA 120404 NU-WG2**	0,4									●															
		CNGA 120408 NU-WG2	0,8									●															
		CNGA 120412 NU-WG2	1,2									●															
		CNGA 120404 NU-WH2	0,4									●															
		CNGA 120408 NU-WH2	0,8									●															
		CNGA 120412 NU-WH2	1,2									●															
LF - Type Sharp cutting edge	with 2 CBN cutting edges	**CNGA 120404 LF-NU2**	0,4																		○						
		CNGA 120408 LF-NU2	0,8																		○						
HS - Type Strong cutting edge	with 2 CBN cutting edges	**CNGA 120408 HS-NU2**	0,8																		●						
Break Master - LV CBN with chipbreaker	with 2 CBN cutting edges	**CNGM 120404 N-LV NU2**	0,4									●															
		CNGM 120408 N-LV NU2	0,8									●															
		CNGM 120412 N-LV NU2	1,2									●															

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

80° Diamond Type | 0° Relief | —

Uncoated

Dimensions (mm)				
CN--	L	IC	S	D_1
0903--	9,7	9,525	3,18	4,4
1204--	12,9	12,7	4,76	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

CNGN / CNGX

● G-Class SumiBoron (Solid CBN Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	CNGN 090308	0,8																			●					
	CNGN 090312	1,2																			●					
	CNGN 120412	1,2																			●					
	CNGN 120416	1,6																			○					

● G-Class SumiBoron (Solid CBN, "Dimple" Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	CNGX 120412	1,2																			○					
	CNGX 120416	1,6																			○					

CNMA / CNMX

● M-Class SumiBoron (CBN, Regrindable Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	CNMA 120404	0,4											●			▲		▲								
	CNMA 120408	0,8											●			▲		▲								
	CNMA 120412	1,2											●													

● M-Class SumiBoron (CBN, One-use Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	CNMA 120404 NS	0,4												●												
	CNMA 120408 NS	0,8												●												
	CNMA 120412 NS	1,2												●												
	CNMA 120404 NU	0,4								●	●	▲	●		▲	▲	●	▲	●							
	CNMA 120408 NU	0,8								●	●	▲	●		▲		●	▲	●							
	CNMA 120412 NU	1,2								●	●	▲	●		▲	▲	●		●							
(Wiper Type)	**CNMA 120408 NU-W**	0,8										▲	▲													

● M-Class SumiDia (PCD, NF Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	CNMX 120402 NF	0,2																							●	
	CNMX 120404 NF	0,4																							●	
	CNMX 120408 NF	0,8																							●	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 7° Relief | With Insert Hole

Dimensions (mm)				
DC__	L	IC	S	D_1
0702--	7,75	6,35	2,38	2,8
11T3--	11,6	9,525	3,97	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

Coated

DCGT / DCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	H Coated CBN BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	H Uncoated CBN BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	K Uncoated CBN BN7000	BN7500	BNS800	S Binderless CBN NCB100	N Uncoated PCD DA90	DA150	DA1000	N Binderless Sumidia NPD10
Break Master - FV, LV CBN with chipbreaker	with 2 CBN cutting edges	DCGT 070204 N-FV NC2	0,4	●	●		●	●																			
		DCGT 11T304 N-FV NC2	0,4	●	●		●																				
		DCGT 11T308 N-FV NC2	0,8	❍	●		●	●																			
	with 2 CBN cutting edges	DCGT 11T304 N-LV NC2	0,4	●	●		❑	●																			
		DCGT 11T308 N-LV NC2	0,8	●	●		●	●																			
Standard - Normal cut geometry	with 2 CBN cutting edges	DCGW 070202 NC2	0,2	●	●	●	●	●	●																		
		DCGW 070204 NC2	0,4	●	●	●	●	●	●																		
		DCGW 070208 NC2	0,8	❍	●			●	●																		
		DCGW 11T302 NC2	0,2	●	●		●	●	●																		
		DCGW 11T304 NC2	0,4	●	●	●	●	●	●	●																	
		DCGW 11T308 NC2	0,8	●	●	●	●	●	●	●																	
	(Wiper Type)	DCGW 11T304 NC-WG2	0,4	●	●		●	●																			
		DCGW 11T308 NC-WG2	0,8	●	●		●	●																			
		DCGW 11T304 NC-WH2	0,4	●	❍		●	●																			
		DCGW 11T308 NC-WH2	0,8	●	●		●	●																			
LE - Type Low cutting force		DCGW 11T302 LE-NC2	0,2	❍																							
		DCGW 11T304 LE-NC2	0,4	●																							
		DCGW 11T308 LE-NC2	0,8	●																							
LT - Type Sharp cutting edge		DCGW 070202 LT-NC2	0,2		●																						
		DCGW 070204 LT-NC2	0,4		●																						
		DCGW 11T302 LT-NC2	0,2		●																						
		DCGW 11T304 LT-NC2	0,4		●																						
		DCGW 11T308 LT-NC2	0,8		●																						
LS - Type Low cutting force	with 2 CBN cutting edges	DCGW 070202 LS-NC2	0,2			●	●	●																			
		DCGW 070204 LS-NC2	0,4			●	●	●																			
		DCGW 11T304 LS-NC2	0,4			●	●	●	●																		
		DCGW 11T308 LS-NC2	0,8			●	●	●	●																		
HS - Type Strong cutting edge	with 2 CBN cutting edges	DCGW 11T304 HS-NC2	0,4		●			●	●																		
		DCGW 11T308 HS-NC2	0,8		●			●	●																		

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 7° Relief With Insert Hole

Dimensions (mm)				
DC--	L	IC	S	D_1
0702--	7,75	6,35	2,38	2,8
11T3--	11,6	9,525	3,97	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

Uncoated

DCGT / DCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H Coated		K	H Uncoated													K		S	N Uncoated			
				CBN																K PM		Binderless CBN	PCD			Binderless Sumidia
Break Master - FV, LV		DCGT 070204 N-FV NU2	0,4									●														
		DCGT 11T304 N-FV NU2	0,4									●														
		DCGT 11T308 N-FV NU2	0,8									●														
CBN with chipbreaker	with 2 CBN cutting edges	DCGT 11T304 N-LV NU2	0,4									●														
		DCGT 11T308 N-LV NU2	0,8									●														
		DCGW 070202 NU2	0,2									●														
		DCGW 070204 NU2	0,4								●	●	▲	●		▲	▲	●			●						
		DCGW 070208 NU2	0,8									●		●		▲					●						
		DCGW 11T302 NU2	0,2																		●						
		DCGW 11T304 NU2	0,4								●	●		●		▲	▲	●		●	●						
	with 2 CBN cutting edges	DCGW 11T308 NU2	0,8								●	●	▲	●		▲	▲	●	▲	●	●						
		DCGW 11T304 NU-WG2	0,4									●														
		DCGW 11T308 NU-WG2	0,8									●														
	(Wiper Type)	DCGW 11T304 NU-WH2	0,4									●														
		DCGW 11T308 NU-WH2	0,8									●														
		DCGW 070204 LF-NU2	0,4																		●						
		DCGW 070208 LF-NU2	0,8																		●						
		DCGW 11T304 LF-NU2	0,4																		●						
LF - Type Sharp cutting edge	with 2 CBN cutting edges	DCGW 11T308 LF-NU2	0,8																		●						
		DCGW 070204 HS-NU2	0,4																		●						
		DCGW 070208 HS-NU2	0,8																		●						
		DCGW 11T304 HS-NU2	0,4																								
HS - Type Strong cutting edge	with 2 CBN cutting edges	DCGW 11T308 HS-NU2	0,8																		●						

● G-Class SumiBoron (CBN, One-Use Type)

		DCGW 11T304 NS	0,4												●												
		DCGW 11T308 NS	0,8												●												
		DCGW 070202 NU	0,2								●	●	▲	●			▲	●	▲	●							
		DCGW 070204 NU	0,4								●	●	▲	●		▲	▲	●	▲	●							
		DCGW 070208 NU	0,8								●	●	▲	●		▲			▲	●							
		DCGW 11T302 NU	0,2								●	●	▲	●		▲	▲	●	▲	●							
		DCGW 11T304 NU	0,4								●	●	▲	●				●	▲	●							
		DCGW 11T308 NU	0,8								●	●	▲	●			▲	●		●							

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 7° Relief | With Insert Hole

Uncoated

Dimensions (mm)				
DC_ _	L	IC	S	D_1
0702--	7,75	6,35	2,38	2,8
11T3--	11,6	9,525	3,97	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

DCMT / DCMW ●●●●●●

● M-Class SumiDia (PCD, Regrindable Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
 	**DCMT 070202**	0,2																						●		
	DCMT 070204	0,4																						●		
	DCMT 11T302	0,2																						●		
	DCMT 11T304	0,4																						●		
	DCMT 11T308	0,8																						●		

● M-Class SumiDia (PCD, NF Type)

 	**DCMT 070201 NF**	0,1																							●	
	DCMT 070202 NF	0,2																							●	
	DCMT 070204 NF	0,4																							●	
	DCMT 070208 NF	0,8																							●	
	DCMT 11T301 NF	0,1																							●	
	DCMT 11T302 NF	0,2																							●	
	DCMT 11T304 NF	0,4																							●	
	DCMT 11T308 NF	0,8																							●	

● M-Class SumiDIA (PCD, One-Use "Break Master" Type)

Break Master - DM  	**DCMT 070202 L-DM NU**	0,2																						○		
	DCMT 070204 L-DM NU	0,4																						○		
	DCMT 11T302 L-DM NU	0,2																						○		
	DCMT 11T304 L-DM NU	0,4																						●		
Break Master - DM  	**DCMT 070202 R-DM NU**	0,2																						○		
	DCMT 070204 R-DM NU	0,4																						●		
	DCMT 11T302 R-DM NU	0,2																						●		
	DCMT 11T304 R-DM NU	0,4																						●		
Break Master - LD  	**DCMT 070202 N-LD NF**	0,2																							○	
	DCMT 070204 N-LD NF	0,4																							○	
	DCMT 11T302 N-LD NF	0,2																							○	
	DCMT 11T304 N-LD NF	0,4																							○	
	DCMT 11T308 N-LD NF	0,8																							○	
Break Master - GD  	**DCMT 070202 N-GD NF**	0,2																							○	
	DCMT 070204 N-GD NF	0,4																							○	
	DCMT 11T302 N-GD NF	0,2																							○	
	DCMT 11T304 N-GD NF	0,4																							○	
	DCMT 11T308 N-GD NF	0,8																							○	

● M-Class SumiDia (PCD, Binderless)

	**DCMW 070202 RH**	0,2																								○
	DCMW 070204 RH	0,4																								○
	DCMW 11T302 RH	0,2																								○
	DCMW 11T304 RH	0,4																								○
	DCMW 11T308 RH	0,8																								○

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

SUMIBORON / SUMIDIA
Indexable Inserts

55° Diamond Type | 0° Relief / With Insert Hole

Coated

Dimensions (mm)				
DN__	L	IC	S	D_1
1104--	11,6	9,525	4,76	3,81
1504--	15,5	12,7	4,76	5,16
1506--	15,5	12,7	6,35	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

DNGA ●●●●●●

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H Coated CBN						K Coated CBN	H Uncoated CBN									K PM Uncoated CBN			S Uncoated CBN Binderless	N Uncoated PCD			N Uncoated PCD Binderless Sumidia
 Standard - Normal cut geometry	 with 2 CBN cutting edges	**DNGA 110404 NC2**	0,4	○	●			●																		
		DNGA 110408 NC2	0,8	○	●																					
		DNGA 110412 NC2	1,2	○	○																					
 Standard - Normal cut geometry	 with 4 CBN cutting edges	**DNGA 150402 NC4**	0,2	○	○																					
		DNGA 150404 NC4	0,4	○	○																					
		DNGA 150408 NC4	0,8	○	○																					
		DNGA 150412 NC4	1,2	○	○				○																	
		DNGA 150604 NC4	0,4	●	●	●	●	●	●	●																
		DNGA 150608 NC4	0,8	●	●	●	●	●	●	●																
		DNGA 150612 NC4	1,2	●	●		●	●	●	●																
	 (Wiper Type)	**DNGA 150404 NC-WG4**	0,4				○	○																		
		DNGA 150408 NC-WG4	0,8				○	○																		
		DNGA 150604 NC-WG4	0,4	●	●		●	●																		
		DNGA 150608 NC-WG4	0,8	●	●		●	●																		
		DNGA 150612 NC-WG4	1,2	●	●		●	●																		
		DNGA 150404 NC-WH4	0,4				○	○																		
		DNGA 150408 NC-WH4	0,8				○	○																		
		DNGA 150604 NC-WH4	0,4	●	●		❑	●																		
		DNGA 150608 NC-WH4	0,8	●	●		❑	●																		
		DNGA 150612 NC-WH4	1,2	●	●		❑	●																		
 **LE** - Type Low cutting force	 with 2 CBN cutting edges	**DNGA 150404 LE-NC2**	0,4	○																						
		DNGA 150408 LE-NC2	0,8	○																						
		DNGA 150412 LE-NC2	1,2	○																						
		DNGA 150604 LE-NC2	0,4	●																						
		DNGA 150608 LE-NC2	0,8	●																						
		DNGA 150612 LE-NC2	1,2	●																						
 **LT** - Type Sharp cutting edge	 with 2 CBN cutting edges	**DNGA 150402 LT-NC2**	0,2		○																					
		DNGA 150404 LT-NC2	0,4		○																					
		DNGA 150408 LT-NC2	0,8		○																					
		DNGA 150412 LT-NC2	1,2		○																					
		DNGA 150604 LT-NC2	0,4		●																					
		DNGA 150608 LT-NC2	0,8		●																					
		DNGA 150612 LT-NC2	1,2		●																					
 **LS** - Type Low cutting force	 with 2 CBN cutting edges	**DNGA 150404 LS-NC2**	0,4						○																	
		DNGA 150408 LS-NC2	0,8						○																	
		DNGA 150412 LS-NC2	1,2						○																	
		DNGA 150604 LS-NC2	0,4			❑	●	●	●																	
		DNGA 150608 LS-NC2	0,8			❑	●	●	●																	
		DNGA 150612 LS-NC2	1,2			❑	●	●	●																	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 0° Relief | With Insert Hole

Coated

Dimensions (mm)				
DN_ _	L	IC	S	D_1
1504--	15,5	12,7	4,76	5,16
1506--	15,5	12,7	6,35	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

DNGA / DNGG

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	H Coated BNC2010	H Coated BNC2020	K Coated BNC100	H Coated BNC160	H Coated BNC200	H Coated BNC300	K Coated BNC500	H Uncoated CBN BN1000	H Uncoated CBN BN2000	H Uncoated CBN BNX10	H Uncoated CBN BNX20	H Uncoated CBN BNX25	H Uncoated CBN BN250	H Uncoated CBN BN300	H Uncoated CBN BN350	H Uncoated CBN BN700	K PM BN7000	K PM BN7500	K PM BNS800	S Binderless CBN NCB100	N Uncoated PCD DA90	N Uncoated PCD DA150	N Uncoated PCD DA1000	N Binderless Sumidia NPD10
 **ES** - Type Crater wear stability	 with 2 CBN cutting edges	**DNGA 150604 ES-NC2**	0,4		●																						
		DNGA 150608 ES-NC2	0,8		●																						
		DNGA 150612 ES-NC2	1,2		●																						
	 with 4 CBN cutting edges	**DNGA 150404 ES-NC4**	0,4		❍																						
		DNGA 150408 ES-NC4	0,8		❍																						
		DNGA 150412 ES-NC4	1,2		❍																						
 **HS** - Type Strong cutting edge	 with 2 CBN cutting edges	**DNGA 150604 HS-NC2**	0,4	●	●		●	●	●																		
		DNGA 150608 HS-NC2	0,8	●	●		●	●	●																		
		DNGA 150612 HS-NC2	1,2	●	●		●	●	●																		
	 with 4 CBN cutting edges	**DNGA 150412 HS-NC4**	1,2						❍																		
Break Master - FV, LV, SV  CBN with chipbreaker	 with 4 CBN cutting edges	**DNGG 150404 N-FV NC4**	0,4	❍	❍		❍	❍																			
		DNGG 150408 N-FV NC4	0,8	❍	❍		❍	❍																			
		DNGG 150412 N-FV NC4	1,2	❍	❍		❍	❍																			
		DNGG 150604 N-FV NC4	0,4	●	●		❑	●																			
		DNGG 150608 N-FV NC4	0,8	●	●		❑	●																			
		DNGG 150612 N-FV NC4	1,2	●	●		❑	●																			
		DNGG 150404 N-LV NC4	0,4	❍	❍		❍	❍																			
		DNGG 150408 N-LV NC4	0,8	❍	❍		❍	❍																			
		DNGG 150412 N-LV NC4	1,2	❍	❍		❍	❍																			
		DNGG 150604 N-LV NC4	0,4	●	●		●	●																			
		DNGG 150608 N-LV NC4	0,8	●	●		●	●																			
		DNGG 150612 N-LV NC4	1,2	●	●		❑	●																			
		DNGG 150408 N-SV NC4	0,8	❍	❍																						
		DNGG 150412 N-SV NC4	1,2	❍	❍																						
		DNGG 150608 N-SV NC4	0,8		●			●																			
		DNGG 150612 N-SV NC4	1,2		●			●																			

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

55° Diamond Type | 0° Relief / With Insert Hole

Uncoated

Dimensions (mm)				
DN--	L	IC	S	D_1
1504--	15,5	12,7	4,76	5,16
1506--	15,5	12,7	6,35	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

DNGA / DNGM

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H K							H									K PM		S	N			
				Coated							Uncoated												Uncoated			
				CBN																			PCD			
				Binderless CBN																			Binderless Sumidia			
	 with 2 CBN cutting edges	**DNGA 150604 NU2**	0,4									●		●		▲	▲	●									
		DNGA 150608 NU2	0,8								●	●	▲	●			▲	●			●						
		DNGA 150612 NU2	1,2								●																
	 (Wiper Type)	**DNGA 150404 NU-WG2**	0,4									❍															
		DNGA 150408 NU-WG2	0,8									❍															
		DNGA 150604 NU-WG2	0,4									❍															
		DNGA 150608 NU-WG2	0,8									❍															
		DNGA 150612 NU-WG2	1,2									●															
		DNGA 150404 NU-WH2	0,4									❍															
		DNGA 150408 NU-WH2	0,8									❍															
		DNGA 150604 NU-WH2	0,4									❍															
		DNGA 150608 NU-WH2	0,8									❍															
		DNGA 150612 NU-WH2	1,2									●															
Break Master - LV 		**DNGM 150404 N-LV NU2**	0,4									❍															
		DNGM 150408 N-LV NU2	0,8									❍															
		DNGM 150412 N-LV NU2	1,2									❍															
		DNGM 150604 N-LV NU2	0,4									●															
		DNGM 150608 N-LV NU2	0,8									●															
		DNGM 150612 N-LV NU2	1,2									●															

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

55° Diamond Type — 0° Relief, With Insert Hole

Coated / Uncoated

Dimensions (mm)				
DN__	L	IC	S	D_1
1506--	15,5	12,7	6,35	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

DNMA ○○○○○○

● M-Class SumiBoron (CBN, Regrindable Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**DNMA 150604**	0,4											●			▲										
	DNMA 150608	0,8											●			▲										
	DNMA 150612	1,2											●			▲										

● M-Class SumiBoron (CBN, One-Use Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**DNMA 150604 NS**	0,4												●												
	DNMA 150608 NS	0,8												●												
	DNMA 150604 NU	0,4									●		●		▲	▲	●	▲	●							
	DNMA 150608 NU	0,8								●	●	▲	●		▲	▲	●	▲	●							
	DNMA 150612 NU	1,2										▲	●													

● M-Class SumiDia (PCD, Binderless)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**DNMA 150408 RH**	0,8																								○
	DNMA 150412 RH	1,2																								○

Round Type — 0° Relief, Without Insert Hole

Coated / Uncoated

Dimensions (mm)				
RN__	L	IC	S	D_1
0903--	9,525	9,525	3,18	–
1203--	12,7	12,7	3,18	–
1204--	12,7	12,7	4,76	–

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

RNGN ○○○○○○

● G-Class SumiBoron (Solid CBN Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
 Solid CBN	**RNGN 090300**	–																			●					
	RNGN 120300	–																			●					
	RNGN 120400	–																			●					

● G-Class SumiBoron (CBN, Full Top Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**RNGN 090300 B**	–					●	●																		

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

Square Type — 0° Relief / With Insert Hole

Coated / Uncoated

Dimensions (mm)				
SN_ _	L	IC	S	D_1
09T3--	9,525	9,525	3,97	4,4
1204--	12,7	12,7	4,76	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

SCGW / SNGA

● G-Class SumiBoron (CBN, One-Use Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		SCGW 09T304 NU	0,4											●					▲	●							
		SCGW 09T308 NU	0,8											●						●							

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Standard - Normal cut geometry	with 4 CBN cutting edges	**SNGA 120408 NC4**	0,8		●			●	●																		
		SNGA 120412 NC4	1,2		○			●	●																		
HS - Type Strong cutting edge	with 2 CBN cutting edges	**SNGA 120408 HS-NC2**	0,8					●	●																		
		SNGA 120412 HS-NC2	1,2					●	●																		
HS - Type Strong cutting edge	with 4 CBN cutting edges	**SNGA 120408 HS-NC4**	0,8		❑																						
		SNGA 120412 HS-NC4	1,2		❑																						

Square Type — 0° Relief / Without Insert Hole

Uncoated

Dimensions (mm)				
SN_ _	L	IC	S	D_1
0903--	9,525	9,525	3,18	–
1204--	12,7	12,7	4,76	–

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

SNGN / SNGX

● G-Class SumiBoron (Solid CBN Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		SNGN 090308	0,8																			●					
		SNGN 090312	1,2																			○					
		SNGN 120412	1,2																			○					
		SNGN 120416	1,6																			○					

● G-Class SumiBoron (Solid CBN, "Dimple" Type)

		SNGX 120412	1,2																			○					
		SNGX 120416	1,6																			○					

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

Square Type

0° Relief
With Insert Hole

Coated / Uncoated

Dimensions (mm)				
SN__	L	IC	S	D_1
1204--	12,7	12,7	4,76	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

SNMA

● M-Class SumiBoron (CBN, One-Use Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**SNMA 120408 NS** **SNMA 120412 NS**	0,8 1,2												❑ ●												
	SNMA 120408 NU **SNMA 120412 NU**	0,8 1,2									● ●		● ●		▲ ▲	▲ ▲	● ●		● ●							

● M-Class SumiDia (PCD, Binderless)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**SNMA 120408 RH** **SNMA 120412 RH**	0,8 1,2																								○ ○

60° Triangle Type

5° Relief

Dimensions (mm)				
TBGN	L	IC	S	D_1
0601--	6,9	3,97	1,59	–
TBGW				
0601--	6,9	3,97	1,59	2,8

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TBGN / TBGW

● G-Class SumiBoron (CBN, Full Top Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**TBGN 060102 B** **TBGN 060104 B**	0,2 0,4					● ●				● ●		● ●													

● G-Class SumiDIA (PCD, NF Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**TBGN 060102 NF** **TBGN 060104 NF**	0,2 0,4																							● ●	

● G-Class SumiDIA (PCD, NF Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
	**TBGW 060102 NF** **TBGW 060104 NF**	0,2 0,4																							● ●	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 7° Relief / With Insert Hole

Coated / Uncoated

Dimensions (mm)				
TC--	L	IC	S	D_1
0902--	9,62	5,56	2,38	2,5
1102--	11,0	6,35	2,38	2,8
16T3--	16,5	9,525	3,97	4,3

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TCGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		TCGW 090204 NC	0,4		●			●																			
		TCGW 090208 NC	0,8		●			●																			
		TCGW 110202 NC	0,2		●			●																			
		TCGW 110204 NC	0,4		●			●		●																	
		TCGW 110208 NC	0,8		●			●																			
	with 3 CBN cutting edges	**TCGW 16T304 NC3**	0,4		●			●																			
		TCGW 16T308 NC3	0,8		●			●																			
		TCGW 090204 NU	0,4																▲	●							
		TCGW 090208 NU	0,8																▲	●							
		TCGW 110202 NU	0,2								●		▲	●					▲	●							
		TCGW 110204 NU	0,4								●	●	▲	●		▲			▲	●							
		TCGW 110208 NU	0,8								●		▲						▲	●							
		TCGW 16T304 NU	0,4								●		▲	●					▲	●							
		TCGW 16T308 NU	0,8																▲	●							

TCMT ●●●●●●

● M-Class SumiDia (PCD, NF Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		TCMT 090202 NF	0,2																						○	
		TCMT 090204 NF	0,4																						●	
		TCMT 110201 NF	0,1																						●	
		TCMT 110202 NF	0,2																						●	
		TCMT 110204 NF	0,4																						●	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 0° Relief | With Insert Hole

Coated

Dimensions (mm)				
TN__	L	IC	S	D_1
1604--	16,5	9,525	4,76	3,81

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TNGA / TNGG

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	H Coated BNC2010	H Coated BNC2020	H Coated BNC100	H Coated BNC160	H Coated BNC200	H Coated BNC300	K Coated BNC500	H Uncoated CBN BN1000	H Uncoated CBN BN2000	H Uncoated CBN BNX10	H Uncoated CBN BNX20	H Uncoated CBN BNX25	H Uncoated CBN BN250	H Uncoated CBN BN300	H Uncoated CBN BN350	H Uncoated CBN BN700	K Uncoated CBN BN7000	K PM BN7500	K Uncoated CBN BNS800	S Binderless CBN NCB100	N Uncoated PCD DA90	N Uncoated PCD DA150	N Uncoated PCD DA1000	N Binderless Sumidia NPD10
 Standard - Normal cut geometry	 with 6 CBN cutting edges	**TNGA 160402 NC6**	0,2	❍	❍																					
		TNGA 160404 NC6	0,4	●	●		●	●	●																	
		TNGA 160408 NC6	0,8	●	●	●	●	●	●																	
		TNGA 160412 NC6	1,2	●	●	❑	●	●	●																	
 **LE** - Type Low cutting force	 with 3 CBN cutting edges	**TNGA 160404 LE-NC3**	0,4	●																						
		TNGA 160408 LE-NC3	0,8	●																						
		TNGA 160412 LE-NC3	1,2	❍																						
 **LT** - Type Sharp cutting edge	 with 3 CBN cutting edges	**TNGA 160402 LT-NC3**	0,2		❍																					
		TNGA 160404 LT-NC3	0,4		❍																					
		TNGA 160408 LT-NC3	0,8		●																					
		TNGA 160412 LT-NC3	1,2		❍																					
 **LS** - Type Low cutting force	 with 3 CBN cutting edges	**TNGA 160404 LS-NC3**	0,4			●	❑	●	●																	
		TNGA 160408 LS-NC3	0,8			●	●	●	❍																	
		TNGA 160412 LS-NC3	1,2			❑	❑	●	❍																	
 **ES** - Type Crater wear stability	 with 6 CBN cutting edges	**TNGA 160404 ES-NC6**	0,4		❍																					
		TNGA 160408 ES-NC6	0,8		●																					
		TNGA 160412 ES-NC6	1,2		❍																					
 **HS** - Type Strong cutting edge	 with 3 CBN cutting edges	**TNGA 160404 HS-NC3**	0,4	●	●		❑	●																		
		TNGA 160408 HS-NC3	0,8	●	●		❑	●	●																	
		TNGA 160412 HS-NC3	1,2	●	●		❑	●	●																	
	 with 6 CBN cutting edges	**TNGA 160412 HS-NC6**	1,2						❍																	
Break Master - FV, LV, SV  CBN with chipbreaker	 with 6 CBN cutting edges	**TNGG 160404 N-FV NC6**	0,4	❍	❍		❑	●																		
		TNGG 160408 N-FV NC6	0,8	❍	❍		●	●																		
		TNGG 160412 N-FV NC6	1,2	❍	❍		❑	●																		
		TNGG 160404 N-LV NC6	0,4	❍	●		●	●																		
		TNGG 160408 N-LV NC6	0,8	❍	●		●	●																		
		TNGG 160412 N-LV NC6	1,2	❍	❍		●	●																		
		TNGG 160408 N-SV NC6	0,8		●			●																		
		TNGG 160412 N-SV NC6	1,2		❍																					

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 7° Relief / With Insert Hole

Uncoated

Dimensions (mm)				
TN__	L	IC	S	D_1
1604--	16,5	9,525	4,76	3,81

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TNGA / TNGM

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H Coated CBN						K Coated CBN	H Uncoated CBN									K PM Uncoated CBN			S Binderless CBN	N Uncoated PCD			Binderless Sumidia
	 with 3 CBN cutting edges	**TNGA 160404 NU3** **TNGA 160408 NU3** **TNGA 160412 NU3**	0,4 0,8 1,2																		❍					
 **LF** - Type Sharp cutting edge	 with 3 CBN cutting edges	**TNGA 160404 LF-NU3** **TNGA 160408 LF-NU3**	0,4 0,8																		❍					
Break Master - LV 	 with 3 CBN cutting edges	**TNGM 160404 N-LV NU3** **TNGM 160408 N-LV NU3** **TNGM 160412 N-LV NU3**	0,4 0,8 1,2									●														

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

TN__ Type neg. Inserts

TP__ Type 11° pos. Inserts

60° Triangle Type — 0° Relief — With Insert Hole

Uncoated

Dimensions (mm)				
TN__	L	IC	S	D_1
1604--	16,5	9,525	4,76	3,81

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TNMA ●●●●●●

● M-Class SumiBoron (CBN, Regrindable Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
 	**TNMA 160404**	0,4											●			▲										
	TNMA 160408	0,8											●			▲										

● M-Class SumiBoron (CBN, One-Use Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
 	**TNMA 160404 NU**	0,4									●		●		▲											
	TNMA 160408 NU	0,8								●	●	▲	●		▲	▲	●									
	TNMA 160412 NU	1,2								●		▲	●													

60° Triangle Type — 11° Relief — Without Insert Hole

Dimensions (mm)				
TP__	L	IC	S	D_1
1103--	11,0	6,35	3,18	–
1603--	16,5	9,525	3,18	–

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TPGN ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
 	**TPGN 110304 NU**	0,4											●					▲	○							
	TPGN 110308 NU	0,8											●					▲	○							
	TPGN 160304 NU	0,4											●					▲	○							
	TPGN 160308 NU	0,8											●					▲	○							

● G-Class SumiDia (PCD, NF Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
 	**TPGN 110304 NF**	0,4																							●	
	TPGN 110308 NF	0,8																							●	
	TPGN 160302 NF	0,2																							●	
	TPGN 160304 NF	0,4																							●	
	TPGN 160308 NF	0,8																							●	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief With Insert Hole

Coated

Dimensions (mm)				
TP__	L	IC	S	D_1
0802--	8,2	4,76	2,39	2,3
0902--	9,62	5,56	2,38	2,5
1103--	11,0	6,35	3,18	3,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TPGT / TPGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type)

Shape		ISO Cat. No.	RE	H Coated CBN BNC2010	H Coated CBN BNC2020	H Coated CBN BNC100	H Coated CBN BNC160	H Coated CBN BNC200	H Coated CBN BNC300	K Coated CBN BNC500	H Uncoated CBN BN1000	H Uncoated CBN BN2000	H Uncoated CBN BNX10	H Uncoated CBN BNX20	H Uncoated CBN BNX25	H Uncoated CBN BN250	H Uncoated CBN BN300	H Uncoated CBN BN350	H Uncoated CBN BN700	K PM Uncoated CBN BN7000	K PM Uncoated CBN BN7500	S Uncoated CBN Binderless BNS800	N Uncoated CBN Binderless NCB100	N Uncoated PCD DA90	N Uncoated PCD DA150	N Uncoated PCD DA1000	Binderless Sumidia NPD10
Break Master - FV CBN with chipbreaker	with 3 CBN cutting edges	TPGT 110304 N-FV NC3	0,4	❍	●		❑	●																		
		TPGT 110308 N-FV NC3	0,8	❍	●		❑																			
Standard - Normal cut geometry		TPGW 080202 NC	0,2		●			●																		
		TPGW 080204 NC	0,4		●			●																		
		TPGW 110304 NC	0,4		●			●																		
		TPGW 110308 NC	0,8		●			●																		
Standard Type	with 3 CBN cutting edges	TPGW 080202 NC3	0,2	❍	❍																					
		TPGW 080204 NC3	0,4	❍	❍																					
		TPGW 090202 NC3	0,2	❍	❍																					
		TPGW 090204 NC3	0,4	❍	❍																					
LE - Type Low cutting force	with 3 CBN cutting edges	TPGW 110302 LE-NC3	0,2	❍																						
		TPGW 110304 LE-NC3	0,4	❍																						
		TPGW 110308 LE-NC3	0,8	❍																						
LT - Type Sharp cutting edge	with 3 CBN cutting edges	TPGW 110302 LT-NC3	0,2		❍																					
		TPGW 110304 LT-NC3	0,4		❍																					
		TPGW 110308 LT-NC3	0,8		❍																					
LS - Type Low cutting force	with 3 CBN cutting edges	TPGW 110304 LS-NC3	0,4						❍																	
		TPGW 110308 LS-NC3	0,8						❍																	

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief With Insert Hole

Uncoated

Dimensions (mm)

TP__	L	IC	S	D_1
0802--	8,2	4,76	2,39	2,3
0902--	9,62	5,56	2,38	2,5
1102--	11,0	6,35	2,38	2,8
1103--			3,18	3,4
1604--	16,5	9,525	4,76	4,3

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TPGT / TPGW

● G-Class SumiBoron (CBN, One-Use Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H Coated						K	H Uncoated CBN									K PM			S Binderless CBN	N Uncoated PCD			Binderless Sumidia
Break Master - FV CBN with chipbreaker	with 3 CBN cutting edges	**TPGT 110304 N-FV NU3**	0,4									●															
		TPGT 110308 N-FV NU3	0,8									●															
		TPGW 080202 NU	0,2									●		●		▲											
		TPGW 080204 NU	0,4								●	●	▲	●		▲											
		TPGW 110304 NU	0,4									●		●		▲	▲	●									
		TPGW 110308 NU	0,8									●		●		▲	▲	●									

● G-Class SumiBoron (CBN, Regrindable Type)

		TPGW 110304	0,4											●		▲											
		TPGW 110308	0,8											●		▲											

● G-Class SumiDia (PCD, NF Type)

		TPGW 080202 NF	0,2																						●		
		TPGW 080204 NF	0,4																						●		
		TPGW 110202 NF	0,2																						○		
		TPGW 110204 NF	0,4																						○		
		TPGW 110208 NF	0,8																						○		
		TPGW 110302 NF	0,2																						●		
		TPGW 110304 NF	0,4																						●		
		TPGW 110308 NF	0,8																						●		
		TPGW 160402 NF	0,2																						○		
		TPGW 160404 NF	0,4																						●		
		TPGW 160408 NF	0,8																						●		

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

60° Triangle Type | 11° Relief With Insert Hole

Uncoated

Dimensions (mm)

TP__	L	IC	S	D_1
0802--	8,2	4,76	2,39	2,3
0902--	9,62	5,56	2,38	2,5
1102--	11,0	6,35	2,38	2,8
1103--			3,18	3,4
1604--	16,5	9,525	4,76	4,3

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

TPMT / TPMW

● M-Class SumiDia (PCD, One-Use "Break Master" Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H K							H									K PM			S	N			
				Coated							Uncoated												Binderless CBN	Uncoated PCD			Binderless Sumidia
				CBN																						
Break Master - DM		TPMT 080204 L-DM NU	0,4																					○		
		TPMT 090204 L-DM NU	0,4																					●		
Break Master - LD		TPMT 080202 N-LD NF	0,2																						○	
		TPMT 080204 N-LD NF	0,4																						○	
		TPMT 090202 N-LD NF	0,2																						○	
		TPMT 090204 N-LD NF	0,4																						○	
		TPMT 110202 N-LD NF	0,2																						○	
		TPMT 110204 N-LD NF	0,4																						○	
		TPMT 110302 N-LD NF	0,2																						○	
		TPMT 110304 N-LD NF	0,4																						○	
		TPMT 110308 N-LD NF	0,8																						○	
		TPMT 160402 N-LD NF	0,2																						○	
		TPMT 160404 N-LD NF	0,4																						○	
		TPMT 160408 N-LD NF	0,8																						○	
Break Master - GD		TPMT 080202 N-GD NF	0,2																						○	
		TPMT 080204 N-GD NF	0,4																						○	
		TPMT 090202 N-GD NF	0,2																						○	
		TPMT 090204 N-GD NF	0,4																						○	
		TPMT 110202 N-GD NF	0,2																						○	
		TPMT 110204 N-GD NF	0,4																						○	
		TPMT 110302 N-GD NF	0,2																						○	
		TPMT 110304 N-GD NF	0,4																						○	
		TPMT 110308 N-GD NF	0,8																						○	
		TPMT 160402 N-GD NF	0,2																						○	
		TPMT 160404 N-GD NF	0,4																						○	
		TPMT 160408 N-GD NF	0,8																						○	

● M-Class SumiDia (PCD, Binderless)

		TPMW 080202 RH	0,2																								○
		TPMW 080204 RH	0,4																								○
		TPMW 110302 RH	0,2																								○
		TPMW 110304 RH	0,4																								○
		TPMW 110308 RH	0,8																								○
		TPMW 160402 RH	0,2																								○
		TPMW 160404 RH	0,4																								○
		TPMW 160408 RH	0,8																								○

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 5° Relief With Insert Hole

Coated / Uncoated

Dimensions (mm)				
VB__	L	IC	S	D_1
1102--	11,0	6,35	2,38	2,8
1103--			3,18	
1604--	16,6	9,525	4,76	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

VBGW ●●●●●●

● G-Class SumiBoron (CBN, One-Use Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H Coated				K			H Uncoated CBN									K	PM		S Binderless CBN	N Uncoated PCD			Binderless Sumidia
 Standard - Normal cut geometry		**VBGW 110202 NC** **VBGW 110204 NC** **VBGW 110208 NC**	0,2 0,4 0,8		● ● ●			● ● ●																			
		**VBGW 110202 NU** **VBGW 110204 NU** **VBGW 110208 NU**	0,2 0,4 0,8									● ●		● ● ●													
		VBGW 160402 NU **VBGW 160404 NU** **VBGW 160408 NU**	0,2 0,4 0,8								● ●	● ●	▲ ▲	● ● ●		▲ ▲	● ●	▲ ▲	● ●								

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

 Standard - Normal cut geometry	 with 2 CBN cutting edges	**VBGW 110204 NC2**	0,4		❑																						
		VBGW 160404 NC2 **VBGW 160408 NC2** **VBGW 160412 NC2**	0,4 0,8 1,2	● ●	● ● ●	● ●	● ●	● ●	● ●	● ●																	
 **LE** - Type Low cutting force		**VBGW 160402 LE-NC2** **VBGW 160404 LE-NC2** **VBGW 160408 LE-NC2**	0,2 0,4 0,8	● ● ●																							
 **LT** - Type Sharp cutting edge		**VBGW 110302 LT-NC2** **VBGW 110304 LT-NC2**	0,2 0,4		○ ●																						
		VBGW 160402 LT-NC2 **VBGW 160404 LT-NC2** **VBGW 160408 LT-NC2**	0,2 0,4 0,8		○ ● ●																						
 **LS** - Type Low cutting force	 with 2 CBN cutting edges	**VBGW 160404 LS-NC2** **VBGW 160408 LS-NC2**	0,4 0,8			● ●	● ●	●																			
 **HS** - Type Strong cutting edge	 with 2 CBN cutting edges	**VBGW 160404 HS-NC2** **VBGW 160408 HS-NC2**	0,4 0,8		● ●			● ●	●																		
	 with 2 CBN cutting edges	**VBGW 160404 NU2** **VBGW 160408 NU2**	0,4 0,8								● ●	● ●	▲ ▲	● ●		▲ ▲											

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 7° Relief With Insert Hole

Coated / Uncoated

Dimensions (mm)				
VC--	L	IC	S	D_1
0802--	8,3	4,76	2,38	2,3
1103--	11,0	6,35	3,18	2,8
1604--	16,6	9,525	4,76	4,4

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

VCMT / VCGW ●●●●●●

● M-Class SumiDia (PCD, NF Type)

Shape		ISO Cat. No.	RE	H K Coated CBN: BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	H K Uncoated CBN: BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	K PM: BN7000	BN7500	S: BNS800	Binderless CBN: NCB100	N Uncoated PCD: DA90	DA150	DA1000	Binderless Sumidia: NPD10
		VCMT 110301 NF	0,1																						●	
		VCMT 110302 NF	0,2																						●	
		VCMT 110304 NF	0,4																						●	
		VCMT 160404 NF	0,4																						●	
		VCMT 160408 NF	0,8																						●	
		VCMT 160412 NF	1,2																						●	
		VCMT 110302 N-LD NF	0,2																						○	
		VCMT 110304 N-LD NF	0,4																						○	
		VCMT 160404 N-LD NF	0,4																						○	
		VCMT 160408 N-LD NF	0,8																						○	
		VCMT 160412 N-LD NF	1,2																						○	
		VCMT 110302 N-GD NF	0,2																						○	
		VCMT 110304 N-GD NF	0,4																						○	
		VCMT 160404 N-GD NF	0,4																						○	
		VCMT 160408 N-GD NF	0,8																						○	
		VCMT 160412 N-GD NF	1,2																						○	

● M-Class SumiDia (PCD, Binderless)

		VCMW 080201 RH	0,1																									○
		VCMW 080202 RH	0,2																									○
		VCMW 080204 RH	0,4																									○
		VCMW 110302 RH	0,2																									○
		VCMW 110304 RH	0,4																									○
		VCMW 160402 RH	0,2																									○
		VCMW 160404 RH	0,4																									○
		VCMW 160408 RH	0,8																									○
		VCMW 160412 RH	1,2																									○

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

		VCGW 080202 NC2	0,2	❍	❍																							
		VCGW 080204 NC2	0,4	❍	❍																							

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

35° Diamond Type | 0° Relief | With Insert Hole

Coated / Uncoated

Dimensions (mm)				
VN--	L	IC	S	D_1
1604--	16,6	9,525	4,76	3,81

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

VNGA / VNGG

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	H Coated CBN BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	K Coated CBN BNC500	H Uncoated CBN BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	K Uncoated CBN BN7000	PM BN7500	BNS800	S Binderless CBN NCB100	N Uncoated PCD DA90	DA150	DA1000	Binderless Sumidia NPD10
	 with 2 CBN cutting edges	**VNGA 160404 NU2**	0,4								●	●									❍						
		VNGA 160408 NU2	0,8								●	●									❍						
	 with 2 CBN cutting edges	**VNGA 160404 NC2**	0,4		●																						
		VNGA 160408 NC2	0,8		●																						
	 with 4 CBN cutting edges	**VNGA 160402 NC4**	0,2	❍	❍																						
		VNGA 160404 NC4	0,4		●																						
		VNGA 160408 NC4	0,8		●																						
 **LT** - Type Sharp cutting edge	 with 2 CBN cutting edges	**VNGA 160402 LT-NC2**	0,2		❍																						
		VNGA 160404 LT-NC2	0,4		●																						
		VNGA 160408 LT-NC2	0,8		●																						
		VNGA 160412 LT-NC2	1,2		❍																						
 **ES** - Type Crater wear stability	 with 4 CBN cutting edges	**VNGA 160404 ES-NC4**	0,4		●																						
		VNGA 160408 ES-NC4	0,8		●																						
		VNGA 160412 ES-NC4	1,2		❍																						
Break Master - FV, - LV  CBN with chipbreaker	 with 4 CBN cutting edges	**VNGG 160404 N-FV NC4**	0,4	❍	❍		●	●																			
		VNGG 160408 N-FV NC4	0,8	❍	●		❑	●																			
		VNGG 160404 N-LV NC4	0,4	●	❍		●	●																			
		VNGG 160408 N-LV NC4	0,8	❍	●		●	●																			

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

35° Diamond Type — 0° Relief / With Insert Hole

Uncoated

Dimensions (mm)				
VN--	L	IC	S	D_1
1604--	16,6	9,525	4,76	3,81

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

VNGM / VNMA ●●●●●●

● M-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
Break Master - LV				H Coated						K Coated	H Uncoated CBN									K PM			S Binderless CBN	N Uncoated PCD			N Binderless Sumidia
 CBN with chipbreaker	 with 2 CBN cutting edges	**VNGM 160404 N-LV NU2**	0,4									●															
		VNGM 160408 N-LV NU2	0,8									●															

● M-Class SumiBoron (CBN, Regrindable Type)

		**VNMA 160404**	0,4											●			▲										
		VNMA 160408	0,8											●			▲										

● M-Class SumiBoron (CBN, One-Use Type)

		**VNMA 160404 NU**	0,4								●	●	▲	●		▲	▲	●									
		VNMA 160408 NU	0,8								●	●	▲	●		▲	▲	●									
		VNMA 160408 NS	0,8												○													

● M-Class SumiDia (PCD, Binderless)

		**VNMA 160408 RH**	0,8																								○
		VNMA 160412 RH	1,2																								○

VNMX ●●●●●●

● M-Class SumiDia (PCD, Regrindable Type)

Shape		ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
				H Coated						K Coated	H Uncoated CBN									K PM			S Binderless CBN	N Uncoated PCD			N Binderless Sumidia
		**VNMX 160404 NF**	0,4																						●	
		VNMX 160408 NF	0,8																						●	

● = Euro stock
○ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

80° Trigon Type — 0° Relief, With Insert Hole

Coated

Dimensions (mm)				
WN__	L	IC	S	D_1
0804--	8,69	12,7	4,76	5,16

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

WNGA

● G-Class SumiBoron (CBN, One-Use Multi-Corner Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	NCB100	DA90	DA150	DA1000	NPD10
		**WNGA 080408 LT-NC3**	0,8		❍																					
	 with 6 CBN cutting edges	**WNGA 080404 NC6** **WNGA 080408 NC6** **WNGA 080412 NC 6**	0,4 0,8 1,2	❍ ❍	● ● ●			● ● ●																		
	 (Wiper Type)	**WNGA 080408 NC-WG6**	0,8	●	●		❍	❍																		
		WNGA 080408 NC-WH6	0,8	●	●		❍	❍																		

80° Special Type — 7° Relief, With Insert Hole

Coated / Uncoated

Dimensions (mm)				
ZN__	L	IC	S	D_1
0401--	–	4,76	1,59	2,3

H Hardened Steel
K Cast Iron
N Non-Ferrous Metal
S Exotic Alloy
PM Sintered Component
Carbide/Hard Brittle Material

ZNEX

● G-Class SumiBoron (CBN, One-Use Type)

Shape	ISO Cat. No.	RE	BNC2010	BNC2020	BNC100	BNC160	BNC200	BNC300	BNC500	BN1000	BN2000	BNX10	BNX20	BNX25	BN250	BN300	BN350	BN700	BN7000	BN7500	BNS800	DA150	DA1000
		**ZNEX 040102 NC** **ZNEX 040104 NC**	0,2 0,4		● ●	▲ ▲	▲ ▲	▲ ▲															
		**ZNEX 040102 LE-NC** **ZNEX 040104 LE-NC**	0,2 0,4	❍ ❍																			
		ZNEX 040102 LT-NC **ZNEX 040104 LT-NC**	0,2 0,4		❍ ❍																		
		ZNEX 040102 NU **ZNEX 040104 NU**	0,2 0,4							● ●	● ●	● ●		▲ ▲				❍					

● = Euro stock
❍ = Stock item in Japan
▲ = To be replaced by new item
❑ = Delivery on request

☞ L4, L5 Edge Specification of SUMIBORON Inserts

SUMIDIA Binderless PCD - Insert Grade NPD10

Negative Inserts

Application: Hard brittle material

	Shape	ISO Cat. No.	Dimensions (mm) Inscribed Circle (IC)	Thick-ness	Hole Size	Nose Radius	Cutting Edge Length	NPD10
55° Diamond Type		**DNMA 150408 RH**	12,70	4,76	5,16	0,8	1,8	❍
		150412 RH				1,2	1,8	❍
Square Type		**SNMA 120408 RH**	12,70	4,76	5,16	0,8	1,7	❍
		120412 RH				1,2	1,7	❍
35° Diamond Type		**VNMA 160408 RH**	9,525	4,76	3,81	0,8	1,8	❍
		160412 RH				1,2	1,5	❍

Note: Clearance angle of cutting edge tip can show deviation due to the production process.

Positive Inserts

Application: Hard brittle material

	Rake Angle	Shape	ISO Cat. No.	Dimensions (mm) Inscribed Circle (IC)	Thick-ness	Hole Size	Nose Radius	Cutting Edge Length	NPD10
80° Diamond Type	7°		**CCMW 03X102 RH**	3,50	1,40	1,9	0,2	1,3	❍
			03X104 RH				0,4	1,3	❍
			CCMW 04X102 RH	4,30	1,80	2,3	0,2	1,7	❍
			04X104 RH				0,4	1,7	❍
			**CCMW 060202 RH**	6,35	2,38	2,8	0,2	1,7	❍
			060204 RH				0,4	1,7	❍
			CCMW 09T302 RH	9,525	3,97	4,4	0,2	1,7	❍
			09T304 RH				0,4	1,7	❍
			09T308 RH				0,8	1,6	❍
55° Diamond Type	7°		**DCMW 070202 RH**	6,35	2,38	2,8	0,2	2,1	❍
			070204 RH				0,4	2,0	❍
			DCMW 11T302 RH	9,525	3,97	4,4	0,2	2,1	❍
			11T304 RH				0,4	1,9	❍
			11T308 RH				0,8	1,6	❍
Triangular Type	11°		**TPMW 080202 RH**	4,76	2,38	2,3	0,2	1,2	❍
			080204 RH				0,4	1,0	❍
			TPMW 110302 RH	6,35	3,18	3,4	0,2	1,5	❍
			110304 RH				0,4	1,3	❍
			110308 RH				0,8	1,0	❍
			TPMW 160402 RH	9,525	4,76	4,4	0,2	2,2	❍
			160404 RH				0,4	2,0	❍
			160408 RH				0,8	1,6	❍
35° Diamond Type	7°		**VCMW 080201 RH**	4,76	2,38	2,3	0,1	2,2	❍
			080202 RH				0,2	1,9	❍
			080204 RH				0,4	1,5	❍
			VCMW 110302 RH	6,35	3,18	2,8	0,2	2,1	❍
			110304 RH				0,4	1,7	❍
			VCMW 160402 RH	9,525	4,76	4,4	0,2	2,1	❍
			160404 RH				0,4	1,7	❍
			160408 RH				0,8	1,8	❍
			160412 RH				1,2	1,5	❍

Note: Clearance angle of cutting edge tip can show deviation due to the production process.

Precision Tools

BSME
☞ M36-38

Very small boring bar - brazed type

- Solid carbide shank boring bar with brazed CBN tip and inner coolant supply.
- For tiny hole diameter boring in hardened steel.
- Min. boring dia. is ø 2,5 mm.

SEXC
☞ M36-39

CBN boring tool for small diameter boring

- Solid carbide shank boring bar with indexable CBN insert and inner coolant supply.
- For small hole diameter boring in hardened steel.
- Min. boring dia. is ø 4,0 mm.

BNBB
☞ M40

Small hole boring tools

- CBN cutting edge is brazed on to a solid carbide shank.
- Small hole boring for hardened steels.
- Min. boring dia. is ø 3,5 mm.



BNZ
☞ M41

Small hole boring bars

- Solid carbide boring bars with economical CBN insert.
- Small hole boring for hardened steels.
- Min. boring dia. is ø 7,0 mm.

BNB
☞ M41

Small hole boring bars

- Solid carbide boring bars with economical CBN and PCD insert.
- Min. boring dia. is ø 10,0 mm.

GWB / PSC
☞ M42-43

CBN Grooving System for Hardened Steels

- Tangential Inserts – Double clamp holder
- Groove Widths from 1,5 – 6,0mm
- New CBN grade for interrupted grooving
- ISO-PSC polygon modular grooving system

BNGG
☞ M44

Threading holders

- CBN cutting edge for hardened steel
- Adjustable threading after regrinding.



DABB
☞ M45

Small hole boring tools

- PCD cutting edge for finishing of small non-ferrous parts
- Min. boring dia. is ø 3,0 mm.
- DABB-C for boring
  DABB-N for profiling and corner grooving

ANX New

M46-51

High speed cutter for Non-ferrous Metal

- Achieves feeds of over vf = 30.000 mm/min
- 6 different edge preparations
- Simple screw-fastening structure enables fine adjustments to be made easily
- Precise applications of coolant to the machining point
- Milling cutter range with diameter from Ø 32-160 mm

RF

M52

High speed face mill for Aluminium

- Finishing and roughing aluminium alloys and non-ferrous materials
- High precision and highspeed machining vc = 5000 m/min
- Alumimum alloy body Run-out less than 10 µm
- Easy assembling

SRF

M53

High speed face mill for Aluminium

- Small diameter cutter for small machines
- High speed roughing and finishing with SumiDia DA2200
- High speed capability of rpm = 20.000
- Economical PCD insert NF type

FMU

M54-55

"BN Finish Mill" for finishing grey cast iron

- High speed machining vc = 1500 m/min
- Excellent surface roughness Rz = 3,2
- Run-out less than 10 µm
- Easy assembling

BNES

M56

"Helical Master" SUMIBORON Endmill

- Spiral CBN brazed cutting edge for super finishing hardened steel (HRC 50 – 60)
- Dry machining
- Stable cutting
- High accuracy
- Excellent swarf evacuation

BNBP

M57

"Mould Finish Master" SUMIBORON Micro Ball Nose Endmills

- High precision machining of hardened steels < HRC 70 with long tool life
- Super tough grade SUMIBORON BN350 prevents chipping of the cutting edge
- R accuracy : ±0,005 mm

NPDRS / NPDB(S)

M58-59

"Mould Finish Master" SUMIDIA Binderless Endmills

- NPDRS - radius endmills
- NPDB(S) - ball nose endmills
- For finishing of carbide and brittle materials
- High precision machining and long tool life

DAL / DDL / DML

M60-61

High precision SUMIDIA Drills

- PCD cutting edge is brazed on to a solid carbide shank.
- From general to high precision drilling of Aluminium alloys
- DML type is suitable for chamfering and stepped drilling

BSME/SEXC Series

Features

- New ultra small boring bar with CBN cutting edge
- Internal coolant
- Easy setting and handling
- High accuracy
- Carbide body for high rigidity
- One sleeve for different diameters

Basic System



2 Types of CBN Small Hole Boring Bar System

BSME - CBN Brazed Cutting Edge Type	SEXC - Indexable CBN Insert Type
Min. bore diameter: Ø 2,5 – 5,0 mm	Min. bore diameter: Ø 4,0 – 6,0 mm
Unique cutting edge shape with high quality and sharpness  Internal coolant hole (standard)	2 corner inserts  Internal coolant hole (standard)
	
Excellent repeatability of boring bar (deviation within 0,020 mm)  Clamp screws Location pin for controlled cutting edge position	

Application Range



Recommended Cutting Conditions

Spindle Speed (*n*)	>2000 min^{-1}	Low speed may cause chattering and chipping on the cutting edge.
Depth of Cut (a_p)	0,01 – 0,15 mm	Excessive depth of cut may cause larger tool deflection resulting in deterioration of bore accuracy.
Feed Rate (f)	0,01 – 0,1 mm/rev	-

Accessories



Mounting Instruction

1. Insert alignment tool into the sleeve until you connect with the pin inside.
   Gently lock the screws to hold.

2. Locate the sleeve into your tool-holding system.
   Gently lock the screws to hold.

3. Clock the flat of the alignment tool into a straight position.

After adjustment, equipped boring bar has automatically cutting peak height of zero on the center of tool.



4. Use pre setting machine to set the diameter of the boring bar.

Application Example

BSME Hardened Alloy Steel Valve Component

The BSME type provides stable machining.
Tool life is over 2 times longer than competitor´s CBN tool.





Work Material:	Hardened alloy steel valve component (automotive component)
Tool:	BSME R50020D2S6
Grade:	BN2000
Cutting Conditions:	v_c = 135 m/min
	f = 0,02 mm/rev
	a_p = 0,10 mm
	Dry

SEXC Bearing Steel Small Automotive Component

The SEXC type provides drastically reduced tool costs.
Tool life is 1,5 times longer than competitor´s brazed CBN tool.





Work Material:	Bearing steel small automotive component (60 HRC)
Holder:	E06D2 SEXC R/L03-04P
Insert:	ECXA 030X02LF (BN2000)
Cutting Conditions:	v_c = 50 m/min (4.000 rpm)
	f = 0,02 mm/rev
	a_p = 0,02 mm
	Wet

BSME Series

BSME-Type with Internal Coolant

BSME
General, Facing



Fig. 1



Fig. 2



Sharp edge (no honing)

■ Boring Bar

Description	Grade		Dimensions (mm)							Fig.	Applicable Sleeve
	BN2000		DMIN	DN	WF	CDX	LF	DCON	RE		
	R	L									
BSME R/L 25020D2S6	●	●	2,5	2,0	1,20	5,3	32,0	6,0	0,2	1	HBSM6020
BSME R/L 25020D3S6	●	●				7,8	34,5				
BSME R/L 25020D4S6	❑	❑				10,3	37,0				
BSME R/L 30020D2S6	●	●	3,0	2,5	1,45	6,3	32,8			2	
BSME R/L 30020D3S6	●	●				9,3	35,8				
BSME R/L 30020D4S6	❑	❑				12,3	38,8				
BSME R/L 35020D2S6	●	●	3,5	3,0	1,70	7,3	33,5				
BSME R/L 35020D3S6	●	●				10,8	37,0				
BSME R/L 35020D4S6	❑	❑				14,3	40,5				
BSME R/L 40020D2S6	●	●	4,0	3,5	1,95	8,3	33,9				
BSME R/L 40020D3S6	●	●				12,3	37,9				
BSME R/L 40020D4S6	❑	❑				16,3	41,9				
BSME R/L 45020D2S6	●	●	4,5	4,0	2,20	9,3	35,0				
BSME R/L 45020D3S6	●	●				13,8	39,5				
BSME R/L 45020D4S6	❑	❑				18,3	44,0				
BSME R/L 50020D2S6	●	●	5,0	4,5	2,45	10,3	35,8				
BSME R/L 50020D3S6	●	●				15,3	40,8				
BSME R/L 50020D4S6	❑	❑				20,3	45,8				

■ Adapter Sleeve and Parts





Description	Stock	Dimensions (mm)		Sleeve Screw	Wrench
		DCB	LF		
HBSM6020	●	6,0	80	BT0506	TH025

■ Alignment Tool



Description	Stock
AFBSM60	●

■ Identification Details

B S M — Sumitomo CBN Product Special Mini

E — Solid Carbide Bar with Inner Coolant

R/L — R: Right Hand L: Left Hand

3 5 0 — Minimum Bore Diameter (ø 3,5 mm)

2 0 — Nose Radius of Edge (ø 0,20 mm)

D 3 — L/D - Ratio of Working Length

S 6 — Shank Diameter

● = Euro stock
❑ = Delivery on request

Recommended Tightening Torque (N·m)

SEXC-Type with Internal Coolant





Boring Bar

Description	Stock		Dimensions (mm)							Applicable Sleeve	Spare Parts: Insert Screw	Spare Parts: N·m	Spare Parts: Wrench
	R	L	DMIN	DN	WF	CDX	LF	DCON	GAMF				
E06D2 SEXC R/L 03-04P	●	●	4,0	3,75	1,95	8	33,75	6,0	13°	HBSM6020	MIB1,6–2,0	0,2	SDBSM
E06D3 SEXC R/L 03-04P	●	●				12	37,75						
E06D2 SEXC R/L 03-05P	●	●	5,0	4,75	2,45	10	35,25		12°		MIB1,6–2,5		
E06D3 SEXC R/L 03-05P	●	●				15	40,25						
E06D2 SEXC R/L 03-06P	●	●	6,0	5,75	2,95	12	36,75		11°		MIB1,6–3,0		
E06D3 SEXC R/L 03-06P	●	●				18	42,75						

Spare Parts




Adapter Sleeve and Parts






Description	Stock	Dimensions (mm)		Sleeve Screw	Wrench
		DCB	LF		
HBSM6020	●	6,0	80	BT0506	TH025

Alignment Tool



Description	Stock
AFBSM60	●

CBN Insert



Description	Grade		Nose Radius RE (mm)	Cutting Edge Preparation
	BN2000	BN7000		
ECXA030X02 LE NU2	●		0,2	sharp + hone
ECXA030X02 LF NU2	●	●	0,2	sharp

Notes:

Applicable wrench SDBSM is recommended when fastening the insert screw.
Please check insert screw occasionally and replace it in time.

Identification Details

E 06 D2 S E X C R/L 03 - 04 P

- **E** — Carbide Bar with Coolant Hole
- **06** — Shank Diameter (ø 6 mm)
- **D2** — L/D Ratio of Working Length
- **S** — Insert Clamp System S = Screw Type
- **E** — Insert Shape E = Diamond 75°
- **X** — Approch Angle of Main Cutting Edge
- **C** — Insert Relief Angle C = 7°
- **R/L** — R: Right Hand L: Left Hand
- **03** — Insert Size (ø IC)
- **04** — Minimum Bore Diameter (ø 4,0 mm)
- **P** — Standard Content includes Wrench

BNBB Type

For Hardened Steel

BNBB type small hole boring tools for hardened work pieces up to diameter 3,5 mm



■ „Sumiboron“ Brazed Boring Tools for Small Hole Boring

	Cat. No.	Stock	Dimensions (mm)					Applicable holder	Grade of brazed cutting edge
			DMIN	DCON	LF	H	RE		
BNBB (Carbide shank) 	BNBB 03 R	▲	3,5	3	60	2,4	0,2	HBB 316	**SUMIBORON (CBN)** **BN250**
	BNBB 04 R	▲	4,5	4	60	3,4	0,2	HBB 416	
	BNBB 05 R	▲	5,5	5	80	4,4	0,2	HBB 516	
	BNBB 06 R	▲	6,5	6	80	5,4	0,2	HBB 616	
	BNBB 08 R	▲	8,5	8	100	7,4	0,2	HBB 816	

■ Holder



Cat. No.	Stock	Dimensions (mm)			
		d_1	LF	d_2	H
HBB 316	●	16	100	3	15
HBB 416	●			4	
HBB 516	●			5	
HBB 616	●			6	
HBB 816	●			8	

■ Spare Parts

Screw	Wrench
	
BT 0404	TH 020

■ Recommended Cutting Conditions

Work Material	SUMIBORON BN250		Notes
Hardened steels ($H_RC45–68$)	Cutting speed (v_c)	30–150 m/min	Low speed may cause chattering in cutting process and chipping occurence on the cutting edge.
	Feed rate (f)	0,03–0,1 mm/rev	–
	Depth of cut (a_p)	0,03–0,2 mm	Excessive depth of cut may cause larger deformation of tool,resulting in deterioration of bore accuracy.

■ Precaution On Use



- Adjust overhang to achieve absolute minimum.
- For use of a small diameter brazed boring tool, select high speed and small feed rate, as much as possible.

● = Euro stock
❍ = Japan stock

▲ = To be replaced by new item

(N·m) Recommended Tightening Torque (N·m)

SUMIBORON Small Hole Boring Bars
BNZ / BNB Type

BNZ type



BNB type



Boring Bars for Small Hole Boring

	Cat. No.	Stock	Dimensions (mm)					Applicable insert	
			DMIN	DCON	LF	H	GAMF		
BNZ (Carbide shank) 	BNZ 606 R	●	7	6	80	5,5	-14°	ZNEX 0401○○	 ZNEX (CBN)
	BNZ 608 R	●	9	8	100	7,5	-12°		
	BNZ 610 R	●	11	10	125	9,5	-10°		
	BNZ 612 R	●	13	12	130	11	-8		
	Holder "HBB616" for BNZ606 (ø d = 6 mm) 								
BNB (Carbide shank) 	BNB 508 R/L	● ●	10	8	140	7	-9°	TBGN 0601○○	 TBGN (CBN)
	BNB 510 R/L	❍ ❍	12	10	140	9	-8°		
	BNB 512 R/L	● ●	14	12	160	11	-6°		
	BNB 516 R/L	● ●	18	16	180	14	-5°		
	BNB 520 R/L	❍ ❍	22	20	180	18	-4°		

Spare Parts for BNZ

Holder	Screw	Wrench
		
BNZ 606 R		
BNZ 608 R	BFTX 0204 N	TRX 06
BNZ 610 R	**0,5** (N·m)	

Spare Parts for BNB

Holder	Clamp	Clamp bold	Nut	Wrench
				
BNB 508 R/L	BNBC	BH 0306	BNBW-2	TH 020
BNB 512 R/L	BNBC	FBUP-3-A0-9	BNBW-4	TH 020
BNB 516 R/L	BNBC	BH 0310	BNBW-4	TH 020
BNB 520 R/L	BNBC	BH 0310	BNBW-7	TH 020

Recommended Cutting Conditions

Cutting speed	80–120 m/min
Feed rate	0,03–0,1 mm/rev
Depth of cut	0,03–0,2 mm

Holders Performance Area





Work material: Alloy steel (H_RC 60)
Cutting conditions: v_c = 100 m/min
f = 0,1 mm/rev
a_p = 0,2 mm

GWB / PSC Type

CBN Grooving System for Hardened Steels

GWB Type

ISO-PSC Polygon Modular

CGA Inserts

Features

Tangential insert

80 degree tangentially mounted insert improves rigidity

Double clamping system

The double clamping system increases stability so even axial feeds are possible.

Coated CBN grade BNC30G

Tough new coated CBN grade for interrupted hard grooving

Wide insert range 1,5–6,0 mm

Wide range of width's and grades for continuous and interrupted cut grooving operations

Grades

Grade	Application	Features
BN250 	Continuous grooving 	Uncoated CBN grade for continuous cut grooving applications
BNC30G 	Interrupted grooving 	Tough new CBN coated grade developed for interrupted cut grooving applications

Grooving Tool Holder GWB Type



External



Spare Parts



Holders

Cat. No.	Stock		Dimensions (mm)								Appl. Insert No.	Clamp finger	Clamp screw	Insert screw	Spring	Wrench
	R	L	H	B	LF	WF	HF	HBH	CW (*)	CDX						
GWB R/L 2020-45	❑	❑	20	20	151 (150)	25	20	5	1,5≤cw≤4,5	3,5 – 5,0	❶	TF 72 (Right handed) TF 73 (Left handed)	BX 0520T	BFTX 0511N	GSP 06	TRX 20
GWB R/L 2525-45	●	●	25	25	151 (150)	30	25	–								
GWB R/L 2525-60	●	●	25	25	151	30	25	–	4,5≤cw≤6,0	5,0	❷					

Remark: Inserts are not included.

Right handed tool holders are applicable with right handed inserts.

● = Euro stock
❑ = Delivery on request
▲ = To be replaced by new item
Recommended Tightening Torque (N·m)

ISO-PSC Polygon Modular CGA Grooving System





Holders

Cat. No.	R	L	Ø (mm)	F (mm)	L (mm)	Cap Screw (7,5 N·m)	Wrench
PSC 40GM00 R/L	●	●	40	22	82,0	BFTX0619N	LT25
PSC 50GM00 R/L	●	●	50	27			
PSC 40GM90 R/L	●	●	40	43	52,5		
PSC 50GM90 R/L	●	●	50	48	55,0		

Cassette

Cat. No.	R	L	Grooving Width (mm)	Grooving Depth (mm)	Inserts	Insert Screw (5,0 N·m)	Wrench	Spring	Clamp Finger	Cap Screw (3,0 N·m)	Wrench
GWBCM R/L 45	●	●	1,5–2,0	3,5	CGA1504□□0	BFTX0511N	TRX20	SCP4A			LH030
			2,5–3,0	4,0							
GWBCM R/L 60	●	●	3,5–6,0	5,0	CGA1506□□0						

CGA Inserts



Cat. No.	Stock BN250 R	Stock BN250 L	Stock BNC30G R	Stock BNC30G L	CW	CDX	IC	S	Insert No.	Applicable Holder
CGA R/L 1504 150	▲	▲	●	●	1,5	3,5	15,875	4,76		GWB R/L 2020-45 GWB R/L 2525-45 GWBCM R/L-45
R/L 1504 200	▲	▲	●	●	2,0					
R/L 1504 250	▲	▲	●	●	2,5	4,0				
R/L 1504 300	▲	▲	●	●	3,0					
R/L 1504 350	▲	▲	●	●	3,5	5,0				
R/L 1504 400	▲	▲	●	●	4,0					
R/L 1504 450	▲	▲	●	●	4,5					
CGA R/L 1506 500	▲	▲	●	●	5,0			6,35		GWB R/L 2525-60 GWBCM R/L-60
R/L 1506 550	▲	▲	●	●	5,5					
R/L 1506 600	▲	▲	●	●	6,0					

Special widths available on request

Recommended Cutting Conditions

Material	Hardened steel
Cutting speed (m/min)	60 80 120 150
Feed rate (mm/rev)	0,03 0,04 0,08 0,1
Grade	BN250, BNC30G

Coolant:
Dry / wet (for continuous cut)
Dry only (for interrupted cut)

Remarks:
To avoid thermal cracking of the cutting edge when interrupted cutting please ensure workpiece remains dry.

BNGG Type

For Hardened Steel



BNGG_TT



„Sumiboron“ Holders



Cat. No.	Stock		Dimensions (mm)			Applicable Insert
	R	L	WF	CDX	LF	
BNGG R/L 2525-TT	▲	❑	28,5	5	150	BNTT 1020 R/L BNTT 1530 R/L

Inserts



Cat. No.	Stock				Dimensions (mm)				Applicable Holder
	BN250		BNX20						
	R	L	R	L	Pitch	RE	LF	S	
BNTT 1020 R/L	▲	▲	▲	❑	1,0–2,0	0,14	25	6,0	BNGG R/L 2525 -TT
BNTT 1530 R/L	▲	▲	▲	❑	1,5–3,0	0,2	25	6,0	

● Inserts also suitable for existing BNG2525R type holders

Spare Parts

Holder	Support	Clamp	Adjust screw	Spring	Screw	Wrench	
							
BNGG R/L 2525 - TT	BNGS R/L TT	BNGC R/L	FMJ	GSP 6	BX 0615 (for clamp) BX 0414 (for support)	LH 050 LH 030	ø1,8x45

Recommended Cutting Conditions

Threading

Cutting speed (v_c)	80–120 m/min
Feed rate (f)	Max. pitch: 3,0 mm

● = Euro stock
❑ = Delivery on request

▲ = To be replaced by new item

SUMIDIA Small Hole Boring Bars
DABB Type



„Sumidia“ Brazed Boring Tools for Small Hole Boring

DABB-CR



DABB-NR



DABB (Solid carbide shank)	Cat. No.	Stock	Dimensions (mm)					Applicable Holder
		DA2200	DMIN	DCON	LF	H	RE	
For small boring 	DABB 025 CR	▲	3,0	2,5	60	2,2	0,1	HBB 2516
	DABB 035 CR	▲	4,0	3,5	60	3,2	0,1	HBB 3516
	DABB 045 CR	▲	5,0	4,5	80	4,1	0,1	HBB 4516
	DABB 060 CR	▲	7,0	6,0	80	5,2	0,1	HBB 616
For profiling and corner grooving 	DABB 025 NR	▲	3,0	2,5	60	2,2	0,1	HBB 2516
	DABB 035 NR	▲	4,0	3,5	60	3,2	0,1	HBB 3516
	DABB 045 NR	▲	5,0	4,5	80	4,1	0,1	HBB 4516
	DABB 060 NR	▲	7,0	6,0	80	5,2	0,1	HBB 616

Recommended Cutting Conditions

Spindle revolution	Feed rate	Depth of cut	Coolant
> 2000 rpm	0,03 – 0,1 mm/rev	0,03 – 0,2 mm	Wet

Holder



Cat. No.	Stock	Dimensions (mm)			
		d_1	LF	d_2	H
HBB 2516	●	16	100	2,5	15
HBB 3516	●			3,5	
HBB 4516	●			4,5	
HBB 616	●			6,0	

Spare Parts

Screw	Wrench
	
BT 0404	TH 020

New

Features

Drastically Reduced Runout Adjustment Time
Simple screw-fastening structure enables fine adjustments to be made easily.

Blade Through Coolant
Secures a supply of coolant to the cutting edge and breaks chips thoroughly.

Lightweight Aluminum Alloy Body
Utilizing aluminum alloy to achieve a total weight of less than 1,3 kg for a Ø 125 mm cutter with 22 teeth.

Product Range

Type	Cat. No.	Body Material	Diameter Range (mm) / No of Teeth							
			Ø32	Ø40	Ø50	Ø63	Ø80	Ø100	Ø125	Ø160
Shell	ANXA 16000RS	Aluminum Alloy					10, 14	12, 18	14, 22	20, 28
Shell	ANXA 16000R (Inch)	Aluminum Alloy					10, 14	12, 18	14, 22	20, 28
Shell	ANXS 16000RS	Steel		6	6, 9	8, 12	10, 14	12, 18	14, 22	
Shell	ANXS 16000R (Inch)	Steel				8, 12	10, 14	12, 18	14, 22	
Shank	ANXS 16000E	Steel	4	6						

Inch Inch Bore

Blade Selection Guide

Work Material	N					
Type	L	G	GX	H	—	W
Cutting Edge Shape						
Features	Low Cutting Force	Standard	Long Edge	High Strength	Corner Radius	Wiper
Applications	Finishing / Light Cutting	General Purpose	Roughing			
Edge Length*	6,0 mm	6,0 mm	9,0 mm	6,0 mm		

*Edge length
GX type = 9,0 mm

Edge Selection Guide



Reduces Running Costs by Drastically Increasing Blade, Insert Regrinding Allowance (to 1,0 mm)

Assuming 0,2 mm of regrinding each time, an edge can be used up to 6 times.
(Peripheral edge cannot be reground.)





If you wish to use reground blades you shall use sets of blades with matching size of the same level in order to keep the balance.

Performances

High-Speed / High-Efficiency Cutting

Realizes ultra-high efficiency machining with v_f = 30.000 mm/min



Comparison: Cutter Diameter Ø 100 mm

	Spindle Speed min^{-1}	Number of Teeth	Feed Rate v_f (mm/min)
ANX Series	18.000	18	32.400
Competitor	9.500	12	11.400

Drastically Reduces Runout Adjustment Time

– Simple screw-fastening structure
– Enables fine adjustments to be made easily
– High-rigidity body





Chip Control

Blade-Through Coolant Chip Breaking

ALNEX ANX Series | Competitor

Work Material:	G-AlSi12Cu
Cutting Conditions:	v_c = 2500 m/min, f_z = 0,05 mm/t, a_p = 0,5 mm, wet

Alnex
ANXS 16000 R(S)

New

Rake Angle		
	Radial	+5°
	Axial	+5°

3 mm 90°

Fig. 1



Fig. 2



Body - ANXS (Steel)

Dimensions (mm)

	Cat. No.	Stock	DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2	No. of Teeth	Weight (kg)	Fig.
Metric	ANXS 16040RS06	❍	38	40	38,5	40	16	8,4	5,6	26	14	9	6	0,3	1
	16050RS06	❍	48	50	48,5	40	22	10,4	6,3	26	18	11	6	0,4	1
	16050RS09	❍	48	50	48,5	40	22	10,4	6,3	26	18	11	9	0,5	1
	16063RS08	❍	61	63	50	40	22	10,4	6,3	26	18	11	8	0,7	1
	16063RS12	❍	61	63	50	40	22	10,4	6,3	26	18	11	12	0,7	1
	16080RS10	❍	78	80	50	50	27	12,4	7	34	35	14	10	1,2	1
	16080RS14	❍	78	80	50	50	27	12,4	7	34	35	14	14	1,2	1
	16100RS12	❍	98	100	80	50	32	14,4	8	32	46	–	12	2,0	2
	16100RS18	❍	98	100	80	50	32	14,4	8	32	46	–	18	2,0	2
	16125RS14	❍	123	125	80	63	40	16,4	9	35	52	–	14	3,9	2
	16125RS22	❍	123	125	80	63	40	16,4	9	35	52	–	22	3,9	2
Inch	ANXS 16063R08	❍	61	63	50	50	25,4	9,5	6	31	20	14	8	0,9	1
	16063R12	❍	61	63	50	50	25,4	9,5	6	31	20	14	12	0,9	1
	16080R10	❍	78	80	50	50	25,4	9,5	6	34	35	14	10	1,2	1
	16080R14	❍	78	80	50	50	25,4	9,5	6	34	35	14	14	1,2	1
	16100R12	❍	98	100	80	50	31,75	12,7	8	36	42	–	12	2,0	2
	16100R18	❍	98	100	80	50	31,75	12,7	8	36	42	–	18	2,0	2
	16125R14	❍	123	125	80	63	38,1	15,9	10	42,5	52	–	14	3,9	2
	16125R22	❍	123	125	80	63	38,1	15,9	10	42,5	52	–	22	3,9	2

Blades are sold separately. If using a blade for corner radius machining (ANB1604R), DC = DCX.

Identification Details

ANX	S	16	100	R	S	18
Cutter Series	Steel Body	Blade Size	Cutter Diameter	Feed Direction	Metric	Number of Teeth

Blades

☞ M50

Recommended Cutting Conditions

☞ M50

Max. Allowable Spindle Speed

Cat. No.	n max (min^{-1})
ANXS 16040RS06	25.000
16050RS06	25.000
16050RS09	25.000
16063RS08	22.000
16063RS12	22.000
16080RS10	20.000
16080RS14	20.000
16100RS12	18.000
16100RS18	18.000
16125RS14	16.000
16125RS22	16.000
ANXS 16063R08	22.000
16063R12	22.000
16080R10	20.000
16080R14	20.000
16100R12	18.000
16100R18	18.000
16125R14	16.000
16125R22	16.000

Spare Parts

Sold separately.

Applicable Cutters	Clamp Screw		Adjustment Screw	Wrench	Adjustment Wrench	Centre Bolt	Assembly Wrench
ANXS 16040RS06	BXA0310IP	2,0	HFJ	TRXW10IP	ANT	BXH0825-D13	HFVT
16050RS_ _						BXH1030-D16	
16063RS_ _							
16080RS_ _						BXH1235-D33	
16100RS_ _						BXH1635-D40	
16125RS_ _						BXH2036-D50	
16063R_ _						BXH1235-D18	
16080R_ _						BXH1235-D33	
16100R_ _						BXH1635-D40	
16125R_ _						BXH2036-D50	

❍ = Japan stock

Recommended Tightening Torque (N·m)

ANXA 16000 R(S)

New

Rake Angle		
	Radial	+5°
	Axial	+5°

3 mm 90°



Fig. 1



Body - ANXA (Aluminum Alloy)

Dimensions (mm)

	Cat. No.	Stock	DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP	D1	D2	No. of Teeth	Weight (kg)
Metric	ANXA 16080RS10	❍	78	80	50	50	27	12,4	7	34	35	14	10	0,5
	16080RS14	❍	78	80	50	50	27	12,4	7	34	35	14	14	0,5
	16100RS12	❍	98	100	50	50	27	12,4	7	34	35	14	12	0,8
	16100RS18	❍	98	100	50	50	27	12,4	7	34	35	14	18	0,9
	16125RS14	❍	123	125	50	50	27	12,4	7	34	35	14	14	1,2
	16125RS22	❍	123	125	50	50	27	12,4	7	34	35	14	22	1,3
	16160RS20	❍	158	160	80	63	40	16,4	9	35	52	29	20	2,6
	16160RS28	❍	158	160	80	63	40	16,4	9	35	52	29	28	2,6
Inch	ANXA 16080R10	❍	78	80	50	50	25,4	9,5	6	34	35	14	10	0,5
	16080R14	❍	78	80	50	50	25,4	9,5	6	34	35	14	14	0,5
	16100R12	❍	98	100	50	50	25,4	9,5	6	34	35	14	12	0,9
	16100R18	❍	98	100	50	50	25,4	9,5	6	34	35	14	18	0,9
	16125R14	❍	123	125	50	50	25,4	9,5	6	34	35	14	14	1,2
	16125R22	❍	123	125	50	50	25,4	9,5	6	34	35	14	22	1,3
	16160R20	❍	158	160	80	63	38,1	15,9	10	42,5	55	30	20	2,4
	16160R28	❍	158	160	80	63	38,1	15,9	10	42,5	55	30	28	2,6

Blades are sold separately. If using a blade for corner radius machining (ANB1604R), DC = DCX.

Identification Details

ANX	A	16	100	R	S	18
Cutter Series	Aluminum Alloy Body	Blade Size	Cutter Diameter	Feed Direction	Metric	Number of Teeth

Blades

☞ M50

Recommended Cutting Conditions

☞ M50

Max. Allowable Spindle Speed

Cat. No.	n max (min^{-1})
ANXA 16080RS10	20.000
16080RS14	20.000
16100RS12	18.000
16100RS18	18.000
16125RS14	16.000
16125RS22	16.000
16160RS20	14.000
16160RS28	14.000
ANXA 16080R10	20.000
16080R14	20.000
16100R12	18.000
16100R18	18.000
16125R14	16.000
16125R22	16.000
16160R20	14.000
16160R28	14.000

Spare Parts

Sold separately.

Applicable Cutters	Clamp Screw		Adjustment Screw	Wrench	Adjustment Wrench	Centre Bolt	Assembly Wrench
ANXA 16080RS_ _	BXA0310IP	2,0	HFJ	TRXW10IP	ANT	BXH1235-D33	HFVT
16100RS_ _							
16125RS_ _						BXH2036-D50	
16160RS_ _							
16080R_ _						BXH1235-D33	
16100R_ _							
16125R_ _							
16160R_ _						BXH2036-D50	

Alnex
ANXS 16000 E

New

Rake Angle	Radial	-2 – 0°
	Axial	+5°

3 mm 90°



Body - ANXS (Steel)

Dimensions (mm)

Cat. No.	Stock	DC	DCX	DMM	LH	LS	LF	No. of Teeth	Weight (kg)
ANXS 16032E04	❍	30	32	20	35	60	95	4	0,3
16040E06	❍	38	40	20	40	60	100	6	0,5

Blades are sold separately.
If using a blade for corner radius machining (ANB1604R), DC = DCX.

Identification Details

ANX	S	16	032	E	04
Cutter Series	Steel Body	Blade Size	Cutter Diameter	Round Shank	Number of Teeth

Spare Parts

Sold separately.

Applicable Cutters	Clamp Screw		Adjustment Screw	Wrench	Adjustment Wrench	Assembly Wrench
						
ANXS 16032E04 16040E06	BXA0310IP	2,0	HFJ	TRXW10IP	ANT	HFVT

Max. Allowable Spindle Speed

Cat. No.	n max (min^{-1})
ANXS 16032E04	10.000
16040E06	10.000

Blades

Application	SUMIDIA
High Speed / Light Cut	N
General Purpose	N
Roughing	N

Cat. No.	DA1000	Cutting Edge Length	Wiper Edge Shape	Applications	Fig.
ANB 1600R-L	❍	6,0	Linear	Low Cutting Force	1
1600R-G	❍	6,0	Arc-Shaped	General Purpose	1
1600R-H	❍	6,0	Arc-Shaped	Strong Edge	1
1600R-GX	❍	9,0	Arc-Shaped	Long Edge	2
1604R	❍	6,0	Linear	Corner Radius	3
1600R-W	❍	–	Arc-Shaped	Wiper	4

Fig. 1


Fig. 2


Fig. 3


Fig. 4


Wiper Blade

Recommended Cutting Conditions

Si content ≤ 12,6 %

Min. - **Optimum** - Max.

ISO	Work Material	Hard-ness	Cutting Speed v_c (m/min)	Feed Rate f_z (mm/t)	Grade
N	Aluminum Alloy	–	2.000–**2.500**–3.000	0,05–**0,13**–0,20	DA1000

Si content ≥ 12,6 %

Min. - **Optimum** - Max.

ISO	Work Material	Hard-ness	Cutting Speed v_c (m/min)	Feed Rate f_z (mm/t)	Grade
N	Aluminum Alloy	–	400–**600**–800	0,05–**0,13**–0,20	DA1000

The above recommended cutting conditions are meant as a guide. Actual conditions will depend on the individual machine rigidity, work clamp rigidity, depth of cut and other factors.

❍ = Japan stock

Recommended Tightening Torque (N·m)

■ ALNEX Series Usage Manual

● Adjustment of the Blades, Runout Alignment

① Before inserting the blade, make sure that the seat and screws are free of debris by cleaning those areas.

② Insert the blade into its seat.

③ While holding the blade against the seat, install the clamping bolt using the provided wrench, pre-tightening the bolt (recommended pre-torque is 1 N·m).

④ Using the provided wrench for the height adjustment screw, set the height to your predetermined value.

⑤ Fully tighten the clamp bolt (recommended torque is 2 N·m).

⑥ Use 1 blade as a datum point and adjust all blade heights to match.

⑦ After tightening, verify that there is no gap between the seat and blade.

② 

③ 
Pre-tighten (1N·m)

④ 
Adjust height

⑤ 
Final tighten (2N·m)

● Balance Adjustments

The cutter comes pre-balanced to a G 6,3 specification.
Under normal circumstances, it is not necessary to adjust the balance of the cutter.



● Clamp Bolts for Arbor

Work Material	Dim.			Max. Torque	Applicable Cutters
	M	L	D		
BXH0825-D13	8	25	13	15	ANXS16040RS_ _
BXH1030-D16	10	30	16	25	ANXS16040RS_ _ , ANXS16063RS_ _
BXH1235-D18	12	35	18	40	ANXS16063R_ _
BXH1235-D33	12	35	33	50	ANXS16080R(S)_ _ , ANXA16080/100/125R(S)_ _
BXH1635-D40	16	35	40	100	ANXS16100R(S)_ _
BXH2036-D50	20	36	50	200	ANXS16125R(S)_ _ , ANXA16160R(S)_ _



● Other Precautions

- Please use only Sumitomo genuine parts.
- Please regularly replace clamp bolts.
- If you wish to reduce the # of effective blades in use, to maintain balance and protect the body, please use dummy blades (set height well below effective blades).
- Please do not operate after releasing the interlock or opening the cover.
- Please avoid use and consult with Sumitomo if you mistakenly crash the body.
- As the blades are very sharp, it is very easy to get hurt when touching the blades with your hands directly, so please wear gloves when taking the blade out of the case to set into the cutter or when setting the cutter into machine tool.

RF Type

High Speed Finishing of Aluminium Alloy

Fig. 1



Fig. 2



■ Body

Cat. No.	Stock	Dimensions (mm)								Number of teeth	max. depth of cut	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP				
RF 4080 RS	●	80	82	60	50	27	12,4	7,0	29	6	3,0	0,7	1
RF 4100 RS	●	100	102	75	50	32	14,4	8,5	29	6		1,0	1
4125 RS	●	125	127	75	63	40	16,4	9,5	29	8		1,6	1
4160 RS	❑	160	162	100	63	40	16,4	9,5	29	10		2,6	2

Remark: PCD blades and inserts are not included.

■ Insert for Roughing and Finishing



Fig. 1



Fig. 2



Fig. 3

Application	Carbide	SUMIDIA		
High Speed / Light cut	N	N	N	
General Purpose	N	N	N	
Roughing	N	N	N	
Cat. No.	**H1**	**DA1000**	**DA2200**	**Fig.**
SDET 1204 ZDFR	●			1
SNEW 1204 ADFR-NF		●	▲	2
SNEW 1204 ADFR-W-NF		❍	▲	3

■ Structure



■ "Sumidia" Blade

PCD grade DA2200	Cat. No.	Stock
Standard type 	RFB	▲
Wiper type 	RFBW	▲

■ Dummy Blade

	RFD	❑

■ Cartridge

Shape	Cat. No.	Stock
For carbide insert 	RFR	●
For Sumidia insert 	RFF	●

■ Cutting Insert Selection

For easy assembling:
- PCD blade RFB
- PCD blade RFB (wiper type)

For finishing:
- Cartridge RFF
- PCD insert SNEW 1204 ADFR-NF (standard type)
  SNEW 1204 ADFR-W-NF (wiper type)
  PCD grade: DA2200

For roughing:
- Cartridge RFR
- Uncoated carbide insert
  SDET 1204 ZDFR, grade: H1

■ Spare Parts

		 10,0 N·m	 3,0 N·m			 5,0 N·m	 TH050 TH015,TH025	
Cover	Position setting stoper	Main clamp screw	Sub clamp screw	Cover clamp screw	Adjustment screw	Insert clamp screw	Hex wrench	Torque wrench
RFC	RFS	BX0620	BTD0510	FBUP2-A0-8	RFJ	BFTX0509N	TH015, TH025 TH050	TTX20

■ Setting Gauge



RF-SET

Dial-gauge is not included.

● = Euro stock
❍ = Japan stock
❑ = Delivery on request
▲ = To be replaced by new item

High Speed Finishing of Aluminium Alloy

Fig. 1



Fig. 2



Body

Cat. No.	Stock	Dimensions (mm)		No. of teeth	Fig.	Weight (Kg)
		DC	DCSFMS			
SRF 30 R-ST	❍	30	-	3	1	0,34
SRF 40 R-ST	❍	40	-	4	1	0,50
SRF 50 RS	❑	50	46,5	5	2	0,59
SRF 63 RS	❑	63	45,0	6	2	0,67

Inserts are sold seperately.

Insert



Fig. 1



Fig. 2



Fig. 3

Application	SUMIDIA
High Speed / Light cut	N
General Purpose	N
Roughing	N

Cat. No.	DA1000	Cutting Edge	Fig.
SNEW 09T3 ADTR-NF	❍	Standard	1
09T3 ADTR-U-NF	❍	Wiper	2
09T3 ADTR-R-NF	❍	Nose Radius	3

- Standard inserts and Wiper inserts can be used on the same cutter body.
- Standard inserts with nose radius should be used where vibration is present. As such, Wiper-inserts will not be applicable.
- Inserts can be regrind 3 times (up to minimum IC diameter 9,225 mm).
- When using reground inserts, it is advisable to reconfirm insert height and cutting diameter with a tool pre-setter.
- Do not mix new and reground inserts, or even inserts with different regrind amount on the same cutter.

Spare Parts



Maximum D.O.C. Guide (SRF50RS, 5 teeth)

The contains guidelines on the maximum D.O.C., determined from internal tests. "O" mark indicates the possible application range. Actual cutting conditions should be set, based on actual machine and work characteristics.

D.O.C. (mm) \ Feed	Feed Speed, v_f (mm/min)		
	2.500	4.000	5.000
	Feed Rate, f_t (mm/tooth)		
	0,05	0,08	0,10
0,5	○	○	○
1,0	○	○	○
1,5	○	○	○
2,0	○	○	○
2,5	○	○	○
3,0	○	○	○
3,5	○	○	–
4,0	○	–	–
4,5	○	–	–
5,0	○	–	–

● Cutting Conditions

Cutter: SRF 50 RS
Insert: SNEW 09T3 ADFR-NF (DA1000)
n : 10.000 rpm
Width: 35 mm at D.O.C. indicated above

Recommended Cutting Conditions for RF and SRF Type Cutters

Work Material		Process	Grade	Cutting Speed (m/min)		Feed Rate (mm/tooth)	Depth of Cut (mm)	
				RF Type	SRF Type		RF Type	SRF Type
Aluminium Alloy	Si < 13 %	Finishing	**DA1000** (PCD)	2.000–5.000	– 4.000	0,05–0,2	– 3,0	– 5,0
		Roughing	H1 (Carbide)	1.000–2.500	–			
	Si ≥ 13 %	Finishing	**DA1000** (PCD)	400–800	– 800			
		Roughing	H1 (Carbide)	200–400	–			

SUMIBORON "BN Finish Mill"
FMU Type

High Speed Finishing of Grey Cast Iron

Features

- High speed machining v_c = 1.500 m/min
- Excellent surface roughness Rz = 3,2 (Ra = 1,0)
- Safety structure for the centrifugal force under high speed cutting conditions
- Run-out is less than 10 µm
- Easy assembling method using the setting gauge
- Running cost is reduced because of economical insert

Application

GG25 – GG30 (HB200 – 250) grey cast iron with pearlite matrix, and ferrite matrix (HB130 – 160)
Application examples: engine block, cylinder block, etc

Specifications

FMU Type: ø 80–ø 315 mm
Insert: SNEW1203ADTR/L
Low cutting force type: SNEW1203ADTR/L-S

Recommended Cutting Conditions

Speed: v_c = 800–2000 m/min
Feed: f_t = 0,1–0,3 mm/tooth
Depth: a_p = 0,5 mm or less
Dry cutting

Performance

● Tool Life Diagram



Work material : GG25 H_B240 (Pearlite)
Cutting speed : v_c = 600–4000 m/min
Feed rate : f_t = 0,15 mm/tooth
Depth of cut : a_p = 0,5 mm, Dry

● Estimated Tool Life



Work material : GG25 H_B240 (Pearlite)
Cutting speed : v_c = 400–4000 m/min
Feed rate : f_t = 0,15 mm/tooth
Depth of cut : a_p = 0,5 mm, Dry

● Milling of ductile cast iron and alloy steel casting do not produce the best results.
● Dry cutting is recommended. Wet cutting will result in chipping of cutting edges in the early stages due to thermal cracking.

● = Euro stock
❑ = Delivery on request
▲ = To be replaced by new item
Recommended Tightening Torque (N·m)

FMU Type

Specifications

Approach angle: 90°
Axial rake angle: + 8°
Radial rake angle: + 2°



Max. depth of cut: 0,5 mm

Structure



Body

Fig. 1



Fig. 2



Fig. 3



Fig. 4



Fig. 5



Cat. No.	Stock	Dimensions (mm)								No. of Teeth	Max. Depth of Cut	Weight (Kg)	Fig.
		DC	DCX	DCSFMS	LF	DCB	KWW	KDP	CBDP				
FMU 4080 RS	●	80	82,8	60	63	27	12,4	7,0	25	6		1,6	1
FMU 4100 RS	●	100	102,8	76	63	32	14,4	8,5	29	8		2,4	2
4125 RS	❑	125	127,8	75	63	40	16,4	9,5	29	10		3,4	2
4160 RS	❑	160	162,8	100	63	40	16,4	9,5	29	12	0,5	5,6	3
FMU 4200 RS	❑	200	202,8	130	63	60	25,7	14,0	38	16		9,2	4
4250 RS	❑	250	252,8	130	63	60	25,7	14,0	38	20		14,3	4
FMU 4315 RS		315	317,8	240	80	60	25,7	14,0	40	24		27,8	5

Inserts

Fig. 1



Fig. 2



Application	CBN	
High Speed / Light cut	K	K
General Purpose	K	K
Roughing		

Cat. No.	BN700	BN7000	Figure
SNEW 1203 ADT R	▲	❍	1
1203 ADT R-S	▲	❍	2

Cartridge



Cartridge	Insert Screw	Adjustment Screw	O-ring	Insert Wrench	Pin
FMUU	BFTX0509N	FMUJ	P3	TRX20	1,8 x 45

Spare Parts



Screw	Screw	Setting clamp	Double screw	Wrench	Wrench	Wrench
BH0620	BTD0609	FMUE	WB5–10	TH040	LH030	LH025

Gauge

RF-SET

Dial-gauge is not included.

BNES Type

Spiral CBN Endmill for Hardened Steel



■ Endmills BNES Type with 1 Spiral Flute



Helix angle : 15°
right-hand cut, right-hand helix

Cat. No.	Stock	Dimensions (mm)				
	BN350	DC	DMM	APMX	LU	LF
BNES 1060	❍	6,0	10	7,0	11	60
BNES 1080	❍	8,0	10	10,0	14	70
BNES 1100	❍	10,0	12	12,0	17	75
BNES 1120	❍	12,0	12	14,0	20	80
BNES 1140	❍	14,0	16	16,0	21,5	80

■ Recommended Cutting Conditions

Cutting speed: v_c (m/min), Spindle revolutions: n (rpm), Feed per tooth: f_t (mm/tooth), Feed speed: v_f (mm/min)

Tooling example	DC	Hardened steel (H_RC 50–57) v_c = 100–170 m/min			Hardened steel (H_RC 58–65) v_c = 80–150m/min		
	ø 6–8	$a_e \leq$ 0,1 mm	n = 4000–9000	v_f (mm/min) = 240–540	$a_e \leq$ 0,08 mm	n = 3200–8000	v_f (mm/min) = 150–370
	ø 10–12	$a_e \leq$ 0,15 mm	n = 2700–5400	v_f (mm/min) = 180–360	$a_e \leq$ 0,12 mm	n = 2100–4800	v_f (mm/min) 120–270
	ø 14–16	$a_e \leq$ 0,2 mm	n = 2000–3800	v_f (mm/min) = 140–260	$a_e \leq$ 0,15 mm	n = 1600–3400	v_f (mm/min) = 110–230

Depth of cut : $a_p \leq$ DC

Recommendation: Dry cutting (Air coolant)
Down-cut milling
Minimise the overhang
Use a rigid machine

■ Performance

● Long Tool Life and High Efficiency





Work material: X155CrVMo12-1
Hardness: H_RC 60

Cutting data:
v_c = 100 m/min (Helical Master)
v_c = 40 m/min (Competitor's coated solid carbide endmill)
v_f = 186 mm/min

Down-cut milling
Dry cutting

● Excellent Surface Roughness

"Helical Master" BNES 1080 ø 8,0



Conventional straight flute CBN endmill, ø 8,0





Work material: 15Cr3
Hardness: H_RC 55–58
Cutting data: v_c = 130 m/min
v_f = 310 mm/min

Down-cut milling
Dry cutting

● = Euro stock
❍ = Japan stock

SUMIBORON "MOULD Finish Master"

BNBP Type



Characteristics / Application

- High precision machining of hardened steels < HRC 70 with long tool life
- Super tough grade SUMIBORON BN350 prevents chipping of the cutting edge
- R accuracy : ±0,005 mm

Endmills



※ Endmill Identification

BNBP 2 R020 - 012 4

- BNBP: MOULD FINISH MASTER
- 2: Number of teeth
- R020: Radius of ball nose
- 012: Neck length (LU)
- 4: Shank Diam.

	Cat. No.	Stock	Dimensions (mm)						
		BN350	RE	DC	LF	DN	DMM	APMX	LU
4,0 mm (Shank Diam.)	BNBP 2 R020-012 4	●	0,2	0,4	50	0,37	4	0,3	1,2
	BNBP 2 R030-015 4	●	0,3	0,6	50	0,57	4	0,4	1,5
	BNBP 2 R050-025 4	●	0,5	1,0	50	0,97	4	0,6	2,5
	BNBP 2 R075-040 4	●	0,75	1,5	50	1,47	4	0,9	4,0
	BNBP 2 R100-055 4	●	1,0	2,0	50	1,97	4	1,4	5,5
6,0 mm (Shank Diam.)	BNBP 2 R020-012 6	●	0,2	0,4	50	0,37	6	0,3	1,2
	BNBP 2 R030-015 6	●	0,3	0,6	50	0,57	6	0,4	1,5
	BNBP 2 R050-025 6	●	0,5	1,0	50	0,97	6	0,6	2,5
	BNBP 2 R075-040 6	●	0,75	1,5	50	1,47	6	0,9	4,0
	BNBP 2 R100-055 6	●	1,0	2,0	50	1,97	6	1,4	5,5

Performance

Wear Resistance



Machined Surface



R1,0 Ball endmill, Work material: X155CrVMo12-1 (H_RC60)
Cutting data: n = 20.000 rpm, f_t = 0,05 mm/tooth (v_f = 2.000mm/min)
a_p = 0,05 mm, a_e = 0,05 mm, Air blast

High Speed Machining



R1,0 Ball endmill, Work material: X155CrVMo12-1 (H_RC60)
Cutting data: n = 40.000 rpm, f_t = 0,05 mm/tooth (v_f = 4.000mm/min)
a_p= 0,05 mm, a_e = 0,05 mm, Oil mist

Excellent surface finish compared with competitor's CBN and coated carbide endmills

Recommended Cutting Conditions

Spindle revolutions: N (rpm), Feed rate per tooth: f_t (mm/tooth), Depth of cut: a_p (mm), Wide of cut: a_e (mm)

Material / Cutting data / Radius (mm)	Pre-hardened steel, Die steel (– HRC52)				Die steel (– HRC62)				High speed tool steel (– HRC70)			
	n (rpm)	f_t (mm/tooth)	d_{oc} (mm)	W_{oc} (mm)	n (rpm)	f_t (mm/tooth)	d_{oc} (mm)	W_{oc} (mm)	n (rpm)	f_t (mm/tooth)	d_{oc} (mm)	W_{oc} (mm)
R 0,2	20.000–50.000	0,02	0,03	0,03	20.000–50.000	0,02	0,01	0,02	20.000–50.000	0,015	0,01	0,02
R 0,3	20.000–50.000	0,02	0,03	0,03	20.000–50.000	0,02	0,01	0,02	20.000–50.000	0,015	0,01	0,02
R 0,5	20.000–50.000	0,03	0,05	0,05	20.000–50.000	0,03	0,03	0,04	20.000–50.000	0,02	0,02	0,03
R 0,75	20.000–50.000	0,04	0,08	0,1	20.000–50.000	0,04	0,05	0,05	20.000–50.000	0,03	0,02	0,05
R 1,0	20.000–50.000	0,05	0,1	0,1	17.000–50.000	0,05	0,05	0,05	17.000–50.000	0,03	0,03	0,05

Important Notes

(1) For stable machining, a more rigid machine is recommended.
(2) Air blast or oil mist coolant is recommended.
(3) Shorten overhang as much as possible.

NPDRS Type

SUMIDIA Binderless Radius Endmill **NPDRS** Type





NPDRS Type Body (for Standard Finishing)

Cat. No.	Stock	Dimensions (mm)							Real effective length with respect to work material gradient angle				
	NPD10	DC	RE	APMX	LU	LF	DN	DMM	0,5°	1°	1,5°	2°	3°
NPDRS 1020 R002-006	❍	0,2	0,02	0,10	0,6	40	0,175	4	0,61	0,62	0,63	0,64	0,66
1020 R005-006	❍	0,2	0,05	0,10	0,6	40	0,175	4	0,61	0,62	0,63	0,64	0,66
1030 R002-010	❍	0,3	0,02	0,15	1,0	40	0,27	4	1,01	1,03	1,04	1,06	1,09
1030 R005-010	❍	0,3	0,05	0,15	1,0	40	0,27	4	1,01	1,03	1,04	1,06	1,09
1050 R005-015	❍	0,5	0,05	0,25	1,5	40	0,47	4	1,61	1,66	1,72	1,78	1,92
NPDRS 1050 R010-015	❍	0,5	0,10	0,25	1,5	40	0,47	4	1,61	1,66	1,71	1,77	1,91
1100 R005-030	❍	1,0	0,05	0,55	3,0	40	0,95	4	3,40	3,52	3,65	3,78	4,08
1100 R010-030	❍	1,0	0,10	0,55	3,0	40	0,95	4	3,40	3,52	3,64	3,77	4,07
1100 R020-030	❍	1,0	0,20	0,55	3,0	40	0,95	4	3,40	3,51	3,63	3,76	4,05
1200 R005-040	❍	2,0	0,05	0,55	4,0	40	1,95	4	4,44	4,59	4,75	4,93	5,33
NPDRS 1200 R010-040	❍	2,0	0,10	0,55	4,0	40	1,95	4	4,43	4,59	4,75	4,92	5,31
1200 R020-040	❍	2,0	0,20	0,55	4,0	40	1,95	4	4,43	4,58	4,74	4,91	5,29

Identification Details

NPDR	S	1	020	R002	-	006
Series Code	For standard finishing	No. of flutes	Cutting diameter	Corner radius		Length below neck

Cutting Diameter and Nose Radius Combinations

DC	RE 0,02	RE 0,05	RE 0,1	RE 0,2
0,2	❍	❍		
0,3	❍	❍		
0,5		❍	❍	
1,0		❍	❍	❍
2,0		❍	❍	❍

Recommended Cutting Conditions

- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.

Work Material		Carbide			
RE (mm)	LU	Spindle Speed (min^{-1})	Feed Rate (mm/min)	a_p (mm)	a_e (mm)
0,2	0,10	40.000	100	0,001	0,001
0,3	0,15	40.000	150	0,002	0,001
0,5	0,25	40.000	200	0,003	0,001
1,0	0,55	40.000	400	0,005	0,003
2,0	0,55	40.000	600	0,010	0,005

❍ = Japan stock

NPDB(S) Type

SUMIDIA Binderless Ballnose Endmill **NPDBS** Type / **NPDB** Type





NPDBS Type Body (for Standard Finishing)

Cat. No.	Stock	Dimensions (mm)							Real effective length with respect to work material gradient angle				
	NPD10	RE	DC	APMX	LF	LU	DN	DMM	0,5°	1°	1,5°	2°	3°
NPDBS 1010–004	❍	0,1	0,2	0,1	0,4	40	0,18	4	0,44	0,45	0,46	0,47	0,49
1020–008	❍	0,2	0,4	0,2	0,8	40	0,38	4	0,83	0,84	0,85	0,86	0,89
1030–010	❍	0,3	0,6	0,3	1,0	40	0,58	4	1,05	1,08	1,10	1,13	1,20
1050–020	❍	0,5	1,0	0,5	2,0	40	0,95	4	2,08	2,13	2,19	2,24	2,38
1100–030	❍	1,0	2,0	1,0	3,0	40	1,95	4	3,13	3,20	3,27	3,35	3,53

NPDB Type Body (for Precision Finishing)

Cat. No.	Stock	Dimensions (mm)							Real effective length with respect to work material gradient angle				
	NPD10	RE	DC	APMX	LF	LU	DN	DMM	0,5°	1°	1,5°	2°	3°
NPDB 1010–004	❍	0,1	0,2	0,1	0,4	40	0,18	4	0,44	0,45	0,46	0,47	0,49
1020–008	❍	0,2	0,4	0,2	0,8	40	0,38	4	0,83	0,84	0,85	0,86	0,89
1030–010	❍	0,3	0,6	0,3	1,0	40	0,58	4	1,05	1,08	1,10	1,13	1,20
1050–020	❍	0,5	1,0	0,5	2,0	40	0,95	4	2,08	2,13	2,19	2,24	2,38
1100–030	❍	1,0	2,0	1,0	3,0	40	1,95	4	3,13	3,20	3,27	3,35	3,53

Identification Details

NPDB	**(S)**	**1**	**030**	**-**	**010**
Series Code	For standard finishing	No. of flutes	Ballnose radius		Length below neck

Recommended Cutting Conditions

- Use a machine with high rigidity for stable cutting.
- Non-water soluble coolant recommended. Supply as a mist or external coolant.
  Take fire prevention precautions to avoid fire hazards caused by sparks igniting during machining or tool breakage.
- Shorten overhang as much as possible.
- Adjust cutting conditions as necessary as machine rigidity and other conditions may vary.
- Depth of cut shown in the table of conditions are maximum depths. Adjust the actual depth of cut to the desired machined surface finish.

● Flat Surface Finishing

Work Material		Carbide			
RE (mm)	LU	Spindle Speed (min^{-1})	Feed Rate (mm/min)	a_p (mm)	a_e (mm)
0,1	0,4	40.000	100	0,001	0,001
0,2	0,8	40.000	150	0,001	0,001
0,3	1,0	40.000	200	0,001	0,001
0,5	2,0	40.000	400	0,001	0,003
1,0	3,0	40.000	600	0,001	0,005

● Copy Finishing

Work Material		Carbide			
RE (mm)	LU	Spindle Speed (min^{-1})	Feed Rate (mm/min)	a_p (mm)	a_e (mm)
0,1	0,4	40.000	100	0,001	0,001
0,2	0,8	40.000	150	0,002	0,001
0,3	1,0	40.000	200	0,003	0,001
0,5	2,0	40.000	400	0,005	0,003
1,0	3,0	40.000	600	0,010	0,005

DAL/DDL/DML Type

From general to High Precision Drilling of Aluminum Alloys!

- High precision DAL type is able to produce holes of IT Class of 7 – 8.
- General DDL type is able to produce holes of IT class of 11 – 12, mainly for drilling of pre-tap holes.
- DML type is DDL type with a chamfer edge, incorporating 2 processes in one operation.

■ DAL Type



Cat. No.	DA2200	DC (DMM)	LCF	OAL	PL
DAL 0500H – 0600H		Ø5 ≤ DC ≤ Ø6	31,6	84,6	1,6
0601H – 0700H		Ø6 < DC ≤ Ø7	36,9	91,9	1,9
0701H – 0800H		Ø7 < DC ≤ Ø8	37,2	92,2	2,2
0801H – 0900H		Ø8 < DC ≤ Ø9	42,5	102,5	2,5
0901H – 1000H		Ø9 < DC ≤ Ø10	42,8	102,8	2,8
1001H – 1100H		Ø10 < DC ≤ Ø11	53,1	113,1	3,1
1101H – 1200H		Ø11 < DC ≤ Ø12	53,4	113,4	3,4

■ DDL Type



Cat. No.	DA2200	DC (DMM)	LCF	OAL	PL
DDL 050V – 060V		Ø5 ≤ DC ≤ Ø6	31,5	81,0	1,0
061V – 070V		Ø6 < DC ≤ Ø7	36,2	91,2	1,2
071V – 080V		Ø7 < DC ≤ Ø8	36,4	91,4	1,4
081V – 090V		Ø8 < DC ≤ Ø9	41,6	101,6	1,6
091V – 100V		Ø9 < DC ≤ Ø10	41,7	101,7	1,7
101V – 110V		Ø10 < DC ≤ Ø11	51,9	111,9	1,9
111V – 120V		Ø11 < DC ≤ Ø12	52,1	112,1	2,1

■ Recommended Conditions

DC (mm)	Cutting Speed (m/min)	Feed Rate (mm/rev)	Drilling Length L/D	Oil
<8	80–250	0,05–0,2	Below 3 x D	Water soluble
≥ 8 ≤ 12		0,1–0,3		

■ Important Notes

- Select a high rigidity machine and high precison tool holder.
- Enough coolant to drilled hole.

■ Application Examples (DAL Type)

Work Shape	Work	Conditions	Results
	A390 High silicon Aluminum	Vc=100m/min f=0,1mm/rev	• Holes by carbide drill was out of specifications after 2.000 holes/reg. • SumiDia drill could drill up to 30.000 holes/reg. • 15 times tool life that of carbide drills.
	A390 High silicon Aluminum (pre-cast hole of ø10)	Vc=120m/min f=0,12mm/rev	• Average 40,000 holes/reg • Surface roughness Ry = 1µm
	ADC10 Aluminum Die Cast	Vc=90m/min f=0,08mm/rev	• More than 50.000 holes and still running

■ Application Examples (DDL Type)

Work Shape	Work	Conditions	Results
	ADC12 Aluminum Die Cast M8 Pre-tap holes	Vc=214m/min f=0,14mm/rev	• Regrind after 100.000 holes
	ADC12 Aluminum Die Cast	Vc=200m/min f=0,17mm/rev	• Regrind after 74.000 holes (2.000m) (Preset tool change)
	AC2A Aluminum Casting	Vc=234m/min f=0,28mm/rev	• Regrind after 80.000 holes (Preset tool change)



■ DML Type



Applicable Tap Size	Cat. No.	Stock DA2200	øD	ød	L	ℓ1	ℓ2
M6	DML 050V		5	8	90	18	36
M8	DML 068V		6,8	10	104	24	48
M10	DML 085V		8,5	12	122	30	60
M12	DML 103V		10,3	14	136	36	72

■ Application Examples (DML Type)

Work Shape	Work	Conditions	Results
	AC4C-T6 Aluminum Casting M6 Pre-tap holes	Vc=100m/min f=0,1mm/rev m/c=6 spindles	• Regrind after 150.000 holes • Tool life for carbide drill is 500 holes. • 30 times tool life that of carbide drills
	AC2C-T2 Aluminum Casting M8 Pre-tap holes	Vc=210m/min f=0,15mm/rev	• 100.000 holes/reg (2.000m) and still running. • Dilling and chamfering in the same process
	AC4C-T6 Aluminum Casting M10 Pre-tap holes	Vc=250m/min f=0,2mm/rev	• 80.000 holes/reg (1,840m) and still running. • Drilling and chamfering in the same process

■ DML Type Possible Profiles



(1) Tolerance for dimension L is more than 0,2mm.
(2) θ° is less than 180°.

N

Technical Guidance References

N1–N24



Basics of Turning

■ Calculating Power Requirement

$$P_c = \frac{d_{oc} \cdot f \cdot v_c \cdot K_c}{60 \times 10^3 \times \eta}$$

$$H = \frac{P_c}{0{,}75}$$

P_c : Net power requirement (KW)
v_c : Cutting speed (m/min)
f : Feed rate (mm/rev)
a_p : Depth of cut (mm)
η : Machine efficiency (0,70 ~ 0,85)
K_c : Specific cutting force (N/mm²)
H : Required horsepower (HP)

● Rough value of specific cutting force (K_c)

General steel :	2.500 ~ 3.000 N/mm²
Cast iron :	1.500 N/mm²
Aluminum :	800 N/mm²

■ Cutting Force



F_1 : Principal force
F_2 : Feed force
F_3 : Back force

● Calculating cutting force

$$P = K_c \cdot q = \frac{k_c \times d_{oc} \times f}{1000}$$

P : Cutting force (N)
K_c : Specific cutting force (N/mm²)
q : Chip area (mm²)
d_{oc} : Depth of cut (mm)
f : Feed rate (mm/rev)

■ Cutting Speed and Cutting Force



■ Rake Angle and Cutting Force



■ Calculating Cutting Speed

① Calculating rotational speed from cutting speed

$$n = \frac{1000 \cdot v_c}{\pi \cdot D}$$

n : Spindle speed (min⁻¹)
v_c : Cutting speed (m/min)
D : Diameter of workpiece (mm)
$\pi \approx 3{,}14$

(Eg.) v_c =150m/min, D=100mm

$$n = \frac{1000 \times 150}{3{,}14 \times 100} = 478\ (\text{min}^{-1})$$

② Calculating cutting speed from rotational speed

$$v_c = \frac{\pi \cdot D \cdot n}{1.000}$$

Refer to the above table



n : Spindle speed (min⁻¹)
v_c : Cutting speed (m/min)
f : Feed rate (mm/rev)
d_{oc} : Depth of cut (mm)
D_m : Diameter of workpiece (mm)

■ Feed Rate and Specific Cutting Force

(For carbon steel)



When feed rate decreases, specific cutting force increases.

■ Roughness

● Theoretical Surface Finish

$$Rz = \frac{f^2}{8 \times r}$$

Rz : Surface finish (mm)
f : Feed rate (mm/rev)
r : Nose radius (mm)



● Actual surface roughness

Steel :
Theoretical surface finish x 1,5 ~ 3
Cast iron :
Theoretical surface finish x 3 ~ 5

● Ways to Improve Surface Finish

① Use an insert with a larger nose radius.

② Optimize the cutting speed and feed rate so that built-up edge does not occur.

③ Select an appropriate insert grade.

④ Use wiper insert.

■ Nose Radius and Cutting Force



Large nose radius increases back force.

Work : 42CrMo4 (Hs38)
Inserts : TNGA2204○○
Holder : PTGNR2525-43
Condition : v_c =100m/min
d_{oc} =4mm
f =0,45mm/rev

Tool Failures and Tool Life

■ Forms of Tool Failures



Cat.	No.	Name of Failure	Cause of Failure
Resulting from Mechanical causes	1~5	Flank Wear	Due to the scratching effect of hard grains contained in the work material.
	6	Chipping	Fine breakages caused by high cutting loads or chattering.
	7	Fracture	Due to the impact of an excessive mechanical force acting on the cutting edge.
Resulting from Chemical reactions	8	Crater Wear	Swaft chips removing tool material as it flow over the top face at high temperatures.
	9	Plastic Deformation	Cutting edge is depressed due to softening at high temperatures.
	10	Thermal Crack	Fatigue from rapid, repeated heating and cooling cycles during machining.
	11	Built-up Edge	Work material is pressure welded on the top face of the cutting edge.

■ Tool Wear

Forms of Tool Wear



Flank wear	Crater wear
	
Wear is rapid initially, then it proceeds more gradually in proportion with cutting time until a certain limit, beyond which it increases rapidly again.	Crater wear is more progressive with no sudden breakdown pattern.

■ Tool Life (V-T)

Measure the relative tool lives of the specified wear, over a range of cutting speeds, then plot the tool life along the X-axis and the cutting speed along the Y-axis on a double logarithm graph.

	Flank wear	Crater wear
Tool wear		
Tool life		

Tool Failure and Remedies

■ Trouble Shooting Guide for Turning

	Damage	Cause	Countermeasures
Tool Edge Failure	Excessive flank wear 	- Grade lacks wear resistance. - Cutting speed ist too fast. - Feed rate ist far too slow.	- Select a wear resistant grade. P30 ⇨ P20 ⇨ P10 K20 ⇨ K10 ⇨ K01 - Use an insert with a larger rake angle. - Decrease the cutting speed. - Increase feed rates.
	Excessive crater wear 	- Grade lacks crater wear resistance. - Rake angle is too small. - Cutting speed is too fast. - Feed rate and depth of cut are too large.	- Select a more crater-resistant grade. - Use an insert with a larger rake angle. - Select an appropriate chipbreaker. - Decrease the cutting speed. - Decrease the D.O.C. and feed rate.
	Cutting edge chipping 	- Grade lacks toughness. - Insert falls off due to chip build-up. - Cutting edge lacks toughness. - Feed rate and depth of cut are too large.	- Change to tougher grades. P10 ⇨ P20 ⇨ P30 K01 ⇨ K10 ⇨ K20 - Increase amount of honing on cutting edge. - Reduce rake angle. - Reduce feed rates and depth of cut.
	Cutting edge fracture 	- Grades lacks toughness. - Cutting edge lacks toughness. - Holder lacks toughness. - Feed rarte is too fast. - Depth of cut is too large.	- Change to tougher grades. P10 ⇨ P20 ⇨ P30 K01 ⇨ K10 ⇨ K20 - Select a chipbreaker with a strong cutting edge. - Select a holder with a larger approach angle. - Select a holder with a larger shank size. - Decrease the D.O.C. and feed rate.
	Build-up edge 	- Inappropriate grade selection. - Dull cutting edge. - Cutting speed is too slow. - Feed rate ist too slow.	- Select a grade with less affinity to the work material. Coated carbide or cermet grades. - Select a grade with a smooth coating. - Use an insert with a larger rake angle. - Reduce amount of honing. - Increase cutting speeds. - Increase feed rates.
	Plastic deformation 	- Grade lacks thermal resistance. - Cutting speed is too fast. - Feed rate is too fast. - Depth of cut is too large. - Not enough cutting fluid.	- Select a more crater-wear-resistant grade. - Use an insert with a larger rake angle. - Decrease the cutting speed. - Reduce feed rates and depth of cut. - Supply a sufficient amount of coolant.
	Notch wear 	- Grade lacks wear resistance. - Rake angle is too small. - Cutting speed is too fast.	- Select a wear resistant grade. P30 ⇨ P20 ⇨ P10 K20 ⇨ K10 ⇨ K01 - Use an insert with a larger rake angle. - Alter depth of cutto shift the notch location.

Chip Control

Type of Chip Generation

	a	b	c	d
Shape				
Condition	Continuous chips with good surface finish.	Chip is sheared and separated by the shear angle.	Chips appear to be torn from the surface.	Chips crack before reaching the cutting point.
Application	Steel, Stainless steel	Steel, Stainless steel (Low speed)	Steel, Cast iron (Very low speed, very small feedrate)	Cast iron, Carbon
Influence factor	Easy ← Work deformation → Difficult Large ← Rake angle → Small Small ← D.O.C. → Large Fast ← Cutting speed → Slow			

Type of Chip Control

Feed rate	A	B	C	D	E
Large feed rate					
Small feed rate					
NC lathe (For automation)	×	×	○	○	△
General lathe (For safety)	×	○	○	○ ~ △	×

Good : C type, D type

Poor
- A type : Twines around the tool or workpiece, damages the machined surface and affects safety.
- B type : Bulky, causes problems in the automatic chip conveyor and chipping occurs easily.
- E type : Causes spraying of chips, poor machined surface due to chattering, chipping, large cutting force and high temperatures.

Factor of Improvement Chip Control

① Increase feed rate



When feedrate increase, chips become thick and chip control improves.



② Decrease side cutting edge



Even if feed rate is the same, smaller side cutting edge angle makes chips thick and chip control improves.



③ Decrease nose radius



Even if depth of cut is the same, smaller nose radius makes chip thick and chip control improves.

* Cutting resistance increases in proportion with the width of the contact surface. Therefore, with a larger nose radius, cutting resistance and back force increases, chattering may also occur. However, with the same feedrate, a smaller nose radius would produce a poorer surface finish.



Basics of Milling

■ Parts of a Milling Cutter



■ Power Requirement

● Calculating cutting force

$$P_c = \frac{d_{oc} \cdot w_{oc} \cdot v_f \cdot K_c}{60 \times 10^6 \times \eta} \text{ (kW)}$$

● Horsepower

$$H = \frac{Pc}{0{,}75}$$

● Chip removal amount

$$Q = \frac{d_{oc} \times w_{oc} \times v_f}{1.000} \text{ (cm}^3\text{/min)}$$

P_c : Net power requirement (kW)
H : Horsepower requirement (HP)
Q : Chip removal amount (cm^3/min)
w_{oc} : Cutting width (mm)
v_f : Feed speed (mm/min)
d_{oc} : Depth of cut (mm)
η : Machine efficiency (0,70 ~ 0,85)
K_c : Specific cutting forrce (N/mm^2)

Eg. rough value
(Steel : 2.500 ~ 3.000
Cast iron : 1.500)

● Relation between feed rate, work material, specific cutting force

Work-piece No.	Alloy steel	Carbon steel	Cast iron	Aluminum alloy
①	1.800	800	200	–
②	1.400	600	160	–
③	1.000	400	120	–

Values in the table show the following properties:
- Tensile strength (N/mm^2) for alloy steel and carbon steel
- Hardness (H_B) for cast iron



● Calculating cutting speed

$$v_c = \frac{\pi \times D \times n}{1.000}$$

v_c : Cutting speed (m/min)
$\pi \approx 3{,}14$
D : Cutter diameter (mm)
n : Rotation speed (rpm)
v_f : Feed speed (mm/min)
f_t : Feed rate (mm/tooth)
z : Number of teeth

● Calculating feed rate

$$v_f = f_t \times z \times n$$

$$f_t = \frac{v_f}{z \times n}$$



Functions of the Various Cutting Angles

	Description	Code	Functions	Influences
① ②	Axial rake angle Radial rake angle	γ_y γ_x	Controls chip removal direction, effects adhesion of the chips and thrust force etc.	Rake angles can vary from positive to negative (large to small) with typical combinations of positive and negative, positive and positive or negative and negative configurations.
③	Approach angle	κ	Controls chip thickness and chip removal direction	The effect of the small approach angle is to reduce the chip thickness and cutting force.
④	True rake angle (Effective rake angle)	γ	Controls cutting performance and ability to retain a cutting edge	- With a positive (large) angle, cutting ability and adhesion resistance are improved but the strength of the cutting edge is weakened. - With negative (small) angle, the strength of the cutting edge is improved but chips will tend to adhere more easily.
⑤	Inclination angle	λ	Controls chip removal direction	- With a positive (large) angle, the chip removal is satisfactory with less cutting resistance but the strengh of the corner is weaker.
⑥	Wiper flat clearance angle	α_f	Controls surface finish	A smaller clearance angle will produce a better surface finish.
⑦	Clearance angle	α	Controls edge strength, tool life and chattering, etc	

True Rake Angle Chart



Example in using the above chart:		Solution:
① γ_y :	Axial rake angle = +10°	True rake angle
② γ_x :	Radial rake angle = -30°	④ γ = - 8°
③ κ :	Approach angle = 30°	

Formula : $\tan\gamma = \tan\gamma_x \cdot \sin\kappa + \tan\gamma_y \cdot \cos\kappa$

Inclination Angle Chart



Example in using the above chart :		Solution:
① γ_y :	Axial rake angle = -10°	Inclination angle
② γ_x :	Radial rake angle = +10°	⑤ λ = - 15°
③ κ :	Approach angle = 65°	

Formula : $\tan\lambda = \tan\gamma_y \cdot \sin\kappa - \tan\gamma_x \cdot \cos\kappa$

Rake Angle Combination

	Negative - Positive Type	Double Positive Type	Double Negative Type
The effects of the various angle configurations with relation to chip formation and chip removal. Chip removal direction Rotation			
Advantage	Excellent chip removal and good cutting action	Good cutting action	Double-sided inserts can be use and higher cutting edge strength
Disadvantage	Only single-sided inserts can be use	Lower cutting edge strength and only single-sided inserts can be use	Dull cutting action
Application	For Steel, Cast iron, Stainless steel, Alloy steel	For general milling of steel For low rigidly work piece	For light milling of cast iron and steel
Typical cutter	WGX, WGC, UFO	DPG	DNX, DGC, DNF
Chips (Eg.) Workpiece: 37Cr4 v_c = 130 m/min f_t = 0.23 mm/tooth d_{oc} = 3 mm			

Basics of Milling

■ Relation Between Engage Angle and Tool Life



Engage angle denotes the angle by which the full length of the cutting edge comes in contact with the workpiece, with reference to the feed direction. The larger E is, the shorter the tool life.

To change the value of E:
1) Increase the cutter size
2) Shift the position of the cutter



● Relation between the number of simultaneously engaged cutting edges and cutting force:



0 or 1 edge in contact

Only 1 edge in contact at any time.

1 or 2 edges in contact

2 edges in contact at any time.

2 to 3 edges in contact

■ To Improve Surface Roughness

① Milling inserts with wiper flat

When all the cutting edges have wiper flats, a few teeth are intentionally elevated to play the role of a wiper insert.

- Insert equipped with straight wiper flat (Face angle: Approx 15' - 1°)
- Insert equipped with curved wiper flat (Eg. curvature R500)

② Integral wiper insert system

A system to protrude one or two inserts (wiper insert) with a smooth curved edge just a little beyond the other teeth to wipe the milled surface.

- (Applies to WGC, RF types etc.)

● Surface roughness without wiper flat



● Surface roughness with straight wiper flat



h : Projected value of wiper insert
Steels : 0,05 mm
Al : 0,03 mm



f : Feed rate per revolution



Hc : Surface roughness with only normal teeth
Hw : Surface roughness with wiper insert

● Influence of different face angles on surface finish



- Workpiece: 34CrMo4
- Cutter: DPG 5160 R (Single tooth)
- v_c = 154 m/min
  f_t = 0,234 mm/tooth
  d_{oc} = 2 mm
- Face angle
  Ⓐ : 28'
  Ⓑ : 6'

● Effects of having wiper insert (example)



- Workpiece: GG25
- Cutter: DPG 4100 R
- Insert: SPKN 1203
- Axial run-out: 0,015 mm
- Radial run-out: 0,04 mm
- v_c = 105 m/min
- f_t = 0,29 mm/tooth (1,45 mm/rev)

Ⓒ : Only normal teeth
Ⓓ : with 1 wiper insert

■ Trouble Shooting Guide for Milling

<table>
<tr><th colspan="2">Trouble</th><th colspan="2">Basic Remedies</th><th>Remedy Examples</th></tr>
<tr><td rowspan="5">Cutting Edge Failure</td><td>Excessive Flank Wear
  </td><td>Tool Material

Cutting Conditions</td><td>- Select a more wear resistant grade.
Carbide
P30 ⇨ P20 ⇨ K20 ⇨ K10 ⇨ { Coated / Cermet
- Reduce cutting speeds.
- Increase feedrate.</td><td>- Recommended insert grades
<table><tr><th></th><th>Steel</th><th>Cast Iron</th><th>Non-Ferrous Alloy</th></tr><tr><td>Finishing</td><td>T250A (Cermet)</td><td>ACK200 (Coated Carbide)
BN700 (SUMIBORON)</td><td>DA1000 (SUMIDIA)</td></tr><tr><td>Roughing</td><td>ACP100 (Coated Carbide)</td><td>ACK200 (Coated Carbide)</td><td>DL1000 (Coated Carbide)</td></tr></table></td></tr>
<tr><td>Excessive Crater Wear
  </td><td>Tool Material

Cutting Conditions</td><td>- Select a crater resistant grade.
- Reduce cutting speeds.
- Reduce depth-of-cut and feed rate.</td><td>- Recommended insert grades
<table><tr><th></th><th>Steel</th><th>Cast Iron</th><th>Non-Ferrous Alloy</th></tr><tr><td>Finishing</td><td>T250A (Cermet)</td><td>ACK200 (Coated Carbide)</td><td>DA1000 (SUMIDIA)</td></tr><tr><td>Roughing</td><td>ACP100 (Coated Carbide)</td><td>ACK200 (Coated Carbide)</td><td>DL1000 (Coated Carbide)</td></tr></table></td></tr>
<tr><td>Cutting Edge Chipping
  </td><td>Tool Material

Cutting Conditions

Tool Design</td><td>- Select tougher grade.
P10 ⇨ P20 ⇨ P30
K01 ⇨ K10 ⇨ K20
- Reduce feed rates.
- Select a negative-positive cutter configuration with a large approach angle.
- Reinforce the cutting edge (Honing).
- Select a strong edge insert (G → H).</td><td>- Recommended insert grades
<table><tr><th></th><th>Steel</th><th>Cast Iron</th></tr><tr><td>Finishing</td><td>ACP200 (Coated Carbide)</td><td>ACK200 (Coated Carbide)</td></tr><tr><td>Roughing</td><td>ACP300 (Coated Carbide)</td><td>ACK300 (Coated Carbide)</td></tr></table>- Recommended cutter: WaveMill WGX type
- Cutting conditions:
Refer to recommended conditions listed in the general catalogue</td></tr>
<tr><td>Partial Fracture of Cutting Edges
  </td><td>Tool Material

Cutting Conditions

Tool Design</td><td>- If it is due to excessive low speeds or very low feed rates, select an adhesion resistant grade.
- If it is due to thermal cracking, select a thermal impact resistant grade.
- Select appropriate conditions with regards to the particular application.
- Select a negative-positive (or negative) cutter configuration with a large approach angle.
- Reinforce the cutting edge (Honing).
- Select a strong edge insert (G → H).
- Increase insert size -
(Thickness in particular).</td><td>- Recommended insert grades
<table><tr><th></th><th>Steel</th><th>Cast Iron</th></tr><tr><td>Roughing</td><td>ACP300
(Coated Carbide)</td><td>ACK300
(Coated Carbide)</td></tr></table>- Recommended cutter: WaveMill WGX type
- Insert thickness: 3,18 → 4,76mm
- Insert type: Standard → Strong edge type
- Cutting conditions:
Refer to recommended conditions listed in the general catalogue</td></tr>
<tr><td rowspan="5">Others</td><td>Unsatisfactory Machined Surface Finish</td><td>Tool Material

Cutting Conditions

Tool Design</td><td>- Select an adhesion resistant grade.
Carbide → Cermet
- Increase cutting speeds.
- Improve axial run-out of cutting edges.
(Use a cutter with less run-out)
(Attach correct inserts)
- Use wiper inserts.
- Use special purpose cutters designed for finishing.</td><td>- Recommended insert grades
<table><tr><th></th><th></th><th>Steel</th><th>Cast Iron</th><th>Non-Ferrous Alloy</th></tr><tr><td>Roughing</td><td>Cutter Insert</td><td>WGX type*
ACP200
(Coated Carbide)</td><td>DGC type*
ACK200
(Coated Carbide)</td><td>FF type*
H1 (Carbide)
DL1000 (Coated Carbide)</td></tr><tr><td>Finishing</td><td>Cutter Insert</td><td>WGC type
T250A
(Cermet)</td><td>FMU type
BN700
(SUMIBORON)</td><td>RF type
DA1000
(SUMIDIA)</td></tr></table>* marked cutters can be fitted with wiper inserts.</td></tr>
<tr><td>Chattering</td><td>Cutting Conditions
Tool Design

Others</td><td>- Reduce feed rates.
- Select a high rake cutter with sharp cutting edges
- Use an irregular pitched cutter.
- Improve workpiece and cutter clamp rigidity.</td><td>- Recommended cutters:
For steel: WaveMill WGX type
For cast iron: DNX type
For Non-ferrous alloy: High speed cutter for aluminium
RF type</td></tr>
<tr><td>Unsatisfactory Chip Control</td><td>Tool Design</td><td>- Select cutter with good chip removal features.
- Reduce number of teeth.
- Enlarge chip pocket.</td><td>- Recommended cutter: WaveMill WGX type</td></tr>
<tr><td>Edge Chipping on Workpiece</td><td>Tool Design

Cutting Conditions</td><td>- Select a large approach angle.
- Select a sharp cutting edge insert (G → L).
- Reduce feed rates.</td><td>- Recommended cutter: WaveMill WGX type</td></tr>
<tr><td>Burr on Workpiece</td><td>Tool Design
Cutting Conditions</td><td>- Select a cutter with sharp cutting edges.
- Increase feed rates.</td><td>- Recommended cutter: WaveMill WGX type + FG breaker
DGC type + FG breaker</td></tr>
</table>

Basics of Endmilling

■ Parts of an Endmill



■ Calculating Cutting Conditions

● Cutting speed

$$v_c = \frac{\pi \cdot D \cdot n}{1.000} \qquad n = \frac{1.000 \cdot v_c}{\pi \cdot D}$$

● Feed rate

$$v_f = f \times n$$

$$v_f = f_t \times z \times n \qquad f_t = \frac{v_f}{z \times n}$$

● Depth of cut (D.O.C)

d_{oc} : Axial D.O.C. (depth)
w_{oc} : Radial D.O.C. (width)

● Notch width (D_1)

$$D1 = 2 \times \sqrt{2 \times R \times d_{oc} - d_{oc}^2}$$

● Cutting speed and feedrate are calculated using the same formula as square endmill.

Side milling



v_c : Cutting speed (m/min)
$\pi \approx 3{,}14$
D : Endmill diameter (mm)
n : Rotational speed (min^{-1})
v_f : Feed speed (mm/min)
f_r : Feed rate per revolution (mm/rev)
f_t : Feed rate per tooth (mm/tooth)
z : Number of teeth

(Ball Endmill)



Slotting



■ Up-cut and Dowm-cut





■ Relation Between Cutting Condition and Deflection

Endmill			Side milling: Work material: Pre-hardened steel (40HRC); Cutting data: v_c = 25m/min, d_{oc} = 12 mm, W_{oc} = 0,8 mm		Slotting: Work material: Pre-hardened steel (40HRC); Cutting data: v_c = 25m/min, d_{oc} = 8 mm, W_{oc} = 8 mm (Up-cut side / Down-cut side)	
Cat. No.	Number of teeth	Helix angle	Feed rate 0,16 mm/rev	Feed rate 0,11 mm/rev	Feed rate 0,05 mm/rev	Feed rate 0,03 mm/rev
			Style	Style	Style	Style
			Up-cut / Down-cut	Up-cut / Down-cut	Up-cut / Down-cut	Up-cut / Down-cut
SSM 2080	2	30°				
SSM 4080	4	30°				



Tool Failure and Remedies

■ Trouble Shooting Guide for Endmilling

	Failure	Cause		Remedies
Cutting Edge Failure	Excessive Wear	Cutting Conditions	- Cutting speed is too fast - Feed rate is too fast	- Decrease cutting speed and feed rate.
		Tool Shape	- The flank relief angle ist too small	- Change to an appropriate flank relief angle.
		Tool Material	- Insufficient wear resistance	- Select a substrate with more wear resistance - Use a coated tool
	Chipping	Cutting Conditions	- Feed rate ist too fast - Cutting depth is too deep - Tool overhang ist too long	- Decrease cutting speed. - Reduce depth of cut - Adjust tool overhang for correct length
		Machine Area	- Work clamps are weak - Tool is not firmly attached	- Clamp the work piece firmly - Make sure the tool is seated in the chuck properly
	Tool Fracture	Cutting Conditions	- Feed rate ist too fast - Cutting depth is too deep - Tool overhang ist too long - Cutting edge is too long	- Decrease cutting speed. - Reduce depth of cut - Reduce tool overhang as much as possible - Select a tool with a shorter cutting edge
Others	Shoulder Deflection	Cutting Conditions	- Feed rate is too fast - Cutting depth is too deep - Tool overhang is too long - Cutting on the down-cut	- Decrease cutting speed. - Reduce depth of cut - Adjust tool overhang for correct length - Change directions to up-cut
		Tool Shape	- Helix angle is large	- Use a tool with a smaller helix angle
	Unsatisfactory Machined Surface Finish	Cutting Conditions	- Feed rate is too fast	- Decrease cutting speed.
			- Packing of chips	- Use air blow - Use an insert with a larger relief pocket.
	Chattering	Cutting Conditions	- Cutting speed is too fast - Cutting on the up-cut - Tool overhang is too long	- Decrease cutting speed. - Change directions to down-cut - Adjust tool overhang for correct length
		Tool Shape	- Rake angle is large	- Use a tool with an appropriate rake angle
		Machine Area	- Work clamps are weak - Tool is not firmly attached	- Clamp the work piece firmly - Make sure the tool is seated in the chuck properly
	Packing of Chip	Cutting Conditions	- Feed rate is too fast - Cutting depth is too deep	- Decrease cutting speed. - Reduce depth of cut
		Tool Shape	- Too many teeth - Packing of chips	- Reduce number of teeth - Use air blow

Basics of Drilling

■ Parts of a Drill



● Point Angle and Force



When point angle is large, thrust becomes large but torque becomes small.

● Point Angle and Burr



When point angle is large, burr height becomes low.

● Min. Requirement Relief Angle



* Large relief angle is needed at the center of the drill.

● Web Thickness and Thrust



Web thinning decreases the thrust concentrated at chisel edge, makes the drill edge sharp and improves chip control. Tool life is also longer.

● Decrease Chisel Width by Thinning



S type : Standard type used generaly.
N type : Suitable for thin web drills.
X type : For hard-to-cut material or deep hole drilling.

● Width of Edge Threatment and Cutting Force



Drill: KDS 215 MAK
Work material: C50 (230HB)
Cutting conditions:
v_c = 50 m/min, Water soluble

Basics of Drilling

■ Reference of Power Requirement and Thrust





Work material:
C48 (220HB)

■ Cutting Condition Selection

● Control cutting force for low rigid machine

The following table shows the relation between edge treatment width and cutting force. If a problem caused by cutting force occurs, reduce either the feedrate or the edge treatment width.

Condition		Edge treatment width			
		0,15mm		0,05mm	
v_c (m/min)	f (mm/rev)	Torque (N• m)	Thrust (N)	Torque (N• m)	Thrust (N)
40	0,38	12,8	2.820	12,0	2.520
50	0,30	10,8	2.520	9,4	1.920
60	0,25	9,2	2.320	7,6	1.640
60	0,15	6,4	1.640	5,2	1.100

Drill : ø10
Work material:
C50 (230HB)

● High speed machining recommendation

When there is surplus capacity with enough machine power and rigidity drilling at normal recommended cutting conditions, we recommend higher drilling speeds.

Wear example



Vc=60m/min　　Vc=120m/min

Work material: C50 (230HB)
Cutting data: f = 0,3 mm/rev
d_{oc} = 50mm
Tool life: 600 holes (Cutting length : 30m)

■ Explanation of Margins (Difference between single and double margins)

● Single Margin (2 guides: circled parts)



● Shape used on most drills

● D Double Margin (4 guides: circled parts)



● 4-point guiding reduces hole bending and undulation for improved stability and accuracy during deep hole drilling.

Basics of Drilling

■ Run-out Accuracy

Run-out of the lip height B and thinning point A are important.



Ⓐ : The run-out accuracy of thinning point
Ⓑ : The difference of lip height



■ Peripheral Run-out Accuracy when Tool Rotates

Drill run-out when mounted on the machine spindle must be within 0,03mm. If the run-out is large, the drilled hole will also be large causing an increase in the horizontal cutting force, which may result in drill breakage if the machine or work clamping is not rigid.



Run-out: within 0,03mm



Drill: MDS120MK
Work material: C50 (230HB)
Cutting data: v_c=50 m/min, f=0,3 mm/rev, d_{oc} =38mm
Water soluble

■ Peripheral Run-out Accuracy when Workpiece Rotates

When use on a lathe, run-out at point A must be within 0,03mm, this value must be similar when taken at position B.



■ Influence of Workpiece Surface

● Workpiece with slanted or uneven surface

If the surface of the hole entrance or exit is slanted or uneven, decrease the feedrate to 0,1~0,15mm/rev at these points.



■ How to Use Long Drill

● Problem

When using a long drill (e.g. XHGS type and XHT type), DAK type or SMDH-D type drills at high rotational speeds, the run-out of the drill tip may cause a position shift at the entry point making the drill hole bent and resulting in drill breakage.



● Remedies

Method 1.



Method 2. Low rotational speed minimizes centrifugal forces and prevents drill bending.



Tool Failure and Remedies

■ Trouble Shooting Guide for Drilling

Failure		Basic Remedies		Remedies Examples
Drill Failure	Excessive Wear on Cutting Edge	Cutting Conditions	- Use higher cutting speeds. - Increase feed rates.	- Vc=80~100m/min - Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid	- Reduce pressure if useing internal coolant. - Use cutting fluid with more lubricity.	- Below 1,5MPa.
	Chisel Point Chipping	Tool Design	- Increase size of chisel width. - Increase amount of honing on cutting edge.	
		Cutting Conditions	- Reduce depth-of cut. - Reduce feed rate at entry point.	- f = 0,05~0,1 mm/rev .
		Others	- Improve workpiece clamping rigidity.	
	Chipping on Peripheral Cutting Edge	Tool Design	- Increase amount of honing on cutting edge. - Reduce the amount of front flank angle.	
		Cutting Conditions	- Reduce cutting speeds. - Increase feed rates.	- Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid Others	- Use cutting fluid with more lubricity. - Improve workpiece clamp rigidity.	
	Margin Wear	Tool Design	- Increase amount of back taper. - Reduce margin width.	
		Cutting Conditions	- Reduce cutting speeds. - Increase feed rates.	- Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid Others	- Use cutting fluid with more lubricity. - Schedule for earlier regrind.	
	Drill Breakage	Tool Design	- Increase amount of back taper. - Reduce margin width.	
		Cutting Conditions	- Reduce cutting speeds.	- Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid Others	- Use cutting fluid with more lubricity. - Improve workpiece clamp rigidity.	
Unsatisfactory Hole Accuracy	Oversized Holes	Tool Design	- Improve overall dril rigidity. (large web, small flute). - Reduce drill point angle.	- 130°~120°
		Cutting Conditions	- Reduce feed rate at entry phase. - Reduce cutting speeds.	- f = 0,05~0,1 mm/rev - Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid Others	- Improve workpiece clamp rigidity. - Improve drill clamp precision. - Improve drill clamp rigidity.	- Drill run-out below 0,02mm
	Poor Surface Finish	Tool Design	- Increase amount of back taper.	
		Cutting Conditions	- Increase cutting speeds.	- Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid	- Use cutting fluid with more lubricity.	
	Holes are Not Straight	Tool Design	- Reduce amount of edge honing.	
		Cutting Conditions	- Reduce feedrates.	- Refer to recommended cutting conditions listed in the general catalogue.
		Others	- Improve workpiece clamp rigidity. - Improve drill clamp precision. - Improve drill clamp ridigity.	- Drill run-out below 0,02mm
Unsatisfactory Chip Control	Packing of Chips	Cutting Conditions	- Increase cutting speeds. - Increase feed rates.	- Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid	- Reduce pressure if using internal coolant.	- Below 1,5MPa.
	Long Stringy Chips	Tool Design	- Reduce amount of edge honing.	
		Cutting Conditions	- Increase feed rates.	- Refer to recommended cutting conditions listed in the general catalogue.
		Cutting Fluid	- Reduce pressure if using internal coolant.	- Below 1,5MPa.

Application Map of the Various Tool Materials



Work Materials and Cutting Speed Recommendations



Influence of Coolant on Tool Life

● Continuous cutting



● Interrupted cutting

Work material: X155CrVMo12-1
Cutting data: v_c = 100 m/min
d_{oc} = 0,2 mm
f = 0,1 mm/rev



Work material: 100Cr6 (HRC58~62)
Insert: TPGN160304
Cutting data: v_c = 100 m/min
d_{oc} = 0,15 mm
f = 0,1 mm/rev

For continuous cutting, the influence of coolant on tool life is minimal. However for interrupted cutting, coolant will shorten the tool life because of thermal cracking.

Relation Workpiece Hardness and Cutting Forces





Work material: C105W1
Cutting data: v_c = 120 m/min
d_{oc} = 0,2 mm
f = 0,1 mm/rev

Back force increases substantially for harder work materials.

Relation between Flank Wear and Cutting Force



Cutting data: v_c = 80 m/min
d_{oc} = 0,15 mm
f = 0,1 mm/rev

For hardened steel machining, back force increases substantially due to the expansion of flank wear.

Workpiece Hardness on Cutting Force and Accuracy



Cutting data: v_c = 120 m/min
d_{oc} = 0,5 mm
f = 0,3 mm/rev
dry

External dimension at the soft zone is smaller due to lower cutting forces.

Relation Cutting Speed and Surface Roughness



Work material: 25CrMo4 (HRC58~62)
Holder: MTXNR2525
Insert: TNMA160408NU

Cutting data:
v_c= 120, 150, 180 m/min
d_{oc} = 0,15 mm
f = 0,045 mm/rev
Wet

At high cutting speeds, surface roughness is more stable.

Improvement of Surface Roughness by Altering the Feedrate

Constant Feedrate	Variable Feedrate
Previous edge position f Stationary notch location	f Shifting notch location
	

Varying the feedrate spreads the notch location over a larger area, surface finish improves and notch wear decreases.

■ Advantages of Using SUMIBORON for Cast Iron Machining

● Higher accuracy



● Longer tool life at higher cutting speeds

GG: Grey cast iron



GGG: Ductile cast iron



■ Turning

● Cast iron structure and wear shape examples

		GG	GGG
Structure			
	Matrix	Pearlite	Pearlite + Ferrite
Tool wear shape	Wet		
	Dry	 Crater wear	

($v_c \geq 200$ m/min)



Work material: GG25
Insert: SNGN120408(BN500)
Cutting data: v_c = 450 m/min
d_{oc} = 0,25 mm
f = 0,15 mm/rev
Continuous cutting





For machining cast iron with SUMIBORON, cutting speeds (Vc) should be 200m/min and above. WET cutting is recommended.

Machine: N/C lathe
Work material: GG25 (HB200)
Holder: MTJNP2525
Insert: TNMA160408(BN500)
Cutting data: v_c = 110~280 m/min
d_{oc} = 0,1 mm
f = 0,1 mm/rev
WET

■ Milling

SUMIBORON BN Finish Mill EASY

- High speed machining Vc = 2000m/min
- Surface Roughness Rz=3,2 (Ra=1,0)
- Running cost is reduced because of economical insert
- Easy insert setting with the aid of a setting gauge
- Safe, anti-centrifugal force construction for high speed conditions



Work material: GG25
Tool material: BN700
Cutting data: d_{oc} = 0,5 mm, f_t = 0,1 mm/tooth, DRY



Dry cutting is recommended for high speed milling of cast iron with SUMIBORON.

■ Powder Metal



Work material: SMF4040 equivalent
Process details: ø100~300mm heavy interrupted facing with grooves and drilled holes. (after 40 passes)
Insert: TNGA160404 Cutting data: f=0.1mm/rev, d=0.1mm, Wet

For general power metal components, carbide and cermet grades can perform up to Vc=100m/min. However, around Vc=120m/min, wear becomes rapid and surface roughness deteriorates with increased burrs.
SUMIBORON on the other hand, exhibits stability and superior wear resistance, burr prevention and surface roughness especially at high speeds.

■ Heat Resistive Alloy

● Ni based alloy

Typical tool damage of CBN tool when cutting Inconel 718

● Influence of cutting speed (Grade BNX20, f =0,06 mm/rev., L=0,72km)



● Influence of feedrate (Grade BNX20, Vc=300m/min, L=0,18km)



● Influence of tool grade (Vc=500m/min, f =0,12 mm/rev, L=0,36km)



Cutting data: d_{oc} = 0,3mm, WET

0,5mm

Cutting data: f = 0,06mm/rev, d_{oc} = 0,3mm, WET



Tool life criteria
Notch wear = 0,25mm
Or flank wear = 0,25mm
BNX20 is recommended for high speed and low feedrate condition.
BN700 is recommended for cutting speeds below 240m/min

Cutting data: f = 0,12mm/rev, d_{oc} = 0,3mm, WET



Tool life criteria
Notch wear = 0,25mm
Or flank wear = 0,25mm
BN700 is recommended for cutting at high feedrates.
(Over f=0,1mm/rev)

● Ti based alloy



Work Material: Ti-6Al-4V
Insert: DNM120404NF
Cutting data: v_c = 100m/min, d_{oc} = 0,1mm, f = 0,05mm/rev, WET
SUMIDIA positive type inserts are extremely good for Ti alloy, due to high cutting edge strength and high wear resistance.



Work Material: Ti-6Al-4V
Insert: DNM120404NF
Cutting data: v_c = 100m/min, d_{oc} = 0,1mm, f = 0,05mm/rev, WET
SUMIDIA positive type inserts are extremely good for Ti alloy, due to high cutting edge strength and high wear resistance.



Work Material: Ti-6Al-4V
Insert: DNMA150412
Cutting data: Vc = 120m/min, d_{oc} = 0,3mm, f =0,25mm/rev, WET
Negative type insert BN700 is excellent for high efficiency cutting. (For large depth of cut and high feedrates)

● Hard facing alloys

Work material: Colmonoy No.6 (Ni-based self fluxing alloy)

Insert: SNGN090308
Cutting data:
v_c = 50, 300 m/min
f = 0,1 mm/rev
d_{oc} = 0,2 mm
Wet



Work material: Stellite SF-20 (Co-based Self-fluxing alloy)

Insert: SNGN090308
Cutting data:
v_c = 50 m/min
f = 0,1 mm/rev
d_{oc} = 0,2 mm
Dry



BNS800
(Vc=300m/min, After 2km Cutting)

Whisker reinforced ceramic
(Vc=50m/min, After 10m Cutting)

BNS800
(After 2km of cutting)

Competitor's solid CBN
(After 2km of cutting)

Cutting Edge Failure

Damage	Remedies	
Large flank wear 	Tool material Tool design Cutting condition	☞ Select a more wear resistant grade. ☞ Reduce the cutting force. ☞ Reduce the NL width and angle. ☞ Positive inserts preferred ☞ Check the cutting speed. ☞ Reduce the cutting speed to less than 200m/min. ☞ Higher feed rate reduces the overall tool-to-work contact time.
Large crater wear 	Tool material Tool design Cutting condition	☞ Crater wear resistant grades are recommended. Continuous ~ Light interrupted cutting = BNC2010 Light ~ Medium interrupted cutting = BNX20 Medium ~ Heavy interrupted cutting = BNX25 ☞ Determine the cutting edge geometry after inspecting the used inserts closely. ☞ Sharpen the cutting edge to prevent crater wear. ☞ Strengthen the cutting edge to prevent crater breakage. ☞ Check the cutting speed. ☞ Reduce the cutting speed to less than 200m/min. ☞ Higher feed rates are recommended.
Breakage at bottom of crater 		
Flaking 	Tool material Tool design Cutting condition	☞ Flaking is caused by high back forces and back force is related to flank wear. ☞ Select a more wear resistant grade. ☞ A sharper cutting edge helps prevent flaking. ☞ Reduce the NL angle and width ☞ Positive inserts preferred ☞ Reduce flank wear with lower speed and higher feed rates. ☞ Reducing tool-to-work contact time effectively reduces flank wear.
Chipping at notch position 	Cutting condition	☞ If surface finish is affected, consider using the “Variable Feed rate” method to improve finishing. ☞ For other cases, use remedies similar to that for normal wear.
Chipping at notch position 	Tool material Tool design Cutting condition	☞ Caused by impact shocks to the cutting edge. Chattering may also be a contributing factor. ☞ Select a tougher grade. ☞ Strengthen the cutting edge. ☞ Large NL angle, Honing. ☞ Higher feed rates are recommended to lessen the number of impacts.
Chipping at nose position 	Tool material Tool design Cutting condition	☞ Caused by impact shocks to the cutting edge. Chattering may also be a contributing factor. ☞ Select a tougher grade. ☞ Strengthen the cutting edge. ☞ Large NL angle, Honing. ☞ Higher feedrates are recommended to lessen the number of impacts.
Thermal crack 	Cutting condition Tool design Tool material	☞ Thermal shocks generate vertical crack lines across the cutting edge. Completely dry condition is recommended. ☞ If dry condition machining is already observed, then reduction of cutting temperatures and cutting force is necessary. ☞ Decrease cutting speed, feedrate, depth of cut. ☞ Sharpen cutting edge. ☞ Select more thermal conductivity grade.

■ Steel and Non-Ferrous Metal Symbols Chart

● Carbon Steels

JIS	AISI	DIN
S10C	1010	C10
S15C	1015	C15
S20C	1020	C22
S25C	1025	C25
S30C	1030	C30
S35C	1035	C35
S40C	1040	C40
S45C	1045	C45
S50C	1049	C50
S55C	1055	C55

● Ni-Cr-Mo Steels

SNCM220	8620	21NiCrMo2
SNCM240	8640	—
SNCM415	—	—
SNCM420	4320	—
SNCM439	4340	40NiCrMo6
SNCM447	—	34NiCrMo6

● Cr Steels

SCr415	—	15CrMo5
SCr420	5120	20Cr4
SCr430	5130	34Cr4
SCr435	5132	37Cr4
SCr440	5140	41Cr4
SCr445	5147	—

● Cr-Mo Steels

SCM415	—	15CrMo5
SCM420	—	20CrMo5
SCM430	4131	25CrMo4
SCM435	4137	34CrMo4
SCM440	4140	42CrMo4
SCM445	4145	—

● Mn Steels and Mn-Cr Steels for Structural Use

SMn420	1522	—
SMn433	1534	—
SMn438	1541	—
SMn443	1541	—
SMnC420	—	—
SMnC443	—	—

● Cr-Mo Steels

SK1	—	—
SK2	W1-11 1/2	—
SK3	W1-10	C105W1
SK4	W1-9	—
SK5	W1-8	C80W1
SK6	—	C80W1
SK7	—	C70W2

● High Speed Steels

JIS	AISI	DIN
SKH2	T1	—
SKH3	T4	S18-1-2-5
SKH10	T15	S12-1-4-5
SKH51	M2	S6-5-2
SKH52	M3–1	—
SKH53	M3–2	S6-5-3
SKH54	M4	—
SKH56	M36	—

● Alloy Tool Steels

SKS11	F2	—
SKS51	L6	—
SKS43	W2-9 1/2	—
SKD1	D3	X210Cr12
SKD11	D2	X155CrVMo12-1
SKD61	—	X40CrVMo5-1

● Grey Cast Iron

FC100	No 20B	GG-10
FC150	No 25B	GG-15
FC200	No 30B	GG-20
FC250	No 35B	GG-25
FC300	No 45B	GG-30
FC350	No 50B	GG-35

● Nodular Cast Iron

FCD400	60-40-18	GGG-40
FCD450	—	GGG-40.3
FCD500	80-55-06	GGG-50
FCD600	—	GGG-60
FCD700	100-70-03	GGG-70

● Ferritic Stainless Steels

SUS405	405	X10CrAl13
SUS429	429	—
SUS430	430	X6Cr17
SUS430F	430F	X7CrMo18
SUS434	434	X6CrMo17 1

● Martensitic Stainless Steels

SUS403	403	—
SUS410	410	X10Cr13
SUS416	416	—
SUS420JI	420	X20Cr13
SUS420F	420F	—
SUS431	431	X20CrNi17 2
SUS440A	440A	—
SUS440B	440B	—
SUS440C	440C	—

● Austenitic Stainless Steels

JIS	AISI	DIN
SUS201	201	—
SUS202	202	—
SUS301	301	X12CrNi17 7
SUS302	302	—
SUS302B	302B	—
SUS303	303	X10CrNiS18 9
SUS303Se	303Se	—
SUS304	304	X5CrNiS18 10
SUS304L	304L	X2CrNi19 11
SUS304NI	304N	—
SUS305	305	X5CrNi18 12
SUS308	308	—
SUS309S	309S	—
SUS310S	310S	—
SUS316	316	X5CrMo17 12 2
SUS316L	316L	X2CrNiMo17 13 2
SUS316N	316N	—
SUS317	317	—
SUS317L	317L	X2CrNiMo18 16 4
SUS321	321	X6CrNiTi18 10
SUS347	347	X6CrNiNb18 10
SUS384	384	—

● Heat Resisting Steels

SUH31	—	—
SUH35	—	—
SUH36	—	X53CrMnNi21 9
SUH37	—	—
SUH38	—	—
SUH309	309	—
SUH310	310	CrNi2520
SUH330	N08330	—

● Ferritic Heat Resisting Steels

SUH21	—	CrAl1205
SUH409	409	X6CrTi12
SUH446	446	—

● Martensitic Heat Resisting Steels

SUH1	—	X45CrSi9 3
SUH3	—	—
SUH4	—	—
SUH11	—	—
SUH600	—	—

References

■ Hardness Scale Comparision Chart

● Approx. metric value and Brinell hardness of steel

Brinell Hardness 10mm Ball 3.000kgf (HB)	Rockwell Hardness				Vickers Hardness 50kgf	Shore Hardness	Traverse Rupture Strength (N/mm^2)
	„A“ Scale Diamond, brale 60kgf (HRA)	„B“ Scale 100kgf 1/10“ Ball (HRB)	„C“ Scale Diamond, brale 150kgf (HRC)	„D“ Scale Diamond, brale 100kgf (HRD)	(HV)	(HS)	
—	85,6	—	68,0	76,9	940	97	—
—	85,3	—	67,5	76,5	920	96	—
—	85,0	—	67,0	76,1	900	95	—
767	84,7	—	66,4	75,7	880	93	—
757	84,4	—	65,9	75,3	860	92	—
745	84,1	—	65,3	74,8	840	91	—
733	83,8	—	64,7	74,3	820	90	—
722	83,4	—	64,0	73,8	800	88	—
712	—	—	—	—	—	—	—
710	83,0	—	63,3	73,3	780	87	—
698	82,6	—	62,5	72,6	760	86	—
684	82,2	—	61,8	72,1	740	—	—
682	82,2	—	61,7	72,0	737	84	—
670	81,8	—	61,0	71,5	720	83	—
656	81,3	—	60,1	70,8	700	—	—
653	81,2	—	60,0	70,7	697	81	—
647	81,1	—	59,7	70,5	690	—	—
638	80,8	—	59,2	70,1	680	80	—
630	80,6	—	58,8	69,8	670	—	—
627	80,5	—	58,7	69,8	667	79	—
601	79,8	—	57,3	68,7	640	77	—
578	79,1	—	56,0	67,7	615	75	—
555	78,4	—	54,7	66,7	591	73	2055
534	77,8	—	53,5	65,8	569	71	1985
514	76,9	—	52,1	64,7	547	70	1890
495	76,3	—	51,0	63,8	528	68	1820
477	75,6	—	49,6	62,7	508	66	1730
461	74,9	—	48,5	61,7	491	65	1670
444	74,2	—	47,1	60,8	472	63	1585
429	73,4	—	45,7	59,7	455	61	1510
415	72,8	—	44,5	58,8	440	59	1460
401	72,0	—	43,1	57,8	425	58	1390
388	71,4	—	41,8	56,8	410	56	1330
375	70,6	—	40,4	55,7	396	54	1270
363	70,0	—	39,1	54,6	383	52	1220
352	69,3	(110,0)	37,9	53,8	372	51	1180
341	68,7	(109,0)	36,6	52,8	360	50	1130
331	68,1	(108,5)	35,5	51,9	350	48	1095

Brinell Hardness 10mm Ball 3.000kgf (HB)	Rockwell Hardness				Vickers Hardness 50kgf	Shore Hardness	Traverse Rupture Strength (N/mm^2)
	„A“ Scale Diamond, brale 60kgf (HRA)	„B“ Scale 100kgf 1/10“ Ball (HRB)	„C“ Scale Diamond, brale 150kgf (HRC)	„D“ Scale Diamond, brale 100kgf (HRD)	(HV)	(HS)	
321	67,5	(108,0)	34,3	50,1	339	47	1060
311	66,9	(107,5)	33,1	50,0	328	46	1025
302	66,3	(107,0)	32,1	49,3	319	45	1005
293	65,7	(106,0)	30,9	48,3	309	43	970
285	65,3	(105,5)	29,9	47,6	301	—	950
277	64,6	(104,5)	28,8	46,7	292	41	925
269	64,1	(104,0)	27,6	45,9	284	40	895
262	63,6	(103,0)	26,6	45,0	276	39	875
255	63,0	(102,0)	25,4	44,2	269	38	850
248	62,6	(101,0)	24,2	43,2	261	37	825
241	61,8	100,0	22,8	42,0	253	36	800
235	61,4	99,0	21,7	41,4	247	35	785
229	60,8	98,2	20,5	40,5	241	34	765
223	—	97,3	(18,8)	—	234	—	—
217	—	96,4	(17,5)	—	228	33	725
212	—	95,5	(16,0)	—	222	—	705
207	—	94,6	(15,2)	—	218	32	690
201	—	93,8	(13,8)	—	212	31	675
197	—	92,8	(12,7)	—	207	30	655
192	—	91,9	(11,5)	—	202	29	640
187	—	90,7	(10,0)	—	196	—	620
183	—	90,0	(9,0)	—	192	28	615
179	—	89,0	(8,0)	—	188	27	600
174	—	87,8	(6,4)	—	182	—	585
170	—	86,8	(5,4)	—	178	26	570
167	—	86,0	(4,4)	—	175	—	560
163	—	85,0	(3,3)	—	171	25	545
156	—	82,9	(0,9)	—	163	—	525
149	—	80,8	—	—	156	23	505
143	—	78,7	—	—	150	22	490
137	—	76,4	—	—	143	21	460
131	—	74,0	—	—	137	—	450
126	—	72,0	—	—	132	20	435
121	—	69,8	—	—	127	19	415
116	—	67,6	—	—	122	18	400
111	—	65,7	—	—	117	15	385

1) Figures within the ( ) are not commonly used
2) Rockwell A, C and D scales utilises a diamond brale
3) 1 N/mm^2 = 1 MPa

■ Finished Surface Roughness

● Types of Surface Roughness Measurements

Types	Symbol	Method of Determination	Descriptive Figure
Maximum Height	※1) Ry	This is the value (expressed in μm) measured from the deepest valley to the highest peak of the reference line, ℓ, extracted from the profile. (Disregard unusually high peaks and deep valleys as they are considered as flaws.)	
Ten-point Mean Roughness	※2) Rz	From the profile, extract a portion to be the reference line, ℓ. Select the 5 highest peak and 5 deepest valleys. Measure the distance between the two lines and express it in μm. (1 μm = 0,001mm)	
Calculated Roughness	Ra	This method is to obtain a center line between the peaks and valleys within the reference line, ℓ. Fold along the center line to superimpose the valleys against the peaks. (Shaded portions with dashed outline on the right figure). Take the total shaded area and divided it by ℓ in μm.	

Designated values of the above types of surface roughness, standard reference length values and the triangular symbol classifications are shown on the table on the right.

※1) Ry : According to new **JIS B 0601**:2001 (Old symbol: Rz)
※2) Rz : According to new **JIS B 0601**:2001 (Old symbol: Rz_{JIS})

Designated values for ※1) Ry	Designated values for ※2) Rz	Designated values for Ra	Standard reference length values, ℓ (mm)	Triangular Symbols
(0,05S) 0,1S 0,2S 0,4S	(0,05Z) 0,1Z 0,2Z 0,4Z	(0,013a) 0,025a 0,05a 0,10a	—	▽▽▽▽
0,8S	0,8Z	0,20a	0,25	
1,6S 3,2S 6,3S	1,6Z 3,2Z 6,3Z	0,4a 0,8a 1,6a	0,8	▽▽▽
12,5S (18S) 25S	12,5Z (18Z) 25Z	3,2a 6,3a	2,5	▽▽
(35S) 50S (70S) 100S	(35Z) 50Z (70Z) 100Z	12,5a 25a	—	▽
(140S) 200S (280S) 400S (560S)	(140Z) 200Z (280Z) 400Z (560Z)	(50a) (100a)	—	—

Remarks: The designated values in the brackets do not apply unless otherwise stated.

Spare Parts

P

P1–P8

Screw

■ Screw

High Precision Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTG0408F	●	M4	0,5	7,5	5,7	T15	61	3,4
BTTG0409F	●	M4	0,5	8,4	6,15	T15	61	3,4
BFTG0513F	●	M5	0,5	13	6,8	T20	61	5,0
BFTG0617F	●	M6	0,75	16,5	8	T25	61	7,5
BFTG0621F	❍	M6	0,75	21	9,5	T25	61	7,5
BFTG0825F	●	M8	0,75	24,5	12	T25	61	7,5

Torx Flat Head Screw

Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTX02506		M						
BFTX02508	●	M2,5	0,45	7,5	3,45	T8	60	-
BFTX0309		M3	0,5	8,8	4,2	T10	60	-
BFTX03508	●	M3,5	0,6	8	5,1	T10	52	2,0
BFTX03584	●	M3,5	0,6	7,4	5,2	T15	60	3,0
BFTX03588	●	M3,5	0,6	8,8	5,2	T15	60	3,4
BFTX0408	●	M4	0,7	8	5,5	T15	60	-
BFTX0414	●	M4	0,7	14,5	5,5	T15	60	3,0
BFTX0515		M5	0,8	15	7	T20	60	-
BFTX0613		M6	1,0	13	9	T25	60	-
BFTX0615		M6	1,0	15	9	T25	60	-
BFTX0617		M6	1,0	17	9	T25	60	-



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTX0203A	●	M2	0,4	3	2,7	T6	90	0,5
BFTX0204A	●	M2	0,4	4,3	2,7	T6	90	0,5
BFTX0305A	●	M3	0,5	5,3	4,3	T10	90	-
BFTX0306A	●	M3	0,5	5,8	4,3	T10	90	2,0
BFTX0307A	●	M3	0,5	6,8	4,3	T10	90	2,0
BFTX0407A	●	M4	0,7	7,3	5,6	T15	90	3,4
BFTX0410A	●	M4	0,7	10,3	5,6	T15	90	3,4
BFTX0509A	●	M5	0,8	9,3	6,9	T20	90	5,0



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTX01604N	●	M1,6	0,35	4,2	2,4	T6	60	0,2
BFTX0203N	●	M2	0,4	3	2,7	T6	60	0,5
BFTX0204N	●	M2	0,4	4,3	2,7	T6	60	0,5
BFTX02205N	●	M2,5	0,45	4,5	3	T6	60	0,5
BFTX02505N	●	M2,5	0,45	4,5	3,45	T8	60	1,1
BFTX02506N	●	M2,5	0,45	5,5	3,45	T8	60	1,5
BFTX02508NV	●	M2,5	0,45	7,5	3,5	T8	60	1,5
BFTX0306N	❑	M3	0,5	5,8	4,2	T10	60	2,0
BFTX0307N	●	M3	0,5	6,5	4,2	T10	60	2,0
BFTX0309N	●	M3	0,5	9	4,2	T10	60	3,0
BFTX0312N		M3	0,5	12	5,4	T10	60	-
BFTX03509N	●	M3,5	0,6	8,5	4,9	T10	60	-
BFTX0406N	●	M4	0,7	6	5,6	T15	60	-
BFTX0407N	●	M4	0,7	7	5,6	T15	60	3,0
BFTX0409N	●	M4	0,7	9	5,6	T15	60	3,4
BFTX0412N	●	M4	0,7	12	5,5	T15	60	3,0
BFTX0509N	●	M5	0,8	9	7	T20	60	5,0
BFTX0511N	●	M5	0,8	11,5	7	T20	60	5,0
BFTX0513N	●	M5	0,8	13	7	T20	60	5,0
BFTX0515N	●	M5	0,8	15	7	T20	60	-
BFTX0615N	●	M6	1,0	15	9	T25	60	5,0
BFTX0619N	●	M6	1,0	19	9	T25	60	5,0

Torx Flat Head Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTX0410T8L	●	M4	0,7	9,6	5,6	T8	60	1,1
BFTX0410T8R	●							

■ Screw

Torx Plus Flat Head Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTX01804IP	●	M1,8	0,35	3,7	2,45	6IP	60	0,5
BFTX02505IP	●	M2,5	0,45	4,5	3,45	8IP	60	-
BFTX02506IP	●	M2,5	0,45	5,5	3,45	8IP	60	-
BFTX0305IP	●	M3	0,5	5,3	3,8	8IP	60	2,0
BFTX0306IP	●	M3	0,5	6	3,8	8IP	60	2,0
BFTX0307IP		M3	0,5	7	4,3	10IP	55	2,0
BFTX0308IP	❍	M3	0,5	8	3,8	8IP	60	-
BFTX03510IP	❍							
BFTX03512IP	●	M3,5	0,6	11,5	5,3	15IP	60	3,0
BFTX03584IP	●	M3,5	0,6	7,4	5,1	15IP	60	-
BFTX03510IP08	●	M3,5	0,6	10	5,3	8IP	60	-
BFTX03510IP15	●	M3,5	0,6	10	5,3	15IP	60	-
BFTX0407IP	●	M4	0,7	8,0	5,6	15IP	60	3,0
BFTX0409IP	●	M4	0,7	9,0	5,6	15IP	60	3,0
BFTX0412IP	●	M4	0,7	12	5,5	15IP	60	3,0
BFTX0418IP	●	M4	0,7	18	5,5	15IP	60	-
BFTX04513IP20	●	M4,5	0,75	13,1	6,8	20IP	60	-
BFTX0511IP	●	M5	0,8	11,5	7	20IP	60	-
BFTX0513IP	●	M5	0,8	13	7	20IP	60	-
BFTX0615IP	●	M6	1,0	15	9	25IP	60	-

Torx Flat Head Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTX03510SD		M3,5	0,6	10	5,3	T10	60	2,0
BFTX03517SD		M3,5	0,6	17	5,3	T10	60	2,0
BFTX0517SD	❑	M5	0,8	17	7,2	T20	60	5,0
BFTX0618SD		M6	1,0	18		T25	60	7,5

Torx Flat Head Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	(N·m)
BFTY02205	●	M2,2	0,45	5,0	3,05	T7	60	-
BFTY02206	●	M2,2	0,45	5,6	3,05	T7	60	1,0

Button Head Cap Screw

Hexagonal Hole Type



T Type with Torx Hole



(BH410T)

Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	(N·m)
BH0304		M3	0,5	4	Full	5,5	2	-
BH0306	●	M3	0,5	6	Full	5,5	2	-
BH0308 (FBUP3-A0-9)	●	M3	0,5	8	Full	5,5	2	1,0
BH0310	●	M3	0,5	10	Full	5,5	2	-
BH03504		M3,5	0,6	4	Full	7	2	-
BH0408		M4	0,7	8	Full	6	2,5	-
BH0415	❍	M4	0,7	15	Full	7,5	2,5	-
BH0510		M5	0,8	10	Full	9,5	3	-
BH0516	●	M5	0,8	16	14,4	9,5	3	-
BH0616	●	M6	1,0	16	14	10,5	4	-
BH0620	●	M6	1,0	20	Full	10,5	4	-
BH0824R		M8	1,25	24	20	12	4	-
BH0824L		M8	1,25	24	20	12	4	-
BH0825	❍	M8	1,25	25	22,5	14	5	-
BH0830R		M8	1,25	30	26	12	4	-
BH0830L		M8	1,25	30	26	12	4	-
BH0832		M8	1,25	32	29,5	14	5	-
BH1030R		M10	1,5	30	26	14	5	-
BH1030L		M10	1,5	30	26	14	5	-
BH1036R		M10	1,5	36	32	14	5	-
BH1036L		M10	1,5	36	32	14	5	-

■ Screw

Phillip Head Cap Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	B	N·m
BHA0525	●	M5	0,8	25,5	9,5	8,5	3	4,0
BHA0625	●	M6	1,0	30	11,3	10,5	4	4,5
BHA0834		M8	1,25	34,2	12,7	12,0	5	-
BHE0407		M4	0,7	9,5	2	5,7	2,5	1,8
BHE0510	❍	M5	0,8	13	3	7,7	3	2,7

Button Head Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	D	B	α°	N·m
BHF0203L		M2	0,4	4	3	1,5	90	
BHF0203B		M2	0,4	5,5	3,5	1,5	90	
BHF0306R		M3	0,5	6,3	4,2	2	90	1,0
BHF0308R		M3	0,5	8	4,2	2	90	1,0
BHF0623	❍	M6	1,0	23	12	4	90	7,0

Set Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	D	B	α°	N·m
BT0306		M3	0,5	6	-	1,5	-	-
BT0310		M3	0,5	10	-	1,5	-	-
BT0404	●	M4	0,7	4	-	2	-	-
BT0506	●	M5	0,8	6	-	2,5	-	-
BT0510		M5	0,8	10	-	2,5	-	-
BT0610		M6	1,0	10	-	3	-	-
BT0612		M6	1,0	12	-	3	-	-
BT0620		M6	1,0	20	-	3	-	-
BT06035T		M6	1,0	3,5	-	T15	-	-

Set Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	B	N·m
BTD0408		M4	0,7	8	2	2,8	2	-
BTD0410		M4	0,7	10	2	2,8	2	-
BTD0412		M4	0,7	12	2	2,8	2	-
BTD0508		M5	0,8	8	3	3,5	2,5	-
BTD05F09		M5	0,5	9	2	4	T15	-
BTD0510	❑	M5	0,8	10	3	3,5	2,5	3,0
BTD0518		M5	0,8	18	4	3,5	2,5	-
BTD0609	❍	M6	1,0	9	2	4	3	-
BTD0615		M6	1,0	15	5	4	3	-
BTD0618		M6	1,0	18	5	4	3	-
BTD0620		M6	1,0	20	5	4	3	-
BTD0812		M8	1,25	12	2	5	4	-
BTD0818		M8	1,25	18	6	5	4	-
BTD0820		M8	1,25	20	6	5	4	-
BTD0825		M8	1,25	25	8,5	5	4	-
BTD0615T		M6	1,0	15	5	4,3	T20	-

Set Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	B	α°	N·m
BTT0407	●	M4	0,5	7	2,6	2	60	-
BTT0411	●	M4	0,5	11	2,6	2	60	-
BTT0511		M5	0,8	11	5	2	20	-
BTT0615		M6	1,0	15	6	2,5	20	

Special Hollow Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	B	N·m
BW0507F	●	M5	0,5	7	1,2	6,3	3,5	-
BW0609F		M6	0,75	9	1,5	7,7	4	-
BW0508F-SD		M5	0,5	8	1,2	6,3	3,5	
BW0810F-SD	❑	M8	0,75	10	1,8	10	5	
BW0912F-SD		M9	0,75	12				

■ Screw

Cap Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	B	N·m
BX0304		M3	0,5	4	Full	5,5	2,5	-
BX0308		M3	0,5	8	Full	5,5	2,5	-
BX0315		M3	0,5	15	Full	5,5	2,5	-
BX0320		M3	0,5	20	Full	5,5	2,5	-
BX0408		M4	0,7	8	Full	7	3	-
BX0410		M4	0,7	10	Full	7	3	-
BX0414	●	M4	0,7	14	Full	7	3	-
BX0425		M4	0,7	25	20	7	3	-
BX0508	❍	M5	0,8	8	Full	8,5	4	-
BX0510	❍	M5	0,8	10	Full	8,5	4	-
BX0512	●	M5	0,8	12	Full	8,5	4	-
BX0515	●	M5	0,8	15	Full	8,5	4	-
BX0520	●	M5	0,8	20	Full	8,5	4	5,0
BX0520T	●	M5	0,8	20	16	8,5	T20	-
BX0615	❍	M6	1,0	15	Full	10	5	-
BX0620	❍	M6	1,0	20	Full	10	5	-
BX0622	●	M6	1,0	22	18	10	5	-
BX0625		M6	1,0	25	18	10	5	-
BX0820		M8	1,25	20	Full	13	6	-

Cap Screw (Torx Plus)



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	B	N·m
BXD02208IP	●	M2,2	0,45	7,5	5,7	3,5	8IP	-
BXD02509IP	●	M2,5	0,45	9	7	4,1	10IP	-
BXD03011IP	●	M3	0,5	10,5	8	4,9	15IP	-
BXD03512IP	●	M3,5	0,6	11,5	8,8	5,5	15IP	-
BXD04014IP	●	M4	0,7	12,5	9,5	6	20IP	-
BXD04515IP	●	M4,5	0,75	14,3	10,8	6,8	25IP	-

Cap Screw (Torx Plus)



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	H	B	N·m
BXA0310IP	❍	M3	0,5	7,5	Full	5,3	2,4	10IP	2,0
									-
									-

Cap Screw with Oil Hole



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	H	B	N·m
BXH0825-D13	❍	M8	1,25	25	Full	13	8	6	-
BXH1030-D16	❍	M10	1,5	30	Full	16	10	8	-
BXH1235-D18	❍	M12	1,75	35	Full	18	12	10	-

Cap Screw with Oil Hole



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	H1	H2	B	N·m
BXH1235-D33	❍	M12	1,75	35	Full	33	10	2	10	-
BXH1635-D40	❍	M16	2,0	35	30	40	10	-	14	-
BXH2036-D50	❍	M20	2,5	36	29	50	14	4	17	-

Cap Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	B	N·m
EHBX0512	❍	M5	0,8	12	10,5	8	4	-

Flat Head Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	B	α°	N·m
FBUP2-A0-8	❑	M3	0,5	10	5,5	2	82	1,0
FBUP3-A0-8		M3,5	0,6	12	7	2	82	1,0
FBUP4-A0-8		M5	0,8	15	9,3	3	82	2,7

Button Head Cap Screw



Cat. No.	Stock	Dimensions (mm) d	Pitch	L	ℓ	D	B	N·m
FBUP3-A0-9	●	M3	0,5	8	Full	5,5	2	1,0

Screw, Lever Pin

■ Screw

Axial adjustment Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
FMJ	●	M4	0,5	15	5	6	3	-



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
FMUJ		M4	0,7	17	10,5	6	1	-



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
RFJ		M4	0,7	12	6	6	2	-



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
SRFJ		M4	0,7	17	10,5	6	2	-

Special Hollow Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
KGBS1111	●	M5	0,5	8	1,2	6	3,5	
KGBS1221	❑	M6	0,75	9	1,5	7,5	4,5	

Torx Flat Head Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	D	B	α°	N·m
KSS1111	●	3,5	0,6	11	5,2	T15	55	3,5
KSS1221	❑	4,5	0,75	12	6,6	T15,3	55	4,5

Screw for Lever Lock

(LCS2B)



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
LCS2B		M3	0,5	10	3,05	3,6	2	-
LCS3	●	M6	1,0	17	10	6	2,5	-
LCS3B-SD	●	M5	0,8	9,5	4,2	5	2	-
LCS3DB-SD	●	M5	0,8	12	6	5	2	-
LCS3S		M6	1,0	15	10	6	2,5	-
LCS3TB-SD	●	M6	1,0	16,7	9,6	6	2,5	-
LCS3TE	●	M6	1,0	15,5	8,5	6	2,5	-
LCS4	●	M8	1,0	21	10	8	3	-
LCS4B-SD	●	M6	1,0	13,4	9	6	2,5	-
LCS41BS-SD	●	M8	1,0	17	9,3	8	3	-
LCS42BS-SD	●	M8	1,0	20,7	9,8	8	3	-
LCS4CA	●	M8	1,0	17,5	10	8	3	-
LCS5	●	M8	1,0	25	12	8	3	-
LCS5B-SD	❑	M8	1,0	20,5	12,3	8	3	-
LCS5DB-SD	❑	M8	1,0	21,1	11,4	8	3	-
LCS6	❍	M10	1,0	27,2	14,4	9,8	4	-
LCS6B-SD	●	M10	1,0	27,2	14,4	10	4	-
LCS10	●	M5	0,8	14,5	8,5	5	2	-
LCS12	●	M6	1,0	17	9,6	6	2,5	-
LCS16	❍	M6	1,0	21	13,6	6	2,5	-
LCS20	●	M8	1,0	23,5	13,2	8	3	-
LCS25		M10	1,0	30	17,4	10	4	-
LCS32		M12	1,0	36	19,3	12	5	-



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	-	D	-	N·m
MIB1.6-2	❑	M1,6	0,35	2,0	-	2,4	-	0,2
MIB1.6-2.5	●	M1,6	0,35	2,5	-	2,4	-	0,2
MIB1.6-3	●	M1,6	0,35	3,0	-	2,4	-	0,2

■ Double Screw

Double Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
WB4-8		M4	0,7	7,5	3	3,0	2	-
WB5-10	●	M5	0,8	10	4	3,8	2,5	-
WB5-12	❍	M5	0,8	12	5	3,8	2,5	-
WB6-13	❍	M6	1,0	13	5	4,5	3	-
WB6-16	●	M6	1,0	16	6	4,5	3	-
WB6-20	❑	M6	1,0	20	8,5	4,5	3	-
WB6-30		M6	1,0	30	12	4,5	3	-
WB8-20		M8	1,25	20	8,5	6,2	4	-
WB8-24		M8	1,25	24	8,5	6,2	4	-
WB8-30	●	M8	1,25	30	11,5	6,2	4	-
WB8F-30	❑	M8	1,0	30	11,5	6,2	4	-

Torx Double Screw



Cat. No.	Stock	Dimensions (mm)						
		d	Pitch	L	ℓ	D	B	N·m
WB6-16T	❑	M6	1,0	16	6	4,5	T20	-
WB6-20T	❍	M6	1,0	20	8,5	4,5	T20	-
WB6-20TL	❍	M6	1,0	20	8,5	4,5	T20	-
WB7-15T	●	M7	1,0	15	5,5	5	T25	-
WB7F-15T	❍	M7	0,75	15	8,5	5,5	T25	-
WB7F-20TL	❍	M7	0,75	20	8,5	5,5	T25	-
WB8-22T	●	M8	1,25	22	8,5	6,2	T27	-
WB8-22TL		M8	1,25	22	8,5	6,2	T27	-
WB8-30T	●	M8	1,25	30	11,5	6,2	T27	-
WB8-30TL		M8	1,25	30	11,5	6,2	T27	-
WB8R-16T	❍	M8	1,25	14	5,5	6,2	T27	-

■ Lever Pin



Cat. No.	Stock	Dimensions (mm)						
		A	H	L	C			
LCL3		3,7	12	10	3,6			
LCL3-SD	●	3,7	12	10	3,55			
LCL3C-SD	❑	3,1	7,8	9,9	3,1			
LCL3D-SD	●	3,7	11,5	12	3,55			
LCL3DB-SD	●	3,1	9,4	11,5	3,1			
LCL3S		3,7	10,6	10	3,6			
LCL3T-SD	❑	2,6	6,3	7,2	2,15			
LCL4		4,7	14	14,55	4,7			
LCL4-SD	●	4,65	13,2	13,35	4,7			
LCL4C-SD	●	4,65	10	13,35	4,7			
LCL4D-SD	●	4,65	14,8	16	4,7			
LCL4T-SD	●	4,65	13,2	13,35	4,7			
LCL5		6	17	17,1	6			
LCL5-SD	●	6	17,3	16,65	6			
LCL5C-SD	❑	7,5	18,1	20,5	7,5			
LCL6-SD	●	7,5	21	20,5	7,5			
LCL8		8,6	25,4	25,4	8,6			



Cat. No.	Stock	Dimensions (mm)						
		A	H	L	C			
LCL06	●	2,5	6,28	7,0	2			
LCL09	●	3,5	9,3	10,75	3			
LCL10	●	3,4	11,8	10,8	3			
LCL12	●	3,7	13,4	12,9	3,5			
LCL16	❍	4,6	17,6	18,4	4,4			
LCL20	❑	6	18,9	20,4	5,6			
LCL32		8,5	26,8	29,8	8			

Shim



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
CCS09T3	●	8,525	2,38	5,4	6,4		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
CNS1204	●	12,57	4,76	4,4	6,0		
CNS1606	❍	15,75	4,76	5,5	7,5		
CNS1906	●	18,70	6,35	5,5	7,5		
CNS2509	❑	25,27	6,35	6,6	9,5		
CNS1203B	●	12,57	3,18	3,4	4,5		
CNS1204B	●	12,57	4,76	4,4	6,0		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
DCS11T3	●	8,5	2,38	5,3	6,4		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		θ°
DGCS13R	●	13,7	3,9	6,8	8,8		5



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
DNS1504	●	12,57	6,35	4,4	6,0		
DNS1506	●	12,57	4,76	4,4	6,0		
DNS1104B	❍	9,45	4,73	3,4	4,5		
DNS1504B	❍	12,57	6,35	4,4	6,0		
DNS1506B	❍	12,57	4,76	4,4	6,0		

Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
HE060011E	●						



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			
LST317SD	●	9,5	2,7	5,2			
LST42SD	●	12,65	3,18	6,9			



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			
LSS32SD	●	9,48	3,18	5			
LSS42SD	●	12,65	3,18	6,9			
LSS53SD	❑	15,85	4,76	7,9			
LSS63SD	●	19	4,76	10			



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			
LSC32SD	●	9,48	3,18	5			
LSC42SD	●	12,65	3,18	6,9			
LSC53SD	●	15,85	4,76	7,9			
LSC63SD	❑	19	4,76	10			



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			
LSD32SD	●	8,5	3,18	5			
LSD42SD	●	12,65	3,18	6,9			

Shim



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			
LSR817	❑	8,4	2,7	5,2			
LSR10	●	8,4	3,18	4,7			
LSR12	●	10	3,18	4,7			
LSR16	●	13,5	4,76	6,3			
LSR20	●	17,2	4,76	7,9			
LSR25		22	6,35	9,5			



Cat. No.	Stock	Dimensions (mm)					
		A	T_1	T_2	d_2		
LSTE31-0	●	9,5	2,7	2,7	5,2		
LSTE31-1	●	9,5	2,67	2,91	5,2		
LSTE31-2	●	9,5	2,64	3,11	5,2		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			θ°
SCND433	❑	12,65	4,76	3,4			80
SCN0903	❑	9,5	3,18	3,4			



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
SCS1204	❑	11,5	3,18	6,4	7,9		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
SNS1204	●	12,57	4,76	4,4	6,0		
SNS1506	❍	15,75	4,76	5,5	7,5		
SNS1906	●	18,92	6,35	5,5	7,5		
SNS2507	❍	25,27	7,93	6,6	9,5		
SNS2509	●	25,27	6,35	6,6	9,5		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		θ°
SVW322		9,5	3,18	4,7	6,5		35
SFW433		12,65	4,76	6,2	8,0		50
SDW323	●	9,5	3,18	4,7	6,5		55
SDW423	●	12,65	3,18	6,2	8,0		55
SDW433	❍						
SCW423	●	12,65	3,18	6,2	8,0		80
SCW433	❍						
SCW635	❍	19	4,76	9	11,5		80



Cat. No.	Stock	Dimensions (mm)					
		D					
SRND32Z	❍	9,5					
SRND42	❍	12,7					



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			
SSND423	❍	12,5	3,18	3,4			
SSN0903	❑						

Shim, Nut

■ Shim



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
SSW423	❑	12,65	3,18	6,2	8		
SSW433	❍	12,65	4,76	6,2	8		
SSW635	❍	19	4,76	9	11,5		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d			θ°
STPD322	●	8,4	3,18	3,4			6
STPD422	❍	11,0	3,18	3,4			6



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
STW323	●	9,5	3,18	4,7	6,5		
STW434	●	12,65	4,76	6,2	8		
STW333	❍						



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
SWW433	●	12,65	5,15	6,2	8		
LSW317	●						



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		θ°
TCS16T3	❑	8,8	2,38	5,3	6,3		7



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
TNS1604	●	9,45	4,76	3,4	4,5		
TNS1603B	❍	9,45	3,18	3,4	4,5		
TNS1604B	❍	9,45	4,76	3,4	4,5		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
TRW5505	●	10,5	4,76	3,4	4,5		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
VCS1604	●	8,25	3,18	5,3	6,4		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
VNS1604	●	9,45	4,76	3,4	4,5		

■ Shim

Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
WFXS4R	●	10,17	3,0	5,5	7,5		



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		θ°
WGCS13R	●	10,7	3,0	5,5	7,5		5



Cat. No.	Stock	Dimensions (mm)					
		A	T	d_1	d_2		
WNS0604	●	9,52	3,18	3,5	4,5		
WNS0804	●	12,57	4,76	4,4	6,3		
WNS0603B	❑	9,27	3,18	3,4	4,5		
WNS0803B	❍	12,57	3,18	3,4	4,5		
WNS0804B	❍	12,57	4,76	4,4	6,0		

■ Seat



Cat. No.	Stock	Dimensions (mm)					
		d	L	H			
PWSS4R	▲	4,6	15	8			

■ Ring



Cat. No.	Stock	Dimensions (mm)					
		A	B	T	d		
ER03	❍	7	2,6	0,6	3		
ER04	●	9	3,5	0,6	4		
ER05	●	11	4,3	0,6	5		

■ Nut



Cat. No.	Stock	Dimensions (mm)					
		L					
BNBW-2	●	3					
BNBW-4	❍	4					
BNBW-7	❑	7					



Cat. No.	Stock	Dimensions (mm)					
		d	L	D	B		
CPM32N	●	M4	7,5	7	3		
CPM43N	●	M5	8,5	7	3		
CPM43S	❍	M5	6	7	3		



Cat. No.	Stock	Dimensions (mm)					
		d	Pitch	L	D	B	
CPV33N	●	M4	0,5	6,0	6,0	2,5	

Shim Pin, Eccentric Pin

■ Shim Pin



Cat. No.	Stock	Dimensions (mm)					
		d	Pitch	L	D	d_1	B
HE060011P	●	M6	0,75	14,5	7,8	5,0	2,5



Cat. No.	Stock	Dimensions (mm)					
		d	D	L			
LP04	●	0,4	1,1	4,7			
LP06	●	0,4	1,1	6,0			
LP07	●	0,4	1,1	7,7			



Cat. No.	Stock	Dimensions (mm)					
		d	H	L			
LSP3		5	3,5	5,5			
LSP3SD	●	5	3,5	5,5			
LSP4		6,7	4	7			
LSP4SD	●	6,7	4	7			
LSP5SD	●	7,7	4,5	8,5			
LSP6SD	●	9,85	5,9	11,1			
LSP8		13,05	10	12			
LSP10	●	5	3,3	6,5			
LSP16	❍	6,6	4,5	9			
LSP20	●	8,2	5,5	9			
LSP25		9,8	6,5	11			
LSP32		13	10	12			



Cat. No.	Stock	Dimensions (mm)					
		d	Pitch	L	D	D_1	d_1
MP317	●	M4	0,7	15,5	6	4	3,7
MP320	●	M4	0,7	19,5	6	4	3,7
MP416	●	M5	0,8	14	7,5	6	5
MP420	●	M5	0,8	20	7,5	6	5
MP432	❍	M5	0,8	32	7,5	6	5
MP531							
MP534							



Cat. No.	Stock	Dimensions (mm)					
		d		L	D		θ°
SPP308	❍	3,2		8	4,8		120



Cat. No.	Stock	Dimensions (mm)					
				L	D		
SPP3	❍			14	3,2		



Cat. No.	Stock	Dimensions (mm)					
		d_1	d_2	L	D	ℓ_1	ℓ_2
VP20	●	M3,5	M4	12,0	5,0	≥4,5	≥4,5
VP25	●	M3,5	M4	17,0	5,0	≥4,5	≥4,5
VP32	●	M3,5	M4	24,0	5,0	≥4,5	≥4,5



Cat. No.	Stock	Dimensions (mm)					
		d	Pitch	L	ℓ	D_1	D_2
VP32B	●	M3,5	0,6	8,0	1,4	5,0	6,5
VP40B	●	M3,5	0,6	11,5	1,4	5,0	6,5

■ Eccentric Pin



Cat. No.	Stock	Dimensions (mm)					
		d	D_1	D_2	L	ℓ	B
CPB34	●	3,4	4,1	5,5	14	5	2,5
CPB35	❍	3,4	4,1	5,5	17	5	2,5
CPB42	●	4,5	5,5	7	14	5	3
CPB43	●	4,5	5,5	7	19	5	3
CPB43S	●	4,5	5,5	7	16	5	3
CPB44T	❑	4,5	5,5	7	22	5	3
CPB45T	❍	4,5	5,5	7	27	5	3
CPB64	❍	6,8	8,2	10,5	24	6,6	4



Cat. No.	Stock	Dimensions (mm)					
		d	D_1	D_2	L	ℓ	B
CPU304C	❍	3,3	5,5	-	10	3,5	3

■ Wrench

Hex Wrench (Torx Plus)



Cat. No.	Stock	Dimensions (mm)					
		B	d	C	b_1	b_2	
TRXW10IP	❍	10IP	2,6	40	75	40	



Cat. No.	Stock	Dimensions (mm)						
		B	d					
TRB10IP	❍	10IP	4					
TRB15IP	❍	15IP	4					
TRB20IP	❍	20IP	4,55					
TRB25IP	❍	25IP						



Cat. No.	Stock	Dimensions (mm)		
		D	L	Remarks
HPS1015	❍	32	99,4	For 10IP, 15IP
HPL2025	❍	35,5	110,3	For 20IP, 25IP

Wrench

■ Wrench

Socket Wrench



Cat. No.	Stock	Dimensions (mm)					
		d_1	d_2	L	H		
ANT	❍	5	2	100	4,5		

Hex Wrench (Hexagonal)



Cat. No.	Stock	Dimensions (mm)					
		B	L	ℓ			
LH020	●	2	50	16			
LH025	●	2,5	56	18			
LH030	●	3	63	20			
LH035	●	3,5	68	22			
LH040	●	4	70	25			
LH050	❍	5	80	28			
LH060		6	90	32			

Cat. No.	Stock	Dimensions (mm)					
LH035K	●						
LH045K	❑						

Torx Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	d	L	ℓ		
LT0806		T8	2,3	45,0	6,0		
LT20	❍	T20	3,9	57,2	19,1		
LT25	❑	T25	4,4	60,3	20,2		
LT27	●	T27	4,96	63,5	21,5		
LT1510	❍	T15	3,26	62	10		

Cat. No.	Stock	Dimensions (mm)					
LT15K	●						

Torx Plus Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	d	L	ℓ		
LT20IP		T20	4,0	57	18,5		
LT25IP		T25	4,5	60	19,5		

Cat. No.	Stock	Dimensions (mm)					
SDBSM	●						

Hex Wrench (Hexagonal)



Cat. No.	Stock	Dimensions (mm)					
		B	b_1	C			
TH015	❍	1,5	35	30			
TH020	●	2	35	39			
TH025	❍	2,5	35	39			

Hex Wrench (Hexagonal)



Cat. No.	Stock	Dimensions (mm)					
		B	b_1	C			
TH030	●	3	48	28			
TH040	●	4	48	37			
TH050	❍	5	48	45			

■ Wrench

Hex Wrench (Hexagonal)



Cat. No.	Stock	Dimensions (mm)					
		B	C	b_1			
HD040	❍	4	75	111			

Torx Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	d	C	B_1		
TRD07	●	T7	2,0	45	70		
TRD08	●	T8	2,3	55	70		
TRD15	❍	T15	3,3	70	100		
TRD20	●	T20	3,9	100	90		
TRD25	●	T25	5,3	80	110		

Torx Plus Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	C	b_1			
TRDR06IP05	●						
TRDR08IP	●	8IP	60	104			
TRDR10IP	●	10IP	80	111			
TRDR15IP	●	15IP	80	111			
TRDR20IP	●	20IP	100	118			
TRDR25IP	●	25IP	100	118			

Torx Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	C	b_1	b_2		
TRX06	●	T6	35,5	15	15		
TRX08	●	T8	38,5	19	19		
TRX10	●	T10	42,1	22	22		
TRX15	●	T15	46	22	27		
TRX20	●	T20	49	22	30		

Torx Plus Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	C	b_1	b_2		
TRX06IP	●	6IP	34	15	15		

Hex Wrench (Hexagonal)



Cat. No.	Stock	Dimensions (mm)					
		B	C	b_1	b_2		
TSW040	❍	4	60	20	40		

Torx Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	d				
TT25	●	T25	4,4				
TT27	●	T27	5,0				

Torx Plus Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	d	C	b_1		
TTR15IP	●	15IP	4,0	80	25,5		

Torx Wrench



Cat. No.	Stock	Dimensions (mm)					
		B	d				
TTX15W	●	T15	4,0				
TTX20	●	T20	3,9				

Index

P

Index

A - C

Index

C - D

D

Index

G - L

Index

Q - S

S - T

V - W

Notes

Target Products	Hazards	Measures
General precautions for cutting tools	The tools have sharp cutting edges. There is a risk of injury if held directly with bare hands.	Always wear protective equipment, such as protective tools when removing the tool from the case or mounting it onto a machine.
	Improper use or incorrect use conditions may cause the tool to breake or scatter, and could cause injury.	Always use protective equipment such as safety covers and protective eyewear. Always use within the scope of the recommended conditions. Refer to the intruction manual, catalogue and other relevant documents.
	The tool could break and fly off if the cutting force increases suddenly because of impact loads or excessive wear and could cause injury.	Always use protective equipment such as safety covers and protective eyewear. Replace the tool at an early stage.
	Very hot chips could scatter or elongated chips could be discharged, and cause injury or burns.	Always use protective equipment such as safety covers and protective eyewear. When removing the chips, always stop the machine, wear protective gloves, and use tools such as nippers or clippers.
	The tool and work materials will become very hot during turning. There is a risk of burn if these are touched directly with bare hands immediately after machining.	Always wear protective equipment such as protective gloves.
	There is a risk of igniting or fires from the sparks generated during turning, or the heat generated from broken pieces and chips.	Do not use in an area where there is a risk of fires or explosions. Always provide fire prevention measures when using water-insoluble turning oil solution.
	When using at a high rotation speed, if the balance including the machine tool holder is poor, the deflection or vibration could cause tool damage and injury.	Always use protective equipment such as safety covers and protective eyewear. Always carry out trial operation, and confirm that there is no deflection, vibration or abnormal noise.
	There is a risk of injury if you touch the burrs formed on the workpiece with bare hands.	Do not touch with bare hands.
General precautions for cutting edge indexable tools	If insert or parts are not properly clamped, they could come off or fly off during turning and cause injury.	Clean the mounting surface and fixing parts free of foreign matter, before mounting the insert. When mounting, use the enclosed spanner and confirm that the insert and parts are securely clamped. Never use parts other than the designated inserts or parts.
	If the parts are tightened excessively with an auxiliary tool such as a pipe, the insert or part could break and come off or fly off.	Do not use auxiliary tools such as pipes. Use the enclosed spanner.
	Using the tool with high-speed rotation is extremely dangerous as the parts or inserts could fly off with the centrifugal force. Pay special attention to safety when handling.	Always use within the scope of the recommended conditions. Refer to the instruction manual, catalog and other relevant documents.
Various cutters and other tools used with rotation	The cutters have very sharp cutting edges. Touching these with bare hands could result in injury.	Always wear protective equipment such as protective gloves.
	Tools could sway or vibrate if the eccentric rotation or balance is poor. There is a risk of injury if they break or fly off.	Keep the rotation speed within the scope of the recommended conditions. Periodically adjust the accuracy and balance of the rotating sections so that eccentric rotation or deflection do not occur because of bearing wear, etc.
Drills	When machining a through hole while rotating the workpiece, a disc-shaped uncut section may fly off at the point of penetration. This disc is sharp and very dangerous.	Always use protective equipment such as safety covers and protective eyewear. Also take measures such as attaching a cover to the chuck section.
	The very small drill has a pointed end, and is very sharp. It could stab or break when directly touched with a finger, and be difficult to remove. The end could fly off if it breaks.	Take special care to safety when handling. Always wear protective gloves and protective eyewear, etc.
Brazing tool	There is a risk of injury if the insert comes off or breaks, etc.	Confirm that the insert is properly brazed before using. Do not use in conditions that could become very hot.
Others	Repeated brazing is dangerous as the insert could break during use.	Do not use an insert that has been repeated brazed as the strength will have dropped.
	Using this product for a purpose other than the designated application can break the machine or tool and is very dangerous.	Observe the designated usage.

Finally,
this brochure describes the basic safety information. For further information, refer to the instruction manual, catalog and other relevant documents for each tool, or contact Sumitomo Electric Hardmetal. Sumitomo Electric Hardmetal will not be held liable for any damage and injuries resulting from changes to the specifications, including alterations and modifications, made without consent from Sumitomo Electric Hardmetal.

Tool Engineering Services

In order to provide a higher level of support and satisfaction for our customers,
Sumitomo Electric Industries has created the Tool Engineering Service system.
We have created several Tool Engineering Centers around the world as bases for this support.
The Tool Engineering Centers provide a wide range of support to assist user manufacturing activities,
with services including training (at the Center), test cuts, technical consulting,
line diagnostics (at the user's site) and tooling proposals.

Tool Engineering Center Locations

Japan

- ▶Itami Tool Engineering Center (**I-TEC**)
- ▶Yokohama Tool Engineering Center (**Y-TEC**)
- ▶Hokkaido Igetalloy Tool Engineering Center (**H-TEC**)
- ▶Tokai Tool Engineering Center (**T-TEC**)
- ▶Kyushu Tool Engineering Center (**K-TEC**)

Overseas

- ▶**Germany / European Design & Engineering Center** (**E-DEC**)
- ▶Thailand / Thailand Tool Engineering Center (**Ti-TEC**)
- ▶Shanghai / Shanghai Tool Engineering Center (**S-TEC**)
- ▶U.S.A. / Americas Tool Engineering Center (**A-TEC**)
- ▶Indonesia / Indonesia Tool Engineering Center (**In-TEC**)
- ▶India Tool Engineering Center

1 Training

To make it easy for anyone to take part, the Centers offer training courses designed for a variety of different training objectives and participants.
*Contact your nearest SEI sales office for detailed training curricula.

2 Performance evaluation technology

To attain improvements in machining on sites, manufacturers must rely on more than just the subjective guidance provided by experience and instinct. Today's advanced measuring instruments can make machining phenomena observable, and clarify problems.



3 Test cuts and technical consulting

The Tool Engineering Centers can make test cuts on user workpieces, and work with users to create more detailed technical proposals. The Centers can also provide solutions to various machining problems, general line diagnostics for machining lines, and tooling support for new lines.
*Contact your nearest SEI sales office for more information.

SUMITOMO
CARBIDE - CBN - DIAMOND

SUMITOMO ELECTRIC

CUTTING TOOLS

WORLDWIDE LOCATIONS

We are strengthening its global position for high-quality products and services, while contributing technology to market needs around the world.





- Sales Network (●)
- Production Network
- Tool Engineering Center

H Sumitomo Electric Industries Ltd. Hardmetal Div.
Sumitomo Electric Hardmetal Corp.

Production Network

P1 Hokkaido Sumiden Precision Co., Ltd.

P2 Hokkaido Precision Tool Co., Ltd.

P3 Tokai Sumiden Precision Tool Co., Ltd.

P4 Kyushu Sumiden Seimitsu Ltd.

P5 Asdex Corporation

P6 Sumitomo Electric Hartmetallfabrik GmbH

P7 Sumitomo Electric Hartmetallfabrik GmbH, organizační složka.

P8 Sumitomo Electric Hardmetal Manufacturing (Changzhou) Co., Ltd

P9 Sumitomo Electric Hardmetal Manufacturing (Thailand), Ltd

P10 PT. Sumiden Hardmetal Manufacturing Indonesia

P11 Motherson Techno Tools Ltd.

P12 Sumitomo Electric Carbide Manufacturing, Inc. (WI)

P13 Sumitomo Electric Carbide Manufacturing, Inc. (OH)

HARDMETAL GROUP

CUTTING TOOLS
EUROPEAN LOCATIONS

S2 Sumitomo Electric Hartmetall GmbH



THE TEC TOOL ENGINEERING CENTER

- T1 Itami Tool Engineering Center (I-Tec)
- T2 Hokkaido Tool Engineering Center (H-Tec)
- T3 Yokohama Tool Engineering Center (Y-Tec)
- T4 Tokai Tool Engineering Center (T-Tec)
- T5 Kyushu Tool Engineering Center (K-Tec)
- T6 European Design & Engineering Center (E-DEC)
- T7 Shanghai Tool Engineering Center (S-Tec)
- T8 Thai Tool Engineering Center (Ti-Tec)
- T9 Indonesia Tool Engineering Center (In-Tec)
- T10 Americas Tool Engineering Center (A-Tec)
- T11 India Tool Engineering Center

Sales Network (●●)
Production Network
Tool Engineering Center

Sales Network

S1 Sumitomo Electric Tool Net, Inc.

S3 Sumitomo Electric Hardmetal Ltd.

S4 SumiSermetal Ticaret ve Sanayi Limited Şirketi

S5 Sumitomo Electric Hardmetal Trading (Shanghai) Co., Ltd.

S6 Superior Engineering Tool Trading (Shanghai) Co., Ltd.

S7 Sumitomo Electric Hardmetal Asia Pacific Pte Ltd.

S8 Sumitomo Electric Hardmetal (Thailand) Ltd.

S9 PT. Sumitomo Electric Hardmetal Indonesia

S10 SEI Carbide Australia Pty Ltd.

S11 Motherson Techno Tools Ltd.

S12 Sumitomo Electric Carbide, Inc.

S13 Sumicarbide Canada Inc.

S14 Sumitomo Electric Hardmetal de Mexico, S.A. de C.V.

S15 Sumitomo Electric Hardmetal do Brasil Ltda.

S16 Taiwan Hong-Yu Precision Tool Co., Ltd.

SUMITOMO

CARBIDE - CBN - DIAMOND

(Germany)
SUMITOMO ELECTRIC Hartmetall GmbH
Konrad-Zuse-Str. 9, 47877 Willich / Germany

Tel. +49 (0)2154-49920, FAX +49 (0)2154-4992161
Info@SumitomoTool.com
www.SumitomoTool.com

(UK and Ireland)
SUMITOMO ELECTRIC Hardmetal Ltd.
Summerleys Road, Princes Risborough
Buckinghamshire HP27 9PW, UK

Tel. +44 (0)1844 - 342081, FAX +44 (0)1844 - 342415
InfoUK@sumitomoTool.com
www.SumitomoTool.com

Distributed by :

(01/20_SHG_Engl.)